



UNIVERSITI PUTRA MALAYSIA

**TENSILE STRENGTH AND FAILURE CHARACTERISTICS OF
COMMON ROOF TRUSS JOINTS**

MAHADZIR ABDUL RAHMAN

FH 2002 5

**TENSILE STRENGTH AND FAILURE CHARACTERISTICS OF COMMON
ROOF TRUSS JOINTS**

By

MAHADZIR ABDUL RAHMAN

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,
in Fulfilment of Requirement for the Degree of Master of Science**

February 2002



Abstract of thesis is presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement of the degree of Master of Science

TENSILE STRENGTH AND FAILURE CHARACTERISTICS OF COMMON ROOF TRUSS JOINTS

By

MAHADZIR ABDUL RAHMAN

February 2002

Chairman : Mohd Ariff Jamaludin, Ph.D.

Faculty : Forestry

Timber joints have always been the weak link in timber construction. Although the load carrying capacity of the timber structure is greater than the applied load, the structural system can fail if the joints are weak. Finger jointing of short off-cut timbers for structural purposes like lightweight roof trusses is an economical method to minimise wastage and to increase recovery rate. The objective of this research was to evaluate the strength and failure characteristics of truss joints made from solid and finger jointed kempas (*Koompassia malaccensis*) with metal plate connectors.

This research assessed the strength properties of truss joints comprising solid and finger-jointed kempas which were jointed with nail plate connectors. The influence of the location of finger joints in the joint system on both the strength and failure characteristics were also studied. Eight joint types, each



having ten replications were tested for joint strengths and failure modes. The type of joint were solid butt-joint (SB), solid T-joint (ST), finger jointed butt-joint type 1 (FB1), finger jointed butt-joint type 2 (FB2) and finger jointed butt-joint type 3 (FB3), finger jointed T-joint type 1 (FT1), finger jointed T-joint type 2 (FT2) and finger jointed T-joint type 3 (FT3).

From this study, specific gravity and moisture content of the samples were not significantly different with each other suggesting that both properties did not significantly influenced the strength and mode of failure of the joints. As such, the differences on their effect on the strength of the joint design was assumed to be minimal.

Types of joint had significantly influence over the maximum strength of the joint system used in the study. Joint made up of solid kempas with butt joint was significantly stronger than that of T-joint. Overlapping the finger joints with nail plate connectors had markedly increased the strength of the butt joint.

T-joint using solid kempas (without finger jointing) was significantly stronger than T-joints having finger jointed members (FT1, FT2 and FT3). The maximum load of these joints were reduced to nearly 50% of the solid timber T-joint. Generally, the wood surface failed at the middle member between the T-joint member and the nail plate connector where some parts of the fibrous material were ripped off from the horizontal member.

There were three types of failure modes associated with joint systems used in this study: tooth withdrawal, nail plate failure and wood failure. Fifty percent of the failure was categorised as tooth withdrawal, whilst both 25% were of types nail plate failure and wood failure respectively.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Master Sains

**KEKUATAN REGANGAN DAN CIRI KEGAGALAN SAMBUNGAN LAZIM
KEKUDA BUMBUNG**

Oleh

MAHADZIR ABDUL RAHMAN

Februari 2002

Pengerusi : Mohd Ariff Jamaludin, Ph.D.

Fakulti : Perhutanan

Sambungan kayu kerap merupakan kelemahan dalam rangkaian binaan kayu. Walaupun keupayaan memikul beban struktur kayu melebihi beban yang dikenakan, sistem binaan boleh mengalami kegagalan jika sambungannya lemah. Penyambungan jejari lebihan kayu yang pendek untuk struktur seperti kekuda bumbung ringan adalah satu kaedah yang ekonomi untuk mengurangkan pembaziran dan meningkatkan kadar pulangan. Objektif kajian ini adalah untuk mempelajari sifat kekuatan dan ciri kegagalan pada kayu padat dan kayu sambungan jejari spesies kempas (*Koompassia malaccensis*) pada sistem sambungan kekuda menggunakan plat paku.

Penyelidikan ini menilai sifat kekuatan sambungan kekuda pada kayu padat dan kayu sambungan jejari kempas yang disambung menggunakan plat paku. Pengaruh posisi sambungan jejari terhadap sifat kekuatan dan ciri

kegagalan pada sistem sambungan juga dikaji. Lapan jenis sambungan dengan sepuluh replikasi setiap satunya telah diuji untuk mengetahui kekuatan dan mod kegagalannya. Sampel-sampel berkenaan adalah kayu padat sambungan hujung bertemu hujung (SB), kayu padat sambungan-T (ST), kayu yang disambung jejari sambungan hujung bertemu hujung jenis 1 (FB1), kayu yang disambung jejari sambungan hujung bertemu hujung jenis 2 (FB2), kayu yang disambung jejari sambungan hujung bertemu hujung jenis 3 (FB3), kayu yang disambung jejari sambungan-T jenis 1 (FT1), kayu yang disambung jejari sambungan-T jenis 2 (FT2) dan kayu yang disambung jejari sambungan-T jenis 3 (FT3).

Hasil daripada kajian menunjukkan perbezaan ketumpatan tentu dan kandungan lembapan untuk semua sampel adalah tidak ketara antara satu sama lain dan boleh dikatakan bahawa kedua-dua sifat ini tidak ketara mempengaruhi sifat kekuatan dan ciri kegagalan semua sambungan. Oleh itu, kesan mereka keatas kekuatan sambungan diandaikan adalah minima.

Jenis-jenis sambungan mempunyai pengaruh yang ketara terhadap kekuatan maksimum sistem penyambungan dalam kajian ini. Penyambungan dari kayu kempas padat dengan sambungan hujung bertemu hujung adalah ketara lebih kuat berbanding sambungan-T. Penindihan sambungan jejari dengan plat paku telah menunjukkan peningkatan kekuatan sambungan hujung bertemu hujung.

Sambungan-T yang menggunakan kayu kempas padat (tanpa sambungan jejeri) adalah ketara lebih kuat jika dibandingkan dengan sambungan-T yang mempunyai anggota sambungan jejeri (FT1, FT2 dan FT3). Beban maksimum untuk semua anggota yang disambung jejeri kebanyakannya berkurangan hampir 50% jika dibandingkan dengan kayu padat sambungan-T. Pada amnya, kegagalan permukaan kayu berlaku pada bahagian tengah antara komponen-T dengan plat paku di mana sebahagian gentian kayu dari komponen melintang terkoyak keluar.

Tiga jenis mod kegagalan dalam sistem sambungan di dapati daripada kajian ini: gigi plat paku tercabut daripada kayu, kegagalan kayu dan kegagalan plat paku. Lima puluh peratus daripada kegagalan dikategorikan sebagai kegagalan yang di sebabkan oleh gigi plat tercabut daripada kayu, sementara masing-masing 25% lagi adalah di sebabkan oleh kegagalan plat paku dan kegagalan kayu.

ACKNOWLEDGEMENTS

First and foremost, I would like to express my most sincere and deepest gratitude to my Advisor, Dr. Mohd Ariff Jamaludin, for his helpful advice, encouragement and constructive criticism throughout the study. I am thankful for his patience and for the knowledge that I acquired from his comments and suggestions.

Sincere thanks are also due to Tuan Haji Mohd Shukari Midon from Forest Research Institute Malaysia (FRIM), Dr. Mansur Ahmad from Universiti Teknologi Mara (UiTM) and Dr. Paridah Md. Tahir for their invaluable advice and constructive criticism that substantially improved this study.

I am also grateful for the cooperation and support given by General Lumber Fabrications and Builders for the supply and fabrication of the timber joints and also Casco Adhesives Sdn. Bhd. for the supply of the adhesives. I also would like to thanks Mr. Semsolbahri Bokhari, Mr. Khairul Azhan Othman and Mr. Mohd Rizal Abdul Rahman for their cooperation and support.

Last but not least, my utmost gratitude to my beloved family: father, mother, brothers and sisters who have been patient and faithfully praying for my success. Not forgotten are friends who contributed towards the success of this project.



I certify that an Examination Committee met on 7th February 2002 to conduct the final examination of Mahadzir Abdul Rahman on his Master of Science thesis entitled "Tensile Strength and Failure Characteristics of Common Roof Truss Joints" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

PARIDAH MD. TAHIR, Ph.D

Lecturer,
Faculty of Forestry,
Universiti Putra Malaysia
(Chairperson)

MOHD ARIFF JAMALUDIN, Ph.D

Lecturer,
Faculty of Forestry,
Universiti Putra Malaysia
(Member)

MOHD SHUKARI MIDON, Ir.

Senior Research Officer,
Timber Engineering Unit,
Forest Product Technology Division,
Institut Penyelidikan Perhutanan Malaysia
(Member)

MANSUR AHMAD, Ph.D

Associate Professor,
Faculty of Applied Science,
Universiti Teknologi MARA
(Member)

SHAMSER MOHAMAD RAMADILI, Ph.D.

Professor/Deputy Dean,
School of Graduate Studies
Universiti Putra Malaysia

Date : 20 APR 2002



This thesis submitted to the Senate of Universiti Putra Malaysia has been accepted as fulfilment of the requirement for the degree of Master of Science.




AINI IDERIS, Ph.D.,
Professor/Dean,
School of Graduate Studies,
Universiti Putra Malaysia

Date: **13** JUN 2002

DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other Institutions.


Mahadzir Abdul Rahman

Date: 26 APR 2012

TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	v
ACKNOWLEDGEMENTS	viii
APPROVAL SHEETS	ix
DECLARATION FORM	x
LIST OF TABLES	xv
LIST OF FIGURES	xvi
LIST OF PLATES	xvii
LIST OF ABRERATION	xviii
CHAPTER	
1 INTRODUCTION	
1.1 General	1
1.2 Justification	3
1.3 Objectives	4
2 LITERATURE REVIEW	
2.1 Timber Trusses	5
2.2 Truss Rafters	6
2.3 Truss Selection	7
2.4 Timber	8
2.5 Consideration in Using Timber	9
2.5.1 Advantages of Timber	10
2.5.1.1 Weight	10
2.5.1.2 Thermal Insulation	11
2.5.1.3 Fire Resistant	12
2.5.1.4 Acoustic Performance	13
2.5.2 Classification of Timber	13
2.5.3 Strength grouping of Timber For Joint Design	15
2.5.4 Timber Species Used	17
2.5.4.1 Kempas	17
2.6 Timber Connected Joints	18
2.7 Mechanical Fasteners	18
2.7.1 Metal Plate Connectors	19
2.7.2 Truss Plate Fabrication	20
2.7.3 Metal Plate Connector Positioning	21



2.7.4	Advantages of Metal Plate Connectors	22
2.7.5	Metal Plate Characteristic	23
2.7.6	Anti-Corrosion Treatment	24
2.7.8	Metal Plate Failure	25
2.7.9	Joint Failure Characteristic	26
2.8	Finger Joint	27
2.8.1	Factor Affecting the Finger Joint Strength	30
2.8.2	Adhesives used in Structural Finger Jointing	31
2.8.3	Phenol Resorcinol Formaldehyde	32
2.9	General Consideration in Design	33
2.9.1	Load at an Angle to the Grain	33
2.9.2	Shrinkage and Swelling	34
2.9.3	Moisture Content	34
2.9.4	Slope of Grain	35
2.9.5	Duration of Load	35
2.10	Influence Factor Effect of Metal Plate Connector Jointing	36
2.10.1	Properties of the Metal Plate Connectors	36
2.10.2	Size of Metal Plate Connector	36
2.10.3	Orientation of Plate and Wood	36
2.10.4	End and Edge Distance	37
2.10.5	Species and Specific Gravity	37
2.10.6	Effect of Moisture Content	38
2.10.7	Effect of Adhesive Between Toothed and Wood	39
3	MATERIALS AND METHODS	
3.1	Material	40
3.1.1	Preparation of Samples	41
3.1.2	Samples Labeling	42
3.1.3	Adhesives Used	49
3.2	Method of Fabrication	50
3.3	Method of Testing	53
3.4	Moisture Content Determination	57
3.5	Specific Gravity Determination	57
3.6	Dry Basic Lateral Load	58
3.7	Permissible Tensile Strength of Steel Plate	59
3.8	Statistical Analysis	60
4	RESULTS AND DISCUSSIONS	
4.1	Test Result	61
4.2	Effect of Specific Gravity and Moisture Content On the Strength of the Joint	64
4.3	Analysis of Dry Basic Load	65
4.3.1	Dry Basic Load	66

4.3.2	Permissible Tensile Strength of Steel Plate	67
4.4	Strength Properties of Nail Plate Joints	68
4.4.1	Butt-joint	68
4.4.2	T-Joint	69
4.4.3	Comparison Between Butt Joint and T-joint	70
4.5	Failure Mode of Nail Plate Joints	72
4.5.1	Butt-Joint	72
4.5.2	T-Joint	76
4.6	Effect of Finger Joint on Nail Plated Butt-joint	81
4.6.1	Effect of Two Finger Joints Near Nail Plate	82
4.6.2	Effect of One Finger Joints Near One Side of Nail Plate	83
4.6.3	Effect of Two Finger Joints Overlap with Nail Plate	84
4.7	Effect of Finger Joint in Nail Plated T-Joint	86
4.7.1	Effect of Finger Joints in Both Members of Nail Plated T-joints	87
4.7.2	Effect of Finger Joint Overlapped with Nail Plate in T-joint	88
4.7.3	Effect of Two Finger Joints Near Nail Plate in T-joint	89
5	CONCLUSIONS AND RECOMMENDATIONS	92
	REFERENCES	94
	APPENDICES	
1	Hydraulic G-clamp for truss fabrication	100
2	Specific Gravity Test Set-up	101
3	Graph of Load (kN) versus Displacement (mm)	102
	VITA	



LIST OF TABLES

Table		Page
2.1	Truss types for lightweight trusses	9
2.2	Weight of some building material	10
2.3	Values of thermal properties for selected building materials	11
2.4	Classification of timber based on density	14
2.5	Strength groups of timbers in Peninsular Malaysia according to MS544: Part 2: 2001	15
2.6	Group classification of timbers for use in joint design	16
2.7	Advantages and disadvantages of mechanical fastening	19
3.1	Toothed metal plate connector specifications.	47
4.1	Result of tensile test loading for nail plated butt-joint (parallel to the grain)	62
4.2	Result of tensile test loading for nail plated T-joint (perpendicular to the grain)	63
4.3	Dry basic load for one tooth for solid kempas joint design (SB vs. ST)	66
4.4	Dry basic load for one tooth for finger-jointed kempas design (FB1 vs. FT2)	66
4.5	Dry basic load for one tooth for finger-jointed kempas design (FB3 vs. FT1)	66
4.6	Permissible Tensile Strength for nail plate	88

LIST OF FIGURES

Figure		Page
2.1	Profile of finger joints	31
3.1	Butt-joint test samples	43
3.2	T-joint test samples	44
3.3	Experimental design for the study	48
4.1	Action of two tension forces will separate the nail plate	73
4.2	Nail plate withdrawal from horizontal member when tension force was applied	77
4.3	Failure occurred at finger joint	84
4.4	Failure occurred at the nail plate as the finger joints were reinforced by the nail plate	85
4.5	Surface of horizontal member was ripped-off at finger joint due to fibre separation caused by applied tension force	88
4.6	Surface of middle portion of horizontal member was ripped off by the nail plate	90
4.7	Both sides of middle portion of horizontal member were ripped off	91

LIST OF PLATES

Plate		Page
3.1	Toothed metal plate connector used in this study	46
3.2	Tooth structure	47
3.3	G-clamp component	50
3.4	Close-up view of G-clamp	51
3.5	Placing of nail plate to the center of the sample before pressing	52
3.6	Pressing the sample to embed the nail plate onto the sample component (front view)	52
3.7	Pressing the sample to embed the nail plate onto the sample component (side view)	53
3.8	Test set-up for parallel joints	54
3.9	Test set-up for perpendicular joints	52
4.1	Nail plate failure in the middle of the butt-joint	75
4.2	Close-up view of nail plate joint failure for the butt-joint design	75
4.3	Butt-joint timber failure at the finger joint	76
4.4	Tooth withdrawal from horizontal member in T-joint for solid timber	78
4.5	Nail plate broken into two halves in the T-Joint	79
4.6	Surface fracture of horizontal member in the finger-jointed T-joint	79
4.7	Close-up view of the wood failure for the FT3 joint	81
4.8	Surface fracture of the finger jointed horizontal member	89

LIST OF ABRERATION

Symbols

AS	- Australian Standard
ANSI	- American National Standards Institute
ASTM	- American Society for Testing and Materials
BS	- British Standard
kN	- Kilo Newton
MS	- Malaysian Standard
PRF	- Phenol Resorcinol Formaldehyde
SIRIM	- Standards and Industrial Research Institute of Malaysia
USDA	- United States Department of Agriculture
SB	- Solid timber butt-joint
FB1	- Butt-joint design type 1 with finger jointed timber members
FB2	- Butt-joint design type 2 with finger jointed timber members
FB3	- Butt-joint design type 3 with finger jointed timber members
SB	- Solid Timber T-joint
FT1	- T-joint design type 1 with finger jointed timber members
FT2	- T-joint design type 2 with finger jointed timber members
FT3	- T-joint design type 3 with finger jointed timber members

CHAPTER I

INTRODUCTION

1.1 General

Timber jointing is the process of fastening together two or more pieces of timber using either mechanical fasteners such as nails, bolts, truss plate connectors or glue and many others. The former is generally known as mechanical joints and the latter as glued joints. Jointing plays a very important role in the construction of a timber structure which may be either a building, a tower or a bridge.

Timber joints have always been the weak link in timber construction and in the design of large timber structures, the joint being heavily stressed when loaded, are often the critical points. This is because all timber structures are made of elements that must be connected together for the transfer of loads between them. The designer must not only know the strength of the wood members of the joint but also the strength of the wide variety of connectors when acting along, across, or at an angle to the grain.

Normally, when design of a joint in a structural assembly begins, the designer first thinks about how much load that a joint can carry or transfer. Then, the designer considers the stress, or the load per unit cross-sectional area of the joint members. The designer must also consider the stress in the joint, load carrying capacity and resultant stresses.

Although the load-carrying capacity of any timber structure is governed by the strength of the timber members, and the strength of the fastener or combination of both, timber joints have very often been the weak link in timber construction (Chu, 1987). In the design of large timber structures, careful considerations should be given to the design of joints as the strength and stability or rigidity of any structure depends heavily on the fastenings that hold its parts together.

In designing wood structures an engineer is responsible not only for the design of the various members but also for the connections. On a typical structural project it is not surprising to find that the design of the connections may comprise half of the work. Furthermore, it is estimated that as much as 90% (Halperin and Bible, 1994) of the structural failures experienced in wood frame buildings originated at the connections.

1.2 Justification

Wood jointing plays an important role in timber structure. Strength of the timber structure mostly depends on the wood joints other than the strength of the timber itself. Metal plate connectors are the most popular fasteners for roof truss joints today. However, only limited studies on the jointing of tropical hardwood using metal plate connectors are published (Mohd Shukari, et.al. 1997,a, b). Much more researches of timber joints especially in tropical timber would be needed to fill in the gaps identified in the previous research.

Roof trusses are constructed to be used for long terms, almost all local fabricators give warranty for ten years. So it must be able to withstand degradation for that period. When the designers and users of wood joint structural members consider their confidence in the load-carrying performance of the product in service, the adequacy of the End-joints and T-joints are usually their number one concern (Prins, 1982). This is because all the timber structures are made of elements that must be connected together for the transfer of loads between them.

In roof truss manufacturing, joints are the most important elements. The strength of joints represent the quality of roof truss. If the joint fails, the roof trusses fail too. It will give more implication to the building structures because the building may collapse.

Usage of timbers beside steels in Malaysia are increasing due to expansion in construction industry mainly for housing, shop house, factory and infrastructure like hospital, school and government office. With the anticipated rise in demand for structural timber by the construction industry today, there is a need for data on working stress and strength properties of joints for efficient use in structural design. Therefore, this study was carried out to determine the strength and examine failure characteristics of tropical timber joints using nail plates in roof truss system.

1.3 Objectives

The objective of this research was to study the strength and failure characteristics of nail plated roof truss joints of different designs. The specific objectives of this study are stated below.

- i) To determine the strength and examine the failure characteristics of different solid kempas (*Koompassia malaccensis*) truss joint system using metal plate connectors.
- ii) To study the strength and failure characteristics of different finger jointed kempas truss joint system with nail plate connectors.
- iii) To compare the strength and failure characteristics of solid kempas and different types of finger jointed kempas truss joints.

CHAPTER II

LITERATURE REVIEW

2.1 Timber Trusses

The earliest remaining visual record of a timber truss is a carving in Trojan's column, in Rome (built AD 104), of a bridge over the Danube River. Supposedly, this bridge was constructed of about 20 trussed timber arches spanning 30 to 40 meter each. The timber trusses of the nineteenth century used iron bolts and rods for fasteners, although they were dependent primarily on skillful carpentry to obtain the well-fitted joints necessary for the transference of both compression and tension stresses. Modern timber connectors have eliminated the need for the skilled artisans of that period.

Apart from the solid floor joist, light timber trusses are the most widely used timber structural component. There are different types available for commercial and particularly for domestic use and modern manufacturing techniques utilising patented connector plates enable the truss to be produced in large quantities with subsequent economic benefits.

Timber trusses represent another common type of fabricated wood component. Heavy wood trusses have a long history of performance, but light

timber trusses are more popular today. The majority of residential timber structures and many commercial and industrial buildings use some form of closely spaced light timber trusses in roof floor systems. Common spans for this trusses range up to 25 m, but larger spans are possible.

2.2 Truss Rafters

The definition of trussed rafters is given in BS 5268: Part 3: 1985 which is the code of practice for trussed rafter roofs; as “light-weight triangulated frameworks spaced at intervals generally not exceeding 600 mm and made from timber members fastened together in one plane”. Pre-fabricated trusses have revolutionised residential roof framing over the last four decades. Today, 75 to 80 percent of all new homes are constructed with metal plate connected wood truss (Smulski 1996, Hoover 2000).

Trussed rafters are engineered components fabricated using strength-graded timber fixed with truss plate connectors. Individual truss designs are prepared by the trussed rafter manufacturer using sophisticated computer programs developed by “System Owners” who also supply the fasteners.