



UNIVERSITI PUTRA MALAYSIA

**DIRECT STRAIN AND STRESS MEASUREMENT FOR
PRESTRESSED STEEL**

SUHAILA BINTI ISAAK

FK 2000 48

**DIRECT STRAIN AND STRESS MEASUREMENT FOR PRESTRESSED
STEEL**

BY

SUHAILA BINTI ISAAK

**Thesis Submitted in Fulfilment of Requirement for the Degree of Master of
Science in the Faculty of Engineering
Universiti Putra Malaysia**

December 2000



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Master of Science

**DIRECT STRAIN AND STRESS MEASUREMENTS FOR
PRESTRESSED STEEL**

By

SUHAILA BINTI ISAAK

December 2000

Chairman : Samsul Bahari bin Mohd. Noor, Ph.D.

Faculty : Engineering

Bridge assessment requires knowledge of the design prestress and of any losses that may occur since stressing. The knowledge on state of stress in prestressing wires of prestressed beams is a very important criteria when assessment is conducted on an existing prestressed concrete structures. The high initial stress could slowly decrease due to creep, shrinkage and relaxation effects. The reduction in stress could also occur abruptly due to slippage and loss of concrete area.

The development of electronic instruments that test, measure, and control industrial processes has gone through a rather impressive growth pattern in recent years. In most industrial applications, the requirement of effective measurement method is very essential.



In general, the strain gauge only measures the change of strain and stress due to loading unless it has been fixed in the steel structure before the steel is stressed. Until now, there are no practical non-destructive methods for measuring residual stress. The hole drilling strain gauge method can be used but destructive in nature

To date, the non-destructive stress measurement of prestressed steel has not yet been established after the steel has been stressed. Therefore, the purpose of this project is to develop the non-destructive residual stress measurement technique for prestressed steel by using resistance measurement as a tool for determining the stress value.

Experimental tests were carried out to find a relationship between stress and resistance for three types of steel such as prestressing steel wire, prestressing steel strand and high tensile steel plate. The stress and resistance relationships obtained from the experiment have been analyzed by using statistical analysis. It was found that resistance in the prestressed steel is proportional to the applied stress.

Based on the stress and resistance relationships obtained from the three types of steel specimens, a software was develop by using Visual Basic to compute the stress value for the measured resistance in the prestressed steel. For the time being, the resistance value is keyed in but should later be able to be improved, so that it will read directly from the interfacing circuit.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk Ijazah Master Sains.

**PENGUKURAN TERUS TERIKAN DAN TEGASAN BAGI KELULI PRA-
TEGASAN**

Oleh

SUHAILA BINTI ISAAK

Disember 2000

Pengerusi : Samsul Bahari bin Mohd. Noor, Ph.D.

Fakulti : Kejuruteraan

Pengetahuan mengenai keadaan tegasan bagi keluli prategasan pada rasuk prategasan merupakan kriteria penting apabila penilaian dijalankan ke atas struktur konkrit prategasan. Nilai tegasan awal yang tinggi akan berkurangan secara perlahan-lahan akibat kesan rayapan, pengecutan dan santon pada struktur tersebut.

Pengurangan dalam tegasan boleh juga berlaku akibat kegelinciran serta kehilangan pada konkrit.

Perkembangan dalam aspek pengujian, pengukuran dan pengawalan proses perindustrian dengan menggunakan peralatan elektronik telah melalui perubahan yang ketara sejak baru-baru ini. Dalam kebanyakan bidang perindustrian, keperluan kepada satu kaedah pengukuran yang berkesan adalah penting.

Secara umumnya, tolok terikan hanya mengukur perubahan terikan dan tegasan terhadap beban kecuali jika ia dipasang pada keluli sebelum ia ditegaskan. Sehingga kini, masih tiada kaedah pengukuran tegasan baki yang tidak membinasakan. Kaedah "hole drilling" menggunakan tolok terikan boleh digunakan tetapi ia sebenarnya memusnahkan struktur keluli

Kini, pengukuran tegasan baki yang sebenar dan tidak membinasakan pada struktur keluli yang telah ditegaskan masih belum diselidiki sepenuhnya.. Oleh itu, objektif projek ini adalah untuk menghasilkan satu kaedah pengukuran tegasan yang tidak membinasakan terhadap keluli pra-tegasan dengan menggunakan kaedah pengukuran rintangan dalam mendapatkan nilai tegasan.

Eksperimen bagi mendapatkan hubungan diantara tegasan dengan rintangan dilakukan terhadap tiga jenis keluli iaitu wayar keluli prategasan, lembar keluli prategasan dan kepingan keluli berkekuatan tinggi. Hubungan antara tegasan dan rintangan yang diperolehi daripada eksperimen telah dianalisa menggunakan analisa secara statistik. Hasilnya mendapati bahawa hubungan diantara rintangan pada kesemua jenis keluli adalah berkadar terus dengan tegasan yang dikenakan.

Berdasarkan kepada hubungan tegasan dan rintangan bagi ketiga-tiga jenis keluli tersebut, suatu perisian telah dibina menggunakan "Visual Basic" bagi mengira nilai tegasan berdasarkan nilai rintangan yang diukur pada keluli prategasan. Buat masa ini, nilai rintangan perlu dimasukkan ke dalam perisian, namun ia perlu dipertingkatkan dengan membina litar antara muka agar ia boleh membaca nilai rintangan yang diukur secara terus.

ACKNOWLEDGEMENTS

In the name of Allah, The Most Merciful and Benevolent, who has made it possible for me to undertake this research work.

I would like to convey my deepest gratitude and most sincere thanks to my supervisor Dr. Samsul Bahari bin Mohd. Noor from the Electrical and Electronic Engineering Department, Universiti Putra Malaysia. His valuable guidance and advice in the pursuance of this project would continuously be referred to, in my future studies. I also wish a grateful appreciation to Dr. Mohd. Saleh bin Jaafar and Mr. Nasri Sulaiman for serving in my supervisory committee and providing suggestions and comments at different stages of this study.

I would like to thank Mr. Halim, Tuan Haji Razali and Mr. Nayan from Faculty of Engineering Universiti Putra Malaysia, for their kindness in assisting in my project. My special thanks go to Mr. Nordin bin Abu and Dr. Mohd. Hanim Osman from Universiti Teknologi Malaysia for their constant assistance, advice and encouragement as well as using facilities in the laboratory.

My appreciation goes out to my dearest parents for their understanding and encouragement. I also would like to express my heartfelt expression to my family member. This thesis is specially dedicated to my husband, Roslli who had shared the difficulties that I went through in completing this thesis and M.Sc course.



I certify that an Examination Committee met on 20th December 2000 to conduct the final examination of Suhaila Binti Isaak on her Master of Science thesis entitled "Direct Strain and Stress Measurement for Prestressed Steel" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

Yousif A. Khalid, Ph.D
Faculty of Engineering
Universiti Putra Malaysia
Chairman

Samsul Bahari Mohd. Noor, Ph.D
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Mohd. Saleh bin Jaafar, Ph.D
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Mr. Nasri bin Sulaiman, MEE
Faculty of Engineering
Universiti Putra Malaysia
(Member)



MOHD. GHAZALI MOHAYIDIN, Ph.D,
Professor/Deputy Dean of Graduate School,
Universiti Putra Malaysia

Date: 05 FEB 2001



This thesis submitted to the Senate of Universiti Putra Malaysia has been accepted as fulfilment of the requirement for degree of Master of Science.



MOHD. GHAZALI MOHAYIDIN, Ph.D.
Professor
Deputy Dean of Graduate School
Universiti Putra Malaysia

Date: 12 APR 2001



DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



(SUHAILA BINTI ISAAK)

Date: 5 - 2 - 2001

TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	iv
ACKNOWLEDGEMENT	vi
APPROVAL SHEETS	vii
DECLARATION FORM	ix
LIST OF TABLES	xiii
LIST OF FIGURES	xiv
LIST OF PLATES	xvii
LIST OF ABBREVIATIONS	xviii
CHAPTER	
I INTRODUCTION	1
Introduction	1
Background Problem	1
Objectives	3
Scope of Study	3
II LITERATURE REVIEW	5
Introduction	5
Residual Stress by Hole Drilling Strain Gauge Method	6
Prestressing Steels	6
Mechanical Properties of Prestressing Structures	8
Strain	8
Elastic Modulus	9
Elastic Limit	11
Tensile Test	11
Electrical Resistance Strain Gauges Circuits	12
Strain Measuring Instruments	21
Measurements on the Tensile Rod	22
Measurements on the Bending Beam	25
Compensation of Superimposed Stresses	26
Compensation of Adverse Effects	28
Cancellation of Cable Errors	30
Wheatstone Bridge	31
Micro Ohmmeter : Resistance Measurement Equipment	35



III	MATERIALS AND METHODS	36
	Introduction	36
	Prestressing Steel Wires	37
	Experiment by Hydraulic Jack Pump	38
	Strain and Stress Measurement	40
	Strain and Resistance Measurement	41
	Experiment by Dartec Machine	42
	Tensile Test	42
	Stress-Resistance Measurement	44
	Prestressing Steel Strand	46
	Tensile Test	46
	Stress-Resistance Measurement	47
	High Tensile Steel Plate	49
	Tensile Test	49
	Stress-Resistance Measurement	50
	Loading Mass Technique	52
	Stress-Resistance Measurement	52
	The Displacement Technique	55
	Stress-Resistance Measurement	55
	The Wheatstone Bridge Arrangement	58
	Software to Compute Stress Value	59
IV	RESULTS AND DISCUSSION	60
	Introduction	60
	Prestressing Steel Wire	60
	Experiment by Hydraulic Jack Pump	60
	Strain-Stress Measurement	60
	Strain-Resistance Measurement	63
	Experiment by Dartec Machine	65
	Tensile Test	65
	Stress-Resistance Measurement	67
	Prestressing Steel Strand	68
	Tensile Test	68
	Stress-Resistance Measurement	71
	High Tensile Steel Plate	72
	Tensile Test Result	72
	Stress-Resistance Measurement	74
	Stress-Resistance Measurement-Loading Mass	75
	Stress-Resistance Measurement-Displacement	76
	Correlation and Regression	78
	Correlation Coefficient	78
	Linear Regression Analysis	80
	Software Development	82
	Resistance, Strain and Stress Analysis	82
	Stress and Resistance Analysis	83

	Stress and Strain Analysis	83
	Strain and Resistance Analysis	83
V	CONCLUSIONS AND RECOMMENDATIONS	89
	Conclusions	89
	Recommendations	92
	REFERENCES	93
	APPENDICES	95
	A The Properties of Test Specimens	96
	B Program Listing	98
	C Linear Regression Analysis	105
	D Actual Properties of Tensile Test Result	111
	VITA	115



LIST OF TABLES

Table		Page
1	Elastic Modulus	10
2	The Effect of Mechanical Stress and the Thermal Expansions	29
3	The Tensile Test Result for Prestressing Steel Wire	65
4	Tensile Test Results for Prestressing Steel Strand	69
5	Tensile Test Results for High Tensile Steel Plate	72
6	Example of Calculation of R^2 Value for Stress – Resistance Data	79



LIST OF FIGURES

Figure		Page
1	Relaxation Values Related to Initial Stress, σ_1 after 1000h for different prestressing steels given depending on initial stress, σ_1	7
2	Typical Stress-Strain Plot	10
3	Resistance Wire	13
4	The Wheatstone Bridge Circuit	18
5	Illustration for the Rules of the Sign in the Wheatstone Bridge	19
6	The Tensile Rod	23
7	The Bending Beam	24
8	Tensile Rod with Bending Moment Superimposed	26
9	Beam According to Figure 7 Fitted with Longitudinal and Lateral Gauges	27
11	Wheatstone Bridge	33
12	The Wheatstone Bridge with Resistor Switch (SW1)	34
13	Strain Gauges Location on Prestressing Steel Wire	39
14	The Initial Condition Before Stressing	40
15	The Condition After Stressed	40
16	Tensile Test Setup Using Extensometer	51
17	The Parallel Balancing Bridge with Loading Mass Model Diagram	54
18	The Parallel Balancing Bridge with E&G Mechanical Test Rig 5091 Diagram	57

19	Parallel Balancing Circuit	58
20	The Relationship between Stress (N/mm^2) and Strain ($\mu\epsilon$) at Location A1, B1 and C1 using Hydraulic Jack Pump	61
21	The Relationship between Stress (N/mm^2) and Strain ($\mu\epsilon$) at Location A1, B1 and C1 (after 2 days) using Hydraulic Jack Pump	62
22	The Relationship of Stress (N/mm^2) and R_s (Ω) using Multimeter	65
23	The Strain-Stress Relationship for Prestressing Steel Wire using Dartec Machine	66
24	The Stress-Resistance Relationship Plotted Graph for Prestressing Steel Wire using Micro-ohmmeter	68
25	The Strain-Stress Relationship for Prestressing Steel Strand using Dartec Machine	70
26	The Stress-Resistance Relationship Plotted Graph for Prestressing Steel Wire using Micro-ohmmeter	71
27	Load-Stroke Results for High Tensile Steel Plate	73
28	Stress-Strain Graph for High Tensile Steel Plate	73
29	The Stress-Resistance Relationship Plotted Graph for High Tensile Steel Plate by using Micro-ohmmeter	74
30	The Relationship between Stress (N/mm^2) and Resistance (Ω) for Loading Range 0-40N using Using Loading Mass Technique	76
31	The Relationship between Displacement (mm) and Resistance (Ω) by using Displacement Technique	77
32	Fitting Best Line for Experiment Stress-Resistance Graph	81
33	The Capture of Main Menu	84

LIST OF PLATES

Plate		Page
1	The Prestressing Steel Wires	37
2	The Hydraulic Jack Pump for Tension Force	42
3	Stress-Resistance Experiment for Prestressing Steel Wire	45
4	The Measurement Apparatus Arrangement with Loading Mass Model	53
5	The Steel Plate with Loading Mass Model	55
6	E & G Mechanical Test Rig and Dial Gauge Meter	56

LIST OF ABBREVIATIONS

L	Length
V	Voltage
R	Resistance
A	Area
E	Modulus of Elasticity
I	Current
G	Gauge Factor
D	Distance
<i>t</i>	Thickness
<i>w</i>	Width
<i>r</i>	Internal resistance
ρ	resistivity
ε	strain
σ	stress
<i>g</i>	acceleration
R_s	Steel plate resistance
R_g	Gauge resistance
R_m	Measured resistance
R_{fixed}, R_1, R_2	Fixed resistor
R_3	Variable resistor
R_k	Measured resistance
R_c	Variable resistor
R_p	Potential Resistance



R_A	Balancing resistor
Δl	The change of length
ΔR	The change of resistance
AC	Alternating Current
DC	Direct Current
DAC	Digital to Analog Converter
ADC	Analog to Digital Converter
UART	Universal Asynchronous Receiver Transmitter
TTL	Transistor-Transistor Logic
CMOS	Complementary Metal-Oxide Semiconductor
$\epsilon m f$	Electromagnetic Field



CHAPTER 1

INTRODUCTION

Introduction

Bridge assessment requires knowledge of the design prestressed and any losses that may have occurred since stressing. The engineer often faced with a problem of determining the stress and strain value during the long life of the bridge. In this case, in-situ determination of residual stress in the assessment of existing bridges. In this project, the use of resistance principle and measurement technique has been used for direct measurement of stress in the prestressed steel after it has been stressed.

Background Problem

During the life of the structure differential foundation, corrosion of steel, deterioration of the concrete and the effect of abnormal loading can cause the state of stress to change. Experimental techniques for the determination of stress in existing bridges structure are very important in providing data to support structural assessment.

In mechanical as well as in civil engineering, a fundamental concern is the soundness of loaded structures. In cases of simple geometry, the load per unit area (stress) can be computed. When it is compared with known values of safe stress for

specific materials and particular types of loading, it should give adequate information on safety. However, the situation is usually more complex and thus requires the measurement of distortions which can be assumed to be proportional to the applied stresses.

In the stress and strain analysis of prestressed concrete, the stress and strain in a section due to prestressing are calculated by considering the effect of a compressive force on a plain concrete section. Meanwhile, the loss in tension in the prestressed steel due to creep, shrinkage and relaxation is estimated. Equations which give the loss in tension in a prestressing tendon can be found in many codes and design recommendation (Ghali, 1989).

The constant demand for improvement in the design of machine and structural parts has led to the development of various experimental techniques for determining stress distributions. These experimental methods are employed for checking of theoretical predictions and evaluating the stresses in certain situations where mathematical approaches are unavailable.

Nowadays, the demand for an in-situ stress measurement technique for the bridge construction industry is become useful. Therefore, the knowledge on state of stress in prestressed steel is an important criteria when assessment is conducted on an existing prestressed concrete structures. This is due to high initial stress that may slowly decreased due to creep, shrinkage and relaxation effects. Moreover, the reduction in stress could also occur due to slippage and loss of concrete area.

To date, the non-destructive stress measurement has not yet been established after the steel has been stressed although the development of electronic instruments that test, measure and control industrial processes have gone through a rather impressive growth pattern in recent years. Strain gauge only measures the change of strain and stress due to loading unless it has been fixed before the steel is first stressed. The hole drilling strain gauge method, which has been established can be used but is destructive in nature.

Objectives

Recognising the fact that the demand for direct stress measurement is an important criteria in bridge assessment, a study of in-situ stress in prestressed steel is considered necessary. Therefore, the objective of this project is to establish the relationship between stress and resistance for measuring residual stress in prestressed steel. By using the relationship that obtained from the experiment, a software would be developed to compute the stress value based on the measured resistance value.

Scope of the study

The project performed can be divided into three main parts. The tensile test has been carried out as the first part in order to verify the ultimate strength and the elastic modulus for each specimen. There are two types of prestressed steel and one

type of high tensile steel that have been used in this project, i.e. prestressing steel wire (7 mm diameter), prestressing steel strand (12.7 mm diameter) and high tensile steel plate (2 mm thickness).

The second part involves the non-destructive resistance measurement for each specimen. The resistance measurement has been employed as a tool to determine stress value due to loading increment in elastic region of all specimens. The strain-resistance and stress-resistance relationship gained from the experiment would be used to measure the value of residual stress.

The final part deals with the developing software based on the established relationship to compute the stress value for a given measured resistance value.

CHAPTER II

LITERATURE REVIEW

Introduction

Nowadays, most of bridge constructions used the prestressed concrete beams or steel structures as their main elements. Prestressed concrete beams usually used prestressing steel material to induce prestressed forces to the beams. Reinforced concrete structures without prestressing generally crack and in some cases have excessive deflection. If the reinforcement is replaced by prestressed steel, cracking and deflection could be controlled. The amount of prestressing may be sufficient to avoid cracking. This condition is referred as full prestressing , as opposed to partial prestressing where controlled cracking is allowed.

Meanwhile, prestressed steel structure is able to save construction material required compared to unstressed steel structure. For structure supporting most of its self-weight, for example long span roof truss, prestressing steel would be able to reduce dead load. This would save material for other members of the construction. That is why many of the bridge structure using the prestressed steel (FHWA, 1998).

Residual Stresses by Hole-Drilling Strain Gauge Method

The hole drilling strain gauge method measures residual stresses near the surface of a material. The method involves attaching strain gauges to the surface, drilling a hole in the vicinity of the gauges, and measuring the relieved strains. The measured strains are then related to relieved principal stresses through a series of equations (Rendler, 1966).

The test method is often described as semi-destructive because the damage that it causes is very localized and in many cases does not significantly affect the usefulness of the specimen. In contrast, most other mechanical methods for measuring residual stress destroy the specimen. Since the test method does cause some damage, it should be applied in those cases where the specimen is expendable.

Prestressing Steels

Prestressing steels, or tendons, are embodied in zones of prestressed concrete members that are subjected to tensile stresses resulting from dead loads and live loads.

As a result of the initial prestressing, these zones of the concrete are subjected to such high compressive prestress that even under a combination of no tensile stresses (full prestressing) or only limited tensile stresses (limited prestressing) can occur in the concrete.