



UNIVERSITI PUTRA MALAYSIA

**PREPARATION AND CHARACTERIZATION OF TAPIOCA
STARCH/POLYCAPROLACTONE/CLAY COMPOSITES**

THEN YOON YEE

FS 2011 6

**PREPARATION AND CHARACTERIZATION OF TAPIOCA
STARCH/POLYCAPROLACTONE/CLAY COMPOSITES**

By

THEN YOON YEE

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,
in Fulfilment of the Requirements for the Degree of Master of Science**

March 2011



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment
of the requirement for the degree of Master of Science

**PREPARATION AND CHARACTERIZATION OF TAPIOCA
STARCH/POLYCAPROLACTONE/CLAY COMPOSITES**

By

THEN YOON YEE

March 2011

Chairman : Yg. Bhg. Professor Dato' Wan Md Zin Wan Yunus, PhD

Faculty : Science

In this work, plasticized tapioca starches (PTSs), blends of PTS and polycaprolactone (PCL), and composites of PTS/clay and PCL/PTS/clay were prepared by melt blending. Both natural clay (MMT) and octadecylamine modified clay (OMMT) were used in this study. OMMT was prepared by cation exchange reaction of Na^+ cation in the interlayer of MMT with octadecylammonium cation from octadecylammonium chloride. X-ray diffraction (XRD) results showed that the OMMT has bigger d-spacing than that of original MMT indicating octadecylammonium cation has successfully intercalated into the clay interlayer. Thermogravimetric analysis (TGA), Fourier transform infrared (FTIR) spectroscopy, and elemental analysis also indicated the presence of octadecylammonium cation in the OMMT.



PTSs were prepared by gelatinizing and plasticizing tapioca starch with water and glycerol, respectively in a Thermo Haake Polydrive internal mixer. Scanning electron micrographs showed that the tapioca starch formed a continuous phase after it was gelatinized and plasticized with water and glycerol. The study indicated that the tensile, thermal and water absorption properties of PTSs were strongly influenced by the contents of water and glycerol. The PTSs were water sensitive and exhibited low tensile properties. The formulation of tapioca starch, glycerol and water in the weight ratio of 5:1:4 was selected to study the effect of MMT, OMMT or PCL addition on its properties.

The composites of PTS/clay were prepared by melt blending of PTS with various amount of MMT or OMMT also in a Thermo Haake Polydrive internal mixer. The XRD and TEM results showed that the composites produced are of intercalated types. Transmission electron micrographs revealed that MMT was better dispersed than that of OMMT in the PTS matrix due to the strong polar interaction between the hydrophilic MMT and PTS. Consequently, higher tensile strength, modulus, thermal stability and storage modulus were observed in PTS/MMT composites compared to those of PTS/OMMT composites as well as neat PTS. However the water resistance property of PTS was improved by the presence of OMMT.

The blends of PCL and PTS were prepared by melt blending of PCL and PTS of different compositions also in a Thermo Haake Polydrive internal mixer. The presence of PCL improved the tensile strength, elongation at break, thermal stability and water resistance property of PTS.

PCL/PTS/clay composites were also prepared by melt blending the blend and clays. XRD results showed that the composites produced are of intercalated types. Transmission electron micrographs revealed that OMMT was better dispersed than that of MMT in the matrix. Significant improvements in tensile strength (> 60%) and elongation at break (> 1000%) were observed by the addition of 1 php of OMMT. Improvement in water resistance property was also observed in PCL/PTS/OMMT composites. In contrast, no obvious properties improvements were observed for PCL/PTS/MMT composites.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai
memenuhi keperluan untuk ijazah Master Sains

**PENYEDIAAN DAN PENCIRIAN KOMPOSIT KANJI UBI
KAYU/POLIKAPROLAKTON/TANAH LIAT**

Oleh

THEN YOON YEE

Mac 2011

Pengerusi : Yg. Bhg. Profesor Dato' Wan Md Zin Wan Yunus, PhD

Fakulti : Sains

Dalam kajian ini, kanji ubi kayu terplastik (PTSs), adunan PTS dan polikaprolakton (PCL) dan komposit PTS/tanah liat dan PCL/PTS/tanah liat telah disediakan melalui proses pengadunan lebur. Kedua-dua tanah liat semula jadi (MMT) dan tanah liat oktadesilamina terubahsuai (OMMT) telah digunakan dalam kajian ini. OMMT telah disediakan melalui kaedah penukaran kation di antara kation Na^+ dalam ruang antara lapisan MMT dengan kation oktadesilammonium dari oktadesilammonium klorida. Keputusan belauan x-ray (XRD) mendapati OMMT mempunyai jarak-d yang lebih besar daripada MMT asal menunjukkan kation oktadesilammonium telah berjaya interkalasi ke dalam ruang antara lapisan tanah liat. Analisis termogravimetrik (TGA), spektroskopi infra-merah jelmaan Fourier (FTIR), dan analisis unsur juga menunjukkan kehadiran kation oktadesilammonium dalam OMMT.

PTSs telah disediakan melalui proses penggelatinan dan pemplastikan kanji ubi kayu dengan menggunakan air dan gliserol, dalam mesin pencampur dalaman *Thermo Haake Polydrive*. Mikrograf imbasan elektron menunjukkan bahawa butiran kanji ubi kayu menjadi fasa berterusan selepas proses penggelatinan dan pemplastikan. Keputusan kajian menunjukkan bahawa kandungan air and gliserol mempunyai pengaruh yang kuat terhadap sifat-sifat ketegangan, terma dan penyerapan air bagi PTSs. PTSs adalah peka terhadap air dan mempunyai sifat tegangan yang rendah. Formulasi kanji ubi kayu, gliserol dan air dalam nisbah 5:1:4 telah dipilih untuk mengkaji kesan penambahan MMT, OMMT atau PCL ke atas sifat-sifat komposit yang dihasilkan.

Komposit PTS/tanah liat telah disediakan dengan mengadun leburan PTS dengan pelbagai kandungan MMT atau OMMT, juga dalam mesin pencampur dalaman *Thermo Haake Polydrive*. Keputusan XRD dan TEM menunjukkan komposit yang terhasil adalah jenis interkalasi. Mikrograf elektron transmisi mendedahkan bahawa MMT menyerak lebih baik daripada OMMT dalam matrik PTS kerana interaksi kutub lebih kuat antara hidrofilik MMT dan PTS. Ini menyebabkan kekuatan tegangan, modulus, kestabilan haba dan modulus simpanan yang lebih tinggi diperhatikan dalam komposit PTS/MMT berbanding dengan komposit PTS/OMMT serta PTS. Tetapi, sifat ketahanan terhadap penyerapan air pada PTS juga telah ditingkatkan dengan kehadiran OMMT.

Adunan PCL dan PTS telah disediakan dengan mengadun leburan PCL dan PTS dalam pelbagai komposisi, juga dalam mesin pencampur dalaman *Thermo Haake Polydrive*. Kekuatan tegangan, pemanjangan takat putus, kestabilan terma dan

ketahanan terhadap penyerapan air bagi PTS telah ditingkatkan dengan kehadiran PCL.

Komposit PCL/PTS/tanah liat juga disediakan dengan mengadun leburan adunan dengan tanah liat. Keputusan XRD menunjukkan komposit yang terhasil adalah jenis interkalasi. Mikrograf elektron transmisi mendedahkan bahawa OMMT menyerakan lebih baik berbanding dengan MMT dalam matrik. Peningkatan ketara dalam kekuatan tegangan ($> 60\%$) dan pemanjangan takat putus ($> 1000\%$) diperhatikan dengan penambahan 1 php OMMT. Peningkatan sifat terhadap ketahanan penyerapan air juga diperhatikan dalam komposit PCL/PTS/OMMT. Sebaliknya, tiada peningkatan sifat yang ketara diperhatikan bagi komposit PCL/PTS/MMT.

ACKNOWLEDGEMENTS

First, I am deeply thankful to my supervisor Prof. Dato' Dr. Wan Md Zin Wan Yunus for his supervision, stimulating suggestions and guidances for the past two years. His patience and encouragement helped me to grow as a student and a researcher. I am grateful to my co-supervisor Dr. Nor Azowa Ibrahim. Her dedication and enthusiasm in science greatly encourage me to work hard and pursue a great goal in research.

I thank the Ministry of Science, Technology and Innovation of Malaysia for its financial support through National Science Fellowship.

My thanks also go to the helpful and encouraging laboratory officers in Chemistry, and Physic Department of Science Faculty, Universiti Putra Malaysia especially Puan Rusnani Amirudin, Puan Zaidina Mohd Daud and Puan Linda for sharing their time and willingness to help. I extend my appreciation to all staffs in the Electron Microscopy Unit, Institute Bioscience, Universiti Putra Malaysia for assisting in the SEM and TEM analyses.

Special thanks go to all my colleagues in polymer group whose have always giving help, suggestions, encouragement and companion during hard times of my study.

Last but not the least, I would like to express my deepest gratitude to my beloved family who have always believes in me, and endured with me during difficult times. Credit is also given to anyone who had either directly or indirectly contributed to the completion of this thesis.



I certify that a Thesis Examination Committee has met on 4 March 2011 to conduct the final examination of Then Yoon Yee on his thesis entitled “Preparation and Characterization of Tapioca Starch/Polycaprolactone/Clay Composites” in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The committee recommends that the student be awarded the Master of Science.

Members of the Thesis Examination Committee were as follows:

Sidik bin Silong, PhD

Associate Professor

Faculty of Science

Universiti Putra Malaysia

(Chairman)

Mohd Zaki bin Abd Rahman, PhD

Associate Professor

Faculty of Science

Universiti Putra Malaysia

(Internal Examiner)

Mansor bin Hj Ahmad @ Ayob, PhD

Associate Professor

Faculty of Science

Universiti Putra Malaysia

(Internal Examiner)

Rusli Daik, PhD

Associate Professor

Faculty of Science and Technology

Universiti Kebangsaan Malaysia

(External Examiner)

NORITAH OMAR, PhD

Associate Professor and Deputy Dean

School of Graduate Studies

Universiti Putra Malaysia

Date: 19 April 2011

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows:

Dato' Wan Md Zin Wan Yunus, PhD

Professor

Faculty of Science

Universiti Putra Malaysia

(Chairman)

Nor Azowa Ibrahim, PhD

Senior Lecturer

Faculty of Science

Universiti Putra Malaysia

(Member)

HASANAH MOHD GHAZALI, PhD

Professor and Dean

School of Graduate Studies

Universiti Putra Malaysia

Date: 12 May 2011

x



DECLARATION

I declare that the thesis is my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously, and is not concurrently, submitted for any other degree at Universiti Putra Malaysia or at any other institution.

THEN YOON YEE

Date: 4 March 2011



TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	v
ACKNOWLEDGEMENTS	viii
APPROVAL	ix
DECLARATION	xi
LIST OF TABLES	xv
LIST OF FIGURES	xvi
LIST OF ABBREVIATIONS	xix
 CHAPTER	
 1 INTRODUCTION	1
1.1 Background of Study	1
1.2 Research Problems	4
1.3 Objectives of Study	5
 2 LITERATURE REVIEW	6
2.1 General Background of Starch	6
2.2 Cassava	6
2.3 Chemical Structure of Starch	7
2.4 Properties of Starch	8
2.5 Polycaprolactone (PCL)	10
2.6 Polymer Blending	11
2.6.1 Starch/Polycaprolactone Blends	11
2.6.2 Problems Exist in the Blends	12
2.7 Polymer/clay Composites	14
2.7.1 Clay	14
2.7.2 Structure of Polymer/clay Composites	17
2.7.3 Characterization of Polymer/clay Composites Structure	19
2.7.4 Preparation of Polymer/clay Composites	20
2.7.5 Properties of Polymer/clay Composites	22
 3 MATERIALS AND METHODS	27
3.1 Materials	27
3.2 Preparation of Organo-modified Clay	27
3.3 Preparation of Plasticized Tapioca Starches (PTSs)	28
3.4 Preparation of PTS/clay Composites	29
3.5 Preparation of PCL/PTS Blends	29
3.6 Preparation of PCL/PTS/clay Composites	30
3.7 Characterizations	31
3.7.1 Fourier Transform Infrared (FTIR) Spectroscopy	31
3.7.2 X-ray Diffraction (XRD)	32
3.7.3 Elemental Analysis	32
3.7.4 Thermogravimetric Analysis (TGA)	32

3.7.5	Tensile Properties Measurement	33
3.7.6	Dynamic Mechanical Analysis (DMA)	33
3.7.7	Scanning Electron Microscopy (SEM)	34
3.7.8	Transmission Electron Microscopy (TEM)	34
3.7.9	Water Absorption Test	34
4	RESULTS AND DISCUSSION	36
4.1	Preparation and Characterization of Organo-modified Clay	36
4.1.1	X-ray Diffraction	36
4.1.2	Fourier Transform Infrared Spectroscopy	37
4.1.3	Elemental Analysis	38
4.1.4	Thermogravimetric Analysis	39
4.2	Preparation and Characterization of Plasticized Tapioca Starches (PTSs)	42
4.2.1	Fourier Transform Infrared Spectroscopy	42
4.2.2	The Effects of Water and Glycerol on the Properties of PTSs	43
4.3	Preparation and Characterization of PTS/clay Composites	52
4.3.1	Fourier Transform Infrared Spectroscopy	52
4.3.2	Dispersion of MMT or OMMT in the PTS Matrix	53
4.3.3	Tensile Properties	58
4.3.4	Dynamic Mechanical Analysis	62
4.3.5	Thermogravimetric Analysis	65
4.3.6	Scanning Electron Microscopy	69
4.3.7	Water Absorption	70
4.4	Preparation and Characterization of PCL/PTS Blends	71
4.4.1	Fourier Transform Infrared Spectroscopy	72
4.4.2	Tensile Properties	73
4.4.3	Thermogravimetric Analysis	75
4.4.4	Scanning Electron Microscopy	78
4.4.5	Water Absorption	78
4.5	Preparation and Characterization of PCL/PTS/clay Composites	80
4.5.1	Fourier Transform Infrared Spectroscopy	80
4.5.2	Dispersion of MMT or OMMT in the PCL/PTS Matrix	81
4.5.3	Tensile Properties	85
4.5.4	Dynamic Mechanical Analysis	89
4.5.5	Thermogravimetric Analysis	91
4.5.6	Scanning Electron Microscopy	95
4.5.7	Water Absorption	95
5	CONCLUSIONS AND RECOMMENDATIONS FOR FUTURE RESEARCH	98
5.1	Conclusions	98
5.2	Recommendations for Future Research	99
REFERENCES		101
APPENDICES		112

**BIODATA OF STUDENT
LIST OF PUBLICATIONS**

114
115

