



**UNIVERSITI PUTRA MALAYSIA**

**EFFECT OF HEAT TREATMENT ON CELLULOSE CRYSTALLINITY OF  
EMPTY FRUIT BUNCH OIL PALM FIBER AND ITS RELATION TO THE  
DIMENSIONAL STABILITY OF MEDIUM DENSITY FIBERBOARD**

**SITI MUNAWARAH BINTI ABDUL HAFID**

**FH 2005 12**



**EFFECT OF HEAT TREATMENT ON CELLULOSE CRYSTALLINITY OF  
EMPTY FRUIT BUNCH OIL PALM FIBER AND ITS RELATION TO THE  
DIMENSIONAL STABILITY OF MEDIUM DENSITY FIBERBOARD**

**By**

**SITI MUNAWARAH BINTI ABDUL HAFID**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra  
Malaysia in Fulfillment of Requirement for the Degree of Master of  
Science**

**November 2005**



*Specially dedicated to*

*Abang*  
*Mak and Bapa , Ma and Ayah*  
*My daughter and My son,*  
*My brothers and sisters*

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Master of Science.

**EFFECT OF HEAT TREATMENT ON THE CELLULOSE CRYSTALLINITY OF EMPTY FRUIT BUNCH OIL PALM FIBER AND ITS RELATION TO THE DIMENSIONAL STABILITY OF MEDIUM DENSITY FIBERBOARD**

By

**SITI MUNAWARAH BINTI ABDUL HAFID**

**November 2005**

**Chairman: Professor Mohd. Hamami Sahri, PhD**

**Faculty: Forestry**

Oil Palm (*Elaeis guinensis*) is an important commercial agriculture plant in Malaysia generating a vast amount of residues, in the form of oil palm trunk (OPT), oil palm frond (OPF) and empty fruit bunch (EFB) which have high potential as raw material in wood-based industry. However, these lignocellulosic materials have poor dimensional stability i.e., high thickness swelling and water absorption. Cellulose crystallinity has been reported to influence the physical properties of the fibers. This study attempts to increase the cellulose crystallinity of oil palm EFB fiber via heat treatment and aimed i) to evaluate the effect of heating temperature on the cellulose crystallinity of oil palm EFB fiber ii) to determine the effect of cellulose crystallinity on thickness swelling (TS) and water absorption (WA) of Medium Density Fiberboard (MDF) made from heat treated oil palm fibers and iii) to establish relationship between cellulose crystallinity and TS and WA.



Oil palm EFB fibers were heated for two hours at different temperatures, 150°C, 160°C, 170°C, and 180°C. Untreated samples were used as control. The crystallinity and crystallite size of the cellulose molecules were investigated using X-ray diffraction (XRD) technique. Chemical analyses were also conducted on both heat treated and untreated EFB fibers to determine the proximate amount of lignin, cellulose and hemicellulose. MDF with the size of 130mm x 130mm x 5mm were produced from these fibers. The density of the MDF was 700 Kg<sup>m</sup><sup>-3</sup>. The effects of cellulose crystallinity to the TS and WA of board were examined.

The proximate amount of chemical components in the EFB fiber in this study was found comparable with those of conventional wood. The lignin content was in the range of 20-27%, cellulose content was 40-47% and hemicellulose content was 23-25%.

The results shows that crystallinity of oil palm EFB cellulose were 21.05% for untreated fiber, 27.09% for fiber heated at 150°C, 26.68% at 160°C, 26.53% at 170°C and 30.84% at 180°C. The corresponding crystallite sizes of the cellulose sample were 3.22 nm, 3.42 nm, 3.64, 3.38 nm and 2.93 nm respectively. Heat treatment was found to increase the cellulose crystallinity of EFB fiber but did not markedly affected the crystallite size.

In this study, MDF made from heat treated EFB of oil palm fiber was found to have relatively high TS and WA and failed to pass the Japanese Industrial Standard (JIS A 5906 – 1983). The TS were 15.9% in the MDF from untreated

fiber, 16.5% for the MDF from fiber heated at 150°C, 16.3% at 160°C, 15.3% at 170°C and 15.6% at 180°C. Meanwhile the WA of the MDF boards was 77.7%, 81.0%, 79.5%, 83.2% and 71.8%, respectively. It was found that the increase in temperature in this study gave no effect to the TS but reduce the WA only at temperature of 180°C. This study found that there were no trend found in the relationship between cellulose crystallinity with TS and WA at various temperatures as the R-squares were very small. There was also no direct effect of increase in cellulose crystallinity to the TS and WA of MDF as the R-squares were very small.

Even though the cellulose crystallinity of EFB fiber increased by heat treatment, it was not sufficient to impart dimensional stability to the MDF board.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia  
sebagai memenuhi keperluan untuk ijazah Master Sains

**KESAN RAWATAN SUHU KE ATAS KRISTALIT SELULOSA GENTIAN  
TANDAN KELAPA SAWIT DAN KAITANNYA TERHADAP KESTABILAN  
DIMENSI MEDIUM DENSITY FIBERBOARD**

Oleh

**SITI MUNAWARAH BINTI ABDUL HAFID**

**November 2005**

**Pengerusi: Profesor Mohd Hamami Sahri, PhD**

**Fakulti: Perhutanan**

Kelapa sawit (*Elaeis guinensis*) adalah merupakan tanaman komersil pertanian di Malaysia yang menghasilkan banyak sisa-sisa dalam bentuk batang (OPT), pelepah (OPF) dan tandan (EFB) yang mempunyai potensi sebagai bahan mentah di dalam industri berasaskan kayu. Walaubagaimanapun, bahan-bahan lignoselulosa ini mempunyai kestabilan dimensi (pembengkakan dan penyerapan air) yang rendah. Kristalit selulosa dipercayai mempengaruhi ciri-ciri fizikal gentian. Oleh itu, kajian ini adalah bertujuan untuk meningkatkan kristalit selulosa gentian tandan kelapa sawit melalui rawatan suhu dan juga untuk i) menilai kesan pemanasan ke atas kristalit selulosa gentian kelapa sawit ii) menentukan kesan-kesan kristalit selulosa ke atas pembengkakan dan penyerapan air oleh MDF yang dibuat dari gentian kelapa sawit yang telah dirawat dengan suhu dan iii) menghasilkan hubungan di antara kristalit selulosa dengan pembengkakan dan penyerapan air.

Gentian tandan kelapa sawit dirawat dengan suhu pada tahap yang berlainan iaitu 150°C, 160°C, 170°C and 180°C selama dua jam. Sampel tanpa rawatan suhu juga disediakan sebagai kawalan. Kristalit dan saiz kristalit molekul selulosa di dalam gentian kelapa sawit dikaji menggunakan teknik 'X-ray diffraction (XRD)'. Analisis kimia juga dijalankan ke atas gentian tandan kelapa sawit tersebut untuk menentukan kandungan lignin, selulosa dan juga hemiselulosa. Papan MDF bersaiz 130mm x 130mm x 5mm dan mempunyai 700 Kg<sup>m</sup><sup>-3</sup> ketumpatan juga dihasilkan dari gentian tandan kelapa sawit tersebut. Kesan kristalit selulosa ke atas pembengkakan dan penyerapan air oleh papan juga dikaji.

Kandungan komponen kimia gentian tandan kelapa sawit yang dianggarkan melalui kajian ini didapati lebih kurang sama dengan kayu biasa. Kandungan ligninnya adalah di antara 20-27%, kandungan selulosa adalah 40-47% dan kandungan hemiselulosanya pula adalah 23-25%.

Hasil daripada kajian menunjukkan kristalit di dalam selulosa gentian kelapa sawit adalah 21.05% di dalam gentian tanpa rawatan, 27.09% untuk gentian yang telah dirawat pada 150°C, 26.68% pada 160°C, 26.53% pada 170°C dan 30.84% pada 180°C. Saiz kristalit sampel selulosa masing-masing adalah 3.22 nm, 3.42 nm, 3.38 nm dan 2.93 nm. Rawatan suhu telah meningkatkan kristalit selulosa gentian tandan kelapa sawit tetapi tidak memberi kesan ke atas saiz kristalit.



Kajian ini juga menunjukkan bahawa MDF daripada gentian tandan kelapa sawit mempunyai pembengkakan dan penyerapan air yang tinggi dan tidak dapat memenuhi keperluan yang digariskan oleh Japanese Industrial Standard (JIS A 5906 1983). Pembengkakan ialah 15.9% bagi papan MDF yang dibuat daripada gentian yang tidak dirawat, 16.5% pada papan MDF dari gentian yang telah dirawat pada 150°C, 16.3% pada 160°C, 15.3% pada 170°C dan 15.6% pada 180°C. Manakala penyerapan air papan MDF masing-masing adalah 77.7%, 81.0%, 79.5%, 83.2% dan 71.8%. Peningkatan suhu didapati tidak mempunyai kesan ke atas tahap pembengkakan papan MDF tetapi tahap penyerapan air papan didapati berkurang pada suhu 180°C. Kajian ini mendapati bahawa hubungan antara kristalit selulosa dengan tahap pembengkakan dan penyerapan air papan MDF pada kebanyakan tahap suhu tidak mempunyai tren kerana R-square yang diperolehi terlalu kecil. Kajian ini juga mendapati tidak ada hubungan di antara peningkatan kristalit selulosa dengan pembengkakan dan penyerapan air papan MDF kerana R-square yang diperolehi juga terlalu kecil.

Kristalit selulosa gentian kelapa sawit meningkat dengan rawatan suhu tetapi, tidak dapat memberikan kestabilan dimensi kepada papan MDF.

## ACKNOWLEDGEMENTS

In the name of Allah, the Almighty.....,

Firstly, the highest gratitude to Allah S.W.T due to His Blessing that I am able to complete and accomplish this study.

I wish to express my heartiest gratitude to my supervisor Prof. Dr. Mohd. Hamami Bin Sahri for his guidance, assistance, advise and comments throughout this study. His valuable comments, support, counseling and encouragement were a guide upon the completion of this study.

I am greatly indebted to my committee members Prof. Dr. Mohamad Deraman (UKM), Prof. Madya Mohd. Zin Bin Jusoh (UPM) and Prof. Madya Dr. Paridah Binti Md. Tahir (UPM) for their assistance, suggestion, valuable comments, encouragements and moral support during this study.

Sincere thanks to all the lecturers and staff of the faculty especially Mr. Harmaen Bin Ahmad Saffian for his help, assistance and support. My sincere thanks also go to Mr. Zaini, laboratory assistance of Material Science laboratory at Department of Physic of Universiti Kebangsaan Malaysia and Mr. Aziz Ngah and Mr. Zahari, laboratory assistances of X-ray Diffraction laboratory at Geology Department, Universiti Kebangsaan Malaysia.

My sincere thanks also extended to my colleague, Shirley Bakansing for her help, moral support, and advice and sharing her knowledge with me.

My deepest appreciation and thanks to my husband Mohamad Azani Bin Alias for his love, concern, encouragements, constructive comments and continuous support. Special thanks and appreciation to my daughter and son, Siti Aisyah and Muhammad Danish, father, mother also my brothers and sisters for their concerns, inspiration and strong support.

I certify that an Examination Committee has met on 22 November 2005 to conduct the final examination of Siti Munawarah Binti Abdul Hafid on her Master of Science thesis entitled "Effect of Heat Treatment on Cellulose Crystallinity of Empty Fruit Bunch Oil Palm Fiber and Its Relation to the Dimensional Stability of Medium Density Fiberboard" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

**Zaidon Ashaari, PhD**

Associate Professor  
Faculty of Forestry  
Universiti Putra Malaysia  
(Chairman)

**Mohd Zobir Hussein, PhD.**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Internal Examiner)

**Fauzi Febrianto, PhD**

Lecturer  
Faculty of Forestry  
Universiti Putra Malaysia  
(Internal Examiner)

**Othman Sulaiman, PhD**

Associate Professor  
School of Industrial Technology  
Universiti Sains Malaysia  
(External Examiner)

---

**HASANAH MOHD. GHAZALI, PhD**

Professor/ Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:



This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The members of the Supervisory Committee are as follows:

**Mohd. Hamami Bin Sahri, PhD**

Professor  
Faculty of Forestry  
Universiti Putra Malaysia  
(Chairman)

**Mohamad Bin Deraman, PhD**

Professor  
Faculty of Science and Technology  
Universiti Kebangsaan Malaysia  
(Member)

**Paridah Binti Md. Tahir, PhD**

Associate Professor  
Faculty of Forestry  
Universiti Putra Malaysia  
(Member)

**Mohd. Zin Bin Jusoh**

Associate Professor  
Faculty of Forestry  
Universiti Putra Malaysia  
(Member)

---

**AINI IDERIS, PhD**

Professor/Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:



## DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not previously or concurrently submitted for any degree at UPM or other institutions.

---

**SITI MUNAWARAH BINTI ABDUL HAFID**

Date:

## TABLE OF CONTENTS

	<b>Page</b>
<b>DEDICATION</b>	ii
<b>ABSTRACT</b>	iii
<b>ABSTRAK</b>	vi
<b>ACKNOWLEDGEMENTS</b>	x
<b>APPROVAL</b>	xi
<b>DECLARATION</b>	xii
<b>LIST OF TABLES</b>	xv
<b>LIST OF FIGURES</b>	xvii
<b>LIST OF PLATES</b>	xix
<b>LIST OF ABBREVIATIONS</b>	xx
 <b>CHAPTER</b>	
<b>1 INTRODUCTION</b>	<b>1</b>
1.1 General	
1.2 Justification	3
1.3 Problem Statements	7
1.4 Objectives	9
 <b>2 LITERATURE REVIEW</b>	
2.1 Introduction	10
2.2 Production of Oil Palm Residues	12
2.3 Oil Palm Empty Fruit Bunches (EFB)	14
2.3.1 Properties	15
2.3.2 Supply	17
2.3.3 Collection and Processing Problems	18
2.3.4 Past Researches	19
2.3.5 Chemical Content	22
2.4 Cellulose	24
2.4.1 Cellulose Crystallinity	25
2.4.2 Cellulose Crystallite Size	31
2.5 Medium Density Fiberboard(MDF)	32
2.5.1 MDF Industry in Malaysia	32
2.5.2 MDF Produced from Palm fibers	33
2.5.3 Properties of MDF Palm Fibers	41
 <b>3 MATERIALS AND METHOD</b>	
3.1 Experimental Design	44
3.2 Heat Treatment	45
3.3 Determination of Chemical Constituents	45
3.4 Determination of Cellulose Crystallinity in Oil Palm EFB Fiber	46
3.4.1 Pellet Preparation	46



	3.4.2	Determination of Cellulose Crystallinity	48
3.5		Medium Density Fiberboard Manufacture	51
	3.5.1	Board Fabrication	52
	3.5.2	Testing Method	53
3.6		Statistical Analysis	55
4		<b>RESULT AND DISCUSSION</b>	
	4.1	Chemical Constituents in Oil Palm EFB Fiber	56
		4.1.1 Lignin	57
		4.1.2 Cellulose	58
		4.1.3 Hemicellulose	60
	4.2	Crystallinity and Crystallite Size of Cellulose	63
		4.2.1 Crystallite Size	64
		4.2.2 Crystallinity	69
	4.3	MDF Board Physical Properties	74
		4.3.1 Thickness Swelling	75
		4.3.2 Water Absorption	77
		4.3.3 Effect of Degree of Cellulose Crystallinity on Board's Dimensional Stability	78
5		<b>CONCLUSIONS AND RECOMMENDATIONS</b>	89
		<b>REFERENCES</b>	92
		<b>APPENDICES</b>	101
		<b>BIODATA OF THE AUTHOR</b>	122

## LIST OF TABLES

Table	Page	
1.1	Estimated Oil Palm Biomass Supply in Malaysia in 2002	2
1.2	Fiber Dimension of Oil Palm Trunks, Fronds and Bunches in Comparison to Rubberwood	4
1.3	Mechanical Properties of Oil Palm Trunk and Rubberwood	5
2.1	Availability of Oil Palm By-Products in Peninsular Malaysia (2004-2006)	13
2.2	Rubberwood Supply for Wood Industry in Malaysia (1997-2000)	14
2.3	Outlooks of Oil palm Empty Fruit Bunch (EFB) Supply in Peninsular Malaysia (tones/year, dry weight)	18
2.4	Cellulose Content of Various Plant Materials	23
2.5	Proximate Chemical Constituent of Oil Palm, Hardwood and Softwood	24
2.6	Crystallinity of Various Cellulose Materials	29
3.1	Standard Values of Mass Absorption Coefficient for Elements C, H, O Itself and Standard Values for The Elements in Cellulose, Hemicellulose and Lignin	51
4.1	Chemical Constituents in EFB Oil Palm Fibers	56
4.2	Lignin Content of Oil Palm EFB Fiber at Various Temperature Levels	58
4.3	Cellulose Content Of oil Palm EFB Fiber at Various Temperature Levels	59
4.4	Hemicellulose Content of Oil Palm EFB Fiber at Various Temperature Levels	61
4.5	Crystallite Size of Cellulose of Oil Palm EFB Fiber	66
4.6	Means and Standard Deviations of Cellulose Crystallite Size of Oil Palm EFB Fiber at Various Temperature Levels	67
4.7	X-ray Intensities from The Peaks 002 Crystalline and Amorphous Scattering of Cellulose in The Samples, The	69





	Estimated Crystallinity	
4.8	Means and Standard Deviations of cellulose Crystallinity at Different Heating Temperatures	69
4.9	Mass Absorption Coefficient for The Element, Molecular Components, EFB (UT, 150°C, 160°C, 170°C and 180°C)	71
4.10	Means and Standard Deviations of Thickness Swelling of MDF	76
4.11	Means and Standard Deviations of Water Absorption of MDF	77

## LIST OF FIGURES

Figure	Page	
2.1	Distribution of Organic Carbon in Organic Matter	23
2.2	Celulose Molecules	25
2.3	Cellobiose Unit and Anhydroglucopyranose Unit (glucose anhydrate unit)	25
2.4	Crystalline and Amorphous Region	27
2.5	Crystalline and Amorphous Regions in Cellulose Chain	27
2.6	Cross-Linking of Cellulose Molecules by Hydrogen Bonds	28
2.7	The Process of Converting EFB Fibrous Strand that Suits to MDF Production	36
4.1	Chemical Content (Lignin, Cellulose And Hemicellulose) in Oil Palm EFB Fiber at Various Temperature Levels	63
4.2	The Diffraction Intensity Over the Angular Angle Range $2(\theta)$ of $5^{\circ}$ - $55^{\circ}$	68
4.3	Cellulose Crystallite Size and Crystallinity of Oil Palm EFB Fiber at Various Temperature Levels	70
4.4	Thickness Swelling and Water Absorption of MDF Board Made from Heat-Treated EFB Fibers	78
4.5	Relationship between Cellulose Crystallinity and Thickness Swelling at Untreated (UT) Sample	82
4.6	Relationship Between Cellulose Crystallinity and Thickness Swelling at $150^{\circ}\text{C}$	83
4.7	Relationship Between Cellulose Crystallinity and Thickness Swelling at $160^{\circ}\text{C}$	83
4.8	Relationship Between Cellulose Crystallinity and Thickness Swelling at $170^{\circ}\text{C}$	83
4.9	Relationship Between Cellulose Crystallinity and Thickness Swelling at $180^{\circ}\text{C}$	84

4.10	Relationship Between Cellulose Crystallinity and Water Absorption of Untreated (UT) Oil Palm EFB Fiber	84
4.11	Relationship Between Cellulose Crystallinity and Water Absorption at 150°C Heat Treatment of Oil Palm EFB Fiber	84
4.12	Relationship Between Cellulose Crystallinity and Water Absorption at 160°C Heat Treatment of Oil Palm EFB Fiber	85
4.13	Relationship Between Cellulose Crystallinity and Water Absorption at 170°C Heat Treatment of Oil Palm EFB Fiber	85
4.14	Relationship Between Cellulose Crystallinity and Water Absorption at 180°C Heat Treatment of Oil Palm EFB Fiber	85
4.15	a) Relationship Between Cellulose Crystallinity and Thickness Swelling (TS);	86
	b) Relationship Between Cellulose Crystallinity and Water Absorption (WA)	93

## LIST OF PLATES

Plate		Page
2.1	Oil Palm Trees ( <i>Elaeis guinensis</i> )	11
2.2	Scene of Oil Palm Plantation in Peninsular Malaysia	12
2.3	a) Oil Palm Empty Fruit Bunch (EFB) b) EFB Fibers	15
2.4	Ultrastructure of Oil Palm EFB Autoclaved in water (a: surface view, b:Silica distribution)	16
2.5	SEM Photograph of the Cross Section of Oil Palm EFB Fibers	17
2.6	MDF from EFB Fibers	22
2.7	Fiber Extractor	35
2.8	Fiber Shortener	36
2.9	The Screw Press	37
2. 10	The Homogenising Screw	37
2.11	The Pelletising Press	38
2.12	The Bladeless Cutting Principle	38
2.13	Processing Trunks and Fronds	39
2.14	Depithing Chips from Trunks	40
3.1	Pellet (Disc Specimen) D: Diameter t: Thickness	47
3.2	Cylindrical Mould with Compression Force	47
3. 3	D-500 Siemen Diffractometer	48
4.1	MDF Board Produced from Heat-treated Oil Palm EFB Fiber	75

## LIST OF ABBREVIATIONS

Å	Angstrom
BS	British Standard
CaO	calcium oksida
Cm <sup>2</sup> /g	centimeter per square gram
EMB	European Standard
g	gram
IB	Internal Bond
JIS	Japanese Standard
Kg/m <sup>2</sup>	Square kilogram per meter
K <sub>2</sub> O	kalium oksida
Kg/m <sup>3</sup>	Cubic kilogram per meter
MOE	Modulus of Elasticity
MOR	Modulus of Rupture
MPa	Mega Pascal
MgO	Magnesium Oksida
N	Newton
N <sub>2</sub>	Nitrogen
NPA	National Particleboard Association

# CHAPTER 1

## INTRODUCTION

### 1.1 General

Oil Palm (*Elaeis guinensis*) is an important commercial agriculture plant in Malaysia and originated from West Africa. The main product from this plant is crude palm oil, which can be further processed into vegetable oil and other industrial and food products. Malaysia is among the highest producer of palm oil production and this is attributed to the climate and good management arising from research and development (R&D) (Yusof and Chan, 2004). The other producing countries are Indonesia, Colombia, Ivory Cost and Papua New Guinea (Yusof and Mohd. Arif, 2005).

Malaysia has over 3.6 million hectares of land covered by oil palm cultivation and the oil only consists about 10% of total biomass produced in the plantation (Mohamad Husin *et al.*, 2002). Therefore, the oil palm plantation generating a large amount of residue in the form of trunk (Oil Palm Trunk), fronds (Oil Palm Frond) and fruit bunches (Empty Fruit Bunch). Mohamad Husin *et al.* (2002) estimated that there were about eight million tones of oil palm trunk (OPT), 22 million tones of oil palm frond (OPF) and about five million tones of empty fruit bunch (Table 1.1). This large amount of residues consists of lignocellulosic materials (Mohd. Zin and Imamura, 1989; Yusof and Muhamad Husin., 1997) and therefore provide an alternative resource for the

wood industry especially in wood composite board industry to complement of impending shortage of rubberwood supply.

Table 1.1: Estimated Oil Palm Biomass Supply in Malaysia in 2002

<b>Oil Palm Biomass</b>	<b>Supply (t/y dry weight) (million tones)</b>
Oil Palm Trunk (OPT)	8
Oil Pal Frond (OPF)	22
Empty Fruit Bunch (EFB)	5

Source: Mohamad Husin *et al.*, (2002)

Generally, wood is made up of three important organic compounds called cellulose, hemicellulose and lignin. Among these three components, cellulose is the most important as it constitutes slightly less than one half the weights of both hardwoods and softwoods. Cellulose is also the main chemical constituent in most wood (Sjöström, 1981).

The reactivity of cellulose is affected by its two-phase morphology i.e crystalline and amorphous regions. Sjöström (1981) indicated that this morphology played major roles on cellulose reactivity. The hydroxyl groups located in the amorphous regions were highly accessible and react readily while those in the crystalline regions with closely packed and strong interchain bonding can be completely inaccessible. Therefore, this morphological nature may affect the composite board in term of its dimensional changes. Crystallinity is very important factor, which in turn affect the physical properties of the board (Wadsworth and Cuculo, 1978).

Realising the importance of cellulose crystallinity, a number of researches have been conducted which covers many aspects. Crystallinity index, is one of the importances which related to the degree of crystallinity can be determined and evaluated. There are many techniques to determine the proportion of crystalline and non-crystalline (amorphous) in the cellulose molecules. There were three main methods of determinations, i.e. the physical, swelling and non-swelling methods are available to measure the degree of crystallinity in the cellulose molecules (Wadsworth and Cuculo., 1978). The physical method, i.e. x-ray diffraction method is the most popular to determine the cellulose crystallinity. With x-ray, it is possible to determine the finer structure in crystallite materials (Stamm, 1964). Krässig (1993) also stated that it is the most versatile method of determining the structure characteristics of cellulose substrate in the small as well as in the wide angle region. In the wide angle region (beyond  $2\theta=6^\circ$ ), the x-ray diffraction allows the determination of the degree of crystallinity, the degree of orientation and from the width at half maximum of the meridional and equatorial reflections, the crystallite length and width dimension respectively (Krässig, 1993).

## **1.2 Justification**

A large amount of lignocellulosic residues from oil palm tree will be available in the future. These residues include trunks, leaf, fruit bunches and fronds consist of solid and fibrous raw materials. Oil palm trunks, which considered being readily available non-wood lignocellulosic material, may be used as a



compliment or a substitute to the timber resources especially for production of wood composite products.

Generally, oil palm residues or oil palm by-products can be converted into fibrous strands and can be utilised in the production of composite board such as cementboard, particleboard, fibreboard, blockboard and others. Mohd. Husin *et al.* (1985) noted that oil palm fibre is short and thin but it is comparable in length to the fibre of rubberwood, the conventional source of raw material in the wood industry (Table 1.2). Salleh (1994) indicated that the oil palm strands also have comparable cellulose content to the average Malaysian hardwoods. Although, the mean fibre length of oil palm strands is much shorter than most Malaysian hardwoods, the fibres width is almost similar with those of medium density or heavy density hardwoods and the cell wall thickness is similar to that of light density hardwood. Therefore oil palm fibre provides an alternative source of raw material in the wood composite industry.

Table 1.2: Fibre dimension of oil palm trunks, fronds and bunches in comparison to rubberwood

Dimension	Part			
	Trunks	Fronds	Bunches	Rubberwood
Length (mm)	1.22	1.52	0.89	1.50
Width (mic)	35.3	-	25.0	40.0
Cell wall thickness (mic)	4.5	-	2.8	0.50

Source: Mohamad. Husin *et al.* (1985)

