



**UNIVERSITI PUTRA MALAYSIA**

***SYNTHESIS AND EVALUATION OF UNDOPED AND SILVER AND  
COPPER DOPED LITHIUM TETRABORATE NANOPARTICLES  
AS THERMOLUMINESCENCE DOSIMETER***

**NASRIN KHALILZADEH**

**FS 2014 4**



**SYNTHESIS AND EVALUATION OF UNDOPED  
AND SILVER AND COPPER DOPED LITHIUM  
TETRABORATE NANOPARTICLES AS  
THERMOLUMINESCENCE DOSIMETER**

**NASRIN KHALILZADEH**

**DOCTOR OF PHILOSOPHY  
UNIVERSITY PUTRA MALAYSIA**

**2014**



**SYNTHESIS AND EVALUATION OF UNDOPED AND SILVER AND COPPER  
DOPED LITHIUM TETRABORATE NANOPARTICLES  
AS THERMOLUMINESCENCE DOSIMETER**

**By**

**NASRIN KHALILZADEH**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in  
Fulfillment of the Requirements for the Degree of Doctor of Philosophy**

**August 2014**

## COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs, and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright© Universiti Putra Malaysia



## DEDICATION

This Thesis is dedicated to my beloved husband, Majid, and my sweetheart son, Danial, who have supported and encouraged me all the way since the beginning of my PhD studies at UPM. Since without their encouragements, I would never be able to accomplish my research. Besides, a special thanks goes to my husband's parents Mr. and Mrs. Mirabolghasemi and my brothers' in law Hadi, Majd, and Dr.Hamed, who like their parents were more than generous with their precious time to give me spiritual supports and encouragements. I feel I am spiritually in debt of my husband's family, and to the memory of my parents who were motivated me for learning through my life journey. Finally, this thesis is dedicated to all those who believe in the richness of learning.

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Doctor of Philosophy

**SYNTHESIS AND EVALUATION OF UNDOPED AND SILVER AND  
COPPER DOPED LITHIUM TETRABORATE NANOPARTICLES AS  
THERMOLUMINESCENT DOSIMETER**

By

**NASRIN KHALILZADEH**

**August 2014**

**Chairman: Professor Elias B Saion, PhD**

**Faculty: Science**

Tissue equivalent thermoluminescence dosimeters (TLDs) are commonly used for monitoring dose of ionizing radiation as personal or medical radiation dosimeters. The commercially available macro-scale lithium tetra borates (LTB) have several drawbacks such as poor Thermoluminescent (TL) intensity, limited dose linearity, losses information with time (fading) and energy dependence, which might be improved by using nano-scale activated LTB, the main goal of this study. LTB is the most popular material for radiation dosimetry because of its effective atomic number ( $Z_{\text{eff}} = 7.4$ ) that close with the  $Z_{\text{eff}}$  of human tissue (7.42). Furthermore, LTB is almost stable chemical compound and can be easily doped with TL sensitizers. In line with this development the objectives of this work were to synthesize and to investigate the structural characteristics and TL properties of undoped LTB and silver and copper doped LTB (LTB-Ag and LTB-Cu) nanoparticles for dosimetric applications. The LTB nanoparticles were synthesized by using innovative single step thermal treatment method. Subsequently, the samples were investigated for thermal stability and phase transition using thermal gravimetric analysis (TGA), derivative thermogravimetry analysis (DTG), and differential scanning calorimetry (DSC). The TGA, DTG, and DSC results showed the triple phases of mass loss were observed. Fourier transform infrared spectroscopy (FT-IR) was used to monitor the formation nanoparticles in the range of  $200\text{--}4000\text{ cm}^{-1}$ . The samples were subjected to different calcination temperatures and found 650, 700, and 750 °C were the principal calcination temperatures based on the X-ray diffraction

(XRD) patterns and transmission electron microscopy (TEM) images. To study the effect of PVP capping agent for regulating nanoparticles' agglomeration, 0.009, 0.018, and 0.027 mol of PVP concentrations were used. The narrowest particle size and size distributions were reached at 0.027 mol of PVP for LTB and LTB-Cu nanoparticles and at 0.018 mol of PVP for LTB-Ag nanoparticles. The average particle sizes determined from TEM size distributions were 3.34, 4.61, and 4.56 nm for LTB, LTB-Cu and LTB-Ag nanoparticles, respectively at calcination temperature of 750 °C. The UV-visible spectroscopy (UV-Vis) was used to determine the optical bandgap of the synthesized nanoparticles. To investigate the TL property of the synthesized nanoparticles, dose response, energy storage ability, and energy dependence of nanophosphors were studied from glow curve of dose response at a variety of dose ranges of 0.005, 0.01, 0.1, 0.5, 1, 10, 100, and 150 Gy. The current nano-scale doped and undoped LTB dosimeters have good physical properties and TL response that they can be produced easily by single step thermal treatment method at effective cost and without by-product effluents.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia  
sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**PEMBUATAN DAN PENILAIAN TIDAK TERDOP DAN TERDOP  
NANOPARTIKEL LITHIUM TETRA BORAT OLEH PERAK DAN  
TEMBAGA SEBAGAI DOSIMETER TERMOPENDARKILAU**

Oleh

**NASRIN KHALILZADEH**

**Ogos 2014**

**Pengerusi: Professor Elias B Saion, PhD**

**Fakulti: Sains**

Tisu dosimeter termopendarkilau setara (TLD) biasanya digunakan untuk memantau dos radiasi mengion sebagai dosimeter radiasi peribadi atau perubatan. Litium tetra borat berskala makro (LTB) boleh didapati secara komersial dan mempunyai beberapa kelemahan seperti keamatan TL rendah, kelinearan dos terhad, kehilangan maklumat dengan masa (pudar) dan pergantungan tenaga, ia boleh diperbaiki dengan menggunakan skala-nano yang diaktifkan LTB, yang merupakan matlamat utama kajian ini. LTB adalah bahan yang paling popular untuk dosimetri radiasi kerana keberkesanan nombor atom ( $Z_{\text{eff}} = 7.4$ ) yang menghampiri dengan  $Z_{\text{eff}}$  tisu manusia (7.42). Tambahan pula, LTB adalah sebatian kimia yang hampir stabil dan mudah didopkan dengan pemeka TL. Selaras dengan perkembangan ini objektif kerja ini adalah untuk mensintesis dan untuk menyiasat ciri-ciri struktur dan sifat-sifat TL yang diadaptasi daripada nanopartikel LTB tidak terdop dan LTB terdop perak dan tembaga (LTB-Ag dan Cu-LTB) untuk aplikasi dosimetrik. Nanopartikel LTB telah disintesis dengan menggunakan langkah inovatif kaedah rawatan haba. Selepas itu, sampel telah disiasat untuk kestabilan terma dan peralihan fasa menggunakan analisis terma gravimetrik (TGA), analisis terma terbitan (DTG), dan kalori pengimbasan kebezaan (DSC). Keputusan TGA, DTG, dan DSC menunjukkan tiga fasa kehilangan jisim telah diperhatikan. Spektroskopi pengubah fourier inframerah (FT-IR) telah



digunakan untuk memantau pembentukan nanopartikel dalam lingkungan 200-4000  $\text{cm}^{-1}$ . Sampel telah diselaraskan kepada suhu pengkalsinan yang berbeza dan didapati 650, 700, dan 750  $^{\circ}\text{C}$  adalah suhu pengkalsinan utama berdasarkan pembelaan corak sinar-X (XRD) dan penghantaran imej mikroskop elektron (TEM). Untuk mengkaji kesan ejen penetapan polimer PVP bagi mengawal selia penumpuan nanopartikel, berkepekatan 0.009, 0.018, 0.027 mol PVP digunakan. Saiz zarah sempit dan saiz agihan telah dicapai pada 0.027 mol PVP untuk nanopartikel LTB dan LTB-Cu dan pada 0.018 mol PVP untuk nanopartikel LTB-Ag. Saiz purata zarah ditentukan dari taburan saiz TEM adalah 3.34, 4.61, dan 4.56 nm untuk nanopartikel LTB, LTB-Cu dan LTB-Ag, masing-masing pada suhu pengkalsinan 750  $^{\circ}\text{C}$ . Spektroskopi UV-tampak (UV-Vis) telah digunakan untuk menentukan pemberian nilai jurang optik nanopartikel yang disintesis. Untuk menyiasat kandungan TL daripada nanopartikel disintesis, pergantungan dos, keupayaan penyimpanan tenaga, dan tenaga nanophosphors dikaji dari lengkung cahaya tindak balas dos di pelbagai julat dos 0.005, 0.01, 0.1, 0.5, 1, 10, 100, dan 150 Gy. Kini dosimeter LTB berskala nano terdop dan tidak terdop LTB mempunyai ciri-ciri fizikal yang baik dan tindak balas TL boleh dihasilkan dengan mudah oleh rawatan terma pada kos yang berpatutan dan tanpa dipengaruhi oleh produk dihasilkan.

## ACKNOWLEDGEMENTS

*In the name of Allah the merciful Beneficent*

I wish to express my sincere appreciation to Prof. Elias Saion who has taught me so much about nanoscience, with whom I began teaching nanotechnology. His knowledge, graciousness, and wisdom will be forever memorable to me.

Moreover, I wish to thank my committee members with gratitude; Prof. Abdul Halim B Shaari, Prof. Mansor B Hashim, Prof. Mansor B HJ Ahmad, and Dr. Noriah Mod Ali for their suggestions, consideration and support through my graduate career. I acknowledge with gratitude Prof. Karen whose grate consideration grew my chemistry knowledge and spirituality as well. I acknowledge Prof. Azmi, Prof. Halimah, and Prof. Jumiah for their kindness and graceful help. I greatly appreciate and wish to thank Mr. Mohd Zain Yusof for his immense help and the Faculty of Science, Physics department lecturers and staff, Institute Bioscience, Faculty of Engineering, and Institute of Advance Technology (ITMA), of University Putra Malaysia, who had contributed to this research. Special thanks to librarians who generally patiently gave me a hand, particularly Jefri who was always there to help, SGS staff who informed and guided me through formal procedures. I acknowledge with gratitude the staff of the Agency Nuclear Malaysia and University Kebangsaan Malaysia who made my work possible.

Besides, a special thank to my lovely friends, Saghi and Afsane who encouraged me to come to UPM, Dr. Mirzaee and Dr. Karimian who believed in me and supported me, Mr. Ghafoori and Dr. Zamani who trust me and made my educational mission possible, Maryam and her sister, Mehrnaz who helped me compassionately. Finally, great thanks to my lovely friends, Saeed and Neda who were accessible all the time days or nights to help me thousands kilometers away, wish you all the best in your life.

Nasrin Khalilzadeh

August 2014

I certify that a Thesis Examination Committee has met on 11 August 2014 to conduct the final examination of Nasrin Khalilzadeh on her thesis entitled "Synthesis and Evaluation of undoped and Silver and Copper Doped Lithium Tetraborate Nanoparticles as Thermoluminescent Dosimeter" in accordance with the Universities and University Collages Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U. (A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

**Azmi bin Zakaria, PhD**

Professor

Faculty of Science

Universiti Putra Malaysia

(Chairman)

**Wan Mahmood bin Mat Yunus, PhD**

Professor

Faculty of Science

Universiti Putra Malaysia

(Internal Examiner)

**Azhar Abdul Rahman, PhD**

Senior Lecturer

Universiti Sains Malaysia

Malaysia

(External Examiner)

**Mohammad Ahmad Ali Omar, PhD**

Senior Lecturer

Qassim University

Saudi Arabia

(External Examiner)



---

**NORITAH OMAR, PhD**

Associate Professor and Deputy Dean

School of Graduate Studies

Universiti Putra Malaysia

Date: 19 September 2014

This thesis submitted to the Universiti Putra Malaysia and has been accepted as fulfillment of the requirements for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

**Elias B Saion, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Chairman)

**Abdul Halim B Shaari, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Mansor B Hashim, PhD**

Professor  
Institute of Advanced Technology  
Universiti Putra Malaysia  
(Member)

**Mansor B HJ Ahmad Ayob, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Noriah Mod Ali, PhD**

Senior Lecturer  
Agency Nuclear Malaysia  
(External member)



---

**BUJANG BIN KIM HUAT, PhD**

Professor and Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 9 Oct, 2014

## Declaration by graduate student

I hereby confirm that:

- this thesis is my original work
- quotations, illustrations and citations have been duly referenced
- The thesis has not been submitted previously or concurrently for any other degree at any institutions
- intellectual property from the thesis any copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be owned from supervisor and deputy vice-chancellor (Research and innovation) before thesis is published (in form of written, printed or in electronic form) including books, journals, modules , proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: \_\_\_\_\_

Date: \_\_\_\_\_

Name and Matric No: Nasrin Khalilzadeh (GS26722)

## Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: \_\_\_\_\_  
Name of  
Chairman of  
Supervisory  
Committee: Prof.Dr.Elias

Signature: \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee: Prof.Dr.Halim

Signature: \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee: Prof. Dr. Mansor B Hashim

Signature: \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee: Prof.Dr.Mansor  
Hj.Ahmad

Signature: \_\_\_\_\_  
Name of  
Member (External) of  
Supervisory  
Committee: Dr. Noriah

## CHAPTER 1

### INTRODUCTION

#### 1.1 Nanostructured materials

Ultrafine structures having an average phase or grain size the order of  $10^{-9}$  m are classified as nanostructured materials ( NSMs ) (Gleiter, 1992). Currently, in a wider meaning of the term, any material that contains grains or clusters below 100 nm, or layers or filaments of that dimension, can be considered as “nanostructured” (Seigel, 1993a). The interest in these materials has been stimulated by the fact that, owing to the small size of the building blocks (particle, grain, or phase) and the high surface-to-volume ratio, these materials are expected to demonstrate unique mechanical, optical, electronic, and magnetic properties (Seigel, 1993b). The properties of NSMs depend on the following four common microstructural features; (1) fine grain size and size distribution(< 100 nm), (2) the chemical composition of the constituent phases, (3) the presence of interfaces, more specifically, grain boundaries, heterophase interfaces, or the free surface, and (4) interactions between the constituent domains. The presence and interplay of these four features together with their combined electronic structure largely determine the unique properties of NSMs. In nanophase materials, a variety of size-related effects can be incorporated by controlling the sizes of the constituent components (Chan, 1990). For example, nanostructured metals and ceramics show improved mechanical properties compared to conventional materials as a result of their ultrafine microstructure. In addition, NSMs have the capability to be sintered at much lower temperatures than conventional powders, enabling the full densification of these materials at relatively lower temperatures. Semiconductor NSMs are currently also considered to have technological applications in optoelectronic devices such as semiconductor quantum dots and photodiodes, owing to the phenomenon of “quantum size effects” caused by the spatial confinement of delocalized electrons in confined grain sizes (Wang, 1991). Magnetic applications of NSMs include fabrication of devices with giant magnetoresistance (GMR) effects, the property used by magnetic heads to read data on computer hard drives, as well as the development of magnetic refrigerators with solid magnets as refrigerants rather than compressed ozone-destroying chlorofluorocarbons (Yoshizawa, 1988). In addition, nanostructured metals and alloy seem to be candidates for new catalytic applications (Beck, 1992).



The development of semiconductor nanoclusters is an area of intense research efforts. These nanoclusters are often referred to as quantum dots and nanocrystals (Steigerwald, 1990). In the nanometer size regime, electron-hole confinement in nanosized spherical semiconductor particles results in three-dimensional size quantization. Bandgap engineering by size and dimension quantization is important as it leads to electrical, optical, magnetic, optoelectronics, and magnetooptical properties substantially different from those observed for the bulk material (Henglein, 1988). As an example, quantum dots can be developed to emit and absorb a desired wavelength of light by changing the particle diameters. This feature allows the construction of a finely tunable and efficient semiconductor laser (Gonsalves, 2000).

## 1.2 Lithium borate Crystals

The lithium borate crystals  $\text{LiB}_3\text{O}_5$  (LBO),  $\text{Li}_2\text{B}_4\text{O}_7$  (LTB),  $\text{Li}_6\text{Gd}(\text{BO}_3)_3$  (LGBO) are typical representatives of an extensive class of wide band-gap dielectrics with mobile cations. Recently these optical materials have been intensively investigated from both the point of view of their fundamental properties, and with respect of their practical application in fields of radiation detectors (Furetta, 2010), dosimetry (Ignatovych, *et al.*, 2004), transformers and optical wave-guides operating in a broad spectral range from the visible region to the vacuum ultraviolet region (Ogorodnikov, *et al.*, 2012). All the crystals are highly transparent down to the cutoff wavelength near 160 nm and their band gaps are estimated to be 8.8–9 eV (Ogorodnikov, 2010). The lithium borate crystals have recently become promising candidates for the realization of neutron imaging using scintillation methods (AM, 2004). Despite variations in chemical composition, these materials have many similar properties. In particular, they have a reduced symmetry of the crystal lattice and a complex elementary cell. The crystal structure of each material consists of the appropriate boron-oxygen anionic groups and lithium cations. The lithium cations occupy the voids in the continuous boron-oxygen network. A distinctive feature of these materials is the sharp contrast between the strong covalent chemical bonds inside the anionic groups and the comparatively weak ionic bonds between the lithium cations and appropriate anionic groups (Islam, 2011; Wooten, *et al.*, 2010).

Lithium tetraborate is one of the selected materials for personal thermoluminescence dosimetry as its effective atomic number ( $Z_{\text{eff}}=7.4$ ) closely matches the  $Z_{\text{eff}}$  of human tissue (7.42) (Furetta, *et al.*, 2001). The borates are brilliant compounds as a TLD due to their close tissue-equivalent properties. Furthermore, they have an almost stable chemical composition and can be doped with TL sensitizers such as rare earth elements, copper or manganese



ions without significant problems. The resultant materials show some desirable features for TL in terms of high sensitivity (El-Faramawya, *et al.*, 2000). However, the conventional macro-scale LTB has several drawbacks such as poor TL intensity, limited dose linearity, loss information (fading) and energy dependence. Takenega *et al.* (1980) replaced Mn with Cu to improve the sensitivity of LTB. They found that TL emission spectra at 365 nm for LTB: Cu, In pellets and LTB: Cu, In, Ag pellets improved the linearity of dosimeter however, those TLs are sensitive to light with a high amount of fading (Prokic, 2001). Thereafter, doping of LTB crystals have received attention as a promising method to produce neutron scintillator with large cross sections for neutron capturing by lithium and boron isotopes (Huy, 2009) in surface acoustic wave devices for intermediate frequency (IF) filters (Senguttuvan, *et al.*, 2002), (Lewis, *et al.*, 1982). Furthermore, the dose range of traditional phosphors does not exceed normally 100 Gy, while higher doses are needed in technological and medical applications. In this connection, nanosized phosphors captured the interest of some researchers because of their better radiation resistance (Banhart, 1999; Uzsaki *et al.*, 2007). Over the past few years nanophosphors have been studied actively, leading to some promising results (Chopra, *et al.*, 2013). Therefore, the LTB based TL materials still attract extensive attentions, due to their attractive properties.

### 1.3 Problem Statement

One of the most important missions in TL dosimetry investigation is invention of new detector materials for radiation monitoring. LTB has been a popular and significant starting material in this regard for a long time (Schulman, *et al.*, 1965).

The TLD material needs to be tissue equivalent and highly sensitive. Moreover, the sizes of TLD materials are required to be as small as possible for lab measurements. Besides, the TLD should not be toxic. Therefore, because of the importance of the tissue equivalent factor, the International Commission on Radiological Protection (ICRP) has published recommended diagnostic reference levels for medical imaging modalities (ICRP, 1996).

Luminescence detectors of ionizing radiation are now comprehensively used in individual dosimetry services due to their excellent dosimetric properties. The most frequently used personal dosimeters are based on optically stimulated luminescence (OSL), radio photoluminescence (RPL) or thermoluminescence (TL). Luminescence detectors have also been applied in clinical dosimetry, especially around new radiation modalities in radiotherapy, such as Intensity Modulated Radiotherapy (IMRT) or ion beam radiotherapy (Olko, 2010).

Although, un-doped LTB crystals show TL emission and its energy dependence is low its sensitivity is much lower than the common detector materials. The idea of adding an activator material came. Thus, a lot of other efforts were made for finding dopants and possible co- doping of LTBs for better TL properties (Patra, *et al.*, 2012; Tiwari, *et al.*, 2010). It is shown by some researchers that some transition metals such as Cu, Ag, Ni, and Co reduced the known drawbacks of LTBs (Ignatovych, *et al.*, 2004; Prokić, 2000). Furthermore, In and Ce was applied as activators to enhance key factors of TL dosimeters (Senguttuvan, 2002). Due to very early in the 1960s Schulman et al. synthesized LTB: Mn for dosimetric purposes. The doped LTB with Mn shows a bit higher sensitivity, but the emission of the material is in the red region that is not favorable for the light detecting systems of the commonly used TL readers (Schulman and Kirk, 1965). Superior results of Cu containing detectors, it becomes the preferred dopant element among other transition elements. This detector showed emission in near UV region (Takenaga, *et al.*, 1980). Comparing to LTB:Mn, the emission of LTB:Cu is more desirable and much better for using with normal TL readers (Azorin, 2013). On the other hand, powder form of LTB: Cu is not wanted for routine application in dosimetry. It should be emphasized that the color of almost all of the commercially prepared lithium borates doped by Cu change (to brownish) after repeated annealing steps (Furetta, *et al.*, 2001).

The mechanism of energy excitation resulting in light emission is the most important point in TL materials sketching. Both the threshold detection dose and validity of measurements depend on the sufficiency of energy transformation. The impact of diverse procedures of energy transfer and energy losses is very different arising from the nature of the TL substance and its composition including intrinsic defects and those induced by impurities. The amount and distribution of these defects can be controlled to a high extent by the synthesis technique. That is why the most significant fact is to find the interdependence of the preparation methods, the structural defects and the TL properties of the material. Although, there are lots of TL materials, the majority of them are not convenient to be employed for dosimetric purposes. The following characteristics are expected from a good material;

Almost a simple glow curve with the main peak at about 200 °C, high sensitivity and stability, persistence to environmental factors, independence of the radiation energy, and sufficient linearity in the specific appropriate range of dose.

Only a few materials have been synthesized so far which meet all the above requirements. However, investigation in this field is ongoing and more appropriate TL materials are to be synthesized in the near future.

## 1.4 Significance of the study

Most of the ionizing radiation that people are exposed in their day-to-day activities come from natural and man-made resources such as invisible radiation from the sky, the ground, the air, and even from food and drink. Such "ionizing" radiations have been utilized in different applications; doctors use X-rays to diagnose diseases or injuries; factories use radiation to check welds in machine components; gamma rays are used to sterilize medical equipments for safe use; and a variety of crops have been produced through radiation-induced mutations. Moreover, about 17 percent of the world's electricity is supplied by nuclear power plants.

Natural and artificial health effects of radiation are both well understood and can be effectively minimized through careful safety measures and practices. The International Atomic Energy Agency (IAEA), together with other international and expert organizations is helping to promote and institute Basic Safety Standards (BSS) on an international basis to ensure that radiation resources and radioactive materials are managed to work under maximum safety, human benefit, and environment protection (IAEA, 2011). Due to the extensive application of ionizing radiation, monitoring is the first and the best intervention to confine the hazards of radiation (IAEA, 1999). In order to secure the personal and the environment, massive investigations have been done to synthesize new materials for dosimetric purposes.

The present study reports for the first time, the properties of LTB, LTB-Cu, and LTB-Ag nano phosphors in pellet form, synthesized through an innovative single step thermal treatment method. The prepared pellets were then employed as a new material to improve linearity, energy storage ability, and energy dependence on microcrystalline material as dosimeters. In the present research, nanophosphors are synthesized from aqueous solutions of metal carbonate, Polyvinylpyrrolidone (PVP), copper (II) and silver nitrate as dopants, and Di-water as solvent at a low calcination temperature followed by grinding and sieving. The proposed method is a less expensive route compared to other methods resulting in a pure production without any toxic material which can be mass produced.

## 1.5 Objectives of the study

The present research is targeted to synthesize un-doped Lithium tetra borate and doped LTB nanophosphors with Cu and Ag by an innovative single step thermal treatment method. To reach to the determined goals, the objectives of the present study are:

1. To synthesize of LTB, LTB-Cu, and LTB-Ag (LTBs) nanophosphors using single step thermal treatment method.
2. To determine thermal stability, crystal structure, optical properties, size and size distribution of prepared nanoparticles.
3. To investigate the effect of PVP concentration on prepared nanophosphores.
4. To investigate the influence of calcination temperature on prepared nanophosphores.
5. To study some main dosimetric properties of achieved LTB, LTB-Cu, and LTB Ag nanophosphors.

## 1.6 Outline of the Thesis

The foremost aim of the present thesis was to develop a single step thermal treatment synthesis and investigate the physical properties of un-doped and doped LTB nanophosphors and their TLD performance as dosimeters for personal, environmental, and medical purposes.

In Chapter 1 detailed definitions and introductions into the context of the research, purposes, and objectives of the investigation are given. Chapter 2 describes the background of the Thermoluminescence and its role in ionizing radiation dosimetry, followed by a general introduction to LTB crystals and a detailed review of  $\text{Li}_2\text{B}_4\text{O}_7$  crystal, its dopant materials, and synthesis methods. As TLDs are prepared in nano regime, Chapter 2 also discusses the properties of the nanostructured materials. Chapter 3 depicts the theory of luminescence and thermoluminescence, energy bands and localized level in crystalline materials. Moreover, the transmission phenomenon is introduced in Chapter 3. The experimental methods and procedures including materials and chemicals

chosen to perform the research work are given in Chapter 4. The following chapter (Chapter 5) presents the details of the experimental results and analyses. And finally the conclusion is offered in Chapter 6.



## REFERENCES

- AM, W. 2004. Response of a lithium gadolinium borate scintillator in monoenergetic neutron fields. *Radiat Prot Dosimetry*, 110, 497-502.
- Arno Ratas, M.D., Mihkel Kerikmäe, Aime Lusta, Hugo Mändarb,, Viktor Seemanb, a.G.S. 2012. Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>:Mn for dosimetry applications: traps and mechanisms. *Proceedings of the Estonian Academy of Sciences*, 4, 279-295.
- Ashraf Chaudhry, M., Altaf, M. 1998. Optical absorption studies of sodium cadmium phosphate glasses. *Materials Letters*, 34, 213-216.
- ATRSpectroscopy (2014). Absorption / Transmission / Reflection Spectroscopy.
- Attix, F.H. 1986. *Introduction to Radiological Physics & Radiation Dosimetry*.
- Azorin, J. 1993. Preparation and properties of thermoluminescent materials. *Phys. Stat. Sol.*
- Azorin, J. 2013. Preparation methods of thermoluminescent materials for dosimetric applications: An overview. *Applied Radiation and Isotopes*.
- Bardeen, F.J.e.a. (1954). Paper presented at the Atlantic City Photoconductivity.
- Beck, D.D. 1992. The Dissociative Adsorption of Hydrogen Sulfide Over Nanophase Titanium Dioxide. *J.Matter.Res.*
- Binder, W., Cameron, J. 1969. *Health Physics*, 17.
- Bjarngard, B. (1967). Paper presented at the 1st Lumin. Dosim. Conf., Stanford.
- Cameron, J., Suntharalingam, N., Kenney, G. (1968). Thermoluminescent Dosimetry. University of Wisconsin Press.
- Chan, R.W. 1990. Chemistry for the 21st Century. *Nature*, 348.
- Chinang Weng, H. 2012. ZnO-coated carbon nanotubes: an enhanced and red-shifted emission band at UV-VIS wavelength. *Journal of Materials Chamistry*, 22, 13747-13750.
- Chopra, V., Singh, L., Lochab, S.P. 2013. Thermoluminescence characteristics of gamma irradiated Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>:Cu nanophosphor. *Nuclear Instruments*



*and Methods in Physics Research Section A: Accelerators, Spectrometers, Detectors and Associated Equipment*, 717, 63-68.

- Christensen, P., Bøtter-Jensen, L., Majborn, B. 1982. Thermoluminescence dosimetry applied to radiation protection. *The International Journal of Applied Radiation and Isotopes*, 33, 1035-1050.
- Daniel, D.J., Madhusoodanan, U., Nithya, R., Ramasamy, P. 2014. Irradiation effect on luminescence properties of fluoroperovskite single crystal (LiBaF<sub>3</sub>:Eu<sup>2+</sup>). *Radiation Physics and Chemistry*, 96, 135-139.
- Danilkin, M., Ratas, A. 2006. Thermoluminescent dosimeter Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>:Mn,Si – a false-dose problem. *Proc. Estonian Acad. Sci. Chem.*, 55.
- Dhanaraj, G. 2010. *Springer handbook of Crystal Growth*.
- Dodson, B.W. 1989. Nanostructured materials -mind over matter. *Mater.Res.Soc.Symp.Proc.*, 160.
- Doull, B., Oliveira, L.C., Yukihiro, E.G. 2013. Effect of Annealing and Fuel Type on the Thermoluminescent Properties of Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> Synthesized by Solution Combustion Synthesis. *Radiation Measurements*.
- Dutrow, B.L., Clark, C.M. (2013). X-ray Powder Diffraction
- El-Faramawya, N.A., El-Kameesy, S.U., Abd-El-Aziz, A.S. 2000. Study of Thermal Treatment and Kinetic Parameters of Prepared Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>: Cu Thermoluminescence Dosimeter *Egypt. J. Sol.*, 23, 103-111.
- Furetta, C. 2003. *Handbook of Thermoluminescence*: World Scientific.
- Furetta, C. 2008. Questions and answers on Thermoluminescence and Optically stimulated.
- Furetta, C., Prokic, M., Salamon, R., Prokic, V., Kitis, G. 2001. Dosimetric characteristics of tissue equivalent thermoluminescent solid TL detectors based on lithium borate. *Nuclear Instruments and Methods in Physics Research Section A: Accelerators, Spectrometers, Detectors and Associated Equipment*, 456, 411-417.
- Furetta, C., Weng, P.-S. 1998. *Operational Thermoluminescence Dosimetry*: World Scientific.
- Furetta, C. 2010. *Handbook of Thermoluminescence*.
- Garlick, G.F.J. 1949. *Luminescence materials*.

Ge, W., Zhang, H., Lin, Y., Hao, X., Xu, X., Wang, J., Li, H., Xu, H., Jiang, M. 2007. Preparation of  $\text{Li}_2\text{B}_4\text{O}_7$  thin films by chemical solution decomposition method. *Materials Letters*, 61, 736-740.

Gharagozlou, M. 2009. Synthesis, characterization and influence of calcination temperature on magnetic properties of nanocrystalline spinel Co-ferrite prepared by polymeric precursor method. *Journal of Alloys and Compounds*, 486, 660-665.

Ginter, R.J., Kirk, R.D. 1957. *Electrochem. Soc.*, 104.

Gleiter, H. 1992. Encyclopedia of materials Science and Engineering *Adv. Mater.*, 4.

Goldman, L.M. 1989. Nanostructured materials -mind over matter. *J.Appl.Phys.*, 60.

Gonsalves, K.E., Rangarajan, S.P., Wang, J. (2002). Chemical synthesis of nanostructured metals, metal alloys, and semiconductors. In N. Hari Singh (Ed.), *Nanostructured Materials and Nanotechnology* (pp. 1-56). San Diego: Academic Press.

Gorelik, V.S.e.a. 2003. Raman and Hyper-Rayleigh Scattering in Lithium tetraborate Crystals. *Journal of Russian Laser Research*, 24.

Gouveia, D.S., Soledade, L.E.B., Paskocimas, C.A., Longo, E., Souza, A.G., Santos, I.M.G. 2006. Color and structural analysis of  $\text{Co}_x\text{Zn}_{7-x}\text{Sb}_2\text{O}_{12}$  pigments. *Materials Research Bulletin*, 41, 2049-2056.

Hashizume, T. (1971). *Radiation Detectors*. Paper presented at the IAEA.

Henglein, A. 1988. Mechanism of reactions on colloidal microelectrodes and size quantization effects. *Top Curr.Chem*, 143.

Huy, T.B. 2009. Growth and luminescent properties of  $\text{Li}_2\text{B}_4\text{O}_7$  single crystal doped with Cu. *Journal of Physics: Conference Series* 187.

IAEA (1999). *Radiation Safety Manual*.

IAEA (2011). Radiation Protection and Safety of Radiation sources. International Basic Safety Standards.

ICDD-FDF-01-076-1115 ICDD-FDF-01-076-1115.

ICDD-PDF-008-0717 ICDD-PDF 18-717.



- ICRP ( 1996). Radiological protection and safety in medicine. , 73 (pp. 1-47).
- Ignatovych, M., Fasoli, M., Kelemen, A. 2012. Thermoluminescence study of Cu, Ag and Mn doped lithium tetraborate single crystals and glasses. *Radiation Physics and Chemistry*, 81, 1528-1532.
- Ignatovych, M., Holovey, V., Watterich, A., Vidóczy, T., Baranyai, P., Kelemen, A., Chuiko, O. 2004. Luminescence characteristics of Cu- and Eu-doped Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>. *Radiation Measurements*, 38, 567-570.
- Ignatovych, M., Holovey, V., Watterich, A., Vidóczy, T., Baranyai, P., Kelemen, A., Chuiko, O. 2004. Luminescence characteristics of Cu- and Eu-doped Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>. *Radiation Measurements*, 38, 567-570.
- Islam, M.M.e.a. 2011. The ionic conductivity in lithium-boron oxide materials and its relation to structural, electronic and defect properties: insights from theory. *Journal of Physics: Condensed Matter*.
- Kakihana, M., Okubo, T., Arima, M., Nakamura, Y., Yashima, M., Yoshimura, M. 1998. Polymerized complex route to the synthesis of pure SrTiO<sub>3</sub> at reduced temperatures: Implication for formation of Sr-Ti heterometallic citric acid complex. *Journal of Sol-Gel Science and Technology*, 12, 95-109.
- Kakihana, M., Yoshimura, M. 1999. Synthesis and characteristics of complex multicomponent oxides prepared by polymer complex method. *Bulletin of the Chemical Society of Japan*, 72, 1427-1443.
- Kelemen, A., Mesterházy, D., Ignatovych, M., Holovey, V. 2012. Thermoluminescence characterization of newly developed Cu-doped lithium tetraborate materials. *Radiation Physics and Chemistry*, 81, 1533-1535.
- Kitis, G., Chen, R., Pagonis, V. 2008. Thermoluminescence glow-peak shape methods based on mixed order kinetics. *Applications and materials science* 1181-1189.
- Koch, C.C. 1997. Synthesis of nanostructured materials by mechanical milling: problems and opportunities. *Nanostruct.Mater.*, 2.
- Koebel, M.M., Jones, L.C., Somorjai, G.A. 2008. Preparation of size-tunable, highly monodisperse PVP-protected Pt-nanoparticles by seed-mediated growth. *Journal of Nanoparticle Research*, 10, 1063-1069.

- Komatsu, R.e.a. 1997. Growth and ultraviolet application of Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> crystals: Generation of the fourth and fifth harmonics of Nd:Y<sub>3</sub>Al<sub>5</sub>O<sub>12</sub> lasers. *Appl. Phy.Lett.*, 70.
- Lewis, B., Shorrocks, N.M., Whatmore, R.W. (1982, 27-29 Oct. 1982). *An Assessment of Lithium Tetraborate for SAW Applications*. Paper presented at the 1982 Ultrasonics Symposium.
- Liu, Z.K., Wang, H., Li, H. 1998. Red shift of plasmon resonance frequency due to the interacting Ag nanoparticles embedded in single crystal SiO<sub>2</sub> by implantation. *Applied Physics Letters*, 72.
- Liveri, V.T. 2006. Controlled Synthesis of Nanoparticles in Microheterogeneous Systems. *Canada: Springer*.
- Mahesh, K.W., P S . Furetta, C. 1989. Thermoluminescence in solids and its applications.
- Maria, A.F. 2010. Response of TL materials to diagnostic radiology X radiation beams. *Applied Radiation and Isotopes*, 68.
- McKeever 2001. Optically stimulated Luminescence dosimetry. *Nuclear Instruments and Methods in Physics Research*, B 184, 29-54.
- McKeever, S.W.S. 1985. Thermoluminescence of Solids: Cambridge University Press.
- McKeever, S.W.S. 1988. Thermoluminescence of solid.
- Mills, B. (2013). Chemistry related images.
- Mott, N.F., Davis, E.A. 2012. Electronic processes in Non-Crystalline Materials.
- Murugan, G.S., Varma, K.B.R. 1999. Structural, dielectric and optical properties of lithium borate-bismuth tungstate glass-ceramics. *Materials Research Bulletin*, 34, 2201-2213.
- Nagirnyi, V., Aleksanyan, E., Corradi, G., Danilkin, M., Feldbach, E., Kerikmäe, M., Kotlov, A., Lust, A., Polgár, K., et al. 2013. Recombination luminescence in Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> doped with manganese and copper. *Radiation Measurements*, 56, 192-195.

- Nakajima, T., Murayama, Y., Matsuzawa, T., Koyano, A. 1978. Development of a new highly sensitive LiF thermoluminescence dosimeter and its applications. *Nuclear Instruments and Methods*, 157, 155-162.
- Nanoparticles by a Novel Method *International Journal of Scientific & Engineering Research*, 4, 155-158.
- Naseri, M., G. 2010. Simple Synthesis and Characterization of Cobalt Ferrite Nanoparticles by a Thermal Treatment Method. *Journal of Nanomaterials*.
- NDTResource. (2014). Ceramic Structures
- NobleprizeWebSite (2014). The Transmission Electron Microscope
- Oberhofer, M., Scharmann, A. 1981. *Applied Thermoluminescence Dosimetry*
- Oberhofer, M., Scharmann, A. 1992. *Techniques and Managements of Personnel Thermoluminescence Dosimetry* sevisec: Kluwer Academic Publishers.
- Ogorodnikov, I.N. (2010). *Radiation effects and defects in lithium borate crystals*. Paper presented at the 11th Europhysical Conference on Defects in Insulating Materials.
- Ogorodnikov, I.N., Poryvai, N.E. 2012. Thermoluminescence kinetics of lithium borate crystals. *Journal of Luminescence*, 132, 1318-1324.
- Olko, P. 2010. Advantages and disadvantages of luminescence dosimetry. *Radiation Measurements*, 45, 506–511.
- Pankove, J. 1971. *Optical processes in Semiconductors*.
- Park, S. (2005). Synthesis of ZnO nanopowder by Solution Combustion Method and its Photocatalytic characteristics. In B. M. Caruta (Ed.), *Nanomaterial new research*.
- Patra, G.D., Tyagi, M., Desai, D.G., Tiwari, B., Sen, S., Gadkari, S.C. 2012. Photo-luminescence properties of Cu and Ag doped Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> single crystals at low temperatures. *Journal of Luminescence*, 132, 1101-1105.
- Pechini, M.P. (1967). USA Patent No. United States Patent Office: S. E. Company.
- Povarennykh, A.S. 1978. The use of infrareds spectra for the determination of minerals. *American Mineralogist*, 63, 956-959.

- Prelipceanu, M.e.a. (2004). *Thermally Stimulated Luminescence and current in new heterocyclic materials for organic field transistors and organic light emitting diodes*. Paper presented at the ICPAM07, Romania.
- Prokić, M. 2000. Effect of lithium co-dopant on the thermoluminescence response of some phosphors. *Applied Radiation and Isotopes*, 52, 97-103.
- Prokic, M. 2001. Lithium borate solid TL detectors. *Radiation Measurements*, 33, 393-396.
- Prokic, M. 1980. Development of highly sensitive  $\text{CaSO}_4 : \text{Dy/Tm}$  and  $\text{MgB}_4\text{O}_7 : \text{Dy/Tm}$  sintered thermoluminescent dosimeters. *Nuclear Instruments and Methods*, 175, 83-86.
- Portal (1971). France Patent No.
- Putnis, A. 1992. Introduction to mineral science.
- Ramadevudu, G.e.a. 2012. FTIR and Optical Absorption Studies of new Magnesium Lead Borate Glasses. *Global Journal of Science Frontier Research Physics and Space Science* 12.
- Ramesh, T.e.a. (2012). Characterization of High Molecular Weight Poly(vinyl chloride) – Lithium Tetraborate Electrolyte Plasticized by Propylene Carbonate *Recent Advances in Plasticizers*.
- Reuven, C., McKeever, S.W.S. 1997. *Theory of Thermoluminescence and Related Phenomena*.
- Rieke, J.R., Daniels, F. 1957. *J.Phys.Chem.*, 61.
- Roosen, A.R., Carter, W.C. 1998. Simulations of microstructural evolution: anisotropic growth and coarsening. *Physica A: Statistical Mechanics and its Applications*, 261, 232-247.
- Rotman, S.R. 1997. *Wide-Gap Luminescent Materials: Theory and Application*. USA: Kluwer
- Schayes, R. (1967). Paper presented at the 1st Int. Conf. Lumin.Dosim., Stanford.
- Schulman, R.D., Kirk, E.J. (1965). Paper presented at the *Luminescence Dosimetry*, USA.
- Scott, P.W.R. (2014). *The Fourier Transform IR Spectrometer*

- Seigel, R.W. 1990. Nanophase materials assembled from atomic cluster. *MRS Bull.*, 60.
- Seigel, R.W. 1993a. Nanostructured materials -mind over matter. *Nanostructure. mater*, 3.
- Seigel, R.W. 1993b. Synthesis and properties of nanophase materials. *Mater.Sci.Eng.*, B19.
- Senguttuvan, N. 2002. Crystal growth and luminescence properties of Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> single crystals doped with Ce, In, Ni, Cu and Ti ions. *Nuclear Instruments and Methods in Physics Research A* 486, 264–267.
- Senguttuvan, N., Ishii, M., Shimoyama, M., Kobayashi, M., Tsutsui, N., Nikl, M., Dusek, M., Shimizu, H.M., Oku, T., et al. 2002. Crystal growth and luminescence properties of Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> single crystals doped with Ce, In, Ni, Cu and Ti ions. *Nuclear Instruments and Methods in Physics Research Section A: Accelerators, Spectrometers, Detectors and Associated Equipment*, 486, 264-267.
- Simonescu, C.M. (2012). Application of FTIR Spectroscopy in Environmental Studies *Advanced Aspects of Spectroscopy*.
- Singh, L., Chopra, V., Lochab, S.P. 2011. Synthesis and characterization of thermoluminescent Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> nanophosphor. *Journal of Luminescence*, 131, 1177-1183.
- Singh, R.J. 2012. Solid State Physics.
- Soares, C.G. 2002. National and International Standards and Calibration of Thermoluminescence Dosimetry system. *Radiation Protection Dosimetry*, 101, 167-171.
- Soares, C.G. 2002. National and International Standards and Calibration of Thermoluminescence Dosimetry system. *Radiation Protection Dosimetry*, 101, 167-171. SSDL (2013).
- SSDL (2013).
- Steigerwald, M.L. 1990. Semiconductor crystallites: a class of large molecules. *Acc.Chem.Res.*
- Takenaga, M., Yamamoto, O., Yamashita, T. 1980. Preparation and characteristics of Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> : Cu phosphor. *Nuclear Instruments and Methods*, 175, 77-78.

ThermoNicolet (2001). Introduction to Fourier transform Infrared spectrometry

Tiwari, B., Rawat, N.S., Desai, D.G., Singh, S.G., Tyagi, M., Ratna, P., Gadkari, S.C., Kulkarni, M.S. 2010. Thermoluminescence studies on Cu-doped Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> single crystals. *Journal of Luminescence*, 130, 2076-2083.

Tochilin, E., Goldstein, N., Miller, W.G. 1969. *Health Physics*, 16.

Universe-review (2014). Microscopes Spectroscopy

Urbach, F. 1953. The Long-Wavelength Edge of Photographic Sensitivity and of the Electronic Absorption of Solids. *Phys. Rev.*, 92, 1324-1324

Wang 1966. *Solid State Electronics*: McGraw-Hill.

Wang, Y. 1991. Fullerenes with metals inside. *J. Phys.Chem.*

Wascerman, G. (1976). Paper presented at the 4th International conf.on Strenght of Metals and alloys.

Wooten, D., Ketsman, I. 2010a. The electronic structure of Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>(110) and Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub>(100). *The European Physical journal , Applied Physics Letter*, 52.

Wooten, D., Ketsman, I., Xiao, J., Losovyj, Y.B., Petrosky, J., McClory, J., Burak, Y.V., Adamiv, V.T., Dowben, P.A. 2010b. The surface core level shift for lithium at the surface of lithium borate. *Physica B: Condensed Matter*, 405, 461-464.

Yamashita, T., Takenaga, M. 1980. Preparation and characteristics of Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> : Cu phosphor *Nuclear Instruments and Methods* 175, 77-78.

Yong , N.L., Ahmad, A., Mohammad, A.V. 2013. Synthesis and Characterization of Silver Oxide

Yoshizawa, Y. 1988. Effect of Additional Cu Element on Structure and Crystallization Behavior of Amorphous Fe-Nb-Si-B Alloys. *J.Appl,Phys.*, 64.