



**UNIVERSITI PUTRA MALAYSIA**

**CHARACTERIZATION OF ALUMINUM-SUBSTITUTED YTTRIUM-  
IRON GARNET NANOPARTICLES PREPARED USING  
THE SOL-GEL TECHNIQUE**

**RAMADAN MASOUD AL-HABASHI**

**ITMA 2006 7**



**CHARACTERIZATION  
OF ALUMINUM-SUBSTITUTED YTTRIUM-IRON  
GARNET NANOPARTICLES PREPARED USING  
THE SOL-GEL TECHNIQUE**

**RAMADAN MASOUD AL-HABASHI**

**MASTER OF SCIENCE  
UNIVERSITI PUTRA MALAYSIA**

**2006**



**CHARACTERIZATION OF ALUMINUM-SUBSTITUTED YTTRIUM-IRON  
GARNET NANOPARTICLES PREPARED USING  
THE SOL-GEL TECHNIQUE**

**By**

**RAMADAN MASOUD AL-HABASHI**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,  
in Fulfilment of the Requirement for the Degree of Master of Science**

**December 2006**



DEDICATION

*To whom their true love and support*

*are behind my success*

*My*

*My*

*My*

*My*

*Son Daughters Wife Parents*

*UPM  
2006*



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the Degree of Master of Science

**CHARACTERIZATION OF ALUMINUM-SUBSTITUTED YTTRIUM-IRON  
GARNET NANOPARTICLES PREPARED USING THE SOL-GEL  
TECHNIQUE**

By

**RAMADAN MASOUD AL-HABASHI**

**December 2006**

**Chairman: Associate Professor Noorhana Binti Yahya, PhD**

**Institute: Advanced Technology**

This project presents preparation and characterization of aluminum substituted yttrium iron garnet (Al-YIG) nanocrystalline powders of compositional variation of  $Y_{3.0-x}Al_xFe_5O_{12}$ , where x was 0, 0.5, 1, 1.5, 2, 2.5 and 3. The samples were synthesized using sol-gel technique. The starting raw materials used to prepare Al-YIG samples were aluminum nitrate ( $Al(NO_3)_3 \cdot 9H_2O$ ), yttrium nitrate ( $Y(NO_3)_3 \cdot 6H_2O$ ) and iron nitrate ( $Fe(NO_3)_3 \cdot 9H_2O$ ). They were weighed according to the formula above, then mixed and dissolved together in solution of citric acid ( $C_6H_8O_7 \cdot H_2O$ ) for a month to form the gel form by using magnetic stirrer equipment at 350 r.p.m at room temperature. The sample was then dried at 110°C in an oven for a day to remove the unneeded water before it was calcined and crushed to obtain fine particles powder. The calcined powder at 600°C, 700°C, 800°C, 850°C and 900°C respectively, were characterized by x-ray diffraction analyzer (XRD) to confirm the garnet phase. All samples were characterized also by RF-Impedance (1 MHz-1.8 GHz) to investigate the magnetic properties. Finally, field emission scanning electron microscopy (FESEM) and energy



dispersive x-ray analyzer (EDX) were used to study the surface morphology and the elemental analysis of Al-YIG samples. The results showed that, the best garnet phase appeared when the sintering temperature was 800°C and Al-YIG nanocrystalline samples with high purity and sizes ranging from 20 to 100 nm were obtained. The magnetic measurement results of Al-YIG samples prepared by sol-gel method, gave high values of real permeability, the highest value of 5.29 was given by  $Y_3Fe_5O_{12}$  sample at about 80 MHz which was attributed to the large grain size, the highest magnetic permeability observed was due to easy movement of domain walls; and it shifted to the high frequency with increasing the amount of aluminum. The widest useful working frequency range appeared for  $Y_3Fe_5O_{12}$  sample and, also shifted to reach high range with increasing the concentration of aluminum.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains

**PENCIRIAN YTTRIUM-IRON GARNET BERPARTIKAL NANO DIGANTI  
DENGAN ALUMINIUM DISEDIAKAN MELALUI TEKNIK SOL-GEL**

Oleh

**RAMADAN MASOUD AL-HABASHI**

**Disember 2006**

**Pengerusi: Profesor Madya Noorhana Binti Yahya, PhD**

**Institut: Teknologi Maju**

Projek ini menjalankan penyediaan dan pencirian yttrium iron garnet (Al-YIG). Berpartikal nano diganti dengan aluminium yang divariasikan komposisinya dengan  $Y_{3.0-x}Al_xFe_5O_{12}$ , dimana x adalah 0, 0.5, 1, 1.5, 2, 2.5 dan 3. Sampel-sampel tersebut di sintasiskan menggunakan teknik sol-gel. Bahan mentah yang digunakan untuk menyediakan sampel Al-YIG adalah aluminium nitrat ( $Al(NO_3)_3.9H_2O$ ), yttrium nitrat ( $Y(NO_3)_3.6H_2O$ ) dan ferrum nitrat ( $Fe(NO_3)_3.9H_2O$ ). Bahan-bahan mentah ini ditimbang dan kemudian dicampur dan dilarutkan di dalam larutan sitrik asid ( $C_6H_8O_7.H_2O$ ) selama sebulan bagi membentuk gel dengan menggunakan alat pengacau bermagnet dengan putaran 350 r.p.m. pada suhu bilik. Sampel kemudiannya dikeringkan di dalam oven pada suhu  $110^\circ C$  selama sehari bagi membuang air yang tidak diperlukan sebelum ianya dibakar dan dihancurkan untuk mendapatkan partikal nano. Serbuk tersebut dibakar pada suhu  $600^\circ C$ ,  $700^\circ C$ ,  $800^\circ C$ ,  $850^\circ C$  dan  $900^\circ C$  dan, kemudian dicirikan dengan analisa pembelauan sinar-x (XRD) bagi mengesahkan fasa garnet. Kesemua sampel juga dicirikan dengan RF-Impedance (1 MHz – 1.8 MHz) bagi mengkaji sifat magnetnya, akhirnya field emission scanning electron microscopy (FESEM) dan energy dispersive x-ray

analyzer (EDX) digunakan bagi mengkaji morfologi permukaan dan analisa elemen bagi sample Al-YIG. Hasil pencirian menunjukkan bahawa fasa garnet terbaik pada suhu pensinteran 800°C dan sampel kristal-nano Al-YIG dengan ketulenan tinggi dan saiz dari 20 hingga 100 nm didapati. Hasil pengukuran sifat magnet bagi sampel Al-YIG yang disediakan dengan kaedah sol-gel, memberikan nilai ketelapan yang tinggi dengan nilai tertinggi adalah 5.29 bagi sampel  $Y_3Fe_5O_{12}$  pada frekuensi 80 MHz. Ini kerana saiz bijian yang besar, mengakibatkan senangnya pergerakan dinding domain dan menyebabkan. Ketelapan meningkat frekuensi fungsian manual bagi sampel  $Y_3Fe_5O_{12}$  juga bertukar bagi mencapai kadar tinggi dengan penambahan kepekatan aluminium.



## ACKNOWLEDGEMENTS

First of all, great thanks to the Most Gracious and Most Merciful ALLAH (S.W.T) without his wish and help this work would not have been possible. I also would like to express the most sincere appreciation to those who made this work possible: Advisory members, Friends and Family.

I would like to thank Asso. Prof. Dr. Noorhana Binti Yahya for providing me with the opportunity to complete my M.Sc. studies under her valuable guidance, for the many useful advice and discussions, for her constant encouragement and guidance, and for co-authoring and reviewing my publications, where her practical experience and technical knowledge made this research and those publications more interesting and relevant. Also special thanks extend to the supervisory committee members; Prof. Dr. Kaida Bin Khalid and Dr. Nor Azowa Ibrahim. I am grateful for their willingness to serve on my supervisory committee, constant encouragement, helpful advice and many fruitful discussions.

I also wish to extend my special appreciation to the staff of Institute Advanced Technology, in special to the head of Advanced Materials and Nanotechnology Laboratory (AMNL), Prof. Dr. Mohd Zobir Hussein for his constant encouragement, kindness and helpful advice; the special thanks to the Program Manager, Electronic Material, AMNL, Asso. Prof. Dr. Mansor Hashim for his kindness and helpful advice; and I would like to thank all my colleagues in Nanotechnology Research Group, AMNL, (Mohd Shamsul Ezzad, Ismayadi Ismail, Beh Hoe Guan, Samaila Bawa Waje, Mohd Hashim Mohd Saad and Liu Wei Wen) for their helpful advice and many fruitful discussions. I also wish to extend my appreciation to Miss Rosnah

Nawang and to the technician of AMNL, Mohd Kadri Bin Masoud, for their kindness, support and for providing help whenever needed. Special thanks extend to the staff of Physics Department, Materials Science Laboratory and X-ray Unit, Faculty of Science, Wan Yusmawati Wan Yusoff and Yusnita Osman, for their helpful and kindness. I would like to thank the technician of FESEM Unit, UTM, Mr. Jefri Bin Samin.

I would like to express my appreciation and thanks to all who have taught me during my life, in special, Mr. Alabyad, head of Plasma Physics Department, Tajoura Research Center, Libya. Ministry of Higher Education of Great Socialist People's Libyan Arab Jamahiriya is gratefully acknowledged for providing the financial support.

I would like to extend my special thanks and appreciation to all my brothers, sisters and mother, brothers, sisters in laws for their unreserved encouragement throughout my study period and before.

Thanks and acknowledgements are meaningless if not extended to my parents who deserve my deepest appreciation. I am grateful for the countless sacrifices they made to ensure that I could pursue my dreams by always being there for me. Real and deepest thanks to them (May ALLAH bless and protect them and may live long and healthy). All praise and thanks words said to them will not be enough.

Lastly but not least, very very special thanks to my wife, son and daughters; confidante and true love. Their love, support, patience and encouragement are behind

my success. They were always there to strengthen my soul during the darker hours and have always lightened-up my days.



I certify that an Examination Committee has met on 21<sup>st</sup> December 2006 to conduct the final examination of Ramadan Masoud Al-Habashi on his Master of Science thesis entitled “Preparation via the Sol-Gel Technique and Characterization of Aluminum Substituted Yttrium Iron Garnet Nanoparticles” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

**Chairman, PhD**

Professor  
Faculty of Graduate Studies  
Universiti Putra Malaysia  
(Chairman)

**Examiner 1, PhD**

Professor  
Faculty of Graduate Studies  
Universiti Putra Malaysia  
(Internal Examiner)

**Examiner 2, PhD**

Professor  
Faculty of Graduate Studies  
Universiti Putra Malaysia  
(Internal Examiner)

**External Examiner, PhD**

Professor  
Faculty of Graduate Studies  
Universiti Putra Malaysia  
(External Examiner)

---

**HASANAH MOHD. GHAZALI, PhD**

Professor/ Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 18 JANUARY 2007



This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Master of Science. The members of the Supervisory Committee are as follows:

**Noorhana Binti Yahya, PhD**

Associate Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Chairman)

**Kaida Bin Khalid, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Nor Azowa Ibrahim, PhD**

Lecturer  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

---

**AINI IDERIS, PhD**

Professor/ Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 8 FEBRUARY 2007



## **DECLARATION**

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.

---

**RAMADAN MASOUD AL-HABASHI**

Date: 15 JANUARY 2007

## TABLE OF CONTENTS

	<b>Page</b>
<b>DEDICATION</b>	ii
<b>ABSTRACT</b>	iii
<b>ABSTRAK</b>	v
<b>ACKNOWLEDGEMENTS</b>	vii
<b>APPROVAL</b>	x
<b>DECLARATION</b>	xii
<b>LIST OF TABLES</b>	xv
<b>LIST OF FIGURES</b>	xvi
<b>LIST OF ABBREVIATIONS</b>	xix
<b>CHAPTER</b>	
<b>1 INTRODUCTION</b>	1
1.1 General	1
1.2 Ceramics	4
1.3 Soft Ferrites	5
1.4 Garnet	7
1.5 Sol-Gel Technique	8
1.6 Aims / Objectives	8
1.7 Thesis Layout	9
<b>2 LITERATURE REVIEW</b>	10
2.1 Introduction	10
2.2 Preparation and Characterization of YIG Samples	10
<b>3 THEORY</b>	20
3.1 Introduction	20
3.2 Paramagnetism	20
3.3 Ferromagnetism	21
3.4 Anti- Ferromagnetism	23
3.5 Ferrimagnetism	23
3.6 Basic Theory	24
3.7 Garnet Structure	30
3.8 Lattice Parameters and Crystal Structures	32
3.9 Sol-Gel Technique	35
3.10 Sintering and Grain Growth	37
3.10.1 Solid-State Sintering	38
3.10.2 Atomic Mechanisms Occurring During Sintering	39
3.10.3 Coarsening	40
3.10.4 Densification	41
3.10.5 Sintering Stages	42
3.10.6 Grain Growth	43
3.10.7 Factors Affecting Solid-State Sintering	44



<b>4</b>	<b>METHODOLOGY</b>	<b>46</b>
4.1	Introduction	46
4.2	Sample Preparation	46
4.2.1	Raw Materials	48
4.2.2	Weighing	48
4.2.3	Mixing	49
4.2.4	Drying	49
4.2.5	Pre-sintering	49
4.2.6	Crushing and Grinding	50
4.2.7	Moulding	50
4.2.8	Sintering	51
4.3	Experimental Measurements	51
4.3.1	Shrinkage	52
4.3.2	Structure & Phase Analysis (XRD)	52
4.3.3	Magnetic Properties Measurements	53
4.3.4	Surface Morphology & Microstructure Studies	54
<b>5</b>	<b>RESULTS AND DISCUSSION</b>	<b>57</b>
5.1	Introduction	57
5.2	XRD Characterization	57
5.3	Shrinkage of Al-YIG Samples	75
5.4	FESEM & EDX Results of Al-YIG Samples	77
5.5	Magnetic Analysis Measurement	92
5.5.1	Real Permeability	92
5.5.2	Loss Factor	94
5.5.3	Quality Factor	95
<b>6</b>	<b>CONCLUSION AND SUGGESTION</b>	<b>97</b>
6.1	Conclusion	97
6.2	Suggestions	98
	<b>REFERENCES</b>	<b>99</b>
	<b>APPENDICES</b>	<b>102</b>
	<b>BIODATA OF THE AUTHOR</b>	<b>133</b>
	<b>LIST OF PUBLICATIONS</b>	<b>134</b>





## LIST OF TABLES

Table		Page
4.1	Weight of the raw materials used to prepare Al-YIG samples.	48
5.1	Intensity and 2Theta for Al-YIG samples calcined at 600°C.	65
5.2	Intensity and 2Theta for Al-YIG samples calcined at 700°C.	67
5.3	Intensity and 2Theta for Al-YIG samples calcined at 800°C.	69
5.4	Intensity and 2Theta for Al-YIG samples calcined at 850°C.	71
5.5	Intensity and 2Theta for Al-YIG samples calcined at 900°C.	73
5.6	Percentage shrinkage of Al-YIG samples.	76
5.7	Elemental analysis of $Y_3Fe_5O_{12}$ sample sintered at 800°C in air.	78
5.8	Elemental analysis of $Y_{2.5}Al_{0.5}Fe_5O_{12}$ sample sintered at 800°C in air.	80
5.9	Elemental analysis of $Y_2Al_1Fe_5O_{12}$ sample sintered at 800°C in air.	82
5.10	Elemental analysis of $Y_{1.5}Al_{1.5}Fe_5O_{12}$ sample sintered at 800°C in air.	84
5.11	Elemental analysis of $Y_1Al_2Fe_5O_{12}$ sample sintered at 800°C in air.	86
5.12	Elemental analysis of $Y_{0.5}Al_{0.5}Fe_5O_{12}$ sample sintered at 800°C in air.	88
5.13	Elemental analysis of $Y_0Al_3Fe_5O_{12}$ sample sintered at 800°C in air.	90
5.14	Average particle sizes were measured by FESEM for Al-YIG samples	91

## LIST OF FIGURES

Figure		Page
3.1	(a) Random orientation of atomic magnetic moments in an unmagnetized substance. (b) When an external field $B$ is applied, the atomic magnetic moments tend to align with the field. (c) The change in spin orientation across the width of a domain wall.	22
3.2	Different magnetic behaviors.	24
3.3	(a) Magnetic field intensity resulting from passage of a current through a loop of radius $r$ . (b) Magnetic moment of current loop of area $A$ .	25
3.4	Structural units and positions of cations in a, c and d sites of YIG structure.	30
3.5	(a) Two dimensional lattice showing the set of planes with the Miller indices (1,1). (b) three dimensional unit cell showing the plane (1 1 1)	32
3.6	Scattering of waves by crystal planes.	33
3.7	Sol-Gel technology and their products.	35
3.8	(a) liquid-phase sintering; (b) solid-state sintering.	37
3.9	Schematic of two possible paths by which a collection of particles can lower its energy, (a) densification and (b) coarsening.	38
3.10	Basic atomic mechanisms that can lead to (a) coarsening and change in pore shape and (b) densification. (c) Thought experiment illustrating how removal of material from the area between particles into the pore leads to shrinkage and densification.	39
3.11	Sintering stages.	42
4.1	Sample preparation and characterization via sol-gel technique flow chart.	47
4.2	Heating and cooling rate during the pre-sintering process.	49
4.3	Dimensional measurement of toroidal sample.	52
4.4	X-ray diffractometer.	53
4.5	RF Impedance/ Material Analyzer (Agilent 4291B, 1MHz -1.8GHz).	54
4.6	(FESEM, SUPRA 35 VP) with energy dispersive x-ray analyzer (EDX).	55
5.1	XRD Pattern of Y3 sample calcined at different temperatures.	58

5.2	XRD Pattern of Y2.5 sample calcined at different temperatures.	59
5.3	XRD Pattern of Y2 sample calcined at different temperatures.	60
5.4	XRD Pattern of Y1.5 sample calcined at different temperatures.	61
5.5	XRD Pattern of Y1 sample calcined at different temperatures.	62
5.6	XRD Pattern of Y0.5 sample calcined at different temperatures.	63
5.7	XRD Pattern of Y0 sample calcined at different temperatures.	64
5.8	XRD Pattern of Al-YIG samples calcined at 600°C.	65
5.9	Intensity vs mole fraction for Al-YIG samples calcined at 600°C.	66
5.10	XRD Pattern of Al-YIG samples calcined at 700°C.	67
5.11	Intensity vs mole fraction for Al-YIG samples calcined at 700°C.	68
5.12	XRD Pattern of Al-YIG samples calcined at 800°C.	69
5.13	Intensity vs mole fraction for Al-YIG samples calcined at 800°C.	70
5.14	XRD Pattern of Al-YIG samples calcined at 850°C.	71
5.15	Intensity vs mole fraction for Al-YIG samples calcined at 850°C.	72
5.16	XRD Pattern of Al-YIG samples calcined at 900°C.	73
5.17	Intensity vs mole fraction for Al-YIG samples calcined at 900°C.	74
5.18	Percentage shrinkage vs mole fraction for Al-YIG samples sintered at 800°C.	76
5.19	FESEM micrograph of Y <sub>3</sub> Fe <sub>5</sub> O <sub>12</sub> sample sintered at 800°C in air.	77
5.20	EDX spectrum of Y <sub>3</sub> Fe <sub>5</sub> O <sub>12</sub> sample sintered at 800°C in air.	78
5.21	FESEM micrograph of Y <sub>2.5</sub> Al <sub>0.5</sub> Fe <sub>5</sub> O <sub>12</sub> sample sintered at 800°C in air.	79
5.22	EDX spectrum of Y <sub>2.5</sub> Al <sub>0.5</sub> Fe <sub>5</sub> O <sub>12</sub> sample sintered at 800°C in air.	79

5.23	FESEM micrograph of $Y_2Al_1Fe_5O_{12}$ sample sintered at 800°C in air.	81
5.24	EDX spectrum of $Y_2Al_1Fe_5O_{12}$ sample sintered at 800°C in air.	81
5.25	FESEM micrograph of $Y_{1.5}Al_{1.5}Fe_5O_{12}$ sample sintered at 800°C in air.	83
5.26	EDX spectrum of $Y_{1.5}Al_{1.5}Fe_5O_{12}$ sample sintered at 800°C in air.	83
5.27	FESEM micrograph of $Y_1Al_2Fe_5O_{12}$ sample sintered at 800°C in air.	85
5.28	EDX spectrum of $Y_1Al_2Fe_5O_{12}$ sample sintered at 800°C in air.	85
5.29	FESEM micrograph of $Y_{0.5}Al_{2.5}Fe_5O_{12}$ sample sintered at 800°C in air.	87
5.30	EDX spectrum of $Y_{0.5}Al_{2.5}Fe_5O_{12}$ sample sintered at 800°C in air.	87
5.31	FESEM micrograph of $Y_0Al_3Fe_5O_{12}$ sample sintered at 800°C in air.	89
5.32	EDX spectrum of $Y_0Al_3Fe_5O_{12}$ sample sintered at 800°C in air.	89
5.33	Average particle size vs mole fraction for Al-YIG samples.	91
5.34	Real permeability vs frequency for Al-YIG samples.	92
5.35	Loss Factor vs frequency for Al-YIG samples.	94
5.36	Q Factor vs frequency for Al-YIG samples.	95

## LIS OF ABBREVIATIONS

YIG	Yttrium iron garnet.
Al-YIG	Aluminum substituted yttrium iron garnet.
FIM	Ferrimagnetic material.
FM	Ferromagnetic material.
XRD	X-ray diffraction.
FESEM	Field emission scanning electron microscopy.
EDX	Energy dispersive x-ray analyzer.
B	Magnetic field.
H	Magnetic field intensity.
K	Kelvin unit.
$\mu_o$	The permeability of free space ( $4\pi \times 10^{-7}$ Wb/(A .m)).
$M$	Magnetization of solid.
$\mu_{ion}$	Net magnetic moment of an ion.
$\mu$	Permeability of solid.
$\mu_r$	Relative permeability.
$\chi_{mag}$	Magnetic susceptibility.
$\mu_{orb}$	Orbital magnetic moment of a single electron.
$\omega_o$	Angular frequency.
$\Pi_0$	Orbital angular momentum of a single electron.
$m_e$	Electron mass.
$l$	Orbital angular momentum quantum number.
$\mu_B$	Bohr magneton ( $9.27 \times 10^{-24}$ A.m <sup>2</sup> ).
$\mu_s$	Spin magnetic moment of a single electron.
$\Pi_s$	Spin angular momentum of a single electron.
s	Spin quantum number ( $\pm 1/2$ ).
$m_l$	Orbital magnetic quantum number.
$J$	Total angular momentum of electrons.
$L$	Total orbital magnetic moment of electrons.
$S$	Total spin angular moment of electrons.
$\lambda$	Wavelength of the incident x-ray beam.
$d_{hkl}$	Distance between adjacent planes in a crystal.



PVA	Polyvinyl alcohol.
$D_0$	Outer diameter of the toroidal sample.
$S_h(\%)$	Percentage shrinkage of a sample.
$\mu'$	Real permeability.
$\mu''$	Loss factor.
Q	Quality factor.
a.u.	Attributry unit.

# CHAPTER 1

## INTRODUCTION

### 1.1 General

Nanotechnology is considered to be the most advanced manufacturing technology and is commonly referred to as the extreme technology. This is due to the fact that as the size reduces into the nanometer range, the materials exhibit peculiar and interesting mechanical and physical properties, e.g. increased mechanical strength, enhanced diffusivity, higher specific heat and electrical resistivity compared to conventional coarse grained counterparts. This field owes its parentage to investigations of reactive species (free atoms, clusters, reactive particles) throughout the 1970s and 1980s, coupled with new techniques and instruments (Pulsed cluster beams, innovations in mass spectrometry, vacuum technology, microscopes, and more). Excitement is high and spread throughout different fields including chemistry, physics, material science, engineering, and biology. This excitement is warranted because nanoscale materials represent a new realm of matter, and the possibilities for interesting basic science as well as useful technologies for society are widespread and real (Klabunde, 2001).

A nanometer,  $10^{-9}$  m, is about ten times the size of the smallest atoms, such as hydrogen and carbon, while a micron is barely larger than the wavelength of visible light, thus invisible to the human eye. A millimeter, the size of a pinhead, is roughly the smallest size available in present day machines. The range of scales from millimeters to nanometers is one million, which is also about the range of scales in



present day mechanical technology, from the largest skyscrapers to the smallest conventional mechanical machine parts.

The definitions of nanoscience and nanotechnology avoided the use of dimensions at all:

- Nanoscience is the study of phenomena and manipulation of materials at atomic, molecular, and macromolecular scales, where properties differ significantly from those at a larger scale.
- Nanotechnologies are the design, characterization, production, and application of structures, devices, and systems by controlling shape and size on the nano scale.
- Nanomaterials cross the boundary between nanoscience and nanotechnology and link the two areas together, so these definitions are very appropriate. It is recognized that the size range that provides the greatest potential and, hence, the greatest interest is that below 100 nm; however, there are still many applications for which larger particles can provide properties of great interest.

Furthermore, nanomaterials cover a hugely diverse range of materials: polymers, metals, and ceramics. Nanoparticles can come in a wide range of morphologies, from spheres, through flakes and platelets, to dendritic structures, tubes, and rods. The sophistication of the production processes for some materials has reached the level in the laboratory where complex three-dimensional structures such as springs, coils, and brushes have been made.

However, the fact that these materials can be made at this scale gives them the potential to have some very interesting properties.



Materials at the nanoscale between 1 nm and 250 nm lie between the quantum effects of atoms and molecules and the bulk properties of materials. It is in this, where many physical properties of materials are controlled by phenomena that have their critical dimensions at the nanoscale. By being able to fabricate and control the structure of nanoparticles, the scientist and engineer can influence the resulting properties and, ultimately, design materials to give desired properties. The ranges of applications where the physical size of the particle can provide enhanced properties that are of benefit are extremely wide.

Nanoparticles and nanomaterials continue to attract a great deal of attention because of their potential impact on an incredibly wide range of industries and markets. Consequently, the technology is evolving rapidly and will develop faster over the coming years (Wolf, 2004).

Ultra-fine microstructures having an average phase or grain size on the order of a nanometer are classified as nanostructure materials. Currently, in a wider meaning of the term, any material that contains grains or clusters below 100 nm, or layers or filaments of that dimension, can be considered to be nanostructure. The interest in these materials has been stimulated by the fact that, owing to the small size of the building blocks (particle, grain, or phase) and the high surface to volume ratio, these materials are expected to demonstrate unique mechanical, optical, electronic, and magnetic properties. The properties of these materials depend on the following four common microstructure features: fine grain size and size distribution (<100 nm), the chemical composition of the constituent phases, the presence of interfaces (grain boundaries, hetero-phase interfaces, and so on), and interactions between the