

# **UNIVERSITI PUTRA MALAYSIA**

USE OF ALKALI-ACTIVATED PALM OIL FUEL ASH REINFORCED BY MICROFIBRES FOR SOFT SOIL STABILISATION

SHAHRAM POURAKBAR

FK 2015 94



# USE OF ALKALI-ACTIVATED PALM OIL FUEL ASH REINFORCED BY MICROFIBRES FOR SOFT SOIL STABILISATION

# UPM

By

SHAHRAM POURAKBAR

Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in Fulfilment of the Requirements for the Degree of Doctor of Philosophy

November 2015

# COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of requirement for the degree of Doctor of Philosophy

# USE OF ALKALI-ACTIVATED PALM OIL FUEL ASH REINFORCED BY MICROFIBRES FOR SOFT SOIL STABILISATION

By

# SHAHRAM POURAKBAR

### November 2015

# Chairman: Professor Bujang Kim Huat, PhD Faculty : Engineering

The construction of heavy structures on soft soils in tropical regions is a high challenging task. The soft soils are generally characterized by low undrained shear strength and poor bearing capacity. Deep mixing is one of the beneficial soil improvement techniques that could be applied successfully to overcome these problems by improving geotechnical characteristics of soils with cement and other traditional cementitious binders. Although such chemical binders can improve many engineering properties of soils, they have several shortcomings.

The primary motivation for this study was to investigate the innovative reuse of a locally available by-product to eliminate traditional binders from deep mixing projects. In this respect, the use of palm oil fuel ash (POFA) as a well-known agricultural waste deserves a special attention. This research consists of four main stages.

The first stage is the performance of the preliminary investigation in order to evaluate the effectiveness of POFA (individually and in combination with cement) on some basic geotechnical characteristics of soft soil. The unconfined compression strength (UCS) was used as a practical indicator to investigate the strength development. According to the test results, combining POFA with cement results in a sharp increase in the UCS of the samples, whereas in the same curing time, the strength development of POFA-stabilized soil was not remarkable.

 $\bigcirc$ 

In the second stage of this research, alkaline activation of POFA was adopted as a viable technique to fully eliminate cementitious binders from geotechnical applications. In simple words, alkali-activated binder is generally a synthetic alkali aluminosilicate which is produced from the reaction of a solid aluminosilicate with pre-designed concentrated aqueous alkaline solutes. Based on the obtained UCS values at curing periods of up to 6 months, using alkali-activated POFA increased the peak strength of soil by up to 70 times compared to that of natural soil.

Beside the shear strength development, in order to increase the tensile strength and ductility of treated soil, the combined effect of fibre inclusion and alkaline activation is described and reported in the third stage. In this stage, along with the POFA in presence of high alkali solutes, mineral wollastonite microfibres (CaSiO<sub>3</sub>) were used as a strong reinforcement inclusion. Beside the UCS test, indirect tensile strength and flexural strength tests were carried out at curing periods of up to 6 months. The test results indicated that the inclusion of fibre reinforcement within alkali-activated POFA, caused a further increase in the peak stress and tensile strength, and decreased the loss of post-peak strength.

In the last stage of this research, a geotechnical design procedure of interaction between a strip footing and stabilized soil is modelled in the laboratory using the column technique. This part takes into account the geotechnical characteristics of the stabilized soil columns and simulates fairly well the coupled effect of alkali-activated POFA and reinforcement inclusion (APR) in deep mixing projects. The test results demonstrated the strong contribution of APR to the soil matrix, which led to a sharp increase in the bearing capacity of up to 204% in the treated soil columns.

Abstrak tesis yang telah dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan ijazah Doktor Falsafah

# PENGGUNAAN ABU BAHAN API KELAPA SAWIT ALKALI-DIAKTIFKAN BERTETULANG MIKROGENTIAN DALAM KAEDAH PENCAMPURAN DALAM

Oleh

## SHAHRAM POURAKBAR

### November 2015

# Pengerusi: Profesor Bujang Kim Huat, PhD Fakulti : Kejuruteraan

Pembinaan struktur berat pada tanah lembut di kawasan tropika adalah satu tugas mencabar yang tinggi. Jenis-jenis tanah ini umumnya mempunyai ciri-ciri kekuatan ricih tak bersalir rendah dan keupayaan galas yang lemah. Pencampuran dalam adalah salah satu daripada teknik pembaikan tanah bermanfaat yang boleh digunakan dengan jayanya untuk mengatasi masalah ini dengan meningkatkan ciri-ciri geoteknikal tanah dengan simen dan pengikat berperekat tradisionallain. Walaupun pengikat kimia boleh meningkatkan banyak ciri-ciri kejuruteraan tanah, mereka mempunyai beberapa kelemahan, terutamanya apabila dilihat dari perspektif alam sekitar. Motivasi utama bagi kajian ini adalah untuk mengenalpastiguna semula inovatif hasil sampingan tempatan sedia ada untuk menghapuskan pengikat tradisional dari projek pencampuran dalam. Dalam hal ini, penggunaan abu bahan api kelapa sawit (POFA) sebagai sisa pertanian terkenal patut diberi perhatian khusus. Kajian ini terdiri daripada empat peringkat utama.

Peringkat pertama ialah prestasi kajian awal untuk menilai keberkesanan POFA (secara individu dan dengan kombinasi simen) dalam mempengaruhi beberapa ciri-ciri asas geoteknikal tanah lembut. Kekuatan mampatan tak terkurung (UCS) telah digunakan sebagai penunjuk praktikal untuk mengenalpastiperkembangan kekuatan. Selain itu, analisis mikrostruktur telah dijalankan untuk mendapatkan tafsiran mekanisme penstabilan. Menurut hasil ujian, penggabungan POFA dengan hasil simen menyebabkan peningkatan mendadak dalam UCS sampel dalam masa 28 hari pengawetan, manakala pada tempoh pengawetan yang sama, perkembangan kekuatan tanah terstabil POFA adalah tidak baik.

Pada peringkat kedua kajian ini, pengaktifan alkali POFA diterima pakai sebagai teknik boleh jaya untuk menghapuskan sepenuhnya simen dan pengikat berperekat lain dari aplikasi geoteknikal. Dalam erti kata yang mudah, pengikat alkali-diaktifkan umumnya adalah aluminosilikat alkali sintetik yang dihasilkan daripada tindak balas aluminosilikat pepejal (sumber pengikat) denganlarutan alkali akueus pekat yang direka bentuk awal. Berdasarkan nilai UCS diperolehi pada tempoh pengawetan sehingga 6 bulan, menggunakan POFA alkali-diaktifkan meningkatkan kekuatan puncak tanah sehingga 70 kali berbanding dengan tanah semula jadi. Selain perkembangan kekuatan ricih, untuk meningkatkan kekuatan tegangan dan kemuluran tanah dirawat, kesan gabungan rangkuman gentian dan pengaktifan alkali digambarkan dan dilaporkan di peringkat ketiga kajian. Selain ujian UCS, kekuatan tegangan tidak langsung dan ujian kekuatan lenturan telah dijalankan pada tempoh pengawetan sehingga 6 bulan. Keputusan ujian menunjukkan bahawa rangkuman gentian tetulang dalamPOFA alkali-diaktifkan, menyebabkan peningkatan lanjut dalam tekanan puncak dan kekuatan tegangan, mengurangkan kehilangan kekuatan selepas puncak.

Pada peringkat terakhir kajian ini, satu prosedur reka bentuk geoteknikal interaksi antara jalur landasan dan tanah terstabil dimodelkan dalam makmal menggunakan teknik lajur. Bahagian ini mengambil kira ciri-ciri geoteknikal daripada tiang-tiang tanah terstabil dan mensimulasikan agak baik kesan ganding POFA alkali-diaktifkan dan rangkuman pengukuhan tetulang (ARS) dalam projek-projek pencampuran dalam. Hasil ujian menunjukkan sumbangan ketara ARS matriks tanah, yang membawa kepada peningkatan ketara dalam keupayaan galas ruangan tanah yang dirawat.

# ACKNOWLEDGEMENTS

First of all, my utmost gratitude goes to Allah.

I would like to express my heartfelt gratitude, indebtedness and deep sense of respect to my parents (Mohsen and Tahereh).

Special appreciation and gratitude are extended to my supervisors, Prof. Bujang, Prof. Hanafi, and Dr. Afshin for their encouragement, patience, supervision, guidance and support from the initial to the final level and completion of this thesis.

I would like to thank the Ministry of Science, Technology, and Innovation (MOSTI) for providing the research grant for financial supporting this research (Escience fund, Vot: 03-01-04-SF2011, behaviour of stabilized clay soil using oil palm dirty gold). Moreover, I would like to thank the Universiti Putra Malaysia for providing a scholarship.

Last but not least, I would also like to acknowledge Mrs. Soheyla Hashemi for her valuable encouragement, support and help.

I certify that a Thesis Examination Committee has met on 26 November 2015 to conduct the final examination of Shahram Pourakbar on her thesis entitled "Use of Alkali-Activated Palm Oil Fuel Ash Reinforced by Microfibres for Soft Soil Stabilisation" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

# Abdul Halim bin Ghazali, PhD

Associate Professor Faculty of Engineering Universiti Putra Malaysia (Chairman)

Thamer Ahmad Mohammad Ali, PhD Professor Faculty of Engineering Universiti Putra Malaysia (Internal Examiner)

Dato' Ismail bin Haji Bakar, PhD Professor Universiti Tun Hussein Onn Malaysia (External Examiner)

Satoru Kawasaki, PhD Professor Hokkaido University Japan (External Examiner)

**ZULKARNAIN ZAINAL, PhD** Professor and Deputy Dean School of Graduate Studies Universiti Putra Malaysia

Date: 15 December 2015

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

# **Bujang Kim Huat, PhD**

Professor Faculty of Engineering University Putra Malaysia (Chairman)

# Mohamed Hanafi Musa, PhD Professor Faculty of Agriculture University Putra Malaysia

(Member)

# Afshin Asadi, PhD

Research fellow Faculty of Engineering University Putra Malaysia (Member)

> **BUJANG BIN KIM HUAT,PhD** Professor and Dean School of Graduate Studies Universiti Putra Malaysia

Date:

# **Declaration by graduate student**

I hereby confirm that:

- this thesis is my original work
- quotations, illustrations and citations have been duly referenced
- the thesis has not been submitted previously or com currently for any other degree at any institutions
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice –Chancellor (Research and innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software

Signature: ·	Date:
8	

Name and Matric No: Shahram Pourakbar GS34390

# Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: Name of Chairman of PROF. DR BUIANG B K HUAT Supervisory Dean Committee: School of Graduate Studies Universiti alaysia 43400 UF Selangor erdano Signature: Name of Member of Supervisory Committee: Signature: Name of Member of Asudi Supervisory Committee:

# TABLE OF CONTENTS

				Page
AF	BSTRAC	Т		i
AF	BSTRAK			iii
AC	CKNOW	LEDGEM	ENTS	v
AF	PROVA	L		vi
DF	ECLARA	TION		viii
	ST OF T	ABLES		xii
	ST OF F	IGURES		xiii
	ST OF A	BBREVIA	ATIONS	xvi
				AVI
CH	HAPTER			
-	1 INT	RODUCT	ION	1
	1.1	General I	Introduction	1
	1.2	Problem	Statement	3
	1.3	Objective	es of the Study	3
	1.4	Organiza	tion of This Dissertation	4
,	• T TT	DATIDI	DEVIEW	5
	2 LIII 21	Introduct		5
	2.1	Soil Stob	ilization	5
	2.2		Traditional Compatitions Matarials	5
		2.2.1	Traditional Cementitious Materials	5
		2.2.2	Pozzolanic Materials	0
		2.2.3	Alkali-activated Materials	9
		2.2.4	Reinforcement Materials	19
	2.3	Deep Mi	xing Method	24
		2.3.1	Introduction	24
		2.3.2	Deep Mixing Installation Pattern	25
		2.3.3	Deep Mixing Design	26
	2.4	Summar	y	28
	3 STA	BILIZAT	ION OF CLAYEY SOIL USING ALKALI-	29
	ACT	IVATED	PALM OIL FUEL ASH	
	31	Introduct	ion	29
	3.2	Materials	and Methods	31
	5.2	3 2 1	Materials used	31
		3.2.1 3.2.2	L aboratory test	36
		3.2.2	Standard Proctor Compaction Test	38
		3.2.5	Unconfined Compressive Strength	38
		2.2.4	PH Value	20
		2.2.5	Analasia of Missource	39
	2.2	3.2.0 Deculta a	Analysis of Microstructure	59
	3.3	Results a $2.2.1$	nd Discussion	40
		3.3.1	the Compactability	40
		3.3.2	Effect of POFA and POFA/Cement Combination on	42
			the Unconfined Compressive Strength	
		3.3.3	Effect of Alkali-activated POFA on Unconfined	45
			Compressive Strength	
		3.3.4	Microstructural Analysis	53
	3.4	Conclusi	ons	57
				- /

4	SOIL ACT INCI	. STABILIZATION WITH INCORPORATING ALKALI- IVATED PALM OIL FUEL ASH AND MICROFIBRES LUSION	59
	4.1	Introduction	59
	4.2	Materials and Methods	60
		4.2.1 Materials	61
		4.2.2 Unconfined Compression Strength	61
		4.2.3 Indirect Tensile Strength	62
		4.2.4 Flexural Strength	63
		4.2.5 Analysis of Microstructure	65
	4.3	Results and Discussion	65
		4.3.1 Effect of Fibre Inclusion on Plain Soil	65
		4.3.2 Effect of Alkali-activated POFA on Soil	66
		4.3.3 Coupled Effect of Fibre Inclusion and Alkali-activated POFA	67
		4.3.4 Effect of Fibre Inclusion on Failure Characteristics	69
		of Treated Samples	
		4.3.5 Toughness	70
		4.3.6 Elastic Stiffness	72
		4.3.7 Indirect Tensile Strength	72
		4.3.8 Flexural Strength	74
		4.3.9 Microstructure Analysis	75
	4.4	Conclusions	82
5	INCO AND	DRPORATION OF ALKALI-ACTIVATED PALM FUEL ASH MICROFIBRE INCLUSION IN DEEP MIXING COLUMN Introduction	83 83
	5.2	Materials and Methods	84
	0.2	5.2.1 Materials	84
		5.2.2 Preparation of Physical Model	84
		5.2.3 Preparation of the Soil–Stabilizers Columns	86
		5.2.4 Model Design	88
		5.2.5 Assembly of Loading Procedure	91
		5.2.6 Prediction of Bearing Capacity	92
		5.2.7 Testing Program	92
	5.3	Results and Discussion	95
		5.3.1 Untreated Case	95
		5.3.2 Treated Cases	95
	5.4	Conclusions	100
6	SUM	MARY, CONCLUSIONS AND RECOMMENDATIONS FOR	101
	FUT	URE RESEARCH	
	6.1	Summary	101
	6.2	General Conclusion	102
	6.3	Recommendations for Future Research	103
DFFF	DENI	°ES	105
RIOD		OF STUDENT	100
LIST	OF P	UBLICATIOS	128

 $\bigcirc$ 

# LIST OF TABLES

Table		Page
2.1	Summary of researches performed on pozzolanic materials for soil Improvement	8
2.2	Historical date in alkaline activation process	8
2.3	Summary of researches performed on alkali-activated binder for soil stabilization	14
2.4	Summary of researches performed on natural-fibres inclusions for soil reinforcement	21
2.5	Summary of researches performed on man-made fibres inclusions for soil reinforcement	22
3.1	Physical characteristics of soil	32
3.2	Chemical composition of clayey soil	33
3.3	Physicochemical properties of POFA (before and after pre- treatment) and cement	35
3.4	Mixture proportions of various series of test specimens	37
3.5	Standard compaction test results of treated clayey soil	42
4.1	Chemical composition of wollastonite microfibre	61
4.2	Mixture proportions of various series of test specimens	64
5.1	Mixture proportions of various series of test specimens	94

G

# LIST OF FIGURES

Figure		Page
2.1	Poly(sialates) structures	15
2.2	Several configurations of deep mixing have been applied in the field including (a) Group column type improvement, (b) Wall type improvement, (c) Grid type improvement, and (d) Block type improvement	26
3.1	Map of the site location of soil	32
3.2	Grain size distribution curve of clayey soil and POFA (before and after ball milling process)	34
3.3	The process of ball milling POFA	35
3.4	Compaction curves for Soil–POFA mixtures (SP group)	41
3.5	Influence of POFA content and age on unconfined compressive strength	43
3.6	UCS results of stabilized-soil samples using cement and cement/POFA mixtures in different percentages	44
3.7	UCS results of the test specimens after (a) 7 days curing, (b) 28 days curing, (c) 90 days curing and (d) 180 days curing	46
3.8	Failure pattern in treated samples using alkali-activated POFA	47
3.9	UCS values of treated soil specimens after 7, 28, 90 and 180 days curing	48
3.10	UCS results of POFA-treated soil in presence of different alkali metals (K+ and Na <sup>+</sup> ) after 7, 90, and 180 days curing	49
3.11	The remaining moisture content of test specimens after different curing times	51
3.12	Relationship between E 50 (MPa) and alkali-activated samples	52
3.13	The average pH values of test samples over a curing period of 7 days	53
3.14	SEM images of (a) natural soil, and (b) treated POFA	54
3.15	The images of stabilized clayey soil (a) with POFA (SP5), and (b) with cement/POFA mixture (CSPa2)	55

6

3.16	SEM micrographs of (a) selected KOH-POFA-soil (KSP20), and (b) selected NaOH-POFA-soil (NSP20)	56
3.17	FTIR of selected alkali-activated samples	57
4.1	Stress-strain behaviour of fibre reinforced plain soil (SR group) after 28, 90, and 180 days curing	66
4.2	Stress-strain behaviour of treated soil samples (S, N-KSP, and N-KSPR) after (a) 28 days, (b) 90 days, and (c) 180 days curing	68
4.3	UCS values of test samples (S, N-KSP, and N-KSPR) after 28, 90, and 180 days curing	69
4.4	Effect of microfibres inclusions on failure characteristics of alkali- activated samples	70
4.5	The normalized strain-energy-absorption capabilities of treatments in test specimens (SR, N-KSP, and N-KSPR group)	71
4.6	Relationship between E 50 (MPa) and treated samples (SR, N-KSP, and N-KSPR group)	72
4.7	Tensile load-deflection relationship in selected treated samples	73
4.8	Tensile failure characteristics of selected samples for indirect tensile strength test:(a) alkali-activated sample without reinforcement inclusion, and (b) reinforced alkali-activated sample	74
4.9	Flexural response of selected test samples after 180 days curing	75
4.10	SEM image of wollastonite microfibre surface	76
4.11	EDS image of wollastonite microfibre surface	76
4.12	SEM image of microfibre inclusion in conjunction with alkali activation	77
4.13	SEM images of microfibre inclusion in conjunction with alkali activation	78
4.14	SEM image of microfibre inclusion in conjunction with alkali- activated POFA (NaOH used as an alkali activator)	79
4.15	SEM image of microfibre inclusion in conjunction with alkali- activated POFA (KOH used as an alkali activator)	80
4.16	FTIR of selected test samples	81
5.1	Model test Box	85

5.2	Consolidation setup: (a) a small pressure from the self-weight of the steel plate and (b) Pressure applied by hydraulic jack	86
5.3	The aluminium guiding plates used to arrange and align the treated soil columns	89
5.4	Parts of extruder extension	89
5.5	Columns installation procedure	91
5.6	Bearing capacity setup	92
5.7	The relationship between vertical stress and displacement/foundation width in two group series (a) NSPR1-3, and (b) KSPR1-3	97
5.8	Measured and calculated bearing capacity factor (Nc) values	98

C

# LIST OF ABBREVIATIONS

POFA	Palm oil fuel ash
DMCs	Deep mixing columns
C-S-H	Calcium silicate hydrate
C-A-H	Calcium aluminium hydrate
APR	Alkali-activated POFA reinforced with microfibres
A-S-H	Aluminium silicate hydrate
α	Replacement area ratio
UCS	Unconfined compression strength
СН	High-plasticity clay
LOI	Loss on ignition
MDD	Maximum dry density
OMC	Optimum moisture content
LL	Liquid limit
PL	Plastic limit
PI	Plasticity index
XRD	X-ray diffraction
XRF	X-ray florescence
SEM	scanning electron microscopy
S	Natural soil
NS	NOH-Soil
CS5	5% Cement + Soil
CS10	10% Cement + Soil
CS15	15% Cement + Soil
SP5	Soil + 5% POFA
SP10	Soil + 10% POFA
SP15	Soil+ 15% POFA
CSP	Cement +Soil + POFA
CS10	10% Cement-soil
CS15	15% Cement-Soil
KSP	Soil-KOH- POFA
NSP	Soil-NaOH-POFA
SR5	Soil + 5% microfibre
SR10	Soil + 10% microfibre
SR15	Soil + 15% microfibre
NSPR5	NaOH-Soil-20% POFA-5% microfibre
KSPR5	KOH-Soil-20% POFA-5% microfibre
NSPR10	NaOH-Soil-20% POFA-10% microfibre
KSPR10	KOH-Soil-20% POFA-10% microfibre
NSPR15	NaOH-Soil-20% POFA-15% microfibre
KSPR15	KOH-Soil-20% POFA-15% microfibre
ITS	Indirect tensile strength
Ν	Number of columns
C <sub>uc</sub>	Undrained shear strength of stabilized column
C <sub>us</sub>	Undrained shear strength of soil
λ	Dimensionless coefficient

C

### **CHAPTER 1**

### **INTRODUCTION**

### 1.1 General Introduction

The utilization of soft and weak soils in tropical areas is currently low, although their construction has become increasingly necessary for economic reasons. These types of soils are generally characterized by low undrained shear strength (less than 25 kPa), extremely high compressibility, and poor bearing capacity (Bergado, Anderson, Miura, and Balasubramaniam 1996; Tingle and Santoni 2003). In such conditions, these soft soils pose obvious problems in the construction industry because of their low bearing capacity even when subjected to a moderate load, leading to liquefaction and/or significant strain softening (Kitazume and Terashi 2013).

Of the soil stabilising techniques, deep mixing columns (DMCs) is becoming well established in an increasing number of countries because it is a cost-effective approach with numerous technical and environmental advantages (Saitoh, Suzuki, and Shirai 1985; Fang, Chung, Yu, and Chen 2001). In DMCs, the chemical agents, which are either slurry (wet mixing) or powder (dry mixing), are mixed into the soft soil to form columns of soil binders. Due to their robustness, easy adoptability, and economic value, cement and lime are employed as stabilizing agents in DMCs to produce stronger and firmer soil, namely soil–cement/lime columns (Kawasaki and Suzuki 1981; Saitoh 1988; Prusinski and Bhattacharja 1999). Although these traditional binders (i.e., cement and lime) can improve many engineering properties of treated soil columns, they have several shortcomings, especially when viewed from an environmental perspective. Recent soil stabilization methods have highlighted the need for full or partial replacement of cement and lime with cleaner and more sustainable materials. These stabilizers should provide strength and durability performances that are either comparable to or better than those of cement and lime within a similar curing duration.

In this respect, alkali-activated binder can constitute an interesting option to fully eliminate traditional the usage of cemenititous binders in geotechnical projects, since calcium is not essential in any part of an alkali-activated structure (Davidovits 1991, 2005). Alkaline activation has a history starting from the 1940's which were first demonstrated by Purdon (1940) and the application as a binder in the construction industry started in Ukraine since the 1960s (Glukhovsky 1965). The theoretical basis of the alkaline activation system was established for the first time in 1979 by the French researcher Davidovits (1979), who introduced the term "geopolymer" to designate a new class of three-dimensional crosslinked chain.

Alkaline activation technique is a term covering synthetic aluminosilicate materials, which are formed by the reaction of any Si–Al raw material (with less or no CaO component) and an alkali solution. This process can be described as a polycondensation



(a reaction that chemically integrates minerals), consisting of aluminum and silica alternately tetrahedrally interlinked by sharing all the oxygen atoms. The process starts when the high hydroxyl concentration of the alkaline medium favours the breaking of the covalent bonds Si–O–Si, Al–O–Al, and Al–O–Si from the vitreous phase of the source material, transforming the silica and alumina ions in colloids and releasing them into the solution. Under this condition, alumino-silicates are transformed into extremely reactive materials to form a well-structured aluminum silicate hydrate (A-S-H) polymerized framework (Davidovits 1988; Davidovits 2005; Khale and Chaudhary 2007).

A large and growing body of literature has investigated the mechanism of the alkaline activation from wide variety of alumino-silicate source materials (Davidovits 1988; Xu and Van Deventer 2000; MacKenzie, Brew, Fletcher, Nicholson, Vagana, and Schmücker 2006; Khale and Chaudhary 2007). A significant body of these studies validate the proposition that alkaline activation provides a promising and sustainable alternative to the use of cement and lime because of (i) the abundant raw material sources and (ii) its lower energy consumption and  $CO_2$  emission. However, relatively little progress has been made towards the utilization of this technique as a viable technology for soil stabilization projects.

In very limited attempts, some geotechnical researchers have investigated the effectiveness of alkali-activated low-calcium and high-calcium fly ash as silica and alumina amorphous sources for soil stabilization (Cristelo, Glendinning, and Pinto 2011; Cristelo, Glendinning, Fernandes, and Pinto 2012a, 2013). Also, Zhang *et al.* (2013) investigated the feasibility of using metakaolin as an alkali-activated soil stabilizer at shallow depth. Their results suggested that the alkali-activated binder is a successful method of deep soil stabilization.

Despite such positive developments, several issues such as the curing condition, the type of alkaline solute, and the role of parent soil (i.e., natural water content, presence of Si and Al in soil and pH) in alkaline activation are not well recognized. Apart from that, to derive the economic benefits of this promising method for the purpose of soil treatment, there is a high need to explore the locally available materials, especially the materials that contribute to the volume of waste. Framed by this context, among the possibilities of utilizing various by-products and natural prime materials in the process of alkaline activation, the use of palm oil fuel ash (POFA) deserves a special attention.

Other than the POFA which was used as a source binder, in order to establish viable solution that provides satisfactory mechanical properties such as tensile strength and ductility in stabilized soil columns, study of a newly proposed mixture of reinforcement inclusion and alkali-activated POFA also described and reported in this research. A special focus is to select an appropriate reinforcement inclusion which is not only suitable in alkaline environments but also provides satisfactory mechanical properties in stabilized soil. As such, amongst various reinforcement inclusions, wollastonite microfibres with chemical composition of  $CaSiO_3$  (40.0- 50.0% of CaO, and 40.0 - 55.0% of SiO<sub>2</sub>) deserve special attention. These mineral microfibres have been formed

in nature from the interaction of silica  $(SiO_2)$  with calcite  $(CaCO_3)$  under high pressure and temperature. It is reasonable to anticipate that utilizing wollastonite microfibres in conjunction with alkali-activated POFA can act as a bridge to lock the particles firmly, to fill voids and pores, resulting in positive effect on the mechanical properties of treated soil.

# 1.2 Problem Statement

Although traditional calcium-based binders (i.e., cement and lime) can improve many engineering properties of soils, they have several shortcomings, especially when viewed from an environmental perspective. In the case of cement, this traditional binder generates around 7% of artificial CO<sub>2</sub> emissions, because of carbonate decomposition (Gartner 2004; Matthews, Gillett, Stott, and Zickfeld 2009). It is estimated that every ton of cement produces around one ton of CO<sub>2</sub>, a major greenhouse gas implicated in global warming (Kim and Worrell 2002; Taylor, Tam, and Gielen 2006; Lothenbach, Scrivener, and Hooton 2011). Beside the emission of CO<sub>2</sub>, another by-product of cement production is NO<sub>x</sub>. Most of these nitrogen oxides are produced in cement kilns, which can contribute to the greenhouse effect and acid rain (Hendriks, Worrell, De Jager, Blok, and Riemer 1998).

Beyond these problems, the use of cementitious binders in soil stabilization shows poor tensile and flexural strength and a brittle behaviour (Sukontasukkul and Jamsawang 2012; Correia, Oliveira, and Custódio 2015). For instance, when the cemented soil column is subjected to seismic loads, either lateral earth pressures (as for deep-mixed soil walls) or horizontal displacements (as in the case of columns installed under the sides of embankments and in slopes), the stabilized soil tends to fail under tension, due to its brittleness (Sukontasukkul and Jamsawang 2012; Correia *et al.* 2015).

POFA is one of the most abundantly produced waste materials in Malaysia which has a strong potential to be used in this technique due to its high siliceous content. It should be mentioned that oil constitutes only 10% of the palm production, while the rest of 90% is the biomass (Ahmad et al., 2008). Despite efforts that have gone into finding reuse applications, considerable amounts of POFA continue to require disposal through landfilling every year and Malaysian government needs to allocate additional hectares of landfill for disposal and spends a ton of money for transporting this waste and maintenance functions. However, by recycling this agro-waste, it can reduce the dumped waste in addition to make sure environmental sustainability.

# 1.3 Objectives of the Study

The main objective of this study is to develop alkali-activated palm fuel ash reinforced with fibre (APR) for the soft soil stabilization. This study not only focuses on the strength and mechanical performance of stabilized soil but also to understand the underlying mechanisms of stabilization. The specific objectives of the study are:

1. To investigate the effect of POFA (individually and in combination with cement) on the geotechnical behaviour of soft soil in order to evaluate the effectiveness of this new soil stabilizer.

2. To investigate the effect of alkali-activated POFA on the strength and underlying mechanisms of stabilized soft soil.

3. To evaluate the effect of incorporating reinforcement inclusion with alkali-activated POFA on the mechanical performance and underlying mechanisms of stabilized soft soil.

4. To determine bearing capacity and settlement for a model of APR-stabilized soft soil with group of columns to simulate a foundation.

# 1.4 Organization of This Dissertation

In addition to the introduction, this thesis is composed of five more chapters. In Chapter 2, in the first stage, different soil stabilization materials including traditional cementitious materials (i.e., cement and lime), pozzolanic materials (supplementary traditional binders), alkali-activated materials (new generation of binders), and reinforcement materials are introduced and reviewed. The second stage of this research chapter describes the fundamental of deep mixing as one of the promising methods of soil stabilization. Chapter 3 presents the effect of POFA (individually and in combination with cement) on some geotechnical behaviour of parent soil to provide a framework for evaluation of this new soil stabilizer for soft soil stabilization. Moreover, this chapter of study describes the alkaline activation technique for the purpose of soil stabilization. In this respect, the role of various factors on the strength and underlying mechanisms of stabilized soil using alkali-activated POFA is investigated. Chapter 4 summarizes the effect of alkali-activated POFA reinforced by wollastonite microfibres (APR) on mechanical performance and underlying mechanisms of stabilized soft soil. Chapter 5 provides further insight about the behaviour of APR-treated soft soil when used as a foundation for a relatively lightweight structure. In this respect, the bearing capacity and settlement of a model APR-stabilized soft soil ground is determined by a group of columns. Chapter 6 presents the conclusions and recommendations of this research.

### REFERENCES

- Ahnberg, H., Ljungkrantz, C., and Holmqvist, L. (1995). *Deep stabilization of different types of soft soils*. Proceedings of 11th Conference on Deep Mixing Method, Copenhagen, Denmark.
- Akpokodje, E. (1985). The stabilization of some arid zone soils with cement and lime. *Quarterly Journal of Engineering Geology and Hydrogeology*, 18(2): 173-180.
- Al-mulali, M.Z., Awang, H., Khalil, H.A., and Aljoumaily, Z.S. (2015). The incorporation of oil palm ash in concrete as a means of recycling: A review. *Cement and Concrete Composites*, 55: 129-138.
- Al Tabbaa, A., and Evans, C. (2003). Deep soil mixing in the UK: geoenvironmental research and recent applications. *Land Contamination and Reclamation*, 11: 1-14.
- Alhassan, M. (2008). Potentials of rice husk ash for soil stabilization. Assumption University Journal of Technology, 11(4): 246-250.
- Ali, F.H., Adnan, A., and Choy, C.K. (1992). Use of rice husk ash to enhance lime treatment of soil. *Canadian Geotechnical Journal*, 29(5): 843-852.
- Amu, O., Adeyeri, J., Haastrup, A., and Eboru, A. (2008). Effects of palm kernel shells in lateritic soil for asphalt stabilization. *Research Journal of Environmental Sciences*, 2(2): 132-138.
- Andersland, O., and Khattak, A. (1979). Shear strength of kaolinite/fiber soil mixtures. Proceeding of 1st International Conference on Soil Reinforcement, paris, France.
- Ariffin, M., Bhutta, M., Hussin, M., Mohd Tahir, M., and Aziah, N. (2013). Sulfuric acid resistance of blended ash geopolymer concrete. *Construction and Building Materials*, 43: 80-86.
- Awal, A., and Abubakar, S.I. (2011). Properties of concrete containing high volume palm oil fuel ash: ashort-term investigation. *Malaysian Journal of Civil Engineering*, 23(2): 164-176.

- Awal, A., and Hussin, M.W. (2011). Effect of palm oil fuel ash in controlling heat of hydration of concrete. Proceeding of the 12th East Asia-Pacific Conference on Structural Engineering and Construction, Hong Kong.
- Awal, A., and Nguong, S.K. (2010). A short-term investigation on high volume palm oil fuel ash (POFA) Concrete. Proceedings of the 35th Conference on our World in Concrete and Structure, Singapore.
- Bakharev, T., Sanjayan, J.G., and Cheng, Y. (1999). Alkali activation of Australian slag cements. *Cement and Concrete Research*, 29(1): 113-120.
- Basha, E., Hashim, R., Mahmud, H., and Muntohar, A. (2005). Stabilization of residual soil with rice husk ash and cement. *Construction and Building Materials*, 19(6): 448-453.
- Becker, E.B., Folliard, K.J., Gilbert, R.B., and Rathje, E.M. (2005). *Mechanical* response of fiber-reinforced soil. PHD Thesis, University of Texas.
- Bell, F. (1996). Lime stabilization of clay minerals and soils. *Engineering geology*, 42(4): 223-237.
- Bergado, D., Anderson, L., Miura, N., and Balasubramaniam, A. (1996). *Lime/cement deep mixing method*. Proceeding of Soft Ground Improvement in Lowland and Environments, Rotterdam: A.A.Balkelma.
- Bernal, S.A., Mejía de Gutiérrez, R., and Provis, J.L. (2012). Engineering and durability properties of concretes based on alkali-activated granulated blast furnace slag/metakaolin blends. *Construction and Building Materials*, 33: 99-108.
- Bouassida, M., and Porbaha, A. (2004). Ultimate bearing capacity of soft clays reinforced by a group of columns-application to a deep mixing technique. *Soils and Foundations*, 44(3): 91-101.
- Broms, B. (2000). *Lime and lime/columns. summary and visions*. Proceedings of the 4th International Conference on Ground Improvement Geosystems, Helsinki, Finland.
- Broms, B. (2003). Deep soil stabilization: design and construction of lime and lime/cement columns. *Royal Institute of Technology, Stockholm, Sweden*.

- Brooks, R.M. (2009). Soil stabilization with fly ash and rice husk ash. *International Journal of Research and Reviews in Applied Sciences*, 1(3): 209-217.
- Brown, O.R., Yusof, M.B., Salim, M.R., and Ahmed, K. (2011). *Compaction* parameters of kaolin clay modified with palm oil fuel ash as landfill liner. Proceeding of Clean Energy and Technology (CET), Kuala lumpur.
- Bruce, D.A. (2001). Practitioner's guide to the deep mixing method. *Proceedings of the ICE-Ground Improvement*, 5(3): 95-100.
- Buchwald, A. (2006). Geopolymer significance for the precast industry. *Betonwerk und Fertigteil-Technik*, 72(7): 170-183.
- Cai, Y., Shi, B., Gao, W., Chen, F.J., and Tang, C.s. (2006). Experimental study on engineering properties of fibre-lime treated soils. *Chinese Journal of Geotechnical Engineering*, 28(10): 1283-1287.
- Campbell, D.H., and Folk, R. (1991). The ancient Egyptian pyramids-concrete or rock. *Concrete International*, 13(8): 28-30.
- Chan, C.M. (2006). A laboratory investigation of shear wave velocity in stabilised soft soils. PHD Thesis, University of Sheffield.
- Chauhan, M.S., Mittal, S., and Mohanty, B. (2008). Performance evaluation of silty sand subgrade reinforced with fly ash and fibre. *Geotextiles and Geomembranes*, 26(5): 429-435.
- Chen, L., and Lin, D.F. (2009). Stabilization treatment of soft subgrade soil by sewage sludge ash and cement. *Journal of Hazardous Materials*, 162(1): 321-327.
- Cheng, T., and Chiu, J. (2003). Fire-resistant geopolymer produced by granulated blast furnace slag. *Minerals Engineering*, 16(3): 205-210.
- Chew, S., Kamruzzaman, A., and Lee, F. (2004). Physicochemical and engineering behavior of cement treated clays. *Journal of geotechnical and geoenvironmental engineering*, 130(7): 696-706.

- Chiew, Y.L., Iwata, T., and Shimada, S. (2011). System analysis for effective use of palm oil waste as energy resources. *Biomass and Bioenergy*, 35(7): 2925-2935.
- Chindaprasirt, P., Chareerat, T., and Sirivivatnanon, V. (2007a). Workability and strength of coarse high calcium fly ash geopolymer. *Cement and Concrete Composites*, 29(3): 224-229.
- Chindaprasirt, P., Homwuttiwong, S., and Jaturapitakkul, C. (2007b). Strength and water permeability of concrete containing palm oil fuel ash and rice husk-bark ash. *Construction and Building Materials*, 21(7): 1492-1499.
- Clark, J. (1998). Future of automotive body materials: steel, aluminum and polymer composites. *Hoogovens Technology, Massachusetts Institute of Technology, Cambridge, MA*.
- Consoli, N.C., de Moraes, R.R., and Festugato, L. (2013). Variables controlling strength of fibre-reinforced cemented soils. *Proceedings of the ICE-Ground Improvement*, 166(4): 221-232.
- Correia, A.A., Oliveira, P.J.V., and Custódio, D.G. (2015). Effect of polypropylene fibres on the compressive and tensile strength of a soft soil, artificially stabilised with binders. *Geotextiles and Geomembranes*, 43(2): 97-106.
- Cristelo, N., Cunha, V.M., Dias, M., Gomes, A.T., Miranda, T., and Araújo, N. (2015a). Influence of discrete fibre reinforcement on the uniaxial compression response and seismic wave velocity of a cement-stabilised sandy-clay. *Geotextiles and Geomembranes*, 43(1): 1-13.
- Cristelo, N., Glendinning, S., Fernandes, L., and Pinto, A.T. (2012a). Effect of calcium content on soil stabilisation with alkaline activation. *Construction and Building Materials*, 29: 167-174.
- Cristelo, N., Glendinning, S., Fernandes, L., and Pinto, A.T. (2013). Effects of alkalineactivated fly ash and Portland cement on soft soil stabilisation. *Acta Geotechnica*, 8(4): 395-405.
- Cristelo, N., Glendinning, S., Miranda, T., Oliveira, D., and Silva, R. (2012b). Soil stabilisation using alkaline activation of fly ash for self compacting rammed earth construction. *Construction and Building Materials*, 36: 727-735.

- Cristelo, N., Glendinning, S., and Pinto, A.T. (2011). Deep soft soil improvement by alkaline activation. *Proceedings of the ICE-Ground Improvement*, 164(2): 73-82.
- Cristelo, N., Miranda, T., Oliveira, D.V., Rosa, I., Soares, E., Coelho, P., and Fernandes, L. (2015b). Assessing the production of jet mix columns using alkali activated waste based on mechanical and financial performance and CO 2 (eq) emissions. *Journal of Cleaner Production*.
- Cwirzen, A., Provis, J.L., Penttala, V., and Habermehl-Cwirzen, K. (2014). The effect of limestone on sodium hydroxide-activated metakaolin-based geopolymers. *Construction and Building Materials*, 66: 53-62.
- Davidovits, J. (1979). SPE PATEC '79. Society of Plastic Engineering, Brookfield Center, USA.
- Davidovits, J. (1984). X-ray analysis and X-ray diffraction of casing stones from the pyramids of Egypt, and the limestone of the associated quarries. Paper Presented at Science in Egyptology Symposia, Manchester, England.
- Davidovits, J. (1988). Geopolymer chemistry and properties. Proceeding of 1st European Conference on Soft Mineralurgy (Geopolymere '88), Compiegne, Paris.
- Davidovits, J. (1991). Geopolymers. Journal of Thermal Analysis and Calorimetry, 37(8): 1633-1656.
- Davidovits, J. (1994). *Properties of geopolymer cements*. Proceeding of First International Conference on Alkaline Cements and Concretes, Kiev, Ukraine.

Davidovits, J. (2005). Geopolymer, Green Chemistry and Sustainable Development Solutions:Proceedings of the World Congress Geopolymer: Geopolymer Institute Press.

- Davidovits, J., and Sawyer, J.L. (1985). Early high-strength mineral polymer: U.S Patent.
- De Aza, P., Guitian, F., and De Aza, S. (1994). Bioactivity of wollastonite ceramics: in vitro evaluation. *Scripta metallurgica et materialia*, 31(8): 1001-1005.

- Degirmenci, N., Okucu, A., and Turabi, A. (2007). Application of phosphogypsum in soil stabilization. *Building and environment*, 42(9): 3393-3398.
- Dermatas, D., and Meng, X. (2003). Utilization of fly ash for stabilization/solidification of heavy metal contaminated soils. *Engineering Geology*, 70(3): 377-394.
- Detphan, S., and Chindaprasirt, P. (2009). Preparation of fly ash and rice husk ash geopolymer. *International Journal of Minerals, Metallurgy and Materials*, 16(6): 720-726.
- Dexter, A., and Kroesbergen, B. (1985). Methodology for determination of tensile strength of soil aggregates. *Journal of Agricultural Engineering Research*, 31(2): 139-147.
- Dey, V., Kachala, R., Bonakdar, A., and Mobasher, B. (2015). Mechanical properties of micro and sub-micron wollastonite fibers in cementitious composites. *Construction and Building Materials*, 82: 351-359.
- Diaz, E., Allouche, E., and Eklund, S. (2010). Factors affecting the suitability of fly ash as source material for geopolymers. *Fuel*, 89(5): 992-996.
- Ding, L., Ma, L., Luo, H., Yu, M., and Wu, X. (2011). Wavelet Analysis for tunnelinginduced ground settlement based on a stochastic model. *Tunnelling and Underground Space Technology*, 26(5): 619-628.
- Druss, D.L. (2002). Guidelines for Design and Installation of Soil-Cement Stabilization. *Geotechnical Special Publication*, 1(3): 527-539.
- Duxson, P., Fernández-Jiménez, A., Provis, J.L., Lukey, G.C., Palomo, A., and Van Deventer, J. (2007a). Geopolymer technology: the current state of the art. *Journal of materials science*, 42(9): 2917-2933.
- Duxson, P., Mallicoat, S., Lukey, G., Kriven, W., and Van Deventer, J. (2007b). The effect of alkali and Si/Al ratio on the development of mechanical properties of metakaolin-based geopolymers. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 292(1): 8-20.
- Duxson, P., Provis, J.L., Lukey, G.C., Mallicoat, S.W., Kriven, W.M., and Van Deventer, J.S. (2005). Understanding the relationship between geopolymer

composition, microstructure and mechanical properties. *Colloids and Surfaces* A: Physicochemical and Engineering Aspects, 269(1): 47-58.

- Dwivedi, A., and Jain, M.K. (2014). Fly ash-waste management and overview: A Review. Recent Research in Science and Technology, 6(1): 11-27.
- Edil, T.B., Acosta, H.A., and Benson, C.H. (2006). Stabilizing soft fine-grained soils with fly ash. *Journal of materials in civil engineering*, 18(2): 283-294.
- Escalante Garcia, J., Campos-Venegas, K., Gorokhovsky, A., and Fernandez, A. (2006). Cementitious composites of pulverised fuel ash and blast furnace slag activated by sodium silicate: effect of Na2O concentration and modulus. *Advances in applied ceramics*, 105(4): 201-208.
- Estabragh, A., Namdar, P., and Javadi, A. (2012). Behavior of cement-stabilized clay reinforced with nylon fiber. *Geosynthetics International*, 19(1): 85-92.
- Fang, Y., Chung, Y., Yu, F., and Chen, T. (2001). Properties of soil-cement stabilised with deep mixing method. *Ground Improvement*, 5(2): 69-74.
- Farouk, A., and Shahien, M.M. (2013). Ground improvement using soil-cement columns: Experimental investigation. *Alexandria Engineering Journal*, 52(4): 733-740.
- Fatahi, B., Khabbaz, H., and Fatahi, B. (2012). Mechanical characteristics of soft clay treated with fibre and cement. *Geosynthetics International*, 19(3): 252-262.
- Fawer, M., Concannon, M., and Rieber, W. (1999). Life cycle inventories for the production of sodium silicates. *The International Journal of Life Cycle* Assessment, 4(4): 207-212.
- Felt, E.J. (1955). Factors influencing physical properties of soil-cement mixtures. *Highway Research Board Bulletin*, 5(108): 170-178.
- Foo, K., and Hameed, B. (2009). Value-added utilization of oil palm ash: A superior recycling of the industrial agricultural waste. *Journal of hazardous materials*, 172(2): 523-531.

- Gandhi, K. (2012). Expansive Soil Stabilization Using Bagasse Ash. International Journal of Engineering, 1(5): 20-27.
- Gartner, E. (2004). Industrially interesting approaches to "low-CO2" cements. *Cement and Concrete research*, 34(9): 1489-1498.
- Gjorv, O.E., and Sakai, K. (2003). Concrete technology for a sustainable development in the 21st century. New York: E & FN Spon Press.

Glukhovsky, V. (1959). Soil silicates. Gostroiizdat Publish. Kiev, USSR.

- Glukhovsky, V. (1965). Soil silicates. Their properties, technology and manufacturing and fields of application. PHD Thesis, Civil Engineering Institute of Kiev.
- Glukhovsky, V., Rostovskaja, G., and Rumyna, G. (1980). *High strength slag-alkaline cements*. Proceedings of the 7th International Congress on the Chemistry of Cement, Paris.
- Goda, Y. (2002). Research Group of Marine Observation Data Analysis and Application. *Coastal Wave Observation, Coastal Development Institute of Technology*, 4: 212-235.
- Gray, D.H., and Al-Refeai, T. (1986). Behavior of fabric-versus fiber-reinforced sand. *Journal of Geotechnical Engineering*, 112(8): 804-820.
- Gray, D.H., and Ohashi, H. (1983). Mechanics of fiber reinforcement in sand. *Journal* of Geotechnical Engineering, 109(3): 335-353.
- Grutzeck, M., Kwan, S., and Dicola, M. (2004). Zeolite formation in alkali-activated cementitious systems. *Cement and concrete research*, 34(6): 949-955.
- Gullu, H., and Hazirbaba, K. (2010). Unconfined compressive strength and postfreeze-thaw behavior of fine-grained soils treated with geofiber and synthetic fluid. *Cold regions science and technology*, 62(2): 142-150.
- Habert, G., D'Espinose de Lacaillerie, J., and Roussel, N. (2011). An environmental evaluation of geopolymer based concrete production: reviewing current research trends. *Journal of cleaner production*, 19(11): 1229-1238.

- Harichane, K., Ghrici, M., and Kenai, S. (2012). Effect of the combination of lime and natural pozzolana on the compaction and strength of soft clayey soils: a preliminary study. *Environmental earth science*, 66(8): 2197-2205.
- Harichane, K., Ghrici, M., Kenai, S., and Grine, K. (2011). Use of Natural Pozzolana and Lime for Stabilization of Cohesive Soils. *Geotechnical and Geological Engineering*, 29(5): 759-769.
- Heah, C., Kamarudin, H., Mustafa Al Bakri, A., Bnhussain, M., Luqman, M., Khairul Nizar, I., and Ruzaidi, C. (2012). Study on solids-to-liquid and alkaline activator ratios on kaolin-based geopolymers. *Construction and Building Materials*, 35: 912-922.
- Hejazi, S.M., Sheikhzadeh, M., Abtahi, S.M., and Zadhoush, A. (2012). A simple review of soil reinforcement by using natural and synthetic fibers. *Construction and Building Materials*, 30: 100-116.
- Hendriks, C.A., Worrell, E., De Jager, D., Blok, K., and Riemer, P. (1998). *Emission* reduction of greenhouse gases from the cement industry. Proceedings of the 4th International Conference on Greenhouse Gas Control Technologies, Interlaken, Switzerland.
- Higgins, D., Kinuthia, J., and Wild, S. (1998). Soil stabilization using lime-activated ground granulated blast furnace slag. *ACI Special Publication*, 178: 1057-1074.
- Horpibulsuk, S., Phetchuay, C., and Chinkulkijniwat, A. (2011). Soil stabilization by calcium carbide residue and fly ash. *Journal of materials in civil engineering*, 24(2): 184-193.
- Hossain, K., and Mol, L. (2011). Some engineering properties of stabilized clayey soils incorporating natural pozzolans and industrial wastes. *Construction and Building Materials*, 25(8): 3495-3501.
- Huat, B.B., Maail, S., and Mohamed, T.A. (2005). Effect of chemical admixtures on the engineering properties of tropical peat soils. *American Journal of Applied Sciences*, 2(7): 1113.
- Hussin, M., Ismail, M.A., Budiea, A., and Muthusamy, K. (2009). Durability of high strength concrete containing palm oil fuel ash of different fineness. *Malaysian Journal of Civil Engineering*, 21(2): 180-194.

- Ismail, M., and Keok, L.S. (2010). Fabrication of bricks from paper sludge and palm oil fuel ash. *Concrete Research Letters*, 1(2): 60-66.
- Janz, M., and Johansson, S. (2002). The function of different binding agents in deep stabilization. *Swedish Deep Stabilization Research Centre, Report*, 9: 1-35.
- Jegandan, S., Liska, M., Osman, A.A., and Al-Tabbaa, A. (2010). Sustainable binders for soil stabilisation. *Proceedings of the ICE-Ground Improvement*, 163(1): 53-61.
- Jo, A.N., Hafez, M., and Norbaya, S. (2011). Study of bearing capacity of lime-cement columns with pulverized fuel ash for soil stabilization using laboratory model. *Electronical Journal of Geotechnical Engineering*, 16: 1595-1605.
- Johari, M., Zeyad, A., Muhamad Bunnori, N., and Ariffin, K. (2012). Engineering and transport properties of high-strength green concrete containing high volume of ultrafine palm oil fuel ash. *Construction and Building Materials*, 30: 281-288.
- Juenger, M., Winnefeld, F., Provis, J., and Ideker, J. (2011). Advances in alternative cementitious binders. *Cement and Concrete Research*, 41(12): 1232-1243.
- Kalla, P., Misra, A., Gupta, R.C., Csetenyi, L., Gahlot, V., and Arora, A. (2013). Mechanical and durability studies on concrete containing wollastonite–fly ash combination. *Construction and Building Materials*, 40: 1142-1150.
- Kamon, M., and Nontananandh, S. (1991). Combining industrial wastes with lime for soil stabilization. *Journal of Geotechnical Engineering*, 117(1): 1-17.
- Kaniraj, S.R., and Havanagi, V.G. (2001). Behavior of cement-stabilized fiberreinforced fly ash-soil mixtures. *Journal of Geotechnical and Geoenvironmental Engineering*, 127(7): 574-584.
- Kavak, A., Bilgen, G., and Capar, O.F. (2011). Using ground granulated blast furnace slag with seawater as soil additives in lime-clay stabilization. *Journal of ASTM International*, 8(7).
- Kawasaki, T., Saitoh, S., Suzuki, Y., and Babasaki, R. (1984). *Deep mixing method using cement slurry as hardening agent*. Proceeding of Seminar on Soil Improvement and Construction Techniques in Soft Ground, Singapore.

- Kawasaki, T., and Suzuki, Y. (1981). On the deep mixing chemical mixing method using cement hardening agent. *Takenaka, Technical Research Report*, 26: 13-42.
- Kawasaki, T., Suzuki, Y., and Suzuki, Y. (1981). On the deep mixing chemical mixing method using cement hardening agent. *Takenaka, Technical Research Report*, 26: 13-42.
- Khale, D., and Chaudhary, R. (2007). Mechanism of geopolymerization and factors influencing its development: a review. *Journal of Materials Science*, 42(3): 729-746.
- Kim, Y., and Worrell, E. (2002). CO2 emission trends in the cement industry: An international comparison. *Mitigation and Adaptation Strategies for Global Change*, 7(2): 115-133.
- Kirsch, K., and Bell, A. (2012). Ground improvement. Boca Raton: CRC Press.
- Kitazume, M. (1996). *Bearing capacity of improved ground with column type DMM*. Proceeding of the 2nd International Conference on Ground Improvement Geosystems, Tokyo.
- Kitazume, M. (2002). *The Deep Mixing Method-Principle, Design and Construction*. Japan: Balkema Press.
- Kitazume, M., Okano, K., and Miyajima, S. (2000). Centrifuge model tests on failure envelope of column type deep mixing method improved ground. *Soils and Foundations*, 40(4): 43-55.

Kitazume, M., and Terashi, M. (2013). The deep mixing method. Leiden: CRC Press.

- Kolias, S., Kasselouri-Rigopoulou, V., and Karahalios, A. (2005). Stabilisation of clayey soils with high calcium fly ash and cement. *Cement and Concrete Composites*, 27(2): 301-313.
- Komnitsas, K., and Zaharaki, D. (2007). Geopolymerisation: a review and prospects for the minerals industry. *Minerals Engineering*, 20(14): 1261-1277.

- Kumar, A., Walia, B.S., and Bajaj, A. (2007). Influence of fly ash, lime, and polyester fibers on compaction and strength properties of expansive soil. *Journal of materials in civil engineering*, 19(3): 242-248.
- Kumar, S., Kumar, R., and Mehrotra, S. (2010). Influence of granulated blast furnace slag on the reaction, structure and properties of fly ash based geopolymer. *Journal of materials science*, 45(3): 607-615.
- Lecomte, I., Henrist, C., Liegeois, M., Maseri, F., Rulmont, A., and Cloots, R. (2006). (Micro)-structural comparison between geopolymers, alkali-activated slag cement and Portland cement. *Journal of the European Ceramic Society*, 26(16): 3789-3797.
- Lee, W., and Van Deventer, J. (2002). The effects of inorganic salt contamination on the strength and durability of geopolymers. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 211(2): 115-126.
- Li, C., Sun, H., and Li, L. (2010). A review: The comparison between alkali-activated slag (Si+Ca) and metakaolin (Si+Al) cements. *Cement and Concrete Research*, 40(9): 1341-1349.
- Lin, T., Jia, D., He, P., and Wang, M. (2010). In situ crack growth observation and fracture behavior of short carbon fiber reinforced geopolymer matrix composites. *Materials Science and Engineering*, 527(9): 2404-2407.
- Lorenzo, G.A., and Bergado, D.T. (2006). Fundamental characteristics of cementadmixed clay in deep mixing. *Journal of materials in civil engineering*, 18(2): 161-174.
- Lothenbach, B., Scrivener, K., and Hooton, R. (2011). Supplementary cementitious materials. *Cement and Concrete Research*, 41(12): 1244-1256.
- Low, N.M., and Beaudoin, J. (1994a). Stability of portland cement-based binders reinforced with natural wollastonite micro-fibres. *Cement and Concrete Research*, 24(5): 874-884.
- Low, N.M., and Beaudoin, J.J. (1993). The effect of wollastonite micro-fibre aspect ratio on reinforcement of Portland cement-based binders. *Cement and Concrete Research*, 23(6): 1467-1479.

- Low, N.M., and Beaudoin, J.J. (1994b). The flexural toughness and ductility of Portland cement-based binders reinforced with wollastonite micro-fibres. *Cement and Concrete Research*, 24(2): 250-258.
- MacKenzie, K.J., Brew, D., Fletcher, R., Nicholson, C., Vagana, R., and Schmücker, M. (2006). Advances in understanding the synthesis mechanisms of new geopolymeric materials. *Ceramic Transactions*, 195(3): 185-199.
- Madlool, N., Saidur, R., Hossain, M., and Rahim, N. (2011). A critical review on energy use and savings in the cement industries. *Renewable and Sustainable Energy Reviews*, 15(4): 2042-2060.
- Madurwar, M.V., Ralegaonkar, R.V., and Mandavgane, S.A. (2013). Application of agro-waste for sustainable construction materials: A review. *Construction and Building Materials*, 38: 872-878.
- Maher, M., and Ho, Y. (1994). Mechanical properties of kaolinite/fiber soil composite. Journal of Geotechnical Engineering, 120(8): 1381-1393.
- Maher, M.H., and Gray, D.H. (1990). Static response of sands reinforced with randomly distributed fibers. *Journal of Geotechnical Engineering*, 116(11): 1661-1677.
- Maliakal, T., and Thiyyakkandi, S. (2013). Influence of randomly distributed coir fibers on shear strength of clay. *Geotechnical and Geological Engineering*, 31(2): 425-433.
- Mamlouk, M.S., Zaniewski, J.P., and Peng, X. (2006). *Materials for civil and construction engineers*. California: Addison-Wesley Press.

Mansour, A., Srebric, J., and Burley, B. (2007). Development of straw-cement composite sustainable building material for low-cost housing in Egypt. *Journal of Applied Sciences Research*, 3(11): 1571-1580.

Marandi, S., Bagheripour, M., Rahgozar, R., and Zare, H. (2008). Strength and ductility of randomly distributed palm fibers reinforced silty-sand soils. *American Journal of Applied Sciences*, 5(3): 209-216.

- Massarsch, K., and Topolnicki, M. (2005). *Regional Report: European practice of soil mixing technology*. Proceeding of International Conference on Deep Mixing– Best Practice and Recent Advances, Stockholm.
- Matthews, H.D., Gillett, N.P., Stott, P.A., and Zickfeld, K. (2009). The proportionality of global warming to cumulative carbon emissions. *Nature*, 459(7248): 829-832.
- McGuire, M., Templeton, E., and Filz, G. (2012). Stability analyses of a floodwall with deep-mixed ground improvement at Orleans Avenue Canal, New Orleans. *Geotechnical and Geological Engineering*, 211(7): 199-209.
- McLellan, B.C., Williams, R.P., Lay, J., Van Riessen, A., and Corder, G.D. (2011). Costs and carbon emissions for geopolymer pastes in comparison to ordinary portland cement. *Journal of cleaner production*, 19(9): 1080-1090.
- Mijarsh, M., Johari, M., and Ahmad, Z. (2014). Synthesis of geopolymer from large amounts of treated palm oil fuel ash: Application of the Taguchi method in investigating the main parameters affecting compressive strength. *Construction and Building Materials*, 52: 473-481.
- Miura, N., Horpibulsuk, S., and Nagaraj, T. (2001). Engineering behavior of cement stabilized clay at high water content. *Soils and Foundations*, 41(5): 33-45.
- Nalbantoğlu, Z. (2004). Effectiveness of class C fly ash as an expansive soil stabilizer. *Construction and Building Materials*, 18(6): 377-381.
- Ndoke, P.N. (2006). Performance of Palm Kernel shells as a partial replacement for coarse aggregate in Asphalt concrete. *Leonardo Electronic Journal of Practices and Technologies*, 5(9): 145-152.
- Nematollahi, B., Sanjayan, J., and Shaikh, F.U.A. (2014). Comparative deflection hardening behavior of short fiber reinforced geopolymer composites. *Construction and Building Materials*, 70: 54-64.
- Ng, T.S., Voo, Y.L., and Foster, S.J. (2012). *Sustainability with ultra-high performance and geopolymer concrete construction*. Innovative Materials and Techniques in Concrete Construction (pp. 81-100). Carfu: Springer publishers.

- Okumura, T. (1996). *Deep mixing method of Japan*. proceeding of the 2nd International Conference on Ground Improvement Geosystem, Tokyo.
- Pacheco-Torgal, F., Castro-Gomes, J., and Jalali, S. (2008). Alkali-activated binders: A review: Part 1. Historical background, terminology, reaction mechanisms and hydration products. *Construction and Building Materials*, 22(7): 1305-1314.
- Palomo, A., and Glasser, F. (1992). Chemically-bonded cementitious materials based on metakaolin. *British Ceramic Transactions*, 91(4): 107-112.
- Palomo, A., Grutzeck, M., and Blanco, M. (1999). Alkali-activated fly ashes: a cement for the future. *Cement and Concrete Research*, 29(8): 1323-1329.
- Pan, Z., Li, D., Yu, J., and Yang, N. (2003). Properties and microstructure of the hardened alkali-activated red mud-slag cementitious material. *Cement and Concrete Research*, 33(9): 1437-1441.
- Papadakis, V., and Tsimas, S. (2002). Supplementary cementing materials in concrete: Part I: efficiency and design. Cement and Concrete Research, 32(10): 1525-1532.
- Park, S.-S. (2011). Unconfined compressive strength and ductility of fiber-reinforced cemented sand. *Construction and Building Materials*, 25(2): 1134-1138.
- Park, S.S. (2009). Effect of fiber reinforcement and distribution on unconfined compressive strength of fiber-reinforced cemented sand. *Geotextiles and Geomembranes*, 27(2): 162-166.
- Park, S.S., Kim, Y.S., Choi, S.G., and Shin, S.E. (2008). Unconfined compressive strength of cemented sand reinforced with short fibers. *Journal of the Korean Society of Civil Engineers*, 28(4C): 213-220.
- Phair, J., and Van Deventer, J. (2001). Effect of silicate activator pH on the leaching and material characteristics of waste-based inorganic polymers. *Minerals Engineering*, 14(3): 289-304.
- Phair, J., and Van Deventer, J. (2002). Characterization of fly-ash-based geopolymeric binders activated with sodium aluminate. *Industrial & engineering chemistry research*, 41(17): 4242-4251.

- Pincus, H., Maher, M., and Ho, Y. (1993). Behavior of fiber-reinforced cemented sand under static and cyclic loads. *Geotechnical and Geological Engineering*, 3(5): 110-127.
- Porbaha, A. (1998). State of the art in deep mixing technology. Part I: Basic concepts and overview. *Ground Improvement*, 2(2): 81-92.
- Porbaha, A., Shibuya, S., and Kishida, T. (2000). State of the art in deep mixing technology. Part III: geomaterial characterization. *Proceedings of the ICE-Ground Improvement*, 4(3): 91-110.
- Prabakar, J., and Sridhar, R. (2002). Effect of random inclusion of sisal fibre on strength behaviour of soil. *Construction and Building Materials*, 16(2): 123-131.
- Provis, J., Duxson, P., Van Deventer, J., and Lukey, G. (2005). The role of mathematical modelling and gel chemistry in advancing geopolymer technology. *Chemical Engineering Research and Design*, 83(7): 853-860.
- Prusinski, J.R., and Bhattacharja, S. (1999). Effectiveness of Portland cement and lime in stabilizing clay soils. *Transportation Research Record: Journal of the Transportation Research Board*, 1652(1): 215-227.
- Purdon, A. (1940). The action of alkalis on blast-furnace slag. *Journal of the Society of Chemical Industry*, 59: 191-202.
- Rahmat, M.N., and Kinuthia, J.M. (2011). Effects of mellowing sulfate-bearing clay soil stabilized with wastepaper sludge ash for road construction. *Engineering Geology*, 117(3): 170-179.
- Raju, V., Abdullah, A., and Arulrajah, A. (2003). Ground treatment using dry deep soil mixing for a railway embankment in Malaysia. Proceedings of the 2nd Conference on Advances in Soft Soil Engineering and Technology, Kuala Lumpur.
- Ramesh, H., Krishna, K.M., and Mamatha, H. (2010). Compaction and strength behavior of lime-coir fiber treated Black Cotton soil. *Geomechanic Engineering*, 2(1): 19-28.

- Rangan, B.V. (2008). Fly ash-based geopolymer concrete. *Your Building Administrator*, 2(3): 110-118.
- Ranjbar, N., Behnia, A., Alsubari, B., Birgani, P.M., and Jumaat, M.Z. (2015). Durability and Mechanical Properties of Self-compacting Concrete Incorporating Palm Oil Fuel Ash. *Journal of Cleaner Production*.
- Ranjbar, N., Mehrali, M., Behnia, A., Alengaram, U.J., and Jumaat, M.Z. (2014). Compressive strength and microstructural analysis of fly ash/palm oil fuel ash based geopolymer mortar. *Materials & Design*, 59: 532-539.
- Ransinchung, G., Kumar, B., and Kumar, V. (2009). Assessment of water absorption and chloride ion penetration of pavement quality concrete admixed with wollastonite and microsilica. *Construction and Building Materials*, 23(2): 1168-1177.
- Roy, D., and Jigang, W. (1997). Concrete chemical degradation: Ancient analogues and modern evaluation. *Mechanisms of chemical degradation*, 5(3): 14-27.
- Roy, D.M., and Silsbee, M. (1991). Alkali activated cementitious materials: an overview. Proceedings of Materials Research Society (MRS), Paris.
- Sabat, A.K. (2012). Stabilization of expansive soil using waste ceramic dust. *Electronic Journal of Geotechnical Engineering*, 17: 3915-3926.
- Sabih, O., Shafique, M.J., and Hussain, R.R. (2011). *Methods of Soil Stabilization*: CRC press.
- Sagoe-Crentsil, K., and Weng, L. (2007). Dissolution processes, hydrolysis and condensation reactions during geopolymer synthesis: Part II. High Si/Al ratio systems. *Journal of materials science*, 42(9): 3007-3014.
- Saitoh, S. (1988). *Experimental study of engineering properties of cement improved ground by the deep mixing method*. PhD Thesis, Nihon University.
- Saitoh, S., Suzuki, Y., and Shirai, K. (1985). Hardening of soil improved by deep mixing method. Proceedings of 11th International Conference on Soil Mechanics and Foundation Engineering, San Francisco.

- Sargent, P., Hughes, P.N., Rouainia, M., and White, M.L. (2013). The use of alkali activated waste binders in enhancing the mechanical properties and durability of soft alluvial soils. *Engineering Geology*, 152(1): 96-108.
- Seco, A., García, B., Prieto, E., Ramirez, F., Miqueleiz, L., Urmeneta, P., and Oroz, V. (2012). Types of Waste for the Production of Pozzolanic Materials-A Review: Intech Press.
- Seco, A., Ramírez, F., Miqueleiz, L., García, B., and Prieto, E. (2011). The use of nonconventional additives in Marls stabilization. *Applied Clay Science*, 51(4): 419-423.
- Shaikh, F.U.A. (2013). Review of mechanical properties of short fibre reinforced geopolymer composites. *Construction and Building Materials*, 43: 37-49.
- Sheeran, D., and Krizek, R. (1971). Preparation of homogeneous soil samples by slurry consolidation. *Journal of Materials*, 6(2): 356-&.
- Shi, C., Jiménez, A.F., and Palomo, A. (2011). New cements for the 21st century: the pursuit of an alternative to Portland cement. *Cement and Concrete Research*, 41(7): 750-763.
- Silva, F., and Thaumaturgo, C. (2003). Fibre reinforcement and fracture response in geopolymeric mortars. Fatigue & Fracture of Engineering Materials & Structures, 26(2): 167-172.
- Singh, H., and Bagra, M. (2013). Improvement in CBR value of soil reinforced with Jute Fiber. International Journal of Innovative Research in Science, Engineering and Technology, 2(8): 3447-3452.
- Sivakumar Babu, G., and Vasudevan, A. (2008). Strength and stiffness response of coir fiber-reinforced tropical soil. *Journal of materials in civil engineering*, 20(9): 571-577.
- Sobolev, K., and Arikan, M. (2002). High volume mineral additive for eco-cement. *American Ceramic Society Bulletin*, 81(1): 39-43.
- Soliman, A., and Nehdi, M. (2011). Effect of Natural Wollastonite Microfibers on Early-Age Behavior of UHPC. *Journal of Materials in Civil Engineering*, 24(7): 816-824.

- Song-Yu, L., Yao-Lin, Y., and Zhi-Duo, Z. (2008). Comparison tests on field bidirectional deep mixing column for soft ground improvement in expressway. *Chinese Journal of Rock Mechanics and Engineering*, 27(11): 2272-2280.
- Songpiriyakij, S., Kubprasit, T., Jaturapitakkul, C., and Chindaprasirt, P. (2010). Compressive strength and degree of reaction of biomass and fly ash-based geopolymer. *Construction and Building Materials*, 24(3): 236-240.
- Sreekanth Chakradhar, R., Nagabhushana, B., Chandrappa, G., Ramesh, K., and Rao, J. (2006). Solution combustion derived nanocrystalline macroporous wollastonite ceramics. *Materials chemistry and Physics*, 95(1): 169-175.
- Standard, B. BS 1377-2: 1990. Methods of test for: Soils for civil engineering purposes-Part, 2.
- Standard, B. (1990). 1377. Methods of Test for Soils and Civil Engineering Purposes. British Standards Institution, London.
- Stevenson, M., and Sagoe-Crentsil, K. (2005). Relationship between composition, structure and strength of inorganic polymers: part 1—metakaolin-derived inorganic polymers. *Journal of Material Science*, 40: 2023-2036.
- Sukontasukkul, P., and Jamsawang, P. (2012). Use of steel and polypropylene fibers to improve flexural performance of deep soil–cement column. *Construction and Building Materials*, 29: 201-205.
- Swanepoel, J., and Strydom, C. (2002). Utilisation of fly ash in a geopolymeric material. *Applied Geochemistry*, 17(8): 1143-1148.
- Tang, C., Shi, B., Gao, W., Chen, F., and Cai, Y. (2007). Strength and mechanical behavior of short polypropylene fiber reinforced and cement stabilized clayey soil. *Geotextiles and Geomembranes*, 25(3): 194-202.
- Tangchirapat, W., Saeting, T., Jaturapitakkul, C., Kiattikomol, K., and Siripanichgorn, A. (2007). Use of waste ash from palm oil industry in concrete. *Waste Management*, 27(1): 81-88.
- Tatsuoka, F., Uchida, K., Imai, K., Ouchi, T., and Kohata, Y. (1997). Properties of cement-treated soils in Trans-Tokyo Bay Highway project. *Proceedings of the ICE-Ground Improvement*, 1(1): 37-57.

- Taylor, M., Tam, C., and Gielen, D. (2006). Energy efficiency and CO2 emissions from the global cement industry. *International Energy Agency*, 5(2): 117-126.
- Temuujin, J., Van Riessen, A., and Williams, R. (2009). Influence of calcium compounds on the mechanical properties of fly ash geopolymer pastes. *Journal of Hazardous Materials*, 167(1): 82-88.
- Terashi, M. (1981). *Ground improved by deep mixing method*. Proceeding of 10th International Conference on Soil Mechanics and Foundation Engineering, Stockholm.
- Terashi, M. (2005). *Keynote lecture: design of deep mixing in infrastructure applications*. International conference on deep mixing best practice and recent advances, Japan.
- Thwe, M.M., and Liao, K. (2002). Effects of environmental aging on the mechanical properties of bamboo–glass fiber reinforced polymer matrix hybrid composites. *Composites Part A: Applied Science and Manufacturing*, 33(1): 43-52.
- Tingle, J.S., and Santoni, R.L. (2003). Stabilization of clay soils with nontraditional additives. *Journal of the Transportation Research Board*, 1819(1): 72-84.
- Topolnicki, M. (2004). In situ soil mixing. Proceedings of the ICE-Ground Improvement, 5(2): 331-428.
- Van Deventer, J., Provis, J., Duxson, P., and Lukey, G. (2007). Reaction mechanisms in the geopolymeric conversion of inorganic waste to useful products. *Journal of hazardous materials*, 139(3): 506-513.
- Van Impe, W.F. (1989). Soil improvement techniques and their evolution. Rotterdam: Balkema Press.
- Van Jaarsveld, J., Van Deventer, J., and Lorenzen, L. (1997). The potential use of geopolymeric materials to immobilise toxic metals: Part I. Theory and applications. *Minerals Engineering*, 10(7): 659-669.
- Van Jaarsveld, J., Van Deventer, J., and Lukey, G. (2002). The effect of composition and temperature on the properties of fly ash-and kaolinite-based geopolymers. *Chemical Engineering Journal*, 89(1): 63-73.

- Van Jaarsveld, J., Van Deventer, J., and Lukey, G. (2003). The characterisation of source materials in fly ash-based geopolymers. *Materials Letters*, 57(7): 1272-1280.
- Vidal, H. (1969). The principle of reinforced earth. Highway research, 5(2): 110-116.
- Wallah, S., and Rangan, B.V. (2006). Low-calcium fly ash-based geopolymer concrete: Long-term properties. *Res. Report-GC2, Curtin University, Australia. pp*: 76-80.
- Wang, H., Li, H., and Yan, F. (2005). Synthesis and mechanical properties of metakaolinite-based geopolymer. Colloids and Surfaces A: Physicochemical and Engineering Aspects, 268(1): 1-6.
- Wang, S.D., Pu, X.C., Scrivener, K., and Pratt, P. (1995). Alkali-activated slag cement and concrete: a review of properties and problems. *Advances in cement Research*, 7(27): 93-102.
- Weil, M., Dombrowski, K., and Buchawald, A. (2009). Life-cycle analysis of geopolymers. Geopolymers, structure, processing, properties and applications. Woodhead Publishing Ltd, 5(3): 194-210.
- Weng, L., and Sagoe-Crentsil, K. (2007). Dissolution processes, hydrolysis and condensation reactions during geopolymer synthesis: Part I—Low Si/Al ratio systems. *Journal of materials science*, 42(9): 2997-3006.
- Wild, S., and Tasong, W. (1999). Influence of ground granulated blastfurnace slag on the sulphate resistance of lime-stabilized kaolinite. *Magazine of Concrete Research*, 51(4): 247-254.
- Winnefeld, F., Leemann, A., Lucuk, M., Svoboda, P., and Neuroth, M. (2010). Assessment of phase formation in alkali activated low and high calcium fly ashes in building materials. *Construction and Building Materials*, 24(6): 1086-1093.
- Xu, H., and Van Deventer, J. (2000). The geopolymerisation of alumino-silicate minerals. *International Journal of Mineral Processing*, 59(3): 247-266.
- Xu, H., and Van Deventer, J.S. (2002). Geopolymerisation of multiple minerals. *Minerals Engineering*, 15(12): 1131-1139.

- Yeung, A.T., Cheng, Y., Tham, L., Au, A.S., So, S.T., and Choi, Y.k. (2007). Field evaluation of a glass-fiber soil reinforcement system. *Journal of performance of constructed facilities*, 21(1): 26-34.
- Yi, Y., Li, C., and Liu, S. (2014). Alkali-activated ground-granulated blast furnace slag for stabilization of marine soft clay. *Journal of materials in civil engineering*, 27(4): 04014146.
- Yin, J.H., and Fang, Z. (2010). Physical modeling of a footing on soft soil ground with deep cement mixed soil columns under vertical loading. *Marine Georesources* and Geotechnology, 28(2): 173-188.
- Yip, C.K., Lukey, G., and Van Deventer, J. (2005). The coexistence of geopolymeric gel and calcium silicate hydrate at the early stage of alkaline activation. *Cement and Concrete Research*, 35(9): 1688-1697.
- Yip, C.K., Lukey, G.C., and Dean, J.S. (2004). Effect of blast furnace slag addition on microstructure and properties of metakaolinite geopolymeric materials. *Advances in Ceramic Matrix Composites*, 153: 187-209.
- Yip, C.K., Lukey, G.C., Provis, J.L., and van Deventer, J.S. (2008). Effect of calcium silicate sources on geopolymerisation. *Cement and Concrete Research*, 38(4): 554-564.
- Yip, C.K., Provis, J.L., Lukey, G.C., and van Deventer, J.S. (2008). Carbonate mineral addition to metakaolin-based geopolymers. *Cement and Concrete Composites*, 30(10): 979-985.
- Yoshizawa, S., Tanaka, M., and Shekdar, A. (2004). Global trends in waste generation. *Recycling, Waste Treatment and Clean Technology*, 7: 1541-1552.
- Yu, Y., Yin, J., and Zhong, Z. (2006). Shape effects in the Brazilian tensile strength test and a 3D FEM correction. *International journal of rock mechanics and mining sciences*, 43(4): 623-627.
- Yunsheng, Z., Wei, S., Qianli, C., and Lin, C. (2007). Synthesis and heavy metal immobilization behaviors of slag based geopolymer. *Journal of hazardous materials*, 143(1): 206-213.

- Yunsheng, Z., Wei, S., and Zongjin, L. (2010). Composition design and microstructural characterization of calcined kaolin-based geopolymer cement. *Applied Clay Science*, 47(3): 271-275.
- Yunsheng, Z., Wei, S., Zongjin, L., Xiangming, Z., and Chungkong, C. (2008). Impact properties of geopolymer based extrudates incorporated with fly ash and PVA short fiber. *Construction and Building Materials*, 22(3): 370-383.
- Yusoff, S. (2006). Renewable energy from palm oil–innovation on effective utilization of waste. *Journal of cleaner production*, 14(1): 87-93.
- Yusuf, M.O., Megat Johari, M.A., Ahmad, Z.A., and Maslehuddin, M. (2014a). Evolution of alkaline activated ground blast furnace slag-ultrafine palm oil fuel ash based concrete. *Materials & Design*, 55: 387-393.
- Yusuf, M.O., Megat Johari, M.A., Ahmad, Z.A., and Maslehuddin, M. (2014b). Strength and microstructure of alkali-activated binary blended binder containing palm oil fuel ash and ground blast-furnace slag. *Construction and Building Materials*, 52: 504-510.
- Zhang, M., Guo, H., El-Korchi, T., Zhang, G., and Tao, M. (2013). Experimental feasibility study of geopolymer as the next-generation soil stabilizer. *Construction and Building Materials*, 47: 1468-1478.
- Zhang, T., Yue, X., Deng, Y., Zhang, D., and Liu, S. (2014). Mechanical behaviour and micro-structure of cement-stabilised marine clay with a metakaolin agent. *Construction and Building Materials*, 73: 51-57.
- Zhu, H., Hua, S., and Chen, Y. (2009). Activating process of geopolymer source material: Kaolinite. *Journal of Wuhan University of Technology and Material Science*, 24(1): 132-136.