



**UNIVERSITI PUTRA MALAYSIA**

**THERMAL DIFFUSIVITY OF ZINC ALUMINUM – LAYERED DOUBLE  
HYDROXIDE USING PHOTOFLASH TECHNIQUE**

**MARYAM RANJBAR GHAZIEAN**

**FS 2009 3**



**THERMAL DIFFUSIVITY OF ZINC ALUMINUM – LAYERED DOUBLE  
HYDROXIDE USING PHOTOFLASH TECHNIQUE**

**By**

**MARYAM RANJBAR GHAZEIAN**

**Thesis submitted to the School of Graduate Studied, Universiti Putra Malaysia, in  
Fulfilment of the Requirements for the Degree of Master of Science**

**February 2009**



## **DEDICATION**

To my beloved parents Sedigheh and Fereydon for their love and concern

To my friend Reza Meimandi Parizi for his support and encouragement



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirements for the degree of Master of Science

**THERMAL DIFFUSIVITY OF ZINC ALUMINUM – LAYERED DOUBLE  
HYDROXIDE USING PHOTOFLASH TECHNIQUE**

By

**MARYAM RANJBAR GHAZIEAN**

**February 2009**

**Chair: Professor W.Mahmood Mat Yunus, PhD**

**Faculty: Science**

Thermal diffusivity of zinc aluminum layered double hydroxide (Zn-Al-LDH) was measured by using photoflash technique. It used a simple camera flash and polyvinylidene difluoride (PVDF) film as signal generating source and detector respectively.

Three series of sample were prepared at pH 7, 8 and 10 and with molar ratios of Zn to Al in a range from 2 to 6 (Zn/Al = 2, 3, 4, 5 and 6).

The ZnO peaks appeared in x-ray diffraction pattern for all samples except for samples prepared at pH 7 with ratio 2 and 3 (Zn/Al = 2 and 3) and sample prepared at pH 8 with ratio 4. The ZnO peaks observed were between  $2\theta = 30^\circ$  to  $2\theta = 37^\circ$ .



Thermal diffusivity for all three series samples (pHs 7, 8 and 10) was measured at room temperature. The thermal diffusivity for all three series of samples was found to increase for the case of molar ratio 2 to 6.

The thermal diffusivity for Zn-Al-LDH at different ratios of Zn-Al-LDH increased with increasing ratio of Zn to Al. The increasing of thermal diffusivity is due to increasing of ZnO. Thermal diffusivity at pH 7, increased from  $0.15 \times 10^{-6} m^2 / s$  to  $0.22 \times 10^{-6} m^2 / s$ . Thermal diffusivity of sample prepared at pH 8 increased from  $0.16 \times 10^{-6} m^2 / s$  to  $0.20 \times 10^{-6} m^2 / s$  while at pH 10, if increased from  $0.20 \times 10^{-6} m^2 / s$  to  $0.25 \times 10^{-6} m^2 / s$ . Thermal diffusivity at pH 7 has the lowest value and at pH 10 has the highest value.

The sample prepared at pH 7 with ratio 4 ( $Zn/Al = 4$ ) was heat-treated at different temperature from  $200^\circ C$  to  $600^\circ C$ , prior to thermal diffusivity measurement at room temperature.

In the case of heat treated samples, the thermal diffusivity increased from  $0.25 \times 10^{-6} m^2 / s$  to  $0.40 \times 10^{-6} m^2 / s$  with increasing treatment temperature.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains

**PENGUKURAN PERESAPAN TERMA UNTUK LAPISAN ZINK ALUMINIUM  
BERGANDA HYDROSIDA MENGGUNAKAN TEKNIK FOTO-KILAT**

Oleh

**MARYAM RANJBAR GHAZIEAN**

**February 2009**

**Pengerusi: Profesor W.Mahmood Mat Yunus, PhD**

**Fakulti: Sains**

Peresapan terma untuk hidroksida berlapis ganda Zink-Aluminium (Zn-Al-LDH) telah diukur menggunakan teknik foto-kilat. Ianya menggunakan cahaya kilat daripada kamera biasa digunakan sebagai sumber isyarat dan filem polyvinilidene diflouride (PVDF) pengesan. Tiga siri sampel disediakan pada pH7, 8, dan 10. Setiap siri mempunyai molar yang berbeza dengan nisbah Zn kepada Al, dalam julat daripada 2 hingga 6 (Zn/Al = 2, 3, 4, 5 dan 6). Puncak-puncak terhasil dalam corak pembelauan sinar-x bagi ZnO untuk semua sampel kecuali bagi sampel yang disediakan pada pH7 dengan molar 2 dan 3 (Zn/Al = 2 dan 3) dan sampel yang disediakan pada pH8 dengan nisbah Zn/Al = 4. Puncak ZnO telah dapat dilihat pada  $2\theta = 30^\circ$  hingga  $2\theta = 37^\circ$ .

Peresapan terma untuk ketiga-tiga siri sampel (pH 7, 8 dan 10) telah diukur pada suhu



bilik. Peresapan terma bagi ketiga-tiga sampel telah didapati meningkat untuk kes yang molarnya 2 hingga 6. Peresapan terma untuk Zn-Al-LDH dengan pada nisbah Zn/Al yang berbeza dengan peningkatan nisbah Zn kepada Al. Peningkatan peresapan terma adalah disebabkan oleh peningkatan ZnO. Peresapan terma pada pH7, meningkat daripada  $0.15 \times 10^{-6} m^2/s$  kepada  $0.22 \times 10^{-6} m^2/s$ . Peresapan terma bagi sampel yang disediakan pada pH8 meningkat daripada  $0.16 \times 10^{-6} m^2/s$  kepada  $0.20 \times 10^{-6} m^2/s$  manakala bnpada pH10 pula meningkat daripada  $0.20 \times 10^{-6} m^2/s$  kepada  $0.25 \times 10^{-6} m^2/s$ . Peresapan terma pada pH7 adalah merupakan nilai peresapan terma yang terendah dan pH10 adalah merupakan yang tertinggi.

Sampel yang disediakan pada pH7 dengan nisbah (Zn/Al = 4) telah diberikan rawatan haba pada suhu yang berbeza-beza daripada  $200^\circ C$  kepada  $600^\circ C$ , keutamaan untuk pengukuran peresapan terma pada suhu bilik. Dalam kes sampel yang telah dirawat oleh suhu, peresapan terma telah meningkat daripada  $0.25 \times 10^{-6} m^2/s$  kepada  $0.40 \times 10^{-6} m^2/s$  dengan peningkatan perawatan suhu.

## ACKNOWLEDGMENTS

In the Name of God, the Most Merciful and Most Beneficent

All praises to God that only by his grace and mercy of him this thesis can be completed.

I would like to express my sincere gratitude to my supervisor, Professor Dr. W. Mahmood Mat Yunus for his guidance and advice during this research, who without his patients and focus none of this would have been possible.

I am also grateful to my supervisory committee members, Professor Dr. Mohd Maarof H. A. Moskin and Professor Dr. Mohd Zobir Hussein for their advice and helpful discussion during this research.

I would like to thanks Dr.Mohammad Yeganeh Ghotbi, Dr.Mehdi Haydari, Amir reza Sadrolhosseini and Mohd Shahril Husin for their help in every way possible and also thankful to all the staff in the Physics Department.

The best appreciation to Reza Meimandi Parizi who has helped and supported me from first day of my stay in Malaysia to end, that I never forget his kindness.

I wish to express my deepest gratitude to my brother and sister, for their moral support and kindness. Last but not least, I wish especially to acknowledge my beloved parents, for their support and encouragement that have motivated me to continue pursuing my





goal. My mother, instilled in me, from an early age, the desire and skills to obtain the Master's degree.



This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were follows:

**W. Mahmood Mat Yunus, PhD.**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Chairman)

**Mohd Maarof Moxin, PhD.**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Mohd Zobir Hussein, PhD.**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**HASANAH MOHD. GHAZALI, PhD**

Professor and Dean  
School of Graduate  
Universiti Putra Malaysia

Date: 9 April 2009



## DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.

Maryam Ranjbar

Date:



## TABLE OF CONTENTS

	<b>Page</b>
<b>ABSTRACT</b>	<b>iii</b>
<b>ABSTRAK</b>	<b>v</b>
<b>ACKNOWLEDGEMENT</b>	<b>vii</b>
<b>APPROVAL</b>	<b>viii</b>
<b>DECLARATION</b>	<b>ix</b>
<b>LIST OF CONTENTS</b>	<b>x</b>
<b>LIST OF TABLES</b>	<b>xiii</b>
<b>LIST OF FIGURES</b>	<b>xiv</b>
<b>LIST OF ABBREVIATIONS</b>	<b>xvii</b>
<b>LIST OF SYMBOLS</b>	<b>xviii</b>
<b>CHAPTER</b>	
<b>1 INTRODUCTION</b>	<b>1</b>
1.1 Photothermal technique	3
1.1.1 Photoflash technique	3
1.2 Thermal Diffusivity of Solid	4
1.3 Thermal Carriers in Solid	5
1.4 Zinc Oxide	6
1.7 Objective	7
1.8 Chapter Organization	7
<b>2 LITERATURE REVIEW</b>	<b>9</b>
2.1 Detection methods	10
2.1.1 Direct detection methods	10
2.1.2 Indirect detection methods	10
2.2 Photoflash technique in thermal diffusivity measurement	11
2.3 Other techniques to measure thermal diffusivity	12
2.4.1 Photoacoustic technique	12
2.4.2 Thermocouple detection	14
2.4.3 Photodeflection technique	15
2.4.4 Photothermal displacement technique	16
2.4.5 Optothermal transient Emission radiometry technique	18
2.5 Layered Double Hydroxides (LDHs)	19
2.6 Application of Layered Double Hydroxides	23
2.6.1 Catalyst	23
2.6.2 Controlled Released	24
2.6.3 Medicine	25



2.7	Thermal behaviors of HTlcs	27
2.6	Reviews on the Preparation Methods of Layered Double Hydroxide	29
2.7	Powder X-ray Diffraction (PXRD)	30
2.8	Fourier Transform Infrared (FTIR)	32
2.9	Scanning Electron Microscopy (SEM) and Carbon Hydrogen and Nitrogen analysis (CHN)	33
<b>3</b>	<b>THEORY32</b>	
3.1	PVDF signal as Generated by the pulse light	35
3.2	Square optical pulse Generated signal	36
3.3	Thermal Insulator backing	38
<b>4</b>	<b>METHODOLOGY</b>	<b>40</b>
4.1	Photoflash	40
4.2	Polyvinildine difluoride (PVDF)	41
4.3	Digital Oscilloscope	43
4.4	Samples preparation	44
4.4.1	Zn-Al-LDH, pH 7, 8 and 10 with ratio 2 to 6	44
4.5	Characterizations of samples	46
4.6	Pressing sample powder	47
4.7	Effect of sample thickness	48
4.7	Experimental procedure	48
4.8	PVDF signal	50
4.9	Signal normalization	51
4.10	Signal averaging and noise reduction	52
4.11	Data analysis	54
4.12	Fitting procedure	55
<b>5</b>	<b>RESULTS AND DISCUSSION</b>	<b>56</b>
5.1	Samples structure	56
5.1.1	The effect of Zn/Al ratio on layered structure of Zn-Al-LDH	57
(a)	Sample prepared at pH = 7	57
(b)	Sample prepared at pH = 8	60
(c)	Sample prepared at pH = 10	61
5.2	Fourier Transform Infrared spectroscopy (FTIR)	63
5.3	Surface Morphology (SEM)	67
5.4	Thermal diffusivity measurement	70
5.5	Effect of Zn to Al molar ratio on thermal diffusivity	72
5.5.1	Sample Prepared at pH 7 with Different Zn to Al Molar Ratios	73
5.5.2	Sample Prepared at pH 8 with Different Zn to Al Molar Ratios	75



5.5.3	Sample Prepared at pH 10 with Different Zn to Al Molar Ratios	77
5.5.4	Effect of Zn to Al molar ratio on thermal diffusivity for pH 7, 8 and 10	79
5.6	Effect of pH on thermal diffusivity of Zn-Al-LDH	81
5.6.1	Thermal diffusivity measurement at various pHs	81
5.6.2	Thermal diffusivity versus percentage nitrogen	82
5.6.3	Percentage nitrogen versus Zn/Al ratio	83
	(a) Ratio 3	83
	(b) Ratio 4	84
	(c) Ratio 5	85
5.7	Effect of heat-treating on thermal diffusivity of Zn-Al-LDH	86
5.7.1	Effect of heat-treatment on structure	86
5.7.2	Thermal diffusivity measurement at different heat treatment	87
<b>6</b>	<b>CONCLUSION AND FURTHER WORK</b>	<b>90</b>
	<b>RECOMMENDATIONS FOR FUTURE RESEARCH</b>	<b>91</b>
	<b>REFERENCES</b>	<b>92</b>
	<b>APPENDICES</b>	<b>98</b>
	<b>BIODATA OF THE STUDENT</b>	<b>102</b>



## LIST OF TABLES

Table	page
5.1. The weight value of $Zn(NO_3)_2$ and $Al(NO_3)_3$ for all ratio (R = 2 to 6) according to gram	59
5.2. Basal spacing for Zn-Al-LDHs synthesized at various pHs, 7, 8 and 10	63
5.3. Thermal diffusivity value for sample synthesized at pH = 7, for all Zn to Al molar ratios (from ratio 2 to 6)	75
5.4. Thermal diffusivity value for sample synthesized at pH = 8, for all Zn to Al molar ratios (from ratio 2 to 6)	76
5.5. Thermal diffusivity value synthesized at pH = 10, for all Zn to Al molar ratios (from ratio 2 to 6)	79
5.6. Table 5.6. Values of thermal diffusivity and thickness for respective samples	89



## LIST OF FIGURES

<b>Figure</b>	<b>page</b>
1.1. The free electrons in metals, semiconductors and insulator	6
1.2. The crystalline structure of Zinc Oxide	7
2.1. The Schematic diagram of photoacoustic cell con-figuration setup (a) open photoacoustic cell; (b) close photoacoustic cell	13
2.2. The schematic of photodeflection technique	15
2.3. The schematic diagram of a measurement and theoretical model of photothermal displacement technique	17
2.4. The experimental setup installed in the heating chamber	17
2.5. The Schematic diagram of the optothermal transient emission Radiometry Technique	18
2.6. The structure of double sheet structure in two dimensions	20
2.7. Idealized structure of a layered double hydroxide, with interlayer carbonateanions	21
2.8. Structure of LDH	23
2.9. Schematic diagram for slow release of the guest from LDH hybrid	25
2.10. Schematic diagram for slow release of the guest from LDH hybrid	26
2.11. TG-DT diagrams of synthesized HTlc (a) $Ni_{0.68}Al_{0.32}(OH)_2(CO_3)_{0.16} \cdot 0.7H_2O$ (b) $Mg_{0.6}Fe_{0.33}(OH)_2(CO_3)_{0.165} \cdot 0.5H_2O$	28
2.12. X-ray patterns of MgAlCI-HTlc (a) and CuCoAl-HTlc (b)	31
2. 13. IR spectra of some M (II) AlCO <sub>3</sub> -HTlcs; MO= Ni (a), and Mg (b); x= 0.25	32
2. 14. IR spectra of NiAlA-HTks; (a) x = 0.25 and A = CO <sub>3</sub> , (b) x = 0.33 and A = CO <sub>3</sub> , (C) x = 0.25 and A = NO <sub>3</sub> , (d) x = 0.33 and A = NO <sub>3</sub>	33
3.1. Schematic diagram of the Four-layer system	35
4. 2. A PVDF film from two sides view	42





4.3 The rise time of the PVDF	43
4.4 The preparation system for mixing $Zn(NO_3)_2$ and $Al(NO_3)_3$ under nitrogen atmosphere when $NaOH$ is adds	45
4.5. The Schematic of sample dimension and high	48
4.6. Schematic diagram of the experimental set up	49
4.7. The state of sample between PVDF and holder	50
4.8. The PVDF response from Zinc – Aluminum layered double hydroxide at room temperature	51
4.9. The signal from Zn – Al – layered double hydroxide and the effect of signal averaging on the noise reduction	53
4.10. PVDF response from Zn – Al –LDH at room temperature (square) fitted by theoretical model (solid line)	54
5.1. The Powder X-ray Diffraction Patterns (PXRD) of Zn-Al-LDH synthesized at pHs 7 and at different ratio of Zn/Al	58
5.2. The Powder X-ray Diffraction Patterns (PXRD) of Zn-Al-LDH synthesized at pHs 8 and different ratio of Zn/Al	60
5.3. The Powder X-ray Diffraction Patterns (PXRD) of Zn-Al-LDH synthesized at pHs 10 at different ratio of Zn/Al	62
5.4. FTIR spectra the samples prepared at pH 7	64
5.5. FTIR spectra the samples prepared at pH 8	65
5.6. FTIR spectra the samples prepared at pH 7 after calcined at 400° C in a furnace	66
5.7. FTIR spectra the samples prepared at pH 7 after calcined at 600° C in a furnace	67
5.8. Surface Morphology of Zn-Al-LDH prepared at pH 7	68
5.9. Surface Morphology of Zn-Al-LDH prepared at pH 8	68
5.10. Surface Morphology of Zn-Al-LDH prepared at pH 10	69



5.11. Surface Morphology of Zn-Al-LDH prepared at pH 7 after 600° C temperature	69
5.12. PVDF response from Zn-AL-LDH sample at room temperature (a) 1.1 mm thickness (b) 0.75 mm	71
5.13. Thermal diffusivity, ( $\alpha$ ) versus thickness of Zn-Al-LDH	72
5.14. Thermal diffusivity of Zn-Al-LDH synthesized at pH 7, with different ratio of Zn/Al from ratio 2 to 6 at room temperature	74
5.15. Thermal diffusivity of Zn-Al-LDH synthesized at pH 8, with different ratio of Zn/Al from ratio 2 to 6 at room temperature	76
5.16. Thermal diffusivity of Zn-Al-LDH synthesized at pH 10, with different ratio of Zn/Al from ratio 2 to 6 at room temperature	78
5.17. Thermal diffusivity of Zn-Al-LDH with different ratio of Zn/Al from ratio 2 to 6 at room temperature	80
5.18. Thermal Diffusivity of Zn-Al-LDH at Various pHs and Ratios (R = 2 to 6)	82
5.19. Thermal diffusivity versus percentage of Nitrogen in the Zn-Al-LDH synthesized at pH, 7, 8 and 10	83
5. 20. Different ratio versus percentage of nitrogen	85
5. 21. The X-ray Diffraction Pattern after different furnace temperatures of 200° - 600°C	87
5 .22. Thermal diffusivity versus furnace temperatures of 200° - 600° C	88

## LIST OF ABBREVIATION

Å	Angstrom
PVDF	Polyvinlidene Difluoride
LDH	layered double hydroxide
PXRD	powder x-ray diffraction
SEM	Scanning Electron Microscopy
FTIR	Fourier Transform Infrared Spectroscopy
CHN	carbon, hydrogen and nitrogen
IR	Infrared characterization
HTLc	hydrotalcite -like compound
OTTER	optothermal transient emission radiometry
Zn-Al-LDH	Zinc Aluminum layered double hydroxide
R	Ratio
N.A	normalized amplitude
L	Thickness of sample
K	Kelvin temperature
YBCO	Y-Ba-Cu-O system
CPC	closed photoacoustic cell
OPC	open photoacoustic cell
BSCCO	Bi-Sr-Ca-Cu-O system



## LIST OF SYMBOLS

$k$	Thermal conductivity
$\alpha$	Thermal diffusivity
$\theta$	angle between the incident ray the scattering planes
$d$	diameter of the sample
$Al(NO_3)_2$	Aluminum nitrate
$Zn(NO_3)_2$	Zinc nitrate
$\lambda$	wavelength of x-ray diffraction
$d$	spacing between the planes
$l$	sample thickness
$(NO_3)^-$	Nitrate
$\rho$	density
$c$	Specific heat
$V$	Voltage
$T$	Time
$f$	Frequency
$I$	Current
$\nabla$	Gradient transverse
$Q$	quantity of heat



## CHAPTER 1

### INTRODUCTION

Thermal diffusivity is one of the most important physical properties of materials that present thermal behavior in the materials. Thermal diffusivity is also one of the most important thermal properties of the photonic and electronic devices. One of the general methods for measurement of thermal diffusivity is the flash method (Parker et al., 1961). The flash method uses a short light pulse to dissipate heat on front surface of the sample. The temperature on the rear surface of the sample is monitored and thermal diffusivity can be calculated by analyzing the temperature profile of the back sample.

For the steady – state conditions, the rate of heat diffusion can be written in Fourier – Biot equation:

$$\frac{Q}{A} = k \left( \frac{\partial T}{\partial x} \right) \quad (1.1)$$

In equation (1.1)  $Q$  is the quantity of heat flowing in a unit time through an area  $A$  under the temperature gradient  $\frac{\partial T}{\partial x}$  and  $k$  is the thermal conductivity.



When thermal properties of materials are independent of temperature but the temperature varies with time (t), equation (1.1) becomes:

$$\rho C_p \frac{\partial T}{\partial t} = k \frac{\partial^2 T}{\partial x^2} \quad (1.2)$$

$$\frac{\partial T}{\partial t} = \frac{k}{\rho C_p} \frac{\partial^2 T}{\partial x^2} \quad (1.3)$$

where  $\rho$  is the density of Zinc-Aluminum-layered double hydroxide and  $C_p$  is the specific heat at constant pressure.

$$\text{Thus} \quad \frac{k}{\rho C_p} = \alpha \quad (1.4)$$

where  $\alpha$  is the thermal diffusivity of the substance.

In the late 1990's, the thermal diffusivity was measured quantitatively with the delicate experiment device and the raw data processing (Bennis et al., 1998; Ogawa et al., 1999). After the year 2000 the measurement was focused on the application of various types of materials and solids. It is important to measure thermal properties and thermal behavior of various types of materials such as liquid, gas and solid materials (metals, nonmetals, semiconductors, bi-layer materials and thin film (Kim et al., 2007). Because thermal properties were used to search the specialty of heat transfer for the materials, which have a microstructure or nanostructure.

Thermal diffusivity is the quantity related to the propagation of heat. Many photothermal techniques have been used to measure thermal diffusivity of solids, liquid and gas.

## **1.1 Photothermal Technique**

One of the most popular methods used for measuring thermal diffusivity is the flash method (Kim et al., 2007). In this technique a pulse of light such as a flash lamp, camera flash or laser is irradiated on the surface of the sample. The effect of this radiation absorption produces a heat called “thermal wave”. By using photothermal method identification of the materials through its properties is made possible (Haydari, 2004).

There are two ways for detecting thermal wave: direct and indirect detection. The direct way such as thermocouple detection and pyroelectric, while indirect detection such as photoacoustic technique and thermal lens.

### **1.1.1 Photoflash Technique**

Photoflash technique is one of the varieties of photothermal techniques, which based on the thermal wave detection due to modulated light absorption in the materials. The set up with a short light pulse diffuse on the surface of the sample. Then the temperature in the back of the sample increased. There is a PVDF sensor in the rear of the sample. The temperature was detected using a PVDF, and then data were sent to the oscilloscope. Then the experimental data were fitted with theoretical model.

The heat has to travel from the front of the sample to the back of the sample, the effect of heat is loss especially when the sample is thicker or the thermal diffusivity of the sample is lower. When the sample has the right thickness the PVDF can detect the heat in the rear of the sample (Haydari, 2004).

## 1.2 Thermal Diffusivity of Solid

Thermal diffusivity is a parameter which determines the time dependent condition for unsteady state. It provides both direct and indirect information for materials of industrial interest. The first exact formula for hydrotalcite was  $[Mg_6Al_2(OH)_{16}CO_3 \cdot 4H_2O]$ . Hydrotalcite is a mineral that can be easily crushed into a white powder similar to talc. Around 1842 in Sweden, LDH was discovered, also at the same time another compound of hydroxycarbonate magnesium and iron was discovered which called pyroaurite because was similar to gold materials when it was heated. Later on isostructural was discovered with hydrotalcite similar layered double hydroxide as having similar features (Cavani et al., 1991).

The extensive work on physico-chemical characterization of the hydrotalcites is the reason why hydrotalcite is used as reference name in many applications. Also the preparation of hydrotalcites in laboratory is simple and relatively inexpensive. To the best of our knowledge, there is no complete report on thermal diffusivity of zinc - aluminum - layered double hydroxide. For these reasons we have focus this study on investigating the thermal diffusivity of zinc - aluminum - layered double hydroxide was



measured at room temperature with different ratios of Zn to Al molar and different pH. Also the thermal diffusivity of Zn-Al-LDH was measured for pH 7 after heat –treated the sample in an electronic furnace at different temperature from 200°C to 600°C.

### **1.3 Thermal Carriers in Solids**

The heat is transferred from a point to another point via conduction, convection or radiation. Normally in solid material, the heat is transferred via conduction. In solid materials with high porosity, the heat can be transferred across a pore by convection and radiation as well as conduction. There are three classes for solid materials; metals, insulators and semiconductors. In metals, the free electrons are so many and the thermal energy is transferred by electrons. In insulator, the free electrons are so few and in semiconductors phonons and electrons are equally important as carriers of thermal energy.

### **1.4 Zinc Oxide**

Zinc oxide is one of the most important chemical compounds with the formula written as ZnO (Figure 1.1). It is insoluble in water but soluble in acids. The color of zinc oxide powder is white. As a mineral was found in nature but the crystal form of zinc oxide is rare (Suzuki et al., 1988). The crystalline of zinc oxide produces the piezoelectric effect and is thermochromic (ability of substance to change color). The crystalline of zinc oxide is able to change from white color to yellow when heated. ZnO is a semiconductor