



UNIVERSITI PUTRA MALAYSIA

**INFLUENCE OF GAMMA RADIATION ON OPTICAL AND
DIELECTRIC PROPERTIES OF DYED POLYVINYL ALCOHOL FILM
DOSIMETERS**

AJIS LEPIT.

FSAS 2004 10



**INFLUENCE OF GAMMA RADIATION ON OPTICAL AND DIELECTRIC
PROPERTIES OF DYED POLYVINYL ALCOHOL FILM DOSIMETERS**

By

AJIS BIN LEPIT

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in
Fulfilment of the Requirements for Degree of Master of Science**

February 2004



Dedication

بِسْمِ اللَّهِ الرَّحْمَنِ الرَّحِيمِ

اقْرَأْ بِاسْمِ رَبِّكَ الَّذِي خَلَقَ # خَلَقَ الْإِنْسَانَ مِنْ عَلَقٍ # اقْرَأْ وَرَبُّكَ
الْأَكْرَمُ # الَّذِي عَلَّمَ بِالْقَلَمِ # عَلَّمَ الْإِنْسَانَ مَا لَمْ يَعْلَمْ - العلق : 1-5

“Proclaim! (or Read!) In the name of thy Lord and Cherisher, Who created, # Created man, out of a (mere) clot of congealed blood: # Proclaim! and thy Lord is Most Bountiful, # He Who taught (the use of) the Pen, # Taught man that which he knew not”. *Versus Al-alaq : 1-5*

To my family

Zuraida Adam

Muhammad Akmal Zulhilmi

Muhammad Akram Irfan

Fatin Najihah

*Who has given all the patience, encouragement, love
and support.*

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirements for the degree of Master of Science

INFLUENCE OF GAMMA RADIATION ON OPTICAL AND DIELECTRIC PROPERTIES OF DYED POLYVINYL ALCOHOL FILM DOSIMETERS

By

AJIS BIN LEPIT

February 2004

Chairman: Associate Professor Elias Bin Saion, Ph.D.

Faculty: Science and Environmental Studies

The influence of γ -rays on the optical absorption and inelastic scattering, dielectric properties and conductivity of radiation-sensitive dyed polyvinyl alcohol (TB/PVA) film dosimeters containing chloral hydrate and acid-sensitive Thymol blue dye were evaluated for possible use as food irradiation indicators. The dyed PVA films of different concentrations of chloral hydrate were irradiated with the absorbed doses ranging up to 12 kGy using γ -rays from Cobalt-60. The dehydrochlorination of chloral hydrate and radiolysis of water molecules induced by ionising radiations accelerated the formation of hydrochloric acid in the polymer matrix, which caused the change in colour of the dosimeters from yellow to red at the critical doses depending on the concentration of chloral hydrate. This radiation-induced colour change was analysed using UV-Vis spectrometer, where the absorption spectra produced two visible maximal bands, peaking at 445 nm and 554 nm. The dose response at 445 nm and 554 nm increases and decreases respectively with absorbed dose. The inelastic Raman scattering spectra of photons corresponding to the Raman frequency shifts of unirradiated and irradiated films were measured using a dispersive Raman spectrometer, which provide direct evidence of molecular



structure changes induced by ionising radiation and the subsequent chemical effects. The spectral intensities of Raman shifts at 815, 1984, 2350 and 2560 cm^{-1} bands correspond to C-Cl, C=O, C=C and S-H bonds respectively were studied, which provide the dose response to the molecular vibration of the dosimeters. From dielectric and conductivity studies it is found that the dyed polymer dosimeters are ionic polymer materials. The dielectric constant (ϵ'), dielectric loss (ϵ'') and the electrical conductivity $\sigma(\omega)$ characteristics of the dosimeters were measured at different frequencies ranging from 20 Hz to 1 MHz. The dielectric constant and dielectric loss increase with absorbed dose at low frequencies and are independent of dose at higher frequencies for all chloral hydrate concentration. The AC conductivity (σ) increases with absorbed dose and frequency due to the formation of radiation-induced free radicals, cations and anions in the polymer matrix and due to ejected electrons in the conduction bands. Thus, the resistance derived from the impedance measurement, decreases with absorbed dose. Finally, the films were subjected to stability tests using digital densitometry method at different time intervals during post-irradiation storage. The results show the change in optical density is minimal over the period of 70 days for all irradiated samples. This suggests the dosimeters have optical absorption stability characteristics for use as alternative radiation-sensitive dosimeters in irradiation facilities as long as they are shielded from sunlight or fluorescent lighting by wrapping with black plastic bag.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains

PENGARUH SINAR GAMMA KEATAS SIFAT-SIFAT OPTIK DAN DIELEKTRIK METERDOS FILEM WARNA POLYVINYL ALCOHOL

Oleh

AJIS BIN LEPIT

Februari 2004

Pengerusi: Profesor Madya Elias Bin Saion, Ph.D.

Fakulti: Sains dan Pengajian Alam Sekitar

Pengaruh sinar- γ ke atas penyerapan optikal dan serakan tidak elastik, sifat-sifat dielektrik dan konduktiviti bagi sinar-sensitif meterdos warna filem polyvinyl alcohol (TB/PVA) yang mengandungi kloral hidrat dan asid sensitif Thymol biru telah dikaji untuk aplikasi kemungkinan sebagai indikator penyinaran makanan. Filem-filem yang berbeza kepekatan bahan kloral hidrat disinarkan dengan dos-dos penyerapan sehingga 12 kGy menggunakan sinar- γ dari kobalt-60. Penyahhidroklorinan kloral hidrat dan radiolisis molekul air diaruhkan oleh sinaran sebagai pemangkin melalui pembentukan asid hidroklorik dalam bahan polimer, yang menyebabkan meterdos berubah warna dari kuning ke merah pada dos kritikal yang bergantung kepada kepekatan bahan kloral hidrat. Perubahan warna ini telah dianalisa menggunakan spektrometer UV-Vis, dimana penyerapan spektrum menghasilkan dua jalur maksima dalam julat cahaya-nampak pada 445 nm dan 554 nm. Dos tindakbalas pada 445 nm meningkat dan 554 nm menurun dengan kenaikan dos penyerapan. Serakan foton tidak elastik spektra Raman bagi filem bergantung kepada perubahan frekuensi Raman sebelum dan selepas penyinaran diukur menggunakan penyebaran spektrometer Raman, bagi menyediakan bukti secara terus

perubahan struktur molekul disebabkan oleh sinar mengion dan seterusnya kesan kimia. Keamatan spektra Raman pada jalur 815, 1984, 2350 dan 2560 cm^{-1} adalah sejajar ikatan dengan C-Cl, C=O, C=C dan S-H adalah telah dikaji, disebabkan tindakbalas dos getaran molekul-molekul meterdos. Dari kajian dielektrik dan konduktiviti didapati bahan meterdos polimer warna adalah bahan-bahan polimer ion. Pemalar dielektrik (ϵ'), kehilangan dielektrik (ϵ'') dan konduktiviti elektrik $\sigma(\omega)$ bagi meterdos, diukur julat frekuensi yang berbeza dari 20 Hz hingga 1 MHz. Pemalar dielektrik dan kehilangan dielektrik bertambah dengan dos penyerapan pada frekuensi rendah dan tidak bergantung pada dos ketika frekuensi tinggi bagi semua kepekatan kloral hidrat. Konduktiviti a.u (σ) bertambah dengan dos penyerapan dan frekuensi dihasilkan oleh pembentukan radikal bebas sinar-teraruh, kation dan anion di dalam matrik polimer yang disebabkan elektron disuntik keluar dalam jalur konduksi. Oleh itu rintangan diperolehi dari pengukuran impedan, menurun dengan dos serapan. Akhir sekali, sampel filem dikehendaki untuk ujian kestabilan menggunakan digital meterketumpatan pada tempoh masa yang berbeza semasa simpanan selepas disinarkan. Keputusan menunjukkan bahawa perubahan ketumpatan optik adalah rendah sepanjang masa 70 hari disimpan untuk semua bahan yang telah disinarkan. Ini boleh dicadangkan meterdos itu mempunyai ciri-ciri kestabilan optik untuk digunakan sebagai meterdos sinar-sensitif alternatif dalam prasarana penyinaran selagi ianya disimpan dan dilindungi daripada cahaya matahari atau flouresen dengan membungkus dengan plastik berwarna hitam.

ACKNOWLEDGEMENTS

All praise and admiration for Allah, the Almighty, Beneficial and the most Merciful, who has enabled me to submit this thesis.

The author gratefully acknowledged Assoc. Prof. Dr. Elias Saion of the Department of Physics, Faculty Science and Environmental Studies, Universiti Putra Malaysia for his assistance, helpful discussions, suggestions, constructive criticisms, motivation, encouragement and time throughout the duration of study. I would also like to thank the committee members Dr. Jumiah Hassan and Assoc. Prof. Dr. Mohd. Zaki Abdul Rahman for their guidance and encouragement. The author also acknowledged the assistance and helpful comments of Hasan Sham of Malaysian Institute for Nuclear Technology Research (MINT) at Bangi, Selangor. Thanks are also due to Mr Taiman Kadni Head of Secondary Standard Dosimetry Laboratory for providing High Dose of Gamma Irradiation facilities, J. L. Sheperd, Jalan Dengkil, Kajang. To the colleagues in Bio-Physics Lab, Department of Physics, Faculty of Sciences and Environmental Studies, UPM Serdang especially for providing the assistance, comments, for their willingness to share knowledge and information, references, etc., is greatly appreciated. Special thanks go to Phang Kee Keong who is responsible for development of real time data acquisition in impedance measurement with LCR meter HP4284A. Lastly, I would like to thank the Malaysian Government and UiTM for granting me the study leave and providing staff scholarship during the course of this study.



TABLE OF CONTENTS

	Page
DEDICATION	ii
ABSTRACT	iii
ABSTRAK	v
ACKNOWLEDGEMENTS	vi
APPROVAL	viii
DECLARATION	x
LIST OF TABLES	xiv
LIST OF FIGURES	xv
LIST OF ABBREVIATIONS/SYMBOLS	xxiii
LIST OF GLOSSARY OF TERMS	xvii
CHAPTER	
I INTRODUCTION	1
Scope of the Present Study	3
Polyvinyl alcohol, Thymol Blue and Chloral Hydrate – Main Composition of Radiation-Sensitive Indicator	3
Problem Statement	6
Objective of Research	7
Significance of Study	8
Outline of the Thesis	9
II LITERATURE REVIEW	
Historical Background of Use Ionizing Radiation for Food Preservation	11
Food Irradiation	14
The Food Irradiation-Process and Application	15
Related Work in Food Irradiation	18
Detection and Measurement of Ionizing Radiation	20
Methods of Dosimetry	21
Polymer Film, Dyes and Chemical as a Dosimetric System	25
Related Work in Dosimeter for Radiation Indicator of Food Irradiation	26
Measurement of Dose at Wide Range of Irradiation by Visual Observation	27
Darkening of Film Dosimeter	29
Colour Changes	29
Dye Colour Bleachable System	30
Other Dosimetric System	31
Vinyl or Acrylics Film Dosimeter	33
Related Work Using Raman Spectroscopy	34
Related Work with Dielectric Properties to Study the Effect of Ionizing Radiation on some Materials	36



III	THEORY OF RADIATION ACTIONS AND OPTICAL AND ELECTRICAL MEASUREMENTS OF RADIATION EFFECT	39
	Interaction of Gamma Ray with Matter	39
	Rayleigh Scattering	40
	Photoelectric Absorption	41
	Compton Scattering	42
	Pair Production	44
	Physical, Chemical and Biological Aspects of Radiation Actions	46
	Illustration of the Radiation Action in Food Preservation	46
	Physical Aspects	47
	Chemical Aspects (Ionization, Excitation, and Free Radical Formation)	48
	Biological Aspects	53
	Irradiation of Food for Preservation	57
	UV-Visible Absorption	59
	Electronic Transition in Molecules	59
	Optical Absorption Spectra	62
	The Beer-Lambert's Law	64
	Raman Spectroscopy	66
	Inelastic Scattering of Light	66
	The Theory of Raman Effect	68
	Dielectric Relaxation	72
	Capacitance and Dielectrics	73
	Dielectric Constant and Loss Factor	75
	Conductivity	79
	Frequency Dependence of Dielectric Constant	82
	Polarization	84
	Electronic Polarization	85
	Ionic Polarization	87
	Orientation or Dipolar Polarization	87
	Space Charge Polarization	87
IV	EXPERIMENTAL PROCEDURES FOR SYNTHESIS AND CHARACTERISATION	88
	Sample Preparations	88
	Preparation of Stock of Indicator	88
	Preparation of Dye PVA Film Dosimeters	89
	Irradiation Source	91
	Irradiation of Dosimeters	92
	Spectra Measurement	93
	Raman Inelastic Scattering Spectra	93
	Raman Spectra Measurement	94
	UV-VIS Absorption Spectra	96
	Method of Samples Measurement with CAMSPEC M350 Double Beam Scanning Spectrophotometer	98
	Stability Measurement	99



	Densitometer	99
	Optical Density	100
	LCR Meter	101
	Dielectric Measurements	102
	Data Processing	104
	Calculation of Impedance Spectroscopy	105
V	UV-VISIBLE ABSORPTION AND RAMAN SCATTERING STUDIES	107
	UV-Visible Absorption Analysis	107
	Absorption Spectra	107
	Dose Response	113
	Estimation of the Critical Dose	115
	Stability Measurement	119
	Pre-irradiation Stability	120
	Post-Irradiation Stability	121
	Colour Stability Stored at Ambient Conditions	124
	Raman Spectral Peak Identifications	127
	The C-Cl Stretching Mode	128
	The C=C, C=O and S-H Stretching Mode	130
VI	MEASUREMENT OF DIELECTRIC RELAXATION AND CONDUCTIVITY	135
	Dielectric Constant Characteristics	135
	Dielectric Loss Characteristics	144
	Dielectrics Loss Tangent Characteristics	149
	Complex Electric Modulus Characteristics	153
	AC Conductivity	159
	Complex Impedance Characteristics	164
VII	CONCLUSION AND SUGGESTION FOR FUTURE WORK	169
	UV-Visible Absorption	170
	Raman Spectra	170
	Dielectrics Properties and Conductivity	172
	Stability of Dyed PVA film	173
	Future Work and Recommendations	174
	BIBLIOGRAPHY	176
	APPENDICES	188
	BIODATA OF THE AUTHOR	195
	LIST OF PUBLICATION/SEMINAR/POSTER	196



LIST OF TABLES

Table		Page
2.1	Advisory Technological Dose Limit for Good Irradiation Practice.	17
4.1	Percentage of light transmittance and calculated optical densities.	
5.1	Raman assignments of dye PVA film dosimeters of those peaks are listed.	127
6.1	Values of activation doses D_0 for various amount chloral hydrate (g) of PVA film indicators.	158
1.1	Specification of Thymol Blue.	188
5.2	Infrared and Raman Characteristics Frequencies of organic	194



LIST OF FIGURES

Figure		Page
2.1	Chemical structures of Thymol blue dye in basic and acidic form.	4
3.1	The scattered photon has less energy than the incident photon and may be scattered through any angle. The recoil electron is always scattered in a 'forward' direction.	44
3.2	Contribution of γ -ray interactions in a medium.	46
3.3	Three stages for the action of ionizing radiation on biological materials.	47
3.4	Mechanism of energy transfer for γ -ray or x-ray (Compton Effect).	50
3.5	Possible pathway for cellular response to ionizing radiation	55
3.6	Biological survival curves.	56
3.7	The possible transition of π , σ and η orbital electrons in molecules.	62
3.8	Absorption spectra of dyed PVA film dosimeters at different doses.	63
3.9	Simple model illustrating Stokes and Anti-Stokes Raman scattering.	69
3.10	Energy level diagrams illustrating Raman scattering.	70
3.11	(a) The charge stored on capacitor plates for a vacuum (b) the increased charged storing capacity resulting from the polarization of dielectric materials.	74
3.12	Representation of non-ideal capacitor (b) Representation of the phase angle θ and loss tangent δ .	78
3.13	Dipole orientation.	83
3.14	Frequency response of dielectric mechanisms.	83

3.15	Types of polarization.	86
4.0	Chemical substances used in preparation of dye polymer film.	88
4.1	Dyed PVA film on a glass plate caster.	90
4.2	Cobalt-60 gamma rays chamber of J.L Sheperd type.	92
4.3	TB/PVA films undergo colour change when exposed to γ -rays.	93
4.4	Raman Spectrometer RSI 2001G, Raman System Inc.	94
4.5	Raman Laser Probe.	94
4.6	Measurement of samples using RSI Raman spectrometer.	95
4.7	A double beam UV-Vis spectrophotometer (CAMSPEC M350).	97
4.8	The digital Densitometer II model 07-440) is used to measure optical densities.	99
4.9	Agilent HP 4284A-LCR Meter.	101
4.10	Capacitance with C_p -G circuit mode selection.	102
4.11	Brass electrodes and cables wire with samples.	102
5.1	Dose response curve for absorption spectra of Thymol Blue dyed PVA film indicator containing 0.1 g of Chloral Hydrate.	108
5.2	pH range of colour change chart for some common acid - base indicators.	109
5.3	Dose response curve for absorption spectra of Thymol Blue dye PVA film indicators containing 0.5 g of Chloral Hydrate.	110
5.4	Dose response curve for absorption spectra of Thymol Blue dye PVA film indicators containing 1.0 g of Chloral Hydrate.	110
5.5	Dose response curve for absorption spectra of Thymol Blue dye PVA	111



	film indicators containing 2.0 g of Chloral Hydrate.	
5.6	Dose response curve for absorption spectra of Thymol Blue dyed PVA film indicator containing 2.5 g of Chloral Hydrate.	111
5.7	The change in absorbance at 554 nm of Thymol Blue dyed PVA indicator at different amount of Chloral Hydrate as a function of absorbed dose.	114
5.8	The change in absorbance at 454 nm of Thymol Blue dyed PVA indicator at different amounts of Chloral Hydrate as a function of absorbed dose.	114
5.9	Change in the colour of indicator film at the 6.8 kGy absorbed dose for 0.1 g of Chloral Hydrate added to the film.	116
5.10	Change in the colour of indicator film at the 5 kGy absorbed dose for 0.5 g of Chloral Hydrate added to the film.	116
5.11	Change in the colour of indicator film at the 4.5 kGy absorbed dose for 1.0 g of Chloral Hydrate added to the film.	117
5.12	Change in the colour of indicator film at the 3.0 kGy absorbed dose for 2.0 g of Chloral Hydrate added to the film.	117
5.13	Change in the colour of indicator film at the 1.5 kGy absorbed dose for 2.5 g of Chloral Hydrate added to the film.	118
5.14	Critical dose versus amount of chloral hydrate.	118
5.15	Optical density of Thymol blue/PVA films stored before and after irradiation for 70 days.	120
5.16	Stability of Thymol blue/PVA films before irradiation stored at	121

	different temperatures.	
5.17	Stability of Thymol blue dyed PVA film dosimeter stored at 5 ^o C after irradiation.	121
5.18	Stability of Thymol blue/PVA films stored at 23 ^o C after irradiation.	122
5.19	Stability of Thymol blue/PVA films stored at 55 ^o C after irradiation.	123
5.20	Post-irradiation stability of Thymol Blue dyed PVA films at absorbed dose 12 kGy stored at different temperatures.	123
5.21	Pre and Post-irradiation stability of Thymol Blue dyed PVA films stored and exposed at ambient conditions.	125
5.22	Relative Raman spectra of TB/PVA film dosimeter for C-Cl bond with different absorbed dose of γ -irradiation.	129
5.23	Decreasing of relative Raman intensity for C-Cl (815 cm ⁻¹) vibration bonds depending on the weight of Chloral Hydrate.	130
5.24	Vibrational Raman spectra for C=C, C=O and S-H bonds for different absorbed doses.	131
5.25	Relative Raman intensity at 1984 cm ⁻¹ of C=C vibration band of film dosimeters at different amount of chloral hydrate as a function of absorbed dose.	132
5.26	Relative Raman intensity at 2350 cm ⁻¹ of C=O vibration band of film dosimeters at different amount of chloral hydrate as a function of absorbed dose.	133
5.27	Relative Raman intensity at 2560 cm ⁻¹ of S-H vibration band of film	133

	dosimeters at different amount of chloral hydrate as a function of absorbed dose.	
6.0	Dielectric constant of pure PVA films irradiated at different doses	136
6.1	Dielectric constant of unirradiated PVA film indicators at different concentrations of chloral hydrate.	137
6.2	Dielectric constant of PVA film indicator doped with 1.0 g chloral hydrates at different absorbed doses.	139
6.3	Dielectric constant of PVA film indicator doped with 2.0 g chloral hydrates at different absorbed doses.	139
6.4	Dielectric constant of PVA film indicator doped with 0.5 g chloral hydrates at different absorbed doses.	140
6.5	Dielectric constant of PVA film indicator doped with 2.5 g chloral hydrates at different absorbed doses.	140
6.6	Dielectric constant for PVA film indicator for different concentrations of chloral hydrate and at absorbed dose of 12 kGy.	142
6.7	Dielectric constant for PVA film indicator for different concentrations of chloral hydrate and at absorbed dose of 8 kGy.	142
6.8	Relative constant as a function of absorbed dose with 0.1 g of chloral hydrate for five fixed frequencies.	143
6.9	Frequency-dependent dielectric loss $\epsilon''(\omega)$ of pure PVA film irradiated with different absorbed doses.	144
6.10	Relative dielectric loss of PVA film indicator containing 2.5 g of chloral hydrates at different doses.	145

6.11	Relative dielectric loss of PVA film indicator containing 1.0 g of chloral hydrates at different doses.	146
6.12	Relative dielectric loss of PVA film indicators at absorbed dose of 12 kGy and at different concentrations of chloral hydrate.	147
6.13	Relative dielectric loss of PVA film indicators at absorbed dose of 8 kGy and at different concentrations of chloral hydrate.	148
6.14	Tan δ versus absorbed dose at various frequencies for pure PVA films without chloral hydrate.	150
6.15	Tan δ versus absorbed dose at various frequencies of PVA film containing 2.0 g of chloral hydrate.	150
6.16	Tan δ versus absorbed dose at various frequencies of PVA film containing 1.0 g of chloral hydrate.	151
6.17	Dissipation factor for PVA film indicator at absorbed dose 8 kGy with different concentration of chloral hydrate.	152
6.18	Dissipation factor for PVA film indicator at absorbed dose 12 kGy with different concentration of chloral hydrate.	152
6.19	Real $M'(\omega)$ spectra as a function frequency for pure PVA film without chloral hydrate at different absorbed doses.	153
6.20	Imaginary $M''(\omega)$ spectra as a function frequency for pure PVA film without chloral hydrate at different absorbed doses.	154
6.21	Real $M'(\omega)$ spectra as a function of frequency for PVA film doped with 2.0 g chloral hydrate at different absorbed doses.	155

6.22	Imaginary $M''(\omega)$ spectra as a function of frequency for PVA film doped with 2.0 g chloral hydrate at different absorbed doses.	155
6.23	Real $M'(\omega)$ spectra as a function of frequency for PVA film doped with 1.0 g chloral hydrate at different absorbed doses.	156
6.24	Imaginary $M''(\omega)$ spectra as a function of frequency for PVA film doped with 1.0 g chloral hydrate at different absorbed doses.	156
6.25	Arrhenius diagram of the relaxation time as function of D^{-1} for PVA film indicators at amount of chloral hydrate.	158
6.26	Frequency-dependent ac conductivity of pure PVA film indicators at different absorbed doses.	160
6.27	Frequency-dependent ac conductivity of pure PVA film indicators at different absorbed doses.	161
6.28	Conductivity versus frequency of dyed PVA films with 1.0 g chloral hydrate at different absorbed doses.	161
6.29	Conductivity versus frequency of unirradiated dyed PVA film indicators doped with chloral hydrate at different concentrations.	162
6.30	Conductivity versus frequency of dyed PVA film indicators irradiated with absorbed dose 4 kGy.	163
6.31	Conductivity versus frequency of dyed PVA film indicators irradiated with absorbed dose 8 kGy.	163
6.32	Conductivity versus frequency of dyed PVA film indicators irradiated with absorbed dose 12 kGy.	164
6.33	Imaginary component (Z'') versus real component (Z') of complex	165

	impedance for all frequencies for PVA films doped with different amount of chloral hydrate and irradiated with the absorbed dose of 4 kGy.	
6.34	Imaginary component (Z'') versus real component (Z') of complex impedance for all frequencies for PVA films doped with different amount of chloral hydrate and irradiated with the absorbed dose of 12 kGy.	166
6.35	The complex plane plots Z'' versus Z' for all frequencies as a function of absorbed dose for pure PVA films.	167
6.36	The complex plane plots Z'' versus Z' for all frequencies as a function of absorbed dose for PVA film indicators doped with 2.0 g amount of chloral hydrate.	168
1.1	Chemical structure of Thymol Blue.	188
5.22a	Raman spectra of chloral hydrate salts using Dispersive Raman Spectrometer.	191
5.22b	Vibrational spectra of Raman using FT-Raman.	192

LIST OF ABBREVIATIONS/SYMBOLS

γ -ray	-	Gamma Ray
BPB	-	Bromophenol Blue
CR	-	Cresol Red
DCP	-	2,6 dichloro phenol indophenol sodium salt
PVA	-	Polyvinyl alcohol
PVB	-	Polyvinyl butyral
PVC	-	Polyvinyl chloride
PS	-	Polystyrene
PMMA	-	Polymethyl methacrylate
TB	-	Thymol blue
ϵ'	-	Dielectric Constant
ϵ''	-	Dielectric Loss
$\tan \delta$	-	Dielectric Loss Tangent
τ	-	Time constant or relaxation time
σ	-	Conductivity
WHO	-	World Health Organization
MINT	-	Malaysia Institute for Nuclear Technology Research
IAEA	-	International Atomic Energy Agency
FAO	-	Food & Agriculture Organization
UV-Vis	-	Ultraviolet – Visible
GIP	-	Good Irradiation Practice
kGy	-	kiloGray
IR	-	Infrared
NaOH	-	Sodium hydroxide



GLOSSARY

This glossary to define a few words in common use in this thesis. Many other quantities and term are defined in appropriate locations in the text.

Absorbed dose Amount of energy deposited by ionizing radiation in a material per unit mass of the material. Usually expressed in the special radiological unit rad or in the SI unit Gray.

Anti-Stokes Raman Scattering Light scattering in which the photons gain energy as a result of photon-molecule collisions.

Chromophore Molecule or part of the molecule that absorbed light.

Dielectric Dielectric is a material in which energy can be stored by the polarization of the molecules. It is a material that increases the capacitance or charge storage ability of a capacitor. Ideally it is a non-conductor of electrical charge so that an applied field does not cause a flow of charge but instead a relative displacement of opposite bound charges and hence polarization of the medium.

Dipolar (orientational) polarization arises when randomly oriented polar molecules in a dielectric are rotated and aligned by the application of a field so as to give rise to a net average dipole moment per molecule. In the absence of the field the dipoles (polar molecules) are randomly oriented and there is no average dipole moment per molecule. In the presence of the field the dipoles rotated, some partially and some fully, to align with the field and hence give rise to net dipole moment per molecule.

Dose (D) Used broadly for energy deposited in matter from radiation. Used in dosimetry for the energy absorbed per unit mass of material, usually by ionization processes. Units are the rad and the Gray (Gy), which are equivalent, respectively, to ergs/g and 1 J/Kg. There, 1 rad = 1/100 Gray or cGy.

Dosimetry The calculation, measurements and other activities required for determining the radiation dose to be delivered.

Electronic polarization Electronic polarization is the displacement of the electron cloud of an atom with respect to the positive nucleus. Its contribution to the relative permittivity of a solid is usually small.

Excitation The addition of energy to a system, transferring it from its ground state to an excited state. Excitation of a nucleus, an atom, or a molecule can result from absorption of photons or from inelastic collision with other particles.

Free Radical A highly reactive chemical species carrying no charge and having a single unpaired electron in an orbital.

