



UNIVERSITI PUTRA MALAYSIA

***CONCURRENT CONCEPTUAL DESIGN OF HYBRID
NATURAL/GLASS FIBER REINFORCED THERMOPLASTIC
COMPOSITES FOR AUTOMOTIVE PARKING BRAKE LEVER***

MUHD RIDZUAN BIN MANSOR

FK 2014 169



**CONCURRENT CONCEPTUAL DESIGN OF HYBRID
NATURAL/GLASS FIBER REINFORCED THERMOPLASTIC
COMPOSITES FOR AUTOMOTIVE PARKING BRAKE LEVER**

By

MUHD RIDZUAN BIN MANSOR

**Thesis Submitted to the School of Graduate Studies, Universiti
Putra Malaysia, in Fulfilment of the Requirements for the
Degree of Doctor of Philosophy**

November 2014

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in
fulfilment of the requirement for the degree of Doctor of Philosophy

**CONCURRENT CONCEPTUAL DESIGN OF HYBRID NATURAL/GLASS
FIBER REINFORCED THERMOPLASTIC COMPOSITES FOR
AUTOMOTIVE PARKING BRAKE LEVER**

By

MUHD RIDZUAN BIN MANSOR

November 2014

Chair: Professor Mohd Sapuan Salit, PhD, P.Eng

Faculty: Engineering

This thesis presents the potential of hybrid polymer composites application made from short natural fiber/glass fiber reinforced thermoplastic composites for the development of automotive parking brake lever component. Concurrent engineering approach was implemented in the overall product development process which covers materials selection, concept design development, theoretical performance analysis and environmental impact assessment to achieve the required component structural strength for safe and operational performances. Analytic Hierarchy Process (AHP) method was first applied in the material selection process where kenaf natural fiber was confirmed as the most suitable candidate material for the hybrid polymer composites formulation. The materials selection process was continued using integrated Analytic Hierarchy Process (AHP) and Technique for Order Preference by Similarity to Ideal Solution (TOPSIS) methods whereby polypropylene was found as the most suitable type of thermoplastic matrix to be used for the hybrid polymer composites formulation. For the concept design development process, a new integrated TRIZ-Morphological Chart-AHP method was used during the conceptual design stage of the hybrid polymer composites automotive parking brake lever component and concept design 2 was selected as the final design concept based on the product design specifications. Rule of Mixtures (ROM) and Rule of Hybrid Mixtures (ROHM) micromechanical models were later employed to predict the Young's modulus of the short kenaf/glass fiber reinforced polypropylene composites where results show that positive hybridization effect was able to be achieved at minimum relative glass fiber content of approximately 87.5 volume percentage compared to kenaf/polypropylene single system for all

varying total fiber contents cases. Finally, the use of hybrid kenaf/glass fiber reinforced polypropylene composites also revealed better environmental performance through life cycle assessment analysis carried out using Eco-indicator 99 method at the end of the product development process. Results showed that approximately 20 percentage reduction of overall environmental impact is achieved by using hybrid kenaf/glass fiber reinforced polypropylene composites compared to glass fiber/polypropylene composites which further strengthened its potential for automotive parking brake lever application.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**REKABENTUK KONSEP SERENTAK KOMPOSIT HIBRID GENTIAN
SEMULA JADI/KACA DIPERKUAT TERMOPLASTIK UNTUK TUIL
BREK LETAK KENDERAAN AUTOMOTIF**

Oleh

MUHD RIDZUAN BIN MANSOR

November 2014

Pengerusi: Profesor Mohd Sapuan Salit, PhD, P.Eng

Fakulti: Kejuruteraan

Tesis ini membentangkan potensi aplikasi komposit polimer hibrid yang diperbuat daripada komposit gentian pendek semula jadi/kaca diperkuat termoplastik untuk membangunkan komponen tuil brek letak kenderaan automotif. Pendekatan kejuruteraan serentak telah digunapakai dalam keseluruhan proses pembangunan produk bagi meliputi pemilihan bahan, pembangunan rekabentuk konsep, analisis prestasi secara teori dan penilaian impak alam sekitar dalam memperoleh kekuatan struktur komponen yang diperlukan ke arah mencapai prestasi keselamatan dan pengoperasian. Kaedah Proses Hirarki Beranalitis (AHP) telah diaplikasikan pada peringkat permulaan dalam proses pemilihan bahan di mana gentian semula jadi kenaf disahkan sebagai calon bahan yang paling sesuai untuk formulasi komposit polimer hibrid tersebut. Proses pemilihan bahan seterusnya disambung menggunakan kaedah integrasi Proses Hirarki Beranalitis (AHP) dan Teknik untuk Susunan Berkeutamaan menurut Persamaan kepada Penyelesaian Ideal (TOPSIS) di mana polipropilena telah didapati merupakan jenis matrik termoplastik yang paling sesuai digunakan untuk formulasi komposit polimer hibrid tersebut. Untuk proses pembangunan rekabentuk, suatu kaedah baru bersepadu TRIZ-Carta Morfologi-AHP telah digunakan semasa peringkat rekabentuk konsep bagi komponen tuil brek letak kenderaan automotif komposit polimer hibrid dan rekabentuk konsep 2 telah dipilih sebagai rekabentuk konsep akhir berdasarkan spesifikasi rekabentuk produk. Model mikromekanikal Hukum Campuran (ROM) dan Hukum Campuran Hibrid (ROHM) seterusnya telah digunakan bagi meramalkan modulus Young komposit gentian pendek kenaf/kaca diperkuat polipropilena yang mana

keputusan menunjukkan kesan penghibridan yang positif mampu diperoleh pada kandungan relatif gentian kaca minima sebanyak kira-kira 87.5 peratus isipadu berbanding sistem tunggal kenaf/polipropilena untuk semua kes kandungan keseluruhan gentian yang berbeza. Akhir sekali, penggunaan komposit gentian kenaf/kaca diperkuat polipropilena juga menunjukkan prestasi alam sekitar yang lebih baik melalui analisis penilaian alam sekitar yang dijalankan menggunakan kaedah Petunjuk-Eko 99 di akhir proses pembangunan produk. Keputusan menunjukkan kira-kira 20 peratus penurunan keseluruhan impak alam sekitar diperoleh dengan menggunakan komposit hibrid gentian kenaf/kaca diperkuat polipropilena berbanding komposit gentian kaca/polipropilena yang mana mengukuhkan lagi potensinya bagi aplikasi tuil brek letak kenderaan automotif.

ACKNOWLEDGEMENTS

In the name of Allah, the Most Gracious and the Most Merciful.

Alhamdulillah, all praise to Allah for the strengths and His blessing in completing this thesis. First and foremost, I wish to express my special appreciation and thanks to Prof. Ir. Dr. Mohd Sapuan Salit, Chairman of the Supervisory Committee for his dedications and overwhelming guidance throughout the completion of the research. I am also very thankful to the members of the Supervisory Committee: Assoc. Prof. Dr. Edi Syams Zainudin, Assoc. Prof. Dr. Hambali Ariff@Arep and Assoc. Prof. Dr. Nuraini Abdul Aziz for your most valuable contributions and assistances in this research. I also wish to extend my deepest gratitude to Universiti Teknikal Malaysia Melaka and Jabatan Pengajian Tinggi, Kementerian Pendidikan Malaysia for providing the opportunity and supports especially through the financial scholarship in pursuing my doctoral study.

Last but not least, I wish to dedicate my heartiest thanks to my beloved parents: Mansor Johari and Ramlah Jusoh, family members and dearest friends for your precious encouragements and endless supports given throughout the entire course of my study. To my beloved wife Ainur Zaireen and my precious children Muhammad Adam and Naurah Amani: Thank you for everything and this is for all of you.

I certify that a Thesis Examination Committee has met on 6 November 2014 to conduct the final examination of Muhd Ridzuan bin Mansor on his thesis entitled "Concurrent Conceptual Design of Hybrid Natural/Glass Fiber Reinforced Thermoplastic Composites for Automotive Parking Brake Lever" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

Barkawi bin Sahari, PhD

Professor/Ir
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Zulkiflle bin Leman, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Thomas Choong Shean Yaw, PhD

Professor/Ir
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Salim Hiziroglu, PhD

Professor
Department of Natural Resource Ecology and Management
Oklahoma State University
(External Examiner)



ZULKARNAIN ZAINAL, PhD

Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 19 March 2015

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Mohd Sapuan Salit, PhD, Ir.

Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Edi Syams Zainudin, PhD

Associate Professor
Faculty of Engineering,
Universiti Putra Malaysia
(Member)

Nuraini Abdul Aziz, PhD

Associate Professor
Faculty of Engineering,
Universiti Putra Malaysia
(Member)

Hambali Arep@Ariff, PhD

Associate Professor
Faculty of Manufacturing Engineering,
Universiti Teknikal Malaysia Melaka
(Member)

BUJANG KIM HUAT, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: _____ Date: _____

Name and Matric No.: MUHD RIDZUAN BIN MANSOR, GS33519

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____

Name of Chairman
of Supervisory
Committee:

Prof. Ir. Dr. Mohd Sapuan Salit

Signature: _____

Name of Member of
Supervisory
Committee:

Assoc. Prof. Dr. Edi Syams Zainudin

Signature: _____

Name of Member of
Supervisory
Committee:

Assoc. Prof. Dr. Nuraini Abdul Aziz

Signature: _____

Name of Member of
Supervisory
Committee:

Assoc. Prof. Dr. Hambali Arep@Ariff

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	iii
ACKNOWLEDGEMENTS	v
APPROVAL	vi
DECLARATION	v
LIST OF TABLES	xiii
LIST OF FIGURES	xv
LIST OF ABBREVIATIONS	xvii
 CHAPTER	
 1 INTRODUCTION	 1
1.1 Background	1
1.2 Problem Statements	4
1.3 Research Objectives	6
1.4 Significance of Study	6
1.5 Scopes and Limitation of Study	6
1.6 Structure of Thesis	7
 2 LITERATURE REVIEW	 9
2.1 Introduction	9
2.2 Automotive Parking Brake Lever	9
2.3 Product Design Specifications of Parking Brake Lever	12
2.3.1 Review on Requirements for Automotive Design	14
2.3.2 Product Design Specifications for Automotive Parking Brake Lever	22
2.4 Hybrid Natural Fiber Composites	22
2.5 Concurrent Design of Hybrid Natural Fiber Composites Structures	25
2.5.1 Materials Selection of Natural Fiber Composites	25
2.5.2 Conceptual Design of Hybrid Natural Fiber Composites	32
2.5.3 Performance Prediction of Natural Fiber Composites	35
2.5.4 Environmental Life Cycle Assessment of Natural Fiber Composites	38
2.6 Summary	42

3	RESEARCH METHODOLOGY	43
3.1	Introduction	43
3.2	The Overall Structure of the Research Works	43
3.3	Parking Brake Lever Model Force Analysis	46
3.4	Market Investigation	47
3.5	Product Design Specifications	48
3.6	Materials Selection of Hybrid Natural Fiber Composites	49
3.6.1	Materials Selection of Best Natural Fiber for Hybrid Natural/Glass Fiber Composites AHP Method	50
3.6.1.1	Development of AHP Hierarchical Framework	52
3.6.1.2	Performing Judgment using Pair-Wise Comparison	54
3.6.1.3	Synthesizing Pair-Wise Judgments and Calculating Priority Vectors	56
3.6.1.4	Performing Consistency Analysis using Consistency Ratio	56
3.6.1.5	Results Validation using Sensitivity Analysis	57
3.6.2	Materials Selection of Best Thermoplastic Matrix for Hybrid Natural/Glass Fiber Composites using integrated AHP-TOPSIS method	58
3.6.2.1	Weighting of Criteria using AHP Method	62
3.6.2.2	Ranking of Alternatives using TOPSIS Method	64
3.7	Conceptual Design Development and Selection of Automotive Parking Brake Lever using Hybrid Natural Fiber Composites	65
3.8	Modeling of Hybrid Natural Fiber Composites	72
3.8.1	Modeling of Kenaf Reinforced Polypropylene Composites	73
3.8.2	Modeling of Hybrid Kenaf/Glass Fiber Reinforced Polypropylene Composites	75
3.9	Life Cycle Assessment of Hybrid Natural Fiber Composites	80
4	RESULTS AND DISCUSSION	85
4.1	Introduction	85
4.2	Materials Selection of Natural Fiber and Matrix Materials for Hybrid Natural/Glass Fiber Thermoplastic Composites Formulation	85
4.2.1	Materials Selection of Best Natural Fiber for Hybrid Natural/Glass Fiber Thermoplastic	85

	Composites Formulation using AHP Method	
4.2.2	Materials Selection of Best Thermoplastic Matrix for Hybrid Natural/Glass Fiber Thermoplastic Composites Formulation using Integrated AHP-TOPSIS Method	89
4.3	Conceptual Design Development and Selection of Hybrid Natural/Glass Fiber Thermoplastic Composites Automotive Parking Brake Lever using Integrated TRIZ-Morphological Chart-AHP Method	93
4.3.1	Final Conceptual Design Development using Integrated TRIZ-Morphological Chart-AHP Method	93
4.3.2	Final Conceptual Design Selection using AHP Method	98
4.4	Theoretical Modeling of Final Natural Fiber Reinforced Thermoplastic Composites and Hybrid Natural/Glass Fiber Reinforced Thermoplastic Composites Young's Modulus	101
4.4.1	Theoretical Modeling of Final Natural Fiber Thermoplastic Composites Young's Modulus using Halpin-Tsai Equation	101
4.4.2	Theoretical Modeling of Final Hybrid Natural/Glass Fiber Thermoplastic Composites Young's Modulus using Rule of Mixture (ROM) and Rule of Hybrid Mixture (RoHM)	103
4.5	Potential Environmental Impact Evaluation of New Automotive Center Lever Parking Brake Lever Design using Hybrid Natural/Glass Fiber Reinforced Thermoplastic Composites and Synthetic Composites	109
5	CONCLUSION AND RECOMMENDATIONS FOR FUTURE RESEARCH	113
5.1	Conclusion	113
5.2	Recommendations for Future Research	115
	REFERENCES	117
	APPENDICES	139
	BIODATA OF STUDENT	143
	LIST OF PUBLICATIONS	145

LIST OF TABLES

Table	Page
2.1 Summary of product design specifications elements for various automotive components	16
2.2 Summary of several developed hybrid natural fiber composites	24
2.3 Examples of AHP applications in composites materials selection	28
2.4 Summary of the application of TRIZ in concurrent engineering for product development	34
2.5 Summary of micromechanical model used for prediction of composites mechanical properties	37
2.6 Examples of LCA application involving natural fiber composites	40
3.1 Decision criteria used in the AHP analysis based on parking brake lever product design specifications	53
3.2 Importance scale for pair-wise comparison analysis	55
3.3 Mechanical properties of lignocellulosic and glass fibers	55
3.4 Thermoplastic matrix material properties	60
3.5 Decision criteria used in the AHP-TOPSIS analysis for the thermoplastic matrices based on the parking brake lever PDS	61
3.6 Importance scale for pair-wise comparison analysis	63
3.7 Parking brake lever PDS elements and their equivalent design indicators	68
3.8 Summary of kenaf fiber polymer composites parking brake lever concept design overall attributes	71
3.9 Shape fitting factor, ζ values	74
3.10 Properties of kenaf fiber and thermoplastic matrices	74
3.11 Material properties of composite fibers and resin	75
3.12 Hybrid short kenaf/glass-fiber/polypropylene polymer composite material properties	76
3.13 Composite micromechanical models	82
3.14 Summary of predicted composites properties	82
3.15 Life cycle inventory and equivalent indicator used based on Eco-indicator 99 method	83
4.1 Rank of alternative priorities obtained by simulating three scenarios of sensitivity analysis for different main criteria with respect to goal	86
4.2 Decision matrix for selecting the best thermoplastic matrix	91
4.3 Normalized matrix	91
4.4 Weighted normalized matrix	91
4.5 The positive and negative ideal solution matrix	92

4.6	Separation of each alternative from the ideal solution and its relative closeness to the ideal solution	92
4.7	Contraction matrix for the kenaf fiber composites parking brake lever design	94
4.8	Design strategy based on identified TRIZ solution principles	95
4.9	Rank of alternative priorities obtained by simulating three scenarios of sensitivity analysis for different main criteria with respect to goal	100
4.10	Kenaf thermoplastic composites Young's modulus for longitudinal and transverse directions at varying fiber loadings	101
4.11	Kenaf thermoplastic composites Young's modulus at varying fiber aspect ratio	101
4.12	Predicted overall Young's modulus for the hybrid short kenaf/glass fiber reinforced polypropylene polymer composite using ROM and RoHM equations at different total fiber loadings	105
4.13	Overall LCA results	109

LIST OF FIGURES

Figure		Page
2.1	Overview of passenger vehicle parking brake system	10
2.2	Parking brake lever subsystem components	11
2.3	Example of Proton Wira center lever parking brake design in (a) assembly view, and (b) exploded view	11
2.4	Product design specification elements	12
2.5	Ecodesign strategies wheel	13
2.6	Example of arguments inflicted during materials selection	25
2.7	Stress-strain curve	31
2.8	Classification of composite micromechanical models	36
3.1	Selected research area in the product development process	44
3.2	Overall structure of research work	45
3.3	Forces acting on the parking brake lever	46
3.4	Automotive parking brake lever product design specifications	49
3.5	AHP methodology for materials selection of best type of natural fiber for hybrid natural/glass fiber composites	51
3.6	Hierarchical framework of decision problem in selecting the best natural fiber to be hybridized with glass fiber reinforced thermoplastic composites for automotive parking brake lever design based on the formulated PDS	53
3.7	Pair-wise comparison between alternative natural fibers with respect to the tensile strength mechanical property for strength sub-criteria	56
3.8	AHP-TOPSIS methodology for materials selection of best type of thermoplastic matrix for hybrid natural/glass fiber composites	59
3.9	Thermoplastic matrix materials selection main criteria and their corresponding material properties as sub-criteria	61
3.10	Pair-wise comparison matrix of sub-criteria with respect to Performance main criteria	63
3.11	Parking brake lever component and its assembly	66
3.12	The overall TRIZ-Morphological Chart-AHP conceptual design approach	67
3.13	AHP hierarchy framework for the kenaf fiber polymer composites parking brake lever concept design selection	69
3.14	Pair-wise comparison between alternative concept designs with respect to the maximum Von Mises stress value for strength sub-criteria	70

3.15	Overall methodology to determine hybrid short kenaf/glass fiber reinforced polypropylene composites Young's modulus	76
3.16	System boundaries for LCA	81
4.1	Overall results of the materials selection	86
4.2	Sensitivity graph of main criteria with respect to goal when priority vector of Performance (PR) is increased by 20% (from 33.3% to 53.3%)	87
4.3	Sensitivity graph of main criteria with respect to goal when priority vector of Weight (WE) is increased by 20% (from 33.3% to 53.3%)	88
4.4	Sensitivity graph of main criteria with respect to goal when priority vector of Cost (CS) is increased by 20% (from 33.3% to 53.3%)	88
4.5	Results of local weight for main criteria and sub-criteria using AHP	89
4.6	Results of global weight for sub-criteria using AHP	89
4.7	Rank of thermoplastic matrix based on AHP-TOPSIS score	93
4.8	Morphological chart of the TRIZ solution principles and their related functional design features	96
4.9	3D CAD model of the new parking brake lever concept designs	98
4.10	Overall AHP results of the concept design selection	99
4.11	Sensitivity graph of main criteria with respect to goal when priority vector of Performance is increased by 20% (from 54.0% to 74.0%)	99
4.12	Young's modulus of the kenaf polymer composites at longitudinal and transverse direction for different fiber loading conditions (constant fiber aspect ratio=27.78; fiber length 1mm; fiber diameter 36 μ m)	102
4.13	Young's modulus of the kenaf polymer composites for different fiber aspect ratio (constant fiber loading at 30 vol%)	102
4.14	Hybrid kenaf/glass fiber/polypropylene composite Young's modulus at 40% total fiber loading	104
4.15	Hybrid kenaf/glass fiber/polypropylene composite Young's modulus at different total fiber loading values	108
4.16	Comparison of environmental impacts between GF/PP and KF/GF/PP composites for parking brake lever design	110
4.17	Eco-indicator contribution by life cycle stages for parking brake lever using glass fiber/polypropylene and kenaf/glass fiber/polypropylene composites	111

LIST OF ABBREVIATIONS

3D	Three Dimensional
ABS	Acrylonitrile Butadiene Styrene
AHP	Analytic Hierarchy Process
ANP	Analytic Network Process
ARIZ	Algorithms Of Inventive Problem Solving
EPB	Electric Parking Brake
CAD	Computer-Aided Design
CDCSMS	Concurrent Design Concept Selection And Materials Selection
CE	Concurrent Engineering
CI	Consistency Index
CLT	Classical Laminate Theory
CMVSS	Canadian Motor Vehicle Safety Regulations
CO ₂	Carbon Dioxide
CR	Consistency Ratio
CS	Customer Satisfaction
CTQ	Cost, Time And Quality
DFA	Design For Assembly
EFB	Empty Fruit Bunch
ELECTRE	Elimination And Et Choice Translating Reality
EU	European Union
FMEA	Failure Mode And Effect Analysis
FMVSS	Federal Motor Vehicle Safety Standards
HDPE	High Density Polyethylene
IPCC	Intergovernmental Panel On Climate Change
IROM	Inverse Rule Of Mixtures
ISO	International Standard Organization
LCA	Life Cycle Assessment
LDPE	Low Density Polyethylene
LKTN	Lembaga Kenaf Dan Tembakau Negara
MADM	Multiple Attribute Decision Making
MCDM	Multi-Criteria Decision Making
MMC	Metal Matrix Composites
MODM	Multiple Objective Decision Making
MoM	Meaning Of Material
NFC	Natural Fiber Composites
NFRP	Natural Fiber Reinforced Polymer
NHTSA	National Highway Traffic Safety Administration
NVH	Noise, Vibration And Harshness
PA 6	Polyamide 6
PDS	Product Design Specifications
PGP	Pre-Emptive Goal Programming
PLLA	Poly-L-Lactide
PP	Polypropylene
PS	Polystyrene

PSI	Preference Selection Index
QFD	Quality Function Deployment
RI	Random Consistency Index
RMS	Reconfigurable Manufacturing System
ROHM	Rule Of Hybrid Mixtures
ROM	Rule Of Mixtures
SME	Small And Medium Enterprise
TOPSIS	Technique For Order Preference By Similarity To Ideal Solution
TPNR	Thermoplastic-Natural Rubber
TRIZ	Theory Of Inventive Problem Solving
UCPTE	European Union For The Co-Ordination Of Production And Transmission Of Electricity
UNECE	United Nations Economic Commissions For Europe
VIKOR	Vise Kriterijumska Optimizacija Kompromisno Resenje
WBCSD	World Business Council For Sustainable Development
WPIM	Weighted Property Index Method

CHAPTER 1

INTRODUCTION

1.1 Background

Traditionally, the design of automotive related products or components is focused on achieving operational performance and meeting safety regulations. For automotive brake component design, various performance and safety regulations must be complied such as the US Federal Motor Vehicle Safety Standards (FMVSS) 571.135 and United Nations Economic Commissions for Europe (UNECE) R13-H (DOT, n.d.; UNECE, n.d.). However, due to the current increasing awareness on environmental impact and subsequently the need towards sustainability, new automotive product designs must also adhere to environmental related requirements imposed by government bodies such as vehicle end-of-life regulation and hazardous substance as well as CO₂ emission performance standard for new passenger vehicles which includes vehicle weight reduction criteria (2000/53/EC, 2000; 2009/443/EC, 2009). Thus, the change has driven new trend in automotive product design and its whole product development process in order to meet the performance, safety and sustainability requirements (Fontaras & Samaras, 2010).

In conjunction to that, many efforts have been made to comply with the legislations by automakers to sustain their product competitiveness in the targeted market. Among the most promising solution towards achieving in both weight reduction and recyclability targets is by using natural fiber composites (NFC) as the substitute material for making car components such as door panel, door trims, dashboards, rear trays etc. (dos Santos et al., 2008; Holbery & Houston, 2006). However, the use of similar material in higher load bearing automotive applications is still limited due to their lower mechanical properties compared to synthetic polymer composites as well as metal alloys. Nevertheless, NFC offers lower density, higher specific strength and Young's modulus as well as good impact properties compared to synthetic polymers (El-Shekeil et al., 2012; Monteiro et al., 2009) and most notably, they are renewable, recyclable and biodegradable source of materials which makes them able to be produced at lower cost (Koronis et al., 2013; Qatu, 2011).

Looking at national perspective, there are many economically available natural fiber resources in Malaysia that can be processed into NFC. The most promising is kenaf fiber which is currently gaining higher focus to become among the top national commodity crop under the supervision of

the Malaysian Lembaga Kenaf dan Tembakau Negara (LKTN) (Anonymous, 2014c). According to the Malaysia LKTN statistics, kenaf plants are currently being planted across Perak, Kelantan, Terengganu, Pahang and Selangor which covers total cultivation area of approximately 2,000 hectares in 2013 and is expected to grow to 10,000 hectares by 2020, showing the vast availability of the resource to be exploited to support mass production activities. Apart from that, kenaf fibers are also currently priced between 1,700 to 2,200/tonne in 2014 compared to jute fiber (price between Ringgit Malaysia 1,590-1,321/tonne) and meshta fiber (price between Ringgit Malaysia 2,205-2,102/tonne), indicating its price competitiveness with other major fibers resources in Asia. The statistics highlight the potential of gaining economical advantage of utilizing kenaf fibers for composites product development especially for the country.

In addition to economic advantage, kenaf fibers also have comparable mechanical properties with many commercially available natural fibers in the market such as jute, flax and hemp which makes them suitable for structural applications. Akil et al. (2011) pointed that kenaf fibers have high tensile strength ranging between 295 to 930 MPa which is comparable to jute (400-800 MPa), flax (800-1500 MPa) and hemp (550-900 MPa). In addition, kenaf fibers also have high Young modulus property approximately 53 GPa which is comparable to jute (10-30 GPa), flax (60-80 GPa) and hemp (70 GPa). They also reported that kenaf fibers inherent superior toughness and high aspect ratio compared to other natural fibers which makes it very suitable to be used as reinforcing fiber especially in thermoplastic composites. Another distinctive advantage of kenaf fibers compared to other natural fibers is in term of lightweight property, whereby kenaf fiber density is reported to be ranging from 1.2 to 1.4 g/cm³ which is comparable to jute (1.46 g/cm³), hemp (1.48 g/cm³) and flax (1.4 g/cm³) (Akil et al., 2011). In addition, kenaf fibers has high cellulose content (72 wt%) which contribute to higher tensile properties due to its crystalline structure comparable with other establish natural fiber used in production cars such as hemp (68 wt%), sisal (65 wt%), jute (61-71 wt%) and flax (71 wt%) (Faruk, Bledzki, Fink, & Sain, 2012).

On the other hand, the application of kenaf fibers for product development may also provide additional benefits apart from renewability and biodegradability for the environment. One notable benefit is by helping to reduce the carbon dioxide level in the atmosphere through kenaf plant cultivation. The photosynthesis process during kenaf cultivation was reported able to produce higher rate of carbon dioxide to oxygen conversion (23.4 mg CO₂/dm²/h) compared to conventional trees (8.7 mg CO₂/dm²/h) under 1000 μ mol/cm²/s (Lee et al., 2014).

Kenaf based polymer composites can be produced either using thermosetting matrix such as epoxy and polyester or using thermoplastic matrix such as polypropylene (PP) and high density polyethylene (HDPE).

However, the use of thermoplastic matrix is of more interest due to its eco-friendly property which are able to be completely recycled as well as low cost and low processing temperature. The low processing temperature is also an advantage considering that natural fiber's mechanical and physical properties will deteriorate when exposed to high temperature of more than 300°C (Mohanty et al., 2004). Kenaf based thermoplastic composites are also able to be manufactured economically in variety of processes such as resin transfer molding, compression molding, injection molding as well as hand lay-up technique. Apart from that, the mechanical properties of the kenaf based thermoplastic composites can also be economically improved using chemical modifications such as fiber treatment and coupling agents (Li et al., 2007). Due to advantages, kenaf composites have been applied for automotive application primarily for trim components such as seatbacks, package trays, door panels and headliners. It is reported that kenaf composites have been applied for developing automotive interiors since the mid-1990s by Toyota Boshoku Corporation. The Japanese carmaker first started using kenaf composites to produce vehicle door trim component, and currently applying similar material to produce other components in its high-end vehicle models (Dungani et al., 2014; Loh et al., 2015). Other application on related NFRP composites by car makers for vehicle weight reduction while complying with the environmental criteria are in the case of Mercedes Benz A-class and Ford Model U hybrid-electric car (Marsh, 2003).

Despite the advantages that NFC able to offer, their hydrophilic and lower mechanical strength nature has limited their application especially to aesthetically related automotive components such as dashboard, floor pan and interior accessories (Akil et al., 2011; Faruk et al., 2012; Friedrich & Almajid, 2013). To address the issue, researchers has also developed hybrid polymer composites where the natural based fiber is combined with synthetic based fiber such as glass fiber using the same matrix (Davoodi et al., 2010; Kumar et al., 2010; Rao et al., 2011).

In general, hybrid composites are made from the combination of pure synthetic fibers (glass/carbon), combination of synthetic fiber with natural fiber (glass/kenaf) or combination of pure natural fibers (oil palm empty fruit bunch/jute) either in unidirectional, woven and randomly fiber orientation (Davoodi et al., 2012; Dong & Davies, 2012; Jawaaid et al., 2012). In the hybridization method, usually two different types of fiber are combined together to form either interply or laminate hybrid, intraply or tow-by-tow hybrid, intimacy mixed hybrid and of type of mixtures (Zhang et al., 2012). The properties of a hybrid composite depend on the fiber content, fiber length, orientation of fibers, extent of intermingling of fibers, fiber to matrix interface, layering pattern of both fibers and also dependent on the failure strain of individual fibers (Jawaaid et al., 2010). The hybrid technique main advantage is giving balance to the performance between the combined fibers such as improving the tensile and flexural properties and improving the chemical resistance of the initial single fiber composites system (Aji et al., 2011). In another report, Burgueno et al. suggested that

through hybridization, the natural fiber based reinforced polymer composites mechanical properties such as strength and Young's modulus are enhanced due to the direct contribution of the stiffer and stronger synthetic fiber, as well as gaining higher dimensional stability with respect to moisture absorption due to the barrier provided by the more impermeable synthetic fibers (Burgueño et al., 2005). Apart from that, a balance of cost are also achieved by utilizing a combination of cheaper type of fiber to reduce the amount of more expensive type of fiber (such as combining low cost natural fiber with higher cost synthetic fiber) in making up the hybrid laminates in order to gain comparable mechanical strength and chemical property as the laminates made from the expensive fibers alone (Jarukumjorn & Suppakarn, 2009).

In this research, the potential of introducing hybrid natural fiber reinforced thermoplastic composites; more specifically using hybrid kenaf/glass fiber reinforced polypropylene composites is explored towards the development of automotive parking brake lever component. The main research is concentrated within the concurrent conceptual design and materials selection framework in the product development process which covers aspects in conceptual design development and selection, modeling of natural fiber composites, product environmental performance assessment and hybrid natural fiber composites materials selection. Among the concurrent engineering design tools applied in this research are Theory of Inventive Problem Solving (TRIZ), Morphological Chart, Analytic Hierarchy Process (AHP) and Life Cycle Assessment (LCA) method. In the end of this research, a new conceptual design of automotive parking brake lever utilizing hybrid kenaf/glass fiber reinforced polypropylene composites is developed which successfully concur with the product design specifications.

1.2 Problem Statements

Conceptual design is regarded as the most important aspects in concurrent engineering (CE) approach as significant total product development cost and product quality is decided during the design stage (Chiu & Okudan, 2014; Ghazilla et al., 2013). The cost is often associated with the higher amount of resources and time in developing the final concept design of the product and identifying the materials to best suit the intended application based on the product design specifications. Apart from that, extra efforts are also embedded within the conceptual design scope in providing useful early insights to product designers on the final product performance such as structural and environmental aspects in order to minimize the risks and possible errors during later product development process. Henceforth, faster and cheaper new product may be developed with higher quality to achieve the cost, time and quality (CTQ) improvement and consequently increasing the probability of achieving successful product launch to the market (Sapuan et al., 2006).

In spite of the successful adoption of CE approach in product development as conventional materials such as metal, its implementation in composites design is still limited (Liu et al., 2004; Yang & Nezu, 1998). Moreover, implementation of CE in composites design related to the application of semi-structural and structural components using NFC are far scarcer compared to using synthetic composites and metal-based materials due to lower structural properties and reduce dimensional stability when exposed to high moisture especially for automotive applications (Duflou et al., 2009; Imihezri et al., 2005; Sapuan, 2005b). Hybridization method has been regarded as the potential solution in boosting NFC application in automotive structural design. One example is for automotive bumper beam component using hybrid kenaf/glass fiber reinforced epoxy composites (Davoodi et al., 2011). However, for other automotive structural components especially for automotive parking brake lever application, the implementation of similar hybrid composites is still limited despite the balance in performance, cost and sustainability advantages they offer compared to synthetic composites thus making it a winning candidate to reduce the use of synthetic composites for semi-structural and structural automotive applications if the design barrier can be demolished.

One of the possible solutions to break the design barrier using hybrid NFC towards automotive parking brake lever application automotive applications is by applying innovative concurrent engineering tools for the development of natural fiber composites product. Among them is through implementing innovative idea generation-concept development-concept selection method during the product conceptual design stage to obtain NFC-friendly component geometry which satisfy the product design specifications. Apart from that, multi-criteria decision making (MCDM) method may also be applied for the materials selection of NFC during the conceptual design stage of the product. The MCDM method capability of incorporating multiple and often conflicting design requirements with varying material properties in the analysis all at the same time will enable systematic and justified decision making process to be performed. Thus, optimum decision on the best natural fiber candidate materials to satisfy the designated product function may be obtained within shorter time.

Other related tools that may be implemented during the component conceptual design process to aid the design process are modeling of the final hybrid NFC to determine the material structural performance as well as environmental performance assessment to determine the potential impact of the new component throughout its entire life cycle. The information obtained from both tools is very useful to composite designers in conducting more thorough decision making process during the conceptual design of the product.

1.3 Research Objectives

The research objectives are as follows:-

- i) To select the best type of natural fiber and thermoplastic matrix materials for hybrid natural fiber composites formulation based on the parking brake lever product design specifications
- ii) To develop conceptual design of new automotive center lever type parking brake lever using hybrid natural fiber composites and determine the final design concept using TRIZ-Morphological Chart-AHP method
- iii) To determine the Young's modulus mechanical property of the final natural fiber composites and hybrid natural fiber composites using theoretical modeling method
- iv) To evaluate the potential environmental impact effect of the new automotive center lever type parking brake lever design using hybrid natural fiber composites and synthetic composites.

1.4 Significance of Study

It is expected that the findings of this study may add to the effort to realize the potential of using hybrid kenaf/glass fiber reinforced NFC in development of new automotive center lever type parking brake lever component. Consequently, the new hybrid NFC can provide the sought after alternative towards improving the lightweight property of the current product while able to adhere successfully to the intended design requirements and better overall sustainable performance. In addition, findings of this study may also help to enhance the knowledge in the implementation of CE approach for NFC product design.

1.5 Scopes and Limitation of Study

The scopes of the present research is limited to the conceptual design stage of natural fiber composite for automotive center lever type parking brake lever application which includes market investigation, development of the product design specification, development of new product conceptual design and final conceptual design selection, materials selection, modeling of NFC and product environmental life cycle assessment. In addition, focus of the research is also given to the utilization of kenaf natural fiber, glass fiber and polypropylene thermoplastic matrix in the formulation of the hybrid natural/synthetic thermoplastic composites for the parking brake lever application.

1.6 Structure of the Thesis

This thesis is structured into 5 chapters. The first chapter is an introduction followed by Chapter 2 which presents comprehensive literature review on relevant areas associated with the topics in this research. Next is Chapter 3 which presents the overall research methodology applied in this research. The research methodology chapter composed of the overall structure of the research works, conceptual design and materials selection for the new automotive parking brake lever using hybrid NFC, modeling of NFC and environmental life cycle assessment for the new parking brake lever design.

The following Chapter 4 presents the results and discussion of the research works. Chapter 4 is divided into four main sections, which covers materials selection for the best type of natural fiber and thermoplastic matrix for the hybrid composites formulation, development of new conceptual design and final concept design selection for the automotive parking brake lever, modeling of the final single system composites and hybrid natural/glass fiber reinforced thermoplastic composites Young modulus performance as well as evaluation of the potential environmental impact of the new automotive parking brake lever design using hybrid natural/glass fiber reinforced thermoplastic composites and synthetic composites.

Finally, in Chapter 5, the overall conclusion and recommendation for future works are presented.

REFERENCES

- 2000/53/EC, D. THE EUROPEAN PARLIAMENT AND OF THE COUNCIL on end-of-life vehicle (2000).
- 2009/443/EC, D. THE EUROPEAN PARLIAMENT AND OF THE COUNCIL on emission performance standards for new passenger car (2009).
- 78/632/EEC, D. EUROPEAN DIRECTIVE 78/632/EEC on interior fittings of motor vehicles (1978).
- Abdi, M. R., & Labib, A. W. (2003). A design strategy for reconfigurable manufacturing systems (RMSs) using Analytical Hierarchical Process (AHP): A case study. *International Journal of Production Research*, 41(10), 2273–2299.
- Abu Talib, A. R., Ali, A., Badie, M. A., Lah, N. A. C., & Golestaneh, A. F. (2010). Developing a hybrid, carbon/glass fiber-reinforced, epoxy composite automotive drive shaft. *Materials and Design*, 31(1), 514–521.
- Ahmed, K. S., & Vijayarangan, S. (2006). Elastic property evaluation of jute-glass fibre hybrid composite using experimental and CLT approach. *Indian Journal of Engineering and Materials Sciences*, 13(5), 435–442.
- Aji, I. S., Zainudin, E. S., Khalina, A., Sapuan, S. M., & Khairul, M. D. (2011). Studying the effect of fiber size and fiber loading on the mechanical properties of hybridized kenaf/PALF-reinforced HDPE composite. *Journal of Reinforced Plastics and Composites*, 30(6), 546–553.
- Aji, I., Zainudin, E., Abdan, K., Sapuan, S. M., & Khairul, M. (2012). Mechanical properties and water absorption behavior of hybridized kenaf/pineapple leaf fibre-reinforced high-density polyethylene composite. *Journal of Composite Materials*, 47(8), 979–990.
- Akil, H. M., De Rosa, I. M., Santulli, C., & Sarasini, F. (2010). Flexural behaviour of pultruded jute/glass and kenaf/glass hybrid composites monitored using acoustic emission. *Materials Science and Engineering: A*, 527(12), 2942–2950.

- Akil, H. M., Omar, M. F., Mazuki, A. A. M., Safiee, S., Ishak, Z. A. M., & Abu Bakar, A. (2011). Kenaf fiber reinforced composites: A review. *Materials and Design*, 32(8-9), 4107–4121.
- Alamri, H., & Low, I. M. (2013). Effect of water absorption on the mechanical properties of nanoclay filled recycled cellulose fibre reinforced epoxy hybrid nanocomposites. *Composites Part A: Applied Science and Manufacturing*, 44(0), 23–31.
- Albiñana, J. C., & Vila, C. (2012). A framework for concurrent material and process selection during conceptual product design stages. *Materials and Design*, 41(0), 433–446.
- Al-Harbi, K. M. A.-S. (2001). Application of the AHP in project management. *International Journal of Project Management*, 19(1), 19–27.
- AlMaadeed, M. A., Kahraman, R., Noorunnisa Khanam, P., & Madi, N. (2012). Date palm wood flour/glass fibre reinforced hybrid composites of recycled polypropylene: Mechanical and thermal properties. *Materials and Design*, 42(0), 289–294.
- Almeida, C. M. V. B., Rodrigues, A. J. M., Bonilla, S. H., & Giannetti, B. F. (2010). Emergy as a tool for Ecodesign: Evaluating materials selection for beverage packages in Brazil. *Journal of Cleaner Production*, 18(1), 32–43.
- Almeida Júnior, J. H. S., Ornaghi Júnior, H. L., Amico, S. C., & Amado, F. D. R. (2012). Study of hybrid intralaminar curaua/glass composites. *Materials and Design*, 42(0), 111–117.
- Alves, C., Ferrão, P. M. C., Silva, A. J., Reis, L. G., Freitas, M., Rodrigues, L. B., & Alves, D. E. (2010). Ecodesign of automotive components making use of natural jute fiber composites. *Journal of Cleaner Production*, 18(4), 313–327.
- Anonymous. (2006). ISO EN 14044-2006: Environmental Management - Life Cycle Assessment - Requirements and Guidelines. International Standard Organization.
- Anonymous. (2012). Thermoplastic resin pricing. Retrieved June 24, 2014, from <http://www.plasticsnews.com/resin-pricing/commodity-tps.htm>
- Anonymous. (2014a). Automotive Plastics Market for Passenger Cars, By Type (Polypropylene, Polyurethane, HDPE, ABS, Polycarbonate &

- Composites), Application (Interior, Exterior & Under Bonnet) & Geography— Trends & Forecasts to 2018. Retrieved June 24, 2014, from <http://www.marketsandmarkets.com/Market-Reports/automotive-plastics-market-passenger-cars-506.html>
- Anonymous. (2014b). Ecodesign strategies guidelines. Retrieved June 24, 2014, from <http://www.matbase.com/guidelines.html>
- Anonymous. (2014c). Malaysian Kenaf. *Lembaga Kenaf dan Tembakau Negara*. Retrieved June 24, 2014, from <http://www.lktn.gov.my/news.php>
- Anonymous. (2014d). Nessei Injection Moulding Machine. Retrieved June 24, 2014, from <http://www.pitfallsinmolding.com/energyeffic1.html>
- Anonymous. (2014e). Parking Brake: Lexus technical training notes. Retrieved June 01, 2014, from www.autoshop101.com/forms/brake06.pdf
- Anuar, H., Wan Busu, W. N., Ahmad, S. H., & Rasid, R. (2008). Reinforced thermoplastic natural rubber hybrid composites with Hibiscus Cannabinus, L and short glass fiber - Part I: Processing parameters and tensile properties. *Journal of Composite Materials*, 42(11), 1075–1087.
- Ardente, F., Beccali, M., Cellura, M., & Mistretta, M. (2008). Building energy performance: A LCA case study of kenaf-fibres insulation board. *Energy and Buildings*, 40(1), 1–10.
- Arib, R. M. N., Sapuan, S. M., Ahmad, M. M. H. M., Paridah, M. T., & Zaman, H. M. D. K. (2006). Mechanical properties of pineapple leaf fibre reinforced polypropylene composites. *Materials and Design*, 27(5), 391–396.
- Ariff, H., Salit, M. S., Ismail, N., & Nukman, Y. (2009). Use of analytical hierarchy process (AHP) for selecting the best design concept. *Jurnal Teknologi*, 49(A), 1–18.
- Ashby, M. F. (2005). *Materials Selection in Mechanical Design* (Third Edit.). Oxford: Elsevier Butterworth-Heinemann.
- Ashby, M. F., & Bréchet, Y. J. M. (2003). Designing hybrid materials. *Acta Materialia*, 51(19), 5801–5821.

- Ashori, A., & Sheshmani, S. (2010). Hybrid composites made from recycled materials: Moisture absorption and thickness swelling behavior. *Bioresource Technology*, 101(12), 4717–4720.
- Athijayamani, A., Thiruchitrambalam, M., Natarajan, U., & Pazhanivel, B. (2009). Effect of moisture absorption on the mechanical properties of randomly oriented natural fibers/polyester hybrid composite. *Materials Science and Engineering: A*, 517(1–2), 344–353.
- Atiqah, A., Maleque, M. A., Jawaidd, M., & Iqbal, M. (2014). Development of kenaf-glass reinforced unsaturated polyester hybrid composite for structural applications. *Composites Part B: Engineering*, 56(0), 68–73.
- Badie, M. A., Mahdi, E., & Hamouda, A. M. S. (2011). An investigation into hybrid carbon/glass fiber reinforced epoxy composite automotive drive shaft. *Materials and Design*, 32(3), 1485–1500.
- Bahraminasab, M., Sahari, B. B., Edwards, K. L., Farahmand, F., Jahan, A., Hong, T. S., & Arumugam, M. (2014). On the influence of shape and material used for the femoral component pegs in knee prostheses for reducing the problem of aseptic loosening. *Materials and Design*, 55(0), 416–428.
- Bakare, I. O., Okieimen, F. E., Pavithran, C., Abdul Khalil, H. P. S., & Brahmakumar, M. (2010). Mechanical and thermal properties of sisal fiber-reinforced rubber seed oil-based polyurethane composites. *Materials and Design*, 31(9), 4274–4280.
- Beer, F. P., Johnston, E. R., Dewolf, J. T., & Mazurek, D. F. (2012). *Mechanics of Materials* (6th Edit.). New York: McGraw-Hill.
- Behzadian, M., Otaghsara, S. K., Yazdani, M., & Ignatius, J. (2012). A state-of-the-art survey of TOPSIS applications. *Expert Systems with Applications*, 39(17), 13051–13069.
- Belingardi, G., Chiandussi, G., Gobetto, E., & Scattina, A. (2010). Bonnet weight reduction and VRU protection: Design proposals implementating non-conventional materials. *International Journal of Automotive Technology*, 11(6), 831–842.
- Benyus, J. M. (1997). *Biomimicry: Innovation Inspired by Nature*. New York: HarperCollins Publisher Inc.

- Bernasconi, A., Davoli, P., & Armani, C. (2010). Fatigue strength of a clutch pedal made of reprocessed short glass fibre reinforced polyamide. *International Journal of Fatigue*, 32(1), 100–107.
- Biagiotti, J., Fiori, S., Torre, L., Lopez-Manchado, M. A., & Kenny, J. M. (2004). Mechanical properties of polypropylene matrix composites reinforced with natural fibers: A statistical approach. *Polymer Composites*, 25(1), 26–36.
- Bourmaud, A., & Baley, C. (2009). Rigidity analysis of polypropylene/vegetal fibre composites after recycling. *Polymer Degradation and Stability*, 94, 297–305.
- Brezet, H., Van Hemel, C., (Paris), UNEP IE Cleaner Production Network, Rathenau Instituut, and Technische Universiteit Delft (1997). *Ecodesign: A promising approach to sustainable production and consumption*. Netherland: Delft University of Technology.
- Bunsell, A. R., & Harris, B. (1974). Hybrid carbon and glass fibre composites. *Composites*, 5(4), 157–164.
- Burgueño, R., Quagliata, M. J., Mohanty, A. K., Mehta, G., Drzal, L. T., & Misra, M. (2005). Hybrid biofiber-based composites for structural cellular plates. *Composites Part A: Applied Science and Manufacturing*, 36(5), 581–593.
- Campbell, F. C. (2010). Introduction to composite materials. In *Structural Composite Materials* (pp. 1–30). Ohio: ASM International.
- Cascini, G., Rissone, P., Rotini, F., & Russo, D. (2011). Systematic design through the integration of TRIZ and optimization tools. *Procedia Engineering*, 9, 674–679.
- Chakladar, N. D., & Chakraborty, S. (2008). A combined TOPSIS-AHP-method-based approach for non-traditional machining processes selection. *Proceedings of the Institution of Mechanical Engineers, Part B: Journal of Engineering Manufacture*, 222(12), 1613–1623.
- Chandrasegaran, S. K., Ramani, K., Sriram, R. D., Horváth, I., Bernard, A., Harik, R. F., & Gao, W. (2013). The evolution, challenges, and future of knowledge representation in product design systems. *Computer-Aided Design*, 45(2), 204–228.
- Chang, C. W., Wu, C. R., Lin, C. T., & Chen, H. C. (2007). An application of AHP and sensitivity analysis for selecting the best slicing machine. *Computers & Industrial Engineering*, 52(2), 296–307.

- Chang, H. T., & Chen, J. L. (2004). The conflict-problem-solving CAD software integrating TRIZ into eco-innovation. *Advances in Engineering Software*, 35(8), 553–566.
- Chen, H., Tu, J., & Guan, S. (2012). Applying the Theory of Problem-Solving and AHP to develop eco-innovative design. In M. Matsumoto et al. (eds) (Ed.), *Design for Innovative Value Towards a Sustainable Society* (pp. 489–494). Dordrecht: Springer Science+Business Media.
- Chiu, M. C., & Okudan, G. (2014). An investigation on the impact of product modularity level on supply chain performance metrics: An industrial case study. *Journal of Intelligent Manufacturing*, 25(1), 129–145.
- Cicala, G., Cristaldi, G., Recca, G., Ziegmann, G., El-Sabbagh, A., & Dickert, M. (2009). Properties and performances of various hybrid glass/natural fibre composites for curved pipes. *Materials and Design*, 30(7), 2538–2542.
- Consultants, Pr. (2000). *Eco-indicator 99 Manual for Designers. Ministry of Housing, Spatial Planning and the Environment*. The Hague, Netherlands.
- Corbière-Nicollier, T., Laban, B. G., Lundquist, L., Leterrier, Y., Månson, J.-A. ., & Jolliet, O. (2001). Life cycle assessment of biofibres replacing glass fibres as reinforcement in plastics. *Resources, Conservation and Recycling*, 33(4), 267–287.
- Cross, N. (1994). *Engineering Design Methods: Strategies for Product Design* (Second Edit.). Chichester, England: John Wiley & Sons.
- Cuenot, F. (2009). CO₂ emissions from new cars and vehicle weight in Europe: How the EU regulation could have been avoided and how to reach it? *Energy Policy*, 37(10), 3832–3842.
- Curran, M. A. (1996). *Environmental life-cycle assessment*. New York: McGraw-Hill.
- Davoodi, M. M., Sapuan, S. M., Ahmad, D., Aidy, A., Khalina, A., & Jonoobi, M. (2011). Concept selection of car bumper beam with developed hybrid bio-composite material. *Materials and Design*, 32(10), 4857–4865.
- Davoodi, M. M., Sapuan, S. M., Ahmad, D., Aidy, A., Khalina, A., & Jonoobi, M. (2012). Effect of polybutylene terephthalate (PBT) on

impact property improvement of hybrid kenaf/glass epoxy composite. *Materials Letters*, 67(1), 5–7.

- Davoodi, M. M., Sapuan, S. M., Ahmad, D., Ali, A., Khalina, A., & Jonoobi, M. (2010). Mechanical properties of hybrid kenaf/glass reinforced epoxy composite for passenger car bumper beam. *Materials and Design*, 31(10), 4927–4932.
- Davoodi, M. M., Sapuan, S. M., Aidy, A., Abu Osman, N. A., Oshkour, A. A., & Wan Abas, W. A. B. (2012). Development process of new bumper beam for passenger car: A review. *Materials and Design*, 40(0), 304–313.
- Deng, Y.-M., & Edwards, K. L. (2007). The role of materials identification and selection in engineering design. *Materials and Design*, 28(1), 131–139.
- DeSimone, L. D., & Popoff, F. (1997). *Eco-efficiency: The Business Link to Sustainable Development*. Massachusetts: MIT Press.
- Dieter, G. E. (2000). *Engineering Design: A Materials and Processing Approach* (Third Edit.). Boston: McGraw-Hill.
- Dong, C., & Davies, I. J. (2012). Optimal design of the flexural behavior of glass and carbon fibre reinforced polymer hybrid composites. *Materials and Design*, 37(0), 450–457.
- Dos Santos, P. A., Giriolli, J. C., Amarasekera, J., & Moraes, G. (2008). Natural fibers plastic composites in automotive applications. In *Proceedings of the 8th SPE Automotive Composites Conference and Exhibition*. Michigan, USA.
- DOT, U. (49). CFR Chapter V. 571.135 FMVSS Standard 135. Passenger car brake system.
- Duflou, J. R., Moor, J. De, Verpoest, I., & Dewulf, W. (2009). Environmental impact analysis of composite use in car manufacturing. *CIRP Annals - Manufacturing Technology*, 58, 9–12.
- Duigou, A., Deux, J.-M., Davies, P., & Baley, C. (2011). PLLA/flax mat/balsa bio-sandwich—Environmental impact and simplified life cycle analysis. *Applied Composite Materials*, 19(3-4), 363–378.
- Dungani, R., Abdul Khalil, H. P. S., Sumardi, I., Suhaya, Y., Sulistyawati, E., Islam, M. N., ... Aprilia, N. A. S. (2014). Non-wood renewable materials: Properties improvement and its application. In K. R.

- Hakeem, M. Jawaid, & U. Rashid (Eds.), *Biomass and Bioenergy* (pp. 1–29). New York: Springer International Publishing.
- Dutra, R. C. L., Soares, B. G., Campos, E. A., & Silva, J. L. G. (2000). Hybrid composites based on polypropylene and carbon fiber and epoxy matrix. *Polymer*, 41(10), 3841–3849.
- Dweiri, F., & Al-Oqla, F. M. (2006). Material selection using analytical hierarchy process. *International Journal of Computer Applications in Technology*, 26(4), 182–189.
- Edwards, K. L., & Deng, Y.-M. (2007). Supporting design decision-making when applying materials in combination. *Materials and Design*, 28, 1288–1297.
- El-Shekeil, Y. A., Sapuan, S. M., Abdan, K., & Zainudin, E. S. (2012). Influence of fiber content on the mechanical and thermal properties of Kenaf fiber reinforced thermoplastic polyurethane composites. *Materials and Design*, 40(0), 299–303.
- Erhard, G. (2006). *Designing with Plastics*. Munich: Hanser Publishers.
- Ertay, T., Büyüközkan, G., Kahraman, C., & Ruan, D. (2005). Quality function deployment implementation based on Analytic Network Process with linguistic data: An application in automotive industry. *Journal of Intelligent and Fuzzy Systems*, 16(3), 221–232.
- Facca, A. G., Kortschot, M. T., & Yan, N. (2006). Predicting the elastic modulus of natural fibre reinforced thermoplastics. *Composites Part A: Applied Science and Manufacturing*, 37(10), 1660–1671.
- Farag, M. M. (1997). *Materials Selection for Engineering Design*. London: Prentice Hall.
- Farag, M. M. (2008). Quantitative methods for material substitution: Application to automotive components. *Materials and Design*, 29, 374–380.
- Faruk, O., Bledzki, A. K., Fink, H.-P., & Sain, M. (2012). Biocomposites reinforced with natural fibers: 2000–2010. *Progress in Polymer Science*, 37(11), 1552–1596.
- Favaro, S. L., Ganzerli, T. A., Neto, A., da Silva, O., & Radovanovic, E. (2010). Chemical, morphological and mechanical analysis of sisal fiber-reinforced recycled high-density polyethylene composites. *Express Polymer Letters*, 4(8), 465–473.

- Fifield, L. S., & Simmons, K. L. (2010). Compression molded, bio-fiber reinforced, high performance thermoset composites for structural and semi-structural applications. In *Proceedings of the 10th Annual Automotive Composite Conference and Exhibition, SPE Automotive and Composite Divisions*. Michigan, USA.
- Finkbeiner, M., & Hoffmann, R. (2006). Application of life cycle assessment for the environmental certificate of the Mercedes-Benz S-Class. *The International Journal of Life Cycle Assessment*, 11(4), 240–246.
- Finnveden, G., Hauschild, M. Z., Ekvall, T., Guinée, J., Heijungs, R., Hellweg, S., ... Suh, S. (2009). Recent developments in Life Cycle Assessment. *Journal of Environmental Management*, 91(1), 1–21.
- Fontaras, G., & Samaras, Z. (2010). On the way to 130 g CO₂/km—Estimating the future characteristics of the average European passenger car. *Energy Policy*, 38(4), 1826–1833.
- Friedrich, K., & Almajid, A. A. (2013). Manufacturing aspects of advanced polymer composites for automotive applications. *Applied Composite Materials*, 20(2), 107–128.
- Fu, S., Xu, G., & Mai, Y. (2002). On the elastic modulus of hybrid particle/short-fiber/polymer composites. *Composites Part B: Engineering*, 33(4), 291–299.
- Ghazilla, R. A. R., Taha, Z., Yusoff, S., Rashid, S. H. A., & Sakundarini, N. (2013). Development of decision support system for fastener selection in product recovery oriented design. *The International Journal of Advanced Manufacturing Technology*, 70(5-8), 1403–1413.
- Girubha, R. J., & Vinodh, S. (2012). Application of fuzzy VIKOR and environmental impact analysis for material selection of an automotive component. *Materials and Design*, 37, 478–486.
- Goedkoop, M., & Huijbregts, M. (2013). ReCiPe 2008.
- González-García, S., Hospido, A., Feijoo, G., & Moreira, M. T. (2010). Life cycle assessment of raw materials for non-wood pulp mills: Hemp and flax. *Resources, Conservation and Recycling*, 54(11), 923–930.
- Gutteridge, P. A., & Waterman, N. A. (1986). *Computer-aided Materials Selection. Encyclopedia of Materials Science and Engineering*. Oxford: Pergamon Press.

- Haik, Y. (2013). Morphological chart and concept generation. Retrieved June 24, 2014, from http://www.eng.fsu.edu/~haik/design/idea_generation.htm
- Halpin, J. C., & Kardos, J. L. (1976). The Halpin-Tsai equations: A review. *Polymer Engineering and Science*, 16(5), 344–352.
- Hambali, A., Sapuan, S. M., Ismail, N., & Nukman, Y. (2009). Application of Analytical Hierarchy Process in the design concept selection of automotive composite bumper beam during the conceptual design stage. *Scientific and Research Essay*, 4(4), 198–211.
- Hambali, A., Sapuan, S. M., Ismail, N., & Nukman, Y. (2010). Material selection of polymeric composite automotive bumper beam using analytical hierarchy process. *Journal of Central South University of Technology*, 17(2), 244–256.
- Hambali, A., Sapuan, S. M., Rahim, A. S., Ismail, N., & Nukman, Y. (2011). Concurrent decisions on design concept and material using analytical hierarchy process at the conceptual design stage. *Concurrent Engineering: Research and Applications*, 19(2), 111–121.
- Hamma, A., Kaci, M., Ishak, Z. A. M., & Pegoretti, A. (2014). Starch-grafted-polypropylene/kenaf fibres composites. Part 1: Mechanical performances and viscoelastic behaviour. *Composites Part A: Applied Science and Manufacturing*, 56(0), 328–335.
- Hashemi, S. (2008). Effect of temperature on tensile properties of injection moulded short glass fibre and glass bead filled ABS hybrids. *eXPRESS Polymer Letters*, 2(7), 474–484.
- Henson, G. (2014). Use of the Halpin-Tsai equations to estimate minor moduli of composite laminae. *Invariant Labs*. Retrieved January 21, 2014, from <http://www.invariantlabs.com/htsimp2.html#CITEnasa>
- Holbery, J., & Houston, D. (2006). Natural-fiber-reinforced polymer composites in automotive applications. *Journal of Minerals, Metals and Materials Society*, 58(11), 80–86.
- Hollebeak, B. (2014). *Today's Technician: Automotive Electricity and Electronics, Classroom and Shop Manual Pack* (6th Edit.). Stamford, USA: Cengage Learning.

- Hosseinzadeh, R., Shokrieh, M. M., & Lessard, L. B. (2005). Parametric study of automotive composite bumper beams subjected to low-velocity impacts. *Journal of Composites Structures*, 68, 419–427.
- Hufenbach, W., Bohm, R., Thieme, M., Winkler, A., Mader, E., Rausch, J., & Schade, M. (2011). Polypropylene/glass fibre 3D-textile reinforced composites for automotive applications. *Materials and Design*, 32, 1468–1476.
- Hwang, C. L., & Yoon, K. P. (1981). *Multiple Attribute Decision Making Methods and Applications*. New York: Springer.
- Imihezri, S. S. S., Sapuan, S. M., Ahmad, M. M. H. M., & Sulaiman, S. (2005). A study of the comparison of 'V' and 'X' ribbing in a composite pedal using mold flow analysis software. *Materials & Design*, 26(2), 157–166.
- Imihezri, S. S. S., Sapuan, S. M., Sulaiman, S., Hamdan, M. M., Zainuddin, E. S., Osman, M. R., & Rahman, M. Z. A. (2006). Mould flow and component design analysis of polymeric based composite automotive clutch pedals. *Journal of Materials Processing Technology*, 171(3), 358–365.
- Ipek, M., Selvi, I. H., Findik, F., Torkul, O., & Cedimog, I. H. (2013). An expert system based material selection approach to manufacturing. *Materials and Design*, 47, 331–340.
- Ishak, M. R., Sapuan, S. M., Leman, Z., Rahman, M. Z. A., Anwar, U. M. K., & Siregar, J. P. (2013). Sugar palm (*Arenga pinnata*): Its fibres, polymers and composites. *Carbohydrate Polymers*, 91(2), 699–710.
- Jacob, M., Thomas, S., & Varughese, K. T. (2004). Natural rubber composites reinforced with sisal/oil palm hybrid fibers: Tensile and cure characteristics. *Journal of Applied Polymer Science*, 93(5), 2305–2312.
- Jahan, A., & Edwards, K. L. (2013). VIKOR method for material selection problems with interval numbers and target-based criteria. *Materials and Design*, 47, 759–765.
- Jahan, A., Ismail, M. Y., Sapuan, S. M., & Mustapha, F. (2010). Material screening and choosing methods – A review. *Materials and Design*, 31(2), 696–705.

- Jarukumjorn, K., & Suppakarn, N. (2009). Effect of glass fiber hybridization on properties of sisal fiber–polypropylene composites. *Composites Part B: Engineering*, 40(7), 623–627.
- Jawaid, M., & Abdul Khalil, H. P. S. (2011). Cellulosic/synthetic fibre reinforced polymer hybrid composites: A review. *Carbohydrate Polymers*, 86(1), 1–18.
- Jawaid, M., Abdul Khalil, H. P. S., & Abu Bakar, A. (2010). Mechanical performance of oil palm empty fruit bunches/jute fibres reinforced epoxy hybrid composites. *Materials Science and Engineering: A*, 527(29–30), 7944–7949.
- Jawaid, M., Abdul Khalil, H. P. S., & Abu Bakar, A. (2011). Woven hybrid composites: Tensile and flexural properties of oil palm-woven jute fibres based epoxy composites. *Materials Science and Engineering: A*, 528(15), 5190–5195.
- Jawaid, M., Abdul Khalil, H. P. S., & Alattas, O. S. (2012). Woven hybrid biocomposites: Dynamic mechanical and thermal properties. *Composites Part A: Applied Science and Manufacturing*, 43(2), 288–293.
- Jee, D. H., & Kang, K. J. (2000). A method for optimal material selection aided with decision making theory. *Materials and Design*, 21(3), 199–206.
- Joshi, S. ., Drzal, L. ., Mohanty, A. ., & Arora, S. (2004). Are natural fiber composites environmentally superior to glass fiber reinforced composites? *Composites Part A: Applied Science and Manufacturing*, 35(3), 371–376.
- Karana, E., Hekkert, P., & Kandachar, P. (2010). A tool for meaning driven materials selection. *Materials and Design*, 31(6), 2932–2941.
- Kardi, T. (2006). Analytic Hierarchy Process (AHP) Tutorial. Retrieved June 24, 2014, from <http://people.revoledu.com/kardi/tutorial/AHP/>
- Khorshidi, R., & Hassani, A. (2013). Comparative analysis between TOPSIS and PSI methods of materials selection to achieve a desirable combination of strength and workability in Al/SiC composite. *Materials and Design*, 52(0), 999–1010.
- Khorshidi, R., Hassani, A., Rauof, A. H., & Emamy, M. (2013). Selection of an optimal refinement condition to achieve maximum tensile

- properties of Al–15%Mg₂Si composite based on TOPSIS method. *Materials and Design*, 46(0), 442–450.
- Kim, Y. S., & Cochran, D. S. (2000). Reviewing TRIZ from the perspective of Axiomatic Design. *Journal of Engineering Design*, 11(1), 79–94.
- Kong, K., Hejda, M., Young, R. J., & Eichhorn, S. J. (2009). Deformation micromechanics of a model cellulose/glass fibre hybrid composite. *Composites Science and Technology*, 69(13), 2218–2224.
- Koo, J. S., & Cho, H. J. (2009). Theoretical method for predicting the weight reduction rate of a box-type car body for rolling stock by material substitution design. *International Journal of Automotive Technology*, 10(3), 355–363.
- Kordkheili, H. Y., Farsi, M., & Rezazadeh, Z. (2013). Physical, mechanical and morphological properties of polymer composites manufactured from carbon nanotubes and wood flour. *Composites Part B: Engineering*, 44(1), 750–755.
- Koronis, G., Silva, A., & Fontul, M. (2013). Green composites: A review of adequate materials for automotive applications. *Composites Part B: Engineering*, 44(1), 120–127.
- Kota, S., & Lee, C.-L. (1993). General Framework for Configuration Design: Part 1— Methodology. *Journal of Engineering Design*, 4(4), 277–289.
- Kremer, G. O., Chiu, M.-C., Lin, C.-Y., Gupta, S., Claudio, D., & Thevenot, H. (2012). Application of axiomatic design, TRIZ, and mixed integer programming to develop innovative designs: a locomotive ballast arrangement case study. *The International Journal of Advanced Manufacturing Technology*, 61(5-8), 827–842.
- Ku, H., Wang, H., Pattarachaiyakoo, N., & Trada, M. (2011). A review on the tensile properties of natural fiber reinforced polymer composites. *Composites Part B: Engineering*, 42(4), 856–873.
- Kumar, M. A., Reddy, G. R., Bharathi, Y. S., Naidu, S. V., & Prasad Naidu, V. N. (2010). Frictional coefficient, hardness, impact strength, and chemical resistance of reinforced sisal-glass fiber epoxy hybrid composites. *Journal of Composite Materials*, 44(0), 3195–3202.
- Kwon, H.-J., Sunthornvarabhas, J., Park, J.-W., Lee, J.-H., Kim, H.-J., Piyachomkwan, K., ... Cho, D. (2014). Tensile properties of kenaf fiber and corn husk flour reinforced poly(lactic acid) hybrid bio-

composites: Role of aspect ratio of natural fibers. *Composites Part B: Engineering*, 56(0), 232–237.

- LaRosa, A. D., Cozzo, G., Latteri, A., Recca, A., Björklund, A., Parrinello, E., & Cicala, G. (2013). Life cycle assessment of a novel hybrid glass-hemp/thermoset composite. *Journal of Cleaner Production*, 44(0), 69–76.
- Lee, C. H., Sapuan, S. M., & Hassan, M. R. (2014). A review of the flammability factors of kenaf and allied fibre reinforced polymer composites. *Advances in Materials Science and Engineering*, 0, 1–8.
- Lee, S. W., & Lee, D. G. (2005). Composite hybrid valve lifter for automotive engines. *Composite Structures*, 71, 26–33.
- Li, T. (2009). Applying TRIZ and AHP to develop innovative design for automated assembly systems. *The International Journal of Advanced Manufacturing Technology*, 46(1–4), 301–313.
- Li, T.-S., & Huang, H.-H. (2009). Applying TRIZ and Fuzzy AHP to develop innovative design for automated manufacturing systems. *Expert Systems with Applications*, 36(4), 8302–8312.
- Li, X., Tabil, L. G., & Panigrahi, S. (2007). Chemical treatments of natural fiber for use in natural fiber-reinforced composites: A review. *Journal of Polymers and the Environment*, 15(1), 25–33.
- Liang, J. Z. (2012). Prediction of Young's modulus of short inorganic fiber reinforced polymer composites. *Composites Part B: Engineering*, 43(4), 1763–1766.
- Lin, M.-C., Wang, C.-C., Chen, M.-S., & Chang, C. A. (2008). Using AHP and TOPSIS approaches in customer-driven product design process. *Computers in Industry*, 59(1), 17–31.
- Liu, Y., Peng, X., & Qin, Y. (2004). FE Simulation for concurrent design and manufacture of automotive sheet-metal parts. *Journal of Materials Processing Technology*, 150(1), 145–150.
- Loh, X. H., Daud, M. A. M., Selamat, M. Z., & Melaka, U. M. (2015). Study on fibre length and composition of kenaf-polypropylene (K-PP) composite for automobile interior parts. *Applied Mechanics and Materials*, 695, 36–39.
- Lopez, J. P., Mutje, P., Pelach, M. A., Mansouri, N. E., Boufi, S., & Vilaseca, F. (2012). Analysis of the tensile modulus of polypropylene

- composites reinforced with stone groundwood fibers. *BioResources*, 7(1), 1310–1323.
- Luo, S., & Netravali, A. N. (1999). Mechanical and thermal properties of environment-friendly “green” composites made from pineapple leaf fibers and poly(hydroxybutyrate-co-valerate) resin. *Polymer Composites*, 20(3), 367–378.
- Luttropp, C., & Lagerstedt, J. (2006). EcoDesign and the Ten Golden Rules: Generic advice for merging environmental aspects into product development. *Journal of Cleaner Production*, 14(15-16), 1396–1408.
- Luz, S. M., Caldeira-pires, A., & Ferrão, P. M. C. (2010). Environmental benefits of substituting talc by sugarcane bagasse fibers as reinforcement in polypropylene composites: Ecodesign and LCA as strategy for automotive components. *Resources, Conservation & Recycling*, 54(12), 1135–1144.
- Macharis, C., Springael, J., Brucker, K. De, & Verbeke, A. (2004). PROMETHEE and AHP: The design of operational synergies in multicriteria analysis. Strengthening PROMETHEE with ideas of AHP. *European Journal of Operational Research*, 153(2), 307–317.
- Mallick, P. K. (2007). *Fiber-Reinforced Composites: Materials, Manufacturing, and Design* (Third Edit.). Boca Raton: CRC Press.
- Maniya, K., & Bhatt, M. G. (2010). A selection of material using a novel type decision-making method: Preference selection index method. *Materials and Design*, 31(4), 1785–1789.
- Mansor, M. R., Sapuan, S. M., Zainudin, E. S., Nuraini, A. A., & Hambali, A. (2013). Hybrid natural and glass fibers reinforced polymer composites material selection using Analytical Hierarchy Process for automotive brake lever design. *Materials and Design*, 51(0), 484–492.
- Mansor, M. R., Sapuan, S. M., Zainudin, E. S., Nuraini, A. A., & Hambali, A. (2014). Conceptual design of kenaf fiber polymer composite automotive parking brake lever using integrated TRIZ – Morphological Chart – Analytic Hierarchy Process method. *Materials and Design*, 54(0), 473–482.
- Marsh, G. (2003). Next step for automotive materials. *Materials Today*, 6(4), 36–43.

- Mayer, R. M. (1993). *Design with Reinforced Plastics: A Guide for Engineers and Designers*. London: The Design Council.
- Mayyas, A., Shen, Q., Abdelhamid, M., Shan, D., Qattawi, A., & Omar, M. (2011). Using quality function deployment and analytical hierarchy process for material selection of body-in-white. *Materials and Design*, 32(5), 2771–2782.
- Mirbagheri, J., Tajvidi, M., Ghasemi, I., & Hermanson, J. C. (2007). Prediction of the elastic modulus of wood flour/kenaf fibre/polypropylene hybrid composites. *Iranian Polymer Journal*, 16(4), 271–278.
- Mirbagheri, J., Tajvidi, M., Hermanson, J. C., & Ghasemi, I. (2007). Tensile properties of wood flour/kenaf fiber polypropylene hybrid composites. *Journal of Applied Polymer Science*, 105(5), 3054–3059.
- Mishra, S., Mohanty, A. K., Drzal, L. T., Misra, M., Parija, S., Nayak, S. K., & Tripathy, S. S. (2003). Studies on mechanical performance of biofibre/glass reinforced polyester hybrid composites. *Composites Science and Technology*, 63(10), 1377–1385.
- Miwa, M., & Horiba, N. (1994). Effects of fibre length on tensile strength of carbon/glass fibre hybrid composites. *Journal of Materials Science*, 29(4), 973–977.
- Mohanty, A. K., Wibowo, A., Misra, M., & Drzal, L. T. (2004). Effect of process engineering on the performance of natural fiber reinforced cellulose acetate biocomposites. *Composites Part A: Applied Science and Manufacturing*, 35(3), 363–370.
- Monteiro, S. N., Lopes, F. P. D., Ferreira, A. S., & Nascimento, D. C. O. (2009). Natural-fiber polymer-matrix composites: Cheaper, tougher, and environmentally friendly. *Journal of Minerals, Metals and Materials Society*, 61(1), 17–22.
- Moon, B. J., Gung, H. G., Lee, S. G., & Kim, D. H. (2014). Parallel model based fault detection algorithm for electronic parking brake system. *International Journal of Automotive Technology*, 15(3), 483–494.
- Mussig, J., Schmehl, M., Buttlar, H.-B. Von, Schonfeld, U., & Arndt, K. (2006). Exterior components based on renewable resources produced with SMC technology — Considering a bus component as example. *Industrial Crops and Products*, 24(2), 132–145.

- Mustafa, A., Abdollah, M. F. Bin, Shuhimi, F. F., Ismail, N., Amiruddin, H., & Umehara, N. (2014). Selection and verification of kenaf fibres as an alternative friction material using Weighted Decision Matrix method. *Materials and Design*, 67(0), 577-582.
- Nayak, S. K., Mohanty, S., & Samal, S. K. (2009). Influence of short bamboo/glass fiber on the thermal, dynamic mechanical and rheological properties of polypropylene hybrid composites. *Materials Science and Engineering: A*, 523(1–2), 32–38.
- Nepal, B., Yadav, O. P., & Murat, A. (2010). A fuzzy-AHP approach to prioritization of CS attributes in target planning for automotive product development. *Expert Systems with Applications*, 37(10), 6775–6786.
- Ozen, E., Kiziltas, A., Kiziltas, E. E., & Gardner, D. J. (2013). Natural fiber blend—nylon 6 composites. *Polymer Composites*, 34(4), 544–553.
- Pahl, G., Beitz, W., Feldhusen, J., & Grote, K. H. (2007). *Engineering Design: A Systematic Approach* (Third Edit.). London: Springer-Verlag London Limited.
- Park, H. S., & Dang, X. P. (2011). Development of a fiber-reinforced plastic armrest frame for weight-reduced automobiles. *International Journal of Automotive Technology*, 12(1), 83–92.
- Peças, P., Ribeiro, I., Silva, A., & Henriques, E. (2013). Comprehensive approach for informed life cycle-based materials selection. *Materials and Design*, 43, 220–232.
- Perçin, S. (2006). An application of the integrated AHP-PGP model in supplier selection. *Measuring Business Excellence*, 10(4), 34–49.
- Pugh, S. (1991). *Total Design: Integrated Methods for Successful Product Engineering*. Wokingham, England: Addison-Wesley Publishing.
- Putri, N. T., & Yusof, S. R. M. (2008). Critical success factors for implementing quality engineering (QE) in Malaysian's and Indonesian's automotive industries: A proposed model. *International Journal of Automotive Industry and Management*, 2(0), 1–15.
- Qatu, M. S. (2011). Application of kenaf-based natural fiber composites in the automotive industry. *SAE Technical Paper*, 2011–01–2015.

- Ramesh, M., Palanikumar, K., & Hemachandra Reddy, K. (2013). Mechanical property evaluation of sisal-jute-glass fiber reinforced polyester composites. *Composites Part B: Engineering*, 48(0), 1–9.
- Rao, H. R., Kumar, M. A., & Reddy, G. R. (2011). Hybrid composites: Effect of fibers on mechanical properties. *International Journal of Macromolecular Science*, 1(0), 9–14.
- Rao, R. V., & Davim, J. P. (2008). A decision-making framework model for material selection using a combined multiple attribute decision-making method. *International Journal of Advanced Manufacturing Technology*, 35(7-8), 751–760.
- Rathod, M. K., & Kanzaria, H. V. (2011). A methodological concept for phase change material selection based on multiple criteria decision analysis with and without fuzzy environment. *Materials and Design*, 32(6), 3578–3585.
- Rebitzer, G., Ekvall, T., Frischknecht, R., Hunkeler, D., Norris, G., Rydberg, T., ... Pennington, D. W. (2004). Life cycle assessment: Part 1: Framework, goal and scope definition, inventory analysis, and applications. *Environment International*, 30(5), 701–720.
- Saaty, T. L. (2005). *Theory and Applications of the Analytic Network Process*. Pittsburgh, PA: RWS Publications.
- Salleh, Z., Taib, Y. M., Hyie, K. M., Mihat, M., Berhan, M. N., & Ghani, M. A. A. (2012). Fracture toughness investigation on long kenaf/woven glass hybrid composite due to water absorption effect. *Procedia Engineering*, 41(0), 1667–1673.
- San, Y. T., Jin, Y. T., & Li, S. C. (2009). *TRIZ: Systematic Innovation in Manufacturing*. Selangor: Firstfruits Sdn Bhd.
- Sapuan, S. M. (2001). A knowledge-based system for materials selection in mechanical engineering design. *Materials and Design*, 22(8), 687–695.
- Sapuan, S. M. (2005a). A conceptual design of the concurrent engineering design system for polymeric-based composite automotive pedals. *American Journal of Applied Sciences*, 2(2), 514–525.
- Sapuan, S. M. (2005b). Concurrent design and manufacturing process of automotive composite components. *Assembly Automation*, 25(2), 146–152.

- Sapuan, S. M. (2006). Using the morphological chart technique for the design of polymeric-based composite automotive pedals. *Discovery and Innovation*, 18(4), 311–317.
- Sapuan, S. M. (2010). *Concurrent Engineering for Composites*. Serdang: UPM Press.
- Sapuan, S. M., & Abdalla, H. S. (1998). A prototype knowledge-based system for the material selection of polymeric-based composites for automotive components. *Composites Part A: Applied Science and Manufacturing*, 29(7), 731–742.
- Sapuan, S. M., Kho, J. Y., Zainudin, E. S., Leman, Z., Ahmed Ali, B. A., & Hambali, A. (2011). Materials selection for natural fiber reinforced polymer composites using analytical hierarchy process. *Indian Journal of Engineering & Materials Sciences*, 18(4), 255–267.
- Sapuan, S. M., Osman, M. R., & Nukman, Y. (2006). State of the art of the concurrent engineering technique in the automotive industry. *Journal of Engineering Design*, 7(2), 143–157.
- Savastano Jr, H., Santos, S. F., Radonjic, M., & Soboyejo, W. O. (2009). Fracture and fatigue of natural fiber-reinforced cementitious composites. *Cement and Concrete Composites*, 31(4), 232–243.
- Schmehl, M., Mussig, J., Schonfeld, U., & Von Buttlar, H.-B. (2008). Life cycle assessment on a bus body component based on hemp and PTP. *Journal of Polymers and the Environment*, 16(1), 51–60.
- Schmidt, W. P., Dahlgvist, E., Finkbeiner, M., Krinke, S., Lazzari, S., Oschmann, D., ... Thiel, C. (2004). Life cycle assessment of lightweight and end-of-life scenarios for generic compact class passenger vehicles. *The International Journal of Life Cycle Assessment*, 9(6), 405–416.
- Serrano, A., Espinach, F. X., Tresserras, J., Rey, R., Pellicer, N., & Mutje, P. (2014). Macro and micromechanics analysis of short fiber composites stiffness: The case of old newspaper fibers-polypropylene composites. *Materials and Design*, 55(0), 319–324.
- Shah, D. U. (2014). Natural fibre composites: Comprehensive Ashby-type materials selection charts. *Materials and Design*, 62(0), 21–31.
- Shanian, A., & Savadogo, O. (2006). A material selection model based on the concept of multiple attribute decision making. *Materials and Design*, 27(4), 329–337.

- Sheu, D. D., & Lee, H.-K. (2011). A proposed process for systematic innovation. *International Journal of Production Research*, 49(3), 847–868.
- Short, D., & Summerscales, J. (1980). Hybrids - A review: Part 2. Physical properties. *Composites*, 11(1), 33–38.
- Sobczak, L., Lang, R. W., & Haider, A. (2012). Polypropylene composites with natural fibers and wood – General mechanical property profiles. *Composites Science and Technology*, 72(5), 550–557.
- Song, Y. S., Youn, J. R., & Gutowski, T. G. (2009). Life cycle energy analysis of fiber-reinforced composites. *Composites Part A*, 40(8), 1257–1265.
- Tenaga Nasional, B. (2014). Malaysian Power Supply Specifications. Retrieved June 24, 2014, from <http://www.tnb.com.my/business/for-housing-developers-electrical-contractors/tnb-electricity-system.html>
- Tucker, I. C., & Liang, E. (1999). Stiffness predictions for unidirectional short-fibre composites: review and evaluation. *Composites Science and Technology*, 59(5), 655–671.
- Ulrich, K. T., & Eppinger, S. D. (2004). *Product Design and Development* (Third Edit.). Boston: McGraw-Hill Irwin.
- UNECE. R13-H Standard for vehicle braking systems.
- Venkateshwaran, N., Elayaperumal, a., & Sathiya, G. K. (2012). Prediction of tensile properties of hybrid-natural fiber composites. *Composites Part B: Engineering*, 43(2), 793–796.
- Vidal, R., Martínez, P., & Garraín, D. (2009). Life cycle assessment of composite materials made of recycled thermoplastics combined with rice husks and cotton linters. *The International Journal of Life Cycle Assessment*, 14(1), 73–82.
- Wan Busu, W. N., Anuar, H., Ahmad, S. H., Rasid, R., & Jamal, N. A. (2010). The Mechanical and physical properties of thermoplastic natural rubber hybrid composites reinforced with Hibiscus Cannabinus, L and short glass fiber. *Polymer-Plastics Technology and Engineering*, 49(13), 1315–1322.
- Wang, F.-K., & Chen, K.-S. (2010). Applying Lean Six Sigma and TRIZ methodology in banking services. *Total Quality Management & Business Excellence*, 21(3), 301–315.

- Wang, J., Shi, S. Q., & Liang, K. (2012). Comparative life-cycle assessment of sheet molding compound reinforced by natural fiber vs . glass fiber. In *Proceedings of the 55th International Convention of Society of Wood Science and Technology August 27-31, 2012 - Beijing, China* (Vol. 2, pp. 1–10).
- Wötzel, K., Wirth, R., & Flake, M. (1999). Life cycle studies on hemp fibre reinforced components and ABS for automotive parts. *Die Angewandte Makromolekulare Chemie*, 272(1), 121–127.
- Wright, I. C. (1998). *Design Methods in Engineering and Product Design*. Maidenhead, Berkshire: Mc-Graw-Hill Publishing Company.
- Wu, W., Chiang, C., & Lin, C. (1998). Comparing the aggregation methods in the analytic hierarchy process when uniform distribution. *WSEAS Transactions on Business and Economics*, 5(3), 82–87.
- Xu, X., Jayaraman, K., Morin, C., & Pecqueux, N. (2008). Life cycle assessment of wood-fibre-reinforced polypropylene composites. *Journal of Materials Processing Technology*, 198(1–3), 168–177.
- Yamashina, H., Ito, T., & Kawada, H. (2002). Innovative product development process by integrating QFD and TRIZ. *International Journal of Production Research*, 40(5), 1031–1050.
- Yang, S., & Nezu, K. (1998). Application of an inverse FE Approach in the concurrent design of sheet stamping. *Journal of Materials Processing Technology*, 79(1), 86–93.
- Yeh, C. H., Huang, J. C. Y., & Yu, C. K. (2011). Integration of four-phase QFD and TRIZ in product R&D: A notebook case study. *Research in Engineering Design*, 22(3), 125–141.
- Yen, S. B., & Chen, J. L. (2005). An eco-innovative tool by integrating FMEA and TRIZ methods. In *Proceeding of the 4th International Symposium on Environmentally Conscious Design and Inverse Manufacturing*. Tokyo, Japan: IEEE. (pp. 678–683)
- Yoon, K. P., & Hwang, C. L. (2005). *Multiple Attribute Decision Making: An Introduction to Quantitative Applications in the Social Sciences*. Thousand Oaks, CA: Sage Publications Inc.
- Yousefpour, M., & Rahimi, A. (2014). Characterization and selection of optimal parameters to achieve the best tribological performance of the electrodeposited Cr nanocomposite coating. *Materials and Design*, 54(0), 382–389.

- Yu, K. M., Lau, C. T., Tong, K. L., & Wong, W. K. (2008). Integrated conceptual design with TRIZ. *TRIZ Journal*, Retrieved June 24, 2014, from <http://www.triz-journal.com/archives/2008/09/02/>.
- Zah, R., Hischier, R., Le, A. L., & Braun, I. (2007). Curaua fibers in the automobile industry: A sustainability assessment. *Journal of Cleaner Production*, 15(11), 1032–1040.
- Zhang, J., Chaisombat, K., He, S., & Wang, C. H. (2012). Hybrid composite laminates reinforced with glass/carbon woven fabrics for lightweight load bearing structures. *Materials and Design*, 36(0), 75–80.
- Zhao, R., Neighbour, G., Deutz, P., & McGuire, M. (2012). Materials selection for cleaner production: An environmental evaluation approach. *Materials and Design*, 37(0), 429–434.
- Zhong, L. X., Fu, S. Y., Zhou, X. S., & Zhan, H. Y. (2011). Effect of surface microfibrillation of sisal fibre on the mechanical properties of sisal/aramid fibre hybrid composites. *Composites Part A: Applied Science and Manufacturing*, 42(3), 244–252.