

UNIVERSITI PUTRA MALAYSIA

CRUSHING BEHAVIOR AND FAILURE MODES OF KENAF FIBRE-REINFORCED COMPOSITE HEXAGONAL TUBES

MUNIR FARAJ ALMABROUK ALKBIR

FK 2016 170



CRUSHING BEHAVIOR AND FAILURE MODES OF KENAF FIBRE-REINFORCED COMPOSITE HEXAGONAL TUBES



Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in Fulfilment of the Requirements for the Degree of Doctor of Philosophy

June 2016

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



DEDICATION

This thesis is gratefully dedicated to:

My beloved Mother and Father for unlimited supports and encouragements throughout my life

The soul of my sister (Halema)

My wife for her patience and understanding

My supervision committee for their support



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy

CRUSHING BEHAVIOR AND FAILURE MODES OF KENAF FIBRE-REINFORCED COMPOSITE HEXAGONAL TUBES

By

MUNIR FARAJ ALMABROUK ALKBIR

June 2016

Chairman Faculty

:

Mohd Sapuan Salit, PhD, PEng Engineering

This research focused on the crashworthiness characteristics of kenaf fibre reinforced composite hexagonal tubes with a variety of configurations. A series of experiments were carried out for composite hexagonal tubes with a different dimension. A hand lay-up technique was used to fabricate the specimens of composite hexagonal tubes performed for crushing Four phases were behaviour, failure mode and crashworthiness parameters of hexagonal composite tubes. The first phase was to study the effect of fibre content on the crashworthiness parameters (i.e, energy absorption and stroke efficiency) and the failure modes of a non-woven kenaf (mat) fibre-reinforced hexagonal composite tube. Various fibre contents were considered, including 25%, 30%, 35% and 40%. A fibre content of 25% to 30% (mass percent) demonstrated the best crashworthiness parameters. A high percentage of fibre loading 40% and more, due to poor bonding between the fibre and matrix, was not capable of transferring load to another, and hence stress was accumulated at certain points of the composite, which led to lower energy absorption mechanical properties. The reinforcing fibers are strong, stiff and effective for improving the mechanical properties of composite materials. However, reinforcing fibres are often brittle and abrasive, lack toughness, and can degrade chemically when exposed to the environment. A few distinct failure modes were identified during the experiments, including the progressive failure mode, in which failure begins at the top end of the tube, and the transverse crack failure mode, which is associated with the buckling failure mode. Phase two was devoted to study the static crushing behaviour of composite hexagonal tubes under uniform axial load. Three lengths of hexagonal composite tubes were tested 50, 100, and 150 mm with same hexagonal angle 45°. Results showed that tube with length 50 mm exhibits a high specific energy absorption as well as higher average crushing load. Phase three involved fabrication and testing of five different hexagonal tubes of reinforced natural kenaf (mat) with different angles from a range of 40° to 60° and in 5° increments of the angle, to determine the effect of geometry on crashworthiness parameters of natural kenaf fibre reinforced composite hexagonal tubes. Results obtained in this phase show that the structures failed in a few distinct failure modes such as progressive failure mode and



fragmentation failure associated with longitudinal cracks. The composite tube with β = 60° exhibited a local buckling failure mode and displayed the highest specific energy absorption capability equal to 9.2 kJ/Kg. On the other hand, the new crashworthiness parameter was introduced as a catastrophic failure mode indicator (CFMI), the last phase was when the specimens were subjected to a lateral quasi-static compressive load. In this phase, the supporting plate was used inside the tube for the following reasons. The main purpose was to improve the energy absorbed by the tubes. The improvements, including the use of energy absorbing materials and structures in the plate inside the tubes, ensure more favourable decelerations during a crash/accident, resulting in fewer injuries to the car occupants. Furthermore, using a supporting plate inside the hexagonal tubes can control the load distribution during the crushing period and can diminish the structure weight. Three configurations of β =40°, β =50° and β =60° of natural non-woven kenaf (mat)/epoxy were laminated. The effects of the hexagonal angles, supporting plate inside the tubes, and failure modes were studied by a lateral compression test. The crashworthiness of the tubes was evaluated by an analysis of the specific energy absorption in quasi-static lateral compression. Specific energy absorption was obtained from the load-displacement curve during testing. The failure mode of the tubes was analysed from high resolution photographs. Overall, the tube with $\beta=40^{\circ}$ had the best crashworthiness among the tubes. Above all, the results showed that the tubes with supporting plates showed better specific energy absorption (SEA) for all tested specimens and exhibited approximately 69% better crashworthiness than the nonsupporting ones. The results also demonstrated that all specimens failed by the longitudinal failure mode.

Abstrack tesis yang dikemukakan kepada senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazh Doktor Falsafah

KELAKUAN PENGHANCURAN DAN MOD KEGAGALAN BAGI TIUB KOMPOSIT HEKSAGON DIPERKUAT GENTIAN KENAF

Oleh

MUNIR FARAJ ALMABROUK ALKBIR

Jun 2016

Pengerusi : Mohd Sapuan Salit, PhD, PEng Fakulti : Kejuruteraan

Penyelidikan ini memfokuskan kepada ciri-ciri pelindungan laga bagi tiub heksagon komposit diperkuat gentian kenaf dengan pelbagai konfigurasi. Satu siri eksperimen telah dijalankan bagi tiub heksagon komposit dengan dimensi yang berbeza. Kaedah bengkalai tangan telah digunakan untuk membikin specimen tiub heksagon komposit. Empat fasa telah dilaksanakan bagi kelakuan penghancuran, mod kegagalan dan parameter pelindungan laga bagi tiub komposit heksagon. Fasa pertama adalah mengkaji kesan kandungan gentian terhadap parameter pelindungan laga (iaitu penyerapan tenaga dan keberkesanan lejang) dan mod kegagalan bagi tiub komposit heksagon diperkuat gentian kenaf tidak tertenun (tikar). Pelbagai kandungan gentian telah dikaji, termasuk 25%, 30%, 35% dan 40%. Kandungan gentian sebanyak 25% ke 30% (peratus jisim) menunjukkan parameter pelindungan laga yang terbaik. Peratusan yang tinggi bagi bebanan gentian 40% atau lebih, disebabkan ikatan yang lemah antara gentian dan matriks, tidak mampu untuk memindahkan beban ke bahagian lain, dan seterusnya tegasan telah terkumpul pada tempat yang tertentu pada komposit, yang menjurus kepada sifat mekanikal penyerapan tenaga yang lebih rendah.Gentian penguat adalah kuat, kukuh dan efektif bagi meningkatkan sifat mekanikal bahan komposit. Walau bagaimana pun, gentian penguat selalunya rapuh dan berlelas, kurang liat, dan boleh merosot secara kimia bila didedahkan kepada persekitaran.Beberapa mod kegagalan berlainan telah dikenal pasti semasa eksperimen, termasuk mod kegagalan progresif, di mana kegagalan bermula pada bahagian hujung atas tiub, dan mod kegagalan rekahan melintang, iaitu yang berkaitan dengan mod kegagalan melengkok. Fasa kedua diuntukkan bagi mengkaji kelakuan penghancuran static bagi tiub komposit heksagon di bawah beban paksian seragam. Tiga kepanjangan bagi tiub komposit heksagon telah diuji 50, 100 dan 150 mm dengan sudut heksagon yang sama 45°. Keputusan menunjukkan bahawa tiub dengan kepanjangan 50 mm menunjukkan penyerapan tenaga spesifik yang tinggi dan juga purata beban penghancuran yang lebih tinggi.Fasa ketiga melibatkan pembikinan dan pengujian bagi lima tiub heksagon yang berbeza bagi gentian kenaf (tikar) dengan sudut yang berbeza daripada julat 40° ke 60° dan dalam 5° kenaikan sudut, bagi menentukan kesan geometri ke atas parameter pelindungan laga bagi tiub heksagon komposit diperkuat gentian kenaf. Keputusan yang diperolehi dalam fasa ini menunjukkan bahawa struktur gagal dalam beberapa mod kegagalan yang berlainan seperti mod kegagalan progresif dan kegagalan pencebisan yang berkaitan dengan rekahan membujur. Tiub komposit dengan $\beta = 60^{\circ}$ mempamerkan mod kegagalan melengkok setempat dan mempamerkan keupayaan penyerapan tenaga spesifik yang tertinggi bersamaan 9.2 kJ/kg. Sebaliknya, parameter pelindungan lagi yang baharu telah diperkenalkan sebagai penunjuk mod kegagalan bencana.Fasa terakhir adalah apabila spesimen dibebankan dengan beban mampatan kuasi-statik sisi. Dalam fasa ini, plat penyokongan telah digunakan di dalam tiub atas alasan berikut. Tujuan utama adalah bagi meningkatkan tenaga yang diserap oleh tiub. Peningkatan termasuk penggunaan bahan penyerapan tenaga dalam bahan dan struktur pada plat di dalam tiub bagi memastikan nyahpecutan yang lebih diingini ketika pelanggaran/kemalangan, menghasil lebih sedikit kecederaan kepada penumpang dan pemandu kereta. Tambahan pula, menggunakan plat di dalam tiub heksagon boleh mengawal agihan beban sewaktu penghancuran dan boleh mengurangkan berat struktur. Tiga tatarajah $\beta=40^{\circ}$, $\beta=50^{\circ}$ dan β =60° bagi epoksi/kenaf tidak tertenun telah telah dilaminat. Kesan sudut heksagon, plat penyokonan di dalam tiub, dan mod kegagalan telah dikaji menggunakan ujian mampatan sisi. Pelindungan laga tiub telah dinilai menggunakan analysis penyerapan tenaga spesifik dalam mampatan sisi kuasi-statik. Penyerapan tenaga specifik telah diperolehi daripada lengkok beban-sesaran ketika pengujian. Mod kegagalan bagi tiub telah dianalisis menggunakan fotograf resolusi tinggi. Secara keseluruhan, tiub dengan β =40° menunjukkan pelindungan laga yang terbaik antara semua tuib. Pada umumnya, keputusan menunjukkan bahawa tiub dengan plat penyokongan menunjukkan penyerapan tenaga spesifik yang lebih baik bagi kesemua specimen yang diuji dan mempamerkan kira-kira 69% pelindungan laga yang lebih baik daripada suatu yang tanpa penyokongan. Keputusan juga menunjukkan bahawa semua specimen gagal dengan mod kegagalan membujur.

AKNOWLEDGEMENTS

First my praise to almighty ALLAH for giving me the ability to complete this work with good health.

I appreciate the financial support of the Libyan Ministry of higher education, during my PhD study.

I would like to express my sincere gratitude to my supervisor Prof. Ir. Dr. Mohd Sapuan Salit for the continuous support of my PhD study and related research, for his patience, motivation, and immense knowledge. His guidance helped me in all the time of research and writing of thesis. I also appreciate the advice of committee members: Assoc. Prof. Dr. Nuraini bit. Abdul Aziz and Dr. Mohamad Ridzwan Ishak, for their insightful comments and encouragement.

My sincere thanks also goes to Assoc. Prof. Dr. Zulkiflle bin Leman. For his highly advise. Also, technicians in the Department Mechanical and Manufacturing Engineering (UPM) they provided me an opportunity to join their team as an intern, and who gave access to the laboratory and research facilities.

I have no enough words to express my profuse thanks to my family for their unconditional love and endless support that gave me strength to complete this work, especially the my kindly mother, my lovely father. A Special thank goes to my wife and children for their understanding, patience. Many thanks to light up my way to complete this work, is worth to mention all my friends for their support and cooperation. Thanks to my colleagues and staff in Faculty of Engineering especially Department Mechanical and Manufacturing Engineering (UPM) for their advice, assistance and kindness. This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Mohd Sapuan Salit, PhD

Professor Faculty of Engineering Unversiti Putra Malaysia (Chairman)

Nuraini Abdul Aziz, PhD

Associate Professor Faculty of Engineering Unversiti Putra Malaysia (Member)

Mohamad Ridzwan Ishak, PhD

Senior Lecturer Faculty of Engineering Unversiti Putra Malaysia (Member)

> **ROBIAH BINTI YUNS,PhD** Professor and Dean School of Graduate Studies Universiti Putra Malaysia

Date

Declaration by Members of Supervisory Committee

This is to confirm that:

- The research conducted and the writing of this thesis was under our supervision;
- Supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: Name of Chairman of Supervisory Committee:	Prof. Dr. Mohd Sapuan Salit
Signature: Name of Member of Supervisory Committee:	Associate Prof Dr.Nuraini bt. Abdul Aziz
Signature: Name of Member of Supervisory Committee:	Dr M ohamed Ridzwan Ishak

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	iii
ACKNOWLEDGEMENTS	V
APPROVAL	vi
DECLARATION	viii
LIST OF TABLES	xiii
LIST OF FIGURES	xiv
LIST OF ABBREVIATIONS	xviii

CHAPTER

1	INT	RODUCTION	1
	1.1	Background	1
	1.2	Significance of study	2
	1.3	Scope of study	3
	1.4	Problem statement	3
	1.5	Objectives	4
	1.6	Thesis Outline	4
		References	6
2	LIT	ERATURE REVIEW	
	2.1	Introduction	9
	2.2	Mechanical and physical properties of natural fibres	11
	2.3	Crashworthiness in composite structure	18
	2.4	Energy absorption in natural reinforced composite tubes	21
		2.4.1 Effect of geometry on peak load	23
		2.4.2 Effect of triggered and non-triggered on specific	
		energy and average load	25
		2.4.3 Shape and geometry	26
	2.5	Industrial application	28
	2.6	Failure mode	30
	2.7	Fabrication Process of Composite Shells.	32
		2.7.1 Hand Lay-up Process	33
		2.7.2 Filament winding process	35
	2.8	Failure Modes, and Crushing Behaviour of Thin Shells	38
		2.8.1 Catastrophic Failure Mode	40
		2.8.2 Progressive Failure Mode	42
	2.9	Failure Modes in Natural Fibre Tubes	43
		2.9.1 Failure Mechanisms	43
	2.10	Conclusion	49
		References	49

3.1Experimental work593.1.1Material and fibre preparation593.1.2Fabrication Process603.1.3The Experimental Procedure603.2Uncertainties Affects the Experimental Results643.2.1Void content643.2.2Calibration of the testing machine653.2.3Mixing up the mixture and adhesion Between layers65	
3.1.1Material and fibre preparation593.1.2Fabrication Process603.1.3The Experimental Procedure603.2Uncertainties Affects the Experimental Results643.2.1Void content643.2.2Calibration of the testing machine653.2.3Mixing up the mixture and adhesion Between layers65	
3.1.2Fabrication Process603.1.3The Experimental Procedure603.2Uncertainties Affects the Experimental Results643.2.1Void content643.2.2Calibration of the testing machine653.2.3Mixing up the mixture and adhesion Between layers65	
3.1.3The Experimental Procedure603.2Uncertainties Affects the Experimental Results643.2.1Void content643.2.2Calibration of the testing machine653.2.3Mixing up the mixture and adhesion Between layers65	
3.2Uncertainties Affects the Experimental Results643.2.1Void content643.2.2Calibration of the testing machine653.2.3Mixing up the mixture and adhesion Between layers65	
3.2.1Void content643.2.2Calibration of the testing machine653.2.3Mixing up the mixture and adhesion Between layers65	
3.2.2Calibration of the testing machine653.2.3Mixing up the mixture and adhesion Between layers65	
3.2.3 Mixing up the mixture and adhesion Between layers 65	
References 67	
4 THE EEFECT OF FIBRE CONTENT ON THE	
CRASHWORTHINESSPARAMETERS OF NATURAL	
KENAF FIBRE-REINFORCED HEXAGONAL COMPOSITE	
TUBES	
Article 1 69	
Acceptanc Lette 94	
Copyright Permission 95	
5 EXPERIMENTAL QUASI- STATIC AXIA CRUSHING OF	
NON-WOVEN KENAF FIBRE/EPOXY HEXAGONAL	
COMPOSITE TUBES	
Article 2 96	
Acceptance Letter 106	
Copyright Permission 107	
6 EFFECT OF GEOMETRY ON CRASHWORTHINESS	
PARAMETERS OF NATURAL KENAF FIBRE	
REINFORCED COMPOSITE TUBES	
Article 3 108	
Acceptance Letter 128	
Copyright Permission 129	
7 I ATEDAL COUSIINC DOODEDTIES OF NON WOVEN	
VENAE (MAT) DEINEODCED EDOVV COMDOSITE	
HEVACONAL THDES	
HEAAGONAL TUBES	
Article 4	
Article 4 130	
Article 4130Acceptance Letter152Conversion152	
Article 4130Acceptance Letter152Copyright Permission153	
Article 4130Acceptance Letter152Copyright Permission1538OUASI-STATIC LATERAL CRUSHING OF NON-WOVEN	
Article 4 130 Acceptance Letter 152 Copyright Permission 153 8 QUASI-STATIC LATERAL CRUSHING OF NON-WOVEN KENAF FIBRE REINFORCED COMPOSITE HEXACONAL	
Article 4 130 Acceptance Letter 152 Copyright Permission 153 8 QUASI-STATIC LATERAL CRUSHING OF NON-WOVEN KENAF FIBRE REINFORCED COMPOSITE HEXAGONAL TURES	
Article 4 130 Acceptance Letter 152 Copyright Permission 153 8 QUASI-STATIC LATERAL CRUSHING OF NON-WOVEN KENAF FIBRE REINFORCED COMPOSITE HEXAGONAL TUBES Article 5 154	
Article 4 130 Acceptance Letter 152 Copyright Permission 153 8 QUASI-STATIC LATERAL CRUSHING OF NON-WOVEN KENAF FIBRE REINFORCED COMPOSITE HEXAGONAL TUBES Article 5 154 Acceptance Letter 161	
Article 4 130 Acceptance Letter 152 Copyright Permission 153 8 QUASI-STATIC LATERAL CRUSHING OF NON-WOVEN KENAF FIBRE REINFORCED COMPOSITE HEXAGONAL TUBES Article 5 154 Acceptance Letter 161 Convright Permission 162	

9 CONCLUSION AND FUTURE WORK			
9.1	New contribution.	165	
	9.1.1 Catastrophic failure mode indictor (CFMI)	165	
	9.1.2 Tube resistant indicator (TRI)	165	
9.2	Failure mode	166	
9.3	Recommendation for future work	167	
BIODATA	OF STUDENT	168	
LIST OF P	UBLICATIONS	169	



 \bigcirc

LIST OF TABLES

Table		Page
2.1	Advantages and disadvantages of natural fibres	15
2.2	Mechanical and physical properties of natural fibres	16
2.3	Energy absorption capability and crash force efficiency of various natural fibres	29
3.1	Mechanical properties of natural kenaf fibre	60
4.1	The properties of the epoxy resin used (D.E.R. TM 331TM)	74
4.2	The mechanical properties of natural kenaf fibre	74
4.3	The relationship between the crashing parameters (C_e , P_m , SE and Et) and the fibre content	87
5.1	The dimension of the tubes	99
5.2	Crashworthiness parameters	103
6.1	Crashworthiness parameters for non-woven kenaf fibre/epoxy composite hexagonal tubes with various angles	121
6.2	Type of crushing failure modes in per-crushing stage	121
7.1	Mechanical properties of natural kenaf fiber	133
7.2	Description of the of non-woven, natural kenaf mat/epoxy hexagonal tubes of each configuration	137

LIST OF FIGURES

Figure		Page
2.1	Diagram of the rotating sample stand used during gelling and curin	10
2.2	Effect of fibre content on tensile properties	12
2.3	Comparison of tensile strength of kenaf/PP-MAPP composites to	12
	other natural fibre composites	
2.4	Comparison of specific modulus of various fibres	13
2.5	Comparison of flexural strength of kenaf/PP-MAPP composites to	13
	other natural fibre composites	
2.6	Scanning electron microscopy tensile fractured specimen	17
2.7	Classifications of natural and synthetic fibres	18
2.8	Various variables that affect the crashworthiness parameters of	19
	composite materials	
2.9	Schematic diagram of criteria affecting the selection of natural	20
	fibre composite materials	
2.10	Flax FRP hollow tube (b) Typical cone under investigation (c)	
	Square silk/epoxy tube (d) Silk/epoxy rectangular composite	21
2.11	Typical load-displacement response	23
2.12	Peak and average load characteristics for composite square tubes	24
2.13	Relationship between crashworthiness parameters and the number	24
	of layers for empty flax/epoxy tubes	
2.14	Plug trigger and (b) four rectangular metallic piece trigger	25
	located on the flat plate	
2.15	Flax/epoxy composite tubes with different configurations.	26
2.16	The effect of the number of plies on the SAE of the specimens	27
2.17	Specific crushing energy data for natural fibres and shells.	29
2.18	Crushing force efficiency, energy data for natural fibres and shells	30
2.19	Progressive crushing of specimens	31
2.20	Local buckling or mid-length buckling	32
2.21	Delamination, tear and buckling	33
2.22	Mold for composite fabrication and composites configuration	34
2.22	using hand- lay-up method	25
2.23	Details of triggering. Different geometrical shapes	35
2.24	Photograph and Schematic illustration of carbon/aramid	30
2.25	Impregnated fibres in filament winding process	37
2.26	Kenar composite snarts without aluminum (left) and with	37
2 27	aluminum (fight)	20
2.27	The principle of a druin-type impregnation unit.	20 20
2.28	Hemp mat	39 40
2.29	Non woven (mot) notural kenef fibre	40
2.30	Deformation patterns and the grushing performance of the square	40
2.51	cross sectional composite tubes	41
2.32	Load-displacement curves and deformation history of RCSCT	42
	specimen under lateral crushing load	
2.33	Deformation patterns and the crushing performance of the circular	44
	cross section composite tubes	

2.34	photographs of different steps of compression test	44
2.35	Examples of NFC tubes with four reinforcement arrangements	45
2.36	Comparative between same to configuration tubes and different	47
	material	
2.37	Crushing of specimens	48
3.1	Energy absorption parameters	61
3.2	Flow chart of the steps used in this work	62
3.3	Non-woven (mat) natural kenaf fibre	63
3.4	Fabrication steps	63
3.5	Instron 3382 universal testing system with a full load range of 100 kN	64
3.6	Microscopic photos of the typical voids inside laminate	66
3.7	Demonstration of how the cutting point and length measuring	67
	affected the test results	
4.1	The growth outlook for natural fibres in the USA from 2000 to 2005 by application	70
4.2	The effect of the fibre content on the tensile strength and modulus	72
4.3	Non-woven kenaf fibre	73
4.4	The hand and electric cutting machines	74
4.5	A schematic diagram of the specimen	76
4.6	The Instron 3382 universal testing system	77
4.7	A schematic of the load- displacement relationship for composite	78
	tubes	
4.8	Load-displacement curves for hexagonal composite tubes with fibre contents of 25%	80
4.9	Load-displacement curves for hexagonal composite tubes with fibre contents of 30	81
4.10	Load-displacement curves for hexagonal composite tubes with fibre contents of 35%	83
4.11	Load-displacement curves for hexagonal composite tubes with fibre contents of 40%	84
4.12	The average crash load (Pm) for the non-woven kenaf (mat)/epoxy	85
4.12	hexagonal tubes The average here $f_{\rm const}$ here $f_{\rm const}$	96
4.15	The energy absorbed (E_t) by non-woven kenal $(mat)/epoxy$	80
4.14	A micrograph of the surface of the wall and the failure modes of the tube	88
5.1	Photographs of (b) non-woven kenaf fibre and (b) geometry	98
5.2	Load –displacement curve and deformation history of (H 100)	100
5.2	specimen under axial load	100
5.3	Load –displacement curve and deformation history of (H.100)	101
5.4	Load displacement sums and deformation history of (U 150)	102
5.4	specimen under axial load	102
6.1	Typical load displacement curve	111
6.2	Non-woven (mat) natural kenaf fibre	112
6.3	Fabrication steps	113
6.4	Universal Testing Machine	114
6.5	Load - displacement curve and deformation history of $\beta.40^\circ$ specimen under axial load	116

0

6.	.6	Load–displacement curve and deformation history of β .45° maximum under axial load	117
6.	.7	Load–displacement curve and deformation history of β .50°	118
		specimen under axial load	
6.	.8	Load–displacement curve and deformation history of β .55° specimen under axial load	119
6.	.9	Load–displacement curve and deformation history of $\beta.60^{\circ}$	120
<i>,</i>	10	specimen under axial load	100
6.	.10	fibre/epoxy composite hexagonal tubes with various angles	122
6.	.11	Comparative specific energy absorption characteristics for 24	123
		layers non-triggered and triggered composite square tubes	
6.	.12	Catastrophic failure mode	124
7.	.1	Non-woven kenaf fiber (mat)	134
7.	.2	Sketch of a typical design of the experiment set-up	136
7.	.3	Load -displacement plots at the pre-crushing stage	138
7.	.4	Peak load characteristics for composite hexagonal tubes at	139
		different angles for supported and non-supported tube	
7.	.5	Experimental set-up	140
7.	.6	Load -displacement curve with crushing stages	140
7.	.7	Load-displacement curves of supporting non-woven natural	141
7	0	kenat/epoxy hexagonal	1.40
7.	.8	epoxy composite hexagonal	142
7.	.9	Tube resistant indicator for the lateral compression test	143
7.	.10	Deformation history of supported hexagonal	145
7.	.11	Comparison between the crushing modes of the supporting plate inside a non-woven Kenaf/epoxy composite tube and empty tubes	145
7.	.12	(A, B, C and D) Fracture in the fiber surface of the non-woven	146
7	13	Damage mechanism of carbon/enoxy packing	147
7. 7	.15	Parcentege of aborbed energy by the two configurations of	147
7.	.14	hexagonal tubes	140
8.	.1	Load–displacement curve of $\beta 40^{\circ}$, $\beta 50^{\circ}$ and $\beta 60^{\circ}$ for lateral crushing load	157
8.	.2	The failure mode of the non- woven natural kenaf epoxy composite hexagonal tube: summarized as longitudinal fracture failure mode	157
Q	3	Optical micrographs showing (a) Fiber fracture, and fiber brookage	158
0.	.5	The energy shorted by the bayagenel composite tubes subjected	150
0.	.4	to lateral crushing load	100

LIST OF ABBREVIATIONS

β	Hexagonal angle (°)
SEA	Specific energy absorption (J/Kg)
S.H.T.β	Hexagonal tube with a supporting plate
E.H.T.β	An empty hexagonal tube
Pi	Peak load kN
TRI	Tube resistant indicator
m	The specimen mass kg
S and Si	Crushing distances (mm)
CFE	Crush Force Efficiency (-)
Es	Specific energy absorption (J/g)
IFI	Initial failure indicator
М	Weight of the specimens (kg)
CFMI	Catastrophic failure mode indictor (%)
P _{cr}	Critical crushing load (kN)
NFR	Natural fiber reinforcement
Pm	Mean crash load kN
(E _t):	Total energy absorbed kJ
SE	Stroke efficiency %

CHAPTER 1

INTRODUCTION

1.1 Background

Fibre reinforced polymers (FRP) are composite materials comprised of a polymer matrix combined with high-strength fibres such as glass, aramid and carbon. Although these composite materials exhibit excellent mechanical properties, they also give rise to environmental pollution due to their non-degradability [1, 2]. Currently, traditional reinforcement materials such as glass and carbon fibres are increasingly being replaced by advanced composite materials, e.g., natural fibre-reinforced polymers (NFRP). It is expected that use of fibre/polymer composites will expand in the near future due to the many advantages offered by these materials such as high strength, low weight and corrosion resistance [3].

Several natural fibres such as hemp, flax, sisal, kenaf, and jute have been used in different industrial applications. Recently, natural fibres have drawn the interest of researchers, engineers and scientists as substitute reinforcements for fibre reinforced polymer (FRP) composites tubes. Due to their fairly good mechanical properties, low cost, high specific strength, environmentally-friendly and bio-degradability, ease of fabrication, and good structural rigidity, these materials can be used in an extensive range of applications, including aerospace and the automotive industry. Previous studies focused on how to introduce the natural fibre materials. The tensile properties of natural fibre reinforce polymers are mainly influenced by Mechanical properties such as tensile properties, flexural properties, and impact strength is strongly affected by fiber content.

In particular, crashworthiness has attracted much attention, especially for the evaluation of crushing behavior and the energy absorbing capability of various composite shapes. In automotive engineering, crashworthiness is defined as the capability of a vehicle to protect its occupants and passengers from serious injury and harm or death in case of accidents or sudden impacts of a specified magnitude. Crashworthiness is related to energy absorption through controlled failure modes that enable the maintenance of a gradual decay in the load profile during energy absorption [4, 5].

Studies of natural fibre-reinforced plastic (NFRP) have been carried out for special geometric shapes of composite tubes that are mainly intended for automobile crashworthy applications due to their favourable strength, weight and corrosion resistance [6-9].Several researchers reported that a well-designed NFRP composite can exhibit better energy absorption than metals; natural composite materials such as kenaf, silk and hemp fibre-reinforced composite tubes subjected to axial crushing will undergo a fracture to obtain energy absorption rather than the fibre deformation exhibited in metal

tubing [10-12]. As reported previously [13], delamination, local buckling, and bending failure modes make the largest contributions to energy absorption.

In recent eras, most studies globally wide were concerned with the difference methods of incorporating natural fibres, such as hemp, flax, kenaf or bagasse into various types of polymer compositions, in order to modify their properties and to decrease their costs and increasing environmental concern and requirement for developing sustainable materials in engineering application [14-17]. Commonly, the method of processing produce the composite structure for both of fibres were Filament winding process, Hand Lay-up Process followed by curing stage to gain the final product to be ready for test [18-20]. The synthetic fibre used as a fibre part not only for increased tensile strength, the flexural rigidity and crashworthiness properties of the final product, however additionally, helped to ligament the natural fibres together and aided to mold for desired final shape [21, 22].

1.2 Significance of study

- 1. Several reasons, including weight saving, low density, corrosion resistance, availability, being renewable, environmentally friendly and ease of handling make natural fibers superiors to syntheses fibers in the automobile manufacturing sector.
- 2. Kenaf fibre was used as reinforcement due to fabricate hexagonal campsite tubes. Due to its low cost, high specific strength, environmentally-friendly and bio-degradability, ease of fabrication, and good structural rigidity, these materials can be used in an extensive range of applications, including aerospace and the automotive industry.
- 3. Kenaf Natural fibre composites-epoxy, are particularly attractive in automotive applications because of lower cost and lower density. Compared to the Glass fibres and carbon fibres Problem Statements
- 4. Catastrophic failure modes in composite structure cause less energy absorption capability and instability in failure.
- 5. The successful development of natural fibres such as kenaf (mat) and yarn would provide opportunities to improve the energy absorption capability and crushing behavior of automobile accidents.
- 6. The findings from the current study are expected to enhance the knowledge in developing high performance of the industrial sector.

1.3 Scope of study

In this work, The kenaf yarn and (mat) fibres were supplied by (IPSB) Innovative Pultrusion Sdn.Bhd., Seremban, Malaysia. The kenaf (mat) originally comes in a mat

form. This research is limited to experiments to study the potential of using kenaf natural fibres reinforced hexagonal composite tubes. In the industrial application.

In this study, the fabrication process involved The wet wrapping process by hand lay-up was used to fabricate the specimens of non-woven kenaf fibre/epoxy composite hexagonal tubes.

Before fabricate the specimens composite, the kenaf fibre must be processed first to find the different size of kenaf fibre. Then, the axial and lateral tests are carried out on this composite. The microstructure of this composite will be observed by using the Scanning Electron Microscope (SEM). In order to achieve the objective, the scope of research was to make a feasibility study on fibre contents for fibre reinforced hexagonal composite tube, fibre loading is used with value of 20% to 40% to get the best composition for the composite. To considered properties of crashworthiness hexagonal composite tubes in this study to Initial peak Load (Pi), Mean-Crushing Load (Pm), Crush Force Efficiency (CFE), Initial Failure Indictor (IFI) and Specific Energy Absorption (Es). At this stage, two new parameters of crashworthiness were introduced from compression test the first one is indicated for the catastrophic failure mode. It presents a criterion for determining withers the tubes crash in catastrophic or otherwise and Tube resistant indicator (TRI), The tube resistant indicator can be defined as the peak load value per average load value. To protect passengers from shock loads, the tube resistant indicator should be kept in unity. Finally, This work limited to investigate few effects of crushing behavioer and failure modes of composite hexagonal tubes such as, the effect of fibre content, effect of length, The effect of geometry, effect of the fibre reinforcement type.

1.4 Problem Statements

Many issues are associated with car bodies, such as using a metal, which leads to a corrosion point in the car body, to obtain better design. Roads and airplanes are designed to absorb crushing energy for passenger safety. This research is allocated to investigate the effect of structural geometry of crushing behavior, failure mechanism, and failure mode and energy absorption capability.

Failure of a structure component defined as the. Inability of the component to carry load. Generally, failure occurs when a component of the structure has no more ability to carry the load, in other words, when the component is no longer capable of satisfactory fulfilling its service function either because of fractures, excessive deformation, deterioration, or any other mechanisms of failure. When failure occurs, it causes a permanent deformation, load redistribution within the structure, and may cause large reductions in laminate stiffness and strength and any of these or all together cause the damage to grow. Some studies have used a filler tube to absorb the energy, but the weight of such tubes is too high. Natural and synthetic fibers are known for its low density, easier fabrication than metallic, and their structural rigidity are high, and can be used for wide applications, such as. Aerospace applications and automotive industry sector. Owing to this, in depth studies had been conducted to evaluate its failure modes and

process of fabrication for axial and lateral crushing behavior to replace metallic materials. In this thesis, Failure modes and geometrical designs such as shapes, triggering, geometry and effect have been studied where these factors affected on crashworthiness parameters

Furthermore, the current work used a supporting plate inside hexagonal tubes for the following reasons. The main purpose was to improve of the energy absorbed by tubes. The improvements, including the use on energy absorbing materials and structures in the plate inside the tubes, ensure more favorable decelerations during a crash/accident, resulting in fewer injuries for the car occupants. Furthermore, using the supporting plate inside hexagonal tubes can control the load distribution during the crushing period and can diminish the structure weight.

1.5 Objectives

The objective of this research work to

- To find out the best value of fibre content that effect on the crashworthiness parameters and the failure modes of non-woven kenaf fibre (mat) reinforced hexagonal composite tubes.
- To examine the influence of response of hexagonal light to quasi-static axial compressive load of non-woven kenaf fibre/epoxy hexagonal composite tubes.
- To investigate the effect of geometry on energy absorption capability and loadcarrying capacity of natural kenaf fibre reinforced composite hexagonal tubes.
- To determine the effect of supporting plates inside the hexagonal tubes with variable side hexagonal angles in terms of the improvement of crashworthiness.
- To investigate experimentally the effect of hexagonal angles on the failure modes and specific energy absorption capability of hexagonal composite tubes.

To achieve these objectives, the following tools were either designed, fabricated or conducted:

- 1. Design and fabrication of novel mandrels with different Hexagonal angles.
- 2. Renovate a filament winding machine.
- 3. Fabrication of hexagonal composite specimens with different tube lengths and differenthexagonal angles.
- 4. Conduct quasi static (axial and lateral) crushing tests.
- 5. Conduct microscopic investigation to characterize the failure modes.

1.6 Thesis Outline

The layout of this thesis is in accordance with Universiti Putra Malaysia alternative thesis format based on publications, in which each research chapter (3 - 9) represent a separate

study that has its own introduction, Materials and methods, Results and discussion, and Conclusion. The details of the thesis structure are presented beneath.

Chapter 1

The problems and the research objectives were clearly highlighted in this chapter. In addition, the significant contribution and scope of this study were also elucidated within the chapter1.

Chapter 2

Literature review, which presents an overview of the developments made in the area of natural fibres reinforced composites, in terms of their physical and mechanical properties, and crashworthiness properties and Failure modes.

Chapter 3

The methodologies by which the current work was approached are in the details in this chapter . Uncertainties affecting the experimental results such as, Void content, Calibration of the testing machine, Reading error and Maxing up the mixture and adhesion between layers were discussed in this chapter.

Chapter 4

This chapter presents the article entitled. The effect of fibre content on the crashworthiness parameters of natural kenaf fibre-reinforced hexagonal composite tubes. Studies an experimentally the effect of the fibre content on the crashworthiness parameters and the failure modes of non-woven kenaf fibre (mat) reinforced hexagonal composite tubes. Various fibre contents were considered, including 25%, 30%, 35% and 40%.

Chapter 5

Presents the behavior of composite hexagonal tubes under constant axial load, article two entitled Experimental quasi – static axial crushing of non-woven kenaf fibre/epoxy hexagonal composite tubes .Three lengths of hexagonal composite tubes were tested 50, 100, and 150 mm. It also addresses experimentally the effect of length on energy absorption capability and load - carrying capacity of non-woven kenaf /epoxy wrapped hexagonal composite tubes under quasi-static axial compressive load.

Chapter 6

This chapter presents the third objective with article four entitled. Effect of geometry on crashworthiness parameters of natural fibre reinforced hexagonal tubes The Inclusive experimental work implements to study the response of non-woven kenaf fibre/epoxy composite hexagonal tubes to quasi-static axial compressive load. A series of experiments carried out for composite hexagonal tubes with different angles from a range of 40° – 60° in 5° steps. This range is suitable for obtaining a regular hexagonal shape.

Chapter 7 and 8

In this chapter, two articles entitled.Lateral crushing properties of non-woven kenaf (mat) –reinforced epoxy composite hexagonal tubes and Quasi-static lateral crushing of non-wovn kenaf fibre reinfored composite Hexagonal tube .

Three configurations of β =40°, β =50° and β =60° of natural non-woven kenaf (mat) /epoxy laminate. The effects of hexagonal angles, supporting plate inside the tubes, and failure modes, were studied by a lateral compression test. The crashworthiness of the tubes was evaluated by analysis of the specific energy absorption in quasi-static lateral compression. Specific energy absorption was obtained from the load–displacement curve during testing. The failure mode of the tubes was analyzed from high resolution photographs.

Chapter 9

Finally, the overall conclusions of the various research articles as well as relevant suggestions for future research were presented in this chapter.

- [1] GR A, Sanjay M, Yogesha B. Review on compartive evaluation of fiber reinforced polymer matrix composite. Carbon. 2014;4000:30.
- [2] Thiruchitrambalam M, Alavudeen A, Athijayamani A, Venkateshwaran N, Perumal AE. Improving mechanical properties of banana/kenaf polyester hybrid composites using sodium laulryl sulfate treatment. Mater Phys Mech. 2009;8:165-73.
- [3] El-Shekeil YA, Sapuan SM, Algrafi MW. Effect of fiber loading on mechanical and morphological properties of cocoa pod husk fibers reinforced thermoplastic polyurethane composites. Materials & Design. 2014;64:330-3.

- [4] Bisagni C. Experimental investigation of the collapse modes and energy absorption characteristics of composite tubes. International Journal of Crashworthiness. 2009;14:365-78.
- [5] Mahdi E, Alkoles O, Hamouda A, Sahari B. Ellipticity ratio effects in the energy absorption of laterally crushed composite tubes. Advanced Composite Materials. 2006;15:95-113.
- [6] Eshkoor R, Ude A, Sulong A, Zulkifli R, Ariffin A, Azhari C. Energy absorption and load carrying capability of woven natural silk epoxy–triggered composite tubes. Composites Part B: Engineering. 2015;77:10-8.
- [7] Holbery J, Houston D. Natural-fiber-reinforced polymer composites in automotive applications. Jom. 2006;58:80-6.
- [8] Yan L, Chouw N. Crashworthiness characteristics of flax fibre reinforced epoxy tubes for energy absorption application. Materials & Design. 2013;51:629-40.
- [9] Joshi SV, Drzal L, Mohanty A, Arora S. Are natural fiber composites environmentally superior to glass fiber reinforced composites? Composites Part A: applied science and manufacturing. 2004;35:371-6.
- [10] Alkbir MFM, Sapuan SM, Nuraini AA, Ishak MR. Effect of geometry on crashworthiness parameters of natural kenaf fibre reinforced composite hexagonal tubes. Materials & Design. 2014;60:85-93.
- [11] Węcławski BT, Fan M, Hui D. Compressive behaviour of natural fibre composite. Composites Part B: Engineering. 2014;67:183-91.
- [12] Ataollahi S, Taher ST, Eshkoor R, Ariffin AK, Azhari CH. Energy absorption and failure response of silk/epoxy composite square tubes: experimental. Composites Part B: Engineering. 2012;43:542-8.
- [13] Eshkoor R, Ude A, Oshkovr S, Sulong A, Zulkifli R, Ariffin A, et al. Failure mechanism of woven natural silk/epoxy rectangular composite tubes under axial quasi-static crushing test using trigger mechanism. International Journal of Impact Engineering. 2014;64:53-61.
- [14] Mohanty AK, Misra M, Drzal LT. Natural fibers, biopolymers, and biocomposites: CRC Press; 2005.
- [15] Oksman K, Skrifvars M, Selin J-F. Natural fibres as reinforcement in polylactic acid (PLA) composites. Composites science and technology. 2003;63:1317-24.
- [16] Faruk O, Bledzki AK, Fink H-P, Sain M. Biocomposites reinforced with natural fibers: 2000–2010. Progress in Polymer Science. 2012;37:1552-96.
- [17] Abilash N, Sivapragash M. Environmental benefits of ecofriendly natural fiber reinforced polymeric composite materials. IJAIEM. 2013;2:54-6.

- [18] Abdalla F, Mutasher S, Khalid Y, Sapuan S, Hamouda A, Sahari B, et al. Design and fabrication of low cost filament winding machine. Materials & Design. 2007;28:234-9.
- [19] Ahmed KS, Acharya NJ, Aslam S, Ali M. Design and Fabrication of Low Cost Filament Winding Machine. Advances n Mechanical Engineering. 2010:128.
- [20] Palanivelu S, Van Paepegem W, Degrieck J, Vantomme J, Kakogiannis D, Van Ackeren J, et al. Crushing and energy absorption performance of different geometrical shapes of small-scale glass/polyester composite tubes under quasistatic loading conditions. Composite Structures. 2011;93:992-1007.
- [21] Jacob M, Thomas S, Varughese KT. Mechanical properties of sisal/oil palm hybrid fiber reinforced natural rubber composites. Composites science and technology. 2004;64:955-65.
- [22] Thwe MM, Liao K. Effects of environmental aging on the mechanical properties of bamboo–glass fiber reinforced polymer matrix hybrid composites. Composites Part A: applied science and manufacturing. 2002;33:43-5

2.10 Conclusion

From the previous literature review, the following can be concluded:

- Many research works are administrated on thin walled synthetic composite shells and only a few studies carried out on natural fibre reinforced composite tubes as well as. Most of them have focused on investigation the effect of different parameters the geometry cross section area, loading conditions, length, thickness, diameter, etc, fibre orientation, composite constituents, laminate sequence, etc. on crushing behavior, crashworthiness parameters , and failure modes.
- Most of these studies and investigations are experimentally carried out where the Effect factors were studied by developing, creating a relation between load applied -displacement were done under axial and lateral compression test.
- The failure modes and crushing behavior in composite tubes depend on the type of material reinforced composite tubes and structure.

The manners in which composite materials absorb energy are a lot of complicated and wildly differ from the same conventional material structures. From a crashworthiness point of view, the problem with failure mode of structure is that when the failure happens the main of the load-carrying capacity is lost, resulting in catastrophic non-crashworthy failure, the instability behavior of composite structures under crushing load and their uncontrolled failure mode are some problems that need more attention. The instability should be avoided to maximize the energy absorption capability and load carrying capacity.

- [1] G.R. Arpitha, M.R. Sanjay, B. Yogesha, Review Article Review on comparative on evaluation of fiber reinforced, Adv. Eng. Appl. Sci. An Int. J. 4 (2014) 44–47.
- [2] M. Thiruchitrambalam, a Alavudeen, a Athijayamani, N. Venkateshwaran, a Elaya Perumal, Improving Mechanical Properties of Banana / Kenaf Polyester Hybrid Composites Using Sodium Laulryl Sulfate Treatment ., Mater. Phys. Mech. 8 (2009) 165–173.
- [3] Y.A. El-Shekeil, S.M. Sapuan, M.W. Algrafi, Effect of fiber loading on mechanical and morphological properties of cocoa pod husk fibers reinforced thermoplastic polyurethane composites, Mater. Des. 64 (2014) 330–333. doi:10.1016/j.matdes.2014.07.034.

- [4] A. K. Mohanty, M. Misra, L.T. Drzal, Surface modifications of natural fibers and performance of the resulting biocomposites: An overview, Compos. Interfaces. 8 (2001) 313–343. doi:10.1163/156855401753255422.
- [5] A. Le Duigou, C. Baley, Y. Grohens, P. Davies, J.Y. Cognard, R. Cr ach'Cadec, et al., A multi-scale study of the interface between natural fibres and a biopolymer, Compos. Part A Appl. Sci. Manuf. 65 (2014) 161–168. doi:10.1016/j.compositesa.2014.06.010.
- [6] Y. Li, Y.-W. Mai, L. Ye, Sisal fibre and its composites: a review of recent developments, Compos. Sci. Technol. 60 (2000) 2037–2055. doi:10.1016/S0266-3538(00)00101-9.
- [7] D. Paukszta, S. Borysiak, The influence of processing and the polymorphism of lignocellulosic fillers on the structure and properties of composite materials-A review, Materials (Basel). 6 (2013) 2747–2767. doi:10.3390/ma6072747.
- [8] G. Koronis, A. Silva, M. Fontul, Green composites: A review of adequate materials for automotive applications, Compos.Part B Eng. 44 (2013) 120–127. doi:10.1016/j.compositesb.2012.07.004.
- [9] G.N. Ramaswamy, T. Sellers, W. Tao, L. Grand, Kenaf nonwo as substrates for laminations, Ind. Crops Prod. 17 (2003) 1–8. doi:10.1016/S0926-6690(02)00040-7.
- [10] C. Bisagni, Experimental investigation of the collapse modes and energy absorption characteristics of composite tubes, Int. J. Crashworthiness. 14 (2009) 365–378. doi:10.1080/13588260902792954.
- [11] O.M.S. Alkoles, E. Mahdi, A.M.S. Hamouda, B.B. Sahari, Ellipticity ratio effects in the energy absorption of axially crushed composite tubes, Appl. Compos. Mater. 10 (2003) 339–363. doi:10.1023/A:1025766609635.
- [12] R.A. Eshkoor, A.U. Ude, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Energy absorption and load carrying capability of woven natural silk epoxy -Triggered composite tubes, Compos. Part B Eng. 77 (2015) 10–18. doi:10.1016/j.compositesb.2015.03.017.
- [13] J. Holbery, D. Houston, Natural-fibre-reinforced polymer composites in automotive applications, Jom. 58 (2006) 80–86.
- [14] S. V. Joshi, L.T. Drzal, A.K. Mohanty, S. Arora, Are natural fiber composites environmentally superior to glass fiber reinforced composites?, Compos. Part A Appl. Sci. Manuf. 35 (2004) 371–376. doi:10.1016/j.compositesa.2003.09.016.
- [15] L. Yan, N. Chouw, Crashworthiness characteristics of flax fibre reinforced epoxy tubes for energy absorption application, Mater. Des. 51 (2013) 629–640. doi:10.1016/j.matdes.2013.04.014.
- [16] M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, Effect of geometry on

crashworthiness parameters of natural kenaf fibre reinforced composite hexagonal tubes, Mater. Des. 60 (2014) 85–93.

- [17] B.T. Wc awski, M. Fan, D. Hui, Compressive behaviour of natural fibre composite, Compos. Part B Eng. 67 (2014) 183–191. doi:10.1016/j.compositesb.2014.07.014.
- [18] S. Ataollahi, S.T. Taher, R.A. Eshkoor, A.K. Ariffin, C.H. Azhari, Energy absorption and failure response of silk/epoxy composite square tubes: Experimental, Compos. Part B Eng. 43 (2012) 542–548. doi:10.1016/j.compositesb.2011.08.019.
- [19] R.A. Eshkoor, A.U. Ude, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, et al., Failure mechanism of woven natural silk/epoxy rectangular composite tubes under axial quasi-static crushing test using trigger mechanism, Int. J. Impact Eng. 64 (2014) 53–61. doi:10.1016/j.ijimpeng.2013.09.004.
- [20] M. Fan, D. Hui, Composites : Part B Compressive behaviour of natural fibre composite, 67 (2014) 183–191. doi:10.1016/j.compositesb.2014.07.014.
- [21] R. Mahjoub, J.M. Yatim, A.R. Mohd Sam, S.H. Hashemi, Tensile properties of kenaf fiber due to various conditions of chemical fiber surface modifications, Constr. Build. Mater. 55 (2014) 103–113. doi:10.1016/j.conbuildmat.2014.01.036.
- [22] P.J. Herrera-Franco, A. Valadez-Gonzlez, Mechanical properties of continuous natural fibre-reinforced polymer composites, Compos. Part A Appl. Sci. Manuf. 35 (2004) 339–345. doi:10.1016/j.compositesa.2003.09.012.
- [23] S. Ochi, Mechanical properties of kenaf fibers and kenaf/PLA composites, Mech. Mater. 40 (2008) 446–452. doi:10.1016/j.mechmat.2007.10.006.
- [24] S.M. Sapuan, a. Leenie, M. Harimi, Y.K. Beng, Mechanical properties of woven banana fibre reinforced epoxy composites, Mater. Des. 27 (2006) 689– 693. doi:10.1016/j.matdes.2004.12.016.
- [25] J. Datta, P. Kopczyska, Effect of kenaf fibre modification on morphology and mechanical properties of thermoplastic polyurethane materials, Ind. Crops Prod. 74 (2015) 566–576. doi:10.1016/j.indcrop.2015.05.080.
- [26] C. Alves, P.M.C. Ferro, A.J. Silva, L.G. Reis, M. Freitas, L.B. Rodrigues, et al., Ecodesign of automotive components making use of natural jute fiber composites, J. Clean. Prod. 18 (2010) 313–327. doi:10.1016/j.jclepro.2009.10.022.
- T. Gurunathan, S. Mohanty, S.K. Nayak, A Review of the Recent Developments in Biocomposites Based on Natural Fibres and Their Application Perspectives, Compos. Part A Appl. Sci. Manuf. 77 (2015) 1–25. doi:10.1016/j.compositesa.2015.06.007.

- [28] B.F. Yousif, S.T.W. Lau, S. McWilliam, Polyester composite based on betelnut fibre for tribological applications, Tribol. Int. 43 (2010) 503–511. doi:10.1016/j.triboint.2009.08.006.
- [29] Y.A. El-Shekeil, S.M. Sapuan, K. Abdan, E.S. Zainudin, Influence of fiber content on the mechanical and thermal properties of Kenaf fiber reinforced thermoplastic polyurethane composites, Mater. Des. 40 (2012) 299–303. doi:10.1016/j.matdes.2012.04.003.
- [30] M. Jawaid, H.P.S.A. Khalil, A.A. Bakar, P.N. Khanam, Chemical resistance, void content and tensile properties of oil palm/jute fibre reinforced polymer hybrid composites, Mater. Des. 32 (2011) 1014–1019. doi:10.1016/j.matdes.2010.07.033.
- [31] M. Boopalan, M. Niranjanaa, M.J. Umapathy, Study on the mechanical properties and thermal properties of jute and banana fiber reinforced epoxy hybrid composites, Compos. Part B Eng. 51 (2013) 54–57. doi:10.1016/j.compositesb.2013.02.033.
- [32] N. Venkateshwaran, A. ElayaPerumal, A. Alavudeen, M. Thiruchitrambalam, Mechanical and water absorption behaviour of banana/sisal reinforced hybrid composites, Mater. Des. 32 (2011) 4017–4021. doi:10.1016/j.matdes.2011.03.002.
- [33] M. Zampaloni, F. Pourboghrat, S.A. Yankovich, B.N. Rodgers, J. Moore, L.T. Drzal, et al., Kenaf natural fiber reinforced polypropylene composites: A discussion on manufacturing problems and solutions, Compos. Part A Appl. Sci. Manuf. 38 (2007) 1569–1580. doi:10.1016/j.compositesa.2007.01.001.
- [34] A. Alavudeen, N. Rajini, S. Karthikeyan, M. Thiruchitrambalam, N. Venkateshwaren, Mechanical properties of banana/kenaf fiber-reinforced hybrid polyester composites: Effect of woven fabric and random orientation, Mater. Des. 66 (2015) 246–257. doi:10.1016/j.matdes.2014.10.067.
- [35] A.W. Van Vuure, J. Baets, K. Wouters, K. Hendrickx, Compressive properties of natural fibre composites, Mater. Lett. 149 (2015) 138–140. doi:10.1016/j.matlet.2015.01.158.
- [36] F.Z. Arrakhiz, M. El Achaby, A.C. Kakou, S. Vaudreuil, K. Benmoussa, R. Bouhfid, et al., Mechanical properties of high density polyethylene reinforced with chemically modified coir fibers: Impact of chemical treatments, Mater. Des. 37 (2012) 379–383. doi:10.1016/j.matdes.2012.01.020.
- [37] A.C. Manalo, E. Wani, N.A. Zukarnain, W. Karunasena, K. Lau, Effects of alkali treatment and elevated temperature on the mechanical properties of bamboo fibre–polyester composites, Compos. Part B Eng. 80 (2015) 73–83. doi:http://dx.doi.org/10.1016/j.compositesb.2015.05.033.
- [38] A.K. Bledzki, P. Franciszczak, Z. Osman, M. Elbadawi, Polypropylene

biocomposites reinforced with softwood, abaca, jute, and kenaf fibers, Ind. Crops Prod. 70 (2015) 91–99. doi:10.1016/j.indcrop.2015.03.013.

- [39] N. Defoirdt, S. Biswas, L. De Vriese, L.Q.N. Tran, J. Van Acker, Q. Ahsan, et al., Assessment of the tensile properties of coir, bamboo and jute fibre, Compos. Part A Appl. Sci. Manuf. 41 (2010) 588–595. doi:10.1016/j.compositesa.2010.01.005.
- [40] H. yan Cheung, M. po Ho, K. tak Lau, F. Cardona, D. Hui, Natural fibrereinforced composites for bioengineering and environmental engineering applications, Compos. Part B Eng. 40 (2009) 655–663. doi:10.1016/j.compositesb.2009.04.014.
- [41] E.P. Ayswarya, K.F. Vidya Francis, V.S. Renju, E.T. Thachil, Rice husk ash A valuable reinforcement for high density polyethylene, Mater. Des. 41 (2012) 1–7. doi:10.1016/j.matdes.2012.04.035.
- [42] M. Jawaid, H.P.S. Abdul Khalil, Cellulosic/synthetic fibre reinforced polymer hybrid composites: A review, Carbohydr. Polym. 86 (2011) 1–18. doi:10.1016/j.carbpol.2011.04.043.
- [43] M. Ramesh, K. Palanikumar, K.H. Reddy, Mechanical property evaluation of sisal-jute-glass fiber reinforced polyester composites, Compos. Part B Eng. 48 (2013) 1–9. doi:10.1016/j.compositesb.2012.12.004.
- [44] S. Kalia, B.S. Kaith, I. Kaur, Pretreatments of natural fibers and their application as reinforcing material in polymer composites-a review, Polym. Eng. Sci. 49 (2009) 1253–1272. doi:10.1002/pen.21328.
- [45] M. Jacob, S. Thomas, K.T. Varughese, Mechanical properties of sisal / oil palm hybrid fiber reinforced natural rubber composites, 64 (2004) 955–965. doi:10.1016/S0266-3538(03)00261-6.
- [46] H.M. Akil, M.F. Omar, A.A.M. Mazuki, S. Safiee, Z.A.M. Ishak, A. Abu Bakar, Kenaf fiber reinforced composites: A review, Mater. Des. 32 (2011) 4107–4121. doi:10.1016/j.matdes.2011.04.008.
- [47] Z. Meng, W. Can-gang, L. Jian-qiao, X. Shu-cai, Z. Xiong, The energy absorption of bamboo under dynamic axial loading, Thin-Walled Struct. 95 (2015) 255–261. doi:10.1016/j.tws.2015.06.017.
- [48] S. Biswas, S. Shahinur, M. Hasan, Q. Ahsan, ScienceDirect Physical, Mechanical and Thermal Properties of Jute and Bamboo Fiber Reinforced Unidirectional Epoxy Composites, Procedia Eng. 105 (2015) 933–939. doi:10.1016/j.proeng.2015.05.118.
- [49] K.M.M. Rao, K.M. Rao, Extraction and tensile properties of natural fibers: Vakka, date and bamboo, Compos. Struct. 77 (2007) 288–295. doi:10.1016/j.compstruct.2005.07.023.

- [50] O. Faruk, A.K. Bledzki, H.P. Fink, M. Sain, Biocomposites reinforced with natural fibers: 2000-2010, Prog. Polym. Sci. 37 (2012) 1552–1596. doi:10.1016/j.progpolymsci.2012.04.003.
- [51] D. Liu, J. Song, D.P. Anderson, P.R. Chang, Y. Hua, Bamboo fiber and its reinforced composites: Structure and properties, Cellulose. 19 (2012) 1449– 1480. doi:10.1007/s10570-012-9741-1.
- [52] M.R. Sanjay, G.R. Arpitha, B. Yogesha, Study on Mechanical Properties of Natural - Glass Fibre Reinforced Polymer Hybrid Composites: A Review, Mater. Today Proc. 2 (2015) 2959–2967. doi:10.1016/j.matpr.2015.07.264.
- [53] R. Malkapuram, V. Kumar, Yuvraj Singh Negi, Recent Development in Natural Fiber Reinforced Polypropylene Composites, J. Reinf. Plast. Compos. 28 (2008) 1169–1189. doi:10.1177/0731684407087759.
- [54] F.Z. Arrakhiz, M. Malha, R. Bouhfid, K. Benmoussa, A. Qaiss, Tensile, flexural and torsional properties of chemically treated alfa, coir and bagasse reinforced polypropylene, Compos. Part B Eng. 47 (2013) 35–41. doi:10.1016/j.compositesb.2012.10.046.
- [55] P. Wambua, J. Ivens, I. Verpoest, Natural fibres: Can they replace glass in fibre reinforced plastics, Compos. Sci. Technol. 63 (2003) 1259–1264. doi:10.1016/S0266-3538(03)00096-4.
- [56] Nur Asilah Binti Che Aziz, Mechanical Performance of Kenaf Fibre Reinforced, (2011) 1–14.
- [57] F.M. Al-Oqla, S.M. Sapuan, Natural fiber reinforced polymer composites in industrial applications: Feasibility of date palm fibers for sustainable automotive industry, J. Clean. Prod. 66 (2014) 347–354. doi:10.1016/j.jclepro.2013.10.050.
- [58] M.M. Davoodi, S.M. Sapuan, D. Ahmad, A. Ali, A. Khalina, M. Jonoobi, Mechanical properties of hybrid kenaf/glass reinforced epoxy composite for passenger car bumper beam, Mater. Des. 31 (2010) 4927–4932. doi:10.1016/j.matdes.2010.05.021.
- [59] N. Saba, M.T. Paridah, M. Jawaid, Mechanical properties of kenaf fibre reinforced polymer composite: A review, Constr. Build. Mater. 76 (2015) 87– 96. doi:10.1016/j.conbuildmat.2014.11.043.
- [60] L. Yan, N. Chouw, Crashworthiness characteristics of flax fibre reinforced epoxy tubesfor energy absorption application, Mater. Des. 51 (2013) 629–640. doi:10.1016/j.matdes.2013.04.014.
- [61] E. Mahdi, A.S.M. Hamouda, A.C. Sen, Quasi-static crushing behaviour of hybrid and non-hybrid natural fibre composite solid cones, Compos. Struct. 66 (2004) 647–663. doi:10.1016/j.compstruct.2004.06.001.
- [62] M. Ramesh, K. Palanikumar, K.H. Reddy, Mechanical property evaluation of

sisal-jute-glass fiber reinforced polyester composites, Compos. Part B Eng. 48 (2013) 1–9. doi:10.1016/j.compositesb.2012.12.004.

- [63] I. Merta, E.K. Tschegg, Fracture energy of natural fibre reinforced concrete, Constr. Build. Mater. 40 (2013) 991–997. doi:10.1016/j.conbuildmat.2012.11.060.
- [64] S. Palanivelu, W. Van Paepegem, J. Degrieck, J. Van Ackeren, D. Kakogiannis, D. Van Hemelrijck, et al., Experimental study on the axial crushing behaviour of pultrudedcomposite tubes, Polym. Test. 29 (2010) 224– 234. doi:10.1016/j.polymertesting.2009.11.005.
- [65] A.M. Elgalai, E. Mahdi, A.M.S. Hamouda, B.S. Sahari, Crushing response of composite corrugated tubes to quasi-static axial[1] Elgalai AM, Mahdi E, Hamouda AMS, Sahari BS. Crushing response of composite corrugated tubes to quasi-static axial loading. Compos Struct 2004:66:665-71. doi:10.1016/j.compstruct.200, Struct. 66 665-671. Compos. (2004)doi:10.1016/j.compstruct.2004.06.002.
- [66] L. Yan, N. Chouw, K. Jayaraman, Effect of triggering and polyurethane foamfiller on axial crushing of natural flax/epoxy composite tubes, Mater. Des. 56 (2014) 528–541. doi:10.1016/j.matdes.2013.11.068.
- [67] R.A. Eshkoor, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Comparative research on the crashworthiness characteristics of woven natural silk/epoxy composite tubes, Mater. Des. 47 (2013) 248–257. doi:10.1016/j.matdes.2012.11.030.
- [68] R.A. Eshkoor, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Effect of trigger configuration on the crashworthiness characteristics of natural silk epoxy composite tubes, Compos. Part B Eng. 55 (2013) 5–10. doi:10.1016/j.compositesb.2013.05.022.
- [69] S.A. Oshkovr, R.A. Eshkoor, S.T. Taher, A.K. Ariffin, C.H. Azhari, Crashworthiness characteristics investigation of silk/epoxy composite square tubes, Compos. Struct. 94 (2012) 2337–2342. doi:10.1016/j.compstruct.2012.03.031.
- [70] L. Yan, N. Chouw, K. Jayaraman, Lateral crushing of empty and polyurethanefoam filled natural flax fabric reinforced epoxy composite tubes, Compos. Part B Eng. 63 (2014) 15–26. doi:10.1016/j.compositesb.2014.03.013.
- [71] S.A. Oshkovr, R.A. Eshkoor, S.T. Taher, A.K. Ariffin, C.H. Azhari, Crashworthiness characteristics investigation of silk/epoxy composite square tubes, Compos. Struct. 94 (2012) 2337–2342. doi:10.1016/j.compstruct.2012.03.031.
- [72] S. Palanivelu, W. Van Paepegem, J. Degrieck, J. Vantomme, D. Kakogiannis, J. Van Ackeren, et al., Crushing and energy absorption performance of different

geometrical shapes of small-scale glass/polyester composite tubes under quasistatic loading conditions, Compos. Struct. 93 (2011) 992–1007. doi:10.1016/j.compstruct.2010.06.021.

- [73] M. Assarar, D. Scida, A. El Mahi, C. Poilâne, R. Ayad, Influence of water ageing on mechanical properties and damage events of two reinforced composite materials: Flaxfibres and glass-fibres, Mater. Des. 32 (2011) 788– 795. doi:10.1016/j.matdes.2010.07.024.
- [74] G. Dorez, A. Taguet, L. Ferry, J.M. Lopez-Cuesta, Thermal and fire behavior of natural fibers/PBS biocomposites, Polym. Degrad. Stab. 98 (2013) 87–95. doi:10.1016/j.polymdegradstab.2012.10.026.
- [75] F.H. Abdalla, S.A. Mutasher, Y.A. Khalid, S.M. Sapuan, A.M.S. Hamouda, B.B. Sahari, et al., Design and fabrication of low cost filament winding machine, Mater. Des. 28 (2007) 234–239. doi:10.1016/j.matdes.2005.06.015.
- [76] C.O.F. Corrugated, C. Shells, D.O.F. Philosophy, Ali mohamed ali elgalai, (2006).
- [77] E. Mahdi, T.A. Sebaey, An experimental investigation into crushing behavior of radially stiffened GFRP composite tubes, Thin-Walled Struct. 76 (2014) 8–13. doi:10.1016/j.tws.2013.10.018.
- [78] S. Misri, S.M. Sapuan, Z. Leman, M.R. Ishak, Torsional behaviour of filament wound kenaf yarn fibre reinforced unsaturated polyester composite hollow shafts, Mater. Des. 65 (2015) 953–960. doi:10.1016/j.matdes.2014.09.073.
- [79] J. Meredith, R. Ebsworth, S.R. Coles, B.M. Wood, K. Kirwan, Natural fibre composite energy absorption structures, Compos. Sci. Technol. 72 (2012) 211– 217. doi:10.1016/j.compscitech.2011.11.004.
- [80] N.A. Warrior, T.A. Turner, E. Cooper, M. Ribeaux, Effects of boundary conditions on the energy absorption of thin-walled polymer composite tubes under axial crushing, Thin-Walled Struct. 46 (2008) 905–913. doi:10.1016/j.tws.2008.01.023.
- [81] S. Jeyanthi, J. Janci Rani, Improving mechanical properties by KENAF natural long fiber reinforced composite for automotive structures, J. Appl. Sci. Eng. 15 (2012) 275–280.
- [82] R. Yahaya, S.M. Sapuan, M. Jawaid, Z. Leman, E.S. Zainudin, Effect of layeringsequence and chemical treatment on the mechanical properties of woven kenaf-aramid hybrid laminated composites, Mater. Des. 67 (2015) 173– 179. doi:10.1016/j.matdes.2014.11.024.
- [83] Y. Ma, T. Sugahara, Y. Yang, H. Hamada, A study on the energy absorption properties of carbon/aramid fiber filament winding composite tube, Compos.

Struct. 123 (2015) 301-311. doi:10.1016/j.compstruct.2014.12.067.

- [84] A. Othman, S. Abdullah, A.K. Ariffin, N.A.N. Mohamed, Investigating the quasi-static axial crushing behavior of polymeric foam-filled composite pultrusion square tubes, Mater. Des. 63 (2014) 446–459. doi:10.1016/j.matdes.2014.06.020.
- [85] A.G. Mamalis, D.E. Manolakos, M.B. Ioannidis, D.G. Chronopoulos, P.K. Kostazos, On the crashworthiness of composite rectangular thin-walled tubes internally reinforced with aluminium or polymeric foams: Experimental and numerical simulation, Compos. Struct. 89 (2009) 416–423. doi:10.1016/j.compstruct.2008.09.008.
- [86] N.K. Gupta, H. Abbas, Lateral collapse of composite cylindrical tubes between flat platens, Int. J. Impact Eng. 24 (2000) 329–346. doi:10.1016/S0734-743X(99)00173-6.
- [87] J. Xu, Y. Ma, Q. Zhang, T. Sugahara, Y. Yang, H. Hamada, Crashworthiness of carbon fiber hybrid composite tubes molded by filament winding, Compos. Struct. 139 (2016) 130–140. doi:10.1016/j.compstruct.2015.11.053.
- [88] S. Ochelski, P. Gotowicki, Experimental assessment of energy absorption capability of carbon-epoxy and glass-epoxy composites, Compos. Struct. 87 (2009) 215–224. doi:10.1016/j.compstruct.2008.01.010.
- [89] E. Mahdi, A.M.S. Hamouda, B.B. Sahari, Y.A. Khalid, Effect of hybridisation on crushing behaviour of carbon / glass fibre / epoxy circular – cylindrical shells, 132 (2003) 49–57.
- [90] S. Ataollahi, S.T. Taher, R.A. Eshkoor, A.K. Ariffin, C.H. Azhari, Energy absorption and failure response of silk/epoxy composite square tubes: Experimental, Compos. Part B Eng. 43 (2012) 542–548. doi:10.1016/j.compositesb.2011.08.019.
- [91] S. Sam-Brew, G.D. Smith, Flax and Hemp fiber-reinforced particleboard, Ind. Crops Prod. 77 (2015) 940–948. doi:10.1016/j.indcrop.2015.09.079.
- [92] K.L. Pickering, M.G. Aruan Efendy, Preparation and mechanical properties of novel bio-composite made of dynamically sheet formed discontinuous harakeke and hemp fibre mat reinforced PLA composites for structural applications, Ind. Crops Prod. 84 (2016) 139–150. doi:10.1016/j.indcrop.2016.02.005.
- [93] A.A.S. Abosbaia, E. Mahdi, A.M.S. Hamouda, B.B. Sahari, Quasi-static axial crushing of segmented and non-segmented composite tubes, Compos. Struct. 60 (2003) 327–343. doi:10.1016/S0263-8223(02)00341-0.
- [94] J.S. Kim, H.J. Yoon, K.B. Shin, A study on crushing behaviors of composite circular tubes with different reinforcing fibers, Int. J. Impact Eng. 38 (2011) 198– 207. doi:10.1016/j.ijimpeng.2010.11.007.

- [95] A.G. Mamalis, D.E. Manolakos, M.B. Ioannidis, D.P. Papapostolou, Crashworthy characteristics of axially statically compressed thin-walled square CFRP composite tubes: Experimental, Compos. Struct. (2004). doi:10.1016/S0263-8223(03)00183-1.
- [96] E.F. Abdewi, S. Sulaiman, A.M.S. Hamouda, E. Mahdi, Effect of geometry on the crushing behaviour of laminated corrugated composite tubes, J. Mater. Process. Technol. 172 (2006) 394–399. doi:10.1016/j.jmatprotec.2005.07.017.
- [97] E.F. Abdewi, S. Sulaiman, A.M.S. Hamouda, E. Mahdi, Quasi-static axial and lateral crushing of radial corrugated composite tubes, 46 (2008) 320–332. doi:10.1016/j.tws.2007.07.018.



4.10 Conclusion

In this study, the effects of different fibre contents on crashing modes and the energy absorbed by nonwoven kenaf (mat) composite hexagonal tubes were investigated under axial compression loads. It was shown that the resin outflow from a composite usually leads to an undesirable void content during the fabrication process, an irregular arrangement of fibres and uneven resin distribution. Various fibre contents, including 25%, 30%, 35% and 40% by mass, were axially compression tested using an the Instron 3382 system at a fixed speed of 15 m/min. Based on the test data, the following conclusions are possible :

- 1. The total amount of energy absorbed decreases as the fibre content increases. This is also the case for the stroke efficiency.
- 2. Axial crashing results in decreasing stroke efficiency, crash efficiency, tensile strain and mean crashing load as the fibre content increases.
- 3. A few distinct failure modes were identified during the experimental tests of the hexagonal composite tubes:

• A progressive failure mode in which the failure starts at the top of the tube.

• A transverse crack failure mode is associated with the buckling failure mode.

• After the crash, the top or bottom end of the hexagonal tubes starts to break and is fragmented into small pieces.

4. Kenaf fibre content of 25% to 30% results in optimum values of the crashworthiness parameters.

- T. Nishino, K. Hirao, M. Kotera, K. Nakamae, H. Inagaki, Kenaf reinforced biodegradable composite, Compos. Sci. Technol. 63 (2003) 1281–1286. doi:10.1016/S0266-3538(03)00099-X.
- [2] S. Shibata, Y. Cao, I. Fukumoto, Lightweight laminate composites made from kenaf and polypropylene fibres, Polym. Test. 25 (2006) 142–148. doi:10.1016/j.polymertesting.2005.11.007.
- [3] a. K. Mohanty, M. Misra, L.T. Drzal, Surface modifications of natural fibres and performance of the resulting biocomposites: An overview, Compos. Interfaces. 8 (2001) 313–343. doi:10.1163/156855401753255422.
- [4] B.T. Wcawski, M. Fan, D. Hui, Compressive behaviour of natural fibre composite, Compos. Part B Eng. 67 (2014) 183–191. doi:10.1016/j.compositesb.2014.07.014.

- [5] M. Zampaloni, F. Pourboghrat, S.A. Yankovich, B.N. Rodgers, J. Moore, L.T. Drzal, et al., Kenaf natural fibre reinforced polypropylene composites: A discussion on manufacturing problems and solutions, Compos. Part A Appl. Sci. Manuf. 38 (2007) 1569–1580. doi:10.1016/j.compositesa.2007.01.001.
- [6] A.K. Mohanty, L.T. Drzal, M. Misra, Novel hybrid coupling agent as an adhesion promoter in natural fibre reinforced powder polypropylene composites, J. Mater. Sci. Lett. 21 (2002) 1885–1888. doi:10.1023/A:1021577632600.
- M. Alkateb, E. Mahdi, On the energy absorption capability of axially crushed composite elliptical cones, Compos. Struct. 66 (2004) 495–501. doi:10.1016/j.compstruct.2004.04.078.
- [8] S.T.W. Lau, M.R. Said, M.Y. Yaakob, On the effect of geometrical designs and failure modes in composite axial crushing: A literature review, Compos. Struct. 94 (2012) 803–812. doi:10.1016/j.compstruct.2011.09.013.
- [9] S. Palanivelu, W. Van Paepegem, J. Degrieck, J. Van Ackeren, D. Kakogiannis, D. Van Hemelrijck, et al., Experimental study on the axial crushing behaviour of pultruded composite tubes, Polym. Test. 29 (2010) 224–234. doi:10.1016/j.polymertesting.2009.11.005.
- [10] A.A.S. Abosbaia, E. Mahdi, A.M.S. Hamouda, B.B. Sahari, Quasi-static axial crushing of segmented and non-segmented composite tubes, Compos. Struct. 60 (2003) 327–343. doi:10.1016/S0263-8223(02)00341-0.
- [11] T. Hou, G.M.K. Pearce, B.G. Prusty, D.W. Kelly, R.S. Thomson, Pressurised composite tubes as variable load energy absorbers, Compos. Struct. 120 (2015) 346–357. doi:10.1016/j.compstruct.2014.09.060.
- [12] Q. Liu, H. Xing, Y. Ju, Z. Ou, Q. Li, Quasi-static axial crushing and transverse bending of double hat shaped CFRP tubes, Compos. Struct. 117 (2014) 1–11. doi:10.1016/j.compstruct.2014.06.024.
- [13] J.S. Kim, H.J. Yoon, K.B. Shin, A study on crushing behaviors of composite circular tubes with different reinforcing fibres, Int. J. Impact Eng. 38 (2011) 198–207. doi:10.1016/j.ijimpeng.2010.11.007.
- [14] S. Ataollahi, S.T. Taher, R.A. Eshkoor, A.K. Ariffin, C.H. Azhari, Energy absorption and failure response of silk/epoxy composite square tubes: Experimental, Compos. Part B Eng. 43 (2012) 542–548. doi:10.1016/j.compositesb.2011.08.019.

- [15] A. Othman, S. Abdullah, A.K. Ariffin, N.A.N. Mohamed, Investigating the quasi-static axial crushing behavior of polymeric foam-filled composite pultrusion square tubes, Mater. Des. 63 (2014) 446–459. doi:10.1016/j.matdes.2014.06.020.
- [16] R.A. Eshkoor, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Comparative research on the crashworthiness characteristics of woven natural silk/epoxy composite tubes, Mater. Des. 47 (2013) 248–257. doi:10.1016/j.matdes.2012.11.030.
- [17] R.A. Eshkoor, A.U. Ude, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, et al., Failure mechanism of woven natural silk/epoxy rectangular composite tubes under axial quasi-static crushing test using trigger mechanism, Int. J. Impact Eng. 64 (2014) 53–61. doi:10.1016/j.ijimpeng.2013.09.004.
- [18] A.M. Elgalai, E. Mahdi, A.M.S. Hamouda, B.S. Sahari, Crushing response of composite corrugated tubes to quasi-static axial loading, Compos. Struct. 66 (2004) 665–671. doi:10.1016/j.compstruct.2004.06.002.
- [19] E. Mahdi, T.A. Sebaey, Crushing behavior of hybrid hexagonal/octagonal cellular composite system: Aramid/carbon hybrid composite, Mater. Des. 63 (2014) 6–13. doi:10.1016/j.matdes.2014.06.001.
- [20] E. Mahdi, A.M.S. Hamouda, Energy absorption capability of composite hexagonal ring systems, Mater. Des. 34 (2012) 201–210. doi:10.1016/j.matdes.2011.07.070.
- [21] E. Mahdi, A.M.S. Hamouda, B.B. Sahari, Y.A. Khalid, Experimental quasistatic axial crushing of cone – tube – cone composite system, 34 (2003) 285– 302.
- [22] E.F. Abdewi, S. Sulaiman, A.M.S. Hamouda, E. Mahdi, Effect of geometry on the crushing behaviour of laminated corrugated composite tubes, J. Mater. Process. Technol. 172 (2006) 394–399. doi:10.1016/j.jmatprotec.2005.07.017.
- [23] Y.A. El-Shekeil, S.M. Sapuan, M.W. Algrafi, Effect of fibre loading on mechanical and morphological properties of cocoa pod husk fibres reinforced thermoplastic polyurethane composites, Mater. Des. 64 (2014) 330–333. doi:10.1016/j.matdes.2014.07.034.
- [24] M. Jawaid, H.P.S. Abdul Khalil, A. Hassan, R. Dungani, A. Hadiyane, Effect of jute fibre loading on the mechanical and thermal properties of oil palm epoxy composites, Compos. Mater. 47 (2012) 1633–1641. doi:10.1016/j.compositesb.2012.04.068.

- [25] M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, Effect of geometry on crashworthiness parameters of natural kenaf fibre reinforced composite hexagonal tubes, Mater. Des. 60 (2014) 85–93.
- [26] F.M. Salleh, A. Hassan, R. Yahya, A.D. Azzahari, Effects of extrusion temperature on the rheological, dynamic mechanical and tensile properties of kenaf fibre/HDPE composites, Compos. Part B Eng. 58 (2014) 259–266. doi:10.1016/j.compositesb.2013.10.068.
- [27] R. Mahjoub, J.M. Yatim, A.R. Mohd Sam, S.H. Hashemi, Tensile properties of kenaf fibre due to various conditions of chemical fibre surface modifications, Constr. Build. Mater. 55 (2014) 103–113. doi:10.1016/j.conbuildmat.2014.01.036.
- [28] Y.A. El-Shekeil, S.M. Sapuan, M. Jawaid, O.M. Al-Shuja'a, Influence of fibre content on mechanical, morphological and thermal properties of kenaf fibres reinforced poly(vinyl chloride)/thermoplastic polyurethane poly-blend composites, Mater. Des. 58 (2014) 130–135. doi:10.1016/j.matdes.2014.01.047.
- [29] D. Rouison, M. Sain, M. Couturier, Resin transfer molding of natural fibre reinforced composites: Cure simulation, Compos. Sci. Technol. 64 (2004) 629– 644. doi:10.1016/j.compscitech.2003.06.001.
- [30] S. Rassmann, R. Paskaramoorthy, R.G. Reid, Effect of resin system on the mechanical properties and water absorption of kenaf fibre reinforced laminates, Mater. Des. 32 (2011) 1399–1406. doi:10.1016/j.matdes.2010.09.006.
- [31] N. Saba, M.T. Paridah, M. Jawaid, Mechanical properties of kenaf fibre reinforced polymer composite: A review, Constr. Build. Mater. 76 (2015) 87– 96. doi:10.1016/j.conbuildmat.2014.11.043.
- [32] A.K. Bledzki, P. Franciszczak, Z. Osman, M. Elbadawi, Polypropylene biocomposites reinforced with softwood, abaca, jute, and kenaf fibres, Ind. Crops Prod. 70 (2015) 91–99. doi:10.1016/j.indcrop.2015.03.013.
- [33] R. Mahjoub, J.M. Yatim, A.R. Mohd Sam, M. Raftari, Characteristics of continuous unidirectional kenaf fibre reinforced epoxy composites, Mater. Des. 64 (2014) 640–649. doi:10.1016/j.matdes.2014.08.010.
- [34] S.M. Dauda, D. Ahmad, A. Khalina, O. Jamarei, Physical and Mechanical Properties of Kenaf Stems at Varying Moisture Contents, Agric. Agric. Sci. Procedia. 2 (2014) 370–374. doi:10.1016/j.aaspro.2014.11.051.

- [35] L. Liu, B.M. Zhang, D.F. Wang, Z.J. Wu, Effects of cure cycles on void content and mechanical properties of composite laminates, Compos. Struct. 73 (2006) 303–309. doi:10.1016/j.compstruct.2005.02.001.
- [36] M. Jawaid, H.P.S.A. Khalil, A.A. Bakar, P.N. Khanam, Chemical resistance, void content and tensile properties of oil palm/jute fibre reinforced polymer hybrid composites, Mater. Des. 32 (2011) 1014–1019. doi:10.1016/j.matdes.2010.07.033.



- P.H. Thornton, R.A. Jeryan, Crash energy management in composite automotive structures, Int. J. Impact Eng. 7 (1988) 167–180. doi:10.1016/0734-743X(88)90024-3.
- [2] M.A. McCarthy, J.F.M. Wiggenraad, Numerical investigation of a crash test of a composite helicopter subfloor structure, Compos. Struct. 51 (2001) 345–359. doi:10.1016/S0263-8223(00)00150-1.
- [3] G. Pitarresi, J.J. Carruthers, A.M. Robinson, G. Torre, J.M. Kenny, S. Ingleton, et al., A comparative evaluation of crashworthy composite sandwich structures, Compos. Struct. 78 (2007) 34–44. doi:10.1016/j.compstruct.2005.08.008.
- S. Palanivelu, W. Van Paepegem, J. Degrieck, J. Van Ackeren, D. Kakogiannis,
 D. Van Hemelrijck, et al., Experimental study on the axial crushing behaviour of pultruded compositetubes, Polym. Test. 29(2010)224–234. doi:10.1016/j.polymertesting.2009.11.005.
- [5] E.S. Mahdi, H. El Kadi, Crushing behavior of laterally compressed composite elliptical tubes: Experiments and predictions using artificial neural networks, Compos. Struct. 83 (2008) 399–412. doi:10.1016/j.compstruct.2007.05.009.
- [6] A.S. Abosbaia, E. Mahdi, A.M.S. Hamouda, B.B. Sahari, A.S. Mokhtar, Energy absorption capability of laterally loaded segmented composite tubes, Compos. Struct. 70 (2005) 356–373. doi:10.1016/j.compstruct.2004.08.039.
- [7] A.G. Mamalis, D.E. Manolakos, M.B. Ioannidis, D.P. Papapostolou, Crashworthy characteristics of axially statically compressed thin-walled square CFRP composite tubes: Experimental, Compos. Struct. 63 (2004) 347–360. doi:10.1016/S0263-8223(03)00183-1.
- [8] M.M. Davoodi, S.M. Sapuan, D. Ahmad, A. Ali, A. Khalina, M. Jonoobi, Mechanical properties of hybrid kenaf/glass reinforced epoxy composite for passenger car bumper beam, Mater. Des. 31 (2010) 4927–4932. doi:10.1016/j.matdes.2010.05.021.
- [9] S.M. Sapuan, a. Leenie, M. Harimi, Y.K. Beng, Mechanical properties of woven banana fibre reinforced epoxy composites, Mater. Des. 27 (2006) 689– 693. doi:10.1016/j.matdes.2004.12.016.
- [10] T. Nishino, K. Hirao, M. Kotera, K. Nakamae, H. Inagaki, Kenaf reinforced biodegradable composite, Compos. Sci. Technol. 63 (2003) 1281–1286. doi:10.1016/S0266-3538(03)00099-X.

- [11] Y.A. El-Shekeil, S.M. Sapuan, M. Jawaid, O.M. Al-Shuja'a, Influence of fiber content on mechanical, morphological and thermal properties of kenaf fibers reinforced poly(vinyl chloride)/thermoplastic polyurethane poly-blend composites, Mater. Des. 58 (2014) 130–135. doi:10.1016/j.matdes.2014.01.047.
- [12] L. Yan, N. Chouw, Crashworthiness characteristics of flax fibre reinforced epoxy tubes for energy absorption application, Mater. Des. 51 (2013) 629–640. doi:10.1016/j.matdes.2013.04.014.
- [13] S.A. Oshkovr, R.A. Eshkoor, S.T. Taher, A.K. Ariffin, C.H. Azhari, Crashworthiness characteristics investigation of silk/epoxy composite square tubes, Compos. Struct. 94 (2012) 2337–2342. doi:10.1016/j.compstruct.2012.03.031.



Acknowledgement

Financial support from Universiti Putra Malaysia through Research, University Grant Scheme vote no. 9301200 is highly appreciated.

- [1] A.E. Stockwell, Simulation of an impact test of the all-composite lear fan aircraft, (2002) 10.
- [2] S.T. Taher, E. Mahdi, A.S. Mokhtar, D.L. Magid, F.R. Ahmadun, P.R. Arora, A new composite energy absorbing system for aircraft and helicopter, Compos. Struct. 75 (2006) 14–23. doi:10.1016/j.compstruct.2006.04.083.
- S. Palanivelu, W. Van Paepegem, J. Degrieck, J. Van Ackeren, D. Kakogiannis,
 D. Van Hemelrijck, et al., Experimental study on the axial crushing behaviour of pultruded composite tubes, Polym. Test. 29 (2010) 224–234. doi:10.1016/j.polymertesting.2009.11.005.
- [4] R.A. Eshkoor, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Effect of trigger configuration on the crashworthiness characteristics of natural silk epoxy composite tubes, Compos. Part B Eng. 55 (2013) 5–10. doi:10.1016/j.compositesb.2013.05.022.
- [5] S. Ochelski, P. Gotowicki, Experimental assessment of energy absorption capability of carbon-epoxy and glass-epoxy composites, Compos. Struct. 87 (2009) 215–224. doi:10.1016/j.compstruct.2008.01.010.
- [6] S. Solaimurugan, R. Velmurugan, Influence of fibre orientation and stacking sequence on petalling of glass/polyester composite cylindrical shells under axial compression, Int. J. Solids Struct. 44 (2007) 6999–7020. doi:10.1016/j.ijsolstr.2007.03.025.
- [7] G. Li, D. Maricherla, K. Singh, S.S. Pang, M. John, Effect of fiber orientation on the structural behavior of FRP wrapped concrete cylinders, Compos. Struct. 74 (2006) 475–483. doi:10.1016/j.compstruct.2005.05.001.
- [8] E. Mahdi, A.M.S. Hamouda, B.B. Sahari, Y.A. Khalid, Effect of hybridisation on crushing behaviour of carbon / glass fibre / epoxy circular – cylindrical shells, 132 (2003) 49–57.
- [9] N.A. Warrior, T.A. Turner, E. Cooper, M. Ribeaux, Effects of boundary conditions on the energy absorption of thin-walled polymer composite tubes under axial crushing, Thin-Walled Struct. 46 (2008) 905–913. doi:10.1016/j.tws.2008.01.023.

- [10] S. Eksi, A.O. Kapti, K. Genel, Buckling behavior of fiber reinforced plasticmetal hybrid-composite beam, Mater. Des. 49 (2013) 130–138. doi:10.1016/j.matdes.2013.02.029.
- [11] A.M. Elgalai, E. Mahdi, A.M.S. Hamouda, B.S. Sahari, Crushing response of composite corrugated tubes to quasi-static axial loading, Compos. Struct. 66 (2004) 665–671. doi:10.1016/j.compstruct.2004.06.002.
- [12] M. Alkateb, E. Mahdi, On the energy absorption capability of axially crushed composite elliptical cones, Compos. Struct. 66 (2004) 495–501. doi:10.1016/j.compstruct.2004.04.078.
- [13] S.M. Sapuan, D. Bachtiar, Mechanical Properties of Sugar Palm Fibre Reinforced High Impact Polystyrene Composites, Procedia Chem. 4 (2012) 101–106. doi:10.1016/j.proche.2012.06.015.
- [14] Y.A. El-Shekeil, S.M. Sapuan, K. Abdan, E.S. Zainudin, Influence of fiber content on the mechanical and thermal properties of Kenaf fiber reinforced thermoplastic polyurethane composites, Mater. Des. 40 (2012) 299–303. doi:10.1016/j.matdes.2012.04.003.
- [15] K. Oksman, M. Skrifvars, J.F. Selin, Natural fibres as reinforcement in polylactic acid (PLA) composites, Compos. Sci. Technol. 63 (2003) 1317– 1324. doi:10.1016/S0266-3538(03)00103-9.
- [16] T. Arai, G. Freddi, R. Innocenti, M. Tsukada, Biodegradation of Bombyx mori Silk Fibroin Fibers and Films, (2003) 16–19.
- [17] R.A. Eshkoor, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Comparative research on the crashworthiness characteristics of woven natural silk/epoxy composite tubes, Mater. Des. 47 (2013) 248–257. doi:10.1016/j.matdes.2012.11.030.
- [18] S. Ataollahi, S.T. Taher, R.A. Eshkoor, A.K. Ariffin, C.H. Azhari, Energy absorption and failure response of silk/epoxy composite square tubes: Experimental, Compos. Part B Eng. 43 (2012) 542–548. doi:10.1016/j.compositesb.2011.08.019.
- [19] E. Mahdi, A.S.M. Hamouda, A.C. Sen, Quasi-static crushing behaviour of hybrid and non-hybrid natural fibre composite solid cones, Compos. Struct. 66 (2004) 647–663. doi:10.1016/j.compstruct.2004.06.001.
- [20] F.M. Salleh, A. Hassan, R. Yahya, A.D. Azzahari, Effects of extrusion temperature on the rheological, dynamic mechanical and tensile properties of kenaf fiber/HDPE composites, Compos. Part B Eng. 58 (2014) 259–266. doi:10.1016/j.compositesb.2013.10.068.

- [21] E. Mahdi, T.A. Sebaey, An experimental investigation into crushing behavior of radially stiffened GFRP composite tubes, Thin-Walled Struct. 76 (2014) 8– 13. doi:10.1016/j.tws.2013.10.018.
- [22] E.F. Abdewi, S. Sulaiman, A.M.S. Hamouda, E. Mahdi, Quasi-static axial and lateral crushing of radial corrugated composite tubes, 46 (2008) 320–332. doi:10.1016/j.tws.2007.07.018.
- [23] L. Yan, N. Chouw, Crashworthiness characteristics of flax fibre reinforced epoxy tubes for energy absorption application, Mater. Des. 51 (2013) 629–640. doi:10.1016/j.matdes.2013.04.014.
- [24] S.A. Oshkovr, R.A. Eshkoor, S.T. Taher, A.K. Ariffin, C.H. Azhari, Crashworthiness characteristics investigation of silk/epoxy composite square tubes, Compos. Struct. 94 (2012) 2337–2342. doi:10.1016/j.compstruct.2012.03.031.
- [25] L. Yan, N. Chouw, K. Jayaraman, Effect of triggering and polyurethane foamfiller on axial crushing of natural flax/epoxy composite tubes, Mater. Des. 56 (2014) 528–541. doi:10.1016/j.matdes.2013.11.068.

3. Specimens with non-supported tubes exhibited the lower peak and average crushing loads.

- L. Yan, N. Chouw, Crashworthiness characteristics of flax fibre reinforced epoxy tubes for energy absorption application, Mater. Des. 51 (2013) 629–640. doi:10.1016/j.matdes.2013.04.014.
- [2] Y.A. El-Shekeil, S.M. Sapuan, M.W. Algrafi, Effect of fiber loading on mechanical and morphological properties of cocoa pod husk fibers reinforced thermoplastic polyurethane composites, Mater. Des. 64 (2014) 330–333. doi:10.1016/j.matdes.2014.07.034.
- [3] V.S. Srinivasan, S. Rajendra Boopathy, D. Sangeetha, B. Vijaya Ramnath, Evaluation of Mechanical and Thermal Properties of Banana-Flax based Natural Fibre composite, Mater. Des. 60 (2014) 620–627. doi:10.1016/j.matdes.2014.03.014.
- [4] V.P. Arthanarieswaran, A. Kumaravel, M. Kathirselvam, Evaluation of mechanical properties of banana and sisal fiber reinforced epoxy composites: Influence of glass fiber hybridization, Mater. Des. 64 (2014) 194–202. doi:10.1016/j.matdes.2014.07.058.
- [5] S.M. Sapuan, a. Leenie, M. Harimi, Y.K. Beng, Mechanical properties of woven banana fibre reinforced epoxy composites, Mater. Des. 27 (2006) 689–693. doi:10.1016/j.matdes.2004.12.016.
- [6] S.A. Oshkovr, R.A. Eshkoor, S.T. Taher, A.K. Ariffin, C.H. Azhari, Crashworthiness characteristics investigation of silk/epoxy composite square tubes, Compos. Struct. 94 (2012) 2337–2342. doi:10.1016/j.compstruct.2012.03.031.
- [7] R.A. Eshkoor, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Comparative research on the crashworthiness characteristics of woven natural silk/epoxy composite tubes, Mater. Des. 47 (2013) 248–257. doi:10.1016/j.matdes.2012.11.030.
- [8] L. Yan, N. Chouw, K. Jayaraman, Lateral crushing of empty and polyurethanefoam filled natural flax fabric reinforced epoxy composite tubes, Compos. Part B Eng. 63 (2014) 15–26. doi:10.1016/j.compositesb.2014.03.013.

- [9] L. Yan, N. Chouw, K. Jayaraman, Effect of triggering and polyurethane foamfiller on axial crushing of natural flax/epoxy composite tubes, Mater. Des. 56 (2014) 528–541. doi:10.1016/j.matdes.2013.11.068.
- [10] T. Sathishkumar, J. Naveen, S. Satheeshkumar, Hybrid fiber reinforced polymer composites - a review, J. Reinf. Plast. Compos. 33 (2014) 454–471. doi:10.1177/0731684413516393.
- [11] V. Fiore, T. Scalici, L. Calabrese, A. Valenza, E. Proverbio, Effect of external basalt layers on durability behaviour of flax reinforced composites, Compos. Part B Eng. 84 (2016) 258–265. doi:10.1016/j.compositesb.2015.08.087.
- [12] M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, Effect of geometry on crashworthiness parameters of natural kenaf fibre reinforced composite hexagonal tubes, Mater. Des. 60 (2014) 85–93.
- [13] R.A. Eshkoor, S.A. Oshkovr, A.B. Sulong, R. Zulkifli, A.K. Ariffin, C.H. Azhari, Effect of trigger configuration on the crashworthiness characteristics of natural silk epoxy composite tubes, Compos. Part B Eng. 55 (2013) 5–10. doi:10.1016/j.compositesb.2013.05.022.
 - [14] J. Meredith, R. Ebsworth, S.R. Coles, B.M. Wood, K. Kirwan, Natural fibre composite energy absorption structures, Compos. Sci. Technol. 72 (2012) 211– 217. doi:10.1016/j.compscitech.2011.11.004.
- [15] S. Ataollahi, S.T. Taher, R.A. Eshkoor, A.K. Ariffin, C.H. Azhari, Energy absorption and failure response of silk/epoxy composite square tubes: Experimental, Compos. Part B Eng. 43 (2012) 542–548. doi:10.1016/j.compositesb.2011.08.019.
- B.T. W??c??awski, M. Fan, D. Hui, Compressive behaviour of natural fibre composite, Compos. Part B Eng. 67 (2014) 183–191. doi:10.1016/j.compositesb.2014.07.014.
- [17] F.M. Salleh, A. Hassan, R. Yahya, A.D. Azzahari, Effects of extrusion temperature on the rheological, dynamic mechanical and tensile properties of kenaf fiber/HDPE composites, Compos. Part B Eng. 58 (2014) 259–266. doi:10.1016/j.compositesb.2013.10.068.
- [18] R. Mahjoub, J.M. Yatim, A.R. Mohd Sam, S.H. Hashemi, Tensile properties of kenaf fiber due to various conditions of chemical fiber surface modifications, Constr. Build. Mater. 55 (2014) 103–113. doi:10.1016/j.conbuildmat.2014.01.036.
- [19] Y.A. El-shekeil, S.M. Sapuan, M. Jawaid, O.M. Al-shuja, Influence of fiber content on mechanical, morphological and thermal properties of kenaf fibers reinforced poly (vinyl chloride)/ thermoplastic polyurethane poly-blend composites, J. Mater. 58 (2014) 130–135. doi:10.1016/j.matdes.2014.01.047.

- [20] D. Rouison, M. Sain, M. Couturier, Resin transfer molding of natural fiber reinforced composites: Cure simulation, Compos. Sci. Technol. 64 (2004) 629– 644. doi:10.1016/j.compscitech.2003.06.001.
- [21] S. Rassmann, R. Paskaramoorthy, R.G. Reid, Effect of resin system on the mechanical properties and water absorption of kenaf fibre reinforced laminates, Mater. Des. 32 (2011) 1399–1406. doi:10.1016/j.matdes.2010.09.006.
- [22] N. Saba, M.T. Paridah, M. Jawaid, Mechanical properties of kenaf fibre reinforced polymer composite: A review, Constr. Build. Mater. 76 (2015) 87– 96. doi:10.1016/j.conbuildmat.2014.11.043.
- [23] R. Mahjoub, J.M. Yatim, A.R. Mohd Sam, M. Raftari, Characteristics of continuous unidirectional kenaf fiber reinforced epoxy composites, Mater. Des. 64 (2014) 640–649. doi:10.1016/j.matdes.2014.08.010.
- [24] A.K. Bledzki, P. Franciszczak, Z. Osman, M. Elbadawi, Polypropylene biocomposites reinforced with softwood, abaca, jute, and kenaf fibers, Ind. Crops Prod. 70 (2015) 91–99. doi:10.1016/j.indcrop.2015.03.013.
- [25] S.M. Dauda, D. Ahmad, A. Khalina, O. Jamarei, Physical and Mechanical Properties of Kenaf Stems at Varying Moisture Contents, Agric. Agric. Sci. Procedia. 2 (2014) 370–374. doi:10.1016/j.aaspro.2014.11.051.
- [26] A.S. Abosbaia, E. Mahdi, A.M.S. Hamouda, B.B. Sahari, A.S. Mokhtar, Energy absorption capability of laterally loaded segmented composite tubes, Compos. Struct. 70 (2005) 356–373. doi:10.1016/j.compstruct.2004.08.039.
- [27] E. Mahdi, T.A. Sebaey, Crushing behavior of hybrid hexagonal/octagonal cellular composite system: Aramid/carbon hybrid composite, Mater. Des. 63 (2014) 6–13. doi:10.1016/j.matdes.2014.06.001.

8.6 Conclusion

This work is a sequel to a series of previous works which published in material & design journal 2014 [3]. In demand to investigate experimentally the effect of hexagonal angles on the failure modes and specific energy absorption capability of the hexagonal composite tubes. The variety of hexagonal tubes with different angles were subjected to quasi-static lateral compression test load upon the results gained, the main conclusion are listed as follows:

- 1. The hexagonal tubes for lateral compression load have exhibited a slight difference of SEA
- 2. The formation of the fracture longitudinal failure mode was observed for all causes.
- 3. Composite hexagonal tube with β 40° exhibited high energy absorption capability under in the lateral crushing.

- Paridah, M. T., Amel B. A., Syeed O. A. S., & Ahmed, Z. Retting process of some bast plant fibres and its effect on fibre quality *BioResourses*. Vol 6. (2011), p. 5260-5281.
- [2] Edeerozey, A. M. M., Akil, H. M., Azhar, A. B., & Ariffin, M. I. Z. Chemical modification of kenaf fibres. Materials Letters, vol 6, (2007). p2023–2025.
- [3] M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak . Effect of geometry on crashworthiness parameters of natural kenaf fibre reinforced composite hexagonal tubes . Mater Des, 60 (2014), p. 85–93
- [4] I.S. Aji, S.M. Sapuan, E.S. Zainudin, K. AbdanKenaf fibres as reinforcement for polymeric composites: a review Int J Mech Mater Eng., vol 4 (2009), p. 239–248
- [5] Y.A. El-Shekeil, S.M. Sapuan, K. Abdan, E.S. Zainudin. Influence of fiber content on the mechanical and thermal properties of Kenaf fiber reinforced thermoplastic polyurethane composites. Mater DesVol 40, (2012) P.299–303.
- [6] S.A. Oshkovr, R.A. Eshkoor, S.T. Taher, A.K. Ariffin, C.H. Azhari .Crashworthiness characteristics investigation of silk/epoxy composite square tubes Composite Structures,. Compos struct 2012; 94: 2337–2342

- [7] S. Ataollahi, S.T. Taher, R.A. Eshkoor, A.K. Ariffin, C.H. Azhari Energy absorption and failure response of silk/epoxy composite square tubes: Experimental COMPOS PART B-ENG 2012; 43: 524–548
- [8] Libo Yan, Nawawi Chouw, Krishnan Jayaraman^b Lateral crushing of empty and polyurethane-foam filled natural flax fabric reinforced epoxy composite tubes compos part b-eng 2012; 43: 524–548 Vol 63, (2014), Pa15–26



LIST OF PUBLICATIONS

As an outcome of this study several publication were published in peer reviewed journals and confereces/ Seminar as fllows

- M.F.M. Alkbir, S. M. Sapuan, Nuraini A.A. And M. R. Ishak Quasi-Static lateral crushing of Non-Woven Kenaf fibre reinforced composite hexagonal tubes, Advanced material research volume 1119 March 2015, Scopus
- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, Effect of geometry on crashworthiness parameters of natural kenaf fibre reinforced composite hexagonal tubes, Materials & Design, vol. 60, pp. 85-93, August 2014 (Impact factor = 3.171) (Q1).
- M.F.M. Alkbir, S. M. Sapuan, Nuraini A.A. And M. R. Ishak Quasi-Static lateral crushing of Non-Woven Kenaf fibre reinforced composite hexagonal tubes, Advanced material research volume 1119 March 2015, Scopus.
- M.F.M. Alkbir, S. M. Sapuan, Nuraini A.A. And M. R. Ishak Lateral Crushing Properties of Non-woven kenaf (mat) Reinforced Epoxy Composite Hexagonal tubes International Journal of Precision Engineering and Manufacturing, July 2016, Volume 17, Issue 7, pp 965–972 (Impact Factor 1.205) (Q 2)
- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak The Effect of Fiber Content on the Crashworthiness Parameters of Natural Kenaf Fiber-Reinforced Hexagonal Composite Tubes, Journal of Engineered Fibers and Fabrics. Volume 11, Issue 1 – 2016) (Impact Factor 0.986) (Q 2).
- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, Effect of Material Type on Crashworthiness Parameters And Failure Modes of natural kenaf fibre Reinforced Composite Hexagonal Tubes. Accepted for a book to be published in CRC press in USA.
- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak , Effect of crashworthiness parameters in natural fibre-reinforced polymer composite tubes: A literature review. Composite Structures, Volume 148, 15 July 2016, Pages 59–73 (Impact Factor = 3.700) (Q 1)
- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak On effects of Geometrical shapes in failure modes in natural– conventional fiber reinforced composite tubes (accepted) Current Analytical Chemistry journal ((Impact Factor =1.132)
- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, Comparative Investigation on the Failure Modes of Natural Kenaf/Epoxy Reinforced Composite Hexagonal Tube Key Engineering Materials (Volume 709), September 2016 Page 7-10 (Impact factor = 0.39 (Q4)

Conferences and Symposium Proceedings

- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, Effect of length in crashworthiness parameters of non-woven kenaf fibre/epoxy composite . Postgraduate Symposium on Composites Science and Technology 2014 and 4th Postgraduate Seminar on Natural Fibre Composites 2014, UPM Serdang
- Alkbir, M. F. M., A. M. S. Hamouda, E. Mahdi and S. M. Sapuan. Effect of Geometry on energy absorption Capability of Composite Hexagonal Tubes. Proceedings, 2nd International Symposium on Metrology & Physics Application and Energy Measurement (ISMPAEM-2004), 24-29 August. Serpong, Tangerang, Indonesia. 1-10
- Alkbir, M. F. M., A. M. S. Hamouda, E. Mahdi and S. M. Sapuan. Experimental quasistatic axial crushing of hexagonal composite tubes. Proceedings, 4th International Materials technology Conference and Exhibition (IMTCE-2004), 23-25 March. Hotel Styana, Kuala Lumpur.
- Munir Faraj M. A.lkbir, S. M. Sapuan, Nuraini Abdul Aziz, and Mohamad Ridzwan Ishak, Effect of Length in Crashworthiness Parameters of Non-Woven Kenaf Fibre/Epoxy Composite Hexagonal Tubes. The Postgraduate Symposium on Composite Science and Technology & 4th Postgraduate Seminar on Natural Fibre Composites, Palm Garden, Selangor, Malaysia. 2014.
- M.F.M. Alkbir, S.M. Sapuan, A.A. Nuraini, M.R. Ishak, M.S.Hamuoda and E.Mahdi Energy Absorption Capability of Hexagonal Composite Structure, 7th International Conference on 6. Postgraduate Education Institute of Graduate Studies, Universiti Teknologi MARA 40450 Shah Alam, Selangor, MALAYSIA.2016.



UNIVERSITI PUTRA MALAYSIA

STATUS CONFIRMATION FOR THESIS / PROJECT REPORT AND COPYRIGHT

ACADEMIC SESSION :

TITLE OF THESIS / PROJECT REPORT :

CRUSHING BEHAVIOR AND FAILURE MODES OF KENAF FIBRE-REINFORCED

NAME OF STUDENT: MUNIR FARAJ ALMABROUK ALKBIR

I acknowledge that the copyright and other intellectual property in the thesis/project report belonged to Universiti Putra Malaysia and I agree to allow this thesis/project report to be placed at the library under the following terms:

- 1. This thesis/project report is the property of Universiti Putra Malaysia.
- 2. The library of Universiti Putra Malaysia has the right to make copies for educational purposes only.
- 3. The library of Universiti Putra Malaysia is allowed to make copies of this thesis for academic exchange.

I declare that this thesis is classified as :

*Please tick (V)



RESTRICTED

CONFIDENTIAL



OPEN ACCESS

(Contain confidential information under Official Secret Act 1972).

(Contains restricted information as specified by the organization/institution where research was done).

I agree that my thesis/project report to be published as hard copy or online open access.

This thesis is submitted for :



Embargo from_	until			
	(date)		(date)	

Approved by:

(Signature of Student) New IC No/ Passport No.: (Signature of Chairman of Supervisory Committee) Name:

Date :

Date :

[Note : If the thesis is CONFIDENTIAL or RESTRICTED, please attach with the letter from the organization/institution with period and reasons for confidentially or restricted.]