



UNIVERSITI PUTRA MALAYSIA

***PHYSICAL AND SUPERCONDUCTING PROPERTIES OF CARBON
NANOFIBERS AND CARBON NANOTUBES $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$
SUPERCONDUCTOR***

NURUL AUNI BINTI KHALID

FS 2017 86



**PHYSICAL AND SUPERCONDUCTING PROPERTIES OF CARBON
NANOFIBERS AND CARBON NANOTUBES $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$
SUPERCONDUCTOR**

By

NURUL AUNI BINTI KHALID

**Thesis Submitted to the School of Graduate Studies, Universiti Putra
Malaysia, in Fulfilment of the Requirements for the Degree of Master of
Science**

November 2016

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Master of Science

PHYSICAL AND SUPERCONDUCTING PROPERTIES OF CARBON NANOFIBERS AND CARBON NANOTUBES $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ SUPERCONDUCTOR

By

NURUL AUNI BINTI KHALID

November 2016

Chairman: Mohd Mustafa bin Awang Kechik, PhD
Faculty: Science

A co-precipitation (COP) process for the synthesis of ultrafine $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ (Y-123) precursor has been developed with the addition of carbon nanofibers (CNFs) and carbon nanotubes (CNTs) nanoparticles with varying amounts of weight percentage (wt. %). Both nanoparticles acted as pinning center to improve the transport critical current density (J_c). The objective of this study was to investigate the flux pinning capability from carbon sources of CNFs and CNTs in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ superconductor. The effects of CNFs and CNTs addition on the superconducting properties (T_c and J_c), phase formation and structural properties, microstructure and surface morphology including the elemental distribution analysis were studied. A non-added Y-123 was used as a reference. The J_c for this sample is 11 A/cm^2 . Introduction of CNFs and CNTs improved J_c significantly. Furthermore, the volume fraction of Y-123 phase was 96.2 % and EDX showed excellent atomic ratio. CNFs addition significantly enhanced the J_c of Y-123 bulk. The $x = 0.4 \text{ wt. \%}$ sample showed the optimal amount as it exhibited the highest T_c and J_c of 88.0 K and 830 A/cm^2 , respectively. CNTs addition showed J_c value of 477 A/cm^2 for the $x = 0.2 \text{ wt. \%}$ sample which gave the optimal amount of CNTs addition. The largest grain size and high percentage of Y-123 phase was also observed in this sample together with good atomic % from EDX and high T_c value. The enhancement of J_c using CNFs and CNTs as artificial pinning centers from this work indicated that these two compounds are suitable for flux trapping. Both samples show increased values of T_c and J_c towards the optimum wt. % of addition and decreased after further addition of dopants.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Master Sains

**FIZIKAL DAN CIRI-CIRI KESUPERKONDUKSIAN BAGI NANOFIBER
KARBON DAN NANOTIUB KARBON SUPERKONDUKTOR $\text{YBa}_2\text{Cu}_3\text{O}_{7-5}$**

Oleh

NURUL AUNI BINTI KHALID

November 2016

Pengerusi: Mohd Mustafa bin Awang Kechik, PhD
Fakulti: Sains

Proses sepemendakan untuk mensintesis serbuk halus pelopor $\text{YBa}_2\text{Cu}_3\text{O}_{7-5}$ (Y-123) telah disediakan dengan tambahan nanofiber karbon (CNFs) dan nanotub karbon (CNTs) dengan jumlah peratusan berat (wt.%) yang berlainan. Kedua-dua nanozarah bertindak sebagai pengepin fluks untuk meningkatkan pengangkutan ketumpatan arus genting (J_c). Objektif kajian ini ialah untuk meningkatkan pengepinan fluks daripada sumber karbon CNFs dan CNTs dalam superkonduktor $\text{YBa}_2\text{Cu}_3\text{O}_{7-5}$. Kesan CNFs dan CNTs terhadap sifat-sifat superkonduktor (T_c dan J_c), fasa dan struktur, mikrostruktur dan morfologi termasuk analisis taburan unsur telah dikaji. Y-123 pukal tanpa tambah disediakan sebagai rujukan. J_c Y-123 tanpa penambahan ialah 11 A/cm^2 . Penambahan CNFs dan CNTs telah meningkatkan J_c . Pecahan isipadu fasa Y-123 menunjukkan peratusan yang tinggi $90 >$ dengan peratus atom yang baik dari EDX. Penambahan CNFs menunjukkan peningkatan ketara nilai J_c . Sampel dengan tambahan bendasing $x = 0.4 \text{ wt. } \%$ menunjukkan jumlah yang optimum kerana ia mempamerkan T_c dan J_c tertinggi dengan masing-masing bersamaan dengan 88.0 K dan 830 A/cm^2 . Penambahan CNTs meningkatkan J_c kepada 477 A/cm^2 bagi sampel $x = 0.2 \text{ wt. } \%$. Saiz butiran terbesar dan peratusan fasa Y-123 yang tinggi juga dikesan melalui sampel ini dengan peratusan atom yang baik daripada EDX dan nilai T_c yang tinggi. Peningkatan J_c menggunakan CNFs dan CNTs sebagai pusat pengepin menunjukkan kedua-dua sebatian sesuai untuk memerangkap fluks. Kedua-dua sampel menunjukkan pertambahan dalam nilai T_c dan J_c ke arah nilai berat peratusan (wt. %) yang optimum dan penurunan berlaku apabila nilai kuantiti bendasing bertambah.

ACKNOWLEDGEMENTS

I would like to express my deepest sincere gratitude to my supervisor Dr. Mohd Mustafa bin Awang Kechik for all his valuable guidance, advices, suggestions, comments and encouragement throughout my research study. With his support and patience, I am able to complete this work.

I would also like to thank my co-supervisor Assoc. Prof. Dr. Chen Soo Kien for giving me the opportunity to share the problems as well as suggestions and assistance during the study. My gratitude goes to Prof. Dr. Abdul Halim Shaari for his kindness regarding the facilities used in the laboratory. A very special thanks also goes to Assoc. Prof. Dr. Azhan Hashim from UiTM Pahang for the laboratory and equipment used in the J_c measurement in Jengka, Pahang.

My thanks go to all lab mates for their help and ideas. I am grateful to Mr. Razak Harun for technical assists in the lab, Mrs Norhaslinda Noruddin and Mrs Kamsiah Alias for XRD analysis and others from the Physics Department.

I wish to thank my friends at UPM with whom I enjoyed throughout my study. They are Atikah, Wathiq, Yusnita, Ariffuddin and Afiq. Special gratitude also goes to Nabilah and Hidayah for their kindness and help. I wish them all the best in their endeavours for a better and prosperous life.

Finally, I would like to extend my sincere appreciation to my wonderful parents Mr. Khalid and Mrs Noor Aziah, my brothers Arif and Alif for their endless love and support me through happy moments in life.

Last but not least, I gratefully acknowledge financial support provided by UPM under graduate research fellowship (GRF) and MyBrain15 from Ministry of Higher Education.

I certify that a Thesis Examination Committee has met on (01 November 2016) to conduct the final examination of (Nurul Auni binti Khalid) on her thesis entitled "Physical and Superconducting Properties of Carbon Nanofibers and Carbon Nanotubes $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductor" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Master of Science.

Members of the Thesis Examination Committee were as follows:

Lim Kean Pah, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Rabaah Syahidah binti Azis, PhD

Senior Lecturer
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Y. Bhg. Roslan Abd. Shukor, PhD

Professor
Pusat Pengajian Fizik Gunaan
Fakulti Sains dan Teknologi
Universiti Kebangsaan Malaysia
Selangor, Malaysia
(External Examiner)

NOR AINI AB. SHUKOR, PhD

Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 27 December 2016

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows:

Mohd Mustafa bin Awang Kechik, PhD

Senior Lecturer
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Chen Soo Kien, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

Azhan bin Hashim, PhD

Associate Professor
Faculty of Applied Sciences
Universiti Teknologi MARA Pahang
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- This thesis is my original work;
- Quotations, illustrations and citations have been duly referenced;
- This thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- Intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- Written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- There is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: _____ Date: _____

Name and Matric No.: Nurul Auni binti Khalid GS38134

Declaration by Members of Supervisory Committee

This is to confirm that:

- The research conducted and the writing of this thesis was under our supervision;
- Supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____
Name of Chairman
of Supervisory
Committee: Dr. Mohd Mustafa bin Awang Kechik

Signature: _____
Name of Member of
Supervisory
Committee: Assoc Prof. Dr. Chen Soo Kien

Signature: _____
Name of Member of
Supervisory
Committee: Assoc Prof. Dr. Azhan bin Hashim

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	ii
ACKNOWLEDGEMENTS	iii
APPROVAL	iv
DECLARATION	vi
LIST OF TABLES	x
LIST OF FIGURES	xii
LIST OF ABBREVIATIONS	xv
CHAPTER	
1 INTRODUCTION	1
1.1 Overview	1
1.2 Problem Statement	3
1.3 Objectives	3
1.4 Thesis Contents	3
2 LITERATURE REVIEW AND THEORY	4
2.1 Fundamentals of Superconductivity	4
2.1.1 A Discovery of Superconductivity	4
2.1.2 Type I Superconductor	7
2.1.3 Type II Superconductor	8
2.1.4 Flux pinning and coherence length in YBCO	9
2.2 Superconducting Properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$	9
2.2.1 YBCO system	9
2.2.2 $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ bulks with nanoparticle inclusions	11
2.2.3 Co-precipitation	12
3 METHODOLOGY	13
3.1 Introduction	13
3.2 Sample preparation	13
3.2.1 Co-precipitation method (COP)	13
3.2.2 Yttrium Barium Copper Oxide (YBCO 123)	15
3.2.3 Nano addition (CNFs and CNTs)	15
3.2.4 Thermogravimetric analysis (TGA)	17
3.2.5 Calcination and sintering	17
3.3 Superconducting properties	19

3.3.1	Critical temperature (T_c) and transport critical current density (J_c) measurement	19
3.4	Physical properties	20
3.4.1	X-ray Diffraction (XRD)	20
3.4.2	Scanning electron microscope (SEM)	21
3.4.3	Energy-dispersive X-ray Spectroscopy Analysis (EDX)	21
4	RESULTS AND DISCUSSION	22
4.1	Characterization of Bulk $\text{YBa}_2\text{Cu}_3\text{O}_{7.5}$	22
4.1.1	Introduction	22
4.1.2	Thermogravimetric analysis (TGA)	22
4.1.3	Critical temperature measurement (T_c)	23
4.1.4	Transport Critical current density measurement (J_c)	24
4.1.5	Phase and structure Identification by XRD analysis	24
4.1.6	Surface morphology by SEM	25
4.1.7	Elemental distribution by EDX analysis	26
4.1.8	Summary	27
4.2	Characterization of $\text{YBa}_2\text{Cu}_3\text{O}_{7.5}$ containing CNFs nanoparticles	28
4.2.1	Introduction	28
4.2.2	Superconducting properties	28
4.2.3	Physical properties	32
4.2.4	Summary	39
4.3	Characterization of $\text{YBa}_2\text{Cu}_3\text{O}_{7.5}$ containing CNTs nanoparticles	40
4.3.1	Introduction	40
4.3.2	Superconducting properties	40
4.3.3	Physical properties	44
4.3.4	Summary	51
5	CONCLUSIONS AND SUGGESTION FOR FUTURE RESEARCHES	52
5.1	Conclusions	52
5.2	Suggestion for future research	53
	REFERENCES	54
	APPENDICES	60
	BIODATA OF STUDENT	66
	LIST OF PUBLICATIONS	67

LIST OF TABLES

Table		Page
2.1	Critical temperature (T_c) and critical field (B_c) in Type I superconductors	7
3.1	Material components used in synthesizing of YBCO	15
3.2	Nano addition components of CNFs and CNTs added into YBCO	16
4.1	Quantitative analysis of major Y-123 phase	27
4.2	T_{c-on} , ΔT_c , J_c at 30 K, volume fraction of Y-123 and grain size	27
4.3	$T_{c-onset}$ (K), $T_{c-offset}$ (K), ΔT_c (K) of $x = 0, 0.2, 0.4, 0.6,$ and 0.8 wt. %	30
4.4	Lattice parameter a, b, c , volume of unit cell, and volume fraction of Y-123 phase	33
4.5	Average grain size of every non-added and added sample	36
4.6	Quantitative analysis of major Y-123 phase	37
4.7	Quantitative analysis of major Y-123 phase	37
4.8	Quantitative analysis of major Y-123 phase	38
4.9	Quantitative analysis of major Y-123 phase	38
4.10	T_{c-on} , ΔT_c , J_c at 30 K, volume fraction of Y-123 and grain size	39
4.11	$T_{c-onset}$ (K), $T_{c-offset}$ (K), ΔT_c (K) of $x = 0, 0.2, 0.4, 0.6$ and 0.8 wt. %	42
4.12	Lattice parameter a, b, c , volume of unit cell, and volume fraction of all phases	45
4.13	Average grain size of every non-added and added sample	48
4.14	Quantitative analysis of major Y-123 phase	49
4.15	Quantitative analysis of major Y-123 phase	49

4.16	Quantitative analysis of major Y-123 phase	50
4.17	Quantitative analysis of major Y-123 phase	50
4.18	T_{c-on} , ΔT_c , J_c at 30 K, volume fraction of Y-123 and grain size	51



LIST OF FIGURES

Figure		Page
2.1	The data of Onne's experiment showing the measured resistance of mercury, which does superconductive	4
2.2	The magnetic field lines which do not trapped into superconductor material, when they are cooled below the T_c is called Meissner's Effect	5
2.3	A magnet levitates over a superconductor also known as "Meissner effect"	5
2.4	The evolution of T_c according to the year of discovery	7
2.5	Magnetization against external magnetic field (M-H) graph for Type II superconductor	8
2.6	The layered perovskite structure of YBCO system	10
3.1	The pathway of general co-precipitation	14
3.2	FESEM micrograph of carbon nanofibers	16
3.3	FESEM micrograph of carbon nanotubes	16
3.4	Mettler Toledo TGA/ SDTA851e	17
3.5	Heating profile for calcination process with heating and cooling rate of 2 °C/min and 1 °C/min respectively	18
3.6	Heating profile for sintering process with heating and cooling rate of 2 °C/min and 1 °C/min respectively	19
3.7	PW 3040/60 MPD X'pert Pro Analytical Philips DY 1861	21
4.1	TGA graph for Y-123 precursor powder	23
4.2	Normalized resistance against temperature for the pure YBCO	24
4.3	XRD pattern for the pure YBCO system	25

4.4	SEM image for the pure YBCO	26
4.5	SEM image for the pure YBCO showing the selected spot for EDX	27
4.6	Normalized resistance against temperature at different weight percentage of $x = 0, 0.2, 0.4, 0.6$ and 0.8 wt. %	29
4.7	$T_{c-onset}$ (K) and variation of T_c at $x = 0, 0.2, 0.4, 0.6,$ and 0.8 wt. %	29
4.8	V - I curve in self-field at 30 K of a) $x = 0.2$ wt. % b) $x = 0.4$ wt. % c) $x = 0.6$ wt. % d) $x = 0.8$ wt. %	31
4.9	The variation of transport J_c against CNFs content	32
4.10	XRD pattern of $YBa_2Cu_3O_{7-\delta}$ system with $x = 0, 0.2, 0.4, 0.6,$ and 0.8 wt. %	33
4.11	SEM images of a) Y-123 + CNFs ($x = 0$ wt. %) b) Y-123 + CNFs ($x = 0.2$ wt. %) c) Y-123 + CNFs ($x = 0.4$ wt. %) d) Y-123 + CNFs ($x = 0.6$ wt. %) e) Y-123 + CNFs ($x = 0.8$ wt. %)	35
4.12	SEM image for $x = 0.2$ wt. % showing the selected spot for EDX	37
4.13	SEM image for $x = 0.4$ wt. % showing the selected spot for EDX	37
4.14	SEM image for $x = 0.6$ wt. % showing the selected spot for EDX	38
4.15	SEM image for $x = 0.8$ wt. % showing the selected spot for EDX	38
4.16	Normalized resistance against temperature at different weight percentage of $x = 0, 0.2, 0.4, 0.6$ and 0.8 wt. %	41
4.17	$T_{c-onset}$ (K) and variation of T_c at $x = 0, 0.2, 0.4, 0.6$ and 0.8 wt. %	41
4.18	V - I curve in self-field at 30 K of a) $x = 0.2$ wt. % b) $x = 0.4$ wt. % c) $x = 0.6$ wt. % d) $x = 0.8$ wt. %	43

4.19	The variation of transport J_c against CNTs content	44
4.20	XRD pattern of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ system with $x = 0, 0.2, 0.4, 0.6$ and 0.8 wt. %	45
4.21	SEM images of a) Y-123 + CNTs ($x = 0$ wt. %) b) Y-123 + CNTs ($x = 0.2$ wt. %) c) Y-123 + CNTs ($x = 0.4$ wt. %) d) Y-123 + CNTs ($x = 0.6$ wt. %) e) Y-123 + CNTs ($x = 0.8$ wt. %)	47
4.22	SEM image for $x = 0.2$ wt. % showing the selected spot for EDX	49
4.23	SEM image for $x = 0.4$ wt. % showing the selected spot for EDX	49
4.24	SEM image for $x = 0.6$ wt. % showing the selected spot for EDX	50
4.25	SEM image for $x = 0.8$ wt. % showing the selected spot for EDX	50

LIST OF ABBREVIATIONS

A	Ampere
Å	Angstrom
BCS Theory	Bardeen-Cooper-Schrieffer Theory
BaCO ₃	Barium carbonate
cm ²	Centimetre square
CNFs	Carbon nanofibers
CNTs	Carbon nanotubes
COP	Co-precipitation
EDX	Energy Dispersive X-ray Analysis
FESEM	Field Emission Scanning Electron Microscope
H_{c1}	Lower critical field
H_{c2}	Upper critical field
HTS	High Temperature Superconductor
ICDD	International Centre for Diffraction Data
J_c	Critical current density
K	Kelvin
nm	Nanometre
SEM	Scanning Electron Microscope
T_c	Critical temperature
TGA	Thermogravimetric analysis
wt. %	Weight percentage
XRD	X-ray Diffraction

Y-123

$\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$

Y-124

$\text{YBa}_2\text{Cu}_4\text{O}_8$

δ

Oxygen deficiency

ξ

Coherence length

λ

Wavelength, Penetration depth



CHAPTER 1

INTRODUCTION

1.1 Overview

Superconductors are of completely different orders, such strange and mysterious materials as it becomes a perfect conductor of electricity after being chilled to unimaginably cold temperatures. In the year of 1911, a physicist unexpectedly noticed that in certain materials, an electric current could flow without removing any heat and it is resistance-less. Mercury was the first superconducting element which exhibited a dramatically drop in resistivity (Dahal, 2011; Kirkpatrick, 2010). Following the year of the first discovery, a number of superconducting materials have been discovered such as lead, aluminium, titanium and tin which superconduct when they were cooled below a critical temperature, T_c (Abd-Shukor, 2004). Those materials are classified as conventional superconductors which are made up of metals and alloys in which the T_c is normally less than 24 Kelvin, until the discovery of MgB_2 in 2001 with the highest T_c of 39 K.

Paul Chu is not a conventional thinker and he wasn't interested in doing the conventional things. By the year of 1986, Paul Chu and his research team discovered the exotic superconducting mixture of yttrium, barium, copper and oxygen (YBCO), with a superconducting transition temperature of 93 K (Hazen, 1989; Blundell, 2009). It was a revolutionary discovery of YBCO which was named as Y-123 with the chemical formula of $YBa_2Cu_3O_{7-\delta}$, as it was the first ever material with T_c above the boiling point of liquid nitrogen (77 K). This simply means that superconductors would no longer require a complex cooling system for their applications, unlike other materials that need liquid helium in their operation which is rather costly. Y-123 superconductor gave huge impacts to the market penetration for power applications (Hawsey and Christen, 2006) due to its high T_c . However, the weak flux pinning and granularity of Y-123 especially at temperatures above 20-30 K seems to have small critical current density, J_c (Dadras, 2009).

In recent years, various synthetic strategies have been employed concerning the pinning center properties in superconducting system (Berdan Özkurt, 2013). A technique of doping and addition of impurities including metal and non-metal elements, nanoparticles, carbon sources and other compounds have shown the dependent on superconducting properties. The influence of the type and amount of chemical compound and impurities can be used to improve both inter-granular and intra-granular critical current density, J_c in different high temperature superconductors (Dadras, 2009). Moreover, the requirement of high performance YBCO bulks in current science and technological applications indicates that doping of YBCO samples with another suitable compound with a right proportions would be a reliable method in order to

achieve highly qualified complex structures (Tepe *et al.*, 2014) by improving its grain boundary superconducting properties (Jian Yong Xiang, 2008).

Many successful groups claim that the improvement of J_c in high temperature superconductor can be obtained by the introduction of nanoparticle addition, which act as artificial pinning centers (Sushant Gupta, 2011; R. Mawassi, 2014; Abd-Ghani, 2012). The effective artificial pinning centers will further enhance a strong J_c at higher fields and higher temperature, which can be achieved when the flux lines are pinned and automatically, their movement will be prevented (Kechik, 2010). In high temperature superconductor (HTS), the effects on the vortex movements, determination of J_c , and other superconducting properties are depending on the engineering artificial pinning centers, over the pinning of flux line through crystal imperfections or so-called defects (Pathak *et al.*, 2008) such as low-angle grain boundaries, twin boundaries, dislocations and non-superconducting phase (Dang, 2010; Zhou *et al.*, 2002). The route of artificially introducing inhomogeneity or second-phase materials as flux pinning sites in the processing of bulk YBCO is a long standing issue (Hamrita *et al.*, 2014).

Nano-phase particles in superconductor links can improve the intra-granular critical current density under high magnetic field (Dadras, 2009). On the other hand, due to the effects of intra-granular, the enhancement of the inter-granular electrical links can have an effective role in the increase of J_c , since the existence of electrically coupled grains can increase inter-granular current flow. Carbon precursor's sources like carbon nanofibers, carbon nanotubes and graphene are particularly interesting due to their nanometer diameter that can serve as the effective pinning centers. In this project, carbon nanofibers (CNFs) and carbon nanotubes (CNTs) are chosen as the impurities to the addition of Y-123.

Carbon nanofibers consist of multi-graphene sheets rolled into concentric cylinders. There are hollow core nanofibers consisting of a single graphite layer or double graphite layers that are stacked parallel or at a certain angle from the fiber axis (Al-Saleh and Sundararaj, 2011). The stacked layers are nested with each other and have different structures including bamboo-like, parallel and cup-stacked. CNFs have excellent mechanical properties, high electrical conductivity and high thermal conductivity, which can be imparted into a wide range of matrices including ceramics and metals. It is very well known that CNFs have a higher tendency to form agglomerates because of their high surface area ($1000 \text{ m}^2/\text{g}$). Carbon nanotubes (CNTs) which act as the carbon precursors usually result in some improvements in upper critical field (H_{c2}) and critical current density (J_c). In addition, CNTs also show some individuality for their high aspect ratio and nanometer width. CNTs and CNFs is a graphitic filament with diameters ranging from 0.4 to 500 nm and lengths in the range of several micrometers to millimetres (Dadras, 2009). Moreover, this kind of carbon does not decay, however it may turn into a part of the crystal matrix as a whole, where they are performed as one of the effective pinning centers (Shekhar *et al.*, 2007).

1.2 Problem Statement

Over the years, many researches have been carried out to investigate the superconducting properties of high temperature superconducting (HTS). High transition temperatures (T_c) and current density (J_c) value play important roles in the practical application of YBCO. However, there is insufficient and low J_c in YBCO samples because of the serious weak links and granularity. This research project proposes to prepare a good quality of pure YBCO-123 via co-precipitation method with view in having the possibility of controlled particle size and morphology. A nanoparticle of CNFs and CNTs are also added to YBCO. Up until now, the effects of CNFs and CNTs adding or doping on Y-123 compound via co-precipitation (COP) method have yet to be reported.

1.3 Objectives

The main objectives of this project are to synthesise and prepare $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ (Y-123) by co-precipitation method. Other purpose is to study the effects of the addition of nano-phase particles from carbon sources into superconductor matrix, which act as artificial pinning center. So, the observation on every possible role played by CNFs and CNTs addition in improving the flux pinning properties of Y-123 compound is studied. The parameters in term of weight percentage (wt. %) is varied with pure sample (0 wt. %) and added samples (0.2 wt. %, 0.4 wt. %, 0.6 wt. % and 0.8 wt. %). Thus, the test and study is carried out through:-

- i) The determination of their superconducting properties such as the trend of critical temperature, T_c and critical current density, J_c .
- ii) The determination of their physical properties such as the phase formation and surface morphology.

1.4 Thesis Contents

Chapter 1 sees a brief introduction on overview of superconductors about YBCO, strategies regarding the pinning center properties, introduction of nanoparticles addition and carbon family (CNFs and CNTs), follows by problem statement and objectives. In Chapter 2, the discussion is focused on the literature reviews and theories which support the project. Some literatures about YBCO system with nanoparticle inclusions have also been reviewed. Meanwhile, the theory of fundamentals in superconductivity is studied based on the discovery, Type I and Type II superconductors as well as the flux pinning and the coherence length. In Chapter 3, the discussion will be on the advantages of the methodology with sample preparation, follows by the characterizations in superconducting and physical properties. In Chapter 4, the experimental data and results obtained as well as the discussions are presented. Finally in the last chapter, Chapter 5, overall explanations and discussions are concluded with the additional suggestions for future research.

REFERENCES

- Abd-Ghani, S. N., Abd-Shukor, Roslan, Kong, Wei. (2012). Effects of Fe₃O₄ Nano Particles Addition in High Temperature Superconductor YBa₂Cu₃O_{7-δ}. Paper presented at the *Advanced Materials Research*.
- Abd-Shukor, R. (2004). Introduction to Superconductivity in Metals, Alloys & Cuprates. Tanjung Malim: Penerbit Universiti Pendidikan Sultan Idris.
- Agail A., R. A.-S. (2014). Effect of Nano-size SnO₂ Addition On (Bi, Pb)-Sr-Ca-Cu-O Superconductor. *Solid State Science and Technology*, 22(1 & 2), 1-6.
- Aima Ramli, A. H. S., Hussein Baqiah, Chen Soo Kien, Mohd Mustafa Awang Kechik, Zainal Abidin Talib (2016). Role of Nd₂O₃ nanoparticles addition on microstructural and superconducting properties of YBa₂Cu₃O_{7-δ} ceramics. *Journal of Rare Earths*, 34(9), 895-900.
- Al-Saleh, M. H., & Sundararaj, U. (2011). Review of the mechanical properties of carbon nanofiber/polymer composites. *Composites Part A: Applied Science and Manufacturing*, 42(12), 2126-2142.
- Azhan H., F. F., S. Y. S. Yusainee, K. Azman, S. Khalida. (2013). Superconducting Properties of Ag and Sb Substitution on Low-Density YBa₂Cu₃O_δ. *Journal Superconductivity and Novel Magnetism*, 26, 931-935.
- Ben Azzouz, F., Zouaoui, M., Mellekh, A., Annabi, M., Van Tendeloo, G., & Ben Salem, M. (2007). Flux pinning by Al-based nanoparticles embedded in YBCO: A transmission electron microscopic study. *Physica C: Superconductivity and its Applications*, 455(1-2), 19-24.
- Berdan Özkurt, M. A. M., A. Sotelo, J. C. Diez. (2013). The Influence of Postannealing on Structural and Superconducting Properties of Bi-2212 Ceramics. *Journal of Superconductivity and Novel Magnetism*, 26(11), 3247-3252.
- Blundell, S. (2009). Superconductivity A Very Short Introduction. New York: Oxford University Press.
- Bourdillon, A., & Bourdillon, N. X. T. (1994). High temperature superconductors: processing and science: Academic Press.
- Brown, C. (2013). Cooper Pairs and Their Influence on Superconductivity Theory. Retrieved from pdfs.semanticscholar.org/b881/86f1e258696b21f75adc0fdb1bda6835e937.pdf
- Charles P. Poole, J. (2000). Handbook of Superconductivity. San Diego: Academic Press (A Harcourt Science and Technology Company).

- Chou, M. J., & Yeu Chen, W. (2012). The critical current density in type-II superconducting bulk materials.
- Dadras, S., Liu, Y., Chai, Y. S., Daadmehr, V., & Kim, K. H. (2009). Increase of critical current density with doping carbon nano-tubes in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$. *Physica C: Superconductivity*, 469(1), 55-59.
- Dahal, K. P. (2011). Superconductivity: A Centenary Celebration. *Himalayan Physics*, 2(2), 26-34.
- Dang, V.-S. (2010). Nanotechnology of Pinning Centres in High Temperature Superconducting $\text{YBa}_2\text{Cu}_3\text{O}_7$ Films. Doctor Of Philosophy, University of Birmingham, Birmingham.
- Dejonghe, L. C., & Rahaman, M. N. (2003). 4.1 Sintering of Ceramics. *Handbook of Advanced Ceramics: Materials, Applications, Processing and Properties*, 187.
- Dew-Hughes, D. (2001). The critical current of superconductors: an historical review. *Low Temperature Physics*, 27(9), 713-722.
- Edgar A Duarte, N. G. R., Pedro A Quintero, Mark W Meisel, Juan C Nino. (2015). Electrospinning of superconducting YBCO nanowires. *Superconductor Science and Technology*, 28(1), 015006.
- Fagnard, J.-F., Vanderbemden, P., Genon, A., Cloots, R., & Ausloos, M. (2003). Intergranular and intragranular properties of superconducting multifilamentary Bi 2223 Ag tapes: comparison of electrical transport and magnetic measurement methods.
- Frank J. Owens and Charles P. Poole, J. (2002). The New Superconductors. New York, Boston, Dordrecht, London, Moscow: Kluwer Academic.
- Guner, S. B., Gorur, O., Celik, S., Dogruer, M., Yildirim, G., Varilci, A., & Terzioglu, C. (2012). Effect of zirconium diffusion on the microstructural and superconducting properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ superconductors. *Journal of Alloys and Compounds*, 540, 260-266.
- Hadi Salamati, A. A. B.-B. a. M. S. (2001). Investigation of weak links and the role of silver addition on YBCO superconductors. *Superconductor Science and Technology*, 14(10), 816-819.
- Hafsa, M. N., Ibrahim, M., & Sharif, S. (2013). Investment casting using multi-jet modelling patterns: the thermogravimetric analysis of visijet® SR200 UV curable acrylate plastic. Paper presented at the *IOP Conference Series: Materials Science and Engineering*.
- Hamadneh, I., Ahmad, A. M., Wahid, M. H., Zainal, Z., & Abd-Shukor, R. (2009). Effect Of Nano-Sized Oxalate Precursor On The Formation Of $\text{GdBa}_2\text{Cu}_3\text{O}_{7.5}$ Phase Via Coprecipitation Method. *Modern Physics Letters B*, 23(16), 2063-2068.

- Hamrita, A., Slimani, Y., Ben Salem, M. K., Hannachi, E., Bessais, L., Ben Azzouz, F., & Ben Salem, M. (2014). Superconducting properties of polycrystalline $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ prepared by sintering of ball-milled precursor powder. *Ceramics International*, 40(1, Part B), 1461-1470.
- Hawsey, R. A., & Christen, D. K. (2006). Progress in research, development, and pre-commercial deployment of second generation HTS wires in the USA. *Physica C: Superconductivity and its Applications*, 445-448, 488-495.
- Hazen, R. M. (1989). *Superconductors The Breakthrough*. London: Unwin Hyman Limited.
- Hoffman. (2010). Superconducting Cuprates. Retrieved January 1, 2010, from <http://hoffman.physics.harvard.edu/materials/CuprateIntro.php>
- Jaworski, P. (2005). Meissner Effect. In *EfektMeisnera.svg* (Ed.), (Vol. 525 × 525 pixels). Poland.
- Jian Yong Xiang, C. F., Damian P. Hampshire. (2008). Bulk nanocrystalline superconducting $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$. *Journal of Physics: Conference Series*, 97, 1-7.
- Keattch, C. J., & Dollimore, D. (1975). *An introduction to thermogravimetry*: Heyden Publishers.
- Kechik, M. M. A. (2007). Ketumpatan Arus Genting Angkutan Pita Superkonduktor Bi-Sr-Ca-Cu-O/Ag dengan Penambahan Fe_3O_4 dan Co_3O_4 sebagai Pusat Pengepin Fluks. Sarjana Sains, Universiti Kebangsaan Malaysia, Bangi.
- Kechik, M. M. A. (2010). Improvement of Critical Current Density in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Films with Nano-Inclusions. Doctor Of Philosophy, University of Birmingham, Birmingham.
- Khurram, A. A., & Nawazish, A. K. (2006). Study of the intergranular coupling of $\text{Cu}_{0.5}\text{Ti}_{0.5}\text{Ba}_2\text{Ca}_{2-y}\text{Mg}_y\text{Cu}_3\text{O}_{10-\delta}$ ($y = 0, 0.5, 1.0$ and 1.5) superconductors. *Superconductor Science and Technology*, 19(6), 679.
- Kim, K. H., Kang, W., Kim, M.-S., Jung, C., Kim, H.-J., Choi, E.-M., Lee, S.-I. (2001). Origin of the high DC transport critical current density for the MgB_2 superconductor.
- King, F. (2008). Finding the critical temperature of a YBCO superconductor using a voltage probe.1-4. Retrieved from physics.wooster.edu/JrIS/Files/King_web_article.pdf
- Larry D. Kirkpatrick, G. E. F. (2010). *Physics: A Conceptual World View* (7 ed.): Cengage Learning.

- Lau, K., & Abd-Shukor, R. (2005). Pinning strength in Ag-sheathed Bi (Pb)-Sr-Ca-Cu-O superconductor tapes studied from current-electric field characteristics. *Journal of Materials Science: Materials in Electronics*, 16(1), 17-19.
- Lortz, R., Tomita, T., Wang, Y., Junod, A., Schilling, J. S., Masui, T., & Tajima, S. (2006). On the origin of the double superconducting transition in overdoped $\text{YBa}_2\text{Cu}_3\text{O}_x$. *Physica C: Superconductivity*, 434(2), 194-198.
- Mawassi R., S. M., M. Roumié, R. Awad, M. Korek, I. Hassan. (2014). Improvement of Superconducting Parameters of $\text{Bi}_{1.8}\text{Pb}_{0.4}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10+\delta}$ Added with Nano-Ag. *Journal of Superconductivity and Novel Magnetism*, 27(5), 1131-1142.
- McHale J., G. H. M., and R. E. Salomon. (1995). Simplified preparation of $\text{REBa}_2\text{Cu}_3\text{O}_{7-x}$ via the acetate method. *Journal of Materials Research*, 10(1), 1-6.
- Min Zhou, A. S., Lina Sun, Peipei Han. (2013). Effect of the oxygen distribution and inhomogeneity on the superconducting properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta} + x$ mol% $\text{Y}_2\text{Ba}_4\text{CuMoO}_y$ superconductors. *Superconductor Science and Technology*, 26(10), 105006.
- Mittal, V. (2012). Characterization Techniques for Polymer Nanocomposites. Abu Dhabi: Wiley Publishers.
- Mody, V. V., Siwale, R., Singh, A., & Mody, H. R. (2010). Introduction to metallic nanoparticles. *Journal of Pharmacy and Bioallied Sciences*, 2(4), 282.
- Nur Jannah Azman, H. A., and Roslan Abd-Shukor. (2014). Transport Critical Current Density of $(\text{Bi}_{1.6}\text{Pb}_{0.4})\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10}$ Ceramic Superconductor with Different Nanosized Co_3O_4 Addition. *Advances in Condensed Matter Physics*, 1-8.
- Ochsenkühn-Petropoulou, M., Argyropoulou, R., Tarantilis, P., Kokkinos, E., Ochsenkühn, K. M., & Parissakis, G. (2002). Comparison of the oxalate co-precipitation and the solid state reaction methods for the production of high temperature superconducting powders and coatings. *Journal of Materials Processing Technology*, 127(1), 122-128.
- Pathak, S. K., Babu, N. H., Iida, K., Denis, T., Matthews, L., Strasik, M., & Cardwell, D. A. (2008). The effect of Ag and Y-24W1 addition on the microstructure and superconducting properties of single grain Y-Ba-Cu-O. *Materials Science and Engineering: B*, 151(1), 40-46.
- Pennicott, K. (2001, Jun 28, 2001). Nanotubes are the new superconductors. *Physics World*.

- Pia Jensen, R. (2016). Structural investigation of $\text{La}_{(2-x)}\text{Sr}_x\text{CuO}_{(4+y)}$ - Following staging as a function of temperature. Master of Science. University of Copenhagen, Denmark.
- Poom Prayoonphokkharat, S. J., Anucha Watcharapasorn. (2012). Fabrication of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Powder with Different Calcination Temperatures. *Journal of the Microscopy Society of Thailand*, 5(1-2), 63-66.
- Prananto, D. (2012). Superconductivity. Retrieved from Simpliphy Simple but not simpler website:
<https://simpliphy.wordpress.com/2012/05/06/superconductivity/>
- Ram Kossowsky, B. R., Dieter Wohlleben, Stamatis K. Patapis. (1992). Physics and Materials Science of High Temperature Superconductors, II (Vol. 209): Kluwer Academic Publishers.
- Rani, P., Jha, R., & Awana, V. (2013). AC Susceptibility Study of Superconducting $\text{YBa}_2\text{Cu}_3\text{O}_7: \text{Ag}_x$ Bulk Composites ($x = 0.0-0.20$): The Role of Intra and Intergranular Coupling. *Journal of Superconductivity and Novel Magnetism*, 26(7), 2347-2352.
- Rohlf, J. W. (1994). Modern physics from alpha to Z. New York: Wiley Publishers, c1994, 1.
- Sahoo, M., & Behera, D. (2012). Study of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}/\text{Al}_2\text{O}_3$ Composite for Structural and Electrical transport Property. *International Journal of Scientific and Research Publications*, 2(9), 1-6.
- Sato, K., & Ohara, S. (2009). Synthesis of NiO/YSZ nanocomposite particles using co-precipitation method. *Transactions of JWRI*, 38(1), 85-88.
- Saxena, A. K. (2012). High-Temperature Superconductors (2nd Edition ed.). India: Springer.
- Schildermans I., M. V. B., E. Knaepen, J. Yperman, J. Mullens, L. C. Van Poucke. (1997). Synthesis of the high temperature superconductor $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ by the hydroxide co-precipitation method. *Physica C: Superconductivity*, 278, 55-61.
- Sekkina, M. A., Tawfik, A. R., Hemeda, O., Dawoud, M. A. T., & El-Attar, S. (2006). Physical Properties of Holmium Promoted Superconductivity in Nd-Doped YBCO HTC-Superconductors. *Turkish Journal of Physics*, 29(6), 329-340.
- Sheahen, T. (2006). Introduction to High-Temperature Superconductivity: Springer US.
- Shekhar, C., Giri, R., Malik, S., & Srivastava, O. (2007). Improved Critical Current Density of MgB_2 -Carbon Nanotubes (CNTs) Composite. *Journal of Nanoscience*.

- Shoushtaria, L., Pishbin, N., Salavati, A., Sohrabi, D., Hosseinib, M., Mahmoodian, M., & Alinejad, N. (n. d). The effects of carbon nano tube addition in YBCO HTS film prepared by Doctor Blades method.
- Smodej, J., Reuning, L., Wollenberg, U., Zinke, J., Pfeiffer, M., & Kukla, P. A.. (2015). Two-dimensional X-ray diffraction as a tool for the rapid, nondestructive detection of low calcite quantities in aragonitic corals. *Geochemistry, Geophysics, Geosystems*, 16(10), 3778-3788.
- Su, X. D., Yang, Z. Q., Wang, Y. Z., Tang, H., Zhang, C., Hua, L., & Qiao, G. W. (1997). The influence of nano-Cu addition on the superconductivity of YBCO Proceedings of the International Conference on Materials and Mechanisms of Superconductivity High Temperature Superconductors V. *Physica C: Superconductivity*, 282, 1615-1616.
- Sushant Gupta, R. S. Y., B. Das. (2011). Flux Pinning by Nano Particles Embedded in Polycrystalline Y-123 Superconductors. *ISST Journal of Applied Physics*, 2(2), 1-5.
- Tachiki M., Y. M., S. Maekawa. (1987). Proceedings of the Yamada Conference XVIII on Superconductivity in Highly Correlated Fermion System. Sendai, Japan: Elsevier Science Publishers B. V. and Yamada Science Foundation.
- Tepe, M., Uzun, Y., & Gokay, U. S. (2014). Superconducting Properties of Melt-Textured Growth $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Materials with Y211 Addition. *Journal of Superconductivity and Novel Magnetism*, 1-4.
- Tomimoto, K., Terasaki, I, Rykov, AI, Mimura, T, Tajima, S. (1999). Impurity effects on the superconducting coherence length in Zn-or Ni-doped $\text{YBa}_2\text{Cu}_3\text{O}_{6.9}$ single crystals. *Physical Review B*, 60(1), 114.
- Vidali, G. (1993). Superconductivity: The Next Revolution?: Cambridge University Press.
- Webster, J. G. (2003). Electrical Measurement, Signal Processing, and Displays: CRC Press.
- Xu, S., Yu, A., Gu, Y., & Wu, X. (2010). Effect of Yb_2O_3 additives on structure and transport properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7.6}$. *Journal of Rare Earths*, 28, 434-436.
- Zhou, L., Chen, S. K., Wang, K. G., Wu, X. Z., Zhang, P. X., & Feng, Y. (2001). Synthesis of ultrafine Y_2BaCuO_5 powder and its incorporation into YBCO bulk by powder melting process. *Physica C: Superconductivity*, 363(2), 99-106.
- Zhou, L., Chen, S. K., Wang, K. G., Wu, X. Z., Zhang, P. X., Feng, Y., Li, S. L. (2002). Preparation of enhanced J_c YBCO bulks by powder melting process with a combination of submicron 211 precursor and Pt addition. *Physica C: Superconductivity*, 371(1), 62-68.

LIST OF PUBLICATIONS

Publication in Index Journal

Nurul Auni Khalid, Mohd Mustafa Awang Kechik, Nur Atikah Baharuddin, Chen Soo Kien, Hussein Baqiah, Nur Nabilah Mohd Yusuf, Abdul Halim Shaari, Azhan Hashim and Zainal Abidin Talib. (2018). Impact of Carbon Nanotubes Addition on Transport and Superconducting Properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$. Journal of Ceramics International.

N. A. Khalid, M. M. Awang Kechik, N. A. Baharuddin, N. N. Mohd Yusuf, S. K. Chen, H. Baqiah and Azhan Hashim. (2018). Comparative Studies on The Superconducting, Phase and Physical Properties of YBCO Added Carbon Nanofibers & Carbon Nanotubes. Journal of Solid State Science & Technology.

Journal and Abstract in conference proceedings

N. A. Khalid, N. A. Baharuddin, M. M. Awang Kechik, S. K. Chen, S. A. Halim & H. Azhan. Study of Structural and Morphological of YBCO and the Role of Carbon Nanotube Addition. Presented at the 5th International Conference Solid State Science & Technology (ICSSST), Bayview Hotel, Pulau Langkawi, 13-15 December 2015.

N. A. Khalid, N. A. Baharuddin, M. M. Awang Kechik, S. K. Chen & S. A. Halim. Synthesis and Characterization of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Superconductor with Nano Addition Of Carbon Nanofibers via Co-Precipitation Method. Presented at the 28th Regional Conference Solid State Science & Technology (RCSST), Copthorne Hotel, Cameron Highlands, 25-27 November 2014.

N. A. Khalid, N. Mohamad Sa'ad, N. N. Mohd Yusuf, N. A. Baharuddin, M. M. Awang Kechik, S. K. Chen & S. A. Halim. The Effect of Sintering Temperature on Superconducting Properties of YBCO via Co precipitation Method. Physics Symposium, Fundamental Science Congress 2014 (FSC 2014), Universiti Putra Malaysia, 19-20 August 2014.