



**UNIVERSITI PUTRA MALAYSIA**

***CHARACTERIZATION AND DEVELOPMENT OF CASSAVA (*Manihot  
esculenta* CRANTZ) / SUGAR PALM (*Arenga pinnata* (WURMB) MERR.)  
FIBER- REINFORCED CASSAVA STARCH HYBRID COMPOSITES***

**AHMED FARAJ IBRAHIM HISSSEN EDHIREJ**

**FK 2018 41**



**CHARACTERIZATION AND DEVELOPMENT OF CASSAVA (*Manihot esculenta* CRANTZ) / SUGAR PALM (*Arenga pinnata* (WURMB) MERR.) FIBER- REINFORCED CASSAVA STARCH HYBRID COMPOSITES**

By

**AHMED FARAJ IBRAHIM HISSEN EDHIREJ**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,  
in Fulfilment of the Requirements for the Degree of Doctor of Philosophy**

**June 2017**

## **COPYRIGHT**

All material contained within the thesis, including without limitation text, logos, icons, photographs, and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Doctor of Philosophy

**CHARACTERIZATION AND DEVELOPMENT OF CASSAVA (*Manihot esculenta* CRANTZ) / SUGAR PALM (*Arenga pinnata* (WURMB) MERR.) FIBER- REINFORCED CASSAVA STARCH HYBRID COMPOSITES**

By

**AHMED FARAJ IBRAHIM HISSEN EDHIREJ**

**June 2017**

**Chairman : Professor Mohd Sapuan Salit, PhD**  
**Faculty : Engineering**

Cassava is a unique plant, which has a number of uses including the manufacture of various foods, bio-fibers, bio-composites and biopolymers. Moreover, it serves as a renewable energy source as a starch. A series of characterization experiments were carried out to explore the potential use of cassava starch, peel, bagasse, polymers, composites and hybrid composites. A casting technique was used to fabricate the specimens. The following five-phases process prepared the hybrid composites from cassava/sugar palm fibers and cassava starch.

The first phase of the process studied the physical, morphological and thermal properties of cassava starch (CS), peel (CP) and bagasse (CB) obtained from a Malaysian cassava plant along with their chemical composition. Thermal characteristic studies using a Thermal Gravimetric Analyzer (TGA) and Differential Scanning Calorimetry (DSC) showed that cassava starch and fibers were thermally stable with a decomposition temperature of 172.87, 177.76 and 169.23 °C for cassava starch, peel and bagasse, respectively. A study on morphological surface indicated that cassava starches were rounded and oval-shaped, bagasse polygonal shaped and peel exhibited as both round and polygonal. The carbohydrate content in starch was 86.47 g/100g. The study showed that the cassava peel and bagasse contained high concentrations of hemicellulose at 23.38, 29.26 %, respectively. It can be concluded that, cassava starch and fiber are suitable to develop materials with acceptable mechanical and thermal properties for various applications such as packaging, automotive and agro-industrial applications.

Phase two involved an investigation of the effects of plasticizers (Fructose, Urea, Triethylene glycol and Triethanolamine), with different concentration, on the physical, thermal and mechanical properties of cassava starch-based films. The moisture content, water solubility and water absorption of the films increased with increasing plasticizer content. Fructose plasticized films showed excellent water resistance when compared to other plasticizers. Film plasticized with 30% fructose showed the highest density at  $1.74 \text{ g/cm}^3$ , while the lowest water content at 10.96% and water absorption at 110%. Films containing fructose presented smooth surfaces without pores. The relative crystallinity decreased with increasing plasticizer content. The film plasticized by 30% fructose presented higher relative crystallinity (0.31). Film plasticized with 30% fructose showed the tensile strength (4.7 MPa) and tensile modulus (69 MPa). Thus, fructose was the most efficient plasticizer agent among the various plasticizers used in this study.

Phase three focused on the use cassava peel with two different particle sizes as a natural filler for thermoplastic starch (TPS) based on the cassava starch. The addition of peel resulted in an increase in the thickness, water content and water absorption of the films while it decreased the density and water solubility. Moreover, scanning electron microscopy showed that the films containing smaller size of peel had a better compact structure and a homogeneous surface without pores. The addition of 6% peel increased the elastic modulus and tensile strength up to 449.74 and 9.62 MPa, respectively, this being the most efficient reinforcing agent. Also, the temperature variation of the dynamic-mechanical parameters of cassava starch/peel composites was investigated using a DMA test. It was observed that the incorporation of peel increased the tensile strength and modulus. In conclusion, cassava starch/peel composite films are suitable for various purposes such as packaging, automotive and agro-industrial application, at a lower cost.

In phase four, cassava starch-based composite film was prepared using the fibrous residual from starch extraction (cassava bagasse) as a filler. Composite films were prepared through the casting technique using fructose as plasticizer and various size and concentration of bagasse. The size and concentration of bagasse significantly influenced the physical properties. It increased the thickness, water solubility and water absorption. It reduced the water content and density of the film. However, there was no significant effect on thermal properties with the addition of bagasse. XRD studies indicated an increase in the crystallinity of the composites with increasing fiber content. SEM micrographs indicated that films with a smaller size of bagasse showed better compact structure and a homogeneous surface. The modulus and tensile strength of composite films was increased from 69.03 to 581.68 MPa and from 4.7 to 10.78 MPa, respectively, by the addition of 6% bagasse, showed the most efficient reinforcing agent owing to its remarkable physical and mechanical properties.

In the final phase, the hybrid composites were successfully prepared using different amounts of fibers, the hybrid composite contains (6% w/w dry starch) cassava bagasse and (0, 2, 4, 6 and 8 % w/w dry starch) sugar palm fiber. The specimens were prepared

by a casting technique using fructose as plasticizer for the cassava starch. The incorporating of SPF significantly influenced the physical properties. It increased the thickness, while it decreased density, water content, water solubility and water absorption of the films. Moreover, XRD studies indicated increasing crystallinity of the composites with increasing of fiber content. The incorporation of SPF increased the relative crystallinity up to 47%, compared to 32% of the CS film. The water barrier vapor permeability (WVP) values decreased with increasing SPF content. The mechanical properties of the films improved with the incorporation of fibers. The modulus and tensile strength of the films increased from 69.03 to 1114.6 MPa and from 4.7 to 20.72 MPa, respectively for film contains 6% CB and 6% SPF, which was the most efficient reinforcing agent. Also, dynamic-mechanical properties of the hybrid composites were investigated using a DMA test. It was observed that the incorporation of SPF increased the storage modulus ( $E'$ ) value from 0.457 GPa of CS to 1.490 GPa of CS-CB/SPF8 hybrid composite film. In conclusion, CB/SPF reinforced CS hybrid composite films are suitable for various purposes such as packaging, and agro-industrial applications, at a much lower cost while having sustainable environmental automotive benefit.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**PENCIRIAN DAN PEMBANGUNAN KOMPOSIT HIBRID KANJI UBI KAYU DIPERKUAT GENTIAN UBI KAYU (*Manihot esculenta* CRANTZ)/IJUK (*Arenga pinnata* (WURMB) MERR.)**

Oleh

**AHMED FARAJ IBRAHIM HISSEN EDHIREJ**

**Jun 2017**

**Pengerusi : Profesor Mohd Sapuan Salit, PhD**  
**Fakulti : Kejuruteraan**

Ubi kayu adalah pokok yang unik mempunyai pelbagai kegunaan yang termasuk pembuatan belbagai makanan bio-gentian, biokomposit dan biopolimer. Tambahan pula, ia memberikan satu sumber tenaga diperbaharui bagi kanji. Satu siri eksperimen telah dijalankan untuk pencirian kanji, kulit, hampas, polimer, komposit dan komposit hibrid daripada ubi kayu. Kaedah penuangan telah digunakan untuk pembikinan sampel. Lima fasa telah dijalankan untuk menyediakan komposit hibrid daripada gentian ubi kayu/enuau dan kanji ubi kayu.

Fasa pertama telah dilaksanakan dengan mengkaji sifat fizikal, morfologi dan termal bagi kanji (CS), kulit (CP) dan hampas (CB) ubi kayu yang diperolehi daripada pokok ubi kayu Malaysia di samping komposisi kimia mereka. Kajian ciri-ciri termal menggunakan penganalisis gravimatrik termal (TGA) dan kalorimetri pengimbasan kebezaan (DSC) telah menunjukkan bahawa kanji dan gentian ubi kayu adalah stabil dari segi termal dengan titik pencairan masing-masing 172.87, 177.76 dan 169.23 °C bagi kanji, kulit dan hampas. Kajian terhadap permukaan morfologi menunjukkan bahawa kanji ubi kayu berbentuk bulat dan membujur, hampas berbentuk poligon dan kulti menunjukkan bentuk bulat dan poligon. Kandungan karbohidrat dalam kanji adalah didapati sebanyak 86.47 g / 100g. Ia memperuntukkan bahawa kulit ubi kayu dan hampas mengandungi kepekatan kandungan hemiselulosa yang tinggi iaitu 23.38 dan 29.26% masing-masing. Ianya boleh disimpulkan bahawa, kanji ubi kayu dan serat adalah sesuai untuk membangunkan bahan dengan ciri-ciri mekanikal dan haba yang boleh diterima untuk pelbagai aplikasi seperti pembungkusan, automotif dan agro-industri.



Fasa kedua melibatkan penyiasatan kesan bahan pemplastik (fruktosa, urea, glykol Tri-etilena dan Triethanolamine) dengan kepekatan yang berbeza pada sifat-sifat fizikal, haba dan mekanikal filem berasaskan kanji ubi kayu. Kandungan lembapan, kelarutan air dan penyerapan air filem meningkat dengan peningkatan kandungan bahan pemplastik. Filem yang menggunakan pemplastik fruktosa menunjukkan rintangan air yang cemerlang berbanding pemplastik lain. Filem yang menggunakan 30% fruktosa menunjukkan ketumpatan paling tinggi ( $1.74 \text{ g / cm}^3$ ), kandungan air yang paling rendah (10.96%) dan penyerapan air yang paling rendah (110%). Filem yang mengandungi fruktosa menunjukkan permukaan yang licin tanpa liang. Kehabluran relatif menurun dengan peningkatan kandungan pemplastik. Filem yang mengandungi 30% fruktosa menunjukkan kehabluran relatif yang lebih tinggi (0.31). Filem yang mengandungi 30% fruktosa menunjukkan kekuatan tegangan tertinggi (4.7 MPa) dan modulus tegangan tertinggi (69 MPa). Oleh itu, fruktosa adalah ejen pemplastik yang paling berkesan di kalangan pelbagai pemplastik yang digunakan dalam kajian ini.

Fasa ketiga memberi tumpuan kepada kegunaan kulit ubi kayu dengan dua saiz zarah yang berbeza sebagai pengisi semula jadi untuk termoplastik kanji (TPS) berdasarkan kanji ubi kayu. Penambahan kulit menghasilkan peningkatan dalam ketebalan, kandungan air dan penyerapan air filem sambil mengurangkan ketumpatan dan keterlarutan air. Selain itu, imbasan mikroskop elektron menunjukkan bahawa filem-filem yang mengandungi kulit bersaiz kecil mempunyai struktur padat yang lebih baik dan permukaan yang homogen tanpa liang. Penambahan 6% kulit meningkatkan modulus elastik dan tegangan sehingga 449.74 dan 9.62 MPa, masing-masing, ini menjadi agen pengukuhan yang paling berkesan. Selain itu, perubahan suhu untuk parameter dinamik-mekanik komposit kanji/kulit ubi kayu disiasat menggunakan ujian DMA. Diperhatikan bahawa penambahan kulit meningkatkan kekuatan tegangan dan modulus. Kesimpulannya, filem komposit kanji/kulit ubi kayu adalah sesuai untuk pelbagai tujuan seperti pembungkusan, automotif dan agro-industri, pada kos yang lebih rendah.

Fasa keempat filem komposit berasaskan kanji ubi kayu telah disediakan dengan menggunakan sisa bergentian dari pengestrakan kanji (hampas ubi kayu) sebagai pengisi. Filem komposit telah disediakan melalui teknik penuangan dengan menggunakan fruktosa sebagai pemplastik dan hampas dengan pelbagai saiz dan kepekatan. Saiz dan kepekatan hampas telah memberikan kesan yang signifikan terhadap sifat fizikal. Ianya menambahkan ketebalan, keterlarutan air, dan juga penyerapan air. Ia juga mengurangkan kandungan air dan ketumpatan filem. Walau bagaimanapun, tiada kesan signifikan penambahan hampas kepada sifat termal. Kajian XRD menunjukkan penambahan kehabluran komposit dengan penambahan kandungan gentian. Mikrograf SEM menunjukkan bahawa filem dengan saiz hampas yang kecil mempunyai struktur padat yang lebih baik dan permukaan homogenan. Modulus dan kekuatan tegangan maksimum filem komposit telah meningkat daripada 69.03 kepada 581.68 MPa dan 4.7 kepada 10.78 MPa, masing-masing, dengan penambahan sebanyak 6% hampas, menunjukkan ianya sebagai ejen pengukuhan yang paling berkesan kerana sifat-sifat yang fizikal dan mekanikal yang bagus.



Untuk fasa terakhir, komposit hibrid telah berjaya disediakan dengan jumlah gentian yang berbeza, komposit hibrid (6% w / w kanji kering) mengandungi hampas ubi kayu dan (0, 2, 4, 6 dan 8% w / w kanji kering) gentian enau. Spesimen telah disediakan melalui teknik penuangan dengan menggunakan fruktosa sebagai pemplastik untuk kanji ubi kayu. Penambahan SPF telah memberikan pengaruh yang signifikan terhadap sifat fizikal. Ianya meningkatkan ketebalan di samping menurunkan ketumpatan, kandungan air, keterlarutan air dan penyerapan air untuk filem. Selain itu, kajian XRD menunjukkan peningkatan kehabluran komposit dengan penambahan kandungan gentian. Sifat mekanik filem telah ditingkatkan dengan penambahan gentian. Penggabungan SPF telah meningkatkan penghabluran relatif sehingga to 47%, berbanding 32% bagi filem CS. Nilai kebolehtelapan air (WVP) telah berkurangan dengan peningkatan kandungan gentian. Modulus dan kekuatan tegangan maksimum filem telah meningkat daripada 69.03 kepada 1114.6 MPa dan 4.7 kepada 20.72 MPa, masing-masing untuk filem mengandungi 6% CB dan 6% SPF, ini menjadikan ianya sebagai agen pengukuhan yang paling berkesan. Seterusnya, sifat dinamik-mekanikal bagi komposit hibrid telah dikaji menggunakan ujian DMA. Telah diperhatikan bahawa penggabungan SPF telah meningkatkan nilai modulus penstoran ( $E'$ ) daripada 0.457 GPa bagi CS kepada 1.490 GPa bagi filem komposit hibrid CS-CB/SPF8. Sebagai kesimpulan, filem komposit hibrid CS diperkuat CB/SPF adalah sesuai untuk pelbagai tujuan seperti pempakejan, automotif dan kegunaan industri agro pada kos yang rendah.

## ACKNOWLEDGEMENTS

First of all, I would like to thank Allah (SWT), who gave me the guidance and the ability to fulfil my research.

Secondly, I am really very thankful to Prof Mohd Sapuan Salit, the main supervisor of my PhD research. I would like to thank him for letting me do this work in such topic, actually he has never hesitated to help me during this period and gave me useful advices.

I would like also to thank Dr. Mohammad Jawaid, Dr. Nur Ismarrubie Zahri, All lecturers and staff in faculty of engineering and INTROP, University Putra Malaysia (UPM), and all friends for their cooperation and encouragement.

I owe a special thanks to my mother (Nuzha) and father (Faraj Edhirej) for their love, encouragement and sincere supplications from childhood to date. I doubt that I will ever be capable of conveying my appreciation fully, but I owe them an eternal gratitude. Thanks to my brothers, sisters, friends and colleagues for their constant moral support. At this moment of accomplishment, I sincerely owe a great deal of invaluable appreciation to my dear wife for her unimpeachable moral support and personal attention which have provided an excellent and smooth basis for accomplishing this tedious work. Words are short to express my deepest sense of gratitude towards her. My sons (Mohammed & Faraj) and daughters (Nuzha, Nour & Duaa) deserve special attention here for providing a stimulating and fun filled atmosphere.

Finally, my thanks go to all those people who knowingly or unknowingly helped me in the successful completion of this work such as the likes of Dr. Muhammed Lamin Sanyang, Dr. Munir Faraj Al Kabir and Ridhwan Jumaidin (PhD student, Malaysian) and many others.

Jazakum Allahu Khairan!

**Ahmed**

I certify that a Thesis Examination Committee has met on 19 June 2017 to conduct the final examination of Ahmed Faraj Ibrahim Hissen Edhirej on his thesis entitled "Characterization and Development of Cassava (*Manihot esculenta* Crantz)/Sugar Palm (*Arenga pinnata* (Wurmb) Merr.) Fiber-Reinforced Cassava Starch Hybrid Composites" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

**B.T. Hang Tuah bin Baharudin, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Mohamad Ridzwan bin Ishak, PhD**

Senior Lecturer  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Edi Syams bin Zainudin, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Parvez Alam, PhD**

Professor  
Åbo Akademi University  
Finland  
(External Examiner)



---

**NOR AINI AB. SHUKOR, PhD**

Professor and Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 28 December 2017

This thesis was submitted to the Senate of the Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

**Mohd Sapuan Salit, PhD**

Professor Ir  
Faculty of Engineering  
University Putra Malaysia  
(Chairman)

**Mohammad Jawaid, PhD**

Senior Lecturer  
Institute of Tropical Forestry and Forest Products. INTROP  
University Putra Malaysia  
(Member)

**Nur Ismarrubie Zahari, PhD**

Associate Professor  
Faculty of Engineering  
University Putra Malaysia  
(Member)

**ROBIAH BINTI YUNUS, PhD**

Professor and Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:

## Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software

Signature: \_\_\_\_\_ Date: \_\_\_\_\_

Name and Matric No.: Ahmed Faraj Ibrahim Hissen Edhirej, GS 40330

## Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) were adhered to.

Signature: \_\_\_\_\_  
Name of Chairman  
of Supervisory  
Committee: Professor Dr. Mohd Sapuan Salit

Signature: \_\_\_\_\_  
Name of Member  
of Supervisory  
Committee: Dr. Mohammad Jawaid

Signature: \_\_\_\_\_  
Name of Member  
of Supervisory  
Committee: Associate Professor Dr. Nur Ismarrubie Zahari

## TABLE OF CONTENTS

	<b>Page</b>
<b>ABSTRACT</b>	i
<b>ABSTRAK</b>	iv
<b>ACKNOWLEDGEMENTS</b>	vii
<b>APPROVAL</b>	viii
<b>DECLARATION</b>	x
<b>LIST OF TABLES</b>	xvi
<b>LIST OF FIGURES</b>	xviii
<b>LIST OF ABBREVIATIONS</b>	xxii
<b>CHAPTER</b>	
<b>1 INTRODUCTION</b>	<b>1</b>
1.1 Overview	1
1.2 Problem Statements	4
1.3 Research Objectives	5
1.4 Significance of Study	5
1.5 Scope and Limitation of Study	6
1.6 Structure of the thesis	6
<b>2 LITERATURE REVIEW</b>	<b>9</b>
2.1 Introduction	9
2.2 Cassava Plant	10
2.2.1 History of Cassava ( <i>Manihot esculenta</i> )	10
2.2.2 Cassava Plant Parts	10
2.2.3 Cassava Application	11
2.3 Bio-products from Cassava	13
2.3.1 Cassava Fiber	15
2.3.1.1 Cassava Bagasse	15
2.3.1.2 Cassava Peels	16
2.3.2 Cassava Polymer	17
2.3.2.1 Cassava Starch	17
2.4 Treatment of Cassava Composites	21
2.4.1 Chemical Treatment	21
2.4.2 Thermal Treatment	23
2.5 Cassava Composites	24
2.6 Properties of Cassava Film	28
2.6.1 Physical Properties of Cassava Film	28
2.6.2 Mechanical Properties of Cassava Film	28
2.7 Cassava Hybrid	29
2.8 Cassava composite application	30
2.9 Sugar palm plant	32
2.9.1 History of sugar palm ( <i>Arenga pinnata</i> )	32
2.9.2 Sugar palm fiber (SPF)	32
2.9.3 Sugar palm fiber composites	33



2.9.4	Properties enhancement of sugar palm fiber composites	34
2.9.5	Application of SPF composites	34
2.10	Conclusion	35
<b>3</b>	<b>METHODOLOGY</b>	<b>36</b>
3.1	Introduction	36
3.2	Extract of starch	37
3.3	Preparation of cassava fibers (peel and bagasse)	37
3.4	Characterization of Cassava starch, Peel and Bagasse	38
3.4.1	Chemical Composition	38
3.4.2	Physical properties	38
3.4.3	Thermal properties	40
3.4.4	Scanning electron microscopy (SEM)	41
3.4.5	Structural properties	42
3.5	Film preparation and characterization	44
3.5.1	Physical properties of films	46
3.5.2	Thermal properties of films	49
3.5.3	Structural properties of films	49
3.5.4	Tensile properties of films	50
3.5.5	Dynamic Mechanical analysis (DMA)	51
<b>4</b>	<b>EXTRACTION OF MALAYSIAN CASSAVA STARCH, PEEL, BAGASSE AND ITS CHARACTERIZATION</b>	<b>52</b>
4.1	Introduction	53
4.2	Materials and Methods	54
4.2.1	Materials	54
4.2.2	Extraction process	54
4.3	Characterization of Cassava starch, Peel and Bagasse	55
4.3.1	Chemical Composition	55
4.3.2	Physical properties	56
4.3.3	Thermal properties	57
4.3.4	Scanning electron microscopy (SEM)	57
4.3.5	Structural properties	57
4.4	Results and Discussion	58
4.4.1	Chemical composition of cassava starch, Peel and Bagasse	58
4.4.2	Physical properties	59
4.4.3	Thermal properties	61
4.4.4	Morphological properties	63
4.5	Conclusion	67
<b>5</b>	<b>EFFECT OF VARIOUS PLASTICIZERS AND CONCENTRATION ON THE PHYSICAL, THERMAL, MECHANICAL AND STRUCTURAL PROPERTIES OF CASSAVA STARCH BASED FILMS</b>	<b>69</b>
5.1	Introduction	70
5.2	Materials and methods	71
5.2.1	Materials	71
5.2.2	Film preparation and characterization	71

5.2.3	Physical properties	71
5.2.4	Thermal properties	73
5.2.5	Structural properties	73
5.2.6	Tensile Test	74
5.3	Results and discussion	74
5.3.1	Physical properties	74
5.3.1.1	Thickness and density	74
5.3.1.2	Moisture Content and Water Solubility	75
5.3.1.3	Water Absorption	76
5.3.2	Thermal properties	77
5.3.2.1	Differential scanning calorimetry (DSC)	77
5.3.2.2	Thermal Gravimetric Analyzer (TGA)	78
5.3.3	Structural properties	79
5.3.3.1	Scanning electron microscopy (SEM)	79
5.3.3.2	Fourier transform infrared (FT-IR) spectroscopy	80
5.3.3.3	X-ray diffraction (XRD)	82
5.3.4	Mechanical properties	84
5.4	Conclusion	86
<b>6</b>	<b>PREPARATION AND CHARACTERIZATION OF CASSAVA STARCH/PEEL COMPOSITE FILM</b>	<b>88</b>
6.1	Introduction	89
6.2	Materials and Method	90
6.2.1	Film preparation and characterization	90
6.3	Characterization	91
6.4	Results and discussion	94
6.4.1	Physical properties	94
6.4.2	Structural properties	101
6.4.3	Tensile properties	105
6.5	Conclusion	111
<b>7</b>	<b>PREPARATION AND CHARACTERIZATION OF CASSAVA BAGASSE REINFORCED HERMOPLASTIC CASSAVA STARCH</b>	<b>113</b>
7.1	Introduction	114
7.2	Materials and Methods	115
7.2.1	Materials	115
7.2.2	Film preparation and characterization	115
7.2.3	Physical properties	115
7.2.4	Morphological properties	117
7.2.5	Tensile properties	117
7.2.6	Structural properties	117
7.2.7	Thermal properties	118
7.3	Results and discussion	119
7.3.1	Physical properties	119
7.3.2	Scanning electron microscopy (SEM)	123
7.3.3	Tensile properties	123
7.3.4	Structural properties	126

7.3.5	Thermal properties	128
<b>8</b>	<b>CASSAVA/SUGAR PALM FIBER REINFORCED CASSAVA STARCH HYBRID COMPOSITES: PHYSICAL, THERMAL AND STRUCTURAL PROPERTIES</b>	134
8.1	Introduction	135
8.2	Materials and Method	136
8.2.1	Characterization of fibers	137
8.2.2	Film preparation and characterization	138
8.2.3	Characterization of films	139
8.2.3.1	Physical properties	139
8.2.3.2	Thermal Gravimetric Analysis (TGA)	140
8.2.3.3	Structural properties	141
8.3	Results and discussion	141
8.3.1	Chemical composition of fiber	141
8.3.2	Physical properties of films	144
8.3.3	Thermal properties of films	146
8.3.4	Structural properties of films	148
8.4	Conclusion	153
<b>9</b>	<b>TENSILE, BARRIER, DYNAMIC MECHANICAL AND BIODEGRADATION PROPERTIES OF CASSAVA/SUGAR PALM FIBER REINFORCED CASSAVA STARCH HYBRID COMPOSITES</b>	155
9.1	Introduction	156
9.2	Material and Method	157
9.2.1	Film preparation and characterization	157
9.2.2	Characterization of fibers	158
9.2.3	Characterization of films	159
9.3	Results and discussion	161
9.3.1	Properties of fibers	161
9.3.2	Properties of films	162
9.4	Conclusion	170
<b>10</b>	<b>CONCLUSIONS AND RECOMMENDATIONS</b>	172
10.1	Conclusions	172
10.2	Recommendations for future research	174
	<b>REFERENCES</b>	175
	<b>APPENDICES</b>	199
	<b>BIODATA OF STUDENT</b>	205
	<b>LIST OF PUBLICATIONS</b>	206

## LIST OF TABLES

Table		Page
2.1	Physico-chemical composition of cassava bagasse (g/100 g dry weight)	16
2.2	Chemical composition of cassava peels	17
2.3	Physico-chemical composition of cassava tubers (100 g basis)	20
2.4	Swelling power, solubility, gel hardness and Pasting properties of native and HMT cassava starches	21
2.5	Reported work cassava based composite	27
2.6	Moisture contents, Water solubility, Water vapor and Mechanical properties of cassava films, as a function of glycerol content	29
2.7	Chemical composition and mechanical properties of fibers from different parts of the sugar palm tree	33
2.8	Reported work sugar palm fibers-based composite	34
4.1	Chemical composition and physical properties A: cassava starch. B: cassava peel and cassava bagasse	59
4.2	Thermal degradation of Cassava Starch, Peel and Bagasse	62
5.1	Physical properties of cassava films incorporated with various plasticizer types and concentrations	75
5.2	DSC of cassava film with different plasticizers type and content	78
6.1	Compositions of TPS matrix based on cassava starch and its composites with different size and concentration of peel	91
6.2	Physical properties of cassava starch/peel composite film with different size and concentration of peel	95
6.3	Thermal properties (obtained by TGA and DTG analyses) of cassava starch/peel composite film with different size and concentration	101
6.4	The relative crystallinity of cassava starch/peel composite film with different size and concentration	105

6.5	DMA of cassava composite film, with different size and concentration of peel. A: Storage Modulus and B: Loss Modulus	110
7.1	physical properties of cassava starch/bagasse composite film with different size and concentration of bagasse	119
8.1	Compositions of TPS matrix based on cassava starch (CS film), its composites with cassava bagasse (CS/CB) and cassava bagasse/sugar palm fiber reinforced cassava starch hybrid composite (CS-CB/SPF)	139
8.2	Chemical composition and physical properties of cassava bagasse and sugar palm fiber.	143
8.3	Physical properties of CS film, CS/CB composite film and CS-CB/SPF hybrid composites films	145
8.4	Thermal properties (obtained by TGA and DTG analyses) of CS film, CS/CB composite film and CS-CB/SPF hybrid composites films	147
8.5	The relative crystallites (RC) of CS film, CS/CB composite film and CS-CB/SPF hybrid composites films	153
9.1	Compositions of TPS matrix based on cassava starch, its composites cassava bagasse and cassava bagasse/sugar palm fiber reinforced cassava starch hybrid composite	158
9.2	Chemical composition and physical properties of cassava bagasse and sugar palm fiber	162
9.3	WVP of CS film, CS/CB composite film and CS-CB/SPF hybrid composite film with different SPF loading	169

## LIST OF FIGURES

Figure		Page
2.1	Cassava plant ( <i>Manihot Esculenta</i> Crantz)	11
2.2	Flow chart for production of cassava starch	19
2.3	Show the effect of treatment on mechanical properties	23
2.4	Extrusion of cassava foam	30
2.5	Starch foam: (a) Pesika Naturpack GmbH; (b) Suedstraerke GmbH	31
2.6	Illustrative picture of cassava starch edible film (blend of 1.0 g of glycerol; 0.3 g of glutaraldehyde; 0.3 g of polyethylene glycol)	31
2.7	Film production by extrusion: (a) acquisition of pellets and (b) formation of tubular film	32
3.1	Flow process of the methodology	36
3.2	Cassava root and its product. A: cassava root. B: cassava peel. C: cassava bagasse. D: cassava starch. E: grinded peel. F: grinded bagasse. G: cassava starch	37
3.3	Gas Pycnometer	39
3.4	Differential Scanning Calorimetry (DSC)	40
3.5	Thermal Gravimetric Analyzer (TGA)	41
3.6	Scanning Electron Microscopy (SEM)	42
3.7	Fourier Transform Infrared Spectroscopy (FTIR)	42
3.8	X-Ray Diffractometer (XRD)	43
3.9	Flow process of solution casting	45
3.10	Hot Water Bath	46
3.11	Desiccator with vacuum pump	46
3.12	Tensile test in progress	50
3.13	Dynamic Mechanical Analyzer (DMA)	51

4.1	Photographs of cassava root and its product. A: cassava root. B: peeled root. C: grated root with water. D: cassava starch. E: cassava peel. F: cassava bagasse	55
4.2	Particle size distribution of (A) cassava starch, (B) Bagasse and (C) Peel	60
4.3	(A) TGA and (B) DTG curves of cassava starch, peel and bagasse	62
4.4	Differential scanning calorimetry traces showing the peak temperature, onset temperature and gelatinization enthalpy of cassava starch, peel and bagasse	63
4.5	Scanning electron micrographs of Cassava starch (A&B), Bagasse (C&D) and Peel (E&F)	64
4.6	FTIR spectra of cassava starch, peel and bagasse	65
4.7	X-ray diffractogram of cassava starch, peel, bagasse and its relative crystallinity	67
5.1	Water Absorption of cassava films with different plasticizers type and content	77
5.2	TGA of cassava film with different plasticizers type and content	79
5.3	SEM micrographs of cassava film with different plasticizers type and content	80
5.4	FTIR spectra of cassava film with different plasticizers type and content	82
5.5	XRD of cassava film with different plasticizers type and content. RC is relative crystallinity	83
5.6	Mechanical properties of cassava film with different plasticizers type and content	85
6.1	Water holding capacity of cassava starch/peel composite film with different size and concentration of peel	97
6.2	The biodegradability of cassava starch/peel composite film with different size and concentration of peel	98
6.3	Thermogram (a) TGA curves and (b) DTG curves of TPS matrix and its composites with different size and concentration of cassava peel	100



6.4	SEM of cassava starch/peel composite film with different size and concentration of peel	102
6.5	FTIR curves of cassava starch/peel composite film with different size and concentration of peel	103
6.6	XRD curves of cassava starch/peel composite film with different size and concentration of peel	105
6.7	Tensile properties of cassava starch/peel composite film with different size and concentration of peel	108
6.8	DMA of cassava composite film, with different size and concentration of peel. A: Storage Modulus and B: Loss Modulus	110
7.1	Water absorption of cassava starch/bagasse composite film with different size and concentration of bagasse	121
7.2	The biodegradability of CS/CB composite film with different size and concentration of bagasse	122
7.3	SEM of cassava starch/bagasse composite film with different size and concentration of bagasse	123
7.4	Tensile properties of cassava starch/bagasse composite film with different size and concentration of bagasse	125
7.5	XRD curves of cassava starch/bagasse composite film with different size and concentration of bagasse. RC is relative crystallinity	126
7.6	FTIR of cassava starch/bagasse composite film with different size and concentration of bagasse	127
7.7	TGA of cassava starch/bagasse composite film with different size and concentration of bagasse	129
7.8	DMA of cassava composite film, with different size and concentration of bagasse. A: Storage Modulus and B: Loss Modulus	131
8.1	X-ray diffractogram of cassava bagasse (CB) and sugar palm fiber (SPF)	143
8.2	Water absorption of CS film (control), CS/CB composite film (0%) and CB/SPF reinforced CS hybrid composites films	146

8.3	Thermogram (A) TGA curves and (B) DTG curves of CS film (control), CS/CB composite film (0%) and CB/SPF reinforced CS hybrid composites films	148
8.4	SEM of A: CS film, B: CS/CB composite film and C-F: CS-CB/SPF hybrid composites films	150
8.5	FTIR spectra of TPS matrix, CS/CB bio-composites and CB/SPF reinforced CS with different sugar palm fibers loading	151
8.6	XRD curves of CS film (control), CS/CB composite film (0%) and CB/SPF reinforced CS hybrid composites films	152
9.1	Tensile properties of CS film, CS/CB composite film and CS-CB/SPF hybrid composite film with different SPF loading. A: tensile strength, B: modulus and C: elongation at break	164
9.2	Figure 9.2: DMA properties of CS film, CS/CB composite film and CS-CB/SPF hybrid composite film with different SPF loading. A: Storage modulus, B: Loss modulus	167
9.3	Degradation properties of CS/CB composite film and CS-CB/SPF hybrid composite film with different SPF loading	168

## LIST OF ABBREVIATIONS

CB	Cassava Bagasse
CP	Cassava Peel
CS	Cassava Starch
DMA	Dynamic mechanical analysis
DSC	Differential scanning calorimetry
DTG	Derivative thermogravimetry
E	Elongation at break
F	Fructose
FTIR	Fourier transform infrared
RC	Relative Crystallinity
SEM	Scanning electron microscope
SPF	Sugar Palm Fiber
TEA	Tri-Ethanol-Amine
TEG	Tri-Ethylene Glycol
TGA	Thermal-gravimetric analysis
TM	Tensile modulus
TPS	Thermoplastic starch
TS	Tensile strength
U	Urea
WA	Water Absorption
WC	Water Content
WS	Water Solubility

WVP

Water Vapor

XRD

X-Ray Diffraction



© COPYRIGHT UPM

# CHAPTER 1

## INTRODUCTION

### 1.1 Overview

Plastics produced from fossil sources have contributed significantly to environmental pollution caused by the accumulation of non-biodegradable solid waste in landfills. This significant problem has prompted a search for new biodegradable materials, not only in the food industry, but also in the medical, automotive, among others. Renewable natural raw materials including flour, starch, natural fibers, proteins, and others become an important alternatives and prominent in developing bioplastics (Tharanathan, 2003). Currently, there is growing interest in using raw materials and agricultural by-products such as from corn, cassava and potato tubers in biodegradable plastics. However, plastics developed from these sources have certain drawbacks of structural stability caused by its stiffness or weakness due to its high hygroscopicity and rapid aging when compared to conventional plastics (Villada, 2005). Therefore, research efforts must be maintained and increased in this field, with the use of local products such as cassava, which is studied in this, and other research projects. These studies intended that the methodology produce functional, applicable, and specific biodegradable plastics, which are reproducible on an industrial scale.

Cassava is a starchy root belonging to the Euphorbiaceae family and is one of the most important energy sources for tropical areas of the world. Although cassava thrives in fertile soil, its comparative advantage to other more profitable crops is their ability to grow in acidic soils of low fertility, with sporadic rainfall or long periods of drought. The crop is widely adapted as it has been planted successfully from sea level up to 1800 meters, at temperatures between 20 and 30°C with an optimum of 24°C, relative humidity between 50 and 90% with an optimum of 72% and an annual rainfall between 600 and 3000 mm with an optimum of 1500 mm (Navia and Villada, 2012). It is widely cultivated in tropical Africa, Asia and Latin America, and it is the fourth most important global crop in developing countries, with an estimated production in 2006 of 2.6 million tons. It is characterized by great diversity of uses both roots and leaves, which can be eaten by humans and animals. Cassava starch products can be used in many industries (Ceballos, 2002). Therefore, one way to extend the value of harvested cassava and improve rural economies is to process excess cassava for starch production. Its production and its byproducts provide an opportunity to develop value-added products for both food and industrial uses that will benefit rural communities. Cassava pulp or bagasse is a byproduct of starch production. Cassava bagasse contains 50–60% residual starch (dry wt basis). It may be dried in the sun and used as filler in cattle feed (Panichnumsin et al., 2010; Sriroth et al., 1999). However, much of the bagasse is simply discarded as a wasted resource (Panichnumsin et al., 2010). In recent years, the use of natural fibers as reinforcing materials in polymers and composites has attracted much attention. Compared to inorganic fillers, the main advantages of lignocellulosics are their renewable nature, biodegradability, low energy consumption, wide variety available throughout the world, low cost and density, as well as high

specific strength and modulus (Bodirlau et al., 2013; Castillo et al., 2013; Gilfillan et al., 2012). Furthermore, they present high sound attenuation, and comparatively easy processing due to their flexibility and non-abrasive nature which allow high filling levels (Al-Oqla and Sapuan, 2014).

A study by Aripin et al. (2013) focused on the determination of the cassava peel potential to act as an alternative for fiber in paper and pulp with respect to the chemical properties. According to the results, there are lower amount of cellulose and holo-cellulose in cassava peels. However, these peels are rich in hemicellulose. Hence, we can conclude that there are significant parameters present in cassava peels, which can be effective as a fiber alternative for bio-composite and industries application. These industries can favor recyclable materials in the future, thereby reducing the environmental problems (Aripin et al., 2013). The cassava root is a rich source of starch, also containing proteins, lipids, fibers and sugars such as glucose, sucrose and fructose. Interest in biodegradable films development from renewable sources is growing due to increased environmental awareness. Among natural polymers, starch has been considered as one of the most promising materials because of its attractive combination of availability, price and performance (Abdillahi et al., 2013). Cassava is an important starch source in some countries like Brazil, Thailand, Malaysia, Indonesia and some regions of Africa. Currently there is growing interest to use raw materials and agricultural by-products from plants such as corn, cassava and potato tubers for biodegradable plastics. However, plastics developed from these sources have certain drawbacks caused by stiffness or weakness due to its high hygroscopicity and rapid aging which affect structural stability when compared to conventional plastics (Villada, 2005). Renewable, natural, raw materials including flour, starch, natural fibers, proteins, and others prominent alternative in developing options for bioplastics (Tharanathan, 2003). However, starch-based materials are brittle with poor mechanical characteristics. Thus, the incorporation of a plasticizer is required to overcome the brittleness of these materials. The principle function of plasticizers is to reduce inter- molecular forces and increase the mobility of polymer chains, which help to decrease the glass transition temperature ( $T_g$ ) of plasticized starch materials, as well as, improve their flexibility. (Forssell et al., 1999; Garcia et al., 2000; Sanyang et al., 2015a; Sanyang et al., 2015c).

Recently, many studies have focused on the use of glycerol (Alves et al., 2007; Bergo et al., 2008; Fadeyibi et al., 2014; Jouki et al., 2013; Souza et al., 2012; Versino and García, 2014; Versino et al., 2015a), urea (Cao et al., 2009; Ma et al., 2006; Ma et al., 2005b; Wang et al., 2014), sorbitol (Kristo and Biliaderis, 2006; Mantzari et al., 2010; Müller et al., 2008), Fructose, glucose and sucrose (Galdeano et al., 2009; Veiga-Santos et al., 2007; Zhang and Han, 2006), xylitol (Fishman et al., 2000; Zhang and Han, 2006) as well as Triethelenglycol and Triethanolamin (Audic and Chaufer, 2005; Cao et al., 2009) as plasticizers of edible and/or biodegradable films. The proportion of plasticizer and its chemical nature influence the physical properties of the processed starch in two ways, viz. (i) by controlling its destructure and depolymerization and (ii) by affecting the final properties of the material, such as its glass transition temperature and modulus. Since starch is attributed to offer a favorable combination



of cost, availability and performance, it is considered to be very effective and valuable when compared to other polymers (Abdillahi et al., 2013).

The role of plasticizers is to enhance the flexibility and processability of starch by reducing the strong intermolecular interactions between starch molecules (Aguirre et al., 2013; Zhong and Li, 2014). As a result, the mobility of polymeric chains increases, which improves flexibility, extensibility and ductility of the plasticized films (Aguirre et al., 2013; Zhong and Li, 2014). Cassava starch like most other biopolymers is hydrophilic in nature due to either their hydroxyl or polar groups. The major challenges for the development of starches as packaging films are their shortcomings related to brittleness, processability, high moisture sensitivity, poor mechanical and barrier properties. The addition of plasticizers to starch films helps to decrease its inherent brittleness by reducing intermolecular forces, increasing the mobility of polymer chains, decreasing the glass transition temperature of these materials and improving their flexibility. The plasticizers must be compatible with the film-forming polymers. Hydrophilic compounds, such as polyols (glycerol and sorbitol) are commonly used in starch film, but sugars, amino acids and fatty acids could also be employed (Galdeano et al., 2009; Petersson and Stading, 2005).

The by-products from the sugar palm tree include foods and beverages, biopolymer, biocomposites, and timber. The sugar palm tree is a member of the Palmae family and naturally a forest species (Siregar, 2005) and it is considered as one of the most diverse multi-purpose trees (Sahari et al., 2012). Almost all parts of the tree can be used, such as the trunk, which provides important local products like sago, vinegar, fresh juice and palm sugar, which can be obtained from this versatile palm tree (Ishak, 2009). Traditionally, the sugar palm fiber has been used in various applications such as in brooms, rope, paintbrushes and roofs. More recently, the incorporation of several different types of fibers into a single matrix has led to the development of hybrid biocomposites. The behavior of hybrid composites is a weighed sum of the individual components, in which there is a more favorable balance between the inherent advantages and disadvantages. By combining sugar palm fiber with another fiber or using a hybrid composite that contains two or more types of fiber, the advantages of one type of fiber could complement with what are lacking in the other. As a result, a balance in cost and performance could be achieved through proper material design (Thwe and Liao, 2003). The properties of a hybrid composite mainly depend upon the fiber content, orientation, extent of intermingling of fibers, fiber to matrix bonding and arrangement of both the fibers. Ishak et al. (2011) have conducted a characterization study on the thermal and tensile properties of sugar palm fibers. In their studies, they found that the green fiber (matured fibers) from the plant give the greatest tensile results because of the optimum chemical composition, which consisted of high cellulose along with a hemicelluloses and lignin content (Ishak et al., 2012)



## 1.2 Problem Statements

Plastics have already substituted many traditional materials, such as wood, stone, leather, metal and ceramic various applications such as packaging, automotive and agro-industrial due to its good performances. Petroleum resources are the only major mineral commodities where many parties fear that their depletion will cause significant scarcities over the decades to come. Besides that, landfill sites are limited and plastics show to breakdown causing mountains of wastes in landfill. There are two approaches to solve this problem: incineration and recycling. Incineration of the plastic wastes produces large amount of carbon dioxide contributing to global warming, and sometimes produces toxic gases, which again contribute to global pollution. On the other hand, recycling is so expensive because it requires more labor and energy for removing of plastics wastes. Plastics must be separated according to the types of plastics, washed, dried, grinded and reprocessed to final product. For these reasons, raw materials that come from sustainable sources are now being considered as an alternative to the existing petroleum based polymers. Among natural polymers, starch has been considered as one of the most promising materials because of its attractive combination of availability, price and performance (Abdillahi et al., 2013; Lopez et al., 2014; Mohanty et al., 2013). Cassava was chosen due to its excellent properties including high purity level, excellent thickening characteristics, abundance, availability, and low cost, and it contains a high concentration of starch. However, starch-based materials are known to be brittle, with poor mechanical properties. Thus, the incorporation of a plasticizer is required to overcome the brittleness of these materials. In this study the effect of various plasticizers and concentration on the properties of thermoplastic cassava starch film have been studied.

Glycerol is most common type of plasticizer, but it did not give the best results when compare to other plasticizer molecules. Different plasticizers were chosen to optimize the most efficient plasticizer type and concentration. Among plasticizers used in this study, fructose provided higher tensile strength and modulus. The efficacy of plasticization is dependent on the molecular weight of the plasticizer since the smaller the molecule weight, the greater the plasticization effect of the plasticizer upon the polymer matrix. Among the samples tested, films plasticized by Tri-Ethylene Glycol exhibited the highest moisture content, followed by samples plasticized by Urea and Tri-Ethanol-Amine. In comparison, the fructose-plasticized films showed the lowest moisture content. This observation can be attributed to the different molecular weight and molecular structure of these plasticizers. The smaller molecule plasticizers such as Glycerol can be easily inserted between polymer chains when compared to larger plasticizer molecules such as fructose, which interrupts the formation of polymer–polymer hydrogen bonds. Even though synthetic fibers are very useful in composite materials and extensively used due to their excellent mechanical, barrier and thermal properties, there are not biodegradable and causes negative effect to the environment. The issues of climate changes and global warming due to pollution and the activity of de-forestation becomes the major reason to use agriculture by-product. The incorporation of cassava peel and bagasse as reinforcement agents in starch based materials aims to enhance their final properties. Hence, matrix-filler compatibility expected, due to their similar chemical nature. Which increased overall strength.

Although this bio-composites exhibited acceptable properties, it still has poor water resistance. To overcome this problem, hybridization the CB with lower hydrophilic natural fiber, the natural fiber that known for their high durability and resistance to water is sugar palm fiber. In term of cost, synthetic fibers are much costly when compared to natural fibers. For these reasons, enormous efforts, time and money have been spent on research to discover a new green material that can replace synthetic fibers. Several studies have shown that sugar palm fibers have great potential to be used as reinforcement in many composite applications. Sugar palm fibers have some advantages over traditional reinforcement fiber materials in terms of cost, density, being renewable, non-toxic, abrasiveness and biodegradability. (Leman et al., 2008b). This task is easier because many of the typical applications of these composites do not require excellent mechanical properties, such as some packaging, gardening items, etc. (Kim et al., 2005). In addition, synthetic fiber has negative effects on human health especially to the skin and eye. More seriously, inhalation of synthetic fibers can cause long term or deadly effects such as lung cancer (Ishak, 2009).

### **1.3 Research Objectives**

The objectives of this research are as follows:

1. Extraction and characterization of starch and fibre (peel and bagasse) from cassava root planted in Malaysia and exploring their potential to be used in the development of bio-composites.
2. Investigate the effect of various plasticizers type and concentration on physical, thermal, mechanical and structural properties of cassava starch based films.
3. Development and characterization of cassava fiber (peel/bagasse) reinforced cassava starch composites at different fiber loading.
4. Development and characterization of cassava/sugar palm fiber reinforced cassava starch hybrid composite at different SPF loading.

### **1.4 Significance of Study**

The significance of this study is to utilize the cassava starch and its byproduct (peel and bagasse) as a replacement for more harmful non-natural composite product. This natural material is an important material in developing the biocomposites products, alone or combined with another material, to produce green composites. The advantages of natural fibers, such as their low cost, low density, abundance, sustainability, recyclability and biodegradability, make them an interesting and necessary research area. The earth needs biocomposites that are low in cost to produce, renewable, biodegradable and environmentally friendly. Replacing petroleum based polymers with the thermoplastic starch may reduce petroleum based polymer production and hence minimise the negative health effects generated from it and reduce the dependence on the petroleum products. During the last decade, natural fibres have attracted the attention of scientists and researchers because of the natural fiber's advantages over conventional reinforcing materials. One of the natural fibres

widely available is sugar palm fibres. Although the SPF is currently used for the traditional application such as ropes, this research can also help to solve the problem of handling by-product from the sugar palm tree. It also plays an important role in the economic life of poor rural people by increasing their income and employment (Ishak et al., 2013; Moge et al., 1991). Limited studies have been reported relating to natural fiber development as a green packaging material. Utilization of CP, CB and SPF, thus, may contribute to solve the waste problem and, at the same time, enhance economic development through a waste to wealth transformation. Moreover, this research would help to evaluate a new hybrid composite based on natural resources that come from the waste of cassava and sugar palm plants and turn them into the new valuable green products.

### **1.5 Scope and Limitation of Study**

The scope of this research is to study the potential of using a cassava starch and its by-product as bio-composites. The CS was extracted from cassava tuber planted in Malaysia and cassava fibers (peel and bagasse) were obtained from the same process. The physical, morphological and thermal properties of CS, CP and CB along with their chemical composition were studied. The effect of different plasticizers type (F, TEA, U and TEG) with concentration of 30, 45 and 60 % w/w dry starch, on the physical, thermal, tensile and structural properties of cassava starch based-film were investigated. The selection of combination was mainly based on physical and tensile properties. Then, the optimum combination of plasticized CS was used to reinforce CB and CP with different fiber loadings. Two different particle size and different fiber loadings were prepared at 3, 6 and 9 % w/w dry starch by using a casting technique. Then, the best combination of composite film among the different fiber type (peel and bagasse) and loading was selected based on the physical and tensile properties which was supported by thermal and structural properties. The selected composite films were hybrid with sugar palm fiber (SPF) in different concentration (2, 4, 6 and 8 % w/w dry starch). These specimens were tested for their mechanical and thermal properties through a tensile and thermogravimetric analysis (TGA). The use of other investigation techniques such as XRD, FTIR and SEM were used to support the results of mechanical properties. Finally, the CS-CB/SPF hybrid composites were submitted to WVP and a biodegradation test to investigate their environmental effect.

### **1.6 Structure of the thesis**

The thesis layout is in accordance with Universiti Putra Malaysia alternative thesis format based on publications, in which each research chapter (4 – 9) represent a separate study that has its own: ‘Introduction’, ‘Materials and methods’, ‘Results and discussion’, and ‘Conclusion’. The details of the thesis structure are presented below.

## **Chapter 1**

The problems statement and the research objectives were clearly highlighted in this chapter. In addition, the significant contribution and scope of study were also illustrated within the chapter.

## **Chapter 2**

A comprehensive literature review on essential areas connected to the topic of this thesis was presented in this chapter.

## **Chapter 3**

This methodology chapter covers every single activity related in this research; from the beginning of material preparing to material processing, testing and results analysis are detailed in this section

## **Chapter 4**

This chapter presents the article entitled “Extraction of Malaysian Cassava Starch. Peel and Bagasse and Its Characterization”. In this article, the study of the physical, morphological and thermal properties of cassava starch, peel and bagasse obtained from Malaysian plant along with their Chemical Composition was accomplished.

## **Chapter 5**

This chapter presented the second article entitled ‘Effect of Various Plasticizers and Concentration on The Physical, Thermal, Mechanical and Structural Properties of Cassava Starch Based Films’. In this article, the effect of four different plasticizer type (Fructose, Urea, Tri-ethyleneglycol and Triethanolamine) and different concentrations (30, 45 and 60%) on the properties of cassava starch films was investigated.

## **Chapter 6**

In this chapter, the article entitled ‘Preparation and Characterization of Cassava Starch/Peel Composite Films’ is presented. This article focused on the use cassava peel with two different particle size as a natural filler for thermoplastic starch (TPS) based on the cassava starch.

## **Chapter 7**

This chapter is focused on a work entitled 'Preparation and Characterization of Cassava Bagasse Reinforced Thermoplastic Cassava Starch'. This article studied the effect of various loading of cassava bagasse with two different particle size on the properties of thermoplastic cassava starch.

## **Chapter 8**

This chapter presents the fifth article entitled 'Cassava/Sugar Palm Fiber Reinforced Cassava Starch Hybrid Composite: Physical, Thermal and Structural Properties'. The hybrid composites were successfully prepared, contains (6% dry starch) CB and (0, 2, 4, 6 and 8 % dry starch) SPF. The effect of the addition of SPF on the Physical, Thermal and Structural Properties of hybrid composites films was investigated.

## **Chapter 9**

This chapter presents the last article entitled 'Tensile, Barrier, Dynamic Mechanical and Biodegradation Properties of Cassava/Sugar Palm Fiber Reinforced Cassava Starch Hybrid Composites'. The effect of the incorporation of sugar palm fiber on the Tensile, Barrier, Dynamic Mechanical and Biodegradation Properties was carried out in this chapter.

## **Chapter 10**

Finally, the overall conclusions from the various research articles as well as relevant suggestions for future research were presented in this chapter.



## REFERENCES

- Abdallah, M., Zitoune, R., Collombet, F., & Bezzazi, B. (2010). Study of mechanical and thermomechanical properties of jute/epoxy composite laminate. *Journal of Reinforced Plastics and Composites*, 29(11), 1669-1680.
- Abdillahi, H., Chabrat, E., Rouilly, A., & Rigal, L. (2013). Influence of citric acid on thermoplastic wheat flour/poly (lactic acid) blends. II. Barrier properties and water vapor sorption isotherms. *Industrial Crops and Products*, 50, 104-111.
- Abdorreza, M. N., Cheng, L., & Karim, A. (2011). Effects of plasticizers on thermal properties and heat sealability of sago starch films. *Food Hydrocolloids*, 25(1), 56-60.
- Abera, S., & Rakshit, S. K. (2003). Processing Technology Comparison of Physicochemical and Functional Properties of Cassava Starch Extracted from Fresh Root and Dry Chips. *Starch- Stärke*, 55(7), 287-296.
- Abraal, H., Andriyanto, H., Samera, R., Sapuan, S., & Ishak, M. R. (2012). Mechanical properties of screw pine (*pandanus odoratissimus*) fibers—unsaturated polyester composites. *Polymer-Plastics Technology and Engineering*, 51(5), 500-506.
- Aderemi, F., & Nworgu, F. (2007). Nutritional status of cassava peels and root sieviate biodegraded with *Aspergillus niger*. *Am.-Eurasian J. Agric. Environ. Sci*, 2, 308-311.
- Aguirre, A., Borneo, R., & León, A. E. (2013). Properties of triticale protein films and their relation to plasticizing–antiplasticizing effects of glycerol and sorbitol. *Industrial Crops and Products*, 50, 297-303.
- Ahmad, Z., Razak, N. H. A., Roslan, N. S. M., & Mosman, N. (2014). Evaluation of Kenaf Fibres Reinforced Starch Based Biocomposite Film through Water Absorption and Biodegradation Properties. *Journal of Engineering Science*, 10, 31.
- Aji, I. S., Zainudin, E. S., Khalina, A., Sapuan, S. M., & Khairul, M. (2011). Studying the effect of fiber size and fiber loading on the mechanical properties of hybridized kenaf/PALF-reinforced HDPE composite. *Journal of Reinforced Plastics and Composites*, 30(6), 546-553.
- Akpa, J. G., & Dagde, K. K. (2012). Modification of Cassava Starch for Industrial Uses. *International Journal of Engineering and Technology*, 2(6), 913-919.
- Al-Oqla, F. M., & Sapuan, S. M. (2014). Natural fiber reinforced polymer composites in industrial applications: feasibility of date palm fibers for sustainable automotive industry. *Journal of Cleaner Production*, 66, 347-354.

- Alves, V. D., Mali, S., Beléia, A., & Grossmann, M. V. E. (2007). Effect of glycerol and amylose enrichment on cassava starch film properties. *Journal of Food Engineering*, 78(3), 941-946.
- Anggraini, V., Sudarmonowati, E., Hartati, N., Suurs, L., & Visser, R. G. (2009). Characterization of cassava starch attributes of different genotypes. *Starch-Stärke*, 61(8), 472-481.
- Anuar, H., & Zuraida, A. (2011). Improvement in mechanical properties of reinforced thermoplastic elastomer composite with kenaf bast fibre. *Composites Part B: Engineering*, 42(3), 462-465.
- Arbelaiz, A., Fernández, B., Valea, A., & Mondragon, I. (2006). Mechanical properties of short flax fibre bundle/poly ( $\epsilon$ -caprolactone) composites: Influence of matrix modification and fibre content. *Carbohydrate Polymers*, 64(2), 224-232.
- Aripin, M., Ashuvila, Mohd Kassim, A. S., Daud, Z., & Mohd Hatta, M. Z. (2013). Cassava Peels for Alternative Fibre in Pulp and Paper Industry: Chemical Properties and Morphology Characterization. *International Journal of Integrated Engineering*, 5(1), 30-33.
- Aro, S., & Aletor, V. (2012). Proximate composition and amino acid profile of differently fermented cassava tuber wastes collected from a cassava starch producing factory in Nigeria. *Livestock Research for Rural Development*, 24(3).
- Aro, S., Aletor, V., Tewe, O., & Agbede, J. (2010). Nutritional potentials of cassava tuber wastes: A case study of a cassava starch processing factory in south-western Nigeria. *Livestock Research for Rural Development*, 22(11), 57-62.
- Asaoka, M., Blanshard, J., & Rickard, J. (1991). Seasonal Effects on the Physico-chemical Properties of Starch from Four Cultivars of Cassava. *Starch-Stärke*, 43(12), 455-459.
- Atiqah, A., Maleque, M., Jawaid, M., & Iqbal, M. (2014). Development of kenaf-glass reinforced unsaturated polyester hybrid composite for structural applications. *Composites Part B: Engineering*, 56, 68-73.
- Audic, J.-L., & Chaufer, B. (2005). Influence of plasticizers and crosslinking on the properties of biodegradable films made from sodium caseinate. *European Polymer Journal*, 41(8), 1934-1942.
- Bachtiar, D., Sapuan, S. M., & Hamdan, M. (2008). The effect of alkaline treatment on tensile properties of sugar palm fibre reinforced epoxy composites. *Materials & Design*, 29(7), 1285-1290.



- Bachtiar, D., Siregar, J. P., Ahmad Shahrizan, S., & MRM, R. (2014). Tensile Properties of Hybrid Sugar Palm/Kenaf Fibre Reinforced Polypropylene Composites. *Applied Mechanics and Materials*, 695, 155-158.
- Bangyekan, C., Aht-Ong, D., & Srikulkit, K. (2006). Preparation and properties evaluation of chitosan-coated cassava starch films. *Carbohydrate Polymers*, 63(1), 61-71.
- Belibi, P., Daou, T., Ndjaka, J., Nsom, B., Michelin, L., & Durand, B. (2014). A Comparative Study of Some Properties of Cassava and Tree Cassava Starch Films. *Physics Procedia*, 55, 220-226.
- Belibi, P. C., Daou, T. J., Ndjaka, J.-M. B., Michelin, L., Brendlé, J., Nsom, B., & Durand, B. (2013). Tensile and water barrier properties of cassava starch composite films reinforced by synthetic zeolite and beidellite. *Journal of Food Engineering*, 115(3), 339-346.
- Bergo, P., Carvalho, R., Sobral, P., Dos Santos, R., Da Silva, F., Prison, J., & Habitante, A. (2008). Physical properties of edible films based on cassava starch as affected by the plasticizer concentration. *Packaging Technology and Science*, 21(2), 85-89.
- Bertuzzi, M., Armada, M., & Gottifredi, J. (2007). Physicochemical characterization of starch based films. *Journal of Food Engineering*, 82(1), 17-25.
- Bismarck, A., Mishra, S., & Lampke, T. (2005). Plant fibers as reinforcement for green composites *Natural fibers, biopolymers, and biocomposites*: CRC Press.
- Bodirlau, R., Teaca, C.-A., & Spiridon, I. (2013). Influence of natural fillers on the properties of starch-based biocomposite films. *Composites Part B: Engineering*, 44(1), 575-583.
- Bonhomme, S., Cuer, A., Delort, A., Lemaire, J., Sancelme, M., & Scott, G. (2003). Environmental biodegradation of polyethylene. *Polymer Degradation and Stability*, 81(3), 441-452.
- Bonilla, J., Fortunati, E., Vargas, M., Chiralt, A., & Kenny, J. M. (2013). Effects of chitosan on the physicochemical and antimicrobial properties of PLA films. *Journal of Food Engineering*, 119(2), 236-243.
- Cané, M. (2005). *En viaje* (Vol. 29): Fundacion Biblioteca Ayacuch.
- Cao, N., Yang, X., & Fu, Y. (2009). Effects of various plasticizers on mechanical and water vapor barrier properties of gelatin films. *Food Hydrocolloids*, 23(3), 729-735.
- Carlmark, A. (2013). Tailoring Cellulose Surfaces by Controlled Polymerization Methods. *Macromolecular Chemistry and Physics*, 214(14), 1539-1544.

- Carta, F., Soccol, C., Ramos, L., & Fontana, J. (1999). Production of fumaric acid by fermentation of enzymatic hydrolysates derived from cassava bagasse. *Bioresource Technology*, 68(1), 23-28.
- Castaño, J., Rodríguez-Llamazares, S., Carrasco, C., & Bouza, R. (2012). Physical, chemical and mechanical properties of pehuen cellulosic husk and its pehuen-starch based composites. *Carbohydrate Polymers*, 90(4), 1550-1556.
- Castillo, L., López, O., López, C., Zaritzky, N., García, M. A., Barbosa, S., & Villar, M. (2013). Thermoplastic starch films reinforced with talc nanoparticles. *Carbohydrate Polymers*, 95(2), 664-674.
- Ceballos, H. (2002). La yuca en Colombia y el mundo: nuevas perspectivas para un cultivo milenario.
- Cereda, M. P., & Takahashi, M. (1996). Cassava wastes: their characterization and uses and treatment in Brazil. *Cassava Flour and Starch: Progress in Research and Development*(271), 221-232.
- Cerqueira, M. A., Souza, B. W., Teixeira, J. A., & Vicente, A. A. (2012). Effect of glycerol and corn oil on physicochemical properties of polysaccharide films—A comparative study. *Food Hydrocolloids*, 27(1), 175-184.
- Chaleomrum, N., Chookietwattana, K., & Dararat, S. (2014). Production of PHA from Cassava Starch Wastewater in Sequencing Batch Reactor Treatment System. *APCBEE Procedia*, 8, 167-172.
- Charles, A., Huang, T., Lai, P., Chen, C., Lee, P., & Chang, Y. (2007). Study of wheat flour–cassava starch composite mix and the function of cassava mucilage in Chinese noodles. *Food Hydrocolloids*, 21(3), 368-378.
- Chauhan, A. (2012). Environment-friendly biodegradable polymers and their applications. *Malaysian Polym. J*, 7, 62-67.
- Chen, G., Liu, B., & Zhang, B. (2014). Characterization of composite hydrocolloid film based on sodium cellulose sulfate and cassava starch. *Journal of Food Engineering*, 125, 105-111.
- Chookietwattana, K. (2014). Lactic Acid Production from Simultaneous Saccharification and Fermentation of Cassava Starch by *Lactobacillus Plantarum* MSUL 903. *APCBEE Procedia*, 8, 156-160.
- Coupland, J. N., Shaw, N. B., Monahan, F. J., O'Riordan, E. D., & O'Sullivan, M. (2000). Modeling the effect of glycerol on the moisture sorption behavior of whey protein edible films. *Journal of Food Engineering*, 43(1), 25-30.
- Daniels, C. A. (1989). *Polymers: structure and properties*: CRC Press.

- De Moraes Teixeira, E., Róz, D., Luzia, A., de Carvalho, A. J. F., & da Silva Curvelo, A. A. (2005). *Preparation and characterisation of thermoplastic starches from cassava starch, cassava root and cassava bagasse*. Paper presented at the Macromolecular symposia.
- De Souza, A. C., Dias, A., Sousa, H. C., & Tadini, C. C. (2014). Impregnation of cinnamaldehyde into cassava starch biocomposite films using supercritical fluid technology for the development of food active packaging. *Carbohydrate Polymers*, *102*, 830-837.
- Debiagi, F., Kobayashi, R. K., Nakazato, G., Panagio, L. A., & Mali, S. (2014a). Biodegradable active packaging based on cassava bagasse, polyvinyl alcohol and essential oils. *Industrial Crops and Products*, *52*, 664-670.
- Debiagi, F., Marim, B. M., & Mali, S. (2014b). Properties of Cassava Bagasse and Polyvinyl Alcohol Biodegradable Foams. *Journal of Polymers and the Environment*, DOI 10.1007/s10924-014-0705-4, 1-8.
- Defloor, I., Dehing, I., & Delcour, J. (1998). Physico- Chemical Properties of Cassava Starch. *Starch- Stärke*, *50*(2- 3), 58-64.
- Doportto, M. C., Dini, C., Mugridge, A., Viña, S. Z., & García, M. A. (2012). Physicochemical, thermal and sorption properties of nutritionally differentiated flours and starches. *Journal of Food Engineering*, *113*(4), 569-576.
- Echebiri, R., & Edaba, M. (2008). Production and utilization of cassava in Nigeria: prospects for food security and infant nutrition. *PAT*, *4*(1), 38-52.
- Edema, M. O., Sanni, L. O., & Sanni, A. I. (2005). Evaluation of maize-soybean flour blends for sour maize bread production in Nigeria. *African Journal of Biotechnology*, *4*(9).
- Eke, J., Achinewhu, S., Sanni, L., Barimalaa, I., Maziya-Dixon, B., & Dixon, A. (2009). Pasting, Color, and Granular Properties of Starches From Local and Improved Cassava Varieties in High Rainfall Region of Nigeria. *International Journal of Food Properties*, *12*(2), 438-449.
- El-Shekeil, Y., Sapuan, S. M., Abdan, K., & Zainudin, E. (2012). Influence of fiber content on the mechanical and thermal properties of Kenaf fiber reinforced thermoplastic polyurethane composites. *Materials & Design*, *40*, 299-303.
- Fadeyibi, A., Osunde, Z., Agidi, G., & Evans, E. (2014). Flow and strength properties of cassava and yam starch-glycerol composites essential in the design of handling equipment for granular solids. *Journal of Food Engineering*, *129*, 38-46.

- Fang, J., Fowler, P., Tomkinson, J., & Hill, C. (2002). The preparation and characterisation of a series of chemically modified potato starches. *Carbohydrate Polymers*, 47(3), 245-252.
- FAOstat, F. (2009). agriculture organization of the United Nations. *Statistical database*.
- Fiorda, F. A., Soares Júnior, M. S., Silva, F. A., Souto, L. R. F., & Grossmann, M. V. E. (2013). Amaranth flour, cassava starch and cassava bagasse in the production of gluten- free pasta: technological and sensory aspects. *International Journal of Food Science & Technology*, 48(9), 1977-1984.
- Fiore, V., Di Bella, G., & Valenza, A. (2015). The effect of alkaline treatment on mechanical properties of kenaf fibers and their epoxy composites. *Composites Part B: Engineering*, 68, 14-21.
- Fishman, M., Coffin, D., Konstance, R., & Onwulata, C. (2000). Extrusion of pectin/starch blends plasticized with glycerol. *Carbohydrate Polymers*, 41(4), 317-325.
- Flores-Hernández, C. G., Colín-Cruz, A., Velasco-Santos, C., Castaño, V. M., Rivera-Armenta, J. L., Almendarez-Camarillo, A., . . . Martínez-Hernández, A. L. (2014). All green composites from fully renewable biopolymers: chitosan-starch reinforced with keratin from feathers. *Polymers*, 6(3), 686-705.
- Forssell, P. M., Hulleman, S. H., Myllärinen, P. J., Moates, G. K., & Parker, R. (1999). Ageing of rubbery thermoplastic barley and oat starches. *Carbohydrate Polymers*, 39(1), 43-51.
- Frost, K., Kaminski, D., Kirwan, G., Lascaris, E., & Shanks, R. (2009). Crystallinity and structure of starch using wide angle X-ray scattering. *Carbohydrate Polymers*, 78(3), 543-548.
- Galdeano, M. C., Mali, S., Grossmann, M. V. E., Yamashita, F., & García, M. A. (2009). Effects of plasticizers on the properties of oat starch films. *Materials Science and Engineering: C*, 29(2), 532-538.
- Garcia, M., Martino, M., & Zaritzky, N. (2000). Lipid addition to improve barrier properties of edible starch-based films and coatings. *JOURNAL OF FOOD SCIENCE-CHICAGO-*, 65(6), 941-947.
- Ghasemlou, M., Khodaiyan, F., & Oromiehie, A. (2011). Physical, mechanical, barrier, and thermal properties of polyol-plasticized biodegradable edible film made from kefiran. *Carbohydrate Polymers*, 84(1), 477-483.
- Gilfillan, W. N., Nguyen, D. M., Sopade, P. A., & Doherty, W. O. (2012). Preparation and characterisation of composites from starch and sugar cane fibre. *Industrial Crops and Products*, 40, 45-54.

- Gindl-Altmutter, W., Keckes, J., Plackner, J., Liebner, F., Englund, K., & Laborie, M.-P. (2012). All-cellulose composites prepared from flax and lyocell fibres compared to epoxy–matrix composites. *Composites Science and Technology*, 72(11), 1304-1309.
- Gleadow, R. M., Evans, J. R., McCaffery, S., & Cavagnaro, T. R. (2009). Growth and nutritive value of cassava (*Manihot esculenta* Cranz.) are reduced when grown in elevated CO<sub>2</sub>. *Plant Biology*, 11(s1), 76-82.
- Glenn, G. M., Klamczynski, A. K., Holtman, K. M., Shey, J., Chiou, B.-S., Berrios, J., . . . Imam, S. H. (2007). Heat expanded starch-based compositions. *Journal of Agricultural and Food Chemistry*, 55(10), 3936-3943.
- Glenn, G. M., Klamczynski, A. P., Ludvik, C., Shey, J., Imam, S. H., Chiou, B.-S., . . . Wood, D. (2006). Permeability of starch gel matrices and select films to solvent vapors. *Journal of Agricultural and Food Chemistry*, 54(9), 3297-3304.
- Gomand, S., Lamberts, L., Derde, L., Goesaert, H., Vandeputte, G., Goderis, B., . . . Delcour, J. (2010). Structural properties and gelatinisation characteristics of potato and cassava starches and mutants thereof. *Food Hydrocolloids*, 24(4), 307-317.
- Gouanvé, F., Marais, S., Bessadok, A., Langevin, D., & Métayer, M. (2007). Kinetics of water sorption in flax and PET fibers. *European Polymer Journal*, 43(2), 586-598.
- Gutiérrez, T. J., Morales, N. J., Pérez, E., Tapia, M. S., & Famá, L. (2014). Physico-chemical properties of edible films derived from native and phosphated cush-cush yam and cassava starches. *Food Packaging and Shelf Life*.
- Habibi, Y., El-Zawawy, W. K., Ibrahim, M. M., & Dufresne, A. (2008). Processing and characterization of reinforced polyethylene composites made with lignocellulosic fibers from Egyptian agro-industrial residues. *Composites Science and Technology*, 68(7), 1877-1885.
- Hachemane, B., Zitoune, R., Bezzazi, B., & Bouvet, C. (2013). Sandwich composites impact and indentation behaviour study. *Composites Part B: Engineering*, 51, 1-10.
- Halonen, H., Larsson, P. T., & Iversen, T. (2013). Mercerized cellulose biocomposites: a study of influence of mercerization on cellulose supramolecular structure, water retention value and tensile properties. *Cellulose*, 20(1), 57-65.
- Haq, M. A., Hasnain, A., & Azam, M. (2014). Characterization of edible gum cordia film: Effects of plasticizers. *LWT-Food Science and Technology*, 55(1), 163-169.



- Haris, T. (1994). *Developmental and Germination Studies of the Sugar Palm (Arenga Pinnata Merr.) Seed*. Universiti Pertanian Malaysia.
- Himmelsbach, D. S., Khalili, S., & Akin, D. E. (2002). The use of FT- IR microspectroscopic mapping to study the effects of enzymatic retting of flax (*Linum usitatissimum* L) stems. *Journal of the Science of Food and Agriculture*, 82(7), 685-696.
- Howeler, R., & Tan, S. (2001). *Cassava's Potential in Asia in the 21st Century: Present Situation and Future Research and Development Needs*. Paper presented at the Proceeding 6th Regional Workshop, held in Ho Chi Minh city. February.
- Huda, M. S., Drzal, L. T., Mohanty, A. K., & Misra, M. (2008). Effect of fiber surface-treatments on the properties of laminated biocomposites from poly (lactic acid)(PLA) and kenaf fibers. *Composites Science and Technology*, 68(2), 424-432.
- Ibrahim, H., Farag, M., Megahed, H., & Mehanny, S. (2014). Characteristics of starch-based biodegradable composites reinforced with date palm and flax fibers. *Carbohydrate Polymers*, 101, 11-19.
- Ishak, M. (2009). Mechanical properties of treated and untreated woven sugar palm fibre-reinforced unsaturated polyester composites. *Master of Science Thesis, Universiti Putra Malaysia, Serdang, Selangor, Malaysia*.
- Ishak, M., Sapuan, S. M., Leman, Z., Rahman, M., & Anwar, U. (2012). Characterization of sugar palm (*Arenga pinnata*) fibres. *Journal of Thermal Analysis and Calorimetry*, 109(2), 981-989.
- Ishak, M., Sapuan, S. M., Leman, Z., Rahman, M., Anwar, U., & Siregar, J. (2013). Sugar palm (*Arenga pinnata*): Its fibres, polymers and composites. *Carbohydrate Polymers*, 91(2), 699-710.
- Iyer, S., Mattinson, D. S., & Fellman, J. K. (2010). Study of the early events leading to cassava root postharvest deterioration. *Tropical Plant Biology*, 3(3), 151-165.
- Jandas, P., Mohanty, S., & Nayak, S. (2013). Surface treated banana fiber reinforced poly (lactic acid) nanocomposites for disposable applications. *Journal of Cleaner Production*, 52, 392-401.
- Jawaid, M., & Khalil, H. A. (2011). Cellulosic/synthetic fibre reinforced polymer hybrid composites: A review. *Carbohydrate Polymers*, 86(1), 1-18.
- John, M. J., & Thomas, S. (2008). Biofibres and biocomposites. *Carbohydrate Polymers*, 71(3), 343-364.

- Jouki, M., Khazaei, N., Ghasemlou, M., & HadiNezhad, M. (2013). Effect of glycerol concentration on edible film production from cress seed carbohydrate gum. *Carbohydrate Polymers*, 96(1), 39-46.
- Jumaidin, R., Sapuan, S. M., Jawaid, M., Ishak, M., & Sahari, J. (2016). Characteristics of thermoplastic sugar palm Starch/Agar blend: Thermal, tensile, and physical properties. *International Journal of Biological Macromolecules*, 89, 575-581.
- Jumaidin, R., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Sahari, J. (2017). Thermal, mechanical, and physical properties of seaweed/sugar palm fibre reinforced thermoplastic sugar palm Starch/Agar hybrid composites. *International Journal of Biological Macromolecules*, 97, 606-615.
- Júnior, J. H. S. A., Júnior, H. L. O., Amico, S. C., & Amado, F. D. R. (2012). Study of hybrid intralaminar curaua/glass composites. *Materials & Design*, 42, 111-117.
- Kaewtatip, K., & Thongmee, J. (2013). Effect of kraft lignin and esterified lignin on the properties of thermoplastic starch. *Materials & Design*, 49, 701-704.
- Kaisangsri, N., Kerdchoechuen, O., & Laohakunjit, N. (2012). Biodegradable foam tray from cassava starch blended with natural fiber and chitosan. *Industrial Crops and Products*, 37(1), 542-546.
- Kaisangsri, N., Kerdchoechuen, O., & Laohakunjit, N. (2014). Characterization of cassava starch based foam blended with plant proteins, kraft fiber, and palm oil. *Carbohydrate Polymers*, 110, 70-77.
- Kampeerapappun, P., Aht-ong, D., Pentrakoon, D., & Srikulkit, K. (2007). Preparation of cassava starch/montmorillonite composite film. *Carbohydrate Polymers*, 67(2), 155-163.
- Kar, K. K., Rana, S., & Pandey, J. (2015). *Handbook of polymer nanocomposites. Processing, performance and application*: Springer.
- Kasemsuwan, T., & Jane, J.-L. (1996). Quantitative method for the survey of starch phosphate derivatives and starch phospholipids by <sup>31</sup>P nuclear magnetic resonance spectroscopy. *Cereal Chemistry*, 73(6), 702-707.
- Ki, O. L., Kurniawan, A., Lin, C. X., Ju, Y.-H., & Ismadji, S. (2013). Bio-oil from cassava peel: A potential renewable energy source. *Bioresource Technology*, 145, 157-161.
- Kim, H. S., Yang, H. S., & Kim, H. J. (2005). Biodegradability and mechanical properties of agro- flour-filled polybutylene succinate biocomposites. *Journal of Applied Polymer Science*, 97(4), 1513-1521.



- Kishi, H., & Fujita, A. (2008). Wood-based epoxy resins and the ramie fiber reinforced composites. *Environmental Engineering and Management Journal*, 7(5), 517-523.
- Kristo, E., & Biliaderis, C. G. (2006). Water sorption and thermo-mechanical properties of water/sorbitol-plasticized composite biopolymer films: Caseinate-pullulan bilayers and blends. *Food Hydrocolloids*, 20(7), 1057-1071.
- Ku, H., Wang, H., Pattarachaiyakoop, N., & Trada, M. (2011). A review on the tensile properties of natural fiber reinforced polymer composites. *Composites Part B: Engineering*, 42(4), 856-873.
- Kuciel, S., & Liber-Knec, A. (2009). Biocomposites on the base of thermoplastic starch filled by wood and kenaf fiber. *Journal of Biobased Materials and Bioenergy*, 3(3), 269-274.
- Larbie, L., Hayford, C. F., & Kaufmann, E. E. (2012). Characterisation of Cassava Fibre for Use as a Biomaterial.
- Lee, H. S., Cho, D., & Han, S. O. (2008). Effect of natural fiber surface treatments on the interfacial and mechanical properties of henequen/polypropylene biocomposites. *Macromolecular Research*, 16(5), 411-417.
- Leerahawong, A., Tanaka, M., Okazaki, E., & Osako, K. (2011). Effects of plasticizer type and concentration on the physicochemical properties of edible film from squid *Todarodes pacificus* mantle muscle. *Fisheries Science*, 77(6), 1061-1068.
- Lehrman, L. (1932). The fatty acid associated with cassava starch. *Journal of the American Chemical Society*, 54(6), 2527-2530.
- Leman, Z. (2009). *Mechanical properties of sugar palm fibre-reinforced epoxy composites*. PhD Thesis, Universiti Putra Malaysia.
- Leman, Z., Sapuan, S., Saifol, A., Maleque, M. A., & Ahmad, M. (2008a). Moisture absorption behavior of sugar palm fiber reinforced epoxy composites. *Materials & Design*, 29(8), 1666-1670.
- Leman, Z., Sapuan, S. M., Saifol, A., Maleque, M. A., & Ahmad, M. (2008b). Moisture absorption behavior of sugar palm fiber reinforced epoxy composites. *Materials & Design*, 29(8), 1666-1670.
- Leman, Z., Sastra, H., Sapuan, S., Hamdan, M., & Maleque, M. (2005). Study on impact properties of *Arenga pinnata* fibre reinforced epoxy composites. *Jurnal Teknologi Terpakai*, 3(1), 14-19.

- Li, H.-g., Oforu, F. K., Li, K.-t., Gu, Q.-y., Wang, Q., & Yu, X.-b. (2014). Acetone, butanol, and ethanol production from gelatinized cassava flour by a new isolates with high butanol tolerance. *Bioresource Technology*, *172*, 276-282.
- Lomelí-Ramírez, M. G., Kestur, S. G., Manríquez-González, R., Iwakiri, S., de Muniz, G. B., & Flores-Sahagun, T. S. (2014). Bio-composites of cassava starch-green coconut fiber: Part II—Structure and properties. *Carbohydrate Polymers*, *102*, 576-583.
- Lomelí Ramírez, M. G., Satyanarayana, K. G., Iwakiri, S., de Muniz, G. B., Tanobe, V., & Flores-Sahagun, T. S. (2011). Study of the properties of biocomposites. Part I. Cassava starch-green coir fibers from Brazil. *Carbohydrate Polymers*, *86*(4), 1712-1722.
- Lopez, O., Garcia, M., Villar, M., Gentili, A., Rodriguez, M., & Albertengo, L. (2014). Thermo-compression of biodegradable thermoplastic corn starch films containing chitin and chitosan. *LWT-Food Science and Technology*, *57*(1), 106-115.
- López, O. V., Castillo, L. A., García, M. A., Villar, M. A., & Barbosa, S. E. (2015). Food packaging bags based on thermoplastic corn starch reinforced with talc nanoparticles. *Food Hydrocolloids*, *43*, 18-24.
- López, O. V., & García, M. A. (2012). Starch films from a novel (*Pachyrhizus ahipa*) and conventional sources: Development and characterization. *Materials Science and Engineering: C*, *32*(7), 1931-1940.
- Lu, Y., Ding, Y., & Wu, Q. (2011). Simultaneous saccharification of cassava starch and fermentation of algae for biodiesel production. *Journal of Applied Phycology*, *23*(1), 115-121.
- Lu, Y., Weng, L., & Cao, X. (2006). Morphological, thermal and mechanical properties of ramie crystallites—reinforced plasticized starch biocomposites. *Carbohydrate Polymers*, *63*(2), 198-204.
- Ludueña, L., Vázquez, A., & Alvarez, V. (2012). Effect of lignocellulosic filler type and content on the behavior of polycaprolactone based eco-composites for packaging applications. *Carbohydrate Polymers*, *87*(1), 411-421.
- Luo, G., Xie, L., Zou, Z., Zhou, Q., & Wang, J.-Y. (2010). Fermentative hydrogen production from cassava stillage by mixed anaerobic microflora: effects of temperature and pH. *Applied Energy*, *87*(12), 3710-3717.
- Ma, X.-F., Yu, J., & Wan, J. (2006). Urea and ethanolamine as a mixed plasticizer for thermoplastic starch. *Carbohydrate Polymers*, *64*(2), 267-273.

- Ma, X., Yu, J., & Kennedy, J. F. (2005a). Studies on the properties of natural fibers-reinforced thermoplastic starch composites. *Carbohydrate Polymers*, 62(1), 19-24.
- Ma, X., Yu, J., & Ma, Y. (2005b). Urea and formamide as a mixed plasticizer for thermoplastic wheat flour. *Carbohydrate Polymers*, 60(1), 111-116.
- Mali, S., Grossmann, M. V. E., Garcia, M. A., Martino, M. N., & Zaritzky, N. E. (2002). Microstructural characterization of yam starch films. *Carbohydrate Polymers*, 50(4), 379-386.
- Mali, S., Sakanaka, L., Yamashita, F., & Grossmann, M. (2005). Water sorption and mechanical properties of cassava starch films and their relation to plasticizing effect. *Carbohydrate Polymers*, 60(3), 283-289.
- Mantzari, G., Raphaelides, S. N., & Exarhopoulos, S. (2010). Effect of sorbitol addition on the physicochemical characteristics of starch–fatty acid systems. *Carbohydrate Polymers*, 79(1), 154-163.
- Matsui, K. N., Larotonda, F., Paes, S., Luiz, D., Pires, A., & Laurindo, J. (2004). Cassava bagasse-Kraft paper composites: analysis of influence of impregnation with starch acetate on tensile strength and water absorption properties. *Carbohydrate Polymers*, 55(3), 237-243.
- Mbey, J.-A., Hoppe, S., & Thomas, F. (2012). Cassava starch–kaolinite composite film. Effect of clay content and clay modification on film properties. *Carbohydrate Polymers*, 88(1), 213-222.
- Mehta, N., & Parsania, P. (2006). Fabrication and evaluation of some mechanical and electrical properties of jute- biomass based hybrid composites. *Journal of Applied Polymer Science*, 100(3), 1754-1758.
- Mello, L. R., & Mali, S. (2014). Use of malt bagasse to produce biodegradable baked foams made from cassava starch. *Industrial Crops and Products*, 55, 187-193.
- Migneault, S., Koubaa, A., Erchiqui, F., Chaala, A., Englund, K., & Wolcott, M. P. (2009). Effects of processing method and fiber size on the structure and properties of wood–plastic composites. *Composites Part A: Applied Science and Manufacturing*, 40(1), 80-85.
- Milagres, A., Santos, E., Piovan, T., & Roberto, I. (2004). Production of xylanase by *Thermoascus aurantiacus* from sugar cane bagasse in an aerated growth fermentor. *Process Biochemistry*, 39(11), 1387-1391.
- Misri, S., Leman, Z., Sapuan, S., & Ishak, M. (2010). *Mechanical properties and fabrication of small boat using woven glass/sugar palm fibres reinforced unsaturated polyester hybrid composite*. Paper presented at the IOP Conference Series: Materials Science and Engineering.

- Mo, X. Z., Zhong, Y. X., Liang, C. Q., & Yu, S. J. (2010). Studies on the properties of banana fibers-reinforced thermoplastic cassava starch composites: Preliminary results. *Advanced Materials Research*, 87, 439-444.
- Mogea, J., Seibert, B., & Smits, W. (1991). Multipurpose palms: the sugar palm (*Arenga pinnata* (Wurmb) Merr.). *Agroforestry Systems*, 13(2), 111-129.
- Mohanty, A. K., Misra, M., & Drzal, L. T. (2005). *Natural fibers, biopolymers, and biocomposites*. Boca Raton, FL: Taylor & Francis Group: CRC Press.
- Mohanty, J. R., Das, S. N., Das, H. C., & Swain, S. K. (2013). Effective mechanical properties of polyvinylalcohol biocomposites with reinforcement of date palm leaf fibers. *Polymer Composites*, 34(6), 959-966.
- Mohanty, J. R., Das, S. N., Das, H. C., & Swain, S. K. (2014). Effect of chemically modified date palm leaf fiber on mechanical, thermal and rheological properties of polyvinylpyrrolidone. *Fibers and Polymers*, 15(5), 1062.
- Mohanty, S., Verma, S. K., & Nayak, S. K. (2006). Dynamic mechanical and thermal properties of MAPE treated jute/HDPE composites. *Composites Science and Technology*, 66(3), 538-547.
- Moorthy, S., & Ramanujam, T. (1986). Variation in properties of starch in cassava varieties in relation to age of the crop. *Starch- Stärke*, 38(2), 58-61.
- Moorthy, S., Wenham, J. E., & Blanshard, J. (1996). Effect of solvent extraction on the gelatinisation properties of flour and starch of five cassava varieties. *Journal of the Science of Food and Agriculture*, 72(3), 329-336.
- Moorthy, S. N. (2002). Physicochemical and functional properties of tropical tuber starches: a review. *Starch- Stärke*, 54(12), 559-592.
- Mujahid, A. A. Z. (2009). Study on impact resistance performance of *Arenga pinnata* fibre reinforced composite. <http://www.slideshare.net/ayamgolek/study-on-impact-resistance-performance-of-arenga-pinnata-fibre-reinforced-composite>. 1 Jun 2016.
- Müller, C. M., Laurindo, J. B., & Yamashita, F. (2009). Effect of cellulose fibers addition on the mechanical properties and water vapor barrier of starch-based films. *Food Hydrocolloids*, 23(5), 1328-1333.
- Müller, C. M., Yamashita, F., & Laurindo, J. B. (2008). Evaluation of the effects of glycerol and sorbitol concentration and water activity on the water barrier properties of cassava starch films through a solubility approach. *Carbohydrate Polymers*, 72(1), 82-87.

- Munthoub, D. I., & Rahman, W. A. W. A. (2011a). Tensile and water absorption properties of biodegradable composites derived from cassava skin/polyvinyl alcohol with glycerol as plasticizer. *Sains Malaysiana*, 40(7), 713-718.
- Munthoub, D. I., & Rahman, W. W. A. (2011b). Tensile and water absorption properties of biodegradable composites derived from cassava skin/polyvinyl alcohol with glycerol as plasticizer. *Sains Malaysiana*, 40(7), 713-718.
- Myllärinen, P., Partanen, R., Seppälä, J., & Forssell, P. (2002). Effect of glycerol on behaviour of amylose and amylopectin films. *Carbohydrate Polymers*, 50(4), 355-361.
- Narkchamnan, S., & Sakdaronnarong, C. (2013). Thermo-molded biocomposite from cassava starch, natural fibers and lignin associated by laccase-mediator system. *Carbohydrate Polymers*, 96(1), 109-117.
- Navia, D. P., & Villada, H. S. (2012). *Thermoplastic Cassava Flour*: INTECH Open Access Publisher.
- Nurulnihar, E., & Tan, S. (2012). Cassava mini-cuttings as a source of planting material. *J. Trop. Agric. and Fd. Sc*, 40(1), 145-151.
- Nuwamanya, E., Baguma, Y., Emmambux, N., & Rubaihayo, P. (2010). Crystalline and pasting properties of cassava starch are influenced by its molecular properties. *African Journal of Food Science*, 4(1), 008-015.
- Obadina, A., & Abiola, S. (2006). Fungal enrichment of cassava peels proteins. *African Journal of Biotechnology*, 5(3), 302-304.
- Ofoefule, A., & Uzodinma, E. (2009). Biogas production from blends of cassava (*Manihot utilissima*) peels with some animal wastes. *International Journal of Physical Sciences*, 4(7), 398-402.
- Okpako, C., Ntui, V., Osuagwu, A., & Obasi, F. (2008). Proximate composition and cyanide content of cassava peels fermented with *Aspergillus niger* and *Lactobacillus rhamnosus*. *Journal of Food Agriculture and Environment*, 6(2), 251.
- Oladipo, I., Adams, J., & Akinwande, J. (2013). Using Cassava Peelings to Reduce Input Cost of Concrete: A Waste-to-Wealth Initiative in Southwestern Nigeria. *Universal Journal of Environmental Research & Technology*, 3(4).
- Olasanmi, B., Akoroda, M., Okogbenin, E., Egesi, C., Kahya, S., Onyegbule, O., . . . Tohme, J. (2014). Bulked segregant analysis identifies molecular markers associated with early bulking in cassava (*Manihot esculenta* Crantz). *Euphytica*, 195(2), 235-244.



- Olomo, V., & Ajibola, O. (2003). Processing factors affecting the yield and physicochemical properties of starch from cassava chips and flour. *Starch-Stärke*, 55(10), 476-481.
- Pan, N., Chen, K., Monego, C. J., & Backer, S. (1998). *The hybrid effects in hybrid fibre composites: experimental study using twisted fibrous structures*. Paper presented at the Proceedings of the Royal Society of London A: Mathematical, Physical and Engineering Sciences.
- Pandey, A., Soccol, C. R., Nigam, P., Soccol, V. T., Vandenberghe, L. P., & Mohan, R. (2000). Biotechnological potential of agro-industrial residues. II: cassava bagasse. *Bioresource Technology*, 74(1), 81-87.
- Panichnumsin, P., Nopharatana, A., Ahring, B., & Chaiprasert, P. (2010). Production of methane by co-digestion of cassava pulp with various concentrations of pig manure. *Biomass and Bioenergy*, 34(8), 1117-1124.
- Parra, D., Tadini, C., Ponce, P., & Lugão, A. (2004). Mechanical properties and water vapor transmission in some blends of cassava starch edible films. *Carbohydrate polymers*, 58(4), 475-481.
- Pasquini, D., Teixeira, E. d. M., Curvelo, A. A. d. S., Belgacem, M. N., & Dufresne, A. (2010). Extraction of cellulose whiskers from cassava bagasse and their applications as reinforcing agent in natural rubber. *Industrial Crops and Products*, 32(3), 486-490.
- Pelissari, F. M., Andrade-Mahecha, M. M., Sobral, P. J. d. A., & Menegalli, F. C. (2013). Comparative study on the properties of flour and starch films of plantain bananas (*Musa paradisiaca*). *Food Hydrocolloids*, 30(2), 681-690.
- Pelissari, F. M., Yamashita, F., Garcia, M. A., Martino, M. N., Zaritzky, N. E., & Grossmann, M. V. E. (2012). Constrained mixture design applied to the development of cassava starch-chitosan blown films. *Journal of Food Engineering*, 108(2), 262-267.
- Pérez, J. C., Lenis, J. I., Calle, F., Morante, N., Sánchez, T., Debouck, D., & Ceballos, H. (2011). Genetic variability of root peel thickness and its influence in extractable starch from cassava (*Manihot esculenta* Crantz) roots. *Plant Breeding*, 130(6), 688-693.
- Petersson, M., & Stading, M. (2005). Water vapour permeability and mechanical properties of mixed starch-monoglyceride films and effect of film forming conditions. *Food Hydrocolloids*, 19(1), 123-132.
- Phan The, D., Debeaufort, F., Voilley, A., & Luu, D. (2009). Biopolymer interactions affect the functional properties of edible films based on agar, cassava starch and arabinoxylan blends. *Journal of Food Engineering*, 90(4), 548-558.

- Pinto, V. Z., Moomand, K., Vanier, N. L., Colussi, R., Villanova, F. A., Zavareze, E. R., & Dias, A. R. (2014). Molecular structure and granule morphology of native and heat- moisture- treated pinhão starch. *International Journal of Food Science & Technology*.
- Poovarodom, N., & Praditduang, S. (1999). The development of packaging from cassava starch. *Packaging Directory Thailand. The Thai Packaging Association*, 41-42.
- Prachayawarakorn, J., Chaiwatyothin, S., Mueangta, S., & Hanchana, A. (2013). Effect of jute and kapok fibers on properties of thermoplastic cassava starch composites. *Materials & Design*, 47, 309-315.
- Prachayawarakorn, J., & Pomdage, W. (2014). Effect of carrageenan on properties of biodegradable thermoplastic cassava starch/low-density polyethylene composites reinforced by cotton fibers. *Materials & Design*, 61, 264-269.
- Prachayawarakorn, J., Ruttanabus, P., & Boonsom, P. (2011). Effect of cotton fiber contents and lengths on properties of thermoplastic starch composites prepared from rice and waxy rice starches. *Journal of Polymers and the Environment*, 19(1), 274-282.
- Preechawong, D., Peesan, M., Rujiravanit, R., & Supaphol, P. (2004). *Preparation and properties of starch/poly (vinyl alcohol) composite foams*. Paper presented at the Macromolecular Symposia.
- Raabe, J., Fonseca, A. d. S., Bufalino, L., Ribeiro, C., Martins, M. A., Marconcini, J. M., . . . Tonoli, G. H. D. (2015). Biocomposite of Cassava Starch Reinforced with Cellulose Pulp Fibers Modified with Deposition of Silica (SiO<sub>2</sub>) Nanoparticles. *Journal of Nanomaterials*.
- Ramírez, M. G. L., Muniz, G. I., Satyanarayana, K. G., Tanobe, V., & Iwakiri, S. (2010). Preparation and characterization of biodegradable composites based on Brazilian cassava starch, corn starch and green coconut fibers. *Matéria (Rio de Janeiro)*, 15(2), 330-337.
- Rao, H. R., Kumar, M. A., & Reddy, G. R. (2011). Hybrid composites: effect of fibers on mechanical properties. *International Journal of Macromolecular Science*, 1(1), 9-14.
- Ray, R. C., Mohapatra, S., Panda, S., & Kar, S. (2008). Solid substrate fermentation of cassava fibrous residue for production of α-amylase, lactic acid and ethanol. *Journal of Environmental Biology*, 29(1/2), 111-115.
- Razali, N., Salit, M. S., Jawaid, M., Ishak, M. R., & Lazim, Y. (2015). A Study on Chemical Composition, Physical, Tensile, Morphological, and Thermal Properties of Roselle Fibre: Effect of Fibre Maturity. *BioResources*, 10(1), 1803-1824.



- Reddy, N., & Yang, Y. (2005). Biofibers from agricultural byproducts for industrial applications. *Trends in Biotechnology*, 23(1), 22-27.
- Rezaei, F., Yunus, R., & Ibrahim, N. A. (2009). Effect of fiber length on thermomechanical properties of short carbon fiber reinforced polypropylene composites. *Materials & Design*, 30(2), 260-263.
- Rodrigues, D. C., Caceres, C. A., Ribeiro, H. L., de Abreu, R. F., Cunha, A. P., & Azeredo, H. (2014). Influence of cassava starch and carnauba wax on physical properties of cashew tree gum-based films. *Food Hydrocolloids*, 38, 147-151.
- Rosa, M. F., Chiou, B. s., Medeiros, E. S., Wood, D. F., Mattoso, L. H., Orts, W. J., & Imam, S. H. (2009). Biodegradable composites based on starch/EVOH/glycerol blends and coconut fibers. *Journal of Applied Polymer Science*, 111(2), 612-618.
- Rowell, R. M., Han, J. S., & Rowell, J. S. (2000). Characterization and factors effecting fiber properties. *Natural Polymers and Agrofibers Bases Composites. Embrapa Instrumentacao Agropecuaria, P. O. Box 741, Sao Carlos, 13560-970 SP, Brazil, 2000.*, 115-134.
- Sahari, J., Sapuan, S. M., Ismarrubie, Z., & Rahman, M. (2011). *Comparative study of physical properties based on different parts of sugar palm fibre reinforced unsaturated polyester composites*. Paper presented at the Key Engineering Materials.
- Sahari, J., Sapuan, S. M., Ismarrubie, Z., & Rahman, M. (2012). Physical and chemical properties of different morphological parts of sugar palm fibres. *Fibres & Textiles in Eastern Europe*, 21-24.
- Sahari, J., Sapuan, S. M., Zainudin, E., & Maleque, M. (2013a). Effect of water absorption on mechanical properties of sugar palm fibre reinforced sugar palm starch (SPF/SPS) biocomposites. *Journal of Biobased Materials and Bioenergy*, 7(1), 90-94.
- Sahari, J., Sapuan, S. M., Zainudin, E., & Maleque, M. (2013b). Thermo-mechanical behaviors of thermoplastic starch derived from sugar palm tree ( *Arenga pinnata* ). *Carbohydrate Polymers*, 92(2), 1711-1716.
- Sahari, J., Sapuan, S. M., Zainudin, E., & Maleque, M. A. (2013c). Mechanical and thermal properties of environmentally friendly composites derived from sugar palm tree. *Materials & Design*, 49, 285-289.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2014). Degradation characteristics of SPF/SPS biocomposites. *Fibres & Textiles in Eastern Europe*.

- Sakina, H., Sarani, Z., & Khairul Zaman, D. (2000). *Chemical characterization of benzylated oil palm empty fruit bunches*. Paper presented at the Symposium on utilization of oil palm tree. oil palm biomass: opportunities and challenges in commercial exploitation, Kuala Lumpur.
- Salgado, P. R., Schmidt, V. C., Ortiz, S. E. M., Mauri, A. N., & Laurindo, J. B. (2008). Biodegradable foams based on cassava starch, sunflower proteins and cellulose fibers obtained by a baking process. *Journal of Food Engineering*, 85(3), 435-443.
- Sánchez, T., Salcedo, E., Ceballos, H., Dufour, D., Mafla, G., Morante, N., . . . Jaramillo, G. (2009). Screening of starch quality traits in cassava (*Manihot esculenta* Crantz). *Starch- Stärke*, 61(1), 12-19.
- Sanyang, Sapuan, S. M., Jawaid, M., Ishak, M., & Sahari, J. (2015a). Effect of Plasticizer Type and Concentration on Dynamic Mechanical Properties of Sugar Palm Starch Based Films. *International Journal of Polymer Analysis and Characterization*(just-accepted).
- Sanyang, Sapuan, S. M., Jawaid, M., Ishak, M. R., & Sahari, J. (2015b). Effect of Plasticizer Type and Concentration on Tensile, Thermal and Barrier Properties of Biodegradable Films Based on Sugar Palm (*Arenga pinnata*) Starch. *Polymers*, 7(6), 1106-1124.
- Sanyang, M. L., Sapuan, S., Jawaid, M., Ishak, M. R., & Sahari, J. (2016a). Effect of sugar palm-derived cellulose reinforcement on the mechanical and water barrier properties of sugar palm starch biocomposite films. *BioResources*, 11(2), 4134-4145.
- Sanyang, M. L., Sapuan, S., Jawaid, M., Ishak, M. R., & Sahari, J. (2016b). Recent developments in sugar palm (*Arenga pinnata*) based biocomposites and their potential industrial applications: A review. *Renewable and Sustainable Energy Reviews*, 54, 533-549.
- Sanyang, M. L., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Sahari, J. (2015c). Effect of Plasticizer Type and Concentration on Tensile, Thermal and Barrier Properties of Biodegradable Films Based on Sugar Palm (*Arenga pinnata*) Starch. *Polymers*, 7(6), 1106-1124.
- Sapuan, S., & Bachtiar, D. (2012). Mechanical properties of sugar palm fibre reinforced high impact polystyrene composites. *Procedia Chemistry*, 4, 101-106.
- Sapuan, S. M., & Maleque, M. (2005). Design and fabrication of natural woven fabric reinforced epoxy composite for household telephone stand. *Materials & Design*, 26(1), 65-71.

- Shakuntala, O., Raghavendra, G., & Samir Kumar, A. (2014). Effect of Filler Loading on Mechanical and Tribological Properties of Wood Apple Shell Reinforced Epoxy Composite. *Advances in Materials Science and Engineering*, 2014, 1-9.
- Shittu, T., Raji, A., & Sanni, L. (2007). Bread from composite cassava-wheat flour: I. Effect of baking time and temperature on some physical properties of bread loaf. *Food Research International*, 40(2), 280-290.
- Shittu, T. A., Aminu, R. A., & Abulude, E. O. (2009). Functional effects of xanthan gum on composite cassava-wheat dough and bread. *Food Hydrocolloids*, 23(8), 2254-2260.
- Shojaee-Aliabadi, S., Hosseini, H., Mohammadifar, M. A., Mohammadi, A., Ghasemlou, M., Ojagh, S. M., & Khaksar, R. (2013). Characterization of antioxidant-antimicrobial  $\kappa$ -Carrageenan films containing satureja hortensis essential oil. *International Journal of Biological Macromolecules*, 52, 116-124.
- Siregar, J. P. (2005). *Tensile and flexural properties of Arenga pinnata filament (ijuk filament) reinforced epoxy composites*. Universiti Putra Malaysia.
- Sivakumar, S., Senthilkumar, P., & Subburam, V. (2001). Carbon from cassava peel, an agricultural waste, as an adsorbent in the removal of dyes and metal ions from aqueous solution. *Bioresource Technology*, 80(3), 233-235.
- Sothornvit, R., & Krochta, J. (2005). Plasticizers in edible films and coatings. *Innovations in food packaging*, 403-433.
- Souza, A., Benze, R., Ferrão, E., Ditchfield, C., Coelho, A., & Tadini, C. (2012). Cassava starch biodegradable films: Influence of glycerol and clay nanoparticles content on tensile and barrier properties and glass transition temperature. *LWT-Food Science and Technology*, 46(1), 110-117.
- Souza, A., Goto, G., Mainardi, J., Coelho, A., & Tadini, C. (2013). Cassava starch composite films incorporated with cinnamon essential oil: Antimicrobial activity, microstructure, mechanical and barrier properties. *LWT-Food Science and Technology*, 54(2), 346-352.
- Soykeabkaew, N., Supaphol, P., & Rujiravanit, R. (2004). Preparation and characterization of jute-and flax-reinforced starch-based composite foams. *Carbohydrate Polymers*, 58(1), 53-63.
- Sreekala, M., George, J., Kumaran, M., & Thomas, S. (2002). The mechanical performance of hybrid phenol-formaldehyde-based composites reinforced with glass and oil palm fibres. *Composites Science and Technology*, 62(3), 339-353.

- Srichuwong, S., & Jane, J.-I. (2007). Physicochemical Properties of Starch Affected by Molecular Composition and Structures. *Food Science and Biotechnology*, 16(5), 663-674.
- Srichuwong, S., Sunarti, T. C., Mishima, T., Isono, N., & Hisamatsu, M. (2005). Starches from different botanical sources I: Contribution of amylopectin fine structure to thermal properties and enzyme digestibility. *Carbohydrate Polymers*, 60(4), 529-538.
- Sriroth, K., Onollakup, R., Piyachomkwan, K., & Oates, C. G. (1999). Biodegradable plastics from cassava starch in Thailand.
- Stone, G. D. (2002). Both Sides Now. *Current Anthropology*, 43(4), 611-630.
- Sudaryanto, Y., Hartono, S., Irawaty, W., Hindarso, H., & Ismadji, S. (2006). High surface area activated carbon prepared from cassava peel by chemical activation. *Bioresource Technology*, 97(5), 734-739.
- Sugumaran, K., Kumar, B. K., Mahalakshmi, M., & Ponnusami, V. (2013). Cassava bagasse—a low cost substrate for thermotolerant xylanase production using *Bacillus subtilis*. *Int J ChemTech Res*, 5(1), 394-400.
- Tanner, K. E., Draper, P. R., Getz, J. J., Burnett, S. W., & Youngblood, E. (2002). Film forming compositions comprising modified starches and iota-carrageenan and methods for manufacturing soft capsules using same: US. Washington, DC: Patents No. 6,340,473.
- Tantatherdtam, R., Tran, T., Chotineeranat, S., ByoungHo, L., SeNa, L., Sriroth, K., & HyunJoong, K. (2009). *Preparation and characterization of cassava fiber-based polypropylene and polybutylene succinate composites*. Paper presented at the Kasetsart Journal, Natural Sciences.
- Teacă, C.-A., Bodîrlău, R., & Spiridon, I. (2013). Effect of cellulose reinforcement on the properties of organic acid modified starch microparticles/plasticized starch bio-composite films. *Carbohydrate Polymers*, 93(1), 307-315.
- Teixeira, E. d. M., Curvelo, A. A., Corrêa, A. C., Marconcini, J. M., Glenn, G. M., & Mattoso, L. H. (2012). Properties of thermoplastic starch from cassava bagasse and cassava starch and their blends with poly (lactic acid). *Industrial Crops and Products*, 37(1), 61-68.
- Teixeira, E. d. M., Pasquini, D., Curvelo, A. A., Corradini, E., Belgacem, M. N., & Dufresne, A. (2009). Cassava bagasse cellulose nanofibrils reinforced thermoplastic cassava starch. *Carbohydrate Polymers*, 78(3), 422-431.
- Tharanathan, R. (2003). Biodegradable films and composite coatings: past, present and future. *Trends in Food Science & Technology*, 14(3), 71-78.

- Thwe, M. M., & Liao, K. (2002). Effects of environmental aging on the mechanical properties of bamboo–glass fiber reinforced polymer matrix hybrid composites. *Composites Part A: Applied Science and Manufacturing*, 33(1), 43-52.
- Thwe, M. M., & Liao, K. (2003). Durability of bamboo-glass fiber reinforced polymer matrix hybrid composites. *Composites Science and Technology*, 63(3), 375-387.
- Tonukari, N. J. (2004). Cassava and the future of starch. *Electronic Journal of Biotechnology*, 7(1), 5-8.
- Ulloa, M. J. V., & PunínBurneo, M. G. (2012). Development of Starch Biopolymers from Waste Organic Materials (Cassava Peel) and Natural Fiber (Agave). 2 (2), 238.
- Vallejos, M. E., Curvelo, A. A., Teixeira, E. M., Mendes, F. M., Carvalho, A. J., Felissia, F. E., & Area, M. C. (2011). Composite materials of thermoplastic starch and fibers from the ethanol–water fractionation of bagasse. *Industrial Crops and Products*, 33(3), 739-746.
- van Soest, J. J., Hulleman, S., De Wit, D., & Vliegthart, J. (1996). Crystallinity in starch bioplastics. *Industrial Crops and Products*, 5(1), 11-22.
- Vandenbergh, L., Soccol, C., Lebeault, J., & Krieger, N. (1998). Cassava wastes hydrolysate an alternative carbon source for citric acid production by *Candida lipolytica*. *Int. Congr. Biotech*, 98.
- Veiga-Santos, P., Oliveira, L., Cereda, M., & Scamparini, A. (2007). Sucrose and inverted sugar as plasticizer. Effect on cassava starch–gelatin film mechanical properties, hydrophilicity and water activity. *Food Chemistry*, 103(2), 255-262.
- Venkateshwaran, N., Elayaperumal, A., & Sathiya, G. (2012). Prediction of tensile properties of hybrid-natural fiber composites. *Composites Part B: Engineering*, 43(2), 793-796.
- Vercelheze, A. E., Fakhouri, F. M., Dall'Antônia, L. H., Urbano, A., Youssef, E. Y., Yamashita, F., & Mali, S. (2012). Properties of baked foams based on cassava starch, sugarcane bagasse fibers and montmorillonite. *Carbohydrate Polymers*, 87(2), 1302-1310.
- Versino, F., & García, M. A. (2014). Cassava (*Manihot esculenta*) starch films reinforced with natural fibrous filler. *Industrial Crops and Products*, 58, 305-314.



- Versino, F., López, O. V., & García, M. A. (2015a). Sustainable use of cassava (*Manihot esculenta*) roots as raw material for biocomposites development. *Industrial Crops and Products*, 65, 79-89.
- Versino, F., López, O. V., & García, M. A. (2015b). Sustainable use of cassava (*Manihot esculenta*) roots as raw material for biocomposites development. *Industrial Crops and Products*, 65, 79-89.
- Villada, H. (2005). Influencia de mezclas de almidón agrio, perfil de temperatura y velocidad de tornillo de un extrusor sencillo en la producción de almidón termoplástico, su caracterización fisicoquímica, mecánica, microestructural y comportamiento durante el almacenamiento. *Universidad del Valle, Facultad de Ingeniería*.
- Villamizar, M. C. N., Araque, V. S., Reyes, C. A. R., & Silva, R. S. (2012). Effect of the addition of coal-ash and cassava peels on the engineering properties of compressed earth blocks. *Construction and Building Materials*, 36, 276-286.
- Wambua, P., Ivens, J., & Verpoest, I. (2003). Natural fibres: can they replace glass in fibre reinforced plastics? *Composites Science and Technology*, 63(9), 1259-1264.
- Wang, J.-l., Cheng, F., & Zhu, P.-x. (2014). Structure and properties of urea-plasticized starch films with different urea contents. *Carbohydrate Polymers*, 101, 1109-1115.
- Westby, A. (2002). Cassava utilization, storage and small-scale processing. *Cassava: biology, production and utilization*, 281-300.
- Whistler, R. (1984). History and future expectation of starch use. *Starch: Chemistry and Technology*, RL Whistler, JN BeMiller, EF Paschell: academic Press, Orlando, FL.
- Woiciechowski, A. L., Nitsche, S., Pandey, A., & Soccol, C. R. (2002). Acid and enzymatic hydrolysis to recover reducing sugars from cassava bagasse: an economic study. *Brazilian archives of biology and technology*, 45(3), 393-400.
- Wongsasulak, S., Yoovidhya, T., Bhumiratana, S., Hongsprabhas, P., McClements, D. J., & Weiss, J. (2006). Thermo-mechanical properties of egg albumen-cassava starch composite films containing sunflower-oil droplets as influenced by moisture content. *Food Research International*, 39(3), 277-284.
- Xu, Y., & Hanna, M. A. (2005). Preparation and properties of biodegradable foams from starch acetate and poly (tetramethylene adipate-co-terephthalate). *Carbohydrate Polymers*, 59(4), 521-529.



- Yaich, H., Garna, H., Besbes, S., Paquot, M., Blecker, C., & Attia, H. (2011). Chemical composition and functional properties of *Ulva lactuca* seaweed collected in Tunisia. *Food Chemistry*, 128(4), 895-901.
- Yang, H., Yan, R., Chen, H., Lee, D. H., & Zheng, C. (2007). Characteristics of hemicellulose, cellulose and lignin pyrolysis. *Fuel*, 86(12), 1781-1788.
- Yin, Y. J., Yao, K. D., Cheng, G. X., & Ma, J. B. (1999). Properties of polyelectrolyte complex films of chitosan and gelatin. *Polymer International*, 48(6), 429-432.
- Yuan, Y., Zhang, L., Dai, Y., & Yu, J. (2007). Physicochemical properties of starch obtained from *Dioscorea nipponica* Makino comparison with other tuber starches. *Journal of Food Engineering*, 82(4), 436-442.
- Zainuddin, S., Ahmad, I., & Kargarzadeh, H. (2013a). Cassava starch biocomposites reinforced with cellulose nanocrystals from kenaf fibers. *Composite Interfaces*, 20(3), 189-199.
- Zainuddin, S. Y. Z., Ahmad, I., Kargarzadeh, H., Abdullah, I., & Dufresne, A. (2013b). Potential of using multiscale kenaf fibers as reinforcing filler in cassava starch-kenaf biocomposites. *Carbohydrate Polymers*, 92(2), 2299-2305.
- Zhang, L., Xie, W., Zhao, X., Liu, Y., & Gao, W. (2009). Study on the morphology, crystalline structure and thermal properties of yellow ginger starch acetates with different degrees of substitution. *Thermochimica Acta*, 495(1), 57-62.
- Zhang, M. Q., Rong, M. Z., & Lu, X. (2005). Fully biodegradable natural fiber composites from renewable resources: all-plant fiber composites. *Composites Science and Technology*, 65(15), 2514-2525.
- Zhang, Q., He, J., Tian, M., Mao, Z., Tang, L., Zhang, J., & Zhang, H. (2011). Enhancement of methane production from cassava residues by biological pretreatment using a constructed microbial consortium. *Bioresource Technology*, 102(19), 8899-8906.
- Zhang, Y., Gan, T., Li, Q., Su, J., Lin, Y., Wei, Y., & Yang, M. (2014a). Mechanical and interfacial properties of poly (vinyl chloride) based composites reinforced by cassava stillage residue with different surface treatments. *Applied Surface Science*, 314, 603-609.
- Zhang, Y., Gan, T., Luo, Y., Zhao, X., Hu, H., Huang, Z., & Qin, X. (2014b). A green and efficient method for preparing acetylated cassava stillage residue and the production of all-plant fibre composites. *Composites Science and Technology*, 102, 139-144.

Zhang, Y., & Han, J. (2006). Mechanical and thermal characteristics of pea starch films plasticized with monosaccharides and polyols. *Journal of Food Science*, 71(2), E109-E118.

Zhong, Y., & Li, Y. (2014). Effects of glycerol and storage relative humidity on the properties of kudzu starch- based edible films. *Starch- Stärke*, 66(5-6), 524-532.

Zhou, Q., Rutland, M. W., Teeri, T. T., & Brumer, H. (2007). Xyloglucan in cellulose modification. *Cellulose*, 14(6), 625-641.

Zobel, H. (1988). Starch crystal transformations and their industrial importance. *Starch- Stärke*, 40(1), 1-7.



## LIST OF PUBLICATIONS

### Journal articles

- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. (2015). Cassava: Its polymer, fiber, composite, and application. *Polymer Composites*, DOI: 10.1002/pc.23614.
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. (2015). Extraction of Malaysian cassava starch, peel and bagasse and its characterization. *Journal of Food science and technology*, JFST-D-15-01789R2.
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. (2017). Effect of various plasticizers and concentration on the physical, thermal, mechanical and structural properties of cassava starch based films. *Starch*, 69.1-2.
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. (2016). Preparation and characterization of casava starch/peel composite film. *Polymer Composites*, DOI: 10.1002/pc.24121
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. (2017). Preparation and characterization of casava bagasse reinforced thermoplastic cassava starch. *Fibers and Polymers* 18.1: 162-171.
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. (2017). Cassava/sugar palm fiber reinforced cassava starch hybrid composites: physical, thermal and structural properties. *IJBIOMAC\_2016\_1367\_R1*. Accepted .
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. (2017). Tensile, barrier, dynamic mechanical and biodegradation properties of cassava/sugar palm fiber reinforcedncassava starch hybrid composites. *Bioresources*. Under review.

### Conferences/Seminars

- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. Application of cassava and cassava composites. *Postgraduate Symposium on Bio-composite Technology 2015*, Faculty of Engineering, University Putra Malaysia, 3rd March, 2015.
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. Effects of various plasticizers and concentration on physical properties of cassava films. *Postgraduate Symposium on Biocomposite Technology 2015*, Faculty of Engineering, Universiti Putra Malaysia, 3rd March, 2015.

Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. Effect of cassava peel and cassava bagasse natural filler on mechanical properties of thermoplastic cassava starch: Comparative study. Advanced Material Conference. Langkawi, Malaysia. 28-29 November 2016.

Edhirej, A., Sapuan, S. M., Jawaid, M., & Zahari, N. I. Effect of cassava peel and cassava bagasse natural filler on physical properties of thermoplastic cassava starch: Comparative study. 5th Postgraduate Simenar. INTROP. UPM. Malaysia. 28 December 2016.

Award

The best paper on the 5th Postgraduate Simenar. INTROP. UPM. Malaysia. 28 December 2016.





**UNIVERSITI PUTRA MALAYSIA**

**STATUS CONFIRMATION FOR THESIS / PROJECT REPORT AND COPYRIGHT**

**ACADEMIC SESSION :** \_\_\_\_\_

**TITLE OF THESIS / PROJECT REPORT :**

CHARACTERIZATION AND DEVELOPMENT OF CASSAVA (*Manihot esculenta* CRANTZ)  
/ SUGAR PALM (*Arenga pinnata* (WURMB) MERR.) FIBER- REINFORCED CASSAVA  
STARCH HYBRID COMPOSITES

**NAME OF STUDENT:** AHMED FARAJ IBRAHIM HISSEN EDHIREJ

I acknowledge that the copyright and other intellectual property in the thesis/project report belonged to Universiti Putra Malaysia and I agree to allow this thesis/project report to be placed at the library under the following terms:

1. This thesis/project report is the property of Universiti Putra Malaysia.
2. The library of Universiti Putra Malaysia has the right to make copies for educational purposes only.
3. The library of Universiti Putra Malaysia is allowed to make copies of this thesis for academic exchange.

I declare that this thesis is classified as :

\*Please tick (✓)

**CONFIDENTIAL**

(Contain confidential information under Official Secret Act 1972).

**RESTRICTED**

(Contains restricted information as specified by the organization/institution where research was done).

**OPEN ACCESS**

I agree that my thesis/project report to be published as hard copy or online open access.

This thesis is submitted for :

**PATENT**

Embargo from \_\_\_\_\_ until \_\_\_\_\_  
(date) (date)

**Approved by:**

\_\_\_\_\_  
(Signature of Student)  
New IC No/ Passport No.:

Date :

\_\_\_\_\_  
(Signature of Chairman of Supervisory Committee)  
Name:

Date :

**[Note : If the thesis is CONFIDENTIAL or RESTRICTED, please attach with the letter from the organization/institution with period and reasons for confidentially or restricted. ]**