



UNIVERSITI PUTRA MALAYSIA

***DEVELOPMENT AND FORMULATION OF COOLANT AND
NON-CORROSIVE AEROSOL FORMING AGENT SYSTEM***

ZHANG XIAOTIAN

FK 2015 128



**DEVELOPMENT AND FORMULATION OF COOLANT AND
NON-CORROSIVE AEROSOL FORMING AGENT SYSTEM**

By

ZHANG XIAOTIAN

**Thesis submitted to the School of Graduate Studies, Universiti Putra Malaysia, in
Fulfilment of the Requirements for the Degree of Doctor of Philosophy**

November 2015

COPYRIGHT

All materials contained within the thesis, including without limitation text, logos, photographs and all other artworks, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the Degree of Doctor of Philosophy

**DEVELOPMENT AND FORMULATION OF COOLANT AND
NON-CORROSIVE AEROSOL FORMING AGENT SYSTEM**

By

ZHANG XIAOTIAN

November 2015

Chair : Associated Professor Mohd Halim Shah Bin Ismail, PhD
Faculty : Engineering

A newly synthesized non-corrosive and effective aerosol fire extinguishing agent together with an effective coolant for hot aerosol cooling were successfully prepared and their properties and working performances were studied and discussed. The new S-type aerosol forming agent which contains 12.2% potassium nitrate, 44.2% strontium nitrate, 8.0% magnesium powder, 17.5% alpha-lactose, 11.1% ammonium nitrate and 7% epoxy binder was formulated to replace the corrosive K-type aerosol forming agents that currently dominates the aerosol fire extinguishant market. The fire suppression time, combustion reaction, combustion velocity, aerosol phase composition, combustion residue composition, aging profile and corrosion performance of this newly synthesized S-type aerosol forming agent were studied and analyzed. This new S-type aerosol forming agent could extinguish a heptanes pan fire in less than 20s in a 1 m³ compartment and the discharged aerosol particles have surface resistivity larger than 20 MΩ which is the threshold insulation level for protecting the electrical devices and electronics according to the Aerosol Fire Extinguishing System, Part1: Condensed Aerosol Fire Extinguishing Device GA 499.1-2004 and GA 499.1-2010. Moreover, this is the first time in the research field of aerosol fire extinguishing agents that dynamic modeling of combustion temperature and pressure inside an aerosol forming agent canister were successfully achieved. During combustion, the temperature at the canister nozzle would rise to over 1000°C very quickly, thus a substantial cooling of the discharged aerosol using any coolant is compulsory. The simulation of the canister's inner pressure and temperature distribution on the coolant geometry provides instructive information on coolant geometry design and packing pattern of coolant. A packing bed randomly packed with Φ 5 mm kaolinite-based spherical coolants was used to cool down the hot aerosol and its temperature was brought down from 1400°C to below 400°C without any additional coolant. The mass of coolants applied is equal to the mass of the newly synthesized aerosol forming agent and the performance of such kaolinite-based coolant is relatively better than other common coolants used for hot aerosol cooling. Properties such as yield stress, thermal conductivity, water activity as well as manufacturing process of kaolinite-based spherical granulate were studied and discussed. The composition for synthesizing the kaolinite-based coolant used in this study is as follows: 42.8% kaolinite powder, 38.8% water, 8.1% epoxy A&B glue, 10.2% ethyl cellulose, and the evaporation of the absorbed water in the kaolinite mineral plays a major role in hot aerosol cooling.

Abstrak tesis yang dikemukakan Kepada Senat, Universiti Putra Malaysia sebagai memenuhi keperluan untuk Ijazah Doktor Falsafah

**PEMBANGUNAN DAN FORMULASI SISTEM PENDINGIN DAN
PEMBENTUKAN AEROSOL TIDAK HAKIS**

By

ZHANG XIAOTIAN

November 2015

Pengerusi : Profesor Madya Mohd Halim Shah Bin Ismail, PhD
Fakulti : Kejuruteraan

Satu sistem terdiri daripada agen aerosol baharu yang tidak menghakis dan berkesan untuk pemadaman api, beserta satu bahan pendingin yang berkesan. Telah berjaya disediakan. Sifat-sifat serta prestasi kerja kedua-duanya telah dikaji dan dibincangkan. Agen pembentuk aerosol jenis-S yang baharu ini mengandungi 12.2% kalium nitrat, 44.2% strontium nitrat, 8.0% serbuk magnesium, 17.5% laktosa-alpha, 11.1% ammonium nitrat dan 7% pengikat epoksi dicipta untuk menggantikan agen pembentuk aerosol jenis-K yang bersifat menghakis yang mendominasi pasaran pemadam api aerosol masa kini. Masa untuk memadamkan api, tindak balas pembakaran, halaju pembakaran, komposisi fasa aerosol, komposisi sisa pembakaran, profil penuaan, dan prestasi pengurangan bagi agen pembentuk aerosol jenis-S yang baru disintesis ini telah dikaji dan dianalisis. Agen pembentuk aerosol jenis-S baharu ini mampu memadamkan api di dalam bekas berisi heptana kurang daripada 20 saat bagi ruang 1 m³ dan zarah-zarah aerosol yang dibebaskan mempunyai rintangan permukaan melebihi 20 MΩ, iaitu tahap ambang penebat bagi melindungi alatan elektrik dan elektronik menurut Sistem Pemadam Api Aerosol, Bahagian 1: Alatan Pemadam Api Aerosol Memeluwap GA 499,1-2004 dan GA 499,1-2010. Sebagai tambahan, buat kali pertamanya di dalam bidang penyelidikan agen pemadam api aerosol, satu pemodelan dinamik tentang suhu dan tekanan pembakaran di dalam tabung agen pembentuk aerosol telah berjaya diperolehi. Semasa kebakaran, suhu pada muncung tabung boleh meningkat kepada 1000°C atau lebih dengan cepat, maka suhu aerosol yang dilepaskan mesti disejukkan secukupnya dengan menggunakan bahan pendingin. Simulasi tentang tekanan dalaman dan agihan suhu di dalam tabung terhadap geometri bahan pendingin telah memberikan maklumat penting untuk reka bentuk geometri dan pola pemadatan bahan pendingin. Satu turus terpadat yang diisi secara rawak dengan bahan pendingin berasaskan kaolinit, berbentuk sfera dengan diameter 5mm, telah digunakan untuk menyejukkan aerosol panas dan suhunya berjaya diturunkan daripada 1400°C kepada kurang 400°C tanpa menggunakan sebarang bahan pendingin tambahan. Jisim bahan pendingin yang digunakan adalah sama dengan jisim agen pembentuk aerosol yang baru disintesis tersebut dan prestasi bahan pendingin berasaskan kaolinit ini adalah lebih baik daripada bahan-bahan pendingin lain yang biasa digunakan untuk menyejukkan aerosol panas. Sifat-sifat seperti tegasan alah, konduktiviti termal, aktiviti air dan juga proses pembuatan butiran sfera berasaskan kaolinit telah dikaji dan dibincangkan. Komposisi penyediaan bahan pendingin berasaskan kaolinit yang digunakan di dalam kajian ini

adalah seperti berikut: 42.8% serbuk kaolinit, 38.8% air, 8.1% pekat epoksi A & B, 10.2% etil selulosa dan penyejukan air yang terserap pada mineral kaolinit memainkan peranan penting dalam penyejukan aerosol panas.



ACKNOWLEDGEMENTS

Here I sincerely appreciate the guidance and help from my supervisor Assoc. Prof. Dr. Mohd Halim Shah Bin Ismail and committee member Prof. Dr. Fakhru'l-Razi Bin Ahmadun and Assoc. Prof. Dr. Norhafiza Binti Abdullah, and the assistance from Pyrogen Sdn Bhd. The thesis cannot be accomplished without the care and support from them and also thanks to Mohd Yusof Bin Harun, who helped me translate the abstract into Bahasa Malaysia.



I certify that a Thesis Examination Committee has met on 24 November 2015 to conduct the final examination of Zhang Xiao Tian on his thesis entitled “Development and Formulation of Coolant and Non-Corrosive Aerosol Forming Agent System” in accordance with the Universiti and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U. (A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

Saari bin Mustapha, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Desa bin Ahmad, PhD

Professor Ir.
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Nor Mariah binti Adam, PhD

Associate Professor Ir.
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Changkook Ryu, PhD

Associate Professor
Sungkyunkwan University
Korea
(External Examiner)



ZULKARNAIN ZAINAL, PhD
Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 16 February 2016

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Mohd Halim Shah Ismail, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Fakhrul-Razi Bin Ahmadun, PhD

Professor
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Norhafiza Binti Abdullah, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Member)

BUJANG BIN KIM HUAT, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/ fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: _____ Date: _____

Name and Matric No.: Zhang Xiaotian, GS32037

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____
Name of
Chairman of
Supervisory
Committee: Mohd Halim Shah Ismail, PhD

Signature: _____
Name of
Member of
Supervisory
Committee: Fakhru`l-Razi Bin Ahmadun, PhD

Signature: _____
Name of
Member of
Supervisory
Committee: Norhafiza Binti Abdullah, PhD

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	ii
ACKNOWLEDGEMENTS	iv
APPROVAL	v
DECLARATION	vii
LIST OF TABLES	xi
LIST OF FIGURES	xii
LIST OF ABBREVIATIONS	xiv
LIST OF NOMECLACTURES	xv
CHAPTER	
1 INTRODUCTION	1
1.1 Background	1
1.2 Problem statement and hypothesis	2
1.3 Importance of study	3
1.4 Objectives	3
1.5 Scope and limitations of study	4
1.6 Thesis layout	4
2 LITERATURE REVIEW	5
2.1 Introduction	5
2.2 Briefing of hot aerosol fire extinguishing technology	5
2.3 Hot aerosol fire extinguishing mechanism	7
2.4 Hazards concerns regarding hot aerosol fire extinguishant	11
2.5 Hot aerosol fire extinguishing agent ingredients	14
2.6 K and S-type hot aerosol fire suppression agents	19
2.7 Design and applications of hot aerosol fire extinguishant	21
2.8 Cooling agent of hot aerosol fire extinguishing technology	24
2.9 Summary	25
3 MATERIALS AND METHODS	28
3.1 Introduction	28
3.2 Materials	31
3.3 Experimental and modeling methods	32
3.3.1 Synthesis of new S-type hot aerosol agent	32
3.3.1.1 Aerosol forming agent preparation	32
3.3.1.2 Aerosol fire extinguishing and anti-corrosion test	32
3.3.1.3 Characterization of aerosol forming agent	33
3.3.2 New S-type AFA combustion modeling	36
3.3.2.1 Nozzle temperature modeling	36
3.3.2.2 Inner canister pressure modeling	37
3.3.3 Hot aerosol coolant design	37
3.3.3.1 Temperature distribution study	38
3.3.3.2 Coolant yield stress and water activity test	38
3.3.3.3 Coolant thermal conductivity test	38

3.3.3.4	Cooling efficiency test	38
4	RESULTS AND DISCUSSION	40
4.1	Introduction	40
4.2	Synthesis of new S-type hot aerosol agent	40
4.2.1	Ingredients optimization and results	40
4.2.2	Fire extinguishing test of newly synthesized AFA	44
4.2.3	Performance of new S-type aerosol forming agent	46
4.3	S-type aerosol agent combustion modelling	62
4.3.1	Unsteady instant-mixing model of heat and temperature	62
4.3.2	Unsteady inner pressure modeling with packing bed	66
4.4	Hot aerosol coolant design	73
4.4.1	Temperature distribution study	74
4.4.2	Coolant granulates synthesis and property characterization	80
4.4.3	Cooling efficiency of synthesized coolant granulate	84
4.5	Discussion	86
5	SUMMARY AND RECOMMENDATION	90
	REFERENCES	94
	APPENDICES	98
	BIODATA OF STUDENT	101
	LIST OF PUBLICATIONS	102

LIST OF TABLES

Table		Page
2.1	Comparison of suppressive mechanisms of common extinguishing agents with hot aerosol technology	6
2.2	Oxidants in hot aerosol forming agent publicized	16
2.3	Reductants in hot aerosol forming agent publicized	18
2.4	C ₂ and K _v values under different conditions	23
2.5	Key Characteristics of Major Extinguishants in Market	23
2.6	Application Areas of Hot Aerosol Extinguishing Agents	24
2.7	Hot aerosol extinguisher coolant	25
3.1	Pugh table for fire suppression agen	30
4.1	Mass of oxygen produced/consumed per each component	41
4.2	Compositions based on Mg/Alpha-Lactose ratios	42
4.3	Compositions based on potassium nitrate/strontium nitrate ratios	43
4.4	Residue mass after aerosol forming agent combustion	48
4.5	Elements analysis of condensed aerosol particles	48
4.6	Elements analysis of residue	50
4.7	Experimental mass ratio of solid to gas	52

LIST OF FIGURES

Figure		Page
2.1	Classifications of hot aerosol fire suppression products	6
2.2	An influence of some aerosols on flame temperature of hydrogenmethane mixture	7
2.3	Sodium hydroxide concentration Vs radical concentration in methane-air mixture	8
2.4	Penetration of particulates in human lung	12
2.5	Alkali metal aerosols influence on hydrogen concentration in a flame of mixture of hydrogen and oxygen	15
2.6	Ions size and oxides boiling point of K-type and S-type elements	20
2.7	Integral blocks of hot aerosol extinguishing system	22
3.1	Research methodology flow chart	29
3.2	Canister structure and testing compartment layout	35
3.3	Front view of testing compartment, iron stand and canister	35
3.4	Close view of iron stand, canister and cup fire of n-heptane	36
3.5	S-type AFA combustion and aerosol discharge	37
3.6	Water chestnut shape roller and pill making machine	39
4.1	Binding time & yield stress Vs epoxy binder mass ratio	43
4.2	Potassium/strontium and Mg/alpha-lactose mass ratio ⁴ Vs fire suppression time	44
4.3	Extinguishing time and relative STD Vs ammonium nitrate mass ratio	46
4.4	Theoretical calculation of redox products composition by Visual Basic	47
4.5	Porosity Vs burning speed	53
4.6	Decomposition of new AFA under 55°C	54
4.7	Decomposition of new AFA under 85°C	55
4.8	DSC of new aerosol forming agent	56
4.9	Heating of pure ammonium nitrate under 55 and 85°C	57
4.10	Heating of new AFA under 55 and 85°C	58
4.11	Heating of pure α -lactose under 55 and 85°C	59
4.12	Aging of new AFA under different working temperatures	60
4.13	DSC of new AFA without ammonium nitrate	61

4.14	Comparison of corrossions on copper plate caused by K-type and new AFA aerosol particles	62
4.15	Heat and temperature transportation in AFA canister	63
4.16	Predicted nozzle temperature and experimental points	66
4.17	Change of state function (P, V & T) during AFA combustion in a anister	67
4.18	Relative inner pressures with different packing porosities	70
4.19	Main factorial effects on averaged relative inner pressure	72
4.20	Mutual factorial effects on averaged relative inner pressure	73
4.21	Perforated cylinder block in cylindrical coordination	74
4.22	Dynamic change of temperature within a perforated cylindrical coolant	77
4.23	Cooling process of perforated cylindrical shape coolant	78
4.24	Free random motion of aerosol in granulates packing bed	79
4.25	Yield stress Vs kaolinite/water ratio and epoxy binder ratio	81
4.26	Water activity Vs kaolinite and water ratio	82
4.27	Thermal conductivity of kaolinite-water-AB binder, AlN and montmorillonite mixture	84
4.28	Nozzle temperature Vs coolant mass applied	85
4.29	Comparison of different coolants	86

LIST OF ABBREVIATIONS

AFA	aerosol forming agent
ALT	Atmospheric Lifetime
DSC	Differential Scanning Calorimetry
G1	Generation 1
G2	Generation 2
G3	Generation 3
GWP	Global Warming Potential
LOAEL	Lowest Observed Adverse Effect
Max	Maximum
ODE	Ordinary Differential Equation
ODP	Ozone Depletion Potential
PCCs	Phosphorus Containing Compounds
PDE	Partial Differential Equation
PVC	Poly Vinyl Chloride
R&D	Research and Development
Redox	Reduction-oxidation
SEM-EDX	Scanning Electron Microscopy with Energy Dispersive X-ray spectroscopy
STD	standard deviation

LIST OF NOMENCLATURES

Symbol	Definition	SI Unit
A	Intersection area of tank	m ²
A _N	Cross section of canister	m ²
A _{in}	Inner surface area of canister	m ²
a _v	Volume function constant	m ³ /s ²
b	Canister wall thickness	m
b _v	Volume function constant	m ³ /s
c	Void of packing bed	m ³
C ₂	Designed fire extinguishing concentration	kg/m ³
C _{pc}	Steel canister heat capacity	J/g•K
C _{pi}	Heat capacity of each reactant and product	J/g•K
\bar{C}_{pg}	Average heat capacity of aerosol gases	J/g•K
\bar{C}_{ps}	Average heat capacity of aerosol particles	J/g•K
d _p	Diameter of primary particles	m
D	Diffusion coefficient	m ² /s
D _f	Fractal dimension	∅
D _p	Equivalent spherical diameter of the packing granulate	m
g	Gravitational acceleration	m/s ²
i	Emissions source for primary particles	
j	Particle size	m
K	Compensation coefficient	∅
k _f	Fractal prefactor	∅
K _v	Volume correction coefficient	∅
K _{TC}	Total heat transfer and conduction coefficient	W/m ² •K
L	Packing bed length	m
L _a	Height of AFA block	m
L _c	Length of canister cylinder	m
m	Number of particle of different sizes	∅
M	Dosage	kg

M_c	Canister mass	kg
\overline{M}_g	Average gases molar mass	g/mol
n	Number of primary particles	∅
N	Number density	m^{-3}
N_A	Avogadro number	mol^{-1}
P_o	Atmospheric pressure	Pa
$Q_{Accumlated}$	Accumulated heat	J/s
Q_e	Extinction coefficient	∅
Q_s	Scattering coefficient	∅
Q_{in}	Source heat generated	J/s
Q_{out}	Heat flux leaving canister	J/s
$Q_{Phase\ change}$	Phase change heat	J/s
Q_r	Radiation heat	J/s
Q_{TC}	Transfer and convection heat	J/s
r_i	Inner radius of canister cylinder	m
r	Numerical radius of particles	m
R	Ideal gas constant	J/mol•K
RAB	Mass ratio of Epoxy A&B binder	∅
Re	Effective forming agent dosage per storage area of tank	kg/m ²
R_g	Radius of gyration of an aggregate	m
RK	Mass ratio of kaolinite	-
RKW	Mass ratio of kaolinite/ water	-
Rw	Mass ratio of water	-
T_0	Initial coolant body temperature	K
$T_{Ae}(t)/T$	Temperature of hot aerosol	K
T_{Air}	Atmospheric temperature	K
T_B	Temperature on outer surface of perforated coolant cylindrical	K
T_I	Redox temperature of AFA block	K
T_H	Inner surface temperature of canister wall	K
T_L	Outer surface temperature of canister wall	K
T_{ND}	Aerosol temperature at nozzle	K

V	Volume under protection	m^3
V_c	Gaseous volumetric flow	m^3/s
V_e	Aerosol velocity passing through an empty canister	m/s
V_s	Average velocity of gases leaving the canister at the nozzle	m/s
W	Burning rate of AFA	kg/s
W_a	Kaolinite based clay water activity	-
W_d	Designed dosage	kg
X	Molar ratio	\square
Y	Kaolinite based clay yield stress	kPa
α_c	Inversed heat diffusivity of coolant material	s/m^2
α_i	Convection heat transfer coefficient	$W/m^2 \cdot K$
α_g	Gas adsorbance	\square
α_o	Natural convection heat transfer coefficient	$W/m^2 \cdot K$
δ	Thickness of perforated cylinder wall	m
ε	Packing porosity	-
η	Dynamic viscosity of disperse medium	$Pa \cdot s$
λ_m	Conductivity of canister wall	$W/m \cdot K$
μ_g	Aerosol gases dynamic viscosity	$Pa \cdot s$
v	Terminal velocity of spherical particles	m/s
ε_g	Gas emittance	\square
ε_m	Canister wall emittance	\square
ρ	Density of particles	kg/m^3
ρ_0	Density of disperse medium	kg/m^3
ρ_g	Density of aerosol gases	kg/m^3
σ	Blackbody radiation constant	$W/m^2 \cdot K^4$
u_i	Stoichiometric number	\square

CHAPTER 1

INTRODUCTION

1.1 Background

Fire extinguishing technology has long been developed in modern human history, and so far it can be classified into inert gas, CO₂, halogen agent, foam, dry powder, water mist or stream and condensed aerosol fire suppression systems. For inert gas and CO₂ fire suppression system, it uses pre-sorted high pressure inert gas or CO₂ for fire extinguishing by cooling and choking of fires through local or total flooding application, but the quantity needed is high and inert gas or CO₂ can cause choking or freezing hazards to humans when they are applied during fire suppression. Halogen fire extinguishing systems like Halon fire suppression systems were once very popular in the market due to its high fire suppression efficiency, but as the problem of ozone depletion caused by using Halon extinguishing agents which contain bromofluoroalkanes (Andrzej & Tsang, 1997), many countries joined the Montreal Protocol which announced the protective actions for ozone layer in 1987, and such act promoted the phase out of Halon extinguishants. Foam fire suppression system is quite efficient for Class B fire (combustible liquid) extinguishing and it forms a foam layer on the combusting liquid and chokes the fire, but such fire suppression system requires large amount of foams and the foams are hard to clean. Dry powder fire suppression system (e.g. ABC powder fire suppression system) has the caking and deliquescence problem of powders and the powders for fire suppression is dirty and corrosive to the environment. Also it is hard to apply dry powder fire suppression system in a total flooding fire suppression mode. Water stream fire extinguishing is clean and cheap, but it has low fire extinguishing efficiency, and water mist fire extinguishing system requires highly pressurized delivery system for a total flooding fire suppression mode.

With the development of fire science and fire technology, new aerosol fire suppression system which includes pre-dispersed particles (cold aerosol) fire suppression and condensed/pyrotechnic aerosol (hot aerosol) fire extinguishing system has been widely applied nowadays. The fire extinguishing mechanism behind condensed aerosol fire suppression is combustion radicals binding and choking. Especially in recent years, hot aerosol fire extinguishing technology has attracted more and more attentions, and such fire extinguishing system is highly efficient compared to traditional fire suppression systems like inert gas, CO₂ and water stream systems. In Malaysia, the market for hot aerosol fire extinguishing system is still growing, some local companies and manufacturers like "Pyrogen Manufacturing Sdn Bhd" has become one of the leader in local hot aerosol fire suppression system manufacturing and distribution. So it is interesting and important to conduct a research on hot aerosol fire extinguishing technology to help better promote the application of such technology in Malaysia.

Hot aerosol fire extinguishing technology was first proposed in 1960s based on pyrotechnics technology in rocket science and it continues developing since then. Hot

aerosol extinguishing agents have high efficiency in fire extinguishing and they do not need to be stored in a pressurized container since they do not need to be driven out by pressurized inert gases. A hard block of hot aerosol fire extinguishing agent sits in an extinguisher canister which has a perforated cap called nozzle, and a fuse attached to the canister ignites the aerosol forming agent to generate the fire extinguishing aerosol which is carried out by aerosol gases produced.

Different from traditional or cold aerosol extinguishing agents, during combustion of hot aerosol fire extinguishing agent, hot aerosol colloids with diameters from 10^{-9} to 10^{-7} meters are generated by redox (reducing-oxidizing) reaction of components in hot aerosol forming agent. Those colloids have diameters much smaller than 4×10^{-6} m at which Brownian motion starts to occur (Fu et al., 2001) and those tiny aerosol particles have high diffusivity and long time to suspend in a fire zone for fire fighting. Generally, the mechanisms behind fire suppression by hot aerosol fire extinguishing agents are both physical and chemical. Physical mechanisms include oxygen isolation and temperature cooling, while chemical mechanism is recombination of fire supporting radicals.

Aerosol forming agent block can be stored under the atmospheric pressure and have low Ozone Depletion Potential (ODP) and Global Warming Potential (GWP) values (Guo & Yue, 2008). Through 40 years development of hot aerosol fire suppression technology, it has come to the third generation of aerosol fire suppression agent which is called S-type (G3) hot aerosol extinguishing agent using strontium nitrate as main oxidant in the aerosol forming agent. But currently, traditional K-type (G2) aerosol fire extinguishing agent which uses potassium nitrate as major oxidant in its hot aerosol forming agent is still dominant in the market of hot aerosol fire extinguishing agents.

1.2 Problem statement and hypothesis

Hot aerosol fire suppression system is a new fire suppression system which is not well developed compared to inert gas, CO_2 , halogen agent, foam and water mist or stream fire suppression system, so is the fire suppression agent used in hot aerosol fire suppression system. Aerosol particles generated by K-type product are corrosive to electrical devices and electronics, thus it is very necessary to develop a non-corrosive hot aerosol fire suppression agent. Also this research purposes to analyze the physical and chemical properties of the novel hot aerosol forming agent synthesized and aims to model and calculate the aerosol temperature and pressure dynamics during aerosol forming agent combustion inside the canister since little knowledge is known about the combustion process of hot aerosol forming agent in a canister. Last, high temperature of aerosol discharged during aerosol forming agent combustion is still a problem which limits the application of hot aerosol fire suppression system, so this research will design and synthesize a new coolant system for hot aerosol cooling.

The current research also hypothesizes that:

1. Corrosion problem caused by K-type hot aerosol forming agent can be largely alleviated by applying a new S-type hot aerosol forming agent.
2. Models can be established to predict the canister nozzle temperature and understand the inner canister pressure during new S-type aerosol forming agent combustion.
3. A cooling bed composed of novel synthesized coolants can efficiently reduce the temperature of hot aerosol compared to some traditionally used coolants.

1.3 Importance of study

This research deals with the synthesis and property analysis of a novel non-corrosive hot aerosol forming agent which can be applied in occasions where delicate electronics and electrical equipments or important archives are presented. Also the research will synthesize efficient coolants for hot aerosol cooling and a hot aerosol fire suppression system which adopts the new non-corrosive hot aerosol forming agent and the new coolants can be widely used and capable to replace the current corrosive K-type hot aerosol fire suppression systems.

Moreover, this research will establish models to describe dynamic changes of nozzle temperature and inner canister pressure during novel hot aerosol forming agent combustion for the design of an efficient coolant system and it helps to increase our knowledge and understanding of the combustion process of hot aerosol forming agent.

1.4 Objectives

The general objective is to develop a new S-type fire suppressive hot aerosol forming agent which generates non-corrosive aerosol to most electronics and electrical devices, and understand the new S-type aerosol combustion process to develop a coolant part for the hot aerosol cooling. The specific objectives are following:

1. To formulation and optimization of a novel non-corrosive aerosol forming agent which is effective in fire extinguishing. The corrosiveness and fire suppression efficiency of the novel non-corrosive aerosol forming agent should meet the requirements in Standards GA 499.1-2010.
2. To synthesize new coolants which are kaolinite based and design the coolant packing pattern for the hot aerosol fire suppression agent. The cooling efficiency of the new coolant system should be high and stable compared to other commonly used coolants for hot aerosol cooling.

3. To model the dynamic changes of nozzle temperature and inner canister pressure based on redox/combustion process study of the novel non-corrosive hot aerosol forming agent.
4. To compare the predicted nozzle temperature with experimental data.

1.5 Scope and limitation of study

The current research only focuses on the synthesis of a new non-corrosive aerosol forming agent, nozzle temperature and inner canister pressure modeling and synthesis of a new type of coolant and its packing design for the hot aerosol cooling. The research will not deal with the design and installation of the hot aerosol fire extinguishing canister/extinguisher, nozzle and ignition system. The whole hot aerosol fire suppression system is a comprehensive and complicated system, and it is impossible to cover all the aspects of hot aerosol fire suppression technology in the current research. Currently, the application of hot aerosol fire suppression system is limited to countries as USA, Russia and China, etc, and it has not been applicable in Malaysia.

1.6 Thesis layout

The thesis is composed of five Chapters. Chapter 1 is “introduction” which includes background, problem statement and hypothesis, importance of study, objectives, scope and limitations of study and thesis layout. Chapter 2 is “literature review” which describes the develop history, fire suppression mechanism, chemical properties and applications of fire suppressive hot aerosol forming agent and the types, properties and applications of hot aerosol coolants. Chapter 3 is “materials and methodology” regarding the formation of research objectives, experimental designs, data collection and analyses. Chapter 4 is “results and discussions” which explains the data and phenomena collected and observed from the experiments and modeling. Last, Chapter 5 is “summary and recommendation” which concludes the finds and contributions of the study.

REFERENCES

- Aerosol fire extinguishing system (2010), Part1: Condensed aerosol fire extinguishing device. GA 499.1.
- Aerosol fire extinguishing system (2004), Part1: Condensed aerosol fire extinguishing device. GA 499.1.
- Agafonov, V.V., Kopylov, S.N., Sychev, A.V., Uglov, V. A & Zhyganov, D. B. (2005). The Mechanism of Fire Suppression by Condensed Aerosols, Proceedings of the 15th HOTWC, Albuquerque, NM.
- Akeredolu, F.A. (1996). Environmental Engineering Notebook. Department of Chemical Engineering, Obafemi Awolowo University, Ile-Ife, Nigeria.
- Andrzej, W.M. & Tsang, W. (1997). Halon Replacements: Technology and Science, ACS Symposium Series, Washington D.C., U.S.
- Baratov, A.N., Baratova, N.A. & Myshak, Y.A. (1998). Practice Of Use Of Aerosol Extinguishing Agents Obtained By Combustion Of Propellants, AOFST Symposiums 3.
- Barin, I. (1989). Thermochemical data of pure substances. VCH Publisers, New York.
- Birchall, J.D. (1970). On the Mechanism of Flame Inhibition by Alkaline Metal Salts. *Combust. Flame.* (14): p.85.
- Block, J.L. (1953). The Thermal Decomposition of Nitroguanidine; NAVORD Report 2705.
- Chen, Z.H. & Yang, R.J. (2003). An Assessment Approach for Halon substitute technique. *Fire Safety Sci.*12(2): p.115.
- Compression Testing of Composites (2010). ASTM D695-10.
- Denisyuk, A. P., Michalev, B. D., Rusin, L. & Germanovich, S.Y. (2003). Pyrotechnical aerosol-forming fire-extinguishing composite and a method of its production. EP 1341587 A2.
- Design code for insulation engineering of industrial equipment and pipe. GB 50264-97:
- Fu, S. & Yao, H. (2001). Physical Chemistry. High Education Press, Beijing.
- Fu, Z.M., Huang, J.Y. & Yang, R.J (2003). The study of thermal decomposition and combustible characteristic of solid micro particle aerosol fire extinguishant. *Fire Techni. & Products Info.* (4): p.46.
- Guo, H.B., Hu, J.G. & Zheng, Y.Y. (2011). A composition of hot aerosol extinguishing agent. CN 101376049 B.
- Guo, H.B., Yue, D.K. (2008). Aerosol Fire Extinguishing Technology. Chemical Industry Press, Beijing.

- Guo, H.B. & Zhang, Z.F. (2012). Fire-Extinguishing Aerosol Composition for Heavy Current Electric Apparatuses. US 8097667 B2.
- Hu, J.G. (2003). The Cooling Technology of Hot Gas Dispersoid. *Initiators & Pyrotechnics*. (4): p.33.
- Hu, Y.H. (2009). Steam hot aerosol fire-extinguishing composition and application method and fire extinguishing device thereof. CN 101376049 A.
- Hu, Y.H. (2011). Steam hot aerosol fire-extinguishing composite and application method and fire extinguishing device thereof. CN 101554520 B.
- Insley, H. & Ewell R.H. (1935). Thermal behavior of the kaolinite minerals. *research paper rp792- Part of Journal of Research of the National Bureau of Standards*. 14: 615-627.
- Jayaweera, T.M., Fisher E.M. & Fleming, J.W. (2005). Flame suppression by aerosols derived from aqueous solutions containing phosphorus. *Combust. Flame*. (141): p.308.
- Ji, T. & Wei, T. (2013). Fire extinguishing composition of copper salts. WO2013023576 A1.
- Jiang, W.J., Dai, Y.Y. & Gu, H.J. (2003). Unit Operation of Chemical Engineering (I). Tsinghua University Press, Beijing.
- Jimoda, L.A. (2012). Effects of Particulate Matter on Human Health, The Ecosystem, Climate and Materials: A Review. *Series: working Living Environ. Prot.* 9(1): p.27.
- Jullien, R., Botet, R. (1987). Aggregation and Fractal Aggregates. World Scientific, Singapore.
- Korobeinichev, O.P., Shmakov, A.G., Chernov, A.A., Bol'shova, T.A., Shvartsberg, V. M., Kutsenogii, K. P. & Makarov, V. I. (2010). Fire Suppression by Aerosols of Aqueous Solutions of Salts. *Combust Explos Shock Waves*. 46(1): p.16.
- Korobeinichev, O.P., Shmakov, A.G., Shvartsberg, V.M., Yakimov, S.A., Kutsenogii, K. P. & Makarov, V. I. (2012). Fire suppression by low-volatile chemically active fire suppressants using aerosol technology. *J. Fire Safety* (51): p.102.
- Kozyrev, V.N., Yemelyanov, V.N., Sidorov, A.I. & Andreev, V.A. (1997). Aerosol-forming composition for the purpose of extinguishing fires. US 5,831,209.
- Kunrath, J.I., Müller, C.S. & Frank, E. (1978). Thermal decomposition of potassium hexacyanoferrate(II) trihydrate. *J. Therm. Anal.* 14(3): p.253.
- Kwon, K. & Kim Y. (2013). Extinction effectiveness of pyrogenic condensed-aerosols extinguishing system. *Korean J. Chem. Eng.* 30(12): p.2254.
- Larson, E.R. (2003). Halogenated Flame Extinguishants-Some Additional Support for the Physical Mechanism. *J. Fire Sci.* (23): p.93.

- Liu, J.X. & Dong, H.B. (2004). Insulation test on the after-discharge precipitate of different kinds of Aerosol. *Fire Sci. & Technol.* 23(2): p.168.
- Meakin, P. (1983). The Vold-Sutherland and Eden models of cluster formation. *J. Colloid Interface Sci.* (96): p.415.
- Pak, Z.P., Mikhailova, M.I., Zhukov, B.P., Krivosheev, N.A., Zhegrov, E.F., Ivankov, L.D., Telepchenkov, V.E., Khalilova, I.B., Rodina, N.A., Chui, G.N., Votyakov, A.G., Agafonov, D.P., Militsyn, G.A. & Deruzhinsky, V.I. (1998). Aerosol-Producing Fire Extinguishant. CA 2089901.
- Petronella, A. & Leenders M. (2003). Gas-generating preparation and use thereof in an air bag. EP 0844223 B1.
- Posson, P.L & Clark, M.L. (2012). Flame Suppressant Aerosol Generate. US 8182711 B2.
- Qiao, H.T., Yang, R.J. & Li, X.D. (2001). Research on Lowering the Flame Temperature of Aerosol-Generating Agent Using Additives. *Chinese J. Explo. & Propell.* (2): p.42.
- Richardson, A.T., Bennett, J.M. (2008). System and Method for Suppressing Fires. US 7455120 B2.
- Schönherr, J. (2002). Foliar Nutrition Using Inorganic Salts: Laws of Cuticular Penetration, ISHS Acta Horticulturae 594, Merano, Italy.
- Sheinson, R.S., Penner-Hahn, J.E. & Indritz, D. (1989). The Physical and Chemical Action of Fire Suppressants. *J. Fire Safety.* (15): p.437.
- Song, R.G. (2003). Cooling Technique of Hot Aerosol. *Fire Techni. & Products Info.* (10): p.17.
- Standard Test method for Assessing the Thermal Stability of Chemicals by Method of Thermal Analysis (1998). ASTM E537-98.
- Stern, A.C., Turner, D.B. & Boubel, R.W. (1984). Fundamental of Air Pollution. Academic Press, London.
- Wang, Q., Li, J.Z., Wei, H.J. et al. (2010). Review on Azotetrazolate Nonmetal Salts. *Chinese J. Energ. Mater.* 18(5): p.592.
- Wanigarathne, P.C., Krauss, R.H., Chelliah, R.J. & Davis, R.J. (2000). Fire Suppression by Particles Containing Metallic Compounds, HOTWC, Albuquerque, NM.
- Williams, B.A. & Fleming, J.W. (1999). Suppression Mechanisms of Alkaline Metal Compounds, HOTWC, Albuquerque, NM.
- Yang, J. (2009). Fire Extinguishment Mechanism and Influence of Aerosol Fire Extinguishment Agent. *J. Southern Yangtze Uni. (Nat. Sci. Ed).* 2(3): p.303.

- Yang, R.J. & Fu, Z.M. (2000). Properties and Fire Extinguishment Mechanism of Pyrotechnic Aerosol. *Initiators & Pyrotechnics*. (4): p.1.
- Ying, Q., Mysliwiec, M., Kleeman, M.J. (2004). Source Apportionment of Visibility Impairment Using a Three-Dimensional Source-Oriented Air Quality Model. *Environ Sci. Technol.* (38): p.1089.
- Yuan, J.Z. & Xia, H.F. (1997). Fine processing and whitening of mineral kaolinite by calcination. *China Non-metallic Mining Industry*. S1.
- Zhang, J.B., Tan, Z.C., Meng S. H. et.al. (1997). Heat capacity and thermal decomposition of dicyandiamide. *Thermochimica Acta*. (307): p.11.
- Zhang, S.R., Shan, J.J., Zhu, Y. et al. (2013). Restructuring Transition Metal Oxide Nanorods for 100% Selectivity in Reduction of Nitric Oxide with Carbon Monoxide. *Nano Lett.* 13(7): p.3310.
- Zhao, Y., Zhang, J.W. & Jia, L.W. (2004). Aerosol fire-extinguishing agent. *Tianjin Chemical Industry*. 18(2): p.7.
- Zhang, Y.F., Liao, G.X., Zhou, X.M., Pan, R.M. & Wang, H. (2006). The Experimental Study of Controlling the Spout Temperature of HEAE. *Eng. Sci.* 8(3): p.79.
- Zhou, X.X., Kazuyuki, M., Wu, J.Z., Yo, Y., Takeshi, T. & Kaoru, Y. (2013). Basic metal nitrate, process for producing the same and gas generating agent composition. US8613821 B2.
- Zhu, C.G., Wang, J., Xie, W.X. et al. (2013). Improving Strontium Nitrate-Based Extinguishing Aerosol by Magnesium Powder. *Fire Technol.* online: <http://link.springer.com/article/10.1007%2Fs10694-013-0361-6>.