



**UNIVERSITI PUTRA MALAYSIA**

***CHARACTERIZATION OF MULTI-WALL CARBON  
NANOTUBE/MULTILAYER  
GRAPHENE FIBRE-REINFORCED SOLDER ALLOY  
COMPOSITES***

**NIMA GHAMARIAN**

**FK 2018 3**



**CHARACTERIZATION OF MULTI-WALL CARBON NANOTUBE/MULTI-LAYER GRAPHENE FIBRE-REINFORCED SOLDER ALLOY COMPOSITES**

By

**NIMA GHAMARIAN**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,  
in Fulfillment of the Requirements for the Degree of Doctor of Philosophy**

**September 2017**

## **COPYRIGHT**

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



## DEDICATION

**Dedicated to my family for their love, support and encouragement**



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Doctor of Philosophy

## **CHARACTERIZATION OF MULTI-WALL CARBON NANOTUBE/MULTI-LAYER GRAPHENE FIBRE-REINFORCED SOLDER ALLOY COMPOSITES**

By

**NIMA GHAMARIAN**

**September 2017**

**Chairman : Associate Professor Azmah Hanim Mohamed Ariff, PhD**  
**Faculty : Engineering**

In this study, the metallurgical effect of multi-wall carbon nanotube (MWCNT) and multi-layer graphene (MLG) on the eutectic Bi-Ag alloy were explored. Plain Bi-2.5Ag and its reinforced solder systems (Bi-2.5Ag + xMWCNT/ xMLG, x= 0.01, 0.03, 0.05, 0.07 and 0.1 wt%) were investigated through melting temperature, electrical conductivity, corrosion behavior, wettability and mechanical strength. The composite samples were produced following the powder metallurgy method. The results presented for mechanical alloying demonstrate that this method was a suitable technique for dispersing MWCNT and MLG in Bi-Ag powders. Overall, MWCNT and MLG increased the melting point. The maximum melting point recorded when 0.1 wt% of nano particles was in the matrix as 272.02 °C and 269.62 °C for MWCNT and MLG, respectively. It was found that for both reinforced nano particles in the matrix, the electrical resistivity decreased; while, the effect of MWCNT on the electrical resistivity of the solder matrix was more than MLG. The maximum decrease of resistivity was observed for the sample with 0.1 wt% of nano particles which is 1.89 ( $\mu\Omega\cdot\text{cm}$ ) for MWCNT and 2.53 ( $\mu\Omega\cdot\text{cm}$ ) for MLG. The result showed that MWCNT and MLG improved the Bi-2.5Ag wettability. However, it was observed that MLG decreases the wetting angle more than MWCNT. The corrosion behavior of Bi-2.5Ag and its composite samples with MWCNT and MLG was investigated by an electrochemical technique. The results from Tafel plot curves which were run in three different acidic electrolytes illustrated that the corrosion rate for all the composite samples increased. Furthermore, it was deduced that the corrosion rate and passivation were the functions of the electrical conductivity of the sample, the electrical conductivity of electrolyte and the number of  $\text{H}^+$  in the corrosive electrolyte. Adding MWCNT and MLG to the Bi-2.5Ag improved the shear strength. However, it was observed that the shear stress of Bi-2.5Ag by adding MWCNT and MLG nano particles just improved to some particular weight percentages of nano particles in the

matrix which were 0.07 wt% for MWCNT and 0.05 wt% for MLG. In a nutshell, adding MWCNT and MLG nano particles to Bi-2.5Ag solder matrix improved the melting behavior, electrical conductivity, wettability and shear strength but negatively impact the corrosion behavior.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**PENCIRIAN KARBON NANOTIUB BERBILANG DINDING/GRAFIN  
BERBILANG LAPIS SERAT MEMPERKUKUH ALOI PATERI KOMPOSIT**

Oleh

**NIMA GHAMARIAN**

**September 2017**

**Pengerusi : Profesor Madya Azmah Hanim binti Mohamed Ariff, PhD**  
**Fakulti : Kejuruteraan**

Yang demikian, dalam kajian ini, kesan metalurgi karbon nanotub berbilang dinding (MWCNT) dan grafin pelbagai lapisan (MLG) dalam eutektik Bi-Ag telah diterokai. Bi-2.5Ag yang diperkukuh dengan pateri sistem (Bi-2.5Ag + xMWCNT / xMLG,  $x = 0.01, 0.03, 0.05, 0.07$  dan  $0.1$  wt%) telah dikaji melalui suhu lebur, pengaliran elektrik, tingkah-laku hakisan, kebole basahan dan kekuatan mekanikal. Sampel komposit dihasilkan menggunakan kaedah metalurgi serbuk. Keputusan yang diperolehi untuk pengalioian mekanikal menunjukkan bahawa kaedah ini adalah satu teknik yang sesuai untuk menyebarkan MWCNT dan MLG dalam serbuk Bi-Ag. Secara keseluruhannya, MWCNT dan MLG telah meningkatkan suhu takat lebur bahan. Takat lebur maksimum direkodkan apabila  $0.1$  wt % zarah nano berada di dalam matriks iaitu  $272.02$  °C dan  $269.62$  °C untuk MWCNT dan MLG. Didapati bahawa untuk kedua-dua zarah nano diperkuat matriks, ketahanan elektriknya berkurangan; manakala, kesan MWCNT pada ketahanan elektrik pateri adalah melebihi daripada MLG. Penurunan maksimum ketahanan diperhatikan bagi sampel dengan  $0.1$  wt% zarah nano iaitu  $1.89$  ( $\mu\Omega\cdot\text{cm}$ ) MWCNT dan  $2.53$  ( $\mu\Omega\cdot\text{cm}$ ) bagi MLG. Keputusan menunjukkan bahawa MWCNT dan MLG menambah baik kebole-basahan Bi-2.5Ag. Walau bagaimanapun, telah diperhatikan bahawa MLG lebih mengurangkan sudut basahan berbanding MWCNT. Kelakuan hakisan Bi-2.5Ag dan sampel komposit dengan MWCNT dan MLG dikaji melalui teknik elektrokimia. Hasil daripada plot Tafel, lengkung yang dijalankan dalam tiga elektrolit yang berbeza menggambarkan bahawa kadar hakisan bagi semua sampel komposit meningkat. Selain itu, dapat disimpulkan bahawa kadar kakisan dan pasivasi adalah bergantung kepada konduktiviti sampel, konduktiviti elektrik elektrolit dan nombor  $H^+$  di dalam elektrolit mengakis. Penambahan MWCNT dan MLG bagi Bi-2.5Ag meningkatkan kekuatan ricih. Walau bagaimanapun, adalah diperhatikan bahawa tegasan ricih Bi-2.5Ag dengan penambahan MWCNT dan MLG zarah nano hanya menambah baik sehingga peratusan berat zarah nano dalam matriks mencapai  $0.07$  wt% bagi MWCNT

dan 0.05 wt% untuk MLG. Secara ringkas, penambahan zarah nano MWCNT dan MLG ke Bi-2.5Ag matrix pateri telah menambah baik tingkah laku peleburan, pengaliran elektrik, kebolehan basahan dan kekuatan ricih, tetapi memberi impak negatif terhadap tingkah laku hakisan bahan.





## ACKNOWLEDGEMENTS

I wish to acknowledge with thanks the significant contribution of my thesis supervisor, Associate Professor Dr. Azmah Hanim binti Mohamed Ariff who has given me her informative explanation regarding this project. I owe a considerable debt to her patience, wisdom, understanding, invaluable guidance and continuous supervision. Also, I gratefully appreciate my committee member Professor Dr. Zulkarnain Zainal and Associate Professor Dr. Janet Hong Ngee Lim for their suggestions, patience and superb co-operations.

I have benefited immeasurably from my association with individuals, who have assisted me in performing many tasks in the production of this project. Unfortunately, there are just too many names and I would hesitate to do so in any event in the fear of inadvertently omitting someone. Special thanks to all my lab mates for their helpfulness, willingness and kindness in guiding and helping out throughout the whole duration of my project.

Finally, I would like to express my heartfelt gratitude to my parents because of their emotional, full strength encouragement and concern towards the completion of this project. They have my profound thanks and gratitude.

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

**Azmah Hanim binti Mohamed Ariff, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Zulkarnain Zainal, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Janet Hong Ngee Lim, PhD**

Associate Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**ROBIAH BINTI YUNUS, PhD**

Professor and Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:

## Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software

Signature: \_\_\_\_\_ Date: \_\_\_\_\_

Name and Matric No: Nima Ghamarian, GS37463

## TABLE OF CONTENTS

	Page
<b>ABSTRACT</b>	i
<b><i>ABSTRACT</i></b>	iii
<b>ACKNOWLEDGEMENTS</b>	v
<b>APPROVAL</b>	vi
<b>DECLARATION</b>	viii
<b>LIST OF TABLES</b>	xiii
<b>LIST OF FIGURES</b>	xiv
<b>LIST OF ABBREVIATIONS</b>	xxi
 <b>CHAPTER</b>	
 <b>1 INTRODUCTION</b>	 1
1.1 Background of Study	1
1.2 Problem Statement	2
1.3 Significance of Study	3
1.4 Objectives of the Research	3
1.5 Scope of Study	4
1.6 Hypotheses	4
1.7 Structure of the Thesis	5
 <b>2 LITERATURE REVIEW</b>	 6
2.1 Introduction	6
2.2 Solder Infrastructure and Electronic Packaging	6
2.3 Lead and Lead Solder	8
2.4 Health and Environment Concerns with Lead	8
2.5 Category of Solder According to Their Melting Point	10
2.6 High Temperature Solder Alloys	14
2.6.1 Sn-Sb Alloys	15
2.6.2 Sn-Ag-Sb Alloys	16
2.6.3 Sn-Cu Alloys	16
2.6.4 Zn-Al Alloys	16
2.6.5 Au-Sn Alloys	16
2.6.6 Bi-Ag Alloys	16
2.7 Bi-Ag Binary Phase Diagram	17
2.8 Effect of component elements on solder	18
2.8.1 Effects of Bismuth on Solder	18
2.8.2 Effect of Silver of on Solder	18
2.8.3 Effect of Carbon Nanotube on Solder	19
2.8.4 Effect of Graphene on Solder	21
2.9 Reinforced Lead Free Solder Systems	22
2.9.1 Effect of Reinforcement on Melting Point	22
2.9.2 Effect of Reinforcement on the Electrical Conductivity	23
2.9.3 Effect of Reinforcement on the Corrosion Behavior	24

2.9.4	Effect of Reinforcement on the Wetting Angle	28
2.9.5	Effect of Reinforcement on Shear Strength	31
2.10	Summary	34
<b>3</b>	<b>METHODOLOGY</b>	36
3.1	Introduction	36
3.2	Experimental Process Description	36
3.3	Materials Used	37
3.3.1	Mechanical Alloying	38
3.3.2	Powder Compaction and Pellet Melting	39
3.3.3	Density Determination	39
3.3.3.1	Bulk Density	39
3.3.3.2	Theoretical Density	40
3.3.3.3	Relative Density	40
3.3.4	Copper Substrate Preparation	40
3.3.5	Cold Mounting, Grinding and Polishing Processes	41
3.4	Measurement Techniques	41
3.4.1	Field Emission Scanning Electron Microscope (FESEM)	42
3.4.2	Transmission Electron Microscope (TEM)	42
3.4.3	Energy Dispersive X-ray (EDX)	43
3.4.4	Atomic Force Microscopy (AFM)	44
3.4.5	X-ray Diffraction (XRD)	44
3.4.6	UV-Visible	45
3.4.7	Surface Area Measurements	46
3.4.8	Raman Spectroscopy	46
3.4.9	Differential Scanning Calorimeter (DSC)	47
3.4.10	Electrical Conductivity Measurements	47
3.4.10.1	Standard Four-Probe Technique	47
3.4.10.2	Measuring Critical Temperature ( $T_c$ )	49
3.4.11	Corrosion Behavior	50
3.4.11.1	Electrochemical Measurement	50
3.4.11.2	Working Electrode	50
3.4.11.3	Reference Electrode	51
3.4.11.4	Auxiliary Electrode	51
3.4.11.5	Cyclic Voltammetry	51
3.4.11.6	Preparation of Corrosive Electrolytes	51
3.4.11.7	Tafel Plot	52
3.4.11.8	Corrosion Current Density	53
3.4.11.9	Pourbaix Diagram	53
3.4.11.10	Atomic Equivalent Weight	53
3.4.11.11	Calculation of Corrosion Rate from the Corrosion Current	55
3.4.11.12	Passivity	56
3.4.12	Wetting Contact Analysis	56
3.4.13	Single Lap Shear Joint strength	57
3.5	Statistical Terminology	58
3.5.1	The Mean	59
3.5.2	Standard Deviation	59

<b>4</b>	<b>RESULT AND DISCUSSION</b>	<b>60</b>
4.1	Introduction	60
4.2	Sample Preparation	60
4.3	Melting Temperature Analysis	72
4.4	Electrical Resistance	77
4.5	Wettability of Plain and Composite Solder Joints	81
4.6	Corrosion Behavior of Bulk Nano-Composite Solder	84
4.6.1	Calculation of the Atomic Equivalent Weight for Bi-2.5Ag	85
4.6.2	Effect of Corrosive Electrolytes on the Polarization Curves of Bi-2.5Ag and its Reinforced Samples with MWCNT and MLG	90
4.6.3	Calculation of Corrosion Rate from the Corrosion Current	105
4.6.4	Behavior of Active-Passive layer	110
4.7	Shear Strength Test and Fractography Analysis	121
4.7.1	Shear Strength Test	122
4.7.2	Fractography Analysis of Solder Joints	125
<b>5</b>	<b>CONCLUSIONS AND RECOMMENDATIONS</b>	<b>129</b>
5.1	Conclusion	129
5.2	Recommendation	130
	<b>REFERENCES</b>	<b>132</b>
	<b>APPENDICES</b>	<b>149</b>
	<b>BIODATA OF STUDENT</b>	<b>166</b>
	<b>LIST OF PUBLICATIONS</b>	<b>167</b>

## LIST OF TABLES

Table	Page
2.1 Different levels in the packaging hierarchy	7
2.2 Materials commonly used in electronic packaging	7
2.3 Maximum concentration values for RoHS restricted substances	10
2.4 List of available lead free solder alloys	13
2.5 Typical candidate for high temperature solder alloys	15
2.6 Melting point, density and CTE results of solder samples with and without carbon nanotube solders	23
2.7 The impact of Ag coated SWCNT weight percentages on the wetting angle of SAC alloy	31
3.1 Example for calculation of 18 g powder weight for mechanical alloying (for Bi-2.5Ag+ 0.01 wt% MWCNT/MLG)	39
4.1 Atomic weight, valency and the mass fraction of elements involved in the corrosion process	90
4.2 Electrical conductivity of corrosive electrolytes (temperature coefficient 2.5 %/°C)	110
4.3 $E_{pp}$ [ $\pm 0.01$ -0.1], $i_{cc}$ [ $\pm 0.0001$ -0.001] and $i_p$ [ $\pm 0.001$ ] for Bi-2.5Ag and its composite system with MWCNT and MLG at different corrosive electrolytes (pH 5)	120

## LIST OF FIGURES

Figure	Page
2.1 Pb-Sn phase diagram	11
2.2 Categorized of solder regarding their melting point	12
2.3 Bi-Ag phase diagram	17
2.4 Schematic illustration of a single wall carbon nanotube (SWCNT) and a multi wall carbon nanotube (MWCNT)	20
2.5 Schematic illustration of (a) Graphene, (b) Bi-layer Graphene, (c) Few layer/multi-layer graphene and (d) Graphite	21
2.6 General corrosion of solder joints on PCB	25
2.7 Definition of good wetting and poor wetting angle condition	29
2.8 The impact of surface tension on the wetting behavior	30
2.9 The improved shear strength for the composite solder joints	33
2.10 Composite solder joints shear strength as an impact of wt% SWCNT	34
3.1 The experimental procedure flow chart of the thesis	36
3.2 Materials used and process	38
3.3 Field Emission Scanning Microscope	42
3.4 Transmission Electron Microscope	43
3.5 Energy Dispersive X-ray	43
3.6 Atomic Force Microscopy	44
3.7 X-ray Diffraction instrument	45
3.8 UV-Visible instrument	46
3.9 Raman Spectrometer	47
3.10 Four point probe schematic setup	48
3.11 The critical temperature measurement setup	49



3.12	Corrosion schematic setup	50
3.13	An example of schematic Tafel plot (polarization curve) illustrating intersection of cathodic and anodic Tafel	52
3.14	The general illustration of corrosion behavior and their position due to potential and Tafel plot	56
3.15	Wetting angle measurement for sample cross-sectional view at the magnification at 20X	57
3.16	Different types of shear joint	57
3.17	The parameters which are involved in the calculation of shear stress	58
4.1	(a) The reinforced solder with less than 0.1 wt% nano particles (b) The reinforced solder with more than 0.1 wt% nano particles	61
4.2	FESEM images of dispersed nano particles in the matrix for 20 min of mixing for (a) 300X magnification and (b) 5000X magnification	62
4.3	Mean diameters of dispersed nano particles in the matrix for 20 min mixing for (a) 300X magnification and (b) 5000X magnification	62
4.4	FESEM images of the dispersed of nano particles in the matrix for 40 min mixing for (a) 300X magnification and (b) 5000X magnification	63
4.5	Mean diameters of the dispersed nano particles in the matrix for 40 min mixing for (a) 300X magnification and (b) 5000X magnification	63
4.6	FESEM images of the dispersed nano particles in the matrix for 180 min mixing for (a) 300X magnification and (b) 5000X magnification	64
4.7	Mean diameters of the dispersed nano particles in the matrix for 180 min mixing for (a) 300X magnification and (b) 5000X magnification	64
4.8	The estimation of mixing time at the magnification of 300X	65
4.9	The estimation of mixing time at the magnification of 5000X	65
4.10	FESEM images of the (a) Bi (b) Ag (c) MWCNT powders before mechanical alloying	66

4.11	TEM images of (a) MWCNT (b) MLG before mechanical alloying	66
4.12	FESEM image of the mixed powders (Bi, Ag and nano particles) after 850 min of mechanical alloying	67
4.13	TEM images of the (a) MWCNT and (b) MLG in presence of Bi and Ag after 850 min of mechanical alloying	67
4.14	Energy dispersive X-ray (EDX) spectrum of (a) Bi (b) Ag (c) MWCNT/ MLG (d) after 850 mechanical alloying	68
4.15	Compressive load vs pellet density	69
4.16	Compressive load vs porosity in the pellet	69
4.17	Compressive load vs compressive extension for the powder compaction	70
4.18	XRD patterns of MLG (•) MWCNT (■) Bi (*) Ag (♦) (a) MLG (b) MWCNT (c) reinforce Bi-2.5Ag with MLG (d) reinforce Bi-2.5Ag with MWCNT	71
4.19	The DSC pattern of Bi-2.5Ag	72
4.20	The effect of reinforced nano particles on the melting point of Bi-2.5Ag	73
4.21	The effect of reinforced nano particles on the specific heat of Bi-2.5Ag	74
4.22	The effect of reinforced nano particles on the enthalpy of Bi-2.5Ag	74
4.23	The effect of reinforced nano particles on the onset of melting for Bi-2.5Ag	75
4.24	The effect of reinforced nano particles on endset melting of Bi-2.5Ag	76
4.25	The effect of reinforced nano particles on the pasty range of Bi-2.5Ag	76
4.26	The effect of reinforced nano particles on the electrical resistivity of Bi-2.5Ag	77
4.27	(a) Optical absorbance and (b) band gap energy of MWCNT (c) optical absorbance and (d) band gap energy of MLG	78

4.28	The distribution of volume (percentage) with respect to the nano particle size for (a) MWCNT (b) MLG	79
4.29	Raman spectra for (a) MWCNT (b) MLG	80
4.30	The electrical resistivity of Bi-2.5Ag against temperature	81
4.31	The effect of flux on the wetting angle of Bi-2.5Ag for (a) without flux (b) with flux	82
4.32	Graphical plot of the wetting angle relative to respective wt% of MWCNT in the solder matrix	82
4.33	Graphical plot of the wetting angle relative to respective wt% of MLG in the solder matrix	83
4.34	Cyclic Voltammogram of Cu substrate with scan rate of 20 mVs <sup>-1</sup> at 0.5M KCl	85
4.35	Pourbaix diagram of Cu	86
4.36	Cyclic Voltammogram of Bi-2.5Ag with scan rate of 20 mVs <sup>-1</sup> at 0.5M KCl	87
4.37	Cyclic Voltammogram of Bi-2.5Ag + 0.1 wt% MWCNT with scan rate of 20 mVs <sup>-1</sup> at 0.5M KCl	87
4.38	Cyclic Voltammogram of Bi-2.5Ag + 0.1 wt% MLG with scan rate of 20 mVs <sup>-1</sup> at 0.5M KCl	88
4.39	Pourbaix diagram of silver	88
4.40	Pourbaix diagram of bismuth	89
4.41	Polarization curves for different weight percentage of MWCNT in the solder matrix in corrosive H <sub>2</sub> SO <sub>4</sub> electrolyte, pH 5	92
4.42	Polarization curves for different weight percentage of MLG in the solder matrix in corrosive H <sub>2</sub> SO <sub>4</sub> electrolyte, pH 5	93
4.43	Polarization curves for different weight percentage of MWCNT in the solder matrix in corrosive HCl electrolyte, pH 5	94
4.44	Polarization curves for different weight percentage of MLG in the solder matrix in corrosive HCl electrolyte, pH 5	95
4.45	Polarization curves for different weight percentage of MWCNT in the solder matrix in corrosive HNO <sub>3</sub> electrolyte, pH 5	96

4.46	Polarization curves for different weight percentage of MLG in the solder matrix in corrosive $\text{HNO}_3$ electrolyte, pH=5	97
4.47	Polarization curves for Cu substrate related to different acids at pH 5	99
4.48	Polarization curves for Bi-2.5Ag (solder matrix) related to different acids at pH 5	99
4.49	Polarization curves for reinforced sample with 0.01 wt% MWCNT related to different acids at pH 5	100
4.50	Polarization curves for reinforced sample with 0.01 wt% MLG related to different acids at pH 5	100
4.51	Polarization curves for reinforced sample with 0.03 wt% MWCNT related to different acids at pH 5	101
4.52	Polarization curves for reinforced sample with 0.03 wt% MLG related to different acids at pH 5	101
4.53	Polarization curves for reinforced sample with 0.05 wt% MWCNT related to different acids at pH 5	102
4.54	Polarization curves for reinforced sample with 0.05 wt% MLG related to different acids at pH 5	102
4.55	Polarization curves for reinforced sample with 0.07 wt% MWCNT related to different acids at pH 5	103
4.56	Polarization curves for reinforced sample with 0.07 wt% MLG related to different acids at pH 5	103
4.57	Polarization curves for reinforced sample with 0.1 wt% MWCNT related to different acids at pH 5	104
4.58	Polarization curves for reinforced sample with 0.1 wt% MLG related to different acids at pH 5	104
4.59	The estimated $i_{\text{corr}}$ for reinforced sample with MWCNT and MLG at corrosive media which contained HCl	106
4.60	The estimated corrosion rate for reinforced sample with MWCNT and MLG at corrosive media which contained HCl	106
4.61	The estimated $i_{\text{corr}}$ for reinforced sample with MWCNT and MLG at corrosive media which contained $\text{HNO}_3$	107

4.62	The estimated corrosion rate for reinforced sample with MWCNT and MLG at corrosive media which contained $\text{HNO}_3$	107
4.63	The estimated $i_{\text{corr}}$ for reinforced sample with MWCNT and MLG at corrosive media which contained $\text{H}_2\text{SO}_4$	108
4.64	The estimated corrosion rate for reinforced sample with MWCNT and MLG at corrosive media which contained $\text{H}_2\text{SO}_4$	109
4.65	Behavior of Active-Passive layer for different weight percentage of MWCNT in solder matrix for corrosive electrolyte which contained $\text{H}_2\text{SO}_4$ is shown	112
4.66	Behavior of Active-Passive layer for different weight percentage of MLG in solder matrix for corrosive electrolyte which contained $\text{H}_2\text{SO}_4$	113
4.67	Behavior of Active-Passive layer for different weight percentage of MWCNT in solder matrix for corrosive electrolyte which contained $\text{HCl}$	114
4.68	Behavior of Active-Passive layer for different weight percentage of MLG in solder matrix for corrosive electrolyte which contained $\text{HCl}$	115
4.69	Behavior of Active-Passive layer for different weight percentage of MWCNT in solder matrix for corrosive electrolyte which contained $\text{HNO}_3$	116
4.70	Behavior of Active-Passive layer for different weight percentage of MLG in solder matrix for corrosive electrolyte which contained $\text{HNO}_3$	117
4.71	The grain boundary grooving of Bi-2.5Ag cross section	121
4.72	Shear load (N) vs. reinforced MWCNT (wt%)	122
4.73	Shear stress (MPa) vs. reinforced MWCNT (wt%)	123
4.74	Shear load (N) vs. reinforced MLG (wt%)	123
4.75	Shear stress (MPa) vs. reinforced MLG (wt%)	124

4.76	(a) Optical microscope image of fractured sample during single lap shear test (upper grip) magnification of 20X for 0.1 wt% of MWCNT in the matrix and (b) AFM image of upper grip fractured sample during single lap shear test	126
4.77	(a) Optical microscope image of fractured sample during single lap shear test (lower grip) magnification of 20X for 0.1 wt% of MWCNT in the matrix and (b) AFM image of lower grip fractured sample during single lap shear test	126
4.78	Striations on the Cu substrate after single lap shear test for the area where solder alloy is completely removed magnification 100X	127
4.79	The load-extension for Bi-2.5Ag and its composited one with 0.1 wt% of MWCNT and MLG	127

## LIST OF ABBREVIATIONS

$\Delta l$	Displacement
$\Delta R$	Differential resistance
$2\theta^\circ$	2 Theta degree
A	Ampere
AFM	Atomic Force Microscopy
Ag	Aurum (Silver)
Au	Argentum (Gold)
BC	Before Christ
BET	Brunauer-Emmer-Taller
BGA	Ball grid array
Bi	Bismuth
C	Coulomb
C.R.	Corrosion rate
CE	Counter electrode
CNT	Carbon nano tube
Co	Cobalt
CTE	Thermal expansion coefficient
Cu	Copper
CV	Cyclic voltammetric
DC	Direct current circuit
DSC	Differential Scanning Calorimeter
$E_{\text{corr}}$	Corrosion potential
EDX	Energy Dispersive X-ray
$E_g$	Band gap energy

EMF	Electromotive force series
$E_{pp}$	Passivation potential
EPR	European Recycling Platform
EW	Equivalent weight
F	Faraday constant
FESEM	Field Emission Scanning Electron Microscope
$\gamma$	Shear strain
TEM	Transmission Electron Microscope
$i_{cc}$	Critical current
$i_{corr}$	Corrosion current
IMC	Intermetallic compound
$i_p$	Passive current
IPP	Integrated product policy
K	Kelvin
MCV	Maximum concentration value
MLG	Multi layer graphene
MWCNT	Multi wall carbon nano tube
$\eta$	Over-potential
Ni	Nickel
Pb	Lead
PBBs	Polybrominated biphenyls
PBDEs	Polybrominated diphenyl ethers
PCB	Printed circuit board
PWB	Printed wiring board
Q	Electric charge



R	Resistance
RE	Reference electrode
RoHS	Restriction of Hazardous Substances
s	Second
SAC	SnAgCu (Tin-silver-copper)
Sb	Antimony
SCE	Standard Calomel Electrode
SLG	Single layer graphene
Sn	Tin
SWCNT	Single wall carbon nano tube
T	Temperature
t	Thickness
T	Shear stress
T <sub>c</sub>	Critical temperature
um	Micrometer
UTM	Universal Testing Machine
UV	Ultra Violet
WE	Working electrode
wt%	Weight percentage
X	Magnification
XRD	X-ray Diffraction
Zn	Zinc
θ	Wetting angle
ρ	Electrical resistivity
ρ	Density

## CHAPTER 1

### INTRODUCTION

#### 1.1 Background of Study

The tendency in utilizing electronic products will be in wireless, portable, and handheld features. This fact drives the industrial growth in the microelectronic technologies. The rapid growth, demands for new materials more than ever (Berni et al., 2016; Sattler, 2016). Solder alloys and conductive adhesives components have been used by electronic manufacturers to provide electrical interconnection between electrical segments and the printed wiring board (PWB)(Dunn, 2015). Lead-Tin (Pb-Sn) alloys are a promising interconnection material. Lead (Pb) has been used since the 1940s in view of its proven reliability with eutectic phase when chemically mixed with tin (Sn) (Plumbridge, 1996).

According to mass production of electronic gadgets, it is impossible to turn a blind eye on the disposal of these products and abandon them in the environment (Kang and Schoenung, 2005; Rydh and Sun, 2005). Solder alloys and conductive adhesives contain a high level of Pb (Li et al., 2005). Pb and its alloys as a heavy metal under certain conditions are harmful to human and environment; therefore some countries impose a law to limit the usage of Pb in the industries. For instance, Canada bans Pb in petrol in 1990 (Bollhöfer and Rosman, 2001), U.S.A in 1996 (Kovarik, 2005), and in 2002 it is banned in the European Union (Bollhöfer and Rosman, 2001).

European Union Parliament and Council resolution, in July 2006, restrict the use of Hazardous Substance (RoHS) in electrical products to avoid Pb in manufacturing. Furthermore, in January 2005, Japan as the paramount electronic gadget producers admitted widening the use of lead free solders instead of lead solders (Hwang, 2004a). The limitation of using Pb in electronic industries carves a path for the scholars to look for lead free alloys to suit their application as high and low temperature solders (Frear and Vianco, 1994).

In the recent times, heat generation and thermal conductivity in electronic device which were used in aerospace, automotive, militaries, nuclear power facilities, oil industry and monitors initiate the need for high temperature lead free solder (Chidambaram et al., 2011; Kang and Sarkhel, 1994; Suganuma, 2001; Suganuma et al., 2009). Some elements such as gold (Au), zinc (Zn), bismuth (Bi) and tin (Sn) have been suggested to replaced Pb as lead free soldering alloys in high temperature applications (Evans, 2007).

Among all suggested high temperature lead free solder alloys, Bismuth-Silver Alloys (Bi-Ag) provides better features for different applications (Shimoda et al., 2012). It

can be concluded from the Bi-Ag phase diagram that a binary system contains only one eutectic reaction, which occurs at 97.5% Bi and at a temperature around 262.5 °C. There are no intermetallic parts, and the low solubility of silver in bismuth precludes solid-solution establishment. The presence of the silver element in the microstructure makes Bi-Ag alloys mechanically stronger and more ductile than pure bismuth (Nahavandi, 2014).

The reliability and applicability of Bi-Ag solder alloy in industries need further investigations considering their advantages (e.g., good electrical conductivity) and disadvantages (e.g., brittleness) (Song et al., 2006, 2007b). Thus, the investigations to improve the physical and mechanical properties of these alloys is ongoing (Spinelli et al., 2014).

Studies have shown that adding alloying elements frequently improves the properties of alloy (Allaoui et al., 2002; Avner, 1964). Improvement in the characteristics of lead free solders by proper selection of the reinforcement materials could advantageously produce better alloy due to its physical and mechanical properties (Gancarz et al., 2014; Yang et al., 2014). In consideration of the aforementioned facts, multi wall carbon nanotube (MWCNT) and multi-layer graphene (MLG) were selected as the reinforcement materials in the current study according to their good electrical conductivity and mechanical strength.

In the nutshell, the eutectic Bi-Ag lead-free solder reinforced with varying weight (0.01, 0.03, 0.05, 0.07 and 0.1 wt%) of multi wall carbon nanotube (MWCNT) and multi-layer graphene (MLG) were analyzed in order to fabricate the composite solder. Powder metallurgy technique was used for mixing and compaction of the elements. Then, the pellets were melted in the furnace on copper (Cu) plates. Physical, shear strength, corrosion behavior and electrical conductivity effects of MWCNT and MLG on lead free eutectic Bi-Ag solder alloy were studied.

## **1.2 Problem Statement**

It is crystal clear that; the wide use of the electronic equipment's. Nowadays, lead (Pb) is a commonly used element in many components of the electronic industry especially as solder alloys (Pb-Sn) (Tribula et al., 1989). Pb in solder materials is used in coatings soldered on printed circuit boards, pins and ends of boards (Lee et al., 2001; Zeng and Tu, 2002).

Due to the fact that Pb is in the class of top seventeen chemical poisoning elements (heavy elements), it leaves no doubt about its harmful effect on human health. Its accumulation in the human body causes disorders in the nervous system, reproductive systems, the disturbance in neurological and physical development, anemia and hypertension (Duruibe et al., 2007).

Prohibiting the use of solder containing Pb in many industries was applied from 2006 in United States of America (USA). Regarding this fact, a new solder alloy, Bi-Ag, as one of the lead-free solder alloys has been considered as a promising replacement for high temperature solder applications (Song et al., 2007b).

But Bi-Ag alloys are still not vastly used in industries. It has some disadvantages such as brittleness, low electrical conductivity and low shear modulus. Tackling this problem and improving the binary phase alloys especially its eutectic has caught the attention of scholars (Song et al., 2007a).

It has been suggested by the researchers that adding one or more elements can be helpful to improve the properties of the alloy (Efzan and Singh, 2014). Due to this fact, the metallurgical effect of multi wall carbon nanotube (MWCNT) and multi-layer graphene (MLG) on eutectic Bi-Ag alloy was studied and proposed in this research.

### **1.3 Significance of Study**

Reliability of interconnection joints is a major concern in the improvement of lead-free solders. The investigation in this subject area must first prioritize the existing trend in the electronic packaging industries. The current choices for replacements of lead alloy system are based on Ag, Bi, Zn and Sn alloy systems. So far, some preference has been placed on the Bi-Ag solder material as a promising candidate but it is not a matured material yet with the required reliability and optimized properties to be use in the industry.

In this research, based on the desirable properties shown by the Bi-Ag binary alloy, an attempt is made to investigate the alternative of nano-composite Bi-2.5Ag for high-temperature application. Therefore, this thesis critically examines and documents the detailed information required to raise the consciousness of researches and electronic industries towards a revamped Bi-Ag lead-free solder, through the incorporation of carbon nanotubes and graphene.

### **1.4 Objectives of the Research**

The objectives of the present work which are effects of multi wall carbon nanotubes and multi-layer graphene on Bi-2.5Ag lead free solder were summarized as follows:

1. To analyze the effect of MWCNT and MLG on the melting performance of Bi-2.5Ag alloys.
2. To determine the effect of MWCNT and MLG on the electrical conductivity of Bi-2.5Ag alloys at room temperature.

3. To investigate the effect of MWCNT and MLG on the corrosion behavior of Bi-2.5Ag alloys by electrochemical method.
4. To determine the effect of MWCNT and MLG on the wetting/contact angle of Bi-2.5Ag alloys on a Cu substrate.
5. To analyze the effect of MWCNT and MLG on the shear strength of Bi-2.5Ag solder using single lap-shear test method.

### 1.5 Scope of Study

The scope of the research is centered on five principal properties of solder alloys which are critical in analyzing the reliability of the solder joints. The effect of reinforcement of Bi-2.5Ag with MWCNT and MLG (Bi-2.5Ag + xMWCNT/xMLG, x= 0.01, 0.03, 0.05, 0.07 and 0.1 wt%) were studied according to the melting temperature, electrical conductivity, corrosion behavior, wetting angle and strengthening of solder composite.

The Bi-2.5Ag composite was produced by mechanical alloying of components which were in the powder form. Differential Scanning Calorimetry (DSC) was used to find the effect of MWCNT and MLG on melting behavior of Bi-2.5Ag. In order to report the wetting angle associated with each experiment (each weight percentage of nano particles in the solder matrix). Six angles were measured by an optical microscope (OM) and the mean value was determined. Due to the importance of electrical resistivity of solder and interconnection alloys for electronic assembly, the effect of MWCNT and MLG on Bi-2.5Ag was studied using Standard Four-Probe Technique. Corrosion behavior of reinforced samples was studied by electrochemical method in three corrosive electrolytes (HCl, HNO<sub>3</sub> and H<sub>2</sub>SO<sub>4</sub>). Furthermore, composite Bi-2.5Ag joints behavior was investigated using single lap-shear test method by 10 kN universal testing machine. In the interest of studying the single lap joints sample failure during the shear test, the fractured samples were randomly selected and investigated using an optical microscope (OM) and atomic force microscopy (AFM).

### 1.6 Hypotheses

The study's research hypotheses are as follow:

H1: Melting behavior of Bi-2.5Ag will be affected by MWCNT and MLG reinforcement. Some researches show significant in melting point while other researches show no effect at all or negligible difference in melting point with addition of MWCNT and MLG in lead free solders.

H2: Electrical conductivity of Bi-2.5Ag will be improved by adding reinforcement nano-particles, since MWCNT and MLG are excellent electrical conductors.

H3: Wettability of Bi-2.5Ag will be improved by adding MWCNT and MLG to the solder matrix up to a certain percentage. After a certain threshold, the wetting angle increase due to agglomeration of the reinforcements.

H4: Corrosion behavior of Bi-2.5Ag will be affected by MWCNT and MLG reinforcement. Not enough information to predict the trend of the behavior and the extent of the difference.

H5: Shear strength of Bi-2.5Ag will be improved by adding reinforcement nanoparticles up to a certain percentage of reinforcement. Beyond a certain threshold value, agglomeration of MWCNT and MLG will have a negative impact on the shear strength of the solder.

## **1.7 Structure of the Thesis**

The thesis was written into five chapters. After an introduction which describes the background of this research, problem statements, and research objective are in the first chapter. The framework structure of the remaining part of the thesis is as follow:

Chapter two gives literature review on the general knowledge within the scope of this research, materials, technologies and methods. Chapter three illustrates in detail the methodologies which were conducted in this study.

Chapter four discusses and explains the results (based on the analyzed experimental data) of the metallurgical effects of multi walled carbon nanotubes or multi-layer graphene on eutectic Bi-2.5Ag lead free solder.

Finally, chapter five summarizes and reviews all the present analyzed works and provides deductions on the observations obtained by this research. In this chapter, recommendations are also given for future research directions.



## REFERENCES

- Abadin, H., Ashizawa, A., Stevens, Y.-W., Lladós, F., Diamond, G., Sage, G., Citra, M., Quinones, A., Bosch, S. J., & Swarts, S. G. (2007). *Toxicological profile for lead*. Atlanta (GA): Agency for Toxic Substances and Disease Registry (US).
- Acton, A. (2011). *Electrolytes: advances in research and application*. Atlanta: Scholarly Editions.
- Adamson, A. W., & Gast, A. P. (1967). *Physical chemistry of surfaces* (Sixth ed.). California: A Wiley-Sons Interscience Publishers.
- Ahmad, Z. (2006). *Principles of corrosion engineering and corrosion control* (First ed.). Oxford: Butterworth-Heinemann.
- Aitken, R., Chaudhry, M., Boxall, A., & Hull, M. (2006). Manufacture and use of nanomaterials: current status in the UK and global trends. *Occupational medicine*, 56(5), 300-306.
- Allaoui, A., Bai, S., Cheng, H.-M., & Bai, J. (2002). Mechanical and electrical properties of a MWNT/epoxy composite. *Composites Science and Technology*, 62(15), 1993-1998.
- Amalu, E., Ekere, N., & Bhatti, R. (2009). *High temperature electronics: R&D challenges and trends in materials, packaging and interconnection technology*. Paper presented at the 2nd International Conference on Adaptive Science & Technology (ICAST) (pp. 146-153). IEEE, Accra, Ghana.
- Anderson, J. (1948). The primary reactions in roasting and reduction processes. *Discussions of the Faraday Society*, 4, 163-173.
- Anyalebechi, P. (2005). Essentials of materials science and engineering. *School of Engineering, Padnos College of Engineering and Computing, Grand Valley State University*, 137-156.
- Arenas, M. F., & Acoff, V. L. (2004). Contact angle measurements of Sn-Ag and Sn-Cu lead-free solders on copper substrates. *Journal of Electronic Materials*, 33(12), 1452-1458.
- Avner, S. H. (1964). *Introduction to physical metallurgy* (Second ed.). New York: McGraw-Hill.
- Baldelli, S., Bao, J., Wu, W., & Pei, S.-s. (2011). Sum frequency generation study on the orientation of room-temperature ionic liquid at the graphene–ionic liquid interface. *Chemical Physics Letters*, 516(4), 171-173.
- Bark, H., Kim, J.-S., Kim, H., Yim, J.-H., & Lee, H. (2013). Effect of multiwalled carbon nanotubes on the thermoelectric properties of a bismuth telluride matrix. *Current Applied Physics*, 13, S111-S114.

- Bath, J. (2007). *Lead-free soldering*. New York: Springer Science & Business Media.
- Baughman, R. H., Zakhidov, A. A., & de Heer, W. A. (2002). Carbon nanotubes--the route toward applications. *Science*, 297(5582), 787-792.
- Beckham, K. F., Kolman, A. E., McGuire, K. M., Puttlitz, K. J., & Quinones, H. (1986). USA Patent No. US4604644 A.
- Berni, R., Catelani, M., Fiesoli, C., & Scarano, V. L. (2016). A Comparison of Alloy-Surface Finish Combinations Considering Different Component Package Types and Their Impact on Soldering Reliability. *IEEE Transactions on Reliability*, 65(1), 272-281.
- Beverskog, B., & Puigdomenech, I. (1997). Revised Pourbaix diagrams for copper at 25 to 300 C. *Journal of the Electrochemical Society*, 144(10), 3476-3483.
- Beyer, H., Sivasubramaniam, V., Hajas, D., Nanser, E., & Brem, F. (2014). *Reliability Improvement of Large Area Soldering Connections by Antimony Containing Lead-Free Solder*. Paper presented at the PCIM Europe 2014; International Exhibition and Conference for Power Electronics, Intelligent Motion, Renewable Energy and Energy Management; Proceedings of (pp. 1-8). .
- Bhat, S. V., Nagasampagi, B. A., & Sivakumar, M. (2005). *Chemistry of natural products*. New York: Alpha Science Int'l Ltd.
- Billah, M. M., Shorowordi, K. M., & Sharif, A. (2014). Effect of micron size Ni particle addition in Sn-8Zn-3Bi lead-free solder alloy on the microstructure, thermal and mechanical properties. *Journal of Alloys and Compounds*, 585, 32-39.
- Bollhöfer, A., & Rosman, K. (2001). Isotopic source signatures for atmospheric lead: the Northern Hemisphere. *Geochimica et Cosmochimica Acta*, 65(11), 1727-1740.
- Boulakia, J. D. C. (1972). Lead in the Roman world. *American Journal of Archaeology*, 76(2), 139-144.
- Brown, M. (1997). *Differential scanning calorimetry—An introduction for practitioners*. Berlin: Springer.
- Butler, S. (2008). European Recycling Platform (ERP): a Pan-European Solution to WEEE Compliance *Electronic Waste Management* (pp. 161-179). Cambridge, UK: The Royal Society Of Chemistry.
- Cadevall, M., Ros, J., & Merkoçi, A. (2016). Bismuth- Based Nanomaterials and Platforms for Sensing and Biosensing Applications. *Functional and Physical Properties of Polymer Nanocomposites*, 159-181.
- Chang, T.-C., Wang, J.-W., Wang, M.-C., & Hon, M.-H. (2006). Solderability of Sn-9Zn-0.5 Ag-1In lead-free solder on Cu substrate: Part 1. Thermal properties, microstructure, corrosion and oxidation resistance. *Journal of Alloys and Compounds*, 422(1), 239-243.



- Chantaramanee, S., Wisutmethangoon, S., Sikong, L., & Plookphol, T. (2013). Development of a lead-free composite solder from Sn–Ag–Cu and Ag-coated carbon nanotubes. *Journal of Materials Science: Materials in Electronics*, 24(10), 3707-3715.
- Charter, M. (2001). *Integrated product policy (IPP) and eco-product development (EPD)*. Paper presented at the Environmentally Conscious Design and Inverse Manufacturing, 2001. Proceedings EcoDesign 2001: Second International Symposium (pp. 672-677), Tokyo, Japan.
- Chen, D., Eisley, N. A., Heidelberger, P., Senger, R. M., Sugawara, Y., Kumar, S., Salapura, V., Satterfield, D. L., Steinmacher-Burow, B., & Parker, J. J. (2011). *The IBM Blue Gene/Q interconnection network and message unit*. Paper presented at the 2011 International Conference for High Performance Computing, Networking, Storage and Analysis (SC) (pp. 1-10). IEEE, Seattle, WA, USA.
- Chen, G., Wu, F., Liu, C., Silberschmidt, V. V., & Chan, Y. (2016). Microstructures and properties of new Sn–Ag–Cu lead-free solder reinforced with Ni-coated graphene nanosheets. *Journal of Alloys and Compounds*, 656, 500-509.
- Chen, G., Wu, F., Liu, C., Xia, W., & Liu, H. (2015). Effects of fullerenes reinforcement on the performance of 96.5 Sn–3Ag–0.5 Cu lead-free solder. *Materials Science and Engineering: A*, 636, 484-492.
- Chen, S.-W., Wang, C.-H., Lin, S.-K., & Chiu, C.-N. (2007). Phase diagrams of Pb-free solders and their related materials systems. *Journal of Materials Science: Materials in Electronics*, 18(1-3), 19-37.
- Chen, Y.-Y., Duh, J.-G., & Chiou, B.-S. (2000). The effect of substrate surface roughness on the wettability of Sn–Bi solders. *Journal of Materials Science: Materials in Electronics*, 11(4), 279-283.
- Chidambaram, V., Hattel, J., & Hald, J. (2011). High-temperature lead-free solder alternatives. *Microelectronic Engineering*, 88(6), 981-989.
- Chinnam, R., Fauteux, C., Neuenschwander, J., & Janczak-Rusch, J. (2011). Evolution of the microstructure of Sn–Ag–Cu solder joints exposed to ultrasonic waves during solidification. *Acta Materialia*, 59(4), 1474-1481.
- Cho, J., & Goodson, K. E. (2015). Thermal transport: Cool electronics. *Nature materials*, 14(2), 136-137.
- Choudhary, V., & Gupta, A. (2011). Polymer/carbon nanotube nanocomposites. *Carbon Nanotubes-Polymer Nanocomposites*, 65-90.
- Chu, K., Kim, D., Sohn, Y., Lee, S., Moon, C., & Park, S. (2013). Electrical and thermal properties of carbon-nanotube composite for flexible electric heating-unit applications. *IEEE Electron Device Letters*, 34(5), 668-670.

- Chung, D. (1995). *Materials for electronic packaging*. Newton: Butterworth-Heinemann.
- Del Castillo, L., Weber, C. T., Mojarradi, M., Carr, G., Hunter, D., Vo, T., Stell, C., Orellana, S., Suh, J.-o., & Nieraeth, D. (2016). *High temperature anode power supply parts and packaging reliability and survivability*. Paper presented at the Aerospace Conference, (pp. 1-9) IEEE, Big Sky, MT, USA.
- Dele-Afolabi, T., Hanim, M. A., Norkhairunnisa, M., Yusoff, H., & Suraya, M. (2015a). Growth kinetics of intermetallic layer in lead-free Sn-5Sb solder reinforced with multi-walled carbon nanotubes. *Journal of Materials Science: Materials in Electronics*, 26(10), 8249-8259.
- Dele-Afolabi, T., Hanim, M. A., Norkhairunnisa, M., Yusoff, H., & Suraya, M. (2015b). Investigating the effect of isothermal aging on the morphology and shear strength of Sn-5Sb solder reinforced with carbon nanotubes. *Journal of Alloys and Compounds*, 649, 368-374.
- Dieter, G., & Bacon, D. (1986). *Mechanical metallurgy*. New York: McGraw-Hill book company.
- Djellal, L., Omeiri, S., Bouguelia, A., & Trari, M. (2009). Photoelectrochemical hydrogen-evolution over p-type chalcopyrite CuInSe 2. *Journal of Alloys and Compounds*, 476(1), 584-589.
- Dugdale, J. S. (2016). *The electrical properties of metals and alloys*. Mineola, NY, USA: Courier Dover Publications.
- Dunn, B. D. (2015). *Materials and Processes: For Spacecraft and High Reliability Applications*. Chichester: Springer.
- Duruibe, J., Ogwuegbu, M., & Egwurugwu, J. (2007). Heavy metal pollution and human biotoxic effects. *International Journal of Physical Sciences*, 2(5), 112-118.
- Dvorak, M., & Wu, Z. (2014). Geometrically induced transitions between semimetal and semiconductor in graphene. *Physical Review B*, 90(11-5415), 1-7.
- Efzan, E., & Singh, A. (2014). Review on the effect of alloying element and nanoparticle additions on the properties of Sn-Ag-Cu solder alloys. *Soldering & Surface Mount Technology*, 26(3), 147-161.
- El-Daly, A., Al-Ganainy, G., Fawzy, A., & Younis, M. (2014a). Structural characterization and creep resistance of nano-silicon carbide reinforced Sn-1.0 Ag-0.5 Cu lead-free solder alloy. *Materials & Design*, 55, 837-845.
- El-Daly, A., El-Taher, A., & Dalloul, T. (2014b). Improved creep resistance and thermal behavior of Ni-doped Sn-3.0 Ag-0.5 Cu lead-free solder. *Journal of Alloys and Compounds*, 587, 32-39.

- Engelhardt, G., Urquidi-MacDonald, M., & MacDonald, D. (1996). A simplified method for estimating corrosion cavity growth rates. *Corrosion Science*, 38(9), 1613-1635.
- Evans, J. W. (2007). *A guide to lead-free solders: physical metallurgy and reliability*. London: Springer Science & Business Media.
- Ferrari, A. C., & Basko, D. M. (2013). Raman spectroscopy as a versatile tool for studying the properties of graphene. *Nature nanotechnology*, 8(4), 235-246.
- Fontana, M. G. (2005). *Corrosion engineering*. New York, USA: Tata McGraw-Hill Education.
- Frankel, G. (1998). Pitting corrosion of metals a review of the critical factors. *Journal of the Electrochemical Society*, 145(6), 2186-2198.
- Frear, D. (2007). Issues related to the implementation of Pb-free electronic solders in consumer electronics. *Journal of Materials Science: Materials in Electronics*, 18(1-3), 319-330.
- Frear, D., & Vianco, P. (1994). Intermetallic growth and mechanical behavior of low and high melting temperature solder alloys. *Metallurgical and Materials Transactions A*, 25(7), 1509-1523.
- Gancarz, T., Pstrus, J., Cempura, G., & Berent, K. (2016). Influence of Li Addition to Zn-Al Alloys on Cu Substrate During Spreading Test and After Aging Treatment. *Journal of Electronic Materials*, 45(12), 6067-6078.
- Gancarz, T., Pstruś, J., Fima, P., & Mosińska, S. (2014). Effect of Ag addition to Zn–12Al alloy on kinetics of growth of intermediate phases on Cu substrate. *Journal of Alloys and Compounds*, 582, 313-322.
- Ghamarian, N., Zainal, Z., Zidan, M., & Tan, W. T. (2013). Photocorrosion of CuInSe<sub>2</sub> Thin Film by Electrochemical Polarization in Acidic and Alkaline Medium. *Int. J. Electrochem. Sci*, 8, 5161-5171.
- Glazer, J. (1994). Microstructure and mechanical properties of Pb-free solder alloys for low-cost electronic assembly: a review. *Journal of Electronic Materials*, 23(8), 693-700.
- Glazer, J. (2013). Metallurgy of low temperature Pb-free solders for electronic assembly. *International Materials Reviews*, 40(2), 65-93.
- Goh, C., Wei, J., Lee, L., & Gupta, M. (2005). Development of novel carbon nanotube reinforced magnesium nanocomposites using the powder metallurgy technique. *Nanotechnology*, 17(1), 7-12.
- Gojny, F. H., Wichmann, M. H., Fiedler, B., Bauhofer, W., & Schulte, K. (2005). Influence of nano-modification on the mechanical and electrical properties of conventional fibre-reinforced composites. *Composites Part A: Applied Science and Manufacturing*, 36(11), 1525-1535.

- Gojny, F. H., Wichmann, M. H., Fiedler, B., Kinloch, I. A., Bauhofer, W., Windle, A. H., & Schulte, K. (2006). Evaluation and identification of electrical and thermal conduction mechanisms in carbon nanotube/epoxy composites. *Polymer*, 47(6), 2036-2045.
- Gulson, B., Mahaffey, K., Mizon, K., Korsch, M., Cameron, M., & Vimpani, G. (1995). Contribution of tissue lead to blood lead in adult female subjects based on stable lead isotope methods. *The Journal of laboratory and clinical medicine*, 125(6), 703-712.
- Guruswamy, S. (1999). *Engineering properties and applications of lead alloys*. New York: CRC Press.
- Han, Y., Jing, H., Nai, S., Xu, L., Tan, C. M., & Wei, J. (2012). Interfacial reaction and shear strength of Ni-coated carbon nanotubes reinforced Sn–Ag–Cu solder joints during thermal cycling. *Intermetallics*, 31, 72-78.
- Han, Y., Nai, S., Jing, H., Xu, L., Tan, C., & Wei, J. (2011). Development of a Sn–Ag–Cu solder reinforced with Ni-coated carbon nanotubes. *Journal of Materials Science: Materials in Electronics*, 22(3), 315-322.
- Hansen, K. S., Jellesen, M. S., Moller, P., Westermann, P. J. S., & Ambat, R. (2009). *Effect of solder flux residues on corrosion of electronics*. Paper presented at the Reliability and Maintainability Symposium, 2009. RAMS 2009. Annual (pp. 502-508). IEEE., Fort Worth, TX, USA.
- Haruna, T., Morikawa, Y., Fujimoto, S., & Shibata, T. (2003). Electrochemical noise analysis for estimation of corrosion rate of carbon steel in bicarbonate solution. *Corrosion Science*, 45(9), 2093-2104.
- Henderson, D. W., Gosselin, T., Sarkhel, A., Kang, S. K., Choi, W.-K., Shih, D.-Y., Goldsmith, C., & Puttlitz, K. J. (2002). Ag 3 Sn plate formation in the solidification of near ternary eutectic Sn–Ag–Cu alloys. *Journal of Materials Research*, 17(11), 2775-2778.
- Hosking, M., & Yost, F. G. (2012). *The mechanics of solder alloy wetting and spreading*. New York, USA: Springer Science & Business Media.
- Hu, X., Xu, T., Keer, L. M., Li, Y., & Jiang, X. (2016). Microstructure evolution and shear fracture behavior of aged Sn<sub>3</sub>Ag<sub>0.5</sub>Cu/Cu solder joints. *Materials Science and Engineering: A*, 673, 167-177.
- Huang, M., Hou, X., Kang, N., & Yang, Y. (2014). Microstructure and interfacial reaction of Sn–Zn–x (Al, Ag) near-eutectic solders on Al and Cu substrates. *Journal of Materials Science: Materials in Electronics*, 25(5), 2311-2319.
- Huang, M., Huang, Y., Ma, H., & Zhao, J. (2011). Mechanical properties and electrochemical corrosion behavior of Al/Sn-9Zn-xAg/Cu joints. *Journal of Electronic Materials*, 40(3), 315-323.



- Humpston, G., & Jacobson, D. M. (2004). *Principles of soldering*. Ohio: ASM international.
- Hunter, J. A. (1991). USA Patent No. US5032474 A.
- Hwang, J. S. (2004a). Solder technologies for electronic packaging and assembly *Electronic Packaging and Interconnection Handbook* (Third ed., pp. 6.1-6.83). New York, USA: McGraw-Hill.
- Hwang, J. S. (2004b). Solder technologies for electronic packaging and assembly. *Electronic Packaging and Interconnection Handbook*, 135-245.
- Hyk, W., & Kitka, K. (2017). Highly efficient and selective leaching of silver from electronic scrap in the base-activated persulfate–ammonia system. *Waste Management*, 60, 601-608.
- Jellesen, M. S., Verdingovas, V., Conseil, H., Piotrowska, K., & Ambat, R. (2014). *Corrosion in electronics: Overview of failures and countermeasures* (pp. 1-10). Paper presented at the European Corrosion Congress, Technical University of Denmark, DK-2800 Lyngby, Denmark.
- Kalpakkian, S., Schmid, S. R., & Sekar, K. V. (2014). *Manufacturing engineering and technology* (Seven ed.). Upper Saddle River, NJ: Pearson.
- Kang, H.-Y., & Schoenung, J. M. (2005). Electronic waste recycling: A review of US infrastructure and technology options. *Resources, Conservation and Recycling*, 45(4), 368-400.
- Kang, S. K., & Sarkhel, A. K. (1994). Lead (Pb)-free solders for electronic packaging. *Journal of Electronic Materials*, 23(8), 701-707.
- Kang, S. K., Shih, D.-Y., Donald, N., Henderson, W., Gosselin, T., Sarkhel, A., Goldsmith, N. C., Puttlitz, K. J., & Choi, W. K. (2003). Ag<sub>3</sub>Sn plate formation in the solidification of near-ternary eutectic Sn-Ag-Cu. *JOM*, 55(6), 61-65.
- Kang, S. K., Shih, D.-Y., Leonard, D., Henderson, D. W., Gosselin, T., Cho, S.-i., Yu, J., & Choi, W. K. (2004). Controlling Ag<sub>3</sub>Sn plate formation in near-ternary-eutectic Sn-Ag-Cu solder by minor Zn alloying. *JOM*, 56(6), 34-38.
- Kang, U.-B., & Kim, Y.-H. (2004). A new COG technique using low temperature solder bumps for LCD driver IC packaging applications. *IEEE Transactions on Components and Packaging Technologies*, 27(2), 253-258.
- Karakaya, I., & Thompson, W. (1988). The Pb– Sn (Lead-Tin) system. *Journal of Phase Equilibria*, 9(2), 144-152.
- Karaköse, E., Kılıçaslan, M. F., & Çolak, H. (2016). Formation of novel rice-like intermetallic phases and changes in the mechanical, microstructural and electrical properties of Sn–5Sb alloys with addition Ag and Bi. *Journal of Alloys and Compounds*, 655, 378-388.

- Kedici, S., Aksüt, A. A., Kılıçarslan, M. A., Bayramog Lu, G., & Gökdemir, K. (1998). Corrosion behaviour of dental metals and alloys in different media. *Journal of oral rehabilitation*, 25(10), 800-808.
- Ko, K. C. (2013). USA Patent No. US9469938 B2. International Business Machines Corporation P. a. T. Office.
- Ko, Y.-K., Kwon, S.-H., Lee, Y.-K., Kim, J.-K., Lee, C.-W., & Yoo, S. (2014). Fabrication and interfacial reaction of carbon nanotube-embedded Sn–3.5 Ag solder balls for ball grid arrays. *Journal of Alloys and Compounds*, 583, 155-161.
- Kobayashi, K., Shohji, I., & Hokazono, H. (2017). *Tensile and Fatigue Properties of Miniature Size Specimens of Sn-5Sb Lead-Free Solder* (Vol. 879, pp. 2377-2382). Paper presented at the Materials Science Forum, Switzerland.
- Kottcamp, H. (1992). *ASM Handbook Volume 3, Alloy Phase Diagrams* (Vol. 3). New York, USA: ASM International.
- Kovarik, W. (2005). Ethyl-leaded gasoline: how a classic occupational disease became an international public health disaster. *International journal of occupational and environmental health*, 11(4), 384-397.
- Kumar, A., Shukla, R., & Venkatachalam, A. (2013). Studies of corrosion and electrochemical behavior of some metals and brass alloy under different media. *Rasayan Journal* 6(1), 12-14.
- Kumar, K. M., Kripesh, V., Shen, L., Zeng, K., & Tay, A. A. (2006). Nanoindentation study of Zn-based Pb free solders used in fine pitch interconnect applications. *Materials Science and Engineering: A*, 423(1), 57-63.
- Kumar, K. M., Kripesh, V., & Tay, A. A. (2008a). Influence of single-wall carbon nanotube addition on the microstructural and tensile properties of Sn–Pb solder alloy. *Journal of Alloys and Compounds*, 455(1), 148-158.
- Kumar, K. M., Kripesh, V., & Tay, A. A. (2008b). Single-wall carbon nanotube (SWCNT) functionalized Sn–Ag–Cu lead-free composite solders. *Journal of Alloys and Compounds*, 450(1), 229-237.
- Kwak, H., & Hubing, D. T. (2007). An overview of advanced electronic packaging technology, CVEL 007-001. Clemson University, South Carolina, USA: Technical Report: .
- Lalena, J. N., Dean, N. F., & Weiser, M. W. (2002). Experimental investigation of Ge-doped Bi-11Ag as a new Pb-free solder alloy for power die attachment. *Journal of Electronic Materials*, 31(11), 1244-1249.
- Lalwani, G., Xing, W., & Sitharaman, B. (2014). Enzymatic degradation of oxidized and reduced graphene nanoribbons by lignin peroxidase. *Journal of Materials Chemistry B*, 2(37), 6354-6362.

- Lee, J.-H., Park, J.-H., Lee, Y.-H., Kim, Y.-S., & Shin, D. H. (2001). Stability of channels at a scalloplike Cu 6 Sn 5 layer in solder interconnections. *Journal of Materials Research*, 16(05), 1227-1230.
- Lee, N.-C. (2002). *Reflow Soldering Processes*. New York: Elsevier.
- Li, D., Conway, P. P., & Liu, C. (2008). Corrosion characterization of tin–lead and lead free solders in 3.5 wt.% NaCl solution. *Corrosion Science*, 50(4), 995-1004.
- Li, L., Cheng, Y., Xu, G., Wang, E., Zhang, Z., & Wang, H. (2014). Effects of indium addition on properties and wettability of Sn–0.7 Cu–0.2 Ni lead-free solders. *Materials & Design*, 64, 15-20.
- Li, L., & Geiser, K. (2005). Environmentally responsible public procurement (ERPP) and its implications for integrated product policy (IPP). *Journal of Cleaner Production*, 13(7), 705-715.
- Li, L., Liu, Y., Gao, H., & Gao, Z. (2013). Phase formation sequence of high-temperature Zn–4Al–3Mg solder. *Journal of Materials Science: Materials in Electronics*, 24(1), 336-344.
- Li, Y., Moon, K.-s., & Wong, C. (2005). Electronics without lead. *Science*, 308(5727), 1419-1420.
- Li, Y., & Wong, C. (2006). Recent advances of conductive adhesives as a lead-free alternative in electronic packaging: materials, processing, reliability and applications. *Materials science and engineering: R: reports*, 51(1), 1-35.
- Liu, J.-C., Wang, Z.-H., Xie, J.-Y., Ma, J.-S., Shi, Q.-Y., Zhang, G., & Suganuma, K. (2016a). Effects of intermetallic-forming element additions on microstructure and corrosion behavior of Sn–Zn solder alloys. *Corrosion Science*, 112, 150-159.
- Liu, J.-C., Zhang, G., Ma, J.-S., & Suganuma, K. (2015). Ti addition to enhance corrosion resistance of Sn–Zn solder alloy by tailoring microstructure. *Journal of Alloys and Compounds*, 644, 113-118.
- Liu, J., Lu, D., Andersson, C., Zou, C., Gao, Y., Yang, B., Zhai, Q., Andersson, C., & Liu, J. (2009). Melting temperature depression of Sn-0.4 Co-0.7 Cu lead-free solder nanoparticles. *Soldering & Surface Mount Technology*, 21(2), 9-13.
- Liu, W., Wang, Y., Ma, Y., Huang, Y., & Yu, Q. (2016b). Interfacial reaction mechanism and kinetics between Au–20Sn and Sn. *Journal of Materials Science: Materials in Electronics*, 27(6), 5982-5991.
- Liu, W., Wang, Y., Ma, Y., Yu, Q., & Huang, Y. (2016c). Interfacial microstructure evolution and shear behavior of Au–20Sn/(Sn) Cu solder joints bonded at 250° C. *Materials Science and Engineering: A*, 651, 626-635.

- Liu, X., Han, Y., Jing, H., Wei, J., & Xu, L. (2013). Effect of graphene nanosheets reinforcement on the performance of Sn–Ag–Cu lead-free solder. *Materials Science and Engineering: A*, 562, 25-32.
- Loh, K. P., Bao, Q., Ang, P. K., & Yang, J. (2010). The chemistry of graphene. *Journal of Materials Chemistry*, 20(12), 2277-2289.
- Mallampati, S., Schoeller, H., Yin, L., Shaddock, D., & Cho, J. (2014). *Developments of high-Bi alloys as a high temperature Pb-free solder (pp. 1328-1334)*. Paper presented at the 2014 IEEE 64th Electronic Components and Technology Conference (ECTC), Orlando, FL, USA.
- Manko, H. H. (1979). *Solders and soldering: materials, design, production and analysis for reliable bonding* (Second ed.). New York: McGraw-Hill.
- Marnix, V., de Goeij, J. J., Kolar, Z. I., Frens, G., Lusse, P. J., Zuiddam, M. R., & van der Drift, E. (2001). Electroless Silver Deposition in 100 nm Silicon Structures. *Journal of the Electrochemical Society*, 148(1), C28-C33.
- Matkowski, P. (2006). *Influence of the intermetallic compounds on the reliability of solder joints, (pp. 61591V-6)*. Paper presented at the Photonics Applications in Astronomy, Communications, Industry, and High-Energy Physics Experiments IV, Wroclaw, Poland.
- Mayer, C. R., Lotfian, S., Molina- Aldareguia, J., & Chawla, N. (2015). High-Temperature Micropillar Compression Creep Testing of Constituent Phases in Lead- Free Solder. *Advanced Engineering Materials*, 17(8), 1168-1174.
- McCormack, M., & Jin, S. (1994). Improved mechanical properties in new, Pb-free solder alloys. *Journal of Electronic Materials*, 23(8), 715-720.
- McDonald, S., Nogita, K., Read, J., Ventura, T., & Nishimura, T. (2013). Influence of composition on the morphology of primary Cu<sub>6</sub>Sn<sub>5</sub> in Sn-4Cu alloys. *Journal of Electronic Materials*, 42(2), 256-262.
- Mei, Z., Holder, H. A., & Vander Plas, H. A. (1996). Low-temperature solders. *Hewlett Packard Journal*, 47, 91-98.
- Menon, S., George, E., Osterman, M., & Pecht, M. (2015). High lead solder (over 85%) solder in the electronics industry: RoHS exemptions and alternatives. *Journal of Materials Science: Materials in Electronics*, 26(6), 4021-4030.
- Miao, H.-W., & Duh, J.-G. (2001). Microstructure evolution in Sn–Bi and Sn–Bi–Cu solder joints under thermal aging. *Materials chemistry and physics*, 71(3), 255-271.
- Minges, M. L. (1989). *Electronic materials handbook: packaging* (Vol. 1). New York: ASM International.
- Moore, K. D., Machuga, S. C., Stafford, J. W., Cholewczynski, K., & Miller, D. B. (1992). USA Patent No. US5120678 A.



- Morozumi, A., Hokazono, H., Nishimura, Y., Mochizuki, E., & Takahashi, Y. (2015). Influence of Antimony on Reliability of Solder Joints Using Sn-Sb Binary Alloy for Power Semiconductor Modules. *Transactions of The Japan Institute of Electronics Packaging*, 8(1), 8-17.
- Myers, J. L., Well, A., & Lorch, R. F. (2010). *Research design and statistical analysis*. New York: Routledge.
- Nahavandi, M. (2014). *Morphological and mechanical characterisation of Bi-Ag alloy as high temperature lead free solder*. Master Thesis, Universiti Putra Malaysia, Malaysia.
- Nai, S., Wei, J., & Gupta, M. (2006). Improving the performance of lead-free solder reinforced with multi-walled carbon nanotubes. *Materials Science and Engineering: A*, 423(1), 166-169.
- Nai, S., Wei, J., & Gupta, M. (2008a). Effect of carbon nanotubes on the shear strength and electrical resistivity of a lead-free solder. *Journal of Electronic Materials*, 37(4), 515-522.
- Nai, S., Wei, J., & Gupta, M. (2008b). Using carbon nanotubes to enhance creep performance of lead free solder. *Materials Science and Technology*, 24(4), 443-448.
- Nai, S., Wei, J., & Gupta, M. (2009). Interfacial intermetallic growth and shear strength of lead-free composite solder joints. *Journal of Alloys and Compounds*, 473(1), 100-106.
- Nicholson, A., & Bloomfield, D. (1992). The Use of Bismuth Alloy Systems for Reflow and Wave Soldering. *Soldering & Surface Mount Technology*, 4(1), 23-26.
- Niranjani, V., Rao, B. C., Singh, V., & Kamat, S. (2011). Influence of temperature and strain rate on tensile properties of single walled carbon nanotubes reinforced Sn-Ag-Cu lead free solder alloy composites. *Materials Science and Engineering: A*, 529, 257-264.
- Niranjani, V., Singh, V., Rao, B. C., & Kamat, S. (2015). Creep Behaviour of SAC387 Lead Free Solder Alloy Reinforced with Single Walled Carbon Nanotubes. *Transactions of the Indian Institute of Metals*, 68(2), 311-317.
- Nordin, N., Said, S., Ramli, R., Weide-Zaage, K., Sabri, M., Mamat, A., Ibrahim, N., Mainal, A., & Datta, R. (2015). Impact of aluminium addition on the corrosion behaviour of Sn-1.0 Ag-0.5 Cu lead-free solder. *RSC Advances*, 5(120), 99058-99064.
- Norman, N. C. (1997). *Chemistry of arsenic, antimony and bismuth*. London: Springer Science & Business Media.
- Offutt, E., & Watt, S. (2003). *The Elements: Silver*. New York: McGraw-Hill.

- Ojebuoboh, F. K. (1992). Bismuth—Production, properties, and applications. *JOM The Journal of The Minerals, Metals & Materials Society (TMS)*, 44(4), 46-49.
- Okamoto, H., & Massalski, T. (1994). Binary alloy phase diagrams requiring further studies. *Journal of Phase Equilibria*, 15(5), 500-521.
- Olson, R. G. (2009). *Technology and Science in Ancient Civilizations*. California: ABC-CLIO.
- Othman, N. K., Teng, K. Y., Jalar, A., Che Ani, F., & Samsudin, Z. (2016). *Electrochemical migration behaviours of low silver content solder alloy SAC 0307 on printed circuit boards (PCBs) in NaCl solution, (pp 3-12)*. Paper presented at the Materials Science Forum, Bern, Switzerland
- Ott, R. L., & Longnecker, M. T. (2015). *An Introduction to Statistical Methods and Data Analysis*. Boston: Cengage Learning.
- Pandher, R., & Lawlor, T. (2009). *Effect of Silver in common lead-free alloys (pp. 1-14)*. Paper presented at the Proceedings of International Conference on Soldering and Reliability, Assembly Materials 109 Corporate Blvd., South Plainfield, USA.
- Park, Y., McDonald, K. J., & Choi, K.-S. (2013). Progress in bismuth vanadate photoanodes for use in solar water oxidation. *Chemical Society Reviews*, 42(6), 2321-2337.
- Patel, A. B. (2015). *Studies in corrosion of copper and its inhibition*. Philosophy Doctorate Dissertation, University of North Dakota, North Dakota, USA.
- Pedramrazi, Z., Chen, C., Haberer, D., Perkins, W., Ficscher, F., & Crommie, M. (2015). *Bottom-up synthesis of N=11 armchair graphene nanoribbons via new  $sp^3$  to  $sp^2$  cyclization route*. Paper presented at the APS March Meeting Abstracts, Berkeley, USA.
- Péraud, J.-P., & Lauga, E. (2014). Geometry and wetting of capillary folding. *Physical Review E*, 89(4), 043011.
- Plumbridge, W. (1996). Solders in electronics. *Journal of Materials Science*, 31(10), 2501-2514.
- Popovic, J., & Ferreira, J. (2005). An approach to deal with packaging in power electronics. *IEEE Transactions on Power Electronics*, 20(3), 550-557.
- Potula, V., & Kaye, W. (2006). The impact of menopause and lifestyle factors on blood and bone lead levels among female former smelter workers: the Bunker Hill Study. *American journal of industrial medicine*, 49(3), 143-152.
- Proença, L., Barroso, H., Figueiredo, N., Lino, A., Capelo, S., & Fonseca, I. (2015). The corrosion resistance of Wiron® 88 in the presence of *S. mutans* and *S. sobrinus* bacteria. *Journal of Materials Science: Materials in Medicine*, 26(1), 1-7.

- Raeder, C., Felton, L., Tanzi, V., & Knorr, D. (1994). The effect of aging on microstructure, room temperature deformation, and fracture of Sn-Bi/Cu solder joints. *Journal of Electronic Materials*, 23(7), 611-617.
- Rahn, A. (1993). *The basics of soldering*. New York, USA: Wiley-Interscience.
- Redondo-Abad, A. L., Diaz-Nogueira, E., Gerez-Pascual, M., & Regife-Vega, J. M. (1981). USA Patent No. US4266972 A. International Business Machines Corporation: P. a. T. Office.
- Rehfeld, K.-M., Rennings, K., & Ziegler, A. (2007). Integrated product policy and environmental product innovations: An empirical analysis. *Ecological Economics*, 61(1), 91-100.
- Robinson, B. H. (2009). E-waste: an assessment of global production and environmental impacts. *Science of the total environment*, 408(2), 183-191.
- Rydh, C. J., & Sun, M. (2005). Life cycle inventory data for materials grouped according to environmental and material properties. *Journal of Cleaner Production*, 13(13), 1258-1268.
- Sattler, M. (2016). Materials Solutions for Power Electronics Packaging Technology and its True Significance. *ATZelektronik worldwide*, 11(4), 38-43.
- Savastiouk, S., Halahan, P. B., & Kao, S. (2006). USA Patent No. US7060601 B2. International Business Machines Corporation: P. a. T. Office.
- Schroeder, S. A., & Mitchell, M. R. (1994). *Fatigue of electronic materials* (Vol. 1153). Philadelphia, USA: ASTM International.
- Shen, Y.-L., Chawla, N., Ege, E., & Deng, X. (2005). Deformation analysis of lap-shear testing of solder joints. *Acta Materialia*, 53(9), 2633-2642.
- Shimoda, M., Yamakawa, T., Shiokawa, K., Nishikawa, H., & Takemoto, T. (2012). Effects of Ag content on the mechanical properties of Bi-Ag alloys substitutable for Pb based solder. *Transactions of JWRI*, 41(2), 51-54.
- Shiue, R.-K., Tsay, L.-W., Lin, C.-L., & Ou, J.-L. (2003). A study of Sn-Bi-Ag-(In) lead-free solders. *Journal of Materials Science*, 38(6), 1269-1279.
- Silva, B. L., Bertelli, F., Canté, M. V., Spinelli, J. E., Cheung, N., & Garcia, A. (2016). Solder/substrate interfacial thermal conductance and wetting angles of Bi-Ag solder alloys. *Journal of Materials Science: Materials in Electronics*, 27(2), 1994-2003.
- Silva, B. L., Cheung, N., Garcia, A., & Spinelli, J. E. (2015). Evaluation of solder/substrate thermal conductance and wetting angle of Sn-0.7 wt% Cu-(0-0.1 wt% Ni) solder alloys. *Materials Letters*, 142, 163-167.
- Sobhy, M., El-Refai, A., & Fawzy, A. (2016). Effect of Graphene Oxide Nano-Sheets (GONSs) on thermal, microstructure and stress-strain characteristics of Sn-5

- wt% Sb-1 wt% Ag solder alloy. *Journal of Materials Science: Materials in Electronics*, 27(3), 2349-2359.
- Song, J.-M., Chuang, H.-Y., & Wen, T.-X. (2007a). Thermal and tensile properties of Bi-Ag alloys. *Metallurgical and Materials Transactions A*, 38(6), 1371-1375.
- Song, J.-M., Chuang, H.-Y., & Wu, Z.-M. (2006). Interfacial reactions between Bi-Ag high-temperature solders and metallic substrates. *Journal of Electronic Materials*, 35(5), 1041-1049.
- Song, J.-M., Chuang, H.-Y., & Wu, Z.-M. (2007b). Substrate dissolution and shear properties of the joints between Bi-Ag alloys and Cu substrates for high-temperature soldering applications. *Journal of Electronic Materials*, 36(11), 1516-1523.
- Sopousek, J., Vrestal, J., Pinkas, J., Broz, P., Bursik, J., Styskalik, A., Skoda, D., Zobac, O., & Lee, J. (2014). Cu-Ni nanoalloy phase diagram—Prediction and experiment. *Calphad*, 45, 33-39.
- Spinelli, J. E., Silva, B. L., & Garcia, A. (2014). Microstructure, phases morphologies and hardness of a Bi-Ag eutectic alloy for high temperature soldering applications. *Materials & Design*, 58, 482-490.
- Suganuma, K. (2001). Advances in lead-free electronics soldering. *Current Opinion in Solid State and Materials Science*, 5(1), 55-64.
- Suganuma, K., Kim, S.-J., & Kim, K.-S. (2009). High-temperature lead-free solders: properties and possibilities. *JOM Journal of the Minerals, Metals and Materials Society*, 61(1), 64-71.
- Suh, D., Kim, D. W., Liu, P., Kim, H., Weninger, J. A., Kumar, C. M., Prasad, A., Grimsley, B. W., & Tejada, H. B. (2007). Effects of Ag content on fracture resistance of Sn-Ag-Cu lead-free solders under high-strain rate conditions. *Materials Science and Engineering: A*, 460, 595-603.
- Suhling, J. C., & Lall, P. (2008). Electronic packaging applications *Springer Handbook of Experimental Solid Mechanics* (pp. 1015-1044). New York, USA: Springer.
- Tan, C., Daud, A. R., & Yarmo, M. A. (2002). Corrosion study at Cu-Al interface in microelectronics packaging. *Applied Surface Science*, 191(1), 67-73.
- Tanaka, K., Fujii, T., & Fujiyama, K. (2014). J-integral approach to creep-fatigue crack propagation in lead-free solder under various loading waveforms. *Advanced Materials Research*, 891, 365-370.
- Terrones, M., Botello-Méndez, A. R., Campos-Delgado, J., López-Urías, F., Vega-Cantú, Y. I., Rodríguez-Macías, F. J., Elías, A. L., Munoz-Sandoval, E., Cano-Márquez, A. G., & Charlier, J.-C. (2010). Graphene and graphite nanoribbons: Morphology, properties, synthesis, defects and applications. *Nano Today*, 5(4), 351-372.



- Tribula, D., Grivas, D., Frear, D., & Morris, J. (1989). Observations on the mechanisms of fatigue in eutectic Pb-Sn solder joints. *Journal of Electronic Packaging*, 111(2), 83-89.
- Tsao, L. (2012). Corrosion resistance of Pb-free and novel nano-composite solders in electronic packaging *Corrosion Resistance*. Taipei: InTech.
- Tsetseris, L., & Pantelides, S. (2014). Graphene: An impermeable or selectively permeable membrane for atomic species? *Carbon*, 67, 58-63.
- Vafaeenezhad, H., Seyedein, S., Aboutalebi, M., & Eivani, A. (2016). Incorporating the Johnson–Cook Constitutive Model and a Soft Computational Approach for Predicting the High-Temperature Flow Behavior of Sn-5Sb Solder Alloy: A Comparative Study for Processing Map Development. *Journal of Electronic Materials*, 46(1), 467-477.
- Vianco, P. T. (1999). *Corrosion Issues in Solder Joint Design*. Denton: University of North Texas.
- Vianco, P. T., & Frear, D. R. (1993). Issues in the replacement of lead-bearing solders. *JOM*, 45(7), 14-19.
- Wang, F.-J., Gao, F., Ma, X., & Qian, Y.-Y. (2006). Depressing effect of 0.2 wt.% Zn addition into Sn-3.0 Ag-0.5 Cu solder alloy on the intermetallic growth with Cu substrate during isothermal aging. *Journal of Electronic Materials*, 35(10), 1818-1824.
- Wang, X.-S., Cui, S.-W., Zhou, L., Xu, S.-H., Sun, Z.-W., & Zhu, R.-Z. (2014). A generalized Young's equation for contact angles of droplets on homogeneous and rough substrates. *Journal of Adhesion Science and Technology*, 28(2), 161-170.
- Weyermann, M., & Brenner, H. (1998). Factors affecting bone demineralization and blood lead levels of postmenopausal women—A population-based study from Germany. *Environmental research*, 76(1), 19-25.
- Wick, P., Manser, P., Limbach, L. K., Dettlaff-Weglikowska, U., Krumeich, F., Roth, S., Stark, W. J., & Bruinink, A. (2007). The degree and kind of agglomeration affect carbon nanotube cytotoxicity. *Toxicology letters*, 168(2), 121-131.
- Wood, E., & Nimmo, K. (1994). In search of new lead-free electronic solders. *Journal of Electronic Materials*, 23(8), 709-713.
- Wu, H., Wu, X., Ge, M., Zhang, G., Wang, Y., & Jiang, J. (2007). Properties investigation on isotropical conductive adhesives filled with silver coated carbon nanotubes. *Composites Science and Technology*, 67(6), 1182-1186.
- Wurm, A., Lellinger, D., Minakov, A. A., Skipa, T., Pötschke, P., Nicula, R., Alig, I., & Schick, C. (2014). Crystallization of poly ( $\epsilon$ -caprolactone)/MWCNT composites: A combined SAXS/WAXS, electrical and thermal conductivity study. *Polymer*, 55(9), 2220-2232.

- Xian, J., Ma, Z., Belyakov, S., Ollivier, M., & Gourlay, C. (2017). Nucleation of tin on the Cu 6 Sn 5 layer in electronic interconnections. *Acta Materialia*, 123, 404-415.
- Xu, L., Zhang, Z., Jing, H., Wei, J., & Han, Y. (2015). Effect of graphene nanosheets on the corrosion behavior of Sn–Ag–Cu solders. *Journal of Materials Science: Materials in Electronics*, 26(8), 5625-5634.
- Yamada, Y., Takaku, Y., Yagi, Y., Nishibe, Y., Ohnuma, I., Sutou, Y., Kainuma, R., & Ishida, K. (2006). Pb-free high temperature solders for power device packaging. *Microelectronics Reliability*, 46(9), 1932-1937.
- Yang, H., Hernandez, Y., Schlierf, A., Felten, A., Eckmann, A., Johal, S., Louette, P., Pireaux, J.-J., Feng, X., & Mullen, K. (2013). A simple method for graphene production based on exfoliation of graphite in water using 1-pyrenesulfonic acid sodium salt. *Carbon*, 53, 357-365.
- Yang, Z., Zhou, W., & Wu, P. (2014). Effects of Ni-coated carbon nanotubes addition on the microstructure and mechanical properties of Sn–Ag–Cu solder alloys. *Materials Science and Engineering: A*, 590, 295-300.
- Yi, P., Xiao, K., Dong, C., Ding, K., Liu, M., & Li, X. (2015). Field Studies of Corrosion Behaviour of printed circuit board and hot air solder levelling During the Marine Environment of Industrial Pollution. *Int. J. Electrochem. Sci*, 10, 7754-7770.
- Young, L. B. H. P. S. (2000). *Influence of chloride and humidity on mechanical strength of tin-lead solder*. Paper presented at the Processing and Fabrication of Advanced Materials VIII, Singapore.
- Yu, D., Zhao, J., & Wang, L. (2004). Improvement on the microstructure stability, mechanical and wetting properties of Sn–Ag–Cu lead-free solder with the addition of rare earth elements. *Journal of Alloys and Compounds*, 376(1), 170-175.
- Yu, L., Dai, D., & He, S. (2014). Graphene-based transparent flexible heat conductor for thermally tuning nanophotonic integrated devices. *Applied Physics Letters*, 105(25), 251104.
- Zeng, G., McDonald, S., & Nogita, K. (2012). Development of high-temperature solders: review. *Microelectronics Reliability*, 52(7), 1306-1322.
- Zeng, K., & Tu, K.-N. (2002). Six cases of reliability study of Pb-free solder joints in electronic packaging technology. *Materials science and engineering: R: reports*, 38(2), 55-105.
- Zhang, Q. (2015). *Investigations on Microstructure and Mechanical Properties of the Cu/Pb-free Solder Joint Interfaces*. Berlin, Germany: Springer.

- Zhang, Q. (2016). Research Progress in Pb-Free Soldering *Investigations on Microstructure and Mechanical Properties of the Cu/Pb-free Solder Joint Interfaces* (pp. 1-33). Berlin, Germany: Springer.
- Zhang, Q., Zhu, Q., Zou, H., & Zhang, Z. (2010). Fatigue fracture mechanisms of Cu/lead-free solders interfaces. *Materials Science and Engineering: A*, 527(6), 1367-1376.
- Živković, D. T., Kostov, A. I., Janković, I. P., & Stojanović, M. L. (2008). Application of high temperature lead-free solder materials in medicine. *Metalurgija*, 14(4), 271-277.
- Zou, C., Gao, Y., Yang, B., & Zhai, Q. (2010). Melting and solidification properties of the nanoparticles of Sn<sub>3</sub>. 0Ag0. 5Cu lead-free solder alloy. *Materials Characterization*, 61(4), 474-480.
- Zu, F., Zhu, Z., Guo, L., Zhang, B., Shui, J., & Liu, C. (2001). Liquid-liquid phase transition in Pb-Sn melts. *Physical Review B*, 64(18), 180203.