



UNIVERSITI PUTRA MALAYSIA

***SYNTHESIS AND CHARACTERIZATION OF CARBON NANOTUBE
AEROGEL FROM WASTE ENGINE OIL VIA FLOATING CATALYST
CHEMICAL VAPOR DEPOSITION FOR OIL SPILL REMOVAL***

HAYDER BAQER ABDULLAH

FS 2018 6



**SYNTHESIS AND CHARACTERIZATION OF CARBON NANOTUBE
AEROGEL FROM WASTE ENGINE OIL VIA FLOATING CATALYST
CHEMICAL VAPOR DEPOSITION FOR OIL SPILL REMOVAL**

By

HAYDER BAQER ABDULLAH

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,
in Fulfillment of the Requirements for Degree of Doctor of Philosophy**

October 2017

COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy

**SYNTHESIS AND CHARACTERIZATION OF CARBON NANOTUBE
AEROGEL FROM WASTE ENGINE OIL VIA FLOATING CATALYST
CHEMICAL VAPOR DEPOSITION FOR OIL SPILL REMOVAL**

By

HAYDER BAQER ABDULLAH

October 2017

Chairman : Associate Professor Irmawati Ramli, PhD
Faculty : Science

Carbon nanotube (CNT) aerogel is a novel nanomaterial with three-dimensional (3D) macrostructure. The long CNTs assemble display high porosity, spinnability, structural stability, and good electrical conductivity. These characteristic represents a critical approach towards practical applications such as supercapacitors, gas storage, catalyst support, filtration, separation, biological sensors and oil spill removal. CNT aerogel is directly synthesized by floating catalyst chemical vapor deposition (FCCVD) using petrochemicals such as methane, cyclohexane, toluene or dichlorobenzene as a carbon source. Nevertheless, the high cost, depletion of the petrochemical products, and environmental aspects have brought the consideration of using waste engine oil (WEO) instead as a carbon source. This work is the first ever attempt to utilize WEO for CNT aerogel production. It was done via catalytic decomposition of WEO with ferrocene as a catalyst through FCCVD method. Prior to the reaction process, WEO was first filtered to remove dirt and any solid particles that might present. This was later followed by fractional distillation of the oil into different fractions which resulted in five (5) fractions. Gas chromatography-mass spectrometry (GC-MS) showed successful separation of low molecular weight hydrocarbons which was necessary for dissolving the catalyst, while Carbon-nitrogen-sulfur (CNS) analysis indicated that each fraction has more than 69% carbon, less than 0.2% nitrogen and less than 0.09% sulfur. The reaction was carried out at 1150 °C and 1200 °C in hydrogen with a flowing rate of 550 - 650 mL min⁻¹. The carbon source solution (10 mL) was continuously injected into the furnace tube at a feeding rate of 10 mL h⁻¹ during one hour reaction time. It was found that all the synthesized CNT aerogel were multi-walled carbon nanotubes (MWCNTs) with 99.14% yield for CNT aerogel 3 synthesized at 1150 °C. Interestingly, CNT aerogel 2-2 and CNT aerogel 3-2 revealed graphenated carbon nanotubes (G-CNTs) structure obtained at reaction temperature 1200 °C. The CNT aerogels had a mesopore distribution with specific

surface area in the range between 80.6 - 222.0 m² g⁻¹. Field emission scanning electron microscopy (FESEM) revealed randomly orientated to entangle thin multi-walled structure. Oil spill removal study was done by conducting benzene, toluene, and *m*-xylene (BTX) as well as kerosene, diesel oil, palm oil and waste engine oil absorption of the synthesized CNTs. Results showed that CNT aerogel 5-2 gave the highest sorption capacity (Q_e) for kerosene in both oil and oil/water system at 71.43 and 75.19 (g g⁻¹), respectively. Absorption capacity was sustained at 90% for benzene, toluene, and *m*-xylene, 93% for kerosene, 87% for diesel fuel, 68% for palm oil, and 65% for waste engine oil even after 10 absorption cycles. Therefore, it can be concluded that CNT aerogel were successfully prepared from WEO by using FCCVD method which produced MWCNT at 1150 °C and graphenated CNT aerogel at 1200 °C. The CNT aerogel showed an excellent sorption capacity for all tested solvents and oils in both oil and oil/water systems with commendable recycle performance.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**SINTESIS DAN PENCIRIAN AEROGEL NANOTIUB KARBON DARI SISA
MINYAK ENJIN MELALUI KAEDAH MANGKIN TERAPUNG
PEMENDAPAN WAP KIMIA UNTUK PENYINGKIRAN TUMPAHAN
MINYAK**

Oleh

HAYDER BAQER ABDULLAH

Oktober 2017

Pengerusi : Profesor Madya Irmawati Ramli, PhD
Fakulti : Sains

Aerogel nanotub karbon (CNT) ialah bahan nano baru dengan makrostruktur tiga dimensi (3D). Himpunan CNT panjang memaparkan keliangan tinggi, kebolehan spin, kestabilan struktur, dan kekonduksian elektrik yang baik. Ciri-ciri ini merupakan pendekatan kritikal ke arah aplikasi praktikal seperti superkapasitor, penyimpanan gas, sokongan pemangkin, penapisan, pemisahan, penderia biologi dan penyingkiran tumpahan minyak. Aerogel CNT disintesis secara langsung secara mangkin terapung pemendapan wap kimia (FCCVD) menggunakan petrokimia seperti metana, sikloheksana, toluena atau diklorobenzena sebagai sumber karbon. Walaubagaimanapun kos yang tinggi, pengurangan produk petrokimia dan aspek-aspek alam sekitar telah membawa pertimbangan kepada penggunaan sisa minyak enjin (WEO) sebagai sumber karbon. Kajian ini merupakan tindakan yang pertama kali dilakukan untuk menggunakan WEO untuk penghasilan aerogel CNT. Ianya dilaksanakan melalui penguraian bermangkin WEO dengan feroseena sebagai pemangkin melalui kaedah FCCVD. Sebelum proses tindak balas, WEO ditapis terlebih dahulu untuk membuang kotoran dan sebarang zarah pepejal yang mungkin hadir. Ini diikuti oleh penyulingan berperingkat minyak menjadi pecahan-pecahan yang berbeza yang menghasilkan lima (5) pecahan Kromatografi gas-spektrometri jisim (GC-MS) menunjukkan kejayaan pemisahan hidrokarbon berat molekul rendah yang diperlukan untuk melarutkan pemangkin, manakala analisis karbon, nitrogen, dan sulfur (CNS) menunjukkan bahawa setiap pecahan mempunyai lebih daripada 69% karbon, kurang daripada 0.2% nitrogen dan kurang daripada 0.09%. Tindak balas telah dilakukan pada suhu 1150 °C dan 1200 °C di dalam hidrogen pada kadar aliran 550 - 650 mL min⁻¹. Larutan sumber karbon (10 mL) disuntik berterusan ke dalam tiub relau melalui pam picagari pada kadar suapan 10 mL j⁻¹ selama satu jam masa tindak balas. Didapati semua aerogel CNT yang disintesis adalah berbilang dinding

nanotub karbon (MWCNT) dengan hasil paling tinggi, 99.14% diperolehi oleh aerogel CNT 3 yang disintesis pada 1150 °C. Menariknya, aerogel CNT 2-2 dan aerogel CNT 3-2 menunjukkan struktur nanotub karbon bergrafen (G-CNTs) diperolehi pada suhu tindak balas 1200 °C. Aerogel CNT tersebut mempunyai taburan leliang meso dan luas permukaan spesifik sekitar 80.6-222.0 m²g⁻¹. Mikroskopi elektron imbasan (SEM) memaparkan orientasi rawak yang mengkusutkan struktur-struktur nipis berbilang-dinding. Kajian penyingkiran tumpahan minyak telah dilakukan dengan menjalankan ujian penyerapan benzena, toluena dan *m*-xilena (BTX) serta kerosen, minyak diesel, minyak kelapa sawit dan sisa minyak enjin ke atas CNT yang disediakan. Hasil kajian menunjukkan aerogel CNT 5 mempunyai kapasiti erapan tertinggi (Q_e) terhadap kerosen bagi kedua-dua sistem minyak dan minyak/air iaitu masing-masing 71.43 dan 75.19 (g g⁻¹). Kapasiti serapan dikekalkan pada 90% untuk benzena, toluena, dan *m*-xilena, 93% untuk kerosen, 87% untuk minyak diesel, 68% untuk minyak kelapa sawit, dan 65% untuk sisa minyak enjin walaupun selepas 10 kitaran serapan. Oleh itu, dapat disimpulkan bahawa aerogel CNT telah berjaya disediakan dari WEO menggunakan kaedah FCCVD yang menghasilkan MWCNT pada suhu 1150 °C dan CNT tergrafen pada suhu 1200 °C. Aerogel CNT tersebut menunjukkan kapasiti erapan yang sangat baik terhadap pelarut dan minyak yang diuji untuk kedua-dua sistem minyak dan air/minyak, dengan prestasi kitaran semula yang dibanggakan.

ACKNOWLEDGEMENTS

بِسْمِ اللَّهِ الرَّحْمَنِ الرَّحِيمِ

First and foremost, I thank to Allah, Most Gracious, Most Merciful, all praise and thanks are due to Allah, for giving me His blessing and strength throughout this research work. I would like to express the most sincere appreciation to those who made this work possible; supervisory members, Friends and Family.

Firstly, I would like to thank my supervisor Associate Professor Dr. Irmawati Ramli for the many useful advice and discussions, for her constant encouragement, guidance, support and patience all the way through my study work. Equally the appreciation extends to the supervisory committee members Dr. Ismayadi Ismail and Professor Dr. Nor Azah yusof, for providing the opportunity to complete my studies under their valuable guidance.

Not forgotten, thanks to all my colleagues and friends, especially from Catalysis Science and Technology Research Centre (PutraCAT), staffs and technicians at Chemistry Department, Faculty of Science and Advanced Institute of Technology (ITMA), Universiti Putra Malaysia.

Financial support from Universiti Putra Malaysia, the Research Management Center at Universiti Putra Malaysia for providing the research grant (GP-IPS/2015/9465500).

-Alhamdulillah-

I certify that a Thesis Examination Committee has met on 23 October 2017 to conduct the final examination of Hayder Baqer Abdullah on his thesis entitled "Synthesis and Characterization of Carbon Nanotube Aerogel from Waste Engine Oil via Floating Catalyst Chemical Vapor Deposition for Oil Spill Removal" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

Mansor bin Hj. Ahmad @ Ayob, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Zulkarnain bin Zainal, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Abdul Halim bin Abdullah, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Le Minh Thang, PhD

Associate Professor
Hanoi University of Science and Technology
Vietnam
(External Examiner)



NOR AINI AB. SHUKOR, PhD

Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 28 December 2017

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the supervisory committee were as follows:

Irmawati Ramli, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Ismayadi Ismail, PhD

Research Officer
Institute of Advance Technology
Universiti Putra Malaysia
(Member)

Nor Azah Yusof, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software

Signature: _____ Date: _____

Name and Matric No.: Hayder Baqer Abdullah, GS38633

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) were adhered to.

Signature: _____

Name of Chairman
of Supervisory
Committee:

Associate Professor Dr. Irmawati Ramli

Signature: _____

Name of Member
of Supervisory
Committee:

Dr. Ismayadi Ismail

Signature: _____

Name of Member
of Supervisory
Committee:

Professor Dr. Nor Azah Yusof

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	iii
ACKNOWLEDGEMENTS	v
APPROVAL	vi
DECLARATION	viii
LIST OF TABLES	xiii
LIST OF FIGURES	xiv
LIST OF ABBREVIATIONS	xix
 CHAPTER	
1 INTRODUCTION	1
1.1 Background and motivation	1
1.2 Research problems	3
1.3 Hypothesis	4
1.4 Objectives of the study	4
1.5 Scope of study	5
1.6 Thesis outline	5
 2 LITERATURE REVIEW	 7
2.1 Introduction	7
2.2 Carbon nanotubes	7
2.3 Synthesis methods of carbon nanotubes	9
2.3.1 Arc discharge	9
2.3.2 Laser ablation	10
2.3.3 Chemical vapor deposition	10
2.4 Carbon nanotubes macrostructure fabrication	10
2.4.1 Vertically aligned and randomly interconnected arrays carbon nanotubes	11
2.5 Aerogel	16
2.5.1 Fabrication of carbon nanotube aerogels	16
2.5.2 Graphene and carbon nanotube aerogel	17
2.6 Aerogels in toxic organic compounds and oil spills removal	20
2.7 Floating catalyst chemical vapor deposition method for CNT aerogel synthesis	22
2.7.1 Carrier gas and gas flow rate	24
2.7.2 Effect of carbon source	25
2.7.3 Effect of catalyst precursor	26
2.7.4 Effect of sulfur	26
2.8 Growth mechanism	27
2.8.1 The role of catalyst	27
2.8.2 The role of sulfur	29

3	MATERIALS AND METHODS	32
3.1	Introduction	32
3.2	Materials	34
3.3	Fractional distillation process	34
3.4	Synthesis of carbon nanotube aerogel	35
3.4.1	Materials	35
3.4.2	Liquid precursor preparation	35
3.4.3	Synthesis parameters	35
3.4.4	Synthesis of CNT aerogel	35
3.4.5	CNT aerogel purification	36
3.5	Characterization of WEO fractions	36
3.5.1	Density	36
3.5.2	Viscosity	37
3.5.3	Carbon-Nitrogen-Sulfur (CNS) analysis	37
3.5.4	Gas chromatography-mass spectrometry	37
3.6	Characterization of CNT aerogel	37
3.6.1	Mass analysis	37
3.6.2	Field emission scanning electron microscopy	38
3.6.3	High-resolution transmission electron microscopy analysis	38
3.6.4	Elemental analysis	38
3.6.5	Thermal analysis	38
3.6.6	Raman spectroscopy	39
3.6.7	Brunauer-Emmett-Teller gas adsorption	39
3.7	Sorption study	39
3.7.1	Liquids sorbate	40
3.7.2	Density and viscosity	40
3.7.3	Sorption capacity	40
3.7.4	Sorption kinetics study	41
3.7.5	Recyclability	42
4	RESULTS AND DISCUSSION	43
4.1	Introduction	43
4.2	Preparation of carbon source	43
4.2.1	Fractional distillation of waste engine oil	43
4.2.2	Density and viscosity of waste engine oil fractions	45
4.2.3	Carbon-nitrogen-sulfur analysis results	45
4.2.4	Gas chromatography-mass spectrometry	46
4.3	Preliminary reaction process	47
4.4	Synthesis of carbon nanotube aerogel	49
4.5	Characterization results of CNT aerogel	51
4.5.1	Morphology analysis	51
4.5.2	Thermal gravimetric analysis	63
4.5.3	Raman spectroscopy	67
4.5.4	Surface area and pore structure	70
4.6	Sorption study for organics and oils	73
4.6.1	Absorption test of benzene and WEO spill on the water test	73
4.6.2	Sorption capacity for organics and oils	74

4.6.3	Kinetic study	76
4.6.4	Recyclability study	81
4.7	Summary	82
5	CONCLUSIONS AND RECOMMENDATIONS	84
5.1	Conclusions	84
5.2	Recommendations	85
	REFERENCES	86
	APPENDICES	99
	BIODATA OF STUDENT	135
	LIST OF PUBLICATIONS	136



LIST OF TABLES

Table		Page
2.1	Properties and applications of CNT and graphene aerogel	19
2.2	Aerogels and their sorption capacity for oils and toxic compounds	21
4.1	The boiling temperature range and products percentage of waste engine oil fractions	44
4.2	Viscosity and density data calculated from the waste engine oil and the fractions	45
4.3	CNS analysis for the waste engine oil and the fractions	46
4.4	Experimental data resulted from CNT aerogel synthesized at 1150 °C	50
4.5	Experimental data resulted from CNT aerogel synthesized at 1200 °C	50
4.6	EDX results, average diameters, yield and purity for synthesized aerogels	63
4.7	Raman shift, intensity of D-band and G-band, and I_D/I_G value for the CNT aerogels	69
4.8	Characteristic results from BET plot and BJH pore size distribution	72
4.9	Density, kinematic viscosity, sorption capacity and pseudo-second-order kinetic parameters for the oil system	75
4.10	Density, kinematic viscosity, sorption capacity and pseudo-second-order kinetic parameters for the oil/water system	75
4.11	Diffusion coefficient (D'), (α), and correlation coefficient (R^2) for oil and oil/water systems	81

LIST OF FIGURES

Figure		Page
2.1	Conceptual diagram of (a) single-walled carbon nanotube and (b) multi-walled carbon nanotube showing typical dimensions of length, width, and inter-tube separation in multi-walled carbon nanotubes	8
2.2	(a) Roll-up of a graphene sheet leading to three different types of SWCNTs (b) the structure of a multi-walled carbon nanotube made up of three shells of differing chirality	9
2.3	SWCNT forest grown with water-assisted CVD	12
2.4	(a) Carbon nanotube cotton on a 35 mm long. (b) SEM images illustrate that CNT cotton spun into fibers. (c) A segment of a CNT fiber spun from the CNT cotton	13
2.5	Optical and SEM images of CNT sponges. (a) Optical image of carbon nanotube sponges. (b) Cross-sectional SEM image of the sponge. (c) TEM image of large-cavity, thin-walled CNTs. (d) Illustration of the sponge consisting of CNT piles	14
2.6	The CNT aerogels: (a) Snapshot of the CNT aerogel deposition process taken by a camera located outside the reactor. (b) the CNT aerogel withstanding a weight of 8.5 g.(c) 1.50 mg/cm ³ -density CNT aerogel; (d) 20 mg/cm ³ -density aerogel synthesized in 15-20 min	15
2.7	Picture SWCNT aerogel (left, 17.4 mg, density: 9.8 mg cm ⁻³); the same sample supporting a 20 g weight (middle, ~1150 times its weight); the same sample after removal of the weight (right)	17
2.8	The scheme and optical images of different CNT macrostructures preparing via FCCVD process	22
2.9	SEM images of CNTs formed in the reactor at different axial locations	23
2.10	SWCNT formation process. (a) Decomposition of the carbon-bearing gas molecule on the catalyst surface. (b) Dissolution of carbon atoms into the catalyst. (c) Nucleation of the cap. (d) Extension of SWCNT	28
2.11	The effect of nanoparticle on cap nucleation	29

2.12	The mechanics of CNT synthesis by the FCCVD method at high temperature	30
3.1	Simplified experimental work of the research	33
3.2	Fractional distillation set-up employed for waste engine oil distillation	34
3.3	Floating catalyst CVD furnace: (1) Injection pump. (2) Injection tube. (3) Ceramic Furnace tube (120 and 5 cm). (4) Furnace chamber. (5) Controller system. (6) Gas regulator board. (7) Inlet tube. (8) Outlet tube	36
4.1	Waste engine oil and oil fractions obtained from fractional distillation (a) waste engine oil, (b) F1, (c) F2, (d) F3, (e) F4, (f) F5, (g) residue	44
4.2	FESEM image showing aggregates of particulates have grown from large catalyst particles during preliminary FCCVD	48
4.3	FESEM image is showing the large diameter the product from reaction F1 under argon gas at 1150 °C	49
4.4	CNT aerogel resulted from WEO fractions. (a-c) related to the CNT aerogel synthesized from (F1-F3) carbon sources at 1150 °C, and the pictures (d-h) related to the CNT aerogel synthesized from (F1-F5) carbon sources at 1200 °C	51
4.5	(a) FESEM image of CNT aerogel 1 showing entangled and network structure, (b) the histogram showing the CNTs main diameter of 17.8 nm	52
4.6	HRTEM images of CNT aerogel 1; (a) showing elbow and Y-junction shape, (b) showing the tip encapsulated Fe nanoparticle (c) nanotube end with a scale bar showing the approximate outer diameter of 20 nm and inner diameter of 6.2 nm, indicating that the nanotube is multi-walled, (d) Y-junction clearly appeared from CNT side	52
4.7	(a) FESEM image of CNT aerogel 2 showing entangled and network structure mostly from curved CNTs, (b) the histogram showing the CNTs main diameter of 23.1 nm	53
4.8	HRTEM images of CNT aerogel 2; (a) typical image, (b) bamboo and elbow shapes make the tube bending with conical tube structure, (c) straight tube showing MWCNT layers and the tip filled with Fe, (d) spherical bamboo shape	54

4.9	(a) FESEM image of CNT aerogel 3 showing linear CNTs entangled well and result in network structure, (b) the histogram showing the CNTs main diameter of 11.2 nm	55
4.10	HRTEM images of CNT aerogel 3; (a) typical image consist of MWCNT entangled, (b) linear CNT structure, (c) linear tube showing MWCNT layers, (d) focused image showing MWCNT layers	55
4.11	(a) FESEM image of CNT aerogel 1-2 showing entangled and network structure mostly from curved CNTs, (b) the histogram showing the CNTs main diameter of 32.5 nm	56
4.12	HRTEM images of CNT aerogel 1-2, the red circles indicate open-ended; (a) curved bamboo structure, (b) linear structure, (c) shows the outer and inner diameter of the MWCNT, (d) high diameters of bamboo shape MWCNT	57
4.13	(a) FESEM image of CNT aerogel 2-2 showing foliate shape covered the tubes, and entangled network structure mostly from linear CNTs, (b) the histogram showing the CNTs main diameter of 27.6 nm	58
4.14	HRTEM images of CNT aerogel 2-2; (a) image of graphenated carbon nanotube (g-CNT), (b) the graphitic foliates nucleation on the CNT, (C) thin graphene foliate come out the MWCNT layers, (d) show clearly Coherent interface structure between MWCNT shells and graphene foliates	59
4.15	(a) FESEM image of CNT aerogel 3-2 showing graphene foliates covered entire carbon nanotubes, (b) the histogram showing the CNTs main diameter of 259.8 nm	59
4.16	HRTEM images of CNT aerogel 3-2; (a) image of graphenated carbon nanotube (g-CNT), (b) thin graphene foliate, (c) elbow and bamboo shape existing in a few places, (d) the graphene foliate thin sheet	60
4.17	(a) FESEM image of CNT aerogel 4-2 showing entangled and network structure mostly from curved and linear CNTs, (b) the histogram showing the CNTs main diameter of 24.3 nm	60
4.18	HRTEM images of CNT aerogel 4-2; (a) entangled curved and linear MWCNTs, (b) bamboo shape with an elbow, (c) showing some linear shape encapsulated with Fe nanoparticle, (d) MWCNT layers with a hollow core	61

4.19	(a) FESEM image of CNT aerogel 5-2 showing entangled and network structure mostly from curved and linear CNTs and some impurity cluster, (b) the histogram showing the CNTs main diameter of 24.2 nm	62
4.20	HRTEM images of CNT aerogel 5-2; (a) typical image of entangled CNT, (b) the curved bamboo shape, (c) high diameters of bamboo structure MWCNT consist of elbow-like shape	62
4.21	TGA and DTG curves, (a) CNT aerogel 1, (b) CNT aerogel 2 and (c) CNT aerogel 3 synthesized at 1150 °C	64
4.22	TGA and DTG curves, (a) CNT aerogel 1-2, (b) CNT aerogel 2-2 and (c) CNT aerogel 3-2 synthesized at 1200 °C	65
4.23	TGA and DTG curves, (a) CNT aerogel 4-2 and (b) CNT aerogel 5-2 synthesized at 1200 °C	66
4.24	Raman spectra for CNT aerogels 1, 2 and 3 produced at 1150 °C	68
4.25	Raman spectra for CNT aerogels 1-2, 2-2 and 3-2 produced at 1200 °C	68
4.26	Raman spectra for CNT aerogels 4-2 and 5-2 produced at 1200 °C	69
4.27	(a) N ₂ absorption isotherm for the of a dry CNT aerogel 1, the Type IV isotherm is observed, indicating that the CNT aerogel contains mesopores. (b) A linear regression on the multi-point BET plot	71
4.28	Pore size distribution of CNT aerogel 1	73
4.29	Digital photograph showing the absorption of benzene and WEO on the water surface using as-synthesized CNT aerogel 5 at different times: (a) t= 0 min, (b) t= 1 min, and (c) t= 2 min for benzene, and (d) t= 0 min, 1 min, and 15 min for WEO	74
4.30	Sorption kinetics of the CNT aerogel of different absorbate, (a) oil system, and (b) oil/water system	77
4.31	Linear regression lines of kinetics plots using the pseudo second order model of benzene absorbed by CNT aerogel 5, (a) for oil system, and (b) for oil/water system	78
4.32	The equilibrium sorption capacity of CNT aerogel 5 for different organic solvents and oils for both oil system and oil/water system	79

4.33	Fractal like - linear driving force plots of benzene absorbed by CNT aerogel 5, (a) for oil system, and (b) for oil/water system	80
4.34	Recyclability performances of the organics and oils absorption capacities of CNT aerogel 3, (a) oil system, and (b) oil/water system	82



LIST OF ABBREVIATIONS AND SYMBOLS

A_S BET	Specific surface area
ASTM	American Society for Testing and Materials
BET	Brunauer-Emmett-Teller
BJH	Barret-Joyner-Halenda
CD	Carbon Deposition
CNTs	Carbon Nanotubes
DWCNT	Double-Walled Carbon Nanotubes
CVD	Chemical Vapor Deposition
EDX	Energy Dispersive X-ray Spectroscopy
FCCVD	Floating Catalyst Chemical Vapor Deposition
FESEM	Field Emission Scanning Electron microscopy
HRTEM	High Resolution Transition Electron microscopy
IUPAC	International Union of Pure and Applied Chemistry
MWCNTs	Multi-Walled Carbon Nanotubes
P_o	Saturated Vapor Pressure
P/P_o	Relative Pressure
SA	Surface Area
Sccm	Standard Cubic Centimeter per Minute
SWCNTs	Single-Walled Carbon Nanotubes
V_p	Total Pore Volume
WEO	Waste Engine Oil

CHAPTER 1

INTRODUCTION

1.1 Background and motivation

The discovery of multi-walled carbon nanotubes (Iijima, 1991) and single-walled carbon nanotubes (Iijima and Ichihashi, 1993), both by Iijima of NEC Laboratories in Japan has stimulated researchers all over the world to explore their remarkable properties. As described by Iijima 1991, multi-walled carbon nanotubes (MWCNTs) consist of two or more concentric graphene sheets while single-walled carbon nanotubes (SWCNTs) consist of a single graphene cylinder. Compared to MWCNTs, SWCNTs exhibit superior properties that emerge from the firm one-dimensionality and crystalline perfection of the structure. These two are often simply called Carbon Nanotubes (CNTs).

Realizing that these structures exhibit remarkable mechanical, electrical, and electronic properties, the focus of the CNTs research has moved to the engineering viewpoint of the production of CNTs. A significant limiting aspect for carbon nanotubes as a commercial material is their size which is limited to small sizes; making it very difficult in transferring their nanoscale properties to macroscale applications. Also, the limits of conventional growth processes, which can grow pristine forests of nanotubes for use in research, or as additives in another process (De Volder *et al.*, 2013). Countless papers have been published describing methods for growing longer nanotubes, some even continuously, but none have been able to demonstrate a material with properties even close to the theoretical limits of individual nanotubes. Up to the present time, the longest nanotubes can be grown only a few centimeters (Zhang *et al.*, 2013b), and although films (Meng *et al.*, 2014), ribbons (Nath and Sahajwalla, 2011) and aerogels (Skaltsas *et al.*, 2011) can be produced in laboratories; these are still agglomerations of individual nanotubes and not continuous structures.

While these are interesting approaches and worthy of further research, they are still under aspiration approach, where the material strength relies upon the van der Waals interactions between the nanotubes, and not on the nanotubes themselves. Even if further research improves the utility of such methods, it must be remembered that the more complicated a process is, the more difficult and expensive it will be to scale up for commercial applications.

It is of fundamental and practical distinction to scale unique properties of individual CNT into macroscopic three-dimensional (3D) porous structures, which take advantage of CNT's flexibility, excellent electrical and thermal properties, and mechanical integrity (Scarselli *et al.*, 2015). Therefore, synthesis assembly of CNTs into 3D porous architectures is of scientific and technological significance to translate the intrinsic features of individual CNT to a macroscopic level (Liu *et al.*, 2011a; Nardecchia *et al.*, 2013), thereby allowing for some unprecedented properties.

The emerging technologies, including energy storage, sensors, water treatment, etc., have driven high demand in the synthesis of lightweight, elastic and robust materials. Beside, controlled porosity are destined to provide a variety of functionalities such as high surface area, low density, mechanical integrity and great transport properties (Hashim *et al.*, 2012). The scientific and engineering challenge is to design and produce these structures in applied dimensions while manage accurate control over their chemical and physical properties at the nanoscale. Carbon nanotubes are extremely appealing with their low density and versatility in many applications. Inspired by some natural structures (Ajayan and Zhou, 2001), creating 3D porous carbon nanotubes macroscopic design, including all properties of CNTs could be a strategy for achieving promising performance for widespread applications. The main forms of the 3D macroscopic design of carbon nanotubes are carbon nanotube array (Cao *et al.*, 2013), carbon nanotube yarn (Miao, 2013), carbon nanotube ribbon (Wang *et al.*, 2014), carbon nanotube sponge (Li *et al.*, 2016a), and carbon nanotube aerogel (Bryning *et al.*, 2007). Carbon nanotube aerogel (CNT aerogel) is self-sustaining assemblies of carbon nanotube tangled well to construct 3D macroscopic design. It shows high porosity, lightweight, spin ability to yarn, structural stability, and excellent electrical conductivity. CNT aerogel exhibits promising candidate material to be employed in various critical applications such as sensors for detecting pressure, gas and chemical vapor, catalysts for chemical adsorption, photocatalysis, water treatment, electrodes in supercapacitors, microbial fuel cells, lithium-ion batteries, dye-sensitized solar cells, environmental materials for chemical removal, capacitive desalination process, and biomaterials for tissue engineering. Therefore, these high-value applications have driven the development of reliable routes for fabrication of CNT aerogel.

The floating catalyst chemical vapor deposition (FCCVD) method is a practical process which produces CNT aerogel through the direct self-sustaining assembling of CNTs in the vapor phase (Gspann *et al.*, 2014; Mikhalchan *et al.*, 2016; Motta *et al.*, 2007). This process can create dens of CNT aerogel in one step and is considered as a promising process for large-scale productions, as well as having the ability to control the aerogel structure due to the self-assembly of pure CNTs in the vapor phase. Basically, the association of CNTs during gas flow produces an aerogel, which is formed by assembly of the grown CNTs by van der Waals attractions before condensation to a tangled CNTs (Gspann *et al.*, 2014). The previous synthesis of CNT aerogel was conducted on commercial carbon sources such as methane, ethanol, hexane, and toluene. To convey in the consideration on the depletion of fossil fuel, waste engine oil (WEO) is the preferred candidate for the imminent studies. However, control the assembly of CNTs in stable form during gas flow remains a main challenge for continuous synthesis of CNT aerogel with desired structures.

Therefore, the motivation to develop a feasible and scalable method of CNT aerogel production with controllable structures based on abundant carbon source is for emerging practical applications.

1.2 Research problems

The high cost of CNTs synthesis, which restricts its large scale in macrostructure production, is the crucial aspect to the success of the development and commercialization of CNTs industries. Practically, the CNTs are currently produced in a relatively high quality but in limited quantities. Therefore, future use of this worthwhile material strongly depends on the development of a technology for its large-scale macrostructure production. Accordingly, large-scale synthesis of CNT aerogel has been the subject of intensive researches, and many attempts have been conducted to optimize and control the CNTs growth.

The CNTs macro-assembling of individual CNTs to aerogel require implementing technologies such as pyrolysis, freeze drying, or supercritical point drying to replace trapped solvents with air (Maleki, 2016). This technique requires the use of specific chemicals, or surfactants, also, the CNT aerogels produced from these methods require the existing of additional binders such as polymers and is typically fragile. Besides, these technologies could require a thermal annealing and purification step to improve the porosity and surface area. Therefore, eventually, the process becomes extremely unfeasible and expensive.

Previous works on synthesis of CNT aerogel using Floating catalyst chemical vapor deposition method, reported that the synthesis of CNT aerogel was succeeded by utilizing methane, ethanol, hexane, and toluene (Gspann *et al.*, 2014; Mikhalchan *et al.*, 2016). Whereas, the escalate depletion of fossil fuel requires decrease dependent on such carbon source and establishes a new one for the CNT aerogel production. Therefore, this study would like to see whether waste engine oil could be used as the carbon source for CNT aerogel production.

Floating catalyst CVD systems provide a convenient space for a mixture of reactants and catalyst components in the gas phase which result in more effective production in high temperature. This feature made FCCVD as an efficient process for the synthesis of large quantities of CNT aerogel. However, the performance of a floating catalyst system toward CNT aerogel production is strongly determined by many essential features, such as the catalyst and promoter ratio, carbon source characteristic, reactor design, and operating conditions such as feedstock flow rate, gas flow rate, reaction temperature and reaction time, that all together determine the CNT aerogel quality. The entire optimization of the FCCVD process is a complicated task, especially with waste engine oil characteristics as a carbon source.

Oil spills which are leakage of petroleum onto the surface of large areas of water are a major worldwide problem. Various pollutants are entering water resources from anthropogenic activities, from conventional pollutants such as BTX (benzene, toluene, Xylene) (Guelli Ulson De Souza *et al.*, 2012), and waste engine oil (Jin *et al.*, 2015). Some of these contaminants could not be removed from water efficiently via traditional water treatment methods. Moreover, more effective and low-cost

technologies to decontaminate and disinfect water for point-of-use purposes are needed, especially in rural regions.

1.3 Hypothesis

Floating catalyst chemical vapor deposition (FCCVD) method has proven as the adequate process for the CNT aerogel production. In the reported works, the researchers used commercially available carbon sources which are commonly a single component hydrocarbon and highly pure such as methane, ethanol, and toluene. These carbon sources are small size and can dissolve catalyst (ferrocene) for the FCCVD process. The process requires mixing the carbon source with ferrocene as a catalyst which must be dissolved well with the carbon source before it was introduced to the furnace chamber. However, in this work, instead of using a single component and highly pure hydrocarbon, a high density and multicomponent hydrocarbon source which is waste engine oil (WEO) was used. Chemically, WEO is a highly viscous liquid which contains long chain hydrocarbons and other impurities. To obtain the smaller size and shorter chain hydrocarbons, fractional distillation must be conducted.

Nevertheless, pre-treated WEO still contains long chain hydrocarbons with high molecular weights that would negatively affect the properties of the resultant products. Therefore, the control of FCCVD parameters such as catalyst ratio, injection rate, gas flow rate, reaction temperature, and reaction time may result with a production of CNT aerogel.

Utilizing thiophene as a promoter would prevent the catalyst particles from coarsening and aggregation. This will increase the opportunity of produce CNTs from multicomponent carbon source by enhancing the adsorbing and dissociation of carbon atoms on the growing ends of the CNTs. Moreover, adding thiophene as a promoter would produce mostly long and small diameter CNTs due to its property as a surfactant which encourages CNTs nucleation and growth and therefore prevents carbon encapsulation on the catalyst particle.

1.4 Objectives of the study

The project is primarily undertaken to synthesize CNT aerogel using waste engine oil via floating catalyst chemical vapor deposition. Under this umbrella, the objectives of the research project are then described as follows:

- 1- To identify and characterize the waste engine oil fractions produced by a fractional distillation process of waste engine oil in order to use them as carbon sources.
- 2- To synthesize CNT aerogel from WEO fractions through the floating catalyst CVD method by controlling the catalyst ratio, injection rate, gas flow rate, reaction temperature parameters.
- 3- To characterize the structure and properties of CNT aerogel produced from waste engine oil.

- 4- To evaluate CNT aerogel for oil spill removal and investigate the absorption ability for several chemicals and oils.

1.5 Scope of study

In this study, the CNT aerogels are synthesized in one step process using floating catalyst chemical vapor deposition (FCCVD) method at the reaction temperature 1150 °C and 1200 °C, and flow rate of hydrogen as a carrier gas of 550-650 sccm in a one hour reaction time. In an effort to develop a potentially feasible and efficient method for the large quantities of CNT aerogel production, the synthesis experiments focused on the design of process based on WEO as a carbon source in FCCVD method. There is no report yet declared the synthesis of CNT aerogel from WEO. The carbon source was prepared from waste engine oil by fractional distillation under nitrogen at 400 °C to attain several fractions which were used as carbon sources. The viscosity and density of the oil fractions were obtained beside CNS and GC-MS analysis, while the CNT aerogels were characterized by FESEM, EDX, HRTEM, TGA, Raman, and BET analysis.

For the ability of synthesized CNT aerogel on absorption application, it was tested for sorption study over hydrocarbons such as benzene, toluene, *m*-xylene and kerosene as well as oils which were diesel fuel, palm oil, and waste engine oil. The equilibrium sorption capacity (Q_e) was calculated by following the weight of CNT aerogel before and after absorption for comparison with other absorbents. In addition, kinetics study were considered by applying Pseudo-second-order model Fractal like - linear driving force (FL-LDF) model for oil and oil/water systems.

1.6 Thesis outline

Chapter 1 gives a motivation of the work presented in the subsequent chapters. Although each chapter briefly introduces itself, the information contained in this chapter is general to state the motivation of the thesis study and gives justification to the problems presented and briefly what measures were undertaken to address them and how that was achieved. The main objectives of the study are also presented in this chapter.

Chapter 2 is a general literature review. The chapter will be brief and will give a description of aims at providing an in-depth understanding of available synthetic methodology and routes of carbon nanotube macrostructure. Emphasis will be on carbon nanotube aerogel. The commonly used CNT synthesis procedures, relevant properties of the CNTs as well as their characteristics will be discussed briefly to reveal their role in carbon nanotube aerogel. The discussion is then shifted towards synthesis method for CNT aerogel emphasis review on floating chemical vapor deposition (FCCVD) method and the growth mechanism of CNTs using this technique.

Chapter 3 describes the experimental work completed to accomplish the goals of this study. The experiments are divided into three sections. The first section is dedicated to the fractional distillation of waste engine oil and the results characterization. The second section deals with CNT aerogel synthesis experimental via FCCVD method and the results characterization. The third section elucidates the absorption study for several chemicals and oils.

Chapter 4 discuss the results of experiments and the data collected from analysis in order to come out with the best description of the project findings. This chapter is divided into three sections. The first section is devoted to the fractional distillation of waste engine oil. Study the properties of the fractions that result from the process compare with WEO by proper characterization. The second section deals with the CNT aerogel synthesized from WEO fractions via FCCVD. Discuss the process parameters that control the CNT aerogel production. Several reaction processes were done as a preliminary study by varying the parameters involved in the formation of CNT aerogel. The parameters investigated are injection rate of reactant, temperature stability during reaction, the position and length of injection tube, sonication time of the reactants, catalyst ratio, and gas flow rate. Then study CNT aerogel production by varying several parameters such as catalyst ratio, gas flow rate, and reaction temperature have done. Morphology analysis, thermal stability, the degree of graphitization, surface area, N₂ adsorption isotherm and pore size distribution are studied. The third section exposes to the sorption study for several chemicals and oils. Investigate the sorption performance of the CNT aerogel sorption study which includes sorption capacity, kinetic study, and recyclability was conducted on various chemicals and oils were selected which are benzene, toluene, *m*-xylene, kerosene, diesel fuel, palm oil, and waste engine oil. The study has done using two system oil and oil in water (oil/water).

Chapter 5 elucidate the conclusions and recommendations for future work.

REFERENCES

- Abdullah, H. B., Ramli, I., Ismail, I., and Yusof, N. A. (2017). Hydrocarbon Sources for the Carbon Nanotubes Production by Chemical Vapour Deposition: A Review. *Pertanika J. Sci. & Technol.*, 25 (2), 379 - 396.
- Adnan, N. L., Ismail, I., and Hashim, M. (2015). Effect of Ferrocene Concentration on the Carbon Nanotube Cotton Synthesized Via Floating Catalyst CVD Method. *Australian Journal of Basic and Applied Sciences*, 9 (12), 109-113.
- Ajayan, P. M., and Zhou, O. Z. (2001). Applications of Carbon Nanotubes. In M. S. Dresselhaus, G. Dresselhaus, & P. Avouris (Eds.), *Carbon Nanotubes: Synthesis, Structure, Properties, and Applications* (pp. 391-425). Berlin, Heidelberg: Springer Berlin Heidelberg.
- Aliev, A. E., Oh, J., Kozlov, M. E., Kuznetsov, A. A., Fang, S., Fonseca, A. F., Ovalle, R., Lima, M. D., Haque, M. H., Gartstein, Y. N., Zhang, M., Zakhidov, A. A., and Baughman, R. H. (2009). Giant-Stroke, Superelastic Carbon Nanotube Aerogel Muscles. *SCIENCE*, 323 (5921), 1575-1578.
- Allen-King, R. M., Grathwohl, P., and Ball, W. P. (2002). New modeling paradigms for the sorption of hydrophobic organic chemicals to heterogeneous carbonaceous matter in soils, sediments, and rocks. *Advances in Water Resources*, 25 (8-12), 985-1016.
- Alonso-Nuñez, G., Valenzuela-Muñiz, A. M., Paraguay-Delgado, F., Aguilar, A., and Verde, Y. (2006). New organometallic precursor catalysts applied to MWCNT synthesis by spray-pyrolysis. *Optical Materials*, 29 (1), 134-139.
- Amaral-Labat, G., Szczurek, A., Fierro, V., Masson, E., Pizzi, A., and Celzard, A. (2012). Impact of depressurizing rate on the porosity of aerogels. *Microporous and Mesoporous Materials*, 152, 240-245.
- Aqel, A., El-Nour, K. M. M. A., Ammar, R. A. A., and Al-Warthan, A. (2012). Carbon nanotubes, science and technology part (I) structure, synthesis and characterisation. *Arabian Journal of Chemistry*, 5 (1), 1-23.
- Arora, N., and Sharma, N. N. (2014). Arc discharge synthesis of carbon nanotubes: Comprehensive review. *Diamond and Related Materials*, 50 (Supplement C), 135-150.
- Audibert, F. (2006). Chapter 3 - Oil composition and the required treatment steps *Waste Engine Oils* (pp. 35-89). Amsterdam: Elsevier.
- Bahr, J. L., Yang, J., Kosynkin, D. V., Bronikowski, M. J., Smalley, R. E., and Tour, J. M. (2001). Functionalization of Carbon Nanotubes by Electrochemical Reduction of Aryl Diazonium Salts: A Bucky Paper Electrode. *J Am Chem Soc*, 123 (27), 6536-6542.

- Bai, S., Li, F., Yang, Q., Cheng, H.-M., and Bai, J. (2003). Influence of ferrocene/benzene mole ratio on the synthesis of carbon nanostructures. *Chemical Physics Letters*, 376 (1–2), 83-89.
- Balandin, A. A., Ghosh, S., Bao, W., Calizo, I., Teweldebrhan, D., Miao, F., and Lau, C. N. (2008). Superior Thermal Conductivity of Single-Layer Graphene. *Nano Lett*, 8 (3), 902-907.
- Barreiro, A., Kramberger, C., Rummeli, M. H., Grüneis, A., Grimm, D., Hampel, S., Gemming, T., Büchner, B., Bachtold, A., and Pichler, T. (2007). Control of the single-wall carbon nanotube mean diameter in sulphur promoted aerosol-assisted chemical vapour deposition. *Carbon*, 45 (1), 55-61.
- Behr, M. J., Gauding, E. A., Mkhoyan, K. A., and Aydil, E. S. (2010). Effect of hydrogen on catalyst nanoparticles in carbon nanotube growth. *Journal of Applied Physics*, 108 (5), 053303.
- Belin, T., and Epron, F. (2005). Characterization methods of carbon nanotubes: a review. *Materials Science and Engineering: B*, 119 (2), 105-118.
- Bi, H., Huang, X., Wu, X., Cao, X., Tan, C., Yin, Z., Lu, X., Sun, L., and Zhang, H. (2014). Carbon Microbelt Aerogel Prepared by Waste Paper: An Efficient and Recyclable Sorbent for Oils and Organic Solvents. *Small*, 10 (17), 3544-3550.
- Bi, H., Yin, Z., Cao, X., Xie, X., Tan, C., Huang, X., Chen, B., Chen, F., Yang, Q., Bu, X., Lu, X., Sun, L., and Zhang, H. (2013). Carbon Fiber Aerogel Made from Raw Cotton: A Novel, Efficient and Recyclable Sorbent for Oils and Organic Solvents. *Adv Mater*, 25 (41), 5916-5921.
- Bryning, M. B., Milkie, D. E., Islam, M. F., Hough, L. A., Kikkawa, J. M., and Yodh, A. G. (2007). Carbon Nanotube Aerogels. *Adv Mater*, 19 (5), 661-664.
- Cao, A., Dickrell, P. L., Sawyer, W. G., Ghasemi-Nejhad, M. N., and Ajayan, P. M. (2005). Super-Compressible Foamlike Carbon Nanotube Films. *SCIENCE*, 310 (5752), 1307-1310.
- Cao, Q., Han, S.-j., Tulevski, G. S., Zhu, Y., Lu, D. D., and Haensch, W. (2013). Arrays of single-walled carbon nanotubes with full surface coverage for high-performance electronics. *Nat Nano*, 8 (3), 180-186.
- Chandrashekar, A., Ramachandran, S., Pollack, G., Lee, J. S., Lee, G. S., and Overzet, L. (2008). Forming carbon nanotube composites by directly coating forests with inorganic materials using low pressure chemical vapor deposition. *Thin Solid Films*, 517 (2), 525-530.
- Chang, S. E., Stone, J., Demes, K., and Piscitelli, M. (2014). Consequences of oil spills: a review and framework for informing planning. *Ecol Soc*, 19 (2), 26.
- Chen, H., Chen, M., Zhang, Y., and Li, Q. (2015). Rational control on floating catalysts for the growth of carbon nanotube assemblies: From vertically

aligned carbon nanotube arrays to carbon nanotube films. *Applied Surface Science*, 353, 651-661.

Chen, N., and Pan, Q. (2013). Versatile Fabrication of Ultralight Magnetic Foams and Application for Oil–Water Separation. *ACS Nano*, 7 (8), 6875-6883.

Cheung, W., Pontoriero, F., Taratula, O., Chen, A. M., and He, H. (2010). DNA and carbon nanotubes as medicine. *Advanced Drug Delivery Reviews*, 62 (6), 633-649.

Cho, W., Schulz, M., and Shanov, V. (2014). Growth and characterization of vertically aligned centimeter long CNT arrays. *Carbon*, 72, 264-273.

Ci, L., Manikoth, S. M., Li, X., Vajtai, R., and Ajayan, P. M. (2007). Ultrathick Freestanding Aligned Carbon Nanotube Films. *Adv Mater*, 19 (20), 3300-3303.

Conroy, D., Moisala, A., Cardoso, S., Windle, A., and Davidson, J. (2010). Carbon nanotube reactor: Ferrocene decomposition, iron particle growth, nanotube aggregation and scale-up. *Chemical Engineering Science*, 65 (10), 2965-2977.

Dalla Betta, R. A., Piken, A. G., and Shelef, M. (1975). Heterogeneous methanation: Steady-state rate of CO hydrogenation on supported ruthenium, nickel and rhenium. *Journal of Catalysis*, 40 (2), 173-183.

De Volder, M. F. L., Tawfick, S. H., Baughman, R. H., and Hart, A. J. (2013). Carbon Nanotubes: Present and Future Commercial Applications. *SCIENCE*, 339 (6119), 535-539.

Deng, J., Yang, B., Chen, C., and Liang, J. (2015). Renewable Eugenol-Based Polymeric Oil-Absorbent Microspheres: Preparation and Oil Absorption Ability. *ACS Sustainable Chemistry & Engineering*, 3 (4), 599-605.

Ding, F., Larsson, P., Larsson, J. A., Ahuja, R., Duan, H., Rosén, A., and Bolton, K. (2008). The Importance of Strong Carbon–Metal Adhesion for Catalytic Nucleation of Single-Walled Carbon Nanotubes. *Nano Lett*, 8 (2), 463-468.

Dong, L., Yang, Q., Xu, C., Li, Y., Yang, D., Hou, F., Yin, H., and Kang, F. (2015). Facile preparation of carbon nanotube aerogels with controlled hierarchical microstructures and versatile performance. *Carbon*, 90, 164-171.

Du, A., Zhou, B., Zhang, Z., and Shen, J. (2013). A Special Material or a New State of Matter: A Review and Reconsideration of the Aerogel. *Materials*, 6 (3), 941.

Du, R., Zhao, Q., Zhang, N., and Zhang, J. (2015). Macroscopic Carbon Nanotube-based 3D Monoliths. *Small*, 11 (27), 3263-3289.

Durães, L., Matias, T., Patrício, R., and Portugal, A. (2013). Silica based aerogel-like materials obtained by quick microwave drying. *Materialwissenschaft und Werkstofftechnik*, 44 (5), 380-385.

- Eatemadi, A., Daraee, H., Karimkhanloo, H., Kouhi, M., Zarghami, N., Akbarzadeh, A., Abasi, M., Hanifehpour, Y., and Joo, S. W. (2014). Carbon nanotubes: properties, synthesis, purification, and medical applications. *Nanoscale Research Letters*, 9 (1), 393.
- Edwards, E. R., Antunes, E. F., Botelho, E. C., Baldan, M. R., and Corat, E. J. (2011). Evaluation of residual iron in carbon nanotubes purified by acid treatments. *Applied Surface Science*, 258 (2), 641-648.
- Fan, X., Buczko, R., Puzos, A. A., Geohegan, D. B., Howe, J. Y., Pantelides, S. T., and Pennycook, S. J. (2003). Nucleation of Single-Walled Carbon Nanotubes. *Physical Review Letters*, 90 (14), 145501.
- Fan, Z., Tng, D. Z. Y., Lim, C. X. T., Liu, P., Nguyen, S. T., Xiao, P., Marconnet, A., Lim, C. Y. H., and Duong, H. M. (2014). Thermal and electrical properties of graphene/carbon nanotube aerogels. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 445, 48-53.
- Feng, J.-M., Li, Y.-L., Hou, F., and Zhong, X.-H. (2008). Controlled growth of high quality bamboo carbon nanotube arrays by the double injection chemical vapor deposition process. *Materials Science and Engineering: A*, 473 (1-2), 238-243.
- Fricke, J., and Tillotson, T. (1997). Aerogels: production, characterization, and applications. *Thin Solid Films*, 297 (1-2), 212-223.
- Gautier, L.-A., Le Borgne, V., and El Khakani, M. A. (2016). Field emission properties of graphenated multi-wall carbon nanotubes grown by plasma enhanced chemical vapour deposition. *Carbon*, 98, 259-266.
- Gavillet, J., Loiseau, A., Journet, C., Willaime, F., Ducastelle, F., and Charlier, J. C. (2001). Root-Growth Mechanism for Single-Wall Carbon Nanotubes. *Physical Review Letters*, 87 (27), 275504.
- Gspann, T. S., Smail, F. R., and Windle, A. H. (2014). Spinning of carbon nanotube fibres using the floating catalyst high temperature route: purity issues and the critical role of sulphur. *Faraday Discussions*, 173 (0), 47-65.
- Guelli Ulson de Souza, S. M. d. A., da Luz, A. D., da Silva, A., and Ulson de Souza, A. A. (2012). Removal of Mono- and Multicomponent BTX Compounds from Effluents Using Activated Carbon from Coconut Shell as the Adsorbent. *Industrial & Engineering Chemistry Research*, 51 (18), 6461-6469.
- Gui, X., Li, H., Wang, K., Wei, J., Jia, Y., Li, Z., Fan, L., Cao, A., Zhu, H., and Wu, D. (2011). Recyclable carbon nanotube sponges for oil absorption. *Acta Materialia*, 59 (12), 4798-4804.
- Gui, X., Wei, J., Wang, K., Cao, A., Zhu, H., Jia, Y., Shu, Q., and Wu, D. (2010). Carbon Nanotube Sponges. *Adv Mater*, 22 (5), 617-621.

- H., B., L., A., J.S., M., and M.M, A. (2010). Synthesis and application of silica aerogel-MWCNT nanocomposites for adsorption of organic pollutants. *SCIENTIA IRANICA*, 17 (2), 122-132.
- Hamilton, J. C., and Blakely, J. M. (1980). Carbon segregation to single crystal surfaces of Pt, Pd and Co. *Surface Science*, 91 (1), 199-217.
- Hashim, D. P., Narayanan, N. T., Romo-Herrera, J. M., Cullen, D. A., Hahm, M. G., Lezzi, P., Suttle, J. R., Kelkhoff, D., Muñoz-Sandoval, E., Ganguli, S., Roy, A. K., Smith, D. J., Vajtai, R., Sumpter, B. G., Meunier, V., Terrones, H., Terrones, M., and Ajayan, P. M. (2012). Covalently bonded three-dimensional carbon nanotube solids via boron induced nanojunctions. *Scientific Reports*, 2, 363.
- Hata, K., Futaba, D. N., Mizuno, K., Namai, T., Yumura, M., and Iijima, S. (2004). Water-Assisted Highly Efficient Synthesis of Impurity-Free Single-Walled Carbon Nanotubes. *SCIENCE*, 306, 1362-1364.
- He, C., Zhao, N., Shi, C., Du, X., and Li, J. (2007). TEM studies of the initial stage growth and morphologies of bamboo-shaped carbon nanotubes synthesized by CVD. *Journal of Alloys and Compounds*, 433 (1–2), 79-83.
- Hoecker, C., Smail, F., Bajada, M., Pick, M., and Boies, A. (2016). Catalyst nanoparticle growth dynamics and their influence on product morphology in a CVD process for continuous carbon nanotube synthesis. *Carbon*, 96, 116-124.
- Hoecker, C., Smail, F., Pick, M., and Boies, A. (2017). The influence of carbon source and catalyst nanoparticles on CVD synthesis of CNT aerogel. *Chemical Engineering Journal*, 314, 388-395.
- Homma, Y. (2015). Carbon Nanotube Synthesis and the Role of Catalyst. In K. Matsumoto (Ed.), *Frontiers of Graphene and Carbon Nanotubes: Devices and Applications* (pp. 125-129). Tokyo: Springer Japan.
- Hong, J.-Y., Sohn, E.-H., Park, S., and Park, H. S. (2015). Highly-efficient and recyclable oil absorbing performance of functionalized graphene aerogel. *Chemical Engineering Journal*, 269, 229-235.
- Iijima, S. (1991). Helical microtubules of graphitic carbon. *Nature*, 354, 56 - 58.
- Iijima, S., and Ichihashi, T. (1993). Single-Shell Carbon Nanotubes of 1-nm Diameter. *Nature*, 363 (6430), 603-605.
- Janas, D., and Koziol, K. K. (2013). Rapid electrothermal response of high-temperature carbon nanotube film heaters. *Carbon*, 59, 457-463.
- Jeong, K. Y., Jung, H. K., and Lee, H. W. (2012). Effective parameters on diameter of carbon nanotubes by plasma enhanced chemical vapor deposition. *Transactions of Nonferrous Metals Society of China*, 22 (Supplement 3), s712-s716.

- Jin, C., Han, S., Li, J., and Sun, Q. (2015). Fabrication of cellulose-based aerogels from waste newspaper without any pretreatment and their use for absorbents. *Carbohydrate Polymers*, 123, 150-156.
- Kabiri, S., Tran, D. N. H., Altalhi, T., and Losic, D. (2014). Outstanding adsorption performance of graphene-carbon nanotube aerogels for continuous oil removal. *Carbon*, 80, 523-533.
- Khosravi, M., and Azizian, S. (2016). A new kinetic model for absorption of oil spill by porous materials. *Microporous and Mesoporous Materials*, 230 (Supplement C), 25-29.
- Kim, M. S., Rodriguez, N. M., and Baker, R. T. K. (1993). The Interplay Between Sulfur Adsorption and Carbon Deposition on Cobalt Catalysts. *Journal of Catalysis*, 143 (2), 449-463.
- Kohlmeyer, R. R., Lor, M., Deng, J., Liu, H., and Chen, J. (2011). Preparation of stable carbon nanotube aerogels with high electrical conductivity and porosity. *Carbon*, 49 (7), 2352-2361.
- Kong, J., Cassell, A. M., and Dai, H. (1998). Chemical vapor deposition of methane for single-walled carbon nanotubes. *Chemical Physics Letters*, 292 (4-6), 567-574.
- Koziol, K., Vilatela, J., Moisala, A., Motta, M., Cunniff, P., Sennett, M., and Windle, A. (2007). High-Performance Carbon Nanotube Fiber. *SCIENCE*, 318 (5858), 1892-1895.
- Lawal, A. T. (2016). Synthesis and utilization of carbon nanotubes for fabrication of electrochemical biosensors. *Materials Research Bulletin*, 73, 308-350.
- Lee, S.-H., Park, J., Kim, H.-R., Lee, J., and Lee, K.-H. (2015). Synthesis of high-quality carbon nanotube fibers by controlling the effects of sulfur on the catalyst agglomeration during the direct spinning process. *RSC Advances*, 5 (52), 41894-41900.
- Lee, S.-H., Park, J., Kim, H.-R., Lee, T., Lee, J., Im, Y.-O., Lee, C.-H., Cho, H., Lee, H., Jun, C.-H., Ahn, Y.-C., Lee, I.-B., and Lee, K.-H. (2016). Synthesis of carbon nanotube fibers using the direct spinning process based on Design of Experiment (DOE). *Carbon*, 100, 647-655.
- Lee, S., Hahm, M. G., Vajtai, R., Hashim, D. P., Thurakitseree, T., Chipara, A. C., Ajayan, P. M., and Hafner, J. H. (2012). Utilizing 3D SERS Active Volumes in Aligned Carbon Nanotube Scaffold Substrates. *Adv Mater*, 24 (38), 5261-5266.
- Li, X., Xue, Y., Zou, M., Zhang, D., Cao, A., and Duan, H. (2016a). Direct Oil Recovery from Saturated Carbon Nanotube Sponges. *ACS Appl Mater Interfaces*, 8 (19), 12337-12343.

- Li, Y., Kinloch, I. A., and Windle, A. H. (2004). Direct Spinning of Carbon Nanotube Fibers from Chemical Vapor Deposition Synthesis. *SCIENCE*, 304 (5668), 276-278.
- Li, Y., Luo, X., Yang, S., Cao, X., Wang, Z., Shi, W., and Zhang, S. (2014). High Specific Monoclonal Antibody Production and Development of an ELISA Method for Monitoring T-2 Toxin in Rice. *Journal of Agricultural and Food Chemistry*, 62 (7), 1492-1497.
- Li, Y., Zhang, R., Tian, X., Yang, C., and Zhou, Z. (2016b). Facile synthesis of Fe₃O₄ nanoparticles decorated on 3D graphene aerogels as broad-spectrum sorbents for water treatment. *Applied Surface Science*, 369, 11-18.
- Liu, B. C., Lee, T. J., Jung, S. I., Park, C. Y., Choa, Y. H., and Lee, C. J. (2005). Synthesis of well-aligned carbon nanotubes with open tips. *Carbon*, 43 (7), 1341-1346.
- Liu, L., Ma, W., and Zhang, Z. (2011a). Macroscopic Carbon Nanotube Assemblies: Preparation, Properties, and Potential Applications. *Small*, 7 (11), 1504-1520.
- Liu, T., Huang, M., Li, X., Wang, C., Gui, C.-X., and Yu, Z.-Z. (2016). Highly compressible anisotropic graphene aerogels fabricated by directional freezing for efficient absorption of organic liquids. *Carbon*, 100, 456-464.
- Liu, W.-W., Aziz, A., Chai, S.-P., Mohamed, A. R., and Tye, C.-T. (2011b). Preparation of iron oxide nanoparticles supported on magnesium oxide for producing high-quality single-walled carbon nanotubes. *New Carbon Materials*, 26 (4), 255-261.
- Luo, J., Tung, V. C., Koltonow, A. R., Jang, H. D., and Huang, J. (2012). Graphene oxide based conductive glue as a binder for ultracapacitor electrodes. *Journal of Materials Chemistry*, 22 (26), 12993-12996.
- Lv, P., Zhang, P., Li, F., Li, Y., Feng, Y., and Feng, W. (2012). Vertically aligned carbon nanotubes grown on carbon fabric with high rate capability for supercapacitors. *Synthetic Metals*, 162 (13-14), 1090-1096.
- Maghsoodi, S., Khodadadi, A., and Mortazavi, Y. (2010). A novel continuous process for synthesis of carbon nanotubes using iron floating catalyst and MgO particles for CVD of methane in a fluidized bed reactor. *Applied Surface Science*, 256 (9), 2769-2774.
- Maleki, H. (2016). Recent advances in aerogels for environmental remediation applications: A review. *Chemical Engineering Journal*, 300, 98-118.
- Meng, F., Li, R., Li, Q., Lu, W., and Chou, T.-W. (2014). Synthesis and failure behavior of super-aligned carbon nanotube film wrapped graphene fibers. *Carbon*, 72, 250-256.
- Miao, M. (2013). Yarn spun from carbon nanotube forests: Production, structure, properties and applications. *Particuology*, 11 (4), 378-393.

- Mikhalchan, A., Fan, Z., Tran, T. Q., Liu, P., Tan, V. B. C., Tay, T.-E., and Duong, H. M. (2016). Continuous and scalable fabrication and multifunctional properties of carbon nanotube aerogels from the floating catalyst method. *Carbon*, 102, 409-418.
- Mirbagheri, S. A., Asghar, K., and Amir Abedin, M. (2012). Macroscopic Synthesis of Vertically Aligned Carbon Nanotubes Using Floating Catalyst Chemical Vapor Deposition Method. *Japanese Journal of Applied Physics*, 51 (1R), 015101.
- Mohana Krishna, V., Abilarasu, A., Somanathan, T., and Gokulakrishnan, N. (2014). Effective synthesis of well graphitized high yield bamboo-like multi-walled carbon nanotubes on copper loaded α -alumina nanoparticles. *Diamond and Related Materials*, 50, 20-25.
- Mohlala, M. S., Liu, X.-Y., Witcomb, M. J., and Coville, N. J. (2007). Carbon nanotube synthesis using ferrocene and ferrocenyl sulfide. The effect of sulfur. *Applied Organometallic Chemistry*, 21 (4), 275-280.
- Motta, M., Kinloch, I., Moisala, A., Premnath, V., Pick, M., and Windle, A. (2007). The parameter space for the direct spinning of fibres and films of carbon nanotubes. *Physica E: Low-dimensional Systems and Nanostructures*, 37 (1-2), 40-43.
- Motta, M., Li, Kinloch, I., and Windle, A. (2005). Mechanical Properties of Continuously Spun Fibers of Carbon Nanotubes. *Nano Lett*, 5 (8), 1529-1533.
- Nardecchia, S., Carriazo, D., Ferrer, M. L., Gutierrez, M. C., and del Monte, F. (2013). Three dimensional macroporous architectures and aerogels built of carbon nanotubes and/or graphene: synthesis and applications. *Chemical Society Reviews*, 42 (2), 794-830.
- Nath, D. C. D., and Sahajwalla, V. (2011). Application of fly ash as a catalyst for synthesis of carbon nanotube ribbons. *J Hazard Mater*, 192 (2), 691-697.
- Neumayer, H., and Haubner, R. (2004). Formation of carbon-nano-fibres and carbon-nanotubes with a vertical flow-reactor. *Diamond and Related Materials*, 13 (4-8), 1191-1197.
- Ni, L., Kuroda, K., Zhou, L.-P., Ohta, K., Matsuishi, K., and Nakamura, J. (2009). Decomposition of metal carbides as an elementary step of carbon nanotube synthesis. *Carbon*, 47 (13), 3054-3062.
- Orlita, M., Faugeras, C., Plochocka, P., Neugebauer, P., Martinez, G., Maude, D. K., Barra, A. L., Sprinkle, M., Berger, C., de Heer, W. A., and Potemski, M. (2008). Approaching the Dirac Point in High-Mobility Multilayer Epitaxial Graphene. *Physical Review Letters*, 101 (26), 267601.
- Ostojic, G. N. (2012). Optical Properties of Assembled Single-Walled Carbon Nanotube Gels. *Chemphyschem*, 13 (8), 2102-2107.

- Oudar, J. (1980). Sulfur Adsorption and Poisoning of Metallic Catalysts. *Catalysis Reviews*, 22 (2), 171-195.
- Parker, C. B., Raut, A. S., Brown, B., Stoner, B. R., and Glass, J. T. (2012). Three-dimensional arrays of graphenated carbon nanotubes. *Journal of Materials Research*, 27 (7), 1046-1053.
- Peigney, A., Coquay, P., Flahaut, E., Vandenberghe, R. E., De Grave, E., and Laurent, C. (2001). A Study of the Formation of Single- and Double-Walled Carbon Nanotubes by a CVD Method. *The Journal of Physical Chemistry B*, 105 (40), 9699-9710.
- Purohit, R., Purohit, K., Rana, S., Rana, R. S., and Patel, V. (2014). Carbon Nanotubes and Their Growth Methods. *Procedia Materials Science*, 6 (Supplement C), 716-728.
- Qi, H., Liu, J., Pionteck, J., Pötschke, P., and Mäder, E. (2015). Carbon nanotube–cellulose composite aerogels for vapour sensing. *Sensors and Actuators B: Chemical*, 213, 20-26.
- Qin, G., Yao, Y., Wei, W., and Zhang, T. (2013). Preparation of hydrophobic granular silica aerogels and adsorption of phenol from water. *Applied Surface Science*, 280, 806-811.
- Rao, F.-B., Li, T., and Wang, Y.-L. (2008). Effect of hydrogen on the growth of single-walled carbon nanotubes by thermal chemical vapor deposition. *Physica E: Low-dimensional Systems and Nanostructures*, 40 (4), 779-784.
- Raty, J.-Y., Gygi, F., and Galli, G. (2005). Growth of Carbon Nanotubes on Metal Nanoparticles: A Microscopic Mechanism from Ab Initio Molecular Dynamics Simulations. *Physical Review Letters*, 95 (9), 096103.
- Reguero, V., Alemán, B., Mas, B., and Vilatela, J. J. (2014). Controlling Carbon Nanotube Type in Macroscopic Fibers Synthesized by the Direct Spinning Process. *Chemistry of Materials*, 26 (11), 3550-3557.
- Saito, R., Dresselhaus, G., and Dresselhaus, M. S. (1998). *Physical Properties of Carbon Nanotubes*: Imperial College Press.
- Scarselli, M., Castrucci, P., De Nicola, F., Cacciotti, I., Nanni, F., Gatto, E., Venanzi, M., and De Crescenzi, M. (2015). Applications of three-dimensional carbon nanotube networks. *Beilstein Journal of Nanotechnology*, 6, 792-798.
- Schwan, M., and Ratke, L. (2013). Flexibilisation of resorcinol-formaldehyde aerogels. *Journal of Materials Chemistry A*, 1 (43), 13462-13468.
- Shah, K. A., and Tali, B. A. (2016). Synthesis of carbon nanotubes by catalytic chemical vapour deposition: A review on carbon sources, catalysts and substrates. *Materials Science in Semiconductor Processing*, 41 (Supplement C), 67-82.

- Shen, Y., Du, A., Wu, X.-L., Li, X.-G., Shen, J., and Zhou, B. (2016). Low-cost carbon nanotube aerogels with varying and controllable density. *Journal of Sol-Gel Science and Technology*, 79 (1), 76-82.
- Simón-Herrero, C., Caminero-Huertas, S., Romero, A., Valverde, J. L., and Sánchez-Silva, L. (2016). Effects of freeze-drying conditions on aerogel properties. *Journal of Materials Science*, 51 (19), 8977-8985.
- Sing, K. S. W. (1985). Reporting physisorption data for gas/solid systems with special reference to the determination of surface area and porosity (Recommendations 1984) *Pure and Applied Chemistry* (Vol. 57, pp. 603).
- Sinnott, S. B., Andrews, R., Qian, D., Rao, A. M., Mao, Z., Dickey, E. C., and Derbyshire, F. (1999). Model of carbon nanotube growth through chemical vapor deposition. *Chemical Physics Letters*, 315 (1-2), 25-30.
- Skaltsas, T., Avgouropoulos, G., and Tasis, D. (2011). Impact of the fabrication method on the physicochemical properties of carbon nanotube-based aerogels. *Microporous and Mesoporous Materials*, 143 (2-3), 451-457.
- Song, C., Ding, L., Yao, F., Deng, J., and Yang, W. (2013). β -Cyclodextrin-based oil-absorbent microspheres: Preparation and high oil absorbency. *Carbohydrate Polymers*, 91 (1), 217-223.
- Song, L., Ci, L., Lv, L., Zhou, Z., Yan, X., Liu, D., Yuan, H., Gao, Y., Wang, J., Liu, L., Zhao, X., Zhang, Z., Dou, X., Zhou, W., Wang, G., Wang, C., and Xie, S. (2004). Direct Synthesis of a Macroscale Single-Walled Carbon Nanotube Non-Woven Material. *Adv Mater*, 16 (17), 1529-1534.
- Stoner, B. R., Raut, A. S., Brown, B., Parker, C. B., and Glass, J. T. (2011). Graphenated carbon nanotubes for enhanced electrochemical double layer capacitor performance. *Applied Physics Letters*, 99 (18), 183104.
- Sui, Z., Meng, Q., Zhang, X., Ma, R., and Cao, B. (2012). Green synthesis of carbon nanotube-graphene hybrid aerogels and their use as versatile agents for water purification. *Journal of Materials Chemistry*, 22 (18), 8767-8771.
- Sui, Z., Zhang, X., Lei, Y., and Luo, Y. (2011). Easy and green synthesis of reduced graphite oxide-based hydrogels. *Carbon*, 49 (13), 4314-4321.
- Sun, H., Xu, Z., and Gao, C. (2013). Multifunctional, Ultra-Flyweight, Synergistically Assembled Carbon Aerogels. *Adv Mater*, 25 (18), 2554-2560.
- Sundaram, R. M., Koziol, K. K. K., and Windle, A. H. (2011). Continuous Direct Spinning of Fibers of Single-Walled Carbon Nanotubes with Metallic Chirality. *Adv Mater*, 23 (43), 5064-5068.
- Talapatra, S., Kar, S., Pal, S. K., Vajtai, R., CiL, Victor, P., Shaijumon, M. M., Kaur, S., Nalamasu, O., and Ajayan, P. M. (2006). Direct growth of aligned carbon nanotubes on bulk metals. *Nat Nano*, 1 (2), 112-116.

- Tanobe, V. O. A., Sydenstricker, T. H. D., Amico, S. C., Vargas, J. V. C., and Zawadzki, S. F. (2009). Evaluation of flexible postconsumed polyurethane foams modified by polystyrene grafting as sorbent material for oil spills. *Journal of Applied Polymer Science*, 111 (4), 1842-1849.
- Unur, E. (2013). Functional nanoporous carbons from hydrothermally treated biomass for environmental purification. *Microporous and Mesoporous Materials*, 168, 92-101.
- Vander Wal, R. L., and Ticich, T. M. (2001). Comparative flame and furnace synthesis of single-walled carbon nanotubes. *Chemical Physics Letters*, 336 (1-2), 24-32.
- Vazquez-Duhalt, R. (1989). Environmental impact of used motor oil. *Science of The Total Environment*, 79 (1), 1-23.
- Vilatela, J. J., Deng, L., Kinloch, I. A., Young, R. J., and Windle, A. H. (2011). Structure of and stress transfer in fibres spun from carbon nanotubes produced by chemical vapour deposition. *Carbon*, 49 (13), 4149-4158.
- Wan, W., Zhang, R., Li, W., Liu, H., Lin, Y., Li, L., and Zhou, Y. (2016). Graphene-carbon nanotube aerogel as an ultra-light, compressible and recyclable highly efficient absorbent for oil and dyes. *Environmental Science: Nano*, 3 (1), 107-113.
- Wang, D., Silbaugh, T., Pfeffer, R., and Lin, Y. S. (2010). Removal of emulsified oil from water by inverse fluidization of hydrophobic aerogels. *Powder Technology*, 203 (2), 298-309.
- Wang, J. N., Luo, X. G., Wu, T., and Chen, Y. (2014). High-strength carbon nanotube fibre-like ribbon with high ductility and high electrical conductivity. *Nature Communications*, 5, 3848.
- Wei, B. Q., Vajtai, R., Jung, Y., Ward, J., Zhang, R., Ramanath, G., and Ajayan, P. M. (2002). Microfabrication technology: Organized assembly of carbon nanotubes. *Nature*, 416 (6880), 495-496.
- Worsley, M. A., Pauzauskie, P. J., Kucheyev, S. O., Zaugg, J. M., Hamza, A. V., Satcher Jr, J. H., and Baumann, T. F. (2009). Properties of single-walled carbon nanotube-based aerogels as a function of nanotube loading. *Acta Materialia*, 57 (17), 5131-5136.
- Worsley, M. A., Satcher, J. H., and Baumann, T. F. (2008). Synthesis and Characterization of Monolithic Carbon Aerogel Nanocomposites Containing Double-Walled Carbon Nanotubes. *Langmuir*, 24 (17), 9763-9766.
- Wu, X., Wu, D., Fu, R., and Zeng, W. (2012). Preparation of carbon aerogels with different pore structures and their fixed bed adsorption properties for dye removal. *Dyes and Pigments*, 95 (3), 689-694.

- Xiaodong, D., Xiaonan, L., Tao, D., Wenkun, Z., Zao, Y., and Weitang, Y. (2016). Fabricating a graphene oxide—bayberry tannin sponge for effective radionuclide removal. *Materials Research Express*, 3 (5), 055002.
- Xu, M., Futaba, D. N., Yamada, T., Yumura, M., and Hata, K. (2010). Carbon Nanotubes with Temperature-Invariant Viscoelasticity from -196° to 1000°C . *SCIENCE*, 330 (6009), 1364-1368.
- Yaglioglu, O., Cao, A., Hart, A. J., Martens, R., and Slocum, A. H. (2012). Wide Range Control of Microstructure and Mechanical Properties of Carbon Nanotube Forests: A Comparison Between Fixed and Floating Catalyst CVD Techniques. *Advanced Functional Materials*, 22 (23), 5028-5037.
- Yah, C. S., Iyuke, S. E., Simate, G. S., Unuabonah, E. I., Bathgate, G., Matthews, G., and Cluett, J. D. (2011). Continuous synthesis of multiwalled carbon nanotubes from xylene using the swirled floating catalyst chemical vapor deposition technique. *Journal of Materials Research*, 26 (5), 640-644.
- Yan, Y., Miao, J., Yang, Z., Xiao, F.-X., Yang, H. B., Liu, B., and Yang, Y. (2015). Carbon nanotube catalysts: recent advances in synthesis, characterization and applications. *Chemical Society Reviews*, 44 (10), 3295-3346.
- Yang, S. J., Kang, J. H., Jung, H., Kim, T., and Park, C. R. (2013). Preparation of a freestanding, macroporous reduced graphene oxide film as an efficient and recyclable sorbent for oils and organic solvents. *Journal of Materials Chemistry A*, 1 (33), 9427-9432.
- Yoshida, H., Takeda, S., Uchiyama, T., Kohno, H., and Homma, Y. (2008). Atomic-Scale In-situ Observation of Carbon Nanotube Growth from Solid State Iron Carbide Nanoparticles. *Nano Lett*, 8 (7), 2082-2086.
- Yu, F., Ma, J., and Wu, Y. (2011a). Adsorption of toluene, ethylbenzene and m-xylene on multi-walled carbon nanotubes with different oxygen contents from aqueous solutions. *J Hazard Mater*, 192 (3), 1370-1379.
- Yu, K., Lu, G., Bo, Z., Mao, S., and Chen, J. (2011b). Carbon Nanotube with Chemically Bonded Graphene Leaves for Electronic and Optoelectronic Applications. *The Journal of Physical Chemistry Letters*, 2 (13), 1556-1562.
- Yu, M.-F., Files, B. S., Arepalli, S., and Ruoff, R. S. (2000). Tensile Loading of Ropes of Single Wall Carbon Nanotubes and their Mechanical Properties. *Physical Review Letters*, 84 (24), 5552-5555.
- Yu, Q., Zhang, R., Deng, S., Huang, J., and Yu, G. (2009). Sorption of perfluorooctane sulfonate and perfluorooctanoate on activated carbons and resin: Kinetic and isotherm study. *Water Research*, 43 (4), 1150-1158.
- Zhang, F., Tang, J., Wang, Z., and Qin, L.-C. (2013a). Graphene-carbon nanotube composite aerogel for selective detection of uric acid. *Chemical Physics Letters*, 590, 121-125.

- Zhang, G., Mann, D., Zhang, L., Javey, A., Li, Y., Yenilmez, E., Wang, Q., McVittie, J. P., Nishi, Y., Gibbons, J., and Dai, H. (2005). Ultra-high-yield growth of vertical single-walled carbon nanotubes: Hidden roles of hydrogen and oxygen. *Proceedings of the National Academy of Sciences of the United States of America*, 102 (45), 16141-16145.
- Zhang, J., Tang, Y.-j., Yi, Y., Ma, K.-f., Zhou, M.-j., Wu, W.-d., and Wang, C.-y. (2016). Large-scale synthesis of novel vertically-aligned helical carbon nanotube arrays. *New Carbon Materials*, 31 (6), 568-573.
- Zhang, R., Zhang, Y., Zhang, Q., Xie, H., Qian, W., and Wei, F. (2013b). Growth of Half-Meter Long Carbon Nanotubes Based on Schulz–Flory Distribution. *ACS Nano*, 7 (7), 6156-6161.
- Zhang, X., Liu, J., Xu, B., Su, Y., and Luo, Y. (2011). Ultralight conducting polymer/carbon nanotube composite aerogels. *Carbon*, 49 (6), 1884-1893.
- Zheng, L., Zhang, X., Li, Q., Chikkannanavar, S. B., Li, Y., Zhao, Y., Liao, X., Jia, Q., Doorn, S. K., Peterson, D. E., and Zhu, Y. (2007). Carbon-Nanotube Cotton for Large-Scale Fibers. *Adv Mater*, 19 (18), 2567-2570.
- Zhong, X.-H., Li, Y.-L., Feng, J.-M., Kang, Y.-R., and Han, S.-S. (2012). Fabrication of a multifunctional carbon nanotube "cotton" yarn by the direct chemical vapor deposition spinning process. *Nanoscale*, 4 (18), 5614-5618.
- Zhu, H., Ci, L., Xu, C., Liang, J., and Wu, D. (2002a). Growth mechanism of Y-junction carbon nanotubes. *Diamond and Related Materials*, 11 (7), 1349-1352.
- Zhu, H. W., Xu, C. L., Wu, D. H., Wei, B. Q., Vajtai, R., and Ajayan, P. M. (2002b). Direct Synthesis of Long Single-Walled Carbon Nanotube Strands. *SCIENCE*, 296 (5569), 884-886.
- Zhu, Z., Bukowski, B., Deskins, N. A., and Zhou, H. S. (2015). Bamboo shaped carbon nanotube supported platinum electrocatalyst synthesized by high power ultrasonic-assisted impregnation method for methanol electrooxidation and related density functional theory calculations. *International Journal of Hydrogen Energy*, 40 (5), 2216-2224.
- Zou, J., Liu, J., Karakoti, A. S., Kumar, A., Joung, D., Li, Q., Khondaker, S. I., Seal, S., and Zhai, L. (2010). Ultralight Multiwalled Carbon Nanotube Aerogel. *ACS Nano*, 4 (12), 7293-7302.