



UNIVERSITI PUTRA MALAYSIA

***SYNTHESIS OF ALKYLAMINE FUNCTIONALIZED GRAPHENE OXIDE
BY GAMMA IRRADIATION***

NORANIZA BINTI AHMAD DAUD

FS 2017 65



**SYNTHESIS OF ALKYLAMINE FUNCTIONALIZED GRAPHENE OXIDE BY
GAMMA IRRADIATION**

By

NORANIZA BINTI AHMAD DAUD

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia in
fulfilment of Requirements for the Degree of Master of Science**

May 2017

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any materials contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



To them this work is dedicated.

My parents Ahmad Daud & Norbaini who gave me strength and courage throughout the journey. Brothers, sister and best friends who housed, nurtured and praying for my success. Without their understanding and support, I would never have completed this project.

Lots of love.



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Master of Science

SYNTHESIS OF ALKYLAMINE FUNCTIONALIZED GRAPHENE OXIDE BY GAMMA IRRADIATION

By

NORANIZA BINTI AHMAD DAUD

May 2017

Chairman : Associate Professor Nor Azowa Binti Ibrahim, PhD
Faculty : Science

This research aims to alter hydrophilic GO to become hydrophobic. Gamma-ray (γ -ray) irradiation technique was used to functionalize GO with various alkyl chain length of an alkylamine. Functionalization of alkylchain onto the GO was confirmed by X-ray Diffraction (XRD), Fourier Transform Infrared (FTIR), Nuclear Magnetic Resonance (^1H NMR), and X-ray Photoelectron Spectroscopy (XPS). XRD analysis showed the diffraction peak of graphite was shifted from $2\theta=26.40^\circ$ to lower angle at $2\theta=10.20^\circ$ corresponding to an increasing the interlayer spacing from 0.34 nm of graphite to 0.87 nm of GO upon oxidation. Further increasing of interlayer up to 2.68 nm for GO-A18 was observed after functionalization suggested the long alkylchain was successful intercalated between graphene sheets. FTIR result verified the existence of oxygen functionalities on GO after been oxidized by modified Hummers method. Functionalization by γ -ray irradiation method was able to attach alkylchain on the surfaces of GO by the appearance of significant peaks around $2928\text{--}2863\text{ cm}^{-1}$ corresponding to the C-H stretching vibration of the alkyl chain (CH_2). ^1H NMR analysis also supported these findings by the emergence of small intensity at $\sim 0.88\text{ ppm}$ ($-\text{CH}_3$) and the very intense signal at $\sim 1.25\text{ ppm}$ ($-\text{CH}_2$). Simultaneously, this method showed reduction effect by removing some of the oxygen functionalities that have been confirmed by decreasing of O/C ratio in XPS analysis. The effects of various alkyl lengths functionalized-GO on morphological and thermal properties were investigated. The addition of alkylchain on GO surfaces significantly improves the thermal stability of GO, suggesting their great potential for hydrophobic material in for various applications. Scanning Electron Microscopy (SEM) analysis showed an increase in surface roughness after functionalization which gives huge influences on the wetting properties of the substance as the water contact angle of GO-A18 gives higher value up to 114.11° . Therefore, this gamma irradiation technique has been successfully functionalized GO and simultaneously reduce them to become hydrophobic materials.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Sarjana Sains

SINTESIS ALKILAMIN PERFUNGSIAN-GRAFIN OKSIDA MENGUNAKAN SINAR GAMMA

Oleh

NORANIZA BINTI AHMAD DAUD

Mei 2017

Pengerusi : Profesor Madya Nor Azowa Binti Ibrahim, PhD
Fakulti : Sains

Kajian ini bertujuan untuk mengubah sifat hidrofilik GO untuk menjadi hidrofobik. Teknik penyinaran sinar gamma (sinar- γ) telah digunakan untuk memfungsikan grafina oksida (GO) dengan pelbagai panjang rantai alkil daripada alkilamin. Perfungsian rantai alkil kepada GO telah disahkan oleh Sinar-X Difraktometer (XRD), Inframerah Jelmaan Fourier (FTIR), Nuklear Magnetik Resonan (^1H NMR), dan Spektroskopi fotoelektron Sinar-X (XPS). Analisis XRD menunjukkan puncak pembelauan grafit telah beralih daripada $2\theta=26.40^\circ$ kepada sudut yang lebih rendah di $2\theta=10.20^\circ$ sepadan dengan peningkatan jarak antara lapisan daripada 0.34 nm grafit kepada 0.87 nm GO selepas pengoksidaan. Peningkatan antara lapis yang berterusan sehingga 2.68 nm untuk GO-A18 diperhatikan selepas perfungsian mencadangkan bahawa rantai alkil panjang telah berjaya diinterkalasi antara kepingan graphene. Keputusan dari FTIR mengesahkan kewujudan kumpulan berfungsi oksigen pada GO selepas teroksida dengan kaedah Hummers yang diubah suai. Perfungsian dengan kaedah penyinaran sinar- γ dapat melekatkan rantai alkil pada permukaan GO dengan kemunculan puncak yang ketara sekitar $2928\text{--}2863\text{ cm}^{-1}$ yang sepadan dengan C-H isyarat getaran rantai alkil (CH_2). Analisis ^1H NMR juga menyokong penemuan ini dengan kemunculan keamatan kecil di $\sim 0.88\text{ ppm}$ ($-\text{CH}_3$) dan isyarat yang sangat kuat pada $\sim 1.25\text{ ppm}$ ($-\text{CH}_2$). Pada masa yang sama, kaedah ini menunjukkan kesan penurunan dengan membuang sebahagian daripada kumpulan berfungsi oksigen yang telah disahkan dengan pengurangan daripada nisbah O/C dalam analisis XPS. Kesan pelbagai panjang alkil dalam GO-terfungsi pada sifat morfologi dan kestabilan terma telah disiasat. Penambahan rantai alkil pada permukaan GO meningkatkan kestabilan terma GO, menunjukkan potensi besar mereka sebagai bahan hidrofobik untuk pelbagai aplikasi. Mikroskop Pengimbasan Elektron (SEM) menunjukkan peningkatan kekasaran permukaan selepas perfungsian yang memberikan pengaruh yang besar terhadap sifat-sifat pembasahan bahan sebagai mana sudut sentuh air untuk GO-A18 memberikan nilai yang tinggi sehingga 114.11° . Oleh itu, teknik sinaran gamma ini telah berjaya memfungsikan GO dan pada masa yang sama menurunkannya untuk menjadi bahan hidrofobik.

ACKNOWLEDGEMENTS

In the name of Allah, the Beneficent, the Merciful

All praise to Allah, the Almighty, on whom ultimately we depend for sustenance and guidance. Indeed, without His help and will, nothing is accomplished.

My sincere appreciation goes to my supervisor Associate Professor Dr Nor Azowa. This thesis would not have been possible without her help, guidance, support, patience, careful reading and valuable constructive comments provided throughout my time as her student. I also like to express my deepest appreciation to both my co-supervisor Dr Ernee Noryana and Dr Zurina for her good advice and continued support. I am indebted to Dr Chieng Buong Woei for his constant encouragement to guide both my research and writing process with his wisdom, knowledge, and experience. I would also like to express my gratitude to all research members, Nuraini Md Sukur, NasAulia Nasarudin, Thiruventhan Karunakaran, Abu Bakar Yauri, and Saleh Isyaku as well as the Department of Chemistry, Faculty of Science, with all technical staffs who directly helped me in accomplishing this study.

I have been extremely lucky to have financial support by Ministry of Higher Education (MOHE) for My Brain (My Master) scholarship and Graduate Research Financial (GRF).

It gives me great pleasure in acknowledging the praying, experienced all of my ups and downs, support and financial help of my parent, Mr. Ahmad Daud Bin Jaafar and Ms Norbaini Binti Hj Yusof. Special thanks, tribute and appreciation to my housemates and all those who have contributed in the successful of this study.

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the Master of Science. The members of the Supervisory Committee were as follows:

Norazowa binti Ibrahim, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Ernee Noryana binti Mohamad, PhD

Senior Lecturer
Faculty of Science
Universiti Putra Malaysia
(Member)

Zurina binti Zainal Abidin, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of the thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____

Name of Chairman
of Supervisory
Committee: _____

Signature: _____

Name of Member
of Supervisory
Committee: _____

Signature: _____

Name of Member
of Supervisory
Committee: _____

TABLE CONTENTS

	Page
ABSTRACT	i
ABSTRAK	ii
ACKNOWLEDGEMENTS	iii
APPROVAL	iv
DECLARATION	vi
LIST OF TABLES	x
LIST OF FIGURES	xi
LIST OF ABBREVIATIONS	xiii
 CHAPTER	
 1 INTRODUCTION	 1
1.1 Background of study	2
1.2 Problem statement	3
1.3 Significant of study	3
1.4 Scope of study	3
1.5 Research objectives	3
 2 LITERATURE REVIEW	 4
2.1 Hydrophobic material	4
2.2 Carbon-based material	7
2.2.1 Carbon Nanotube (CNT)	7
2.2.2 Graphene	8
2.2.3 Graphene Oxide	8
2.2.4 Reduced Graphene Oxide	9
2.3 Synthesis of GO	10
2.3.1 Brodie's Method	11
2.3.2 Staudenmaier's Method	11
2.3.3 Hoffman and Hummers Method	12
2.3.4 Modified Hummers Method	12
2.4 Modification of GO	13
2.5 Radiation Processing	16
2.5.1 Gamma Irradiation	17
2.5.2 Gamma Irradiation in Food and Agriculture	17
2.5.3 Gamma Irradiation in polymer	18
 3 MATERIALS AND METHODS	 20
3.1 Materials	20
3.2 Preparation of Graphene Oxide	20
3.3 Functionalization of Graphene Oxide	20
3.4 Characterization	21
3.4.1 X-ray Diffraction (XRD)	21
3.4.2 Fourier Transform Infrared Analysis (FTIR)	21
3.4.3 Thermogravimetric Analysis (TGA)	21
3.4.4 Nuclear Magnetic Resonance (NMR)	21

3.4.5	X-ray Photoelectron Spectroscopy Analysis (XPS)	22
3.4.6	Scanning Electron Microscopy (SEM)	22
3.4.7	Water Contact Angle and Surface Energy Analysis	22
4	RESULTS AND DISCUSSION	
4.1	X-ray diffraction (XRD)	23
4.1.1	XRD analysis of graphite and GO	23
4.1.2	XRD analysis of GO and functionalized-GO	24
4.2	Proposed Reaction Mechanism	26
4.3	Fourier Transform Infrared Analysis (FTIR)	29
4.3.1	FTIR analysis of graphite and GO	29
4.3.2	FTIR analysis of GO, A18 and GO-A18	30
4.3.3	FTIR analysis of GO and functionalized-GO	31
4.4	Thermogravimetric Analysis (TGA)	33
4.4.1	TGA of graphite and GO	33
4.4.2	TGA of GO, A18 and GO-A18	33
4.4.3	TGA of GO and functionalized-GO	35
4.5	Nuclear Magnetic Resonance (NMR)	37
4.6	X-ray Photoelectron Spectroscopy (XPS)	40
4.6.1	XPS survey scan spectrum	40
4.6.2	Deconvoluted XPS C1s spectra	41
4.6.3	Deconvoluted XPS O1s spectra	42
4.6.4	Deconvoluted XPS N1s spectra	43
4.7	The structure and wetting propertie of GO and functionalized-GO	44
4.7.1	Scanning Electron Microscopy	45
4.7.2	Water Contact Angle analysis and surface energy	47
4.8	Percentage of Grafting	49
5	CONCLUSION AND RECCOMENDATION	
5.1	Conclusion	51
5.2	Recommendation for Future Work	51
	REFERENCES	52
	APPENDICES	61
	BIODATA OF STUDENT	66
	LIST OF PUBLICATIONS	67

LIST OF TABLES

Table	Page
2.1 Summary of GO synthesis methods	12
2.2 List of graphene-based superhydrophobic surfaces (Meng and Park, 2014)	13
3.1 Amount of GO and alkylamine used for functionalization	20
4.1 2θ and d-spacing of graphite, GO, and functionalized-GO	25
4.2 Type and average bond energy	28
4.3 Band assignment of FTIR spectra of GO, ODA, and GO-ODA	31
4.4 Degradation and maximum decomposition temperature of GO, A18, and GO-A18	34
4.5 Degradation temperature and maximum degradation temperature of GO and functionalized-GO	37
4.6 Elemental data results for GO and functionalized-GO	41
4.7 Surface energy of GO and functionalized-GO	49
4.8 Data analysis of GO and GO-A	49
4.9 Percentage of grafting of functionalized-GO	50

LIST OF FIGURES

Figure		Page
2.1	Schematic diagram representing water contact angle on hydrophilic, hydrophobic and superhydrophobic surface (Nuraje <i>et al.</i> , 2013)	4
2.2	Application of hydrophobic materials and surfaces (Xue <i>et al.</i> , 2016)	5
2.3	Lotus effect: (a) lotus leaf; (b) scanning electron microscopy (SEM) image of micropapillae present on the surface of a lotus leaf; (c) image of a water droplet on a lotus leaf; (d) structural diagram of micro- and nano-structure of single micropapilla (Meng and Park, 2014)	6
2.4	Different type of carbon based materials (Nada <i>et al.</i> , 2015)	7
2.5	Structure of Graphene Oxide (Nasrollah <i>et al.</i> , 2015)	8
2.6	Photographs of GO and rGO dispersion in water	9
2.7	Synthesis of GO from graphite (Chua and Pumera, 2014)	10
2.8	Electromagnetic spectrum (Zamanian and Hardiman, 2005)	16
4.1	XRD patterns of GO and graphite	23
4.2	XRD patterns for graphite, GO and rGO (Mishra <i>et al.</i> , 2014)	24
4.3	XRD patterns of GO and functionalized-GO	24
4.4	Probable scheme for attachment of alkylamine onto GO surfaces	26
4.5	FTIR spectra of graphite and GO	29
4.6	FTIR spectra of GO, A18 and GO-A18	30
4.7	FTIR spectra of GO and functionalized-GOs	31
4.8	TGA of graphite and GO	32
4.9	TGA of GO, A18, and GO-A18	33
4.10	DTG of GO, A18 and GO-A18	34
4.11	TGA thermograms of GO and functionalized-GOs	36
4.12	DTG thermograms of GO and functionalized-GOs	36

4.13	^1H NMR spectrum of functionalized-GO in CDCl_3	38
4.14	Nitrogen peak on ^1H NMR spectrum of functionalized-GO	39
4.15	Binding energy of GO and functionalized-GO	41
4.16	Deconvolution of C1s peak of GO and functionalized-GO	42
4.17	Deconvolution of O1s peak of GO and functionalized-GO	43
4.18	Deconvolution of N1s peak of GO and functionalized-GO	44
4.19	Vacuum filtration result for functionalized-GO	45
4.20	SEM micrograph of graphite and GO	46
4.21	SEM micrograph of functionalized-GO	47
4.22	Water contact angle of functionalized-GO	48
4.23	Bar chart for percentage of grafting of functionalized-GO	50

LIST OF ABBREVIATIONS

nm	Nanometer
Sm^{-1}	siemens per meter
wt %	weight percentage
•OH	oxidative radical
•H	reductive radical
\bar{e}	Electron
λ	wavelength

CHAPTER 1

INTRODUCTION

1.1 Background of study

The usage of hydrophobic material in the recent years is very popular especially as a coating material due to the presence of desired features such as waterproof, corrosion-resistant and stable against bio-fouling and inorganic materials (in some cases). However, water is often detrimental to the materials when the surface is penetrated to moisture. This is because most of the surfaces are design to work under dry conditions. For that reason, the investigation on the synthesis and preparation of hydrophobic materials become popular among the researcher. To prepare the materials with a larger contact angle, one should combine the effect of the surface roughness which is mainly governed by both chemical composition and geometrical microstructure of the surface (Mohamed *et al.*, 2015).

Graphene has become a matter of interest in science and another research field since it was introduced in 2004. It has been exploited in various application due to the amazing properties such as high Young's modulus, strength, good mobility of charge carrier and good in thermal conductivity (Li *et al.*, 2014). However, production of graphene is quite difficult because each layer of graphene that exist in graphite is hold by strong Van der Waals forces. Graphene oxide (GO) is another derivative of graphene that consists of highly oxygen-containing functional groups on their basal planes and edges which can be synthesized by chemical oxidation of graphite. Various oxygen functionalities that exist on GO surfaces make them easily disperse in water and several polar solvents. Recently, GO has attracted much attention due to its outstanding unique and physical property such as good thermal conductivity, high mechanical strength, and also have very good electrical (Compton *et al.*, 2010) and optical characteristics (Zhu *et al.*, 2010; Loh *et al.*, 2010). This great and amazing properties makes GO suitable for use in a numerous of technological applications such as composite materials, sensors, hydrogen storage and semiconductor materials for electronic devices.

After all, very few studies have examined water-graphene interactions which could be an important study, if GO has to be used in conformal coatings. Apart from that, various functionalities on the surface of GO make it an ideal platform for chemical modification, which may generate materials with fabulous properties. The introduction of hydrophobic groups on GO surface is an attractive objective, especially when aiming for compatibilization with non-polar substances and making of coating materials. For this project, GO was used as the main materials for modification by altering its surfaces in order to improve the hydrophobicity.

Hydrophobicity can be improved by increasing surface roughness with introducing a new substance that owns hydrophobic properties with low surface energy. Various low surface energy materials have been used to modify materials surface to become

hydrophobic. Fluorinated compounds, the long alkyl chain of fatty acids, and silanes are compounds that have low surface energy and the ability to attach with various substrates (Meng and Park, 2014). Intercalation of organic molecules in the gallery spacing of layered materials is one of the common modification technique since they can lead to potential applications such as catalytic supports. Numerous method had been established for modification of GO. Recently, gamma-ray (γ -ray) irradiation has attracted attention among researchers in providing not only an environmental friendly method but also feasible, cost effective and can be performed at room temperature as well.

In the present research work, an easy and efficient method will be used to synthesize functionalize-GO that possesses hydrophobic properties by using γ -ray irradiation. GO will be functionalized with a different chain length of alkylamine keeping the other parameters fixed at certain values. The chain length of alkylamine present on GO will change the surface roughness which lead to production of a good hydrophobicity materials.

1.2 Problem statement

Although graphene has attracted numerous attention from research field because of their wide-ranging in industrial and various applications, there are still some obstacles to produce graphene in large scale. GO has been seen as a trigger to the production of graphene through various methods. In fact, GO has been studied for a longer time period than graphene. However, GO somehow is difficult to be incorporated and distributed homogeneously into some of the matrices for applications, especially with hydrophobic materials. Despite focusing on their amazing properties, still, not much research has been done on hydrophobicity properties of GO. Recently, many researchers conducted the investigation on the chemically modified of GO in order to improve properties of GO such as solubility, hydrophobicity and interfacial interactivity with target matrix. However, producing functionalized-GO in large-scale and at low cost is still a challenge which should be overcome before widespread application. Most of the commonly employed modification techniques are often complex that usually possesses long reaction time, involving toxic reagents with specific reaction condition which will restrict the large-scale production. Therefore, a novel route that combines the economic benefits and convenience of chemical synthesis with possessing high reduction efficiency, has been a target for the preparation of functionalized-GO. In this research, the preparation and characterization of GO are presented at first. Subsequently, the functionalization of GO with alkylamine had been done through gamma-ray irradiation method. The investigation on the hydrophobic characteristics of functionalized-GO will be carried out and the results of this study are presented in this thesis.

1.3 Significant of study

Compared with the chemical modifications method, the use of the γ -ray radiation method for functionalized GO has been highlighted to provide a safe, shorter reaction time and environment-friendly to alter the chemical or physical properties of this materials. In addition, the capability of this technique to reduce GO makes it very effective in tuning the hydrophilic GO becomes hydrophobic.

1.4 Scope of study

Due to cheap and readily available in bulk quantities, graphite has been used as a starting material for preparation of GO. The method for preparation of GO is through modified Hummer's method. X-ray diffraction analysis (XRD) was conducted to confirm the increasing of an interlayer between graphene sheets upon oxidation process. In order to improve the hydrophobicity of GO, the resulted GO is further functionalized with various type of alkylamine through γ -ray radiation method. Nuclear Magnetic Resonance (NMR) and X-ray photoelectron Spectroscopy analysis (XPS) was performed in order to verify the formation of the new bond upon functionalization. The structure and wetting properties of functionalized-GO were observed via Scanning Electron Microscopy (SEM) and Water Contact Angle (WCA) analysis respectively. In addition, the investigation on the thermal stability of the functionalized-GO was performed using Thermogravimetry analysis (TGA).

1.5 Research objectives

The main objectives of the study are:

- 1) to synthesize GO using an improved Hummer's method.
- 2) to functionalize GO with alkylamine through gamma irradiation.
- 3) to investigate the effect of different chain length of alkylamine on the hydrophobicity behavior of functionalized-GO.

REFERENCES

- Ammar, A., Al-Enizi, A. M., AlMaadeed, M. A., and Karim, A. (2016). Influence of graphene oxide on mechanical, morphological, barrier, and electrical properties of polymer membranes. *Arabian Journal of Chemistry*, 9(2), 274–286.
- Ansón-Casaos, A., Puértolas, J. A., Pascual, F. J., Hernández-Ferrer, J., Castell, P., Benito, A. M., and Martínez, M. T. (2014). The effect of gamma-irradiation on few-layered graphene materials. *Applied Surface Science*, 301, 264–272.
- Arthi G, Paulchamy B, L. B. (2015). A Simple Approach to Stepwise Synthesis of Graphene Oxide Nanomaterial. *Journal of Nanomedicine & Nanotechnology*, 06(01), 2–5.
- Appelhans, D. J., Carr, L. D., & Lusk, M. T. (2010). Embedded ribbons of graphene allotropes: an extended defect perspective. *New Journal of Physics*, 12(12), 125006.
- Bao, H., Pan, Y., Ping, Y., Sahoo, N. G., Wu, T., Li, L., and Gan, L. H. (2011). Chitosan-functionalized graphene oxide as a nanocarrier for drug and gene delivery. *Small (Weinheim an Der Bergstrasse, Germany)*, 7(11), 1569–78.
- Bartelmeß, J., Quinn, S. J., & Giordani, S. (2014). Chem Soc Rev Carbon nanomaterials : multi-functional agents for biomedical fluorescence and Raman imaging. *Chemical Society Reviews*, 44, 4672–4698.
- Barthlott, W., Neinhuis, C., Verlot, H., and Schott, C. L. (1997). Purity of the sacred lotus, or escape from contamination in biological surfaces, 202, 1–8.
- Bertolini, A., Mestres, C., Colonna, P., and Raffi, J. (2001). Free radical formation in UV- and gamma-irradiated cassava starch. *Carbohydrate Polymers*, 44, 269-271.
- Bhat, R., and Karim, A. A. (2009). Impact of Radiation Processing on Starch. *Comprehensive Reviews in Food Science and Food Safety*, 8, 44-58.
- Bhat, R., Sridhar, K. R., and Bhushan, B. (2007). Free radicals in velvet bean seeds (*Mucuna pruriens* L. DC.) and their status after γ -irradiation and conventional processing. *LWT-Food Science and Technology*, 40(9), 1570–1577.
- Bhat, R., Sridhar, K. R., and Tomita-Yokotani, K. (2007). Effect of ionizing radiation on antinutritional features of velvet bean seeds (*Mucuna pruriens*). *Food Chemistry*, 103(3), 860–866.
- Boinovich, L. B., and Emelyanenko, A. M. (2008). Hydrophobic materials and coatings : principles of design, properties and applications, 77(7). 583-600.
- Brodie, B. C. (1859). On the Atomic Weight of Graphite. *Philosophical Transactions of the Royal Society of London*, 149(9), 249–259.
- Buccheri, M. A., Angelo, D. D., and Scalese, S. (2016). Synthesis of few-layered, high-purity graphene oxide sheets from different graphite sources for biology. *2D Materials*, 3(1), 1-17
- Cao, Y., Feng, J., and Wu, P. (2010). Alkyl-functionalized graphene nanosheets with improved lipophilicity. *Carbon*. 48(5), 1683-1685.

- Carreira, L. G., Mendes, L. C., Ribeiro, M. R. G., and Sebastião, P. J. (2013). Organically-Expanded Graphite/Octadecylamine: Structural, Thermal and Relaxation Evaluation*. *Materials Science and Application*, 4, 281–286.
- Chen, J., Li, Y., Huang, L., Li, C., and Shi, G. (2015). High-yield preparation of graphene oxide from small graphite flakes via an improved Hummers method with a simple purification process. *Carbon*, 81, 826–834.
- Chen, J., Yao, B., Li, C., and Shi, G. (2013). An improved Hummers method for eco-friendly synthesis of graphene oxide. *Carbon*, 64(1), 225–229.
- Chen, P., Song, L., Liu, Y., and Fang, Y. (2007). Synthesis of silver nanoparticles by γ -ray irradiation in acetic water solution containing chitosan. *Radiation Physics and Chemistry*, 76(7), 1165–1168.
- Chen, Y., Tao, J., Ezzeddine, A., Mahfouz, R., Al-Shahrani, A., Alabedi, G., and Khashab, N. (2015). Superior Performance Nanocomposites from Uniformly Dispersed Octadecylamine Functionalized Multi-Walled Carbon Nanotubes. *Journal of Carbon Research*, 1(1), 58–76.
- Chen, Z., Dong, L., Yang, D., and Lu, H. (2013). Superhydrophobic graphene-based materials: surface construction and functional applications. *Advanced Materials*, 25(37), 5352–5359.
- Chmielewski, A. G., Haji-Saeid, M., and Ahmed, S. (2005). Progress in radiation processing of polymers. *Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms*, 236(1), 44–54.
- Choudhary, S., Mungse, H. P., and Khatri, O. P. (2012). Dispersion of alkylated graphene in organic solvents and its potential for lubrication applications. *Journal of Materials Chemistry*, 22(39), 21032–21039.
- Chua, C. K., and Pumera, M. (2014). Chemical reduction of graphene oxide: a synthetic chemistry viewpoint. *Chemical Society Reviews*, 43(1), 291–312.
- Claire Berger, Zhimin Song, and Xueben Li, X. W. (2006). Electronic Confinement and. *Science*, 312, 1191–1196.
- Compton, O. C., Dikin, D. A., Putz, K. W., Brinson, L. C., and Nguyen, S. T. (2010). Electrically conductive “alkylated” graphene paper via chemical reduction of amine-functionalized graphene oxide paper. *Advanced Materials*, 22(8), 892–896.
- Compton, O. C., and Nguyen, S. T. (2010). Graphene oxide, highly reduced graphene oxide, and graphene: Versatile building blocks for carbon-based materials. *Small*, 6(6), 711–723.
- Cota, S. S., Vasconcelos, V., Jr, M. S., Carvalho, L. L., Rezende, D. B., and Côrrea, R. F. (2007). Changes in Mechanical Properties Due To Gamma Irradiation of High-Density Polyethylene (HDPE), 24(02), 259–265.
- Crick, C. R., and Parkin, I. P. (2010). Preparation and characterisation of superhydrophobic surfaces. *Chemistry-A European Journal*, 16(12), 3568–3588.
- Dawes, K., Glover, L. C., and Vroom, D. A. (2007). The Effects of Electron Beam and gamma-Irradiation on Polymeric Materials. *Physical Properties of Polymers*

Handbook, 25, 867–887.

- De Kerf, M., Mondelaers, W., Lahorte, P., Vervaet, C., and Remon, J. P. (2001). Characterisation and disintegration properties of irradiated starch. *International Journal of Pharmaceutics*, 221(1-2), 69–76.
- Diehl, J. F. (2002). Food irradiation—past, present and future. *Radiation Physics and Chemistry* 63(3), 211–215.
- Drelich, J., and Marmur, A. (2014). Physics and applications of superhydrophobic and superhydrophilic surfaces and coatings. *Surface Innovations*, 2(4), 211–227.
- Dumée, L. F., Feng, C., He, L., Allieux, F.-M., Yi, Z., Gao, W., and Kong, L. (2014). Tuning the grade of graphene: Gamma ray irradiation of free-standing graphene oxide films in gaseous phase. *Applied Surface Science*, 322, 126–135.
- Ehlermann, D. A. E. (2002). Current situation of food irradiation in the European Union and forthcoming harmonization. *Radiation Physics and Chemistry*, 63(3), 277–279.
- El-din, H. M. N., El-Naggar, A. W. M., and Ali, F. I. (2003). Miscibility of poly(vinyl alcohol)/polyacrylamide blends before and after gamma irradiation. *Polymer International*, 52(2), 225–234.
- Fan, Z., Wang, K., Wei, T., Yan, J., Song, L., and Shao, B. (2010). An environmentally friendly and efficient route for the reduction of graphene oxide by aluminum powder. *Carbon*, 48(5), 1686–1689.
- Farkas, J. (1998). Irradiation as a method for decontaminating food: A review. *International Journal of Food Microbiology*, 44(3), 189–204.
- Gao, W. (2015). The chemistry of graphene oxide. *Graphene Oxide: Reduction Recipes, Spectroscopy, and Applications*, 39, 61–95.
- Gao, X., and Jiang, L. (2004). Biophysics: Water-repellent legs of water striders. *Nature*, 432(7013), 36–36.
- Gnanaprakasam, P., and Selvaraju, T. (2014). Green synthesis of self assembled silver nanowire decorated reduced graphene oxide for efficient nitroarene reduction. *The Royal Society of Chemistry*, 4(47), 24518–24525.
- Gonc, G., Marques, P. A. A. P., Barros-timmons, A., Bdkin, I., and Singh, M. K. (2010). Graphene oxide modified with PMMA via ATRP as a reinforcement filler. *Journal Of Materials Chemistry*, 20, 9927–9934.
- Grayfer, E. D., Makotchenko, V. G., Nazarov, A. S., Kim, S. J., and Fedorov, V. E. (2011). Graphene: chemical approaches to the synthesis and modification. *Russian Chemical Reviews*, 80(8), 751–770.
- Guerrero-Contreras, J., and Caballero-Briones, F. (2015). Graphene oxide powders with different oxidation degree, prepared by synthesis variations of the Hummers method. *Materials Chemistry and Physics*, 153, 209–220.
- Hernandez, Y., Nicolosi, V., Lotya, M., Blighe, F., Sun, Z., De, S., and Coleman, J. N. (2008). High yield production of graphene by liquid phase exfoliation of graphite.

Nature Nanotechnology, 3(9), 563–568.

- Herrera-alonso, M., Abdala, A. A., Mcallister, M. J., Aksay, I. A., and Prud, R. K. (2007). Intercalation and Stitching of Graphite Oxide with Diaminoalkanes, *American Chemical Society*, 5, 3351–3353.
- Hofmann, U., and König, E. (1937). Investigations on Graphitic. *Journal of Inorganic and General Chemistry*, 234(4), 311–336.
- Hro-an, M. (1981). Krautite, $\text{MnHAsO}_4 \cdot \text{H}_2\text{O}$ -an intracrystalline reactive mineral. *American Mineralogist*, 66, 432–435.
- Jo, C., Lee, J.-W., Cho, K.-H., Yook, H.-S., and Byun, M., W. (2002). Quality properties of sausage made with gamma irradiated natural casing from intestine of pork or lamb. *Radiation Physics and Chemistry*, 63(3), 365–367.
- K. Z. Mohd Dahlan. (2009). Radiation Processing. In *Physical Methods, Instruments and Measurements* (Vol. IV).
- Kovtyukhova, N. I., Ollivier, P. J., Martin, B. R., Mallouk, T. E., Chizhik, S. A., Buzaneva, E. V., & Gorchinskiy, A. D. (1999). Layer-by-Layer Assembly of Ultrathin Composite Films from Micron-Sized Graphite Oxide Sheets and Polycations. *Chemistry of Materials*, 11(3), 771–778.
- Kwon, Y. J., Cho, H. Y., Na, H. G., Lee, B. C., Kim, S. S., and Kim, H. W. (2014). Improvement of gas sensing behavior in reduced graphene oxides by electron-beam irradiation. *Sensors and Actuators B: Chemical*, 203, 143–149.
- Lee, K. P., Gopalan, A. I., Santhosh, P., Lee, S. H., and Nho, Y. C. (2007). Gamma radiation induced distribution of gold nanoparticles into carbon nanotube-polyaniline composite. *Composites Science and Technology*, 67(5), 811–816.
- Lee, S., Eom, S. H., Chung, J. S., and Hur, S. H. (2013). Large-scale production of high-quality reduced graphene oxide. *Chemical Engineering Journal*, 233, 297–304.
- Lehtinen, O., Tsai, I., Jalil, R., Nair, R. R., Keinonen, J., Kaiser, U., and Irina, V. (2014). Non-invasive transmission electron microscopy of vacancy defects in graphene produced by ion irradiation. *Nanoscale*, 6(12), 1–22.
- Leila Shahriary, A. A. A. (2014). Graphene Oxide Synthesized by using Modified Hummers Approach. *International Journal of Renewable Energy and Environmental Engineering*, 02(01), 58–63.
- Lerf, A., He, H., Forster, M., and Klinowski, J. (1998). Structure of Graphite Oxide Revisited. *The Journal of Physical Chemistry B*, 102(23), 4477–4482.
- Li, F., and Chen, Z. (2013). Graphene-Based Materials, *Science*, 320, 1170–1171.
- Li, J., Zeng, X., Ren, T., and van der Heide, E. (2014). The Preparation of Graphene Oxide and Its Derivatives and Their Application in Bio-Tribological Systems. *Lubricants*, 2, 137–161.
- Li, J., Zhang, B., Li, L., Ma, H., Yu, M., and Li, J. (2014). γ -ray irradiation effects on graphene oxide in an ethylenediamine aqueous solution. *Radiation Physics and Chemistry*, 94, 80–83.

- Li, W., Tang, X.-Z., Zhang, H.-B., Jiang, Z.-G., Yu, Z.-Z., Du, X.-S., and Mai, Y. W. (2011). Simultaneous surface functionalization and reduction of graphene oxide with octadecylamine for electrically conductive polystyrene composites. *Carbon*, 49(14), 4724–4730.
- Li, X., Magnuson, C. W., Venugopal, A., Tromp, R. M., Hannon, J. B., Vogel, E. M., and Ruoff, R. S. (2010). Large-Area Graphene Single Crystals Grown by Low-Pressure chemical vapour deposition of methane on copper. *Journal of the American Chemical Society*, 133(9), 2816–2819.
- Li, X., Wang, H., Robinson, J. T., Sanchez, H., Diankov, G., and Dai, H. (2009). Simultaneous Nitrogen-Doping and Reduction of Graphene Oxide. *Journal of the American Chemical Society*, 131(13), 15939–15944.
- Li, Z., Zhang, W., Luo, Y., Yang, J., and Hou, J. G. (2009). How graphene is cut upon oxidation? *Journal of the American Chemical Society*, 131(18), 6320–6331.
- Lin, Z., Liu, Y., and Wong, C. (2010). Facile fabrication of superhydrophobic octadecylamine-functionalized graphite oxide film. *Langmuir: The ACS Journal of Surfaces and Colloids*, 26(20), 16110–16114.
- Liu, G., Wang, Y., Pu, X., Jiang, Y., Cheng, L., and Jiao, Z. (2015). One-step synthesis of high conductivity silver nanoparticle-reduced graphene oxide composite films by electron beam irradiation. *Applied Surface Science*, 349, 570–575.
- Liu, T., Ma, Y., Xue, S., and Shi, J. (2012). Modifications of structure and physicochemical properties of maize starch by γ -irradiation treatments. *LWT-Food Science and Technology*, 46(1), 156–163.
- Liu, Y., Chen, S., Zhong, L., and Wu, G. (2009). Preparation of high-stable silver nanoparticle dispersion by using sodium alginate as a stabilizer under gamma radiation. *Radiation Physics and Chemistry*, 78(4), 251–255.
- Loh, K. P., Bao, Q., Eda, G., and Chhowalla, M. (2010). Graphene oxide as a chemically tunable platform for optical applications. *Nature Chemistry*, 2(12), 1015–1024.
- Loryuenyong, V., Totepvimarn, K., Eimburanaprat, P., Boonchompoo, W., and Buasri, A. (2013). Preparation and characterization of reduced graphene oxide sheets via water-based exfoliation and reduction methods. *Advances in Materials Science and Engineering*, 2013, 1–3.
- M. Choucair P. Thordason and J.A. Stide. (2011). Gram-Scale Production Of Graphene Based On Solvothermal Synthesis. *Nature Nanotechnology*, 1–3.
- Ma, W. S., Li, J., Deng, B. J., and Zhao, X. S. (2013). Preparation and characterization of long-chain alkyl silane-functionalized graphene film. *Journal of Materials Science*, 48(1), 156–161.
- Madani, M. (2011). Structure, optical and thermal decomposition characters of LDPE graft copolymers synthesized by gamma irradiation. *Current Applied Physics*, 11(1), 70–76.
- Marcano, D. C., Kosynkin, D. V., Berlin, J. M., Sinitskii, A., Sun, Z., Slesarev, A., and Tour, J. M. (2010). Improved Synthesis of Graphene Oxide. *ACS Nano*, 4(8),

4806–4814.

- Mcallister, M. J., Li, J., Adamson, D. H., Schniepp, H. C., Abdala, A. a, Liu, J., and Aksay, I. A. (2007). Expansion of Graphite. *American Cehmical Society*, 19(4), 4396–4404.
- Meng, L., and Park, S. (2014). Superhydrophobic carbon-based materials : a review of synthesis, structure, and applications, 15(2), 89–104.
- Merkoçi, A., Pumera, M., Llopis, X., Pérez, B., Del Valle, M., and Alegret, S. (2005). New materials for electrochemical sensing VI: Carbon nanotubes. *Trends in Analytical Chemistry*, 24(9), 826–838.
- Miao, M., Hawkins, S. C., Cai, J. Y., Gengenbach, T. R., Knott, R., and Huynh, C. P. (2011). Effect of gamma-irradiation on the mechanical properties of carbon nanotube yarns. *Carbon*, 49(14), 4940–4947.
- Mishra, S. K., Tripathi, S. N., Choudhary, V., and Gupta, B. D. (2014). Chemical SPR based fibre optic ammonia gas sensor utilizing nanocomposite film of PMMA/reduced graphene oxide prepared by in situ polymerization. *Sensors and Actuators B*, 199, 190–200.
- Mohamed, A. M. A., Abdullah, A. M., and Younan, N. A. (2015). Corrosion behavior of superhydrophobic surfaces: A review. *Arabian Journal of Chemistry*, 8(6), 749–765.
- Moura, E. A., Ortiz, A., Wiebeck, H., Paula, A. B., Silva, A. L., and Silva, L. G. (2004). Effects of gamma radiation on commercial food packaging films-study of changes in UV/VIS spectra. *Radiation Physics and Chemistry*, 71(1-2), 201–204.
- Muthoosamy, K., Bai, R. G., Abubakar, I. B., Sudheer, S. M., Lim, H. N., Loh, H.-S., and Manickam, S. (2015). Exceedingly biocompatible and thin-layered reduced graphene oxide nanosheets using an eco-friendly mushroom extract strategy. *International Journal of Nanomedicine*, 10(1), 1505–19.
- Nada F. Atta, Ahmad. G. and E. H. E-Ads. (2015). Graphene-A Platform for Sensor and Biosensor Applications. *World 's largest Science, Technology & Medicine Open Access book publisher*, 2, 38–84.
- Nasrollahzadeh, M., Babaei, F., Fakhri, P., and Jaleh, B. (2015). Synthesis, characterization, structural, optical properties and catalytic activity of reduced graphene oxide/copper nanocomposites. *Royal society of chemistry Advances*, 5(14), 10782–10789.
- Nguyen, D. D., Tai, N.-H., Lee, S.-B., and Kuo, W.-S. (2012). Superhydrophobic and superoleophilic properties of graphene-based sponges fabricated using a facile dip coating method. *Energy & Environmental Science*, 5(7), 7908-7912.
- Nuraje, N., Khan, W. S., Yu, L., Ceylan, M., and Asmatulu, R. (2013). Superhydrophobic Electrospun Nanofibers. *Journal of Materials Chemistry A*, 1, 1929–1946.
- Park, S., and Ruoff, R. S. (2009). Chemical methods for the production of graphenes. *Nature Nanotechnology*, 4, 45–47.

- Pei, S., and Cheng, H. M. (2012). The reduction of graphene oxide. *Carbon*, 50(9), 3210-3228.
- Prakash, A., Guner, A. R., Caporaso, F., and Foley, D. M. (2000). Effects of low-dose gamma irradiation on the shelf life and quality characteristics of cut Romaine Lettuce packaged under modified atmosphere. *Journal of Food Science*, 65, 549 – 553.
- Ragesh, P., Anand Ganesh, V., Nair, S. V., and Nair, A. S. (2014). A review on “self-cleaning and multifunctional materials.” *Journal of Materials Chemistry A*, 2, 14773–14797.
- Rosky, P. J. (2010). Exploring nanoscale hydrophobic hydration. *Faraday Discussions*, 146, 13–18; discussion 79–101, 395–501
- Ryu, S. H., and Shanmugaraj, A. M. (2014). Influence of long-chain alkylamine-modified graphene oxide on the crystallization, mechanical and electrical properties of isotactic polypropylene nanocomposites. *Chemical Engineering Journal*, 244, 552–560.
- Sanderson, R.T. (1976). Chemical bonds and bond energy. New York: Academic Press.
- Sehgal, T., and Rattan, S. (2010). Synthesis, Characterization and Swelling Characteristics of Graft Copolymerized Isotactic Polypropylene Film, 2010.
- Shanmugaraj, A. M., Yoon, J. H., Yang, W. J., and Ryu, S. H. (2013). Synthesis, characterization, and surface wettability properties of amine functionalized graphene oxide films with varying amine chain lengths. *Journal of Colloid and Interface Science*, 401, 148–154.
- Sharin, S., Rahman, I. A., Ahmad, A. F., Mohd, H. M. K., Mohamed, F., Radiman, S., and Bastamam, I. S. A. (2015). Penurunan grafin oksida kepada grafin menggunakan sinar gama. *Malaysian Journal of Analytical Sciences*, 19(6), 1223–1228.
- Sharma, T., Aggarwal, S., Kumar, S., Mittal, V. K., Kalsi, P. C., and Manchanda, V. K. (2007). Effect of gamma irradiation on the optical properties of CR-39 polymer. *Journal of Materials Science*, 42(4), 1127–1130.
- Shin, H.-J., Kim, K. K., Benayad, A., Yoon, S.-M., Park, H. K., Jung, I.-S., and Lee, Y. H. (2009). Efficient Reduction of Graphite Oxide by Sodium Borohydride and Its Effect on Electrical Conductance. *Advanced Functional Materials*, 19(12), 1987–1992.
- Seki S., Tsuneaki S., Masaaki O., Akinori S., and Daisuke. S. (2015). High-Energy Charged Particles Their Chemistry and Use as versatile Tools for Nanofabrication. *Springer Briefs in Molecular Science*, 1-9.
- Sliter, G. (1981). Radiation Effects on Organic Materials in Nuclear Plants. 3-15.
- Sobon, G., Sotor, J., Jagiello, J., Kozinski, R., Zdrojek, M., Holdynski, M., and Abramski, K. M. (2012). Graphene Oxide vs Reduced Graphene Oxide as saturable absorbers for Er-doped passively mode-locked fiber laser. *Optics Express*, 20(17), 19463-19476

- Sridhar, V., Jeon, J. H., and Oh, I. K. (2010). Synthesis of graphene nano-sheets using eco-friendly chemicals and microwave radiation. *Carbon*, 48(10), 2953-2957.
- Stankovich, S., Piner, R. D., Nguyen, S. T., and Ruoff, R. S. (2006). Synthesis and exfoliation of isocyanate-treated graphene oxide nanoplatelets. *Carbon*, 44(15), 3342-3347.
- Staudenmaier, L. (1898). A process for presentation of graphitic acid. *Journal of the American Chemical Society*, 31(2), 1481-1487.
- Sun, L., and Fugetsu, B. (2013). Mass production of graphene oxide from expanded graphite. *Materials Letters*, 109, 207-210.
- Tan, L.-L., Ong, W.-J., Chai, S.-P., and Mohamed, A. R. (2013). Reduced graphene oxide-TiO₂ nanocomposite as a promising visible-light-active photocatalyst for the conversion of carbon dioxide. *Nanoscale Research Letters*, 8(1), 465.
- Trojanowicz, M. (2006). Analytical applications of carbon nanotubes: a review. *Trends in Analytical Chemistry*, 25(5), 480-489.
- Wang, C., Lan, Y., Li, X., Yu, W., and Qian, Y. (2015). Improving the mechanical, electrical, and thermal properties of polyimide by incorporating functionalized graphene oxide. *High Performance Polymers*, 1-9.
- Wang, C., Liu, Z., Wang, S., and Zhang, Y. (2016). Preparation and properties of octadecylamine modified graphene oxide/styrene-butadiene rubber composites through an improved melt compounding method. *Journal of Applied Polymer Science*, 133(4), 1-9.
- Wang, J.-N., Zhang, Y.-L., Liu, Y., Zheng, W., Lee, L. P., and Sun, H.-B. (2015). Recent developments in superhydrophobic graphene and graphene-related materials: from preparation to potential applications. *Nanoscale*, 7(16), 7101-7114.
- Wang, S., Zhang, Y., Abidi, N., and Cabrales, L. (2009). Wettability and surface free energy of graphene films. *Langmuir*, 25(18), 11078-11081.
- Wang, S., Zhang, Y., Ma, H.-L., Zhang, Q., Xu, W., Peng, J., and Zhai, M. (2013). Ionic-liquid-assisted facile synthesis of silver nanoparticle-reduced graphene oxide hybrids by gamma irradiation. *Carbon*, 55, 245-252.
- Wang, Y., Li, Z., Wang, J., Li, J., and Lin, Y. (2011). Graphene and graphene oxide: biofunctionalization and applications in biotechnology. *Trends in Biotechnology*, 29(5), 205-212.
- Wang, Z., Dong, Y., Li, H., Zhao, Z., Wu, H. Bin, Hao, C., and Lou, X., W., D. (2014). Enhancing lithium-sulphur battery performance by strongly binding the discharge products on amino-functionalized reduced graphene oxide. *Nature Communications*, 5, 1-8.
- William S. and Hummers., R. E. O. (1958). Preparation of Graphitic Oxide. *Journal of the American Chemical Society*, 80(6), 1339-1339.
- Xue, C., Jia, S., Zhang, J., and Ma, J. (2016). Surfaces for practical applications : an overview Large-area fabrication of superhydrophobic surfaces for practical applications: an overview, *Science Technology and Advanced Materials*, 11, 1-15.

- Yang, S. Y., Lin, W. N., Huang, Y. L., Tien, H. W., Wang, J. Y., Ma, C. C. M., and Wang, Y. S. (2011). Synergetic effects of graphene platelets and carbon nanotubes on the mechanical and thermal properties of epoxy composites. *Carbon*, 49(3), 793–803.
- Zamanian, A., and Hardiman, C. (2005). Electromagnetic radiation and human health: A review of sources and effects. *EMR & Human Health*, 16, 16–26.
- Zhang, B., Li, L., Wang, Z., Xie, S., Zhang, Y., Shen, Y., and Li, J. (2012). Radiation induced reduction: an effective and clean route to synthesize functionalized graphene. *Journal of Materials Chemistry*, 22(16), 7775.
- Zhang, L., and Resasco, D. E. (2009). Single-walled carbon nanotube pillars: A superhydrophobic surface. *Langmuir*, 25(8), 4792–4798.
- Zhang, M., Gao, B., Vanegas, D. C., McLamore, E. S., Fang, J., Liu, L., and Chen, H. (2014). Simple approach for large-scale production of reduced graphene oxide films. *Chemical Engineering Journal*, 243, 340–346.
- Zhang, S.-P., and Song, H.-O. (2012). Supramolecular graphene oxide-alkylamine hybrid materials: variation of dispersibility and improvement of thermal stability. *New Journal of Chemistry*, 36(9), 1733–1738.
- Zhu, C., Guo, S., Fang, Y., and Dong, S. (2010). Reducing sugar: new functional molecules for the green synthesis of graphene nanosheets. *ACS Nano*, 4(4), 2429–2437.
- Zhu, Y., Murali, S., Cai, W., Li, X., Suk, J. W., Potts, J. R., and Ruoff, R. S. (2010). Graphene and graphene oxide: Synthesis, properties, and applications. *Advanced Materials*, 22(35), 3906–3924.