



UNIVERSITI PUTRA MALAYSIA

***PROPERTIES OF RESIN-TREATED OIL PALM WOOD HEATED USING
CONVENTIONAL OVEN AND MICROWAVE WITH DIFFERENT
DENSIFICATION PARAMETERS***

NURUL AZWA BINTI AHMAD

FH 2015 19



**PROPERTIES OF RESIN-TREATED OIL PALM WOOD HEATED USING
CONVENTIONAL OVEN AND MICROWAVE WITH DIFFERENT
DENSIFICATION PARAMETERS**

By

NURUL AZWA BINTI AHMAD

**Thesis Submitted to the School of Graduate Studies, Universiti Putra
Malaysia, in Fulfillment of the Requirements for the Degree of
Master of Science**

June 2015

COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made any material contained within the thesis for non-commercial purpose from the copyright holder. Commercial use of the material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



DEDICATION

'Praise be to Allah S.W.T. who created the heavens and the earth, and made the darkness and light' (Al-An'am 1)

All praise to Allah. I am thankful to Allah for giving me peace, good life and success through my parents and family's great prayers. I pray everyone will be blessed continuously by Him and I greatly appreciate their undivided support, patience and sacrifices while I'm pursuing my professional aim. In the name of Allah (Subhanahu Wa Taalaa). This thesis is dedicated to:

My Late Father

Almarhum Ahmad Ariffin

May Allah have mercy on his soul and grants him Jannah

My Mother

Khotijah Salleh

My Beloved Husband

Zulkhairi Mokhtar

My Uncle and My Auntie

Zuber Abdul Hamid and Rosnah Safee

My Parents In Law

Mokhtar Abdullah and Asmak Md Noor

My Daughter

Nur Qaireen Alisya Zulkhairi

Nur Qaira Aulia Zulkhairi

All my family members

And

My Supervisor, Associate Professor Dr. Edi Suhaimi Bakar who helped me throughout this journey.

May Allah S.W.T. blesses you and grants you success and Jannah.

Last Quote

“ There is always a hope for them who pray, and there is always a solution for them who work hard”



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the Degree of Master of Science

PROPERTIES OF RESIN-TREATED OIL PALM WOOD HEATED USING CONVENTIONAL OVEN AND MICROWAVE WITH DIFFERENT DENSIFICATION PARAMETERS

By

NURUL AZWA BINTI AHMAD

June 2015

Chairman : Associate Professor Edi Suhaimi Bakar, PhD
Faculty : Forestry

A study was undertaken to evaluate the physical and mechanical properties of Oil Palm Wood (OPW) treated with low molecular weight phenol formaldehyde (Lmw-PF) resin. The objectives of the study were to determine the effect of dual combination heating systems (oven heating and microwave heating) with different densification parameters on the weight gain, physical and mechanical properties of the treated OPW.

A preliminary study conducted revealed that the suitable drying by combination oven with temperature 70°C dried until 80% moisture content (MC) and microwave heating (dried until final MC 50%) used and proceeded for the different densification parameters processes. The samples were densified to 50% densification from the thickness of 40 mm to 20 mm at a temperature of 150°C for three durations namely 30 minutes, 35 minutes and 40 minutes using 85 bar pressure. Four pressing cycles were applied for each process which consists of one cycle until three cycles with different compressed thickness. The compressed samples were then tested with the formaldehyde emission test, Fourier Transform Infra-Red (FTIR) as well as physical and mechanical tests.

As for physical testing, the data analysis showed that the compression steps and durations did not give significant effect to the densities of the samples. The analysis also showed that the density profile between the different parts (surface and core) of the samples were also insignificant ($p > 0.05$). As for density gain study, the study showed that the mean percentage density gain values ranged from 94% to 116%. The compression duration and step were

found to give significant effect to the density gain of the treated OPW. The weight gain study showed that the mean values range was 12.04% and 21.41% respectively. The mean water absorption values of the compressed samples were between 8.73% and 19.73%. The compression steps and durations gave significantly different to the water absorption rate of the compressed samples at $P < 0.05$. The thickness swelling of the control samples was found to be higher than the thickness swelling of the compressed samples. Mixed results were recorded when mean values between compression durations were compared. It was hard to determine which compression duration caused a huge increment of thickness swelling since compression step may have also affected the results.

The formaldehyde emission test showed that the longer compression duration and cycles gave a lower formaldehyde emission rate of the samples. However, the formaldehyde emission mean values for the treated samples were found to be too high when compared with the required FE value (0.1 mg/L) by the American National Standard Institute (ANSI) for indoor applications.

Mechanical properties of the treated and untreated OPW were also assessed. Comparison on the mean values of the Modulus of Rupture (MOR) was made between each compression step and duration. The compression step and the compression duration gave no significant effect to the mean MOR values. On the other hand, the Modulus of Elasticity (MOE) results showed that the compression step gave no significant effect ($p > 0.05$) to the MOE of the OPW samples. Like MOR, the highest mean MOE values came from the samples impregnated with Lwm-PF compressed with compression step C: Thickness 4cm – 3.5cm – 2.5cm – 2cm (3 cycles). The compression duration did not really give significant effect in improving the elasticity of the OPW samples. The compression strength comparison showed that treated OPW performed better than untreated samples. The best mean compression strength value was 88.90N/mm² obtained from samples treated with Lwm-PF and compressed with compression step C for 40 minutes. The compression step was found to cause insignificant effect to the hardness of the OPW samples. The treated OPW samples were found superior to the control samples. The highest mean hardness value was found from the treated OPW samples compressed with compression C for 35 min.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk Ijazah Master Sains

**SIFAT-SIFAT KAYU KELAPA SAWIT DIRAWAT MELALUI GABUNGAN
PEMANASAN KONVENSIONAL OVEN DAN PEMANASAN MIKROWAVE
DENGAN PEMADATAN BERBEZA**

Oleh

NURUL AZWA BINTI AHMAD

Jun 2015

Pengerusi : Profesor Madya Edi Suhaimi Bakar, PhD
Fakulti : Perhutanan

Satu kajian telah dijalankan untuk menilai sifat-sifat fizikal dan mekanikal Kayu Kelapa Sawit (KKS) dirawat dengan berat molekul rendah fenol formaldehid resin (LMW-PF). Objektif kajian ini ialah:1) untuk menentukan kesan sistem gabungan pemanasan (pemanasan ketuhar dan pemanasan gelombang mikro) dengan parameter pemadatan yang berbeza pada berat KKS dirawat;2) untuk menentukan kesan dua sistem pemanasan gabungan (pemanasan ketuhar dan pemanasan gelombang mikro) dengan parameter pemadatan berbeza pada sifat-sifat fizikal dan mekanikal OPW yang dirawat.

Kajian awal yang dijalankan menunjukkan bahawa pengeringan sesuai melalui kombinasi ketuhar dengan suhu 70°C dikeringkan sehingga kandungan 80% kelembapan (MC) dan pemanasan gelombang mikro (kering sehingga MC akhir 50%) digunakan dan diteruskan untuk parameter proses pemadatan berbeza. Sampel melalui 50% pemadatan dari ketebalan 40mm hingga 20mm pada suhu 150°C selama tiga jangka masa iaitu 30 minit, 35 minit dan 40 minit menggunakan 85 tekanan bar. Empat kitaran menekan telah digunakan untuk setiap proses yang melibatkan kitaran satu hingga tiga dengan ketebalan pemadatan berbeza. Sampel dimampatkan kemudiannya diuji dengan ujian pelepasan formaldehid, Fourier Transform Infra-Merah (FTIR) serta ujian fizikal dan mekanikal.

Bagi ujian fizikal, analisis data menunjukkan bahawa langkah-langkah mampatan dan tempoh tidak memberi kesan yang ketara kepada ketumpatan sampel. Analisis juga menunjukkan bahawa kepadatan profil antara bahagian yang berlainan (permukaan dan teras) daripada sampel juga

tidak ketara ($p > 0.05$). Bagi ketumpatan keuntungan kajian, kajian menunjukkan bahawa nilai keuntungan ketumpatan purata peratusan adalah di antara 94% hingga 116%. Tempoh mampatan dan langkah didapati memberi kesan kepada pertambahan ketumpatan KKW yang dirawat. Penambahan berat sampel menunjukkan bahawa nilai min berkisar masing-masing adalah 12.04% dan 21.41%. Nilai penyerapan purata air sampel dimampatkan adalah di antara 8.73% dan 19.73%. Langkah-langkah mampatan dan tempoh memberi perubahan ketara berbeza dengan kadar penyerapan air sampel yang dimampatkan pada $P < 0.05$. Bengkak ketebalan sampel kawalan didapati lebih tinggi daripada bengkak ketebalan sampel yang dimampatkan. Hasil yang pelbagai telah direkodkan apabila nilai purata antara jangka mampatan berbeza. Adalah sukar untuk menentukan perimeter yang menyebabkan kenaikan besar bengkak ketebalan apabila langkah mampatan juga boleh mempengaruhi keputusan.

Ujian pelepasan formaldehid menunjukkan bahawa tempoh mampatan yang lebih lama dan kitaran menunjukkan kadar pelepasan formaldehid lebih rendah daripada sampel. Walau bagaimanapun, pelepasan formaldehid nilai purata sampel yang dirawat didapati terlalu tinggi jika dibandingkan dengan nilai FE yang diperlukan (0.1 mg / L) oleh ANSI untuk keperluan dalaman.

Sifat-sifat mekanikal KKW yang dirawat dan tidak dirawat juga telah dinilai. Perbandingan nilai purata Modulus pecah (MOR) telah dibuat antara setiap langkah mampatan dan jangka masa. Langkah mampatan dan tempoh mampatan tidak memberikan kesan yang besar kepada purata nilai MOR. Sebaliknya, Kajian Modulus Keanjalan (MOE) hasil kajian menunjukkan bahawa langkah mampatan tidak memberi sebarang kesan yang signifikan ($p > 0.05$) kepada MOE sampel KKW. Seperti MOR, nilai purata paling tinggi MOE datang dari sampel dirawat dengan LWM-PF dimampatkan dengan langkah mampatan C: Ketebalan 4cm - 3.5cm - 2.5cm - 2cm (3 kitaran). Tempoh mampatan tidak benar-benar memberi kesan yang besar dalam meningkatkan keanjalan sampel KKW. Kekuatan mampatan perbandingan menunjukkan bahawa KKW yang dirawat memberi keputusan yang lebih baik daripada sampel yang tidak dirawat. Nilai purata mampatan kekuatan yang terbaik adalah 88.90 N / mm^2 diperolehi daripada sampel dirawat dengan LWM-PF dan dimampatkan dengan langkah mampatan C selama 40 minit. Langkah mampatan didapati menyebabkan kesan yang tidak ketara kepada kekerasan sampel OPW. Sampel OPW dirawat didapati lebih tinggi daripada sampel kawalan. Yang paling tinggi nilai kekerasan min didapati dari sampel OPW dirawat dimampatkan dengan mampatan C selama 35 min.

ACKNOWLEDGEMENTS

In the name of Allah, Most Gracious, Most Merciful

All praise and glory to Almighty Allah (Subhanahu Wa Taalaa) who gave me courage and patience to carry out this work. Peace and blessing of Allah be upon last Prophet Muhammad (Peace Be upon Him).

I would like to express my unrestrained appreciation to my thesis advisor Assoc. Prof. Dr. Edi Suhaimi Bakar, for his constant help and guidance. He has been helping me out and supported me throughout the course of this work and on several other occasions. Thanks are also due to Professor Dr Zaidon Ashaari and Professor Mohd Zin Jusoh for their attention, cooperation, comments and constructive criticism. Acknowledgement is due to the Higher Ministry of Education and School of Graduates Study for their financial support towards mycourse.

I also acknowledge my fellow friends, especially Puteri Nur Khairunnisha Ismail and Toh Sook Ping for the stimulating discussion, for the sleepless night working together preparing the samples and special thanks especially to all the staff of the Faculty of Forestry who guided and helped me while doing my research, staff of Forest Research Institute Malaysia (FRIM) who helped my friend and I regarding cutting the sample and also allowed me to run the FTIR test there, staff of the Sarawak Forestry Corporation, Kuching Sarawak in Applied Forest Science and Industry Development (AFSID) department who helped me done the Density Profile test and also to all that involved directly or indirectly in my research work, thank you so much. For everyone of you, I can only pray that God will bestow upon you a blessed life

Finally, I extend my acknowledgement and heartfelt of love to my late father, mothers, auntie, uncle, parents in law, brothers and sister, who have been with me all the time to spur my spirits. Specially and most sincerely, I would like to pay my warmest tribute to my beloved husband whose great patient love and strong emotional support made my life pleasant even upon this demanding and challenging period.

I certify that a Thesis Examination Committee has met on 12 June 2015 to conduct the final examination of Nurul Azwa binti Ahmad on her thesis entitled "Properties of Resin-Treated Oil Palm Wood Heated Using Conventional Oven and Microwave with Different Densification Parameters" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Master of Science.

Members of the Thesis Examination Committee were as follows:

Rasmina binti Halis, PhD

Senior Lecturer
Faculty of Forestry
Universiti Putra Malaysia
(Chairman)

Zaidon bin Ashaari, PhD

Professor
Faculty of Forestry
Universiti Putra Malaysia
(Internal Examiner)

Othman Sulaiman, PhD

Professor
Universiti Sains Malaysia
Malaysia
(External Examiner)



ZULKARNAIN ZAINAL, PhD
Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 5 November 2015

This thesis was submitted to the Senate of the Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The member of the Supervisor Committee were as follows:

Edi Suhaimi Bakar, PhD

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Chairman)

Mohd Zin bin Jusoh, PhD

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software

Signature: _____ Date: _____

Name and Matric No.: Nurul Azwa Binti Ahmad , GS26374

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) were adhered to.

Signature: _____

Name of Chairman
of Supervisory
Committee:

Associate Professor Dr.Edi Suhaimi Bakar

Signature: _____

Name of Member
of Supervisory
Committee:

Associate Professor Dr.Mohd Zin bin Jusoh

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	iii
ACKNOWLEDGEMENTS	v
APPROVAL	vi
DECLARATION	viii
LIST OF TABLES	xii
LIST OF FIGURES	xiii
LIST OF ABBREVIATIONS	xv
CHAPTER	
1 INTRODUCTION	1
1.1 Background	1
1.2 Problem Statement	2
1.3 Objectives	3
2 LITERATURE REVIEW	4
2.1 Oil Palm Tree	4
2.2 The Availability of Oil Palm Trunk	5
2.3 The Characteristic of Oil Palm Trunk (OPT)	6
2.4 Oil Palm Trunk Drying	9
2.5 Oil Palm Trunk Treatment	10
2.6 Types of Drying	11
2.6.1 Microwave Drying	11
2.6.2 Drying by Conventional Oven	12
2.7 Compressed Wood and Processed Involved	13
2.8 Low Molecular Weight Phenol Formaldehyde	13
3 MATERIALS AND METHODS	16
3.1 Materials	16
3.1.1 Oil Palm Wood	16
3.1.2 Resin	20
3.2 Impregnation of Lmw-PF Resin	21
3.3 Preliminary Study: Re-drying Determination	22
3.4 Re-drying Variables	24
3.5 The Modified Compreg	24
3.6 Physical and Mechanical Testing of Laboratory Fabricated Oil Palm Wood	26
3.6.1 Density	26
3.6.2 Density Gain	27
3.6.3 Weight Percent Gain	27
3.6.4 Thickness Swelling and Water Absorption	27
3.6.5 Density Profile	28
3.6.6 Formaldehyde Emission Study	28
3.6.6.1 Testing Chemical	28

3.6.6.2	Test Specimens	28
3.6.6.3	Sample Retrieval	29
3.6.6.4	Formaldehyde Content Study	29
3.6.6.5	Formaldehyde Standard Solution	30
3.6.6.6	The Calibration Curve Determination	30
3.6.6.7	The Calculation of the Formaldehyde Emission Concentration	31
3.6.7	Fourier Transformed Infra-Red (FTIR)	31
3.7	Mechanical and physical testing of laboratory fabricated oil palm wood	32
3.7.1	Static Bending	32
3.7.2	Compression Strength Parallel to the Grain	33
3.7.3	Shear Strength Parallel to the Grain	34
3.7.4	Janka Hardness	35
3.8	Data Analysis Method	36
4	RESULTS AND DISCUSSIONS	37
4.1	Introduction	37
4.2	Physical Properties	38
4.2.1	Density Gain	38
4.2.2	Weight Percent Gain (WPG)	39
4.2.3	Water Absorption and Thickness Swelling	40
4.2.4	Density Profile	41
4.2.5	Evaluation of Hot Pressing Compression Step on Formaldehyde Emission	42
4.2.6	Fourier Transform Infra-Red (FTIR)	46
4.3	Mechanical Properties	47
4.3.1	Static Bending (MOE and MOR)	47
4.3.2	Compression Strength Parallel to Grain	49
4.3.3	Shear Strength and Hardness	51
5	CONCLUSION AND RECOMMENDATIONS	53
5.1	Conclusions	53
5.2	Recommendations	54
	REFERENCES	56
	APPENDICES	66
	BIODATA OF STUDENT	67
	LIST OF PUBLICATIONS	68

LIST OF TABLES

Table		Page
2.1	Areas under Oil Palm (Mature and Immature)-2014	5
3.1	The properties of Lmw-PF Resin with value	20
3.2	Seven re-drying variables applied for the samples placed under re-drying combinations group	23
3.3	Experimental Design	25
4.1	Preliminary Result on the Weight Percent Gain	37
4.2	The relationship between compression steps, compression duration and profile density of the treated OPW samples	43
4.3	The Effect of Hot-pressing Compression Step to the FE Result for the Treated OPW	45

LIST OF FIGURES

Figure		Page
2.1	Cross section of an Oil Palm Trunk	7
2.2	Structure of vascular bundle of oil palm wood at transverse section detail with the existence of parenchymatous ground tissue, vessels, fibres and phloem (photo by E. Baucker, 2005)	7
2.3	Vascular bundles with vessel of oil palm trunk (Hashimet <i>al.</i> ,2012)	8
3.1	Oil Palm Tree at UPM's Oil Palm Plantation	16
3.2	Polygon Sawing Pattern (Bakaret <i>al.</i> , 2006).	17
3.3	Process Flow of Sample Preparation	18
3.4	The Process flow for the impregnation process, re-drying process and compression process	19
3.5	Oil Palm Wood Samples after impregnation with LMW-PF	22
3.6	Picture (a), (b) and (c) show Re-Drying Parameter Used	24
3.7	Schematic Review of Densification process	26
3.8	Determination of calibration curve using different standard solution range 0.00,0.50,1.00,1.50,2.00 and 2.50 mg/l	31
3.9	Schematic Diagram of Static Bending Test	33
3.10	Schematic Diagram of Compression Strength Parallel to the Grain Test	34
3.11	Schematic Diagram of Shear Strength Parallel to Grain Test	35
3.12	Schematic Diagram of Hardness Test	36
4.1	Mean values of density gain to treat OPW under different parameters	38
4.2	Mean values of weight percent gain (WPG) to the treated OPW under different parameters	39

4.3	Mean water absorption (%) values of the OPW samples treated with different parameters	41
4.4	Mean TS (%) values of the OPW samples treated with different parameters	42
4.5	FTIR Spectra for Treated (1) Oil Palm Wood	46
4.6	FTIR Spectra for Treated (2) Oil Palm Wood	47
4.7	Mean Modulus of Rupture (MOR) values for the treated and untreated OPW	48
4.8	Modulus of Elasticity (MOE) of the treated and untreated OPW	49
4.9	Mean compression parallel to grain values to different parameters	50
4.10	Mean shear strength values of treated and untreated OPW at different parameters	51
4.11	Mean hardness values of treated and untreated OPW at different compression step.	52

LIST OF ABBREVIATIONS

ANOVA	Analysis of variance
Approx	Approximately
C	Celsius
CT	Control Treated
CU	Control Untreated
FE	Formaldehyde Emission
FRIM	Forest Research Institute Malaysia
FTIR	Fourier Transformed Infra-red
KKS	Kayu Kelapa Sawit
LSD	Least significant different
Lmw-PF	Low molecular weight phenol formaldehyde
MC	Moisture content
Min	Minutes
MOE	Modulus of elasticity
MOR	Modulus of rupture
MPOB	Malaysia Palm Oil Board
MS	Malaysia Standard
OPT	Oil palm trunk
OPW	Oil palm wood
PF	Phenol formaldehyde
RH	Relative Humidity
TS	Thickness swelling
UPM	Universiti Putra Malaysia

WA	Water absorption
WPG	Weight percent gain
cm	centimeter
mm	milimeter
M	magnetron
ha	hectares



CHAPTER 1

INTRODUCTION

1.1 Background

Demand for wood has increased in line with population growth, economy and technology development due to its versatility. It is renewable, biodegradable, non-toxic, energy-efficient and environmental-friendly (Anon, 2012). Hence, wood has become a popular raw material for housing and furniture applications due to the properties that it has.

Unfortunately, the increasing demand of natural timbers has exceeded the long-term supply of natural timbers and plantation forests. Timbers need longer time to grow and achieve suitable age, maturity and diameter before it can be harvested. As the timbers grow slowly, the loggers / suppliers need to wait for a long period of time before they could supply the timbers to the market and meet its demand. There is no way for the loggers or suppliers to supply the wood before the required time is met, unless they supply fast-growing timbers. However, normally, fast-growing timbers have inferior properties as compared to slow-growing timbers. In the view of quality demand which keeps rising, supplying fast-growing timbers is not a good option. This surely has caused decrements to the supply of the timbers

The decreasing supply of timbers is also due to several factors such as reduction of forest areas for open mining, industrial plantation and infrastructure development. Another contributor is public awareness on forest preservation that forced the loggers to reduce the exploitation of timbers from the forests. It has been discovered the decrease of natural timber supply has happened since the last two decades and it keeps happening until today.

This situation has given a massive negative impact to wood-based industry as it makes wood manufacturers difficult to find suitable raw materials for their productions (Bakar, 2008). Therefore, any alternatives must be sought, including those from agricultural residues. One of the strategic alternative materials is oil palm residues from oil palm plantations. As one of the most important commercial crops in Malaysia, huge amount of oil palm residues is left underutilized in the field and these, especially the trunk, can be used as wood alternatives (Bakar *et al.*, 2005).

The commercial value of oil palm lies mainly in the oil that can be obtained from the mesocarp of the fruit—palm oil and the kernel of the nut—palm kernel oil. The remainders are considerable amount of lignocellulosic residues such as

fronds, trunks, and empty fruit bunches. Among these residues, oil palm trunk (OPT) offers the best properties which are comparable to those of wood. The total area under oil palm cultivation is 5,392,235 hectares in Malaysia, where 4,689,321 hectares matured trees and 702,914 hectare immature trees (MPOB, 2014).

It is now needful to conduct continuous research and development to find ways to convert oil palm residues into useful and valuable material. Many researches have proven that OPT can be transformed into value-added products such as plywood, particleboard and laminated veneer lumber (Nordin *et al.* 2014; Sulaiman *et al.*, 2008). A study has shown that oil palm wood (OPW) from the outer part of the OPT can be used as solid wood (Bakar *et al.*, 2008). Based on those studies and the data of the total current replanting area, it is projected that about 12 million m³ OPW can be produced annually in Malaysia.

Wood from the outer part of the OPT, “outer lumbers”, offer the best properties. Yet, this part of lumber still has four main imperfections that need to be improved; i.e. very low in strength, bad in dimensional stability, very low in durability, and very poor in machining characteristic. Therefore, effective methods for properties enhancement need to be sought. By looking at the properties that OPT has, it was reported that impregnation using phenol formaldehyde and followed by compression to produce ‘compreg’ OPW is one of the best ways to tackle the imperfections of OPT (Bakar *et al.*, 1999). The Modification Impregnation method which consists of drying, impregnation, re-drying, and hot pressing densification has proven to be the effective method to improve the quality of OPW. Using low molecular weight Phenol formaldehyde resin (Lwm-PF), of various concentrations, impregnation times, re-dying conditions, and hot-pressing densification process, the optimum treatment condition of OPW has been disclosed (Bakar *et al.*, 2005). The dimensional stability, strength, durability and the machining characteristic of OPW can be improved significantly. These improved properties as well as good appearance make the treated OPW to be used as a material for production of non-structural components (Bakar *et al.*, 2007). Based on its physical and mechanical properties, (Bakar *et al.*, 2007) revealed that the PF-treated OPW is suitable for internal and non-structural applications.

1.2 Problem Statement

Oil Palm Tree (*Elaeis Guineensis*) has become one of the most valuable commercial crops in Malaysia where it produces significant biomass that can be converted into a value-added product (Sulaiman *et al.*, 2012). OPT, which felled after 25 years is less expensive and abundantly available where it can be difficult to degrade the trunk due to the higher density variability especially between the inner and the outer part of the trunk. By treating the

OPW with the suitable chemicals such as synthetic or natural polymers in fluid form, it can increase the properties of the OPW and can be a replace the usage of solid wood. There were few methods to increase wood density such as by compressing wood to reduce void volume, impregnating the void volume with suitable chemicals or by using a combination of impregnation and compression (Bustos *et. al.*, 2011). Treatments to the OPT with low molecular weight phenol formaldehyde (Lwm-PF) resin can increase the properties and replace the usage of solid wood, but the suitable parameter to be used is still not established yet. Based on the physical and mechanical studies of low molecular weight (600mw) phenol formaldehyde treated Oil Palm Wood (OPW) done by Bakar *et al.* (2007), it was suggested that Lwm-PF-treated OPW can be used for non-structural and indoor applications.

Unfortunately, the formaldehyde emission of the Lwm-PF-treated OPW was quite high (Amarullah, 2010) and not suitable for indoor applications. Thus, a system needs to be established to increase the properties of the OPW and to control/reduce the formaldehyde emission so that it can be a substitute of solid wood. There are numerous studies on how heat treatment affects the properties of wood (Bekhta *et. al.*, 2009, Bekhta and Niemz 2003, Boonstra and Tjerrdsma 2006, Ozcan *et. al.*, 2012). Densification of wood with heat and compression has some advantages over wood with treated by heat without compressed. (Boonstra and Blomberg 2007, Bami and Mohebbi 2011). Densification of OPW can increase the density and solve the porous structures that obtain in OPW. However, densifying the treated OPW to achieve best properties by heat and compression seen to be used for different applications. Therefore this research was carried out to obtain more information as well as finding ways on the best properties OPW and formaldehyde emission of Lwm-PF (which was dried with the most efficient drying step and fabricated with the most suitable compression step). However, the hot pressing variables using combination system still not yet optimized. Thus, it is important to know the effect of hot pressing cycles and times on the physical and mechanical properties of the samples that used a combination of oven and microwave method in the heating stage. Manufacturing parameters such as pre-treatment, pressure, temperature, and chemical properties have been found to have an important influence on the properties of compressed wood (Shahbazi *et. al.*, 2005; Cai *et. al.*, 1992; Hsu *et. al.*, 1988; Hillis 1984).

1.3 Objectives

The objective of this study is:

- To determine the effect of dual heating systems (oven heating and microwave heating) with different hot-pressing parameters on the weight percent gain, physical and mechanical properties of the treated OPW.

REFERENCES

- Abdul Hamid, S., Ahmad Shakri, M.S., Abdul Aziz, A.L., Masniza, S., Haslina M., and Wan Srihati. (2005). Properties and performance of coated oil palm stem veneers. In: Proceedings Third International Symposium on Surfacing and Finishing of Wood. IUFRO Working Party 5-04.12. Surfacing and Finishing of Wood. Kyoto International Community House, Kyoto, Japan.
- Abdul Khalil, H.P.S., Bhat, A.H., Jawaid, M., Amouzgar, P., Ridzuan, R., and Said, M.R. (2010). Agro-wastes: Mechanical and physical properties of resin impregnated oil palm trunk lumber, *Journal of Polymer Composites* 31(4), 638-644.
- Abdul Khalil, H.P.S., NurulFazita, M.R., Bhat, A.H., Jawaid, M. and NikFuad, N.A. (2009). Development and material properties of new hybrid plywood from oil palm biomass. *Materials & Design*, Vol. 31(1):417-424.
- Adachi, K., Inoue, M., Kanniyama, K., Rowell, R. M., and Kawai, S. (2004). Water removal of wet veneer by roller pressing, *J. Wood Sci.* 50, 479- 483
- Aikfei, A. (2010). Properties and decay resistance of mahang (*Macaranga sp.*) treated with phenolic resin and acrylic monomer using vacuum-pressure process, Msc. Thesis, Universiti Putra Malaysia: Serdang
- Amarullah, M., Bakar, E.S., Zaidon A., and Sahri, M.H., (2009). Formaldehyde Emission of Treated Oil Palm Wood using Low-Molecular Weight Phenol Formaldehyde Resin. Paper Presented at the 7th Pacific Regional Wood Anatomy Conference. Kuala Lumpur. 3-5 August, 2009.
- Amarullah. (2010). Formaldehyde Emission and Properties of Phenol Formaldehyde-Treated Oil Palm Wood. Thesis submission for Master of Science Universiti Putra Malaysia.
- Amouzgar, P., Abdul Khalil, H.P.S., Babak Salamatinia, Ahmad Zuhairi Abdullah, A.M., Issam. (2010). Optimization of bioresource material from oil palm trunk core drying using microwave radiation; a response surface methodology application. *Bioresource Technology* 101. Pp. 8396-8401.
- Anis M, H, Kamarudin, W.H., WanHasamudin (2007). Current status of oil palm biomass supply. In: Proceedings of the 7th national seminar on the utilization of oil palm tree. Malaysia: Oil Palm Tree Utilization Committee (OPTUC); 2007.

Anon,(2012).Source:

- (i) http://www.btimes.com.my/Current_News/BTIMES/articles/NKEApalm/Article/ – [Last Accessed – 23 Mar2012];
- (ii) <http://www.frost.com/prod/servlet/presentation.pag?Src=RSS&docid=235377871> – [Last Accessed – 23 Mar2012];
- (iii) Nelson timber plant (2012 startup) <http://www.nzwood.co.nz/industrynews/2011/08/17/new-technology-for-nelson-timber-plant-for-2012-startup/> - [Last Accessed – 23 Mar2012];

Antti, A.L. and Perre P.A., Microwave applicator for on line wood drying: Temperature and moisture distribution in wood. *Wood Science and Technology* 1999, 33, 123-138.

Bakar, E.S., Rachman, O., Hermawan, D., Karlinasari, L., and Rosdiana, N.. (1998). Utilization of oil palm trees as building and furniture materials (I): Physical and chemical properties, and durability of oil palm wood. *Journal Teknologi Hasil Hutan*, 11(1).

Bakar, E.S., Rachman, O., and Rusdiana, W.N.. (1998). Utilization of Oil Palm Trees as Building and Furniture Material: Basic Properties of Oil Palm Wood (in Indonesia). *Indonesian Journal of Forest Products and Technology*, 1: 1-12.

Bakar, E.S., Rachman, O., Darmawan, W., and Hidayat, I. (1999). Utilization of oil palm trees as building and furniture material (II): Mechanical properties of oil palm wood. *Journal Teknologi Hasil Hutan*, 12(1): 10-20.

Bakar, E.S., Rachman, Darmawan, W. and Hidayat, I. (1999). Utilization of Oil Palm Trunk (*Elaeis guineensis* Jacq) as construction materials and furniture (II): Mechanical properties of oil palm wood, *Journal of Forest Products Technology*, Vol. XII (1):10-20.

Bakar, E.S. (2000). Utilization of Oil Palm Trunk as Housing and Furniture Material. Project Report. Faculty of Forestry, Universiti Putra Malaysia.

Bakar, E.S. and Y.S. Hadi. (2001). Quality Improvement of Oil Palm Wood: Impregnated with Phenolic Resin. *Journal Teknologi Hasil Hutan*, 14(2): 24-31.

Bakar, E.S., Paridah, M.T., and Sahri, M.H. (2005). Properties Enhancement of Oil Palm wood through the Compreg Method. *Journal of Wood Science and Technology*, 2: 91-92.

Bakar, E.S., Febrianto, F., Wahyudi, I. and Zaidon, A. (2006). Polygon sawing: An optimum sawing pattern for oil palm stems. *Journal of Biological Science*, 6(4): 744-749.

- Bakar. E.S., Paridah, M.T., Febrianto, F., Sahri, M.H., and W.C. Tang. (2007). Properties Enhancement of Oil Palm Wood Through Modified Compreg Method. A Comprehensive Solution to Oil Palm Wood's Properties Flaws. In Proceeding of the 7th National Conference on Oil Palm Tree Utilization: Strategizing for Commercial Exploitation. Held in Sunway Resort Hotel & Spa, Petaling Jaya, Nov.13-15, 2007.
- Bakar, E.S., Sahri. M.H., and P.S. H'ng. (2008). Anatomical Characteristics and Utilization of Oil Palm Wood. In: The Formation of Wood in Tropical Forest Trees: A Challenge from the Perspective of Functional Wood Anatomy, Editor: Tadashi Nobuchi and MohdHamamiSahri. UPM Press, Selangor: Chapter 12: p. 161-180. ISBN 978-967-5026-12-6.
- Bakar, E.S., Sahri, M.H., and P.S. H'ng. (2008). Anatomical Characteristics and Utilization of Oil Palm Wood, ed. T. Nobuchiet *al.*, p. 221-230. Serdang: Universiti Putra Malaysia Press.
- Bami L.K. and Mohebbay B. (2011). Bio resistance of poplar wood compressed by combined hydro-thermo-mechanical wood modification (CHTM) : soft and brown rot. *International Biodeterioration and Biodegradation* 65:866-870.
- Basiron, Y. (2007). "The palm oil production through sustainable plantations," *Eur.J. Lipid Sci. Technol.*109(4), 289-295.
- Bekhta, P. A., and Marutzky, R. (2007). Reduction of glue consumption in the plywood production by using previously compressed veneer. *HolzRohWerkst* 65(1), 87-88
- Bekhta, P., Hiziroglu, S., and Shelpelyuk, O. (2009). Properties of plywood manufactured from compressed veneer as building material. *Material and Design* 30:947-953.
- Bekhta, P., and Niemz P. (2003). Effect of high temperature on the change in color, dimension stability and mechanical properties of spruce wood. *Holzforchung* 57: 539-546.
- Boonstra M.J. and Blomberg, J. (2007). Semi-isostatic densification of heat-treated radiate pine. *Wood Science and Technology* 41:607-617.
- Boonstra, M.J., and Tjeerdsma, B. (2006). Chemical analysis of heat treatment softwoods. *HolzalsRoh- und Werkstoff*64: 204-211.
- Bootle, K.R. (1983). *Wood in Australia Types, Properties and Uses*, McGraw-Hill, Sydney, Australia, 1983.

- Boswell, J.T., Hunt, M.L. (1991). A survey of air emission from reconstituted wood plants. In Proc. Of 25th Inter. Particleboard/ Composite Material Symp.; Maloney, T.M., Ed.; Washington State Univ.: Pullum, WA, 1991; 125-146.
- British Standard. BS 373: 1957. Methods of Testing Small Clear Specimens of Timber. United Kingdom: British Standards Institution Group.
- Bustos, C.A., Escobar, W.G, Cloutier, A., Fang, C-H., and Carrasco, P.V. (2011). Densification of wood veneer combined with oil-heat treatment. Part 3: Cell wall mechanical properties determined by nanoindentation, *BioResources* 7(2), 1525-1532.
- Cai, L., Han, S., and W. Deng, (1992). Chemical and physical changes of steam treated wood chip, *J. Northeast For. Univ.* 4(1), 48-52
- Choowang, R., and Hiziroglu, S. (2015). Properties of Thermally-compressed Oil Palm Trunk (*Elaeis guineensis*). *Journal of Tropical Forest Science* 27(1):39-46.
- Dungani, R., Jawaid, M., Abdul Khalil, H. P. S., Jasni., Aprilia, S., Hakeem, K. R., Hartati, S., and Islam, M. N. (2013). "A review on quality enhancement of oil palm trunk waste by resin impregnation: Future materials," *BioRes.* 8(2), 3136-3156.
- Engler, N. (2009). The Way Wood Works. *Woodworking magazine.* p. 1-4.
- Fairhurst, T.H., Mutert, E. (1999). Introduction to Oil Palm Production. *BetterCrops International*, 13: 1-6.
- Forest Products Laboratory. (1999). Wood Handbook – Wood as an engineering material. Gen. Tech. Rep. FPL-GTR-113, Madison, WI: US. Department of Agriculture, Forest Service, Forest Products Laboratory, 463p.
- Furuno, T., Y., Imamura, and H. Kajita, (2004). The modification of wood by treatment with low molecular weight phenol-formaldehyde resin: A properties enhancement with neutralized phenolic-resin and resin penetration into wood cell walls, *Journal Wood Sci. Technol.* 37(5) 349- 361.
- Hansson, L., A.L., Antti. (2003). The effect of microwave drying on Norway Spruce wood strength: a comparison with conventional drying. *Journal of Materials Processing Technology.* 141. P 41-50.
- Hartley, C.W.S. (1984). The Oil Palm. Third Edition, Longmans, Green and Co.Ltd. London. p. 45-51.
- Hartley, C.W.S. (1988). The Oil Palm. Longman Scientific and Technical, Third Edition. p. 19-23.

- Hashim, R., Wan Nadhari, W.N.A., Sulaiman, O., Sato, M., Hiziroglu, S., Kawamura, F., Sugimoto, T., Tay, G.S., and Tanaka, R. (2012). "Properties of binderless particleboard panels manufactured from oil palm biomass," *BioResources* 7(1), 1352-1365
- Haslett, A. N. (1990). Suitability of oil palm trunk for timber uses. *Journal of Tropical Forest Science*, 2(3):43-51
- Hill, C.A.S. (2006). Wood Modification: Chemical, Thermal and other Processes. In: *Modifying the Properties of Wood*, Hill, C.A.S. (Ed.). John Wiley and Sons Ltd., London, ISBN: 978-0-470-02172-9, p:19-97
- Ho, K.S. & L.T. Hong, (1991). Processing, seasoning and protection of oil palm lumber. Proceedings of the National Symposium on oil palm by-products for Agro-based Industries, Kuala Lumpur. PORIM Bulletin No. 11: 43-51
- Hon, D.N.S. (2003). Analysis of Adhesives, In Handbook of Adhesive Technology (Eds. Pizzi, A., and Mittal, K.L.). Marcel Dekker Inc. New York. 293-324 pp
- Hoong, Y.B., Paridah, M.T., Loh, Y.F., Koh, M.P., Luqman, C.A., and Zaidon, A. (2010). *Acacia mangium* tannin as formaldehyde scavenger for low molecular weight phenol formaldehyde resin in bonding tropical plywood. *Journal of Adhesion Technology* 24:1563-1664.
- Hsu, W.E., Schwald, W., Schwald, J., and Shield, J.A. (1988). Chemical and physical changes required for producing dimensionally stable wood-based composites, *Wood Sci. Technol.* 22, 281-289
- Kajita, H. and Imamura, Y. (1991). *Wood Science Technology*. 26, pp. 63-70
- Kamaruddin, H., Mohamad, H., Ariffin, D., and Jalani, S. (1997). An Estimated Availability of Oil Palm Biomass in Malaysia. *PORIM Occasional Paper No 37*. PORIM and Ministry of Primary Industries, Malaysia. Selangor, pp. 100
- Khoo, K.C., W. Killmann, S.C. Lim, and Mansor. (1991). "Characteristics of the oil palm stem," *Research Pamphlet No. 107: Oil Palm Stem Utilisation*, Kuala Lumpur Malaysia, FRIM, 19-48.
- Killmann, W. and S.C. Lim. (1985). Anatomy and Properties of Oil Palm Stem. In *Proceedings of the National Symposium on Oil Palm By-Products for Agro-based Industries*, ed. S.C. Lim et al., p. 18-42. Kuala Lumpur: Palm Oil Research Institute Malaysia.
- Killmann, W. (1988). Oil palm stem densification using ammonia treatment: A preliminary study. *Journal of Tropical Forest Science*, 1(1):1-10, July 1988.

- Kultikova, E.V. (1999). " Structure and properties relationship of densified wood," MSc dissertation, Virginia Polytechnic Inst. and State Univ., Blacksburg, VA(USA).
- Leskovsek, U., and S. Medved. (2011). Heat and moisture transfer in fibrous thermal insulation with tight boundaries and a dynamical boundary temperature, *Int. J. Heat Mass Transfer* 54 (19-20), 4333-4340.
- Lim, S.C. and K.S. Gan.(2005). Characteristic and Utilization of Oil Palm Stem. FRIM Bulletin no.35.
- Malaysian Standard. Ms 1787: PART 15: 2005: Determination of Formaldehyde Emission by Desiccator Method. Department of Standards Malaysia.
- Mohd Nasir Amiruddin; Ayat K Ab. Rahman and Faizah, S.(2003). Market Potential and Challenges for the Malaysian Palm Oil Industry in Facing Competition from Other Vegetable Oils".
- Mohd. Zin, J., MohdHanafi, M.T., Zaidon, A. & MohdHamani, S. (1991). Shrinkage properties of palm wood. In M.P. Koh, M.Y. Mohd. Nor, K.C. Khoo, & M.N. Nurulhuda (Eds.). Seminar Proceeding: Oil Palm Trunk and Other Palmwood Utilization. Oil Palm Fiber Utilisation Committee Malaysia, Kuala Lumpur.19-26.
- MPOB. (2014). Statistic of Palnted Area of Oil Palm Wood in Malaysia, http://econ.mpob.gov.my/economy/industry2/profile_menu.htm accessed on 17/07/2015.
- MPOB. (2007). Statistic of Planted Area of Oil Palm Wood in Malaysia, <http://econ.mpob.gov.my/economy/annual/stat2007/Area1.htm> accessed on 20/8/2008.
- Malaysian Palm Oil Board Statistics, (2011). (<http://www.mpob.gov.my>).
- Malaysian Palm Oil Board. (2014). Oil Palm and The Environment. (<http://www.mpob.gov.my>).
- Markessini, C., ,E.Athanassiadou., and, S. Tsiantzi, (2010). Producing panels with formaldehyde emission at wood level. *7th European Wood-based Panel Symposium* 13-15 October 2010, Hannover, Germany.
- Nadhari, W.N.A.W., R.Hashim, O.Sulaiman, N. Jumhuri.,(2014). Drying kinetics of oil palm trunk waste in control atmosphere and open air convection drying. *International Journal of Heat and Mass Transfer* 68:14-20
- NorainiRazali. (2009). Synthesis and characterization of mesoporous base catalyst for transesterification of palm oil. Thesis submission for Master Science, UniversitiSains Malaysia.

- Nordin, K., M.A.Jamaludin, M. Ahmad, Samsi, H.W., Salleh, A.H., and Z.Jallaludin, (2014). Minimizing the environmental burden of oil palm trunk residues through the development of laminated veneer lumber products. *Management Environment Quality* 15(5), 484-490
- Nurlzreen, F.A., A. Zaidon, M.A. Rabi'atolAdawiah, E.S. Bakar, M.T. Paridah, S. MohdHamami, and U.M.K. Anwar. (2011). Enhancing the Properties of Low Density
- Hardwood *Dyercostulatathrough* Impregnation with Phenolic Resin Admixed with Formaldehyde Scavenger. *Journal of Applied Science* 11(20), 3474-3481.
- Nuess, M., and Price, S. (2007). Indoor Air Pollutant: (<http://www.healthgoods.com>). Accessed on 3 May 2014.
- Ozcan, S., Ozcifci, A., Hiziroglu, S., and Toker, H., (2012). Effect of heat treatment and surface roughness on bonding strength. *Construction and Building Materials* 33:7-13.
- Pizzi, A. (1994). Phenolic Resin Adhesives, In Handbook of Adhesive Technology (Eds. Pizzi, A., and Mittal, K.L.). Marcel Dekker Inc. New York. Pp 329-346.
- Poljansek, I. and Krajnc, M. (2005). Characterization of Phenol-Formaldehyde Prepolymer Resins by Line FT-IR Spectroscopy, *ActaChimSlov*, pp 238-244.
- Rahman, M. B. A., Z. I. Ishak, D. K. Abdullah, A. M. A. Aziz, M. I. Basri, and A.B. Salleh, J. Oil Palm Res. 24 (2013)1267.
- Rabi'atolAdawiah, M.A., A. Zaidon, F.A. Nurlzreen, E.S. Bakar, S. MohdHamami, and M.T. Paridah. (2012). Addition of Urea as formaldehyde scavenger for low molecular weight phenol formaldehyde treated compreg wood. *Journal of Tropical Forest Science* 24(3): 265- 274.
- Ratanawilai, T., ChumthongT., and KirdkongS..(2006).An investigation on the mechanical properties of trunk of palm oil trees for the furniture industry. *Journal of Oil Palm Research*, Specialissue:114–121
- Razak, W., W.S. Hashim, M. Aminuddin, S. Othman, and S. Rafidah, (2008). Properties of Laminated Veneer lumber from Oil Palm Trunks. *Journal of Plant Science*, 3, 255-259.
- Roffael, E., (1993). Formaldehyde Release from Particle Board and Other Wood Based Panels. FRIM, Kepong. KualaLumpur.

- Rosen H.N. (1987). Drying of wood and wood products, in: A.S. Mujumdar (Ed.), *Handbook of Industrial Drying*, Marcel Dekker, New York, USA, 1987.
- Rowell, R. M. (2012). Chemical modification of wood to produce stable and durable composites, *Cellulose Chem. Technol.*, 46(7-8), 443-448.
- Rowell, R. M., Ibach, R. E., McSweeney, J., and Nilsson, T. (2009) *Procs. 4th European Conference on Wood Modification*, Stockholm, Sweden, p. 489.
- Rowell, R.M. (2005). Ch.4:Chemical modification of wood, *Handbook of Wood Chemistry, Wood Composites*, R.M. Rowell (ed.), CRC Press, Boca Raton, USA, 381-420.
- Ryu, J.Y., Imamura, Y., Takahashi, M., and Kajita, H. (1993). Effect of Molecular Weight and Some Other Properties of Resin on the Biological Resistance of Phenolic Resin Treated Wood. *MokuzaiGakkaishi*, 39. Pp486-492.
- Ryu, J.Y., Takahashi, M., Imamura, Y., Sato, T. (1991). Biologival resistance of phenol-resin treated wood, *MokuzaiGakkaishi*37(9), 852-858.
- Shahbazi, A., Li, Y., and Mims, M.R. (2005). Application of sequential aqueous steam treatments to the fractionation of softwood, *Appl. Biochem. Biotech.* 121-124, 973-988.
- Schiffman, R.F. (1987). Microwave and Dielectric Dying, in: A.S. Mujumdar (Ed.), *Handbook of Industrial Drying*, Marcel Dekker, New York, USA, 1987.
- Seborg, R.M., Millett, M.A., and Stamm, A.J. (1962). "Heat-stabilized compressed wood (staypack)," Forest Product Laboratory, United States Department of Agriculture, Forest Service, Report No. 1580 (revised).
- Siburian, R.A.F., Sianturi, H.L., and Ahmad, F. (2005). Impregnation of palm oil trunk with polyblene polypropylene/rubber natural and acrilate acid, *Journal Nature Indonesia* 8, 48-53.
- Sitti Fatimah, M.R., Othman, S., Rokiah H., Takamitsu, A., Akhihiko, K., Hisashi, A., Yoshinori, M., and Yutaka, M.. (2009). Characterization of parenchyma and vascular bundle of oil palm trunk as function of storage time. *Lignocellulose* 1(1),33-34.
- Stamm, A.J., Seborg, R.M. (1939). Resin Treated Plywood, *Industrial and Engineering Chemistry*, 31, pp. 897-902.

- Stamm, A.J., and Seborg, R.M. (1941). "Resin treated, laminated, compressed wood," *Trans. Am. Inst. Chem. Eng.* 37,385-397.
- Stephen, R.S., Kutscha, N.P. (1987). Effect of Resin Molecular Weight on Bonding of Flakeboard, Wood, and Fiber Science, 19, pp. 353-356.
- Sulaiman, O., Nurjannah S., Noor Afeefah, N., Rokiah, H., Mazlan, I., and Sato, M. (2012). "The potential of Oil Palm Trunk Biomass as an alternative source for compressed wood," *Bioresources* 7(2), 2688-2706.
- Szymonaa, K., Cichya, A., Borysiuka, P., San, P.H., and Maminska, M. (2011). Selected Physical Properties of Furfurylated oil palm trunk (*Elaeisguineensis* Jacq.), *Annals of Warsaw University of Life Sciences- SGGW Forestry and Wood Technology* 76, 129-133.
- Thomas, P. (2000). *Trees: Their Natural History*. Cambridge: Cambridge University Press.
- Torgovnikov, G. (1993). *Dielectric Properties of Wood and Wood-based materials*. Springer, Berlin.
- Turner, W. (1994). A Study of the Power Density Distribution Generated During the Combined Microwave and Convection Drying of Softwood, in: *Proceeding of the 9th International Drying Symposium*, Gold Coast, Australia, August, 1994.
- UIHaqBhat, I., Abdullah, C.K., Abdul Khalil, H.P.S., Hakimi Ibrahim, M., and NurulFazita, M.R. (2010). Properties enhancement of resin impregnated agro waste: Oil palm trunk lumber, *Journal of Reinforced Plastics and Composites* 29(22), 3301-3308.
- Unsal, O., Candan, Z., Buyuksari, U., Korkut, S., Chang, Y.S and Yeo, H. (2011). Effect of Thermal Compression Treatment On the Surface Hardness, Vertical Density Profile and Thickness Swelling of Eucalyptus Wood Boards by Hot Presing, *MokchaeKonghak*, Vol 39(2):148-155.
- Unsal, O., Kartal, S.N., Cendan, Z., Avango, R.A., Clausen, C.A., and Green, F. (2009). Decay and termite resistance, water absorption and swelling of thermally compressed wood panels, *Int. Biodeter. Biodegr.* 63, 548-552.
- Wang, W., Gardner, D.J. (1999). Investigation of volatile organic compound press emissions during particleboard production: Part 1. UF-bound southern pine. *Forest Prod. J.*, 49 (3), 65-72

- Winandy, E.J. and Rowell, R.M. (2005). *Chemistry of Wood Strength, Handbook of Wood Chemistry and Wood Composites*, Taylor and Francis
- Wong, T.S., Paridah, M.T., Zaidon, A., Edi Suhaimi, B., and Azmi, I. (2008). Effects of presteaming and compressing pressure on the dimensional stability of densified wood, In: *Proc. Of National Conference on Forest Product*. Kuala Lumpur, Malaysia pp 183-189.
- Xiaodong, W., Alexander, S., Mohammad, M., and Hu, L.J. (2005). Evaluation of density distribution in wood-based panels using X-Ray scanning, 14th International Symposium on Nondestructive Testing of Wood, May 2005, University of Applied Sciences, Germany, Eberswalde. (<http://www.ndt.net/article/v11n04/wang/wang.htm>). Accessed on 2nd May 2014
- Yano, H., Hirose, A., Collings, P.J., and Yazaki, Y. (2001). Effects of removal matrix substances as a pretreatment in the production of high strength resin-impregnated wood based materials. *Journal of Material Science Letters* 20:1125-1126
- Yap, T.N., L.T., Gan, O.K., Chew, C.Y., Ho, H. Adinan, and E.C. Chua. (1991). Extraction and processing of palm hearts. In *proceedings of Oil Palm Trunk and Other Palm Wood Utilization*, ed. L.T. Gan, p. 20-31. Kuala Lumpur: Ministry of Primary Industries.
- Yoshihara, H., and Tsunematsu, S. (2007). Bending and shear properties of compressed Sitka spruce. *Wood Science and Technology* 41:117-131
- Zaidon, A., Edi Suhaimi, B., and Paridah, M.D.T. (2010). Compreg laminates from low density tropical hardwoods. *Proceedings of the International Convention of Society of Wood Science and Technology and United Nations Economic Commission for Europe-Timber Committee*, October 11-14, 2010, Geneva, Switzerland.
- Zhao, H., I. Turner, and G. Torgovnikov. (1998). An Experimental and Numerical Investigation of the microwave Heating of Wood, *J. Microwave Power and Electromagnetron Energy*, 33(2)(1998):121-133.