



UNIVERSITI PUTRA MALAYSIA

***ANALYTICAL MODEL FOR PARTIALLY PRESTRESSED CONCRETE
BEAM-COLUMN ELEMENTS***

MILAD HAFEZOLGHORANI ESFAHANI

FK 2017 45



**ANALYTICAL MODEL FOR PARTIALLY PRESTRESSED CONCRETE
BEAM-COLUMN ELEMENTS**

By

MILAD HAFEZOLGHORANI ESFAHANI

**Thesis Submitted to the School of Graduate Studies, Universiti Putra
Malaysia, in Fulfillment of the Requirements for Degree of
Doctor of Philosophy**

February 2017

All materials contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



DEDICATION

I dedicate this thesis to my wonderful parents, Dr. Mohammad Hafezolghorani Esfahani and Dr. Mehrnoush Foroudastan for their love and supports. Without their support and faith in me, I would not be the person I am today.



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the Degree of Doctor of Philosophy

ANALYTICAL MODEL FOR PARTIALLY PRESTRESSED CONCRETE BEAM-COLUMN ELEMENTS

By

MILAD HAFEZOLGHORANI ESFAHANI

February 2017

Chairman : Associate Professor Farzad Hejazi, PhD
Faculty : Engineering

Nowadays, the demand for buildings and bridges with long span and light weight capable of withstanding any type of dynamic loading is increasing. The application of partially prestressing technique to reduce the yielding and damages in concrete members and structures offers an alternative solution to conventional reinforced concrete (RC) or fully prestressed concrete (FPC) approaches. Although partially prestressed concrete (PPC) has been widely used as a simple and economical construction technique for structures with medium to large span, there are no proper analytical and numerical models and detailed building code provisions for PPC elements. Besides, based on an extensive review of the literature, there is less information available about the possibility of identifying the damage in partially prestressed concrete beams and frame structures during earthquake excitation. Hence, in this study a new analytical model for PPC frame elements subjected to static and dynamic loads is developed. For this purpose, constitutive law and mathematical model for the three dimensional PPC beam-column element are formulated and a special finite element algorithm is developed. In order to develop three-dimensional nonlinear finite element formulations, the PPC frame element is represented by two nodes and an elastic element in between to reflect the elastic behavior of the member and two plastic hinges at each end of the member to reflect the inelastic behavior of the member. The elastic stiffness matrix of a three-dimensional PPC beam-column element with two nodes was developed during the present study; meanwhile, the elasto-plastic stiffness matrix of the three-dimensional PPC frame element having plastic hinges at both ends was derived using plasticity theory. Therefore, in order to detect the damages and determine the location of plastic hinges during dynamic loading in element, formulation for plasticity and yielding surface mechanism of PPC frame element is derived. A third degree polynomial using regression analysis was fitted to the results obtained from PPC section analysis to represent the mathematical model of the yield surface for each section. The developed analytical model and plasticity theory were codified and implemented in a special finite element program named ARCS3D in order to perform inelastic static and dynamic analysis for PPC structures.

In order to validate the developed analytical model, plasticity formulation and the developed FE computer program code, five conventional RC and PPC beams and frames were fabricated and tested experimentally for cyclic load using dynamic actuator. The results showed a good correlation between the numerical analysis and the experimental tests. Several parametric studies were also undertaken for low-rise, medium-rise, and high-rise partially prestressed concrete framed buildings subjected to 2D nonlinear pushover and time history analysis. Furthermore, nonlinear pushover analysis was conducted on three-dimensional four-story RC and PPC buildings. Also, 3D nonlinear dynamic time history analysis was performed on the four-story RC and PPC frame buildings subjected to multi-directional EL-Centro earthquake accelerations. The functionality and effects of PPC buildings were then interpreted from different perspectives, such as variation of displacements, peak accelerations and plastic hinge formation. The results of numerical and experimental models indicated that application of the partially prestressed concrete members in structural systems effectively increased the strength and safety of the structure during dynamic loading. Also, the developed FEM program was able to successfully identify damage occurrence in PPC structural element during applied dynamic loads. To be more specific, a comparison between results shown that the ultimate capacity, degree of flexibility and energy dissipation capacity of the PPC beam specimens improved up to 70 %, 93 % and 300 % compared to the conventional RC beam specimen. From the experimental PPC frame results, the lateral load capacity and stiffness improved up to 34 % and 17 % compared to the RC frame. Also, no crack happened in the beam of the PPC frame under super imposed dead load. Furthermore, based on the parametric studies, application of PPC members in multi-storey concrete buildings subjected to seismic loads indicated a noticeable delay in the failure process, however, conventional RC buildings collapsed at the first stage of analysis. Ultimately, this study facilitates the analysis and design procedures of the multi-storey PPC and RC buildings as well as bridges in an efficient computation time which is more economical compared to normal design methods.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk Ijazah Doktor Falsafah

MODEL ANALATIKA BAGI UNSUR-UNSUR TIANG-RASUK KONKRIT SEPARA PRATEGASAN

Oleh

MILAD HAFEZOLGHORANI ESFAHANI

Februari 2017

Pengerusi : Profesor Madya Farzad Hejazi, PhD
Fakulti : Kejuruteraan

Pada masa kini, permintaan bagi bangunan dan jambatan berentang panjang serta ringan dan mampu menahan apa jua jenis pembebanan dinamik, semakin meningkat. Penggunaan teknik prategasan separa bagi mengurangkan alahan konkrit dan kegagalan dalaman anggota konkrit dan struktur, menawarkan penyelesaian alternatif kepada teknik konvensional konkrit bertetulang (RC) atau konkrit prategasan sepenuhnya (FPC). Walaupun konkrit prategasan separa (PPC) telah digunakan secara meluas sebagai teknik pembinaan yang menjimatkan serta mudah bagi pembinaan struktur dengan rasuk rentang sederhana, juga besar, namun tiada model berangka yang sesuai dan tiada analisis yang betul digunakan dan tiada peruntukan kod untuk unsur-unsur bangunan terperinci PPC. Selain itu, berdasarkan kajian literature yang meluas, terdapat maklumat yang kurang yang boleh didapati mengenai kemungkinan mengenal pasti kerosakan di sebahagian prategasan rasuk konkrit dan kerangka struktur semasa pengujian gempa bumi. Oleh itu, dalam kajian ini model analisis baru untuk unsur-unsur rangka PPC tertakluk kepada beban statik dan dinamik dibangunkan. Untuk tujuan ini, undang-undang jujuk dan model matematik untuk tiga PPC dimensi unsur rasuk-tiang digubal dan algoritma unsur terhingga khas dibangunkan. Dalam usaha untuk membangunkan tiga dimensi linear rumusan unsur terhingga, elemen rangka PPC diwakili oleh dua nod dan elemen elastik di antara untuk menggambarkan kelakuan elastik anggota dan dua engsel plastik pada setiap hujung anggota untuk mencerminkan tingkah laku yang tidak boleh berubah ahli. Matriks kekukuhan anjal daripada dimensi unsur PPC rasuk-tiang tiga dengan dua nod telah dibangunkan semasa kajian ini; sementara itu, matriks kekukuhan elasto-plastik unsur rangka PPC tiga dimensi mempunyai plastik bergantung pada kedua-dua hujung diperolehi dengan menggunakan teori keplastikan. Oleh itu, untuk mengesan kerosakan dan menentukan lokasi engsel plastik semasa pembebanan dinamik dalam elemen, formulasi untuk keplastikan dan mekanisme permukaan alah elemen rangka PPC dibangunkan. Persamaan regresi menggunakan polinomial darjah ketiga telah dipadankan untuk keputusan analisa yang diperolehi daripada bahagian analisis PPC, untuk mewakili model matematik permukaan hasil untuk setiap bahagian. Analisis model dan teori keplastikan yang dibangunkan telah dimaktub dan dilaksanakan dalam program unsur terhingga khusus yang dinamakan ARCS3D untuk melaksanakan analisis

statik tak elastik dan analisa dinamik untuk struktur PPC. Dalam usaha untuk mengesahkan rumusan model analisis, teori keplastikan yang dibangunkan dan kod program komputer FE, lima rasuk dan kerangka konvensional RC dan PPC telah direka dan diuji secara eksperimen untuk kenaaan beban kitaran menggunakan penggerak dinamik. Hasil kajian menunjukkan korelasi yang baik antara analisis berangka dan ujian eksperimen. Beberapa kajian parametrik juga telah diambil untuk kerangka bangunan konkrit separa prategasan, bertingkat rendah, bertingkat sederhana, dan bertingkat tinggi tertakluk kepada beban mahu-mengalah 2D tak linear dan analisis sejarah masa. Tambahan lagi, analisis mahu-mengalah 2D tak linear telah dijalankan ke atas bangunan empat tingkat, tiga dimensi, RC dan PPC. Juga, analisis dinamik sejarah masa, 3D linear, telah dilakukan ke atas empat tingkat kerangka bangunan RC dan PPC tertakluk kepada daya gempa bumi pecutan pelbagai hala EL-Centro. Fungsi dan kesan bangunan PPC kemudiannya ditafsirkan dari perspektif yang berbeza, seperti perubahan anjakan, pecutan puncak dan pembentukan engsel plastik. Keputusan model berangka dan eksperimen menunjukkan bahawa penyertaan daripada anggota konkrit prategasan separa dalam sistem struktur berkesan meningkatkan kekuatan dan keselamatan struktur semasa pengenaan beban dinamik. Tambahan lagi, program FEM yang dibangunkan berjaya mengenalpasti kejadian kerosakan di elemen struktur PPC semasa beban dinamik digunakan. Untuk lebih spesifik, perbandingan antara keputusan-keputusan menunjukkan bahawa keupayaan muktamad, tahap fleksibiliti dan kapasiti tenaga pelepas daripada spesimen rasuk PPC bertambah baik sehingga 70%, 93% dan 300% berbanding dengan spesimen rasuk konvensional RC. Daripada keputusan eksperimen kerangka PPC, kapasiti beban lateral dan ketegangan meningkat sehingga 34% dan 17% berbanding dengan kerangka RC. Tambahan lagi, tiada retak berlaku dalam rasuk kerangka PPC di bawah kenaaan beban galas mati. Juga, berdasarkan kajian parametrik, penggunaan elemen PPC di bangunan konkrit bertingkat dan tertakluk kepada beban seismik menunjukkan kelewatan ketara dalam proses kegagalan, bagaimanapun, bangunan RC konvensional runtuh pada peringkat pertama analisis. Akhir sekali, kajian ini memudahkan analisis dan reka bentuk prosedur bangunan PPC pelbagai tingkat dan bangunan RC serta jambatan dan membolehkan masa pengiraan yang cekap, yang lebih menjimatkan berbanding dengan kaedah reka bentuk normal.

ACKNOWLEDGEMENTS

Firstly, I would like to express my sincere gratitude to my advisor Associate Professor Farzad Hejazi for the continuous support of my PhD study and related research, for his patience, motivation, and immense knowledge. His guidance helped me in all the time of research and writing of this thesis.

Besides, I would like to thank the rest of my supervisor committee Prof. Dato' Ir. Mohd Saleh Jaffar, Prof. Dato' Ir. Abang Abdullah Abang Ali and Ir. Dr. Voo Yen Lei, for their insightful comments and encouragement.

My sincere thanks also go to Mr. Mohammad Haffis Hamid, Mr. Muhammad Mustaqim and Mr. Zain who gave access to the structural laboratory and research facilities.

Last but not the least; I would like to thank my family, my parents and my brothers and sister for supporting me spiritually throughout writing this thesis and my life in general.

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Farzad Hejazi, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Mohd Saleh Jaafar, PhD

Professor, Ir
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Abang Abdullah Abang Ali, PhD

Professor, Ir
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Voo Yen Lei, PhD

Adjunct Professor
Faculty of Civil Engineering
Universiti Putra Malaysia
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____

Name of Chairman of

Supervisory Committee:

Associate Professor. Dr. Farzad Hejazi

Signature: _____

Name of Member of

Supervisory Committee:

Professor Ir. Dr. Mohd Saleh Jaafar

Signature: _____

Name of Member of

Supervisory Committee:

Professor Ir. Abang Abdullah Abang Ali

Signature: _____

Name of Member of

Supervisory Committee:

Associate Professor. Dr. Voo Yen Lei

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	iii
ACKNOWLEDGMENTS	v
APPROVAL	vi
DECLARATIONS	viii
LIST OF TABLES	xiv
LIST OF FIGURES	xvi
 CHAPTER	
1 INTRODUCTION	1
1.1 General Overview	1
1.2 Brief Review of Earlier Works	2
1.3 Problem Statement	4
1.4 Objectives of the Study	4
1.5 Scope and Limitation of Work	5
1.6 Organization of the Thesis	6
 2 LITERATURE REVIEW	7
2.1 Introduction	7
2.2 Numerical Models for Reinforced and Prestressed Concrete Members	7
2.2.1 Analytical models for RC members	8
2.2.2 Analytical models for prestressed concrete members	13
2.3 Practical Design Codes and Experimental Studies	19
2.4 Software Modeling	22
2.5 Seismic Behaviour of Prestressed Concrete Structures	24
2.6 Summary	26
 3 ANALYSIS OF PRESTRESSED/REINFORCED CONCRETE FRAME BUILDINGS	27
3.1 Introduction	27
3.2 Material Models for RC, FPC and PPC Sections	28
3.2.1 Stress-strain relationship used for concrete	28
3.2.2 Stress-strain relationship for steel reinforcing bar	30
3.2.3 Stress-strain relation for prestressing steel strand	31
3.3 Yield Surface of Frame Elements	32
3.3.1 Analysis of prestressed/reinforced concrete sections	32
3.3.2 Basic axial load-moment interaction for concrete sections	34
3.3.3 Axial force-bending moment interaction curve	36
3.3.4 Ultimate axial compression and tension loads of RC sections	37
3.3.5 Ultimate axial compression and tension loads of PPC section	38

3.3.6	Balanced axial load and moment in RC sections	40
3.3.7	Balanced axial load and moment in PPC sections	45
3.3.8	Ultimate moment capacity of RC sections	51
3.3.9	Ultimate moment capacity of PPC sections	55
3.3.10	Axial force-moment interaction curve for PPC frame elements	59
3.4	Yield Surface for 3D RC and PPC Frame Elements Analysis	60
3.5	Partially Prestressed Concrete Frame Structures	64
3.5.1	Frame element	64
3.5.2	Prestressing tendon element	65
3.6	Analytical Model	65
3.6.1	Proposed analytical model for RC beam-column element	66
3.6.2	Development of analytical model for prestressing tendon	67
3.7	Mathematical model for PPC frame element	67
3.7.1	Formulation of frame element in the space	67
3.7.2	Formulation of the prestressing tendon in the space	69
3.8	Development of Constitutive Model for PPC Frame Element	70
3.8.1	Elastic stiffness matrix for RC frame element	71
3.8.2	Elastic stiffness matrix for prestressing tendon element	72
3.8.3	Elastic stiffness matrix of PPC frame element	73
3.8.4	Elasto-plastic and plastic stiffness properties	75
3.9	Numerical Computation and Computer Program Code	75
3.9.1	Analytical technique for PPC frame buildings	76
3.9.2	Nonlinear static analysis procedure	77
3.9.3	Nonlinear dynamic analysis procedure	77
3.9.4	Procedure of inelastic analysis RC and PPC frame structures	77
3.9.5	Development of finite element computer program software	81
3.10	Finite Element Software Package ABAQUS	84
3.11	Summary	85
4	EXPERIMENTAL TESTS AND SPECIMEN DESCRIPTIONS	87
4.1	Introduction	87
4.2	Description of specimens	87
4.2.1	Material properties	93
4.3	Specimens Fabrication	95
4.3.1	Formwork	95
4.3.2	Reinforcing cages	95
4.3.3	Anchorage set	96
4.3.4	Mixing and casting procedure	98
4.4	Instrumentations for the beam specimens	99
4.4.1	Strain gauges	100
4.4.2	Linear voltage differential transducers (LVDTs)	101
4.4.3	Loading equipments	102
4.5	Instrumentations for the frame specimens	103
4.5.1	Strain gauges	103

4.5.2	Test set up of RC and PPC frames under cyclic loading	105
4.6	Loading Procedure	105
4.7	Summary	107
5	RESULTS AND DISCUSSION	108
5.1	Introduction	108
5.2	Reinforced Concrete Frame Element (B1)	108
5.2.1	Validation of experimental model and FE program	108
5.2.2	Validation of plasticity and yield surface theory	116
5.3	Partially Prestressed Concrete Frame Element (B2)	121
5.3.1	Validation of experimental model and FE program	121
5.3.2	Validation of plasticity and yield surface theory	128
5.4	Partially Prestressed Concrete Frame Element (B3)	133
5.4.1	Validation of experimental model and FE program	133
5.4.2	Validation of plasticity and yield surface theory	141
5.5	Comparison of the RC and PPC Beam Specimens	146
5.5.1	Experimental and numerical results	146
5.5.2	Developed yield surface theory	149
5.6	Nonlinear Lateral Cyclic Loading for RC and PPC Frames	151
5.7	Application of the Developed ARCS3D Software for Analysis of One Bay One Storey Reinforced Concrete Frame (F1)	154
5.7.1	Validation of the developed analytical model and FE program	155
5.7.2	Validation of plasticity and yielding surface theory	157
5.8	Application of the Developed ARCS3D Software for Analysis of One Bay One Storey Partially Prestressed Concrete Frame (F2)	161
5.8.1	Validation of the developed analytical model and FE program	161
5.8.2	Validation of plasticity and yielding surface theory	164
5.9	Comparison between RC Frame (F1) and PPC Frame (F2)	169
5.10	Seismic Behavior of Partially Prestressed Concrete Structures	171
5.10.1	Five-storey RC and PPC frame buildings	176
5.10.2	Ten-storey RC and PPC frame buildings	184
5.10.3	Fifteen-storey RC and PPC frame buildings	190
5.10.4	Three-dimensional four-storey building model	195
5.11	Summary	199
6	CONCLUSION AND RECOMMENDATIONS	200
6.1	General Conclusions	200
6.2	Specific Conclusions	201
6.3	Recommendations for Future Study	202

REFERENCES	203
APPENDICES	211
BIODATA OF STUDENT	223
LIST OF PUBLICATIONS	224



LIST OF TABLES

Table	Page
4.1 Experimental test models	87
4.2 Material and geometrical characteristics of the beam and frame specimens	92
4.3 Partial prestressing indices for the specimens	92
4.4 Concrete mix proportion for concrete Grade 40 (per meter cube)	93
5.1 Comparison of numerical and test results at $\frac{1}{4}$ and $\frac{3}{4}$ span of B1	114
5.2 Comparison of numerical and test results at mid-span of the B1	115
5.3 Trend line equation and corresponding R2 factors specimen B1	115
5.4 Yield function constants and sectional properties in X and Y directions for B1	116
5.5 Comparison of numerical and test results at $\frac{1}{4}$ and $\frac{3}{4}$ span of B2	127
5.6 Comparison of numerical and test results at mid-span of B2	128
5.7 Trend line equations and corresponding R2 factors specimen B2	128
5.8 Yield function constants and sectional properties in X and Y directions of specimen B2 from developed FE program	129
5.9 Comparison of numerical and test results at $\frac{1}{4}$ and $\frac{3}{4}$ span of B3	139
5.10 Comparison of numerical and test results at mid-span of B3	140
5.11 Trend line equations and corresponding R2 factors for B3	140
5.12 Yield function constants and sectional properties in X and Y directions for B3 from the developed FE program	141
5.13 Geometrical characteristics and reinforcement arrangement of the beam specimens	147
5.14 Comparison of beams results obtained from the experiment tests	148
5.15 Comparison of beams results from developed FE program	149
5.16 Yield function constants and sectional properties in X and Y directions for B1, B2 and B3	149
5.17 Material properties for concrete with SCDP model in class B40	151
5.18 Comparison of numerical analysis and test results for frame F1	157
5.19 Yield function constants and sectional properties of beam and column in model F1	158
5.20 Comparison of numerical analysis and test results for frame F2	164

5.21	Yield function constants and sectional properties of beam and column in model F2	165
5.22	Number of plastic hinge formations in the five-storey RC and PPC frame models subjected to time history analysis	183
5.23	Maximum top displacements in X-direction of ten-storey models subjected to magnified accelerations of El-Centro excitation	189
5.24	Maximum top displacements in Y-direction of ten-storey models subjected to magnified accelerations of El-Centro excitation	189
5.25	Number of plastic hinge formations in the 10-storey RC and PPC frame models subjected time history analysis	189
5.26	Maximum displacements in X-dir of 15-storey models subjected to different magnified accelerations of El-Centro excitation	194
5.27	Maximum displacements in Y-dir of 15-storey models subjected to different magnified accelerations of El-Centro excitation	194
5.28	Number of plastic hinge formations in the 15-storey RC and PPC frame models subjected time history analysis	195

LIST OF FIGURES

Figure	Page
2.1 Frame elements (a) concentrated plasticity approach (b) distribution plasticity approach (Hejazi, 2012)	9
2.2 Developed analytical model for RC frame element (Thanoon et al., 2004)	10
2.3 Developed 3D yield surface including axial force-biaxial moments interaction (Thanoon et al., 2004)	11
2.4 Idealized combined shear, bending moment and torsion interaction curve (Mullapudi et al., 2010)	12
2.5 Trussed-beam analytical model for post-tensioned concrete beam (Ozkul, 2007)	22
2.6 Modeling of PT system in ABAQUS (Huang, 2012)	23
3.1 Methodology flowchart of present study	29
3.2 Constitutive relation for Concrete (Medland and Taylor, 1971)	30
3.3 Stress-Strain curves for steel reinforcement (Hejazi, 2012)	31
3.4 Stress-Strain curve for prestressing steel strand (Tadros, 1992)	31
3.5 Possible strain distribution cases for a PPC cross-section	33
3.6 Possible types of concrete sections	34
3.7 Key points of axial force-bending moment interaction curve of frame elements	37
3.8 Force in reinforcing steel, tendon and concrete based on equilibrium equations	40
3.9 Computation flowchart of axial force and moment for concrete	42
3.10 Computation flowchart of axial force and bending moment due to normal reinforcing steel	44
3.11 Strain diagram of PPC section	48
3.12 Computation flowchart of axial force and bending moment due to prestressing tendon	50
3.13 Possible strain distribution diagrams to find the failure regions	60
3.14 3D initial and fully plastic interaction surfaces (Hejazi, 2012)	61
3.15 Proposed axial force-biaxial moments interaction curves about (Hejazi, 2012)	63
3.16 Torsion-bidirectional shear forces interaction surface	63

3.17	Three-dimensional yield surface for RC and PPC sections	64
3.18	Framed structure including beam-column elements	65
3.19	Prestressing tendon element for modeling PPC structure	65
3.20	Proposed constitutive model for RC element (Hejazi, 2012)	66
3.21	Real tendon element and 3D constitutive model	67
3.22	Analytical model for 3D RC frame element (Hejazi-2012)	68
3.23	End displacements and forces for a frame element in space	69
3.24	Analytical model for a 3D two-node prestressing tendon	70
3.25	End displacements and forces for a 3D PPC frame element	73
3.26	Schematic view to dynamic analysis of the PPC buildings	78
3.27	Procedure of elastic and inelastic dynamic analysis of structure	82
3.28	Process of analysis of RC and PPC buildings in ARCS3D	83
3.29	Procedure of pre-processor, processor and post-processor parts	84
3.30	Kent and Park Model for compressive behavior of concrete (Park and Paulay, 1975)	85
4.1	Cross-sections of the beam specimens (B1, B2 and B3)	88
4.2	Dimensional and reinforcement details	89
4.3	Dimensional, cross-section and reinforcement details	90
4.4	Concrete cube test under compression machine	93
4.5	Stress-Strain curve of cold worked deformed bar (BS 4449, 1997)	94
4.6	Stress-Strain curve for prestressing strands used in the experiment	94
4.7	The formworks for beam and frame specimens	95
4.8	Shear and longitudinal reinforcement placed in the formworks of beam and frame specimens	96
4.9	'K' range anchorage set for post-tensioned specimens (British Standards, BS 4447 and ACI Code, 301)	96
4.10	Anchorage set used in specimen B2	97
4.11	Anchorage set used in specimen B3	97
4.12	Anchorage set used in specimen F2	98
4.13	Checking strain gauge, formworks on vibrator table and procedure of concrete pouring	99
4.14	Data logger for recording data (strain, deflection and load)	99
4.15	Strain gauges for steel and concrete	100

4.16	Steel and concrete strain gauges	100
4.17	Location of strain gauges on the beam specimens	101
4.18	50 mm range linear voltage differential transducers (LVDT)	102
4.19	Loading equipment for the beam specimens	102
4.20	Schematic view of the LVDTs and loading equipment locations	103
4.21	Location of strain gauges on the frame specimens F1 and F2	104
4.22	Schematic view of test set up for RC and PPC frames	105
4.23	Superimposed dead load on the RC and PPC frames	106
4.24	Cyclic loading history used in experimental tests and FE models	107
4.25	Earthquake records of El-Centro (1940-USA)	107
5.1	Specimen B1 before test	109
5.2	Load-deflections at 1/4, 1/2 and 3/4 of the RC beam span (B1)	109
5.3	Deflection profile of the RC beam specimen (B1)	110
5.4	Vertical load-concrete surface strain curves of specimen B1	111
5.5	Vertical load- steel reinforcement strain curves of specimen B1	112
5.6	RC beam specimen (B1) in developed FE program (ARCS3D)	112
5.7	Reaction force-deflection curves for the developed FE program and test results at 1/4 and 3/4 span of the B1	113
5.8	Load-deflection curves obtained from the numerical model and test results at mid-span of the B1	115
5.9	Axial force-bending moment interaction curves and 2D yield surface of specimen B1 around X and Y axes from ARCS3D	117
5.10	Three dimensional yield surface of the Specimen B1	118
5.11	Moment-deflection curves obtained from the numerical analysis and test results of specimen B1	118
5.12	Comparison between key points (C) obtained from numerical analysis and test results	119
5.13	Deformed configuration and crack pattern at failure of B1	120
5.14	Number and location of plastic hinges formed in specimen B1 from the developed FE program	120
5.15	Specimen B2 before test	121
5.16	Load-deflections at 1/4, 1/2 and 3/4 of the beam span (B2)	122
5.17	Deflection profile of the PPC beam specimen (B2)	122
5.18	Vertical load-concrete surface strain curves of specimen B2	124
5.19	Vertical load- steel reinforcement strain curves of specimen B2	124

5.20	PPC beam specimen (B2) in developed FE program (ARCS3D)	125
5.21	Reaction force-deflection curves of the developed FE program and test results at $\frac{1}{4}$ and $\frac{3}{4}$ span of the B2	126
5.22	Load-deflection curves obtained from the numerical model and test results at mid-span of the B2	127
5.23	Axial force-bending moment interaction curves and 2D yield surfaces of specimen B2 around X and Y axes	130
5.24	Three dimensional yield surface of the specimen B2	130
5.25	Moment-deflection curves obtained from the numerical analysis and test results of specimen B2	131
5.26	Comparison between key points (C) obtained from numerical analysis and test results of specimen B2	131
5.27	Deformed configuration and crack pattern at failure of B2	132
5.28	Number and location of plastic hinges formed in specimen B2 from the developed FE program	133
5.29	Specimen B3 before tes	133
5.30	Load-deflections measured at $\frac{1}{4}$, $\frac{1}{2}$ and $\frac{3}{4}$ of beam span (B3)	134
5.31	Deflection profile of the PPC beam specimen (B3)	134
5.32	Vertical load-concrete surface strain curves of specimen B3	136
5.33	Vertical load- steel reinforcement strain curves of specimen B3	137
5.34	PPC beam specimen (B3) in developed FE program (ARCS3D)	138
5.35	Reaction force-deflection curves of the developed FE program and test results at $\frac{1}{4}$ and $\frac{3}{4}$ span of the B3	138
5.36	Load-deflection curves obtained from the numerical model and test results at mid-span of the B3	140
5.37	Axial force-bending moment interaction curves and 2D yield surface of specimen B3 around X and Y axes	142
5.38	Three dimensional yield surface of specimen B3	143
5.39	Moment-deflection curves obtained from the numerical analysis and test results of specimen B3	143
5.40	Comparison between key points (C) obtained from numerical analysis and test results of specimen B3	144
5.41	Comparison between moments obtained from numerical analysis and test results of specimen B3 when axial force is 500 kN	144
5.42	Deformed configuration and crack pattern at failure of B3	145
5.43	Number and location of plastic hinges formed in specimen B3 from the developed FE program	145

5.44	Geometrical data and reinforcement arrangement of the specimens	146
5.45	Comparison between load-deflection curves at mid-span of the beam specimens B1, B2 and B3 from the experimental tests	147
5.46	Comparison between load-deflection curves at mid-span of the beam specimens B1, B2 and B3 from developed FE program	148
5.47	Comparison between yield surfaces of the beams B1, B2 and B3	150
5.48	FE meshes of (a) RC and PPC frames (b) reinforcement and Prestressing strand	152
5.49	Lateral cyclic load-displacement curves of specimen F1 from experimental test and FE model	153
5.50	Deformed configuration and damages in frame specimen F1	153
5.51	Lateral cyclic load-displacement curves of specimen F2 from experimental test and FE model	154
5.52	Deformed configuration and damages in frame specimen F2	154
5.53	One bay one story reinforced concrete frame (F1)	155
5.54	Hysteresis loops and skeleton curve for Specimen F1	156
5.55	Pushover curves for F1 from numerical and experimental results	157
5.56	Interaction and 2D yield surface curves of the beam and column about X and Y axes of the sections in frame F1	159
5.57	3D yield surfaces for the structural members	159
5.58	Formation of plastic hinges in the RC frame (F1)	160
5.59	Crack propagation and first crack in the RC frame (F1)	160
5.60	Inelastic response of force-displacement curves	161
5.61	One bay one story partially prestressed concrete frame (F2)	162
5.62	Hysteresis loops and skeleton curve for Specimen F2	163
5.63	Pushover curves for F2 from numerical and experimental results	163
5.64	Interaction and 2D yield surface curves of the beam and column about X and Y axes of the sections in frame F2	166
5.65	3D yield surfaces of the structural elements of specimen F2	166
5.66	Formation of plastic hinges in the PPC frame (F2)	167
5.67	Crack propagation in beam and column of the PPC frame (F2)	168
5.68	Inelastic response of force-displacement curves for specimen F2	168
5.69	Skeleton curves for RC and PPC frames	169
5.70	Pushover curves for RC and PPC frames from numerical analysis	170

5.71	Comparison of maximum strain values in RC and PPC frames	171
5.72	Multi-storey frame buildings in the developed FE program	172
5.73	3D models of the four-storey RC and PPC buildings	172
5.74	Sectional properties of the beams and columns	173
5.75	Interaction curves and 2D yield surfaces of conventional RC beam and column	174
5.76	Interaction curves and 2D yield surfaces of PPC beam element	175
5.77	3D yield surfaces for structural elements of buildings	176
5.78	Pushover curves of the 5-storey RC and PPC buildings	177
5.79	Story drift ratio due to pushover load along X direction	177
5.80	Time history of top node displacement subjected to El-Centro excitations (PGA=0.34g)	178
5.81	Time history of top node displacement subjected to El-Centro excitations (PGA=2*0.34g)	179
5.82	Time history of top node displacement subjected to El-Centro excitations (PGA=3*0.34g)	180
5.83	Time history of top node displacement subjected to El-Centro excitations (PGA=4*0.34g)	181
5.84	Maximum top node displacements of the five-storey frame subjected to magnified accelerations of El-Centro excitation	182
5.85	Story drift ratio for magnified El-Centro records in X direction	183
5.86	Pushover curves of the 10-storey RC and PPC buildings	184
5.87	Story drift ratio due to pushover load along X direction	185
5.88	Time history of top node displacement subjected to El-Centro excitations (PGA=0.34g)	186
5.89	Time history of top node displacement subjected to El-Centro excitations (PGA=2*0.34g)	187
5.90	Time history of top node displacement subjected to El-Centro excitations (PGA=3*0.34g)	188
5.91	Time history of top node displacement subjected to El-Centro excitations (PGA=4*0.34g)	188
5.92	Pushover curves of the 15-storey RC and PPC buildings	190
5.93	Story drift ratio due to pushover load along X direction	191
5.94	Time history of top node displacement subjected to El-Centro excitations (PGA=0.34g)	192
5.95	Time history of top node displacement subjected to magnified El-Centro excitations (PGA=2*0.34g)	192

5.96	Time history of top node displacement subjected to magnified El-Centro excitations ($PGA=3*0.34g$)	193
5.97	Time history of top node displacement subjected to magnified El-Centro excitations ($PGA=4*0.34g$)	194
5.98	Displacement versus reaction force subjected to monotonic load	195
5.99	Area under the reaction force-displacement curves	196
5.100	Dynamic response of four-storey RC and PPC buildings subjected to El-Centro earthquake excitations	198
5.101	Number of plastic hinge formation in the four-storey RC and PPC buildings subjected to time history analysis	198



CHAPTER 1

INTRODUCTION

1.1 General Overview

Prestressing concrete is a widely-used technique which was introduced in the early 1940s to overcome the natural weakness of concrete in tension (i.e. cracking and deflections) from externally applied loads. For the past two decades, the practice of prestressing tendons in prestressed beams has not been limited to bridges and industrial structures but also has been included in commercial and residential buildings. Concrete can be stressed either by pre-tensioning or post-tensioning. Pre-tensioned concrete is mostly used in prefabricated constructions, in which the members are firstly fabricated then assembled at site. As the name implies, prestressing strands are stretched before concrete hardening to ensure a full bond between concrete and prestressing strands. After releasing strands, the tensile forces in the pre-tensioned strands are transferred to the concrete until an equivalency between steel strands and concrete is achieved. This technique is mostly used to build parking structures, office buildings, stadiums and schools, and considerably decreases the total construction time and cost. On the other hand, post-tensioning strands are released after the concrete hardening. Post-tensioning would be performed using internally bonded, internally unbonded and externally unbonded tendons. Post-tensioning is mainly applied for strengthening and repair of existing structures. This method is mostly used for segmental bridges, post-tensioned slabs, continuous beams, etc. Moreover, longer spans can be achieved using post-tensioning in comparison with pre-tensioning.

The technical literature reveals that combining conventional reinforcing steels and prestressing steel strands to strengthen a flexural concrete member is normally implied by the term partially prestressed element. In current practice, partial prestressing is accepted as a technique in between full prestressing and conventional (non-prestressed) reinforcing. Prestressed strands are used to control deflections and crack widths. On the other hand, further non-prestressed reinforcement would add to the ultimate capacity without significant change in the cracking moment. In practice, partially prestressed concrete elements are employed with their design based on rational analysis, on satisfying the conditions of both serviceability and ultimate strength constraints and finally on the engineering judgment.

In comparison to reinforced concrete, with partial prestressing greater clear span with same member depth, enhanced crack control and smaller member sizes can be achieved. Moreover, steel and concrete material properties are effectively utilized.

Based on the few number of published studies, (Abeles, 1963; Hawkins, 1977; Park and Thompson, 1980; Naaman, 1986; Harajli, 1993 and 2006; Au and Du, 2004; Karayannis and Chalioris, 2013; Burgueno and Sun, 2014; Rakaa and Astawaa, 2014; Iskhakov and Ribakov, 2015) in comparison with fully prestressed concrete structures, the use of partial prestressing may enhance ductility and energy absorption capability, improve economy, as well as reduce the camber and creep deformation due to prestress. In a seismic event, the reinforcing steel will dissipate energy in a ductile manner while the post-tensioning cables along the length of the frame will provide elastic action that creates a self-righting force to pull the joint and frame back toward its original position. Although partial prestressing technique has been used in many structures, dynamically, the structural behavior of the PPC structures is yet to be well understood.

Hence, in this study a new analytical model for PPC frame elements subjected to static and dynamic loads is developed. For this purpose, constitutive law and mathematical model for the three-dimensional PPC beam-column element are formulated and a special finite element algorithm is developed. Moreover, in order to detect the damages and determine the location of plastic hinges during dynamic loading in PPC structures, formulation for plasticity and yielding surface mechanism of PPC frame element is derived. Hence, the hypothesis of the current study is development of an approach to facilitate the analysis and design procedures of multi-storey and long-span PPC buildings and bridges in an efficient computation time which is more economical in comparison with other design methods.

1.2 Brief Review of Earlier Works

Prestressed concrete members are essential in many places today in order to fully make use of concrete compressive strength and control deflection and cracking. Due to those advantages, research on the behavior of prestressed concrete members has seen impressive developments. Partially prestressed concrete structures bridge the gap between fully prestressed concrete structures and reinforced concrete structures (Allouche et Al., 1999). To be more specific, in such a structure, tension and cracking in concrete due to flexure are permitted under service dead and live loads. Hence, in the last two decades, partially prestressed techniques have been found to be attractive methods for engineers to design concrete bridges and buildings with desired form, simple and economical construction of medium to large span.

The analysis of a PPC element has additional levels of difficulty compared to the analysis of conventional reinforced concrete (RC) and fully prestressed concrete (FPC) members. On the other hand, published research on nonlinear dynamic behavior FPC and PPC structures subjected to earthquake loading is much less than conventional RC structures. Therefore, this study focuses on a new constitutive law and mathematical model for PPC frame elements subjected to

static and dynamic loading. Besides, a new mathematical model for identifying the damages in partially prestressed concrete beams and frame structures during earthquake excitation is considered. Abeles (1959 and 1963) discussed partial prestressing and possibilities for its practical application. He declared the essential features, ways of approach, philosophy of design, practical application in England, and differences between fully and partially prestressing techniques. In 1977, Hawkins reviewed analytical and experimental studies related to seismic behavior of precast reinforced and fully prestressed concrete structures. Thompson and Park (1980) demonstrated that prestressed concrete has been widely used for structures carrying gravity loads but has not been as widely accepted for use in structural systems which resist seismic loading. They investigated the ductility of a few prestressed and partially prestressed concrete beams sections.

The nonlinearity of the three-dimensional nature of PPC elements was not considered during this research. Naaman et al. (1986) compared experimental data with a proposed nonlinear analytical model to evaluate the flexural ductility of PPC elements under only static loading conditions. Harajli (1993) examined only experimentally the flexural capacity of 16 PPC beam specimens strengthened by external prestressing tendons under firstly cyclic fatigue loading then, subjected to monotonically increasing load to failure. In 2006, he also presented a comprehensive assessment of the main parameters that influence the ultimate stress in un-bonded tendons and discussed the reasons behind the scatter in the predictions of test results in the literature. Au and Du (2004) explained the behavior of PPC sections under static loads. Effect of amount of steel and FRP prestressing tendons on the ductility of the bonded partially prestressed members was considered for two-dimensional static analysis sections. Karayannis and Chalioris (2013) estimated the required partial prestressing on the basis of crack control of concrete. In this study, empirical formulations (ACI318 and Euro-code 2) were used instead of developing a comprehensive analytical model. They also offered design charts and numerical paradigms for PPC rectangular and T-shape beams.

A considerable amount of work and effort was put in by Thanoon et al. (2004) and Hejazi (2010) to develop analytical and numerical methods for nonlinear behavior of conventional concrete building structures. Furthermore, formulation for plasticity and yielding surface mechanism of RC frame elements was derived in order to detect damages during dynamic loading procedure.

Due to lack of a comprehensive analytical model, plasticity theory and FE program for analysis of PPC members, ABAQUS software was utilized by Burgueno and Sun (2014) to investigate damages during manufacturing of pre-tensioned beams. Damaged plasticity analysis was conducted in the ABAQUS for this purpose. Therefore, structural performance of PPC buildings under dynamic loads with respect to the plastic hinge formation mechanism in building components is not available.

1.3 Problem Statement

The growing use of prestressing technique for buildings and bridges with long span and light weight subjected to dynamic loads, has resulted in a need to increase the current knowledge of the behavior of PPC beam-column elements. Based on the extensive review of literature, it is observed that there is no comprehensive research on the three-dimensional seismic behavior of PPC structures. Consequently, there are crucial unresolved gaps in the understanding and assessment of PPC elements including:

- i. There is no information about yield surface and plasticity theory for PPC frame elements in order to detect the damages and determine the location of plastic hinges during dynamic loading.
- ii. Most of the available literature and building code provisions on the behavior of concrete members were dedicated to conventional reinforced concrete and fully prestressed concrete members. However, few researchers have focused on the two-dimensional structural behavior of PPC elements. Thus, there is no unique and specific analytical and numerical model for PPC frame elements.
- iii. Modeling a simple prestressed element using existing finite element software is very complicated because all parts (i.e. concrete, normal reinforcement and prestressing steel strand) should be defined separately and then assembled. Moreover, another challenge in analyzing of PPC elements is assigning a suitable interaction between different materials, which is a time consuming procedure and requires experience. These issues increase the percentage of deviation, computation time as well as the cost of a project.
- iv. According to a comprehensive review of the literature, there is lack of FE algorithm and computer program associated with a failure criteria theory to identify the exact place of damaged areas in three-dimensional prestressed structures under dynamic loads.
- v. In the technical review of the literature, there is insufficient number of experimental tests available to verify and validate the structural performance of PPC beams and frame buildings under static and dynamic loads with respect to the plastic hinge formation mechanism.

1.4 Objectives of the Study

The general objective of the current study is development of a new analytical model associated with a plastic hinge formation mechanism for PPC frame elements to facilitate the seismic analysis and design procedures of multi-story PPC and RC buildings as well as bridges in an efficient computation time which is more economical in comparison with normal methods of design. Thus, specific objectives that contribute to this aim include:

1. To develop formulation for plasticity and yielding surface mechanism of PPC frame elements to detect the damages and determine the location of plastic hinges during dynamic loading.
2. To develop a new constitutive law and finite element model for PPC frame elements.
3. To formulate and develop a new FEM algorithm and subsequently implement it in the FE program package in order to perform nonlinear static and dynamic analysis of PPC structures, and validating the FE program by conducting sufficient number of experimental tests.

1.5 Scope and Limitation of Work

To ensure that the above objectives are achieved, the present study is organized as follows:

- 1) In the current study, constitutive law and mathematical model for beam-column elements are considered.
- 2) Three-dimensional finite element formulations are implemented for beam-column elements.
- 3) In the numerical analysis, nonlinear characteristics of all material are considered.
- 4) 3D yielding surface and plasticity mechanism for PPC frame elements is implemented.
- 5) Newmark's systematic step-by step integration approach has been chosen for nonlinear analyses. Computation strategies are presented for the predication of time history response.
- 6) Experimental tests are conducted to validate the developed formulations and plasticity theory.

Furthermore, limitations of the present study are presented as follows:

- 1) Effects of prestress losses are not considered in finite element formulations.
- 2) Un-bonded prestressed technique is not considered in this study.
- 3) Effect of tensile strength in concrete is also not considered.

1.6 Organization of the Thesis

The thesis comprises five chapters and the summaries of these chapters are provided below.

The significance and definition of the problem statement of the present investigation have been highlighted in Chapter 1 along with the objectives and scope of the study.

Chapter 2 reviews relevant previous studies in the literature about analytical model, inelastic analysis, finite element formulations, yielding surface and hinge formation as well as experimental tests which have been done related to RC, FPC and PPC elements and structures.

The detailed methodology of this study is discussed in Chapter 3. Formulation of plasticity and yielding surface mechanism of PPC frame element and its development is presented. Also, development of 3D nonlinear PPC frame elements and finite element procedure for nonlinear static and dynamic analysis is derived. Development of numerical computation procedure and computer program code

A general description of the test specimens, material properties, instrumentation arrangements and loading procedure of experimental tests are explained in Chapter 4.

Chapter 5 extensively reports the comparison between numerical and experimental results of conventional reinforced concrete and PPC beam and frame specimens under flexural and cyclic analysis in order to validate the developed analytical model, plasticity formulation and the developed FE computer program code. In addition, seismic performance assessment of multi-story PPC structures is investigated under severe superimposed dead and live loads.

Chapter 6 summarizes the present study and provides its major and specific conclusions. The scope of future works and recommendations are also discussed.

REFERENCES

- ACI Committee 318. (1995). *Building code requirements for structural concrete*. Farmington Hills, Detroit, Michigan, USA.
- ACI Committee 318. (2005). *Building code requirements for structural concrete*. American Concrete Institute, Farmington Hills, Detroit, Michigan, USA.
- Agrawal, G., & Bhattacharya, B. (2010). Partial safety factor design of rectangular partially prestressed concrete beams in ultimate flexural limit state. *Journal of Structural Engineering*, 37(4), 257–267.
- Alameh, A., & Harajli, M. (1989). Deflection of Progressively Cracking Partially Prestressed Concrete Flexural Members. *PCI Journal*, 34(3), 94–128.
- Al-ani, H., Hasan, W. M., & El-khatieb, M. (2012). Statistical Identification of a Prestressed Concrete Beam with Unbonded Tendons Using Modal Data. *Jordan Journal of Civil Engineering*, 6(1), 109–121.
- Al-Bermani, F., & Kitipornchai, S. (1990). Nonlinear analysis of thin-walled structures using least element/member. *Journal of Structural Engineering*, 116(1), 215–234.
- Al-Gahtani, A., Al-Saadoun, S., & Abul-Feilat, E. (1995). Design optimization of continuous partially prestressed concrete beams. *Computers & Structures*, 55(2), 365–370.
- Al-Jurmaa, M., & Abdul-Razzak, A. (2009). Analysis of Pretensioned Partially Prestressed Concrete Beams. *Researchgate.net*, 6(2), 26–32.
- Alkhairi, F., & Naaman, A. (1993). Analysis of beams prestressed with unbonded internal or external tendons. *Journal of Structural Engineering*, 119(9), 2680–2700.
- Allouche, E., Campbell, T., & Green, M. (1998). Tendone stress in continuous unbonded prestressed concrete members. *PCI Journal*, 43(6), 86–93.
- Anderson, J. C., & Townsend, W. H. (1977). Models for RC frames with degrading stiffness. *Journal of the Structural Division*, 103(12), 2361–2376.
- ARCS3D. (2015). Finite element program, Analysis of reinforced concrete structures, Copyright by University Putra, Malaysia.
- Ariyawardena, N., & Ghali, A. (2002). Prestressing with unbonded internal or external tendons: analysis and computer model. *Journal of Structural Engineering*, (December), 1493–1501.
- Au, F. T. K., & Du, J. S. (2004). Partially prestressed concrete. *Progress in Structural Engineering and Materials*, 6(2), 127–135.
- Ayoub, A., & Filippou, F. (2009). Finite-element model for pretensioned prestressed concrete girders. *Journal of Structural Engineering*, 136(4), 401–409.
- Balaguru, P. (1981). Analysis of prestressed concrete beams for fatigue loading. *PCI Journal*, 26(3), 70–94.
- Bennett, E. (1984). Partial Prestressing-A Historical Overview. *PCI Journal*, 29(5), 104–117.
- British Standard 5328-2. (1997). *Concrete. Methods for specifying concrete mixes*.
- Brecolotti, M., Ubertini, F., & Venanzi, I. (2009). Natural frequencies of prestressed concrete beams: theoretical prediction and numerical validation. *Atti Del XIX Congresso AIMETA*, 14–17.

- Bruggeling, A. (1985). Partially Prestressed Concrete Structures-A Design Challenge. *PCI Journal*, 30(2), 140–171.
- Burgueño, R., & Sun, Y. (2014). Stress transfer characteristics of sheathed strand in prestressed concrete beams: computational study. *PCI Journal*, 59(3), 95–109.
- Campbell, T. ., & Kodur, V. (1990). Deformation controlled nonlinear analysis of prestressed concrete continuous beams. *PCI Journal*, 35(5), 42–55.
- Caro, L. a., Martí-Vargas, J. R., & Serna, P. (2013). Prestress losses evaluation in prestressed concrete prismatic specimens. *Engineering Structures*, 48, 704–
- Chen, X., & Liu, X.-L. (2012). No TitleLimit analysis for reinforced concrete beams with rectangular cross-section under bending and torsion. *Journal of Shanghai Jiaotong University/Shanghai Jiaotong Daxue Xuebao*, 46(10), 1573–1580.
- Chern, J., You, C., & Bazant, Z. (1992). Deformation of progressively cracking partially prestressed concrete beams. *PCI Journal*, 1(37), 74–84.
- Chowdhury, S. (2001). Crack Width Predictions of Reinforced and Partially Prestressed Concrete Beams: A Unified Formula. ... *Proceedings of the International Conference on ...*, 1, 327–334.
- Chowdhury, S. . (1999). *Damping Characteristics of Reinforced and Partially Prestressed Concrete Beams*. Griffith University, Queensland, Australia.
- Cohn, M., & MacRae, A. (1984). Prestressing optimization and its implications for design. *PCI Journal*, 29(4), 68–83.
- Dall'Asta, A., Ragni, L., & Zona, A. (2007). Simplified method for failure analysis of concrete beams prestressed with external tendons. *Journal of Structural Engineering*, (January), 121–131.
- Devalapura, R. K., & Tadros, M. K. (1992). Stress-strain modeling of 270 ksi low-relaxation prestressing strands. *PCI Journal*, 9(270), 100–106.
- Dilger, W., & Suri, K. (1986). Steel stresses in partially prestressed concrete members. *PCI Journal*, 31(3), 88–112.
- El-Mezaini, N., & Lu, E. Ç. g . (1992). Finite element analysis of prestressed and reinforced concrete structures. *Journal of Structural Engineering*, 117(10), 2851–2864.
- Eurocode 2. (1992). *Design of concrete structures – Part 1-1: general rules and rules for buildings*.
- Eurocode 2. (2004). *Design of concrete structures – Part 1-1: general rules and rules for buildings*.
- Fafitis, A. (2000). Interaction Surfaces of Reinforced Concrete Sections in Biaxial Bending by Green's Theorem. In *8th International Conference on Computing in Civil and Building Engineering* (pp. 90–97).
- Fanning, P. (2001). Nonlinear models of reinforced and post-tensioned concrete beams. *Electronic Journal of Structural Engineering*, 1, 111–119.
- Faur, A., Mircea, C., & Păstrav, M. (2012). A Modeling Technique for Precast Concrete Frames with Hybrid Connections. *Constructii.utcluj.ro*, 55(3).
- Figueiras, J., & Povoas, R. (1994). Modelling of prestress in non-linear analysis of concrete structures. *Computers & Structures*, 53(I).
- Furlong, R., Hsu, C., & Mirza, S. (2004). Analysis and design of concrete columns for biaxial bending-overview. *ACI Structural Journal*, 101(3), 413–423.
- Ghali, A. (1986). A Unified Approach for Serviceability Design of Prestressed and Non prestressed Concrete Structures. *PCI Journal*, 31(2), 118–137.

- Ghali, A., & Elbadry, M. (1989). Serviceability design of continuous prestressed concrete structures. *PCI Journal*, 34(1), 54–91.
- Guest, S. (2004). The stiffness of prestressed frameworks : a unifying approach. *International Journal of Solids and Structures*, (1986).
- Hafezolzghorani, M., Hejazi, F., Vaghei, R., Jaafar, M. S. B., & Karimzade, K. (2017). Simplified Damage Plasticity Model for Concrete. *Structural Engineering International*, 27(1), 68–78.
- Han, Jian, Q., Li, Bao, Z., & Song, Sheng, X. (2011). Research on Seismic Performance of Prestressed Precast Reinforced Concrete Intelligent Structure. *Applied Mechanics and Materials*, 50, 1003–1007.
- Han, M. Y., Hwang, E.-S., & Lee, C. (2003). Prestressed concrete girder with multistage prestressing concept. *Structural Journal*, 100(6), 723–731.
- Harajli, H., & Kanj, Y. (1993). Service Load Behavior of Concrete Members Prestressed With Unbonded Tendons. *Journal of Structural Engineering*, 118(9), 2569–2589.
- Harajli, M. (1993). Strengthening of concrete beams by external prestressing. *PCI Journal*, 38(6), 76–88.
- Harajli, M. H. (2006). On the stress in unbonded tendons at ultimate: Critical assessment and proposed changes. *ACI Structural Journal*, 103(6), 803–812.
- Harajli, M., & Hijazi, S. (1991). Evaluation of the ultimate steel stress in partially prestressed concrete members. *PCI JOURNAL*, 36(1), 62–82.
- Harajli, M., & Naaman, A. (1985). Evaluation of the Ultimate Steel Stress in Partially Prestressed Flexural Members. *PCI Journal*, 30(5), 54–81.
- Hawkins, N. M. (1977). Seismic Resistance of Prestressed and Precast Concrete Structures. *PCI Journal*, 22(6), 80–110.
- Hejazi, F. (2012). *Development of an earthquake energy dissipation system in reinforced concrete framed buildings*. PhD thesis, Departement of Civil and Structural Engineering, Universiti Putra Malaysia.
- Heo, S., Shin, S., & Lee, C. (2013). Flexural Behavior of Concrete Beams Internally Prestressed with Unbonded Carbon-Fiber-Reinforced Polymer Tendons. *Journal of Composites for Construction*, (April), 167–175.
- Hinton, E., & Owen, D. R. J. (1986). *Finite elements in plasticity: Theory and practice*. Pineridge Press Limited.
- Hsu, C. (1985). Biaxially loaded L-shaped reinforced concrete columns. *Journal of Structural Engineering*, 111(12), 2576–2595.
- Huang, L., Lu, Y., & Shi, C. (2013). Unified Calculation Method for Symmetrically Reinforced Concrete Section Subjected to Combined Loading. *ACI Structural Journal*, 110(1), 127.
- Huang, Y. (2012). *Finite element method for post-tensioned prestressed concrete structures*. PhD Thesis, Department of Engineering, UMI University, Norman, Oklahoma.
- Iskhakov, I., & Ribakov, Y. (2015). Ultimate limit state of pre-stressed reinforced concrete elements. *Materials and Design*, 75, 9–16.
- Jarallah, H. K. (2005). *Inelastic seismic response of R.C. framed buildings with a soft storey*. PhD Thesis, Civil Engineering, Roorkee, India.
- Joint ACI-ASCE Committee 423. (2000). *State-of-the-art report on partially prestressed concrete*. Farmington Hills, MI, USA.
- Jr, G. G., & Belarbi, A. (2009a). Model for reinforced concrete members under torsion, bending, and shear. I: Theory. *Journal of Engineering Mechanics*,

- 135(9), 961–969.
- Jr, G. G., & Belarbi, A. (2009b). Model for Reinforced Concrete Members under Torsion, Bending, and Shear. II: Model Application and Validation. *Journal of Engineering Mechanics*, 135(9), 970–977.
- Karayannis, C. G., & Chalioris, C. E. (2013). Design of partially prestressed concrete beams based on the cracking control provisions. *Engineering Structures*, 48, 402–416.
- Kawakami, M., & Ghali, A. (1996). Cracking, ultimate strength and deformations of prestressed concrete sections of general shape. *PCI Journal*, 41(4), 114–122.
- Khaleel, M., & Itani, R. (1993). Optimization of partially prestressed concrete girders under multiple strength and serviceability criteria. *Computers & Structures*, 49(3).
- Kien, N. D. (2008). Dynamic Response of Prestressed Timoshenko Beams Resting on Two-Parameter Foundation to Moving Harmonic Load. *TECHNISCHE MECHANIK*, 3(4), 237–258.
- Kim, K. S., & Lee, D. H. (2012). Nonlinear analysis method for continuous post-tensioned concrete members with unbonded tendons. *Engineering Structures*, 40, 487–500.
- Koshikawa, T., Ueda, M., Kikuchi, M., & Saito, T. (2008). Structural performance of precast prestressed concrete frames with hybrid post-tensioned connections. In *The 14th World Conference on Earthquake Engineering*. Beijing, China.
- Laskar, A., Howser, R., Mo, Y., & Hsu, T. (2010). Modeling of Prestressed Concrete Bridge Girders. In *Earth and Space 2010, ASCE* (pp. 2870–2887).
- Lee, S., Shin, K., & Kang, T. (2015). Flexural strengthening of continuous concrete beams using external prestressed steel bars. *PCI Journal*.
- Li, F. (2012). The Research on Seismic Response of Prestressed Concrete Flat Beam in Pseudo-dynamic Test. In *2nd International Conference on Electronic & Mechanical Engineering and Information Technology* (pp. 806–809).
- Loov, R. (1988). A General Equation for the Steel Stress for Bonded Prestressed Concrete Members. *PCI Journal*, 33(6), 108–137.
- Lou, T., Lopes, S. M. R., & Lopes, A. V. (2013). Nonlinear and time-dependent analysis of continuous unbonded prestressed concrete beams. *Computers & Structures*, 119, 166–176.
- Lou, T., & Xiang, Y. (2006). Finite element modeling of concrete beams prestressed with external tendons. *Engineering Structures*.
- Mahin, S., Sakai, J., & Jeong, H. (2006). Use of partially prestressed reinforced concrete columns to reduce post-earthquake residual displacements of bridges. ... *Seismic Conference on Bridges & ...*, 18–20.
- Marovic, P., Nikolic, Ž., & Galic, M. (2005). Some aspects of 2D and/or 3D numerical modelling of reinforced and prestressed concrete structures. *Engineering Computations*, 22(5/6), 684–710.
- Marsono, A., Ying, W., Tap, M., Chieh, Y., & Haddadi, A. (2015). Standard Verification Test for Industrialised Building System (IBS) Repetitive Manufacturing. In *Procedia CIRP 26* (Vol. 26, pp. 252–257).
- Mast, R. (1998). Analysis of cracked prestressed concrete sections: A practical approach. *PCI Journal*, 43(4), 80–91.

- Medland, I. C., & Taylor, D. A. (1971). Flexural rigidity of concrete column sections. *Journal of the Structural Division*, 97(2), 573–586.
- Moazzami, S., & Bertero, V. V. (1987). Three-dimensional inelastic analysis of reinforced concrete frame-wall structure. *College of Engineering, University of California*.
- Morcous, G., Henin, E., Fawzy, F., Lafferty, M., & Tadros, M. K. (2014). A new shallow precast/prestressed concrete floor system for multi-story buildings in low seismic zones. *Engineering Structures*, 60, 287–299.
- Morgen, B., & Kurama, Y. (2004). A friction damper for post-tensioned precast concrete beam-to-column joints. *PCI Journal*, 49(4), 112–133.
- Mostafaei, H., & Vecchio, F. (2008). Uniaxial shear-flexure model for reinforced concrete elements. *Journal of Structural Engineering*, 134(9), 1538–1547.
- Mostafaei, H., Vecchio, F. ., & Kabeyasawa, T. (2009). A simplified axial-shear-flexure interaction approach for load and displacement capacity of reinforced concrete columns. In *ATC & SEI 2009 Conference* (pp. 753–764).
- Moucessian, A., & Campbell, T. (1988). Prediction of the load capacity of two-span continuous prestressed concrete beams. *PCI Journal*, 33(3), 130–151.
- Moustafa, S. (1977). Design of partially prestressed concrete flexural members. *PCI Journal*, 22(1), 12–29.
- Moustafa, S. E. (1986). Nonlinear Analysis of Reinforced and Prestressed Concrete Members. *PCI Journal*, 31(5), 126–147.
- Mullapudi, T., & Ayoub, A. (2012). Analysis of reinforced concrete columns subjected to combined axial, flexure, shear, and torsional loads. *Journal of Structural Engineering*, (April), 561–573.
- Naaman, A. (1977). Ultimate analysis of prestressed and partially prestressed sections by strain compatibility. *PCI Journal*, 22(1), 32–51.
- Naaman, A. (1983). An approximate nonlinear design procedure for partially prestressed concrete beams. *Computers & Structures*, 11(2), 287–299.
- Naaman, A. E., Harajii, M. H., & Wight, J. K. (1986). Analysis of Ductility in Partially Prestressed Concrete Flexural Members. *PCI Journal*, 31(3), 64–87.
- Naaman, A. E., Siriakorn, A., Rao, W. H., Prasada, A., Rajagopalan, K., & Tam, A. (1979). Serviceability based design of partially prestressed beams. *PCI Journal*, 2(24), 64–89.
- Naaman, A., & Hamza, A. (1993). Prestress Losses in Partially Prestressed High Strength Concrete Beams. *PCI Journal*, 38(3), 98–114.
- Navarro Gregori, J., Miguel Sosa, P., Fernández Prada, M. a., & Filippou, F. C. (2007). A 3D numerical model for reinforced and prestressed concrete elements subjected to combined axial, bending, shear and torsion loading. *Engineering Structures*, 29(12), 3404–3419.
- Nawy, E., & Chiang, J. (1980). Serviceability Behavior of Post-Tensioned Beams. *PCI Journal*, 25(1), 75–95.
- Nigam, N. C. (1967). *Inelastic interactions in the dynamic response of structures. Technical Report: Caltech EERL.1967.006*. Pasadena, California.
- Nishiyama, M., & Wei, Y. (2007). Effect of post-tensioning steel anchorage location on seismic performance of exterior beam-to-column joints for precast, prestressed concrete members. *PCI Journal*, 52(2), 18–30.
- Okumus, P., & Oliva, M. (2013). Evaluation of crack control methods for end zone cracking in prestressed concrete bridge girders. *PCI Journal*, 58(2), 91–105.
- Ozkul, O. (2007). *A new methodology for the analysis of concrete beams*

- prestressed with unbonded tendons*. PhD Thesis, Departement of Civil and Environmental Engineering, The State University of New Jersey, USA.
- Park, H.-G., Kang, S., & Choi, K. (2013). Analytical model for shear strength of ordinary prestressed concrete beams. *Engineering Structures*, 46, 94–103.
- Park, R., & Paulay, T. (1975). *Reinforced concrete structures*. John Wiley & Sons.
- Park, R., & Thompson, K. (1977). Cyclic load tests on prestressed and partially prestressed beam-column joints. *PCI Journal*, 22(5), 84–110.
- Park, S., & Naaman, A. (1999). Shear behavior of concrete beams prestressed with FRP tendons. *PCI Journal*, 44(1), 74–85.
- Pellegrino, C., & D'Antino, T. (2013). Experimental behaviour of existing precast prestressed reinforced concrete elements strengthened with cementitious composites. *Composites Part B: Engineering*, 55, 31–40.
- Peterson, D., & Tadros, M. (1985). Simplified Flexural Design of Partially Prestressed Concrete Members. *PCI Journal*, 30(3), 50–69.
- Pisani, M. (2005). Geometrical nonlinearity and length of external tendons. *Journal of Bridge Engineering*, (June), 302–311.
- Pisani, M. (2009). Numerical Analysis of Continuous Beams Prestressed with External Tendons. *Journal of Bridge Engineering*, (April), 93–101.
- Powell, H., & Chen, P. (1986). 3D beam-column element with generalized plastic hinges. *Journal of Engineering Mechanics*, 112(7), 627–641.
- Preciado, A., Sperbeck, S. T., & Ramírez-Gaytán, A. (2016). Seismic vulnerability enhancement of medieval and masonry bell towers externally prestressed with unbonded smart tendons. *Engineering Structures*, 122, 50–61.
- Rahal, K. (2007). Combined torsion and bending in reinforced and prestressed concrete beams using simplified method for combined stress-resultants. *ACI Structural Journal*, (104).
- Rakaa, I. G. P., & Astawaa, M. D. (2014). State-of-the-art report on partially-prestressed concrete earthquake-resistant building structures for highly-seismic region. *Procedia Engineering*, 95(Scescm), 43–53.
- Recupero, A., D'Aveni, A., & Gherzi, A. (2005). Bending Moment–Shear Force Interaction Domains for Prestressed Concrete Beams. *Journal of Structural Engineering*, 131(9), 1413–1421.
- Row, D. G., & Paulay, T. (1973). Biaxial flexure and axial load interaction in short rectangular reinforced concrete columns. *Society for Earthquake Engineering*, 6(3), 110–121.
- Ruiz, M. F., Rupf, M., & Muttoni, A. (2013). Post-tensioned girders with low amounts of shear reinforcement: Shear strength and influence of flanges. In *Engineering structures* (Vol. 56, pp. 357–371).
- Saatcioglu, M. (1984). Computer-aided aseismic design of reinforced concrete structures. *Computer-Aided Analysis and Design of Concrete Structures*, 859.
- Seguirant, S., Brice, R., & Khaleghi, B. (2005). Flexural strength of reinforced and prestressed concrete T-beams. *PCI Journal*, 50(1), 44–73.
- Sen, R., & Jr, D. H. (1990). Ultimate capacity of biaxially prestressed members. *Journal of Structural Engineering*, 116(11), 3020–3038.
- Shushkewich, K. (1990). Moment-curvature relationships for partially prestressed concrete beams. *Journal of Structural Engineering*, 116(10), 2815–2823.
- Skogman, B., Tadros, M., & Grasmick, R. (1988a). Ductility of Reinforced and Prestressed Concrete Flexural Members. *PCI Journal*, 33(6), 94–107.
- Skogman, B., Tadros, M., & Grasmick, R. (1988b). Flexural strength of prestressed

- concrete members. *PCI Journal*, 33(5), 96–123.
- Smith, I. M., & Griffiths, D. V. (2004). Programming the finite element analysis. *ACI Material Journal*, 87(5), 433–439.
- SNI-1726 Committee. (2012). *Seismic-Resistant Design Code for Buildings (SNI 1726:2012)*. Jakarta, Indonesia.
- Spinella, N. (2013). N-M- χ interaction for arbitrary cross section under biaxial bending and axial load. *Pollack Periodica*, 8(3), 87–100.
- Su, X., & Zhu, B. (1994). Algorithm for hysteresis analysis of prestressed-concrete frames. *Journal of Structural Engineering*, 120(6), 1732–1744.
- Tadros, M., Ghali, A., & Dilger, W. (1977). Effect of non-prestressed steel on prestress loss and deflection. *PCI Journal*, 22(2), 50–63.
- Talaeitaba, S., & Torki, M. (2014). Nonlinear finite element analysis of RC beams under combined shear and torsion to extract linear and curvilinear ranges of interaction curves. *SCIENTIA IRANICA*, 21(4), 1249–1262.
- Tanchan, P. (2001). *Flexural Behavior of High Strength Concrete Beams Prestressed with Unbonded Tendons*. PhD Thesis. The State University of NJ, New Brunswick, NJ.
- Thanoon, W. a. (1993). *Inelastic dynamic analysis of concrete frames under non-nuclear blast loading*. PhD Thesis, Departement of Civil Engineering, Roorkee, India.
- Thanoon, W. a., Paul, D. K., Jaafar, M. S., & Trikha, D. N. (2004). Influence of torsion on the inelastic response of three-dimensional r.c. frames. *Finite Elements in Analysis and Design*, 40(5-6), 611–628.
- Thompson, K., & Park, R. (1980). Ductility of Prestressed and Partially Prestressed Concrete Beam Sections. *PCI Journal*, 25(2), 46–70.
- Tseng, W. S., & Penzien, J. (1975a). Seismic analysis of long multiple span highway bridges. *Earthquake Engineering & Structural Dynamics*, 4(1), 1–24.
- Tseng, W. S., & Penzien, J. (1975b). Seismic analysis of long multiple-span highway bridges. *Earthquake Engineering & Structural Dynamics*, 4(1), 1–24.
- Vasdravellis, G., Karavasilis, T. L., & Uy, B. (2013). Finite element models and cyclic behavior of self-centering steel post-tensioned connections with web hourglass pins. *Engineering Structures*, 52, 1–16.
- Vázquez-Herrero, C., Martínez-Lage, I., & Martínez-Abella, F. (2013). Transfer length in pretensioned prestressed concrete structures composed of high performance lightweight and normal-weight concrete. *Engineering Structures*, 56, 983–992.
- Vu, N. a., Castel, A., & François, R. (2010). Response of post-tensioned concrete beams with unbonded tendons including serviceability and ultimate state. *Engineering Structures*, 32(2), 556–569.
- Wang, G., & Hsu, C. (1992). Complete Biaxial Load-Deformation Behavior of RC Columns. *Journal of Structural Engineering*, 118(9), 2590–2609.
- Wu, X., & Lu, X. (2002). Tendon model for nonlinear analysis of externally prestressed concrete structures. *Journal of Structural Engineering*, (January), 96–104.
- Wu, X., Otani, S., & Shiohara, H. (2001). Tendon model for nonlinear analysis of prestressed structures. *Journal of Structural Engineering*, (April), 398–405.
- Xue, W., Cheng, B., Zheng, R., Li, L., & Li, J. (2010). Seismic Performance of

- Nonprestressed and Prestressed HPC Frames under Low Reversed Cyclic Loading. *Journal of Structural Engineering*, 137(11), 1254–1262.
- Yang, K.-H., Mun, J.-H., & Kim, G.-H. (2013). Flexural behavior of post-tensioned normal-strength lightweight concrete one-way slabs. *Engineering Structures*, 56, 1295–1307.
- Yee, P., & Adnan, A. (2011). Performance of IBS Precast Concrete Beam-Column Connections Under Earthquake Effects: A Literature Review. *American J. of Engineering and Applied Sciences*, 4(1), 93–101.
- Zhang, J., & Xu, S.-Y. (2009). Seismic response simulations of bridges considering shear-flexural interaction of columns. *Structural Engineering and Mechanics*, 31(5), 545–566.

