



UNIVERSITI PUTRA MALAYSIA

***COCONUT PULP WASTE EXTRACT (*Cocos nucifera* L.) AS
CORROSION INHIBITOR FOR MILD STEEL IN 1.0 M ACID CORROSION***

NORIN HAFIZAH BINTI RAHIM

FK 2017 58



**COCONUT PULP WASTE EXTRACT (*Cocos nucifera* L.) AS CORROSION
INHIBITOR FOR MILD STEEL IN 1.0 M ACID CORROSION**

By

NORIN HAFIZAH BINTI RAHIM

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in
Fulfilment of the Requirements for the Degree of Master of Science**

April 2017

COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Master of Science

COCONUT PULP WASTE EXTRACT (*Cocos nucifera* L.) AS CORROSION INHIBITOR FOR MILD STEEL IN 1.0 M ACID CORROSION

By

NORIN HAFIZAH BINTI RAHIM

April 2017

Chairman : Shafreeza Binti Sobri, PhD
Faculty : Engineering

Corrosion control method, especially the use of inhibitors has gained monumental importance nowadays. The demand for green inhibitor to replace toxic one has increased tremendously. The use of local wastes which are organic in nature for the production of green corrosion inhibitor is no doubt the trend of the day. To arrive at an inexpensive, non-toxic and eco-friendly inhibitor formulation, the present study on the use of coconut pulp waste extract of *Cocos nucifera* L. has been carried out. Coconut pulp waste were chosen to be extracted and investigated in terms of their corrosion inhibition efficiencies for mild steel in 1.0 M HCl using weight loss analysis at different inhibitor concentrations and immersion time, tafel polarization curve and impedance curve at different inhibitor concentrations. The interaction between inhibitor and specimen surface was study using Langmuir, Freundlich and Temkin adsorption isotherms. Weight loss measurement were conducted at different of immersion time which is at 6, 12, 18, 24 and 48 hours. Result from weight loss study showed that as the concentration of the inhibitor increases, the rate of corrosion decreases. It also showed that as the concentration of the inhibitor increases, the inhibition efficiency also increases up to 94.52 %. Further examination study using scanning electron microscopy (SEM) showed the deposition of coconut pulp extract on the metal surface. In potentiodynamic polarization method and electrochemical impedance spectroscopy the electrochemical measurement were carried out using Autolab Potentiostat/Galvonastat. The experiments were conducted using 250 ml of electrolyte (1 M HCl) without and with different concentrations of the extracts of 2, 4, 6, 8, and 10 % v/v. The obtained inhibition efficiencies of extracts from polarization measurements was 89.38 % and 83.47 % from the impedance measurement. The impedance measurement revealed that when the concentration of the coconut pulp increased the charge transfer resistance increased and the double layer capacitance decreased. In polarization measurement the value from corrosion current E_{corr} suggested that coconut pulp extract is a mixed type nature of the inhibitor molecules. The adsorption interaction between the corrosion inhibitor with mild steel surface obey the Langmuir adsorption isotherm as the value of the correlation coefficient (R^2) is very near to unity. From the value of free energy of adsorption ($\Delta G^{\circ}_{\text{ads}}$) showed a spontaneous adsorption and physisorption process is occurred.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains

EKSTRAK HAMPAS KELAPA (*Cocos nucifera* L.) SEBAGAI PERENCAT KAKISAN KEPADA KELULI LEMBUT DALAM 1.0 M LARUTAN ASID

Oleh

NORIN HAFIZAH BINTI RAHIM

April 2017

Pengerusi : Shafreeza Binti Sobri, PhD
Fakulti : Kejuruteraan

Kaedah kawalan hakisan, terutamanya penggunaan perencat telah meraih perhatian penting pada masa kini untuk menggantikan perencat yang bertoksik kepada mesra alam. Penggunaan bahan buangan yang organik secara semulajadi untuk menghasilkan perencat mesra alam adalah tidak lagi meragukan. Untuk mencapai satu formulasi perencat yang murah, tidak mengandungi toksik dan mesra alam, kajian menggunakan ekstrak hampas kelapa telah di jalankan. Kelapa sisa pulpa telah dipilih untuk diekstrak dan disiasat dari segi kecekapan perencatan kakisan untuk keluli lembut dalam 1.0 M HCl menggunakan kaedah penurunan berat pada masa rendaman dan berbeza kepekatan perencat, polarisasi tafel dan impedans pada berbeza kepekatan perencat. Interaksi antara permukaan keluli lembut dan perencat juga di siasat menggunakan Langmuir, Freundlich dan Temkin penjerapan isoterma. Pengukuran berat badan telah dijalankan di masa yang berbeza rendaman iaitu pada 6, 12, 18, 24 dan 48 jam. Dalam kaedah penurunan berat, spesimen direndam dalam 100 ml elektrolit (1.0 M HCl) tanpa dan dengan kepekatan yang berbeza daripada ekstrak 2, 4, 6, 8, dan 10 v/v%. Keputusan daripada kajian penurunan berat menunjukkan bahawa bertambah kepekatan perencat, kadar kakisan berkurangan. Ia juga menunjukkan bahawa bertambah kepekatan perencat, kecekapan perencatan juga meningkat sehingga 94.52%. Kajian pemeriksaan lanjut dengan menggunakan mikroskop elektron pengimbas (SEM) menunjukkan bahawa pemendapan ekstrak pulpa kelapa pada permukaan logam. Autolab Potentiostat / Galvonastat di gunakan dalam kaedah polarisasi potentiodynamic dan elektrokimia impedans spektroskopi. Kajian ini telah dijalankan dengan menggunakan 250 ml elektrolit (1 M HCl) tanpa dan dengan kepekatan yang berbeza daripada ekstrak 2, 4, 6, 8, dan 10 v/v%. Kecekapan perencatan diperolehi daripada ekstrak dari ukuran polarisasi adalah 89.38% dan 83.47% dari pengukuran galangan. Pengukuran impedance menunjukan kepekatan pulpa kelapa meningkat rintangan pemindahan caj meningkat dan lapisan kemuatan double menurun. Dalam pengukuran polarisasi nilai daripada E_{corr} semasa kakisan mencadangkan bahawa ekstrak pulpa kelapa adalah sejenis sifat campuran molekul inhibitor. Interaksi penjerapan antara perencat dan permukaan keluli lembut adalah mematuhi penjerapan Langmuir di mana nilai pekali korelasi adalah sangat hampir dengan satu. Daripada nilai tenaga bebas penjerapan (ΔG°_{ads}) menunjukkan penjerapan dan physisorption proses spontan yang berlaku.

ACKNOWLEDGEMENTS

Firstly, I would like to express my sincere gratitude to my supervisor Dr Shafreeza binti Sobri for the supervision of my master for her patience, motivation, and immense knowledge. Her guidance helped me in all the time of research and writing of this thesis. Furthermore, I would like to thank the rest co-supervisors, Assoc. Prof. Dr Zurina Binti Zainal Abidin and Assoc. Prof. Dr Janet Lim Hong Ngee for their generous support, encouragement and opinion.

I would like also to thank to University Putra Malaysia (UPM) for the Fundamental Research Grant Scheme (FRGS), The Ministry of Higher Education and Universiti Teknologi Mara (UiTM) for a scholarship for the financial support for my graduates study.

Finally, I would like to thank my family, to my parents, siblings and my spouse for providing me with unfailing support and continuous encouragement throughout my years of study and through the process of researching and writing this thesis. This accomplishment would not have been possible without them.

Thank you.

I certify that a Thesis Examination Committee has met on April 27, 2017 to conduct the final examination of Norin Hafizah Binti Rahim on her thesis entitled “Coconut Pulp Waste Extract (*Cocos nucifera* L.) As Corrosion Inhibitor For Mild Steel In 1.0 M Acid Corrosion” in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Master of Science.

Members of the Thesis Examination Committee were as follows:

Rozita Omar, PhD

Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Dayang Radiah Awang Biak, PhD

Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Yusairie Mohd, PhD

Senior Lecturer
Faculty of Applied Sciences
Universiti Teknologi Mara (UiTM)
Shah Alam, Selangor
Malaysia
(External Examiner)

NOR AINI BINTI AB SHUKOR, PhD

Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 8 August 2017

This thesis was submitted to the Senate of University Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows:

Shafreeza Sobri, PhD

Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Zurina Zainal Abidin, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Janet Lim Hong Ngee, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____
Name of
Chairman of
Supervisory
Committee: Shafreeza Sobri

Signature: _____
Name of
Member of
Supervisory
Committee: Zurina Zainal Abidin

Signature: _____
Name of
Member of
Supervisory
Committee: Janet Lim Hong Ngee

TABLE OF CONTENTS

ABSTRACT	Page
<i>ABSTRAK</i>	i
ACKNOWLEDGEMENTS	ii
APPROVAL	iii
DECLARATION	iv
LIST OF ABBREVIATIONS	v
LIST OF SYMBOLS	x
LIST OF FIGURES	xi
LIST OF TABLES	xiii
	xvi

CHAPTER

1	INTRODUCTION	
	1.1 Background of study	1
	1.2 Problem statement	2
	1.3 Significance of the research	2
	1.2 Objectives	3
	1.3 Scope of study	3
2	LITERATURE REVIEW	
	2.1 Corrosion Definition	4
	2.2 Corrosion Rate	4
	2.3 Types of corrosion	4
	2.3.1 Wet corrosion	5
	2.3.2 Dry corrosion	5
	2.4 Classification of corrosion	7
	2.5 Corrosion control and prevention	9
	2.6 Definition of corrosion inhibitor	10
	2.7 Inorganic Inhibitor (Anodic inhibitor/Cathodic inhibitor)	10
	2.8 Organic Inhibitor	10
	2.8.1 Natural/Green inhibitor	11
	2.8.2 Chemical/Synthetic inhibitor	13
	2.9 Mixed inhibitor	13
	2.10 Inhibitor in acid solutions	14
	2.11 Mechanism inhibition in electrochemical study	15
	2.12 Adsorption mechanism in corrosion inhibition	15
	2.13 Adsorption isotherm and surface coverage	16
	2.13.1 Langmuir Isotherm	16
	2.13.2 Temkin Isotherm	17
	2.13.3 Freundlich Isotherm	17
	2.14 Adsorption of corrosion inhibitors onto metals	17
	2.15 Structural characterizatio in coconut pulp waste extract	18
	2.16 Mild Steel	21
	2.17 Mild steel in acid media	22
	2.18 Mild steel corrosion	22

3	METHODOLOGY	
3.1	Chemical and Reagent	23
3.2	Instrumentation	23
3.2.1	SEM and EDX analysis	23
3.2.2	Fourier Transform Infrared Spectroscopy (FTIR)	24
3.2.3	Autolab Potentiostat/Galvonostat	24
3.3	Preparation of Corrosion Inhibitor (Coconut Pulp Extract)	24
3.4	Preparation of the mild steel specimen	26
3.5	Preparation of Acid Media and Inhibitor Solution	26
3.6	Physical characterization of coconut pulp extract	26
3.7	Weight Loss Analysis	26
3.8	Electrochemical Analysis	27
3.8.1	Potentiodynamic Polarization Measurement	27
3.8.2	Electrochemical Impedance Spectroscopy (EIS)	28
3.9	Thermodynamic and kinetic study	30
3.10	Summary of the methodology	31
4	RESULTS AND DISCUSSION	
4.1	Characterization of coconut pulp powder and extract	32
4.2	Weight Loss study	35
4.2.1	Effects of Concentration Inhibitor	36
4.2.2	Effects of Immersion Time	39
4.3	Electrochemical Study	41
4.3.1	Potentiodynamic Polarization Measurement	41
4.3.2	Electrochemical Impedance Spectroscopy (EIS)	44
4.4	Adsorption Isotherm	46
4.4.1	Langmuir isotherm	46
4.4.2	Temkin isotherm	49
4.4.3	Freundlich isotherm	51
4.5	Behaviour of adsorption isotherm	53
4.6	SEM and EDX studies	53
5	CONCLUSION	
5.1	Conclusion	56
5.2	Recommendation	56
	REFERENCES	57
	APPENDICES	65
	BIODATA OF STUDENT	69
	LIST OF PUBLICATIONS	70

LIST OF ABBREVIATIONS

AC	Alternating-current
C_{inh}	Corrosion Inhibitor
CPE	Constant phase element
CR	Corrosion rate
E_a	Activation Energy
IE	Inhibition efficiency
IE %	Percentage of inhibition efficiency
OCP	Open circuit potential
Pt	Platinum electrode
R	Gas constant
v/v %	Volume per volume percent

LIST OF SYMBOLS

$^{\circ}\text{C}$	Degree celsius
A	Ampere
Ag/AgCl	Silver/Silver chloride
β_a	Anodic tafel slope
β_c	Cathodic tafel slope
C	Concentration
C_{dl}	Double layer capacitance
cm	Centimeter
cm^2	Centimeter square
E_{corr}	Corrosion potential
f_{max}	The frequency at the apex of the Nyquist plot
g	Gram
$\text{g cm}^{-2} \text{h}^{-1}$	Gram per square centimeter hour
g cm^{-3}	Gram per cubic centimeter
HCl	Hydrochloric acid
I^0_{corr}	Corrosion current density value without extract
I^i_{corr}	Corrosion current density value with extract
K^{-1}	Kelvin ⁻¹
kJ/mol	Kilojoules per mole

m^2	Meter square
mm/year	Millimeter per year
mV	Millivolt
mV dec ⁻¹	Millivolt per decade
mV/s	Millivolt per second
R	Gas constant
R'_{ct}	Charge transfer resistance in the absence of extract
R^0_{ct}	Charge transfer resistance in the presence of extract
R^2	Correlation coefficient
R_{ct}	Resistance of charge transfer
R_s	Resistance of solution
V	Volt
W_0	The weight loss values in the absence of inhibitor
W_i	The weight loss values in the presence of inhibitor
ΔG°_{ads}	Free energy of adsorption
θ	Degree of surface coverage
μA	Microampere
$\mu A\ cm^{-2}$	Microampere per square centimeter
$\mu F/cm^2$	Micro farad centimeter square
$\Omega\ cm^2$	Ohm centimeter square

LIST OF FIGURES

Figure	Page
2.1 Flow chart of corrosion prevention	9
2.2 Illustration of the mechanism organic inhibitor through adsorption of the inhibitor on the metal surface.	15
2.3 Ferrous Classification	21
3.1 Flow diagram of preparation of corrosion inhibitor	25
3.2 Flow chart of the weight loss study	27
3.3 Summary of potentiodynamic polarization measurement	28
3.4 Summary of Electrochemical impedance spectroscopy (EIS) measurement	29
3.5 Equivalent circuit model for Nyquist plot	30
3.6 Flow diagram of the experimental processes involved during this research	31
4.1 FTIR spectrum of coconut pulp powder	32
4.2 FTIR spectrum of extract of coconut pulp extract	33
4.3 FTIR spectrum of <i>Areca catechu</i> extract	34
4.4 Graph of weight loss against concentration of coconut pulp extract for mild steel in 1.0 M HCl at different time of immersion at temperature 25°C	37

4.5	Graph of corrosion rate against concentration of coconut pulp extract for mild steel in 1.0 M HCl at different time of immersion at temperature 25°C	37
4.6	Graph of IE % against concentration of coconut pulp extract for mild steel in 1.0 M HCl at different time of immersion at temperature 25°C	38
4.7	Graph of weight loss against time of immersion for mild steel in 1.0 M HCl at different concentration of coconut pulp extract at temperature 25°C	39
4.8	Graph corrosion rate against time of immersion for mild steel in 1.0 M HCl at different concentration of coconut pulp extract at temperature 25°C	40
4.9	Graph Inhibition efficiency (IE %) against time of immersion for mild steel in 1.0 M HCl at different concentration of coconut pulp extract at temperature 25°C	41
4.10	Potentiodynamic polarization parameter curves for different concentration of coconut pulp extract of mild steel in 1M HCl.	42
4.11	Graph of IE % against concentration of coconut pulp extract for mild steel in 1.0 M HCl at different concentration of inhibitor in the potentiodynamic study	43
4.12	Nyquist plot for mild steel in the different concentration of coconut pulp extract in 1M HCl	44
4.13	Graph of IE % against concentration of coconut pulp extract for mild steel in 1.0 M HCl at different concentration of inhibitor in the EIS study	45
4.14	Langmuir adsorption isotherm for mild steel in 1M HCl containing different concentration of coconut pulp extract at 6-48 hours by weight loss study	47

4.15	Langmuir adsorption isotherm for mild steel in 1M HCl containing different concentration of coconut pulp extract by EIS Method and Potentiodynamic Method.	48
4.16	Temkin adsorption isotherm for mild steel in 1M HCL containing different concentration of coconut pulp extract at 6-48 hours by weight loss study	49
4.17	Temkin adsorption isotherm for mild steel in 1M HCL containing different concentration of coconut pulp extract by EIS Method and Potentiodynamic Method.	50
4.18	Freundlich adsorption isotherm for mild steel in 1M HCl containing different concentration of coconut pulp extract at 6-48 hours by weight loss study	51
4.19	Freundlich adsorption isotherm for mild steel in 1M HCl containing different concentration of coconut pulp extract by EIS Method and Potentiodynamic Method.	52
4.20	(a) SEM micrograph and (b) EDX spectra of polished mild steel surface	54
4.21	(a) SEM micrograph and (b) EDX spectra of mild steel in 1.0 M HCl	54
4.22	(a) SEM micrograph and (b) EDX spectra of mild steel in 10 %v/v concentration inhibitor	54

LIST OF TABLES

Table	Page
2.1 Comparison between wet corrosion and dry corrosion	6
2.2 Classification of corrosion	7
2.3 Previous study on the green inhibitor	11
2.4 Characteristic IR absorption	18
2.5 Previous study of active compound in the green inhibitor	20
4.1 Inhibition efficiencies, degree of surface coverage θ , corrosion rates and weight loss of mild steel in 1.0 M HCl	35
4.2 Potentiodynamic polarization parameter for different concentration of coconut pulp extract of mild steel in 1M HCL.	42
4.3 Electrochemical impedance parameters for different concentration of coconut pulp extract of mild steel in 1M HCL.	45
4.4 Free energy of adsorption (ΔG°_{ads}) of Langmuir isotherm at different concentration of coconut pulp extract on mild steel surface in 1 M HCl at 6-48 hours by weight loss study	47
4.5 Free energy of adsorption (ΔG°_{ads}) Langmuir Isotherm at different concentration of coconut pulp extract on mild steel surface by EIS Method and Potentiodynamic Method.	48
4.6 Free energy of adsorption (ΔG°_{ads}) of Temkin isotherm at different concentration of coconut pulp extract on mild steel surface in 1 M HCl at 6-48 hours by weight loss study	49
4.7 Free energy of adsorption (ΔG°_{ads}) of Temkin Isotherm at different concentration of coconut pulp extract on mild steel surface by EIS Method and Potentiodynamic Method.	50

4.8	Free energy of adsorption ($\Delta G^{\circ}_{\text{ads}}$) of Freundlich isotherm at different concentration of coconut pulp extract on mild steel surface in 1 M HCl at 6-48 hours by weight loss study	51
4.9	Free energy of adsorption ($\Delta G^{\circ}_{\text{ads}}$) of Freundlich Isotherm at different concentration of coconut pulp extract on mild steel surface by EIS Method and Potentiodynamic Method.	52
4.10	EDX analysis of mild steel in 1.0 M HCl in the absence and presence of concentration inhibitor	53





CHAPTER 1

INTRODUCTION

1.1 Background of study

In recent years, mild steel is widely used in the engineering material of construction industry because of its excellent in mechanical properties, easy fabrication and also very economical compared to other metallic materials. Often, mild steel is used in the fabrication of reaction vessel and storage tanks (Kamal & Sethuraman, 2012). Meanwhile hydrochloric acid (HCl) acid is broadly utilized in several industries as pickling of steel, production of inorganic and organic compound, oil well acidification, descaling and cleaning agents to remove the unwanted oxide films and corrosion products (Afia et al., 2012; Chen et al., 2013). Compared to other mineral acids, HCl is generally used because of its benefits which are low cost, productive and straightforward (Gopiraman et al., 2012).

In the presence of acid, mild steel will corrode easily especially in petrochemical industries which is in cleaning process, the reaction between the hydrochloric acid and the mild steel will form a corrosion (Anupama et al., 2015). Another example is the removal of harmful rust in some industrial processes which is carried out by mainly acid pickling using hydrochloric acid solution. Thus, corrosion caused by mild steel in the presence of acidic solution need to be solved and overcome as it is the main concern nowadays (Li et al., 2009).

The effects of the corrosion on the environment is important and need to be addressed because the corrosion problem have become worldwide. Corrosion can cause adverse impact on the industry and effect economic losses due to cost needed for replacement of affected equipment and structure for repairing purpose (Al-amiery et al., 2015). These effects of corrosion affect the economy as well as can give some negative implications to people working in the industry and the area nearby. The example of an industry that is affected by the corrosion is the petroleum industry and it also is estimated that the corrosion costs 2.5 billion dollar/annum loss (Afia et al., 2014).

To overcome the effects of corrosion, many methods have been used to protect the metals, but among the method the use of inhibitor is very famous because of it is easy to apply (Raja & Sethuraman, 2008). Inhibitors are substances that decelerate the rate of corrosion (Rajalakshmi & Safina, 2012). Good inhibitors contain heterocyclic compounds containing O, S and N as heteroatoms (Kamal & Sethuraman, 2012). The utilization of inhibitors in slowing down the rate of corrosion has turned out to be proficient and generally practicable. Nonetheless, most of the compounds that build this inhibitor are toxic to the environments and human (Bhawsar, 2015). Due to the toxicity of these inhibitor, researchers have discovered other alternative to replace the toxic inhibitor. This is called green inhibitor which are non- toxic and not harmful to the environment (Sangeetha et al., 2011). In addition, due to the high operating cost of

synthetic inhibitor and its environmental effects, the research findings show the synthetic corrosion inhibitor cannot be utilized (Kamal & Sethuraman, 2012). As result of that, there are research being carried out recently to find the potential use of green corrosion inhibitor (Ji et al., 2015). The utilization of natural product to protect metal against corrosion has become popular and there are many reports on the effectiveness of the natural product in the inhibition of the metal in various acid media. The source of the natural product comes from fruits, plants and their peels which are a very good source for active organic compound (Muthukrishnan et al., 2015). Therefore, the utilization of natural product is not only low cost but also is environment friendly (Kamal & Sethuraman, 2012).

The research on the natural products as green inhibitor for corrosion inhibitor is an important field to study due to eco-friendly and the source of the natural products are cheap, readily available, and ecologically acceptable (Abdel-Gaber et al., 2006). Recent literature study shows that green inhibitor are found in natural product and proved to be effective against corrosion. These product among them are spirulina plantesis (Kamal & Sethuraman, 2012), litchi (Ramananda Singh et al., 2015), watermelon rind (Odewunmi et al., 2014), mangrove tannin (Shah et al., 2013), turmeric and ginger (Aziz & Sirat, 2015), apricot juice (Yaro et al., 2013). As a result, researchers have come up with a good number of naturally occurring substances which can be used as inhibitors for metals corrosion in different aggressive mediums.

In the present study, the selected natural product which is a waste from coconut pulp of *Cocos nucifera L* is examined for its potential to inhibit corrosion of mild steel in acid media. Furthermore there are no recent study about this natural product on the reported literature. *Cocos nucifera L* is an unbranched monoecious plant of the Palmae family. Coconut is one of the key plantation crops of the tropics which is a member of the monocotyledonous family Aracaceae (Yong et al., 2009).

1.2 Problem statement

In recent years, industrial sectors are concerned with the corrosion of metal and alloys and they also received huge attention from researcher to overcome these problems (Alamiery et al., 2015). To decelerate the rate of corrosion or to stop the corrosion to occur, it has become an interesting and comprehensive field to be explored and studied. One of the common methods to deal with this problems is using the chemical inhibitor. The chemical inhibitor derived from the compound of synthetic origins has their own limitation which is not environmental friendly (Afia et al., 2014). Furthermore, due to the increasing of ecological awareness and the rigid environmental regulation, researchers begin to find other alternative methods to substitute the inhibitor from the hazardous to the eco-friendly inhibitor (Kamal & Sethuraman, 2012). Natural products are cheap and environmental safe. Hence, the benefits of using natural product extracts as corrosion inhibitors is welcome as they are environmental friendly. The extracts of the plant products are heteroatoms groups, molecular and electronic structures which show close similarity to those of conventional organic inhibitor molecules that serve as corrosion inhibitor (Özcan et al., 2008).

1.3 Significance of the research

As mentioned above, industrial sectors are affected due to corrosion. Therefore, the use of natural inhibitor rather than synthetic inhibitor is the best solution to overcome or minimizing the corrosion. In this research, the waste from coconut pulp was used as corrosion inhibitor for mild steel in acid solution. The coconut pulp extract which is from waste is very valuable and the cost of materials is very low. It shows environmentally safe besides materials are eco-friendly (Yaro et al., 2013). Here trash is being used to create wealth. Therefore, the findings of this research will give beneficial for all industries that use mild steel under corrosive media. As a consequence, this research brings benefits which is environmentally safe and it is applicable to all industries to decelerate the corrosion.

1.4 Objectives

The objectives of the research are:

- 1 To evaluate the inhibition efficiency of coconut pulp waste extract as corrosion inhibitor in 1.0 M HCl using weight loss analysis (at different inhibitor concentrations and immersion time), tafel polarization curve and impedance curve (at different inhibitor concentrations).
- 2 To study the interaction between inhibitor and specimen surface using Langmuir, Freundlich and Temkin adsorption isotherms.

1.5 Scope of study

The scope of this study focuses on the inhibitive properties of waste product of coconut pulp (*Cocos nucifera* L.) in acid media on mild steel in 1.0 M HCl. In this research, there are divided and focused into 5 parts. Firstly is the preparation and characterization of active compound of inhibitor in coconut pulp waste extract. The coconut pulp waste extract was prepared from the waste material of coconut pulp to a powder form before reflux process. The functional group contained in the coconut pulp waste was identified using FTIR analysis. Secondly is the weight loss study to know the inhibition efficiency of the mild steel in 1.0M HCl at different concentration of inhibitor and time of immersion. Different concentration of 2, 4, 6, 8, and 10 % v/v of coconut pulp extract were used at different time immersion at 6, 12, 18, 24, and 48 hours. Results from the weight loss analysis were used to study the interaction between inhibitor and mild steel surface. There are three types of different isotherms were studied namely langmuir, freundlich and temkin isotherms. Electrochemical measurement which is tafel polarization curve and impedance curve were recorded using a three-electrode cell by Autolab potentiostat. Lastly it is to study and compare the morphology of the surface with and without the presence of inhibitor using SEM and EDX analysis.

REFERENCES

- Afia, L., Benali, O., Salghi, R., Ebenso, E. E., Jodeh, S., Zougagh, M., & Hammouti, B. (2014). Steel corrosion inhibition by acid garlic essential oil as a green corrosion inhibitor and sorption behavior. *International Journal of Electrochemical Science*, 9(12), 8392–8406.
- Afia, L., Salghi, R., Bazzi, E. H., Zarrouk, A., Hammouti, B., Bouri, M., Bammou, L. (2012). Argan hulls extract: green inhibitor of mild steel corrosion in 1 M HCl solution. *Research on Chemical Intermediates*, 38(8), 1707–1717.
- Al-amiry, A. A., Al-majedy, Y. K., Kadhum, A. A. H., & Mohamad, A. B. (2015). New Coumarin Derivative as an Eco-Friendly Inhibitor of Corrosion of Mild Steel in Acid Medium, *Molecules*, 20, 366–383.
- Anagement, M., Al-haj-ali, A. M., Jarrah, N. A., Azu, N. D. M. U., & Rihan, O. (2014). Thermodynamics and Kinetics of Inhibition of Aluminum in Hydrochloric Acid by Date Palm Leaf Extract. *Journal Of Applied Science And Environmental*, 18(3), 543–551.
- Anupama, K. K., Ramya, K., Shainy, K. M., & Joseph, A. (2015). Adsorption and electrochemical studies of Pimenta dioica leaf extracts as corrosion inhibitor for mild steel in hydrochloric acid. *Materials Chemistry and Physics*, 167, 28–41.
- Anupama, K. K., & Abraham, J. (2012). Electroanalytical studies on the corrosion inhibition behavior of guava (Psidium guajava) leaves extract on mild steel in hydrochloric acid. *Research on Chemical Intermediates*, 39(9), 4067–4080.
- Asworth, V., Booker, C., Charlton, H., & Fairhurst, J. (2012). A Short Introduction To Corrosion and Its Control Corrosion of Metals and Its Prevention. *Corrosion&Protection*, 1–9.
- Aziz, M., & Sirat, H. M. (2015). Turmeric And Ginger As Green Inhibitors Of Mild Steel Corrosion In Acidic Medium. *Journal of Material and Environmental Science*, 6(5), 1480–1487.
- Abdel-Gaber, A. M., Abd-El-Nabey, B. A., Sidahmed, I. M., El-Zayady, A. M., & Saadawy, M. (2006). Inhibitive action of some plant extracts on the corrosion of steel in acidic media. *Corrosion Science*, 48(9), 2765–2779.
- B.G.Clubley. (1988). Chemical Inhibitors for Corrosion Control: The Proceedings of an

International Symposium, Organized by the Industrial Division of the Royal Society of Chemistry and the Institution of Corrosion Science and Technology, University of Manchester, 21st-22nd April 1988.

Banerjee, S., Srivastava, V., & Singh, M. M. (2012). Chemically modified natural polysaccharide as green corrosion inhibitor for mild steel in acidic medium. *Corrosion Science*, 59, 35–41.

Bentiss, F., Traisnel, M., Gengembre, L., & Lagrenée, M. (1999). New triazole derivative as inhibitor of the acid corrosion of mild steel: Electrochemical studies, weight loss determination, SEM and XPS. *Applied Surface Science*, 152, 237–249.

Bhawsar, J. (2015). Experimental and computational studies of Nicotiana tabacum leaves extract as green corrosion inhibitor for mild steel in acidic medium. *Alexandria Engineering Journal*, 54(3), 769–775.

Bothi, P., Kaleem, A., Abdul, A., Osman, H., & Awang, K. (2013). Neolamarckia cadamba alkaloids as eco-friendly corrosion inhibitors for mild steel in 1 M HCl media. *Corrosion Science*, 69, 292–301.

Chen, G., Zhang, M., Pang, M., Hou, X., Su, H., & Zhang, J. (2013). Extracts of Punica granatum Linne husk as green and eco-friendly corrosion inhibitors for mild steel in oil fields. *Research on Chemical Intermediates*, 39, 3545–3552.

Craig, B., & Pohlman, S. L. (1992). Forms of Corrosion. *ASM Metals Handbook - Vol. 13*.

Coates, J. (2006). Interpretation of Infrared Spectra, A Practical Approach. *Encyclopedia of Analytical Chemistry*, 1–23. Newtown, USA.

Dasami, P. M., Parameswari, K., & Chitra, S. (2015). Corrosion inhibition of mild steel in 1M H₂SO₄ by thiadiazole Schiff bases. *Measurement*, 69, 195–201.

Ding, S., Chang, B., Wu, C., Lai, M., & Chang, H. (2005). Electrochemical Evaluation Of Avidin-Biotin Interaction On Self-Assembled Gold Electrodes. *Electrochimica Acta*. 50, 3660–3666.

Dong-dong, L., & Yong-mei, F. (2008). Construction and Characterization of a cDNA Library from the Pulp of Coconut (Cocos nucifera L.). *Agricultural Sciences in China*, 7(September), 1071–1076.

- El-lateef, H. M. A. (2015). Experimental and computational investigation on the corrosion inhibition characteristics of mild steel by some novel synthesized imines in hydrochloric acid solutions. *Corrosion Science*, 92, 104–117.
- Elbouchtaoui, M. C., Anejjar, A., Salghi, R., Chebli, B., Hassani, L. M. I., Hmamouchi, M., & Hammouti, B. (2014). Inhibition of steel corrosion in 1 M HCl by the essential oil of *Thymus pallidus*. *Der Pharma Chemica*, 6(4), 406–414.
- Ghosh, K. S., Maiti, T. K., & Dasgupta, S. (2004). Green tea polyphenols as inhibitors of ribonuclease A. *Biochemical and Biophysical Research Communications*, 325, 807–811.
- Gopiraman, M., Sakunthala, P., Kesavan, D., Alexramani, V., Kim, I. S., & Sulochana, N. (2012). An investigation of mild carbon steel corrosion inhibition in hydrochloric acid medium by environment friendly green inhibitors. *Journal of Coatings Technology and Research*, 9(1), 15–26.
- Hamdaoui, O., & Naffrechoux, E. (2007). Modeling of adsorption isotherms of phenol and chlorophenols onto granular activated carbon. Part I. Two-parameter models and equations allowing determination of thermodynamic parameters. *Journal of Hazardous Materials*, 147(1-2), 381–394.
- Helen, L. Y. S., Rahim, A. A., Saad, B., Saleh, M. I., & Raja, P. B. (2014). Aquilaria Crassna Leaves Extracts – a Green Corrosion Inhibitor for Mild Steel in 1 M HCl Medium. *International Journal of Electrochemical Science*, 9, 830–846.
- Hussin, M. H., & Kassim, M. J. (2010). Electrochemical Studies of Mild Steel Corrosion Inhibition in Aqueous Solution by Uncaria gambir Extract. *Journal of Physical Science*, 21(1), 1-13.
- Ibrahim, T. H., & Zour, M. A. (2011). Corrosion Inhibition of Mild Steel using Fig Leaves Extract in Hydrochloric Acid Solution. *International Journal of Electrochemical Science*, 6(12), 6442.
- Ibrahim, M., Nada, A., Kamal, D. E., & Richardson, J. (2005). Density functional theory and FTIR spectroscopic study of carboxyl group. *Indian Journal of Pure & Applied Physics*, 3610(December), 911–917.
- Jackson, J. (2014). Application of corrosion inhibitors for steels in acidic media for the oil and gas industry : A review. *Corrosion Science*, 86, 17–41.
- Ji, G., Anjum, S., Sundaram, S., & Prakash, R. (2015). Musa paradisica peel extract as

- green corrosion inhibitor for mild steel in HCl solution. *Corrosion Science*, 90, 107–117.
- Kamal, C., & Sethuraman, M. G. (2012). Spirulina platensis as A novel green inhibitor for acid corrosion of mild steel. *Arabian Journal of Chemistry*, 5, 155–161.
- Kamal, C., & Sethuraman, M. G. (2013). Hydroclathrus clathratus marine alga as a green inhibitor of acid corrosion of mild steel. *Research on Chemical Intermediates*, 39(8), 3813–3828.
- Kassim, M. J., & Wei, T. K. (2012). Plants Polyphenols : An Alternative Corrosion Inhibitor Source for Green, 2(2), 22–24. The Proceedings of 2nd Annual International Conference Syiah Kuala University 2012 & 8th IMT-GT Uninet Biosciences Conference Banda Aceh.
- Kanayo, K., Joseph, S., & Tomi, O. (2016). Corrosion inhibition and adsorption mechanism studies of Hunteria umbellata seed husk extracts on mild steel immersed in acidic solutions. *Alexandria Engineering Journal*, 55(1), 673–681.
- Karthik, G., & Sundaravadivelu, M. (2015). Studies on the inhibition of mild steel corrosion in hydrochloric acid solution by atenolol drug. *Egyptian Journal of Petroleum*.
- Kumar, K. P. V., Pillai, M. S. N., & Thusnavis, G. R. (2010). Inhibition of mild steel corrosion in Hydrochloric acid by the seed husk extract of Jatropha curcas, 1(2), 119–128.
- Kuznetsov, V., Maljusch, A., Souto, R. M., Bandarenka, A. S., & Schuhmann, W. (2014). Electrochemistry Communications Characterisation of localised corrosion processes using scanning electrochemical impedance microscopy. *Electrochemistry Communications*, 44, 38–41.
- Li, X., Deng, S., Fu, H., & Li, T. (2009). Adsorption and inhibition effect of 6-benzylaminopurine on cold rolled steel in 1.0 M HCl. *Electrochimica Acta*, 54(16), 4089–4098.
- Maa, P. (2011). Corrosion and Corrosion Protection. Handbook of Hot-dip Galvanization. Weinheim
- Mittal, A., Kurup, L., & Mittal, J. (2007). Freundlich And Langmuir Adsorption Isotherms And Kinetics For The Removal Of Tartrazine From Aqueous Solutions

Using Hen Feathers. *Journal of Hazardous Material*, 146, 243–248.

Mourya, P., Banerjee, S., & Singh, M. M. (2014). Corrosion inhibition of mild steel in acidic solution by *Tagetes erecta* (Marigold flower) extract as a green inhibitor. *Corrosion Science*, 85, 352–363.

Muthukrishnan, P., Jeyaprabha, B., & Prakash, P. (2013). Corrosion Inhibition and Adsorption Behavior of *Setaria verticillata* Leaf Extract in 1M Sulphuric Acid. *Journal of Materials Engineering and Performance*, 22(12), 3792–3800.

Natarajan, K. A. (2014). Corrosion: Introduction. *Advances in Corrosion Engineering*. Bangalore.

Nechifor, G., Pascu, D. E., Neagu, M. P., Traistaru, G. A., & Albu, P. C. (2015). Comparative study of temkin and floryhuggins isotherms for adsorption of phosphate anion on membranes. *UPB Scientific Bulletin, Series B: Chemistry and Materials Science*, 77(2), 63–72.

Nwabanne, J. T., & Okafor, V. N. (2012). Adsorption and Thermodynamics Study of the Inhibition of Corrosion of Mild Steel in H₂SO₄ Medium Using *Vernonia amygdalina*. *Journal of Minerals and Materials Characterization and Engineering*, 11, 885–890.

Obi-egbedi, N. O., Obot, I. B., & Umoren, S. A. (2012). *Spondias mombin* L . as a green corrosion inhibitor for aluminium in sulphuric acid : Correlation between inhibitive effect and electronic properties of extracts major constituents using density functional theory. *Arabian Journal of Chemistry*, 5(3), 361–373.

Odewunmi, N. a., Umoren, S. a., & Gasem, Z. M. (2014). Utilization of watermelon rind extract as a green corrosion inhibitor for mild steel in acidic media. *Journal of Industrial and Engineering Chemistry*, 21, 239–247.

Odewunmi, N. A., Umoren, S. A., Gasem, Z. M., Ganiyu, S. A., & Muhammad, Q. (2015). 1-Citrulline : An active corrosion inhibitor component of watermelon rind extract for mild steel in HCl medium. *Journal of the Taiwan Institute of Chemical Engineers*, 1–9.

Oguzie, E. E., Li, Y., & Wang, F. H. (2007). Corrosion Inhibition And Adsorption Behavior Of Methionine On Mild Steel In Sulfuric Acid And Synergistic Effect Of Iodide Ion. *Journal of Colloid and Interface Science*, 310, 90–98.

Özcan, M., Solmaz, R., Kardaş, G., & Dehri, İ. (2008). Adsorption properties of

barbiturates as green corrosion inhibitors on mild steel in phosphoric acid. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 325(1-2), 57–63.

P. Bothi Raja & M.G. Sethuraman (2010). Studies on the Inhibition of Mild Steel Corrosion by Rauvolfia serpentina in Acid Media. *Journal of Material Engineering and Performance*. 19, 761–766

Patel, N. S., Jauhariand, S., Mehta, G. N., Warad, I., & Hammouti, B. (2013). Mild Steel Corrosion Inhibition by Various Plant Extracts in 0.5 M Sulphuric acid. *International Journal of Electrochemical Science*, 8, 2635–2655.

Popov, B. N. (2015). Chapter 5 - Basics of Corrosion Measurements. (pp. 181–237). Amsterdam. Elsevier.

Rafael Martinez Palou, Octavio Olivares-Xomelt and Natalya V. Likhanova. (2011). Environmentally friendly corrosion inhibitors. *Developments in Corrosion Protection*, 257–303.

Rahimi, M., & Vadi, M. (2014). Langmuir, Freundlich and Temkin Adsorption Isotherms of Propranolol on Multi-Wall Carbon Nanotube. *Journal. of Modern Drug Discovery And Drug Delivery Research*, 1–3.

Raja, P. B., & Sethuraman, M. G. (2008). Natural products as corrosion inhibitor for metals in corrosive media — A review. *Materials Letters*, 62(1), 113–116.

Rajalakshmi, R., & Safina, a. S. (2012). Staminate Flower of Cocos Nucifera as Green Inhibitor for Mild Steel in HCl Medium. *E-Journal of Chemistry*, 9(3), 1632–1644.

Ramananda Singh, M., Gupta, P., & Gupta, K. (2015). The litchi (Litchi Chinensis) peels extract as a potential green inhibitor in prevention of corrosion of mild steel in 0.5M H₂SO₄ solution. *Arabian Journal of Chemistry*, 1–6.

Roberge, P. R., & Pierre, R. (1999). *Handbook of Corrosion Engineering Library of Congress Cataloging-in-Publication Data*. Mc-Graw Hill. United States of America.

Sato, N. (2011). Basics of Corrosion Chemistry. *Green Corrosion Chemistry and Engineering: Opportunities and Challenges*, 1–32. First Edition. Edited by Sanjay K. Sharma. Published by Wiley-VCH Verlag GmbH & Co. KGaA.

Shoesmith, D. W. (1987). Kinetics of aqueous corrosion. *ASM Handbook: Corrosion*

- Sangeetha, M., Rajendran, S., Muthumegala, T. S., & Krishnaveni, a. (2011). Green corrosion inhibitors-An Overview. *Zastita Materijala*, 52, 3.
- Shah, a. M., Rahim, a. a., Hamid, S. a., & Yahya, S. (2013). Green inhibitors for copper corrosion by Mangrove tannin. *International Journal of Electrochemical Science*, 8(2), 2140–2153.
- Sharifnia, S. (2013). Characterization, Isotherm and Kinetic Studies for Ammonium Ion Adsorption By Light Expanded Clay Aggregate (LECA). *Journal Of Saudi Chemical Society*.
- Shreir, L. L. (1994). Corrosion Control. Volume 2, Second Edition. Oxford : Butterworth-Heinemann
- Singh, A., Ahamad, I., & Quraishi, M. A. (2012). Piper longum extract as green corrosion inhibitor for aluminium in NaOH solution. *Arabian Journal of Chemistry*.
- Singh, A. K., Mohapatra, S., & Pani, B. (2016). Corrosion Inhibition Effect Of Aloe Vera Gel: Gravimetric And Electrochemical Study. *Journal of Industrial and Engineering Chemistry*.33, 288–297.
- State, K., State, E., & State, K. (2012). Langmuir , Freundlich , Temkin and Dubinin – Radushkevich Isotherms Studies of Equilibrium Sorption of Zn^{2+} Unto Phosphoric Acid Modified Rice Husk. *Journal of Applied Chemistry*, 3(1), 38–45.
- Tamara Radetic (2011). Fundamentals of Scanning Electron Microscopy and Energy Dispersive X-ray Analysis in SEM and TEM SEM: Basic Principles SEM: Electron Gun, NFM Spring School on Electron Microscopy.Serbia.
- Turcio-ortega, D., Pandiyan, T., & García-ochoa, E. M. (2007). Electrochemical Impedance Spectroscopy (EIS) Study of the Film Formation of 2-imidazoline Derivatives on Carbon Steel in Acid Solution. *Corrosion Science*, 13(2), 163–166.
- Umoren, S. A., Eduok, U. M., Solomon, M. M., & Udoh, A. P. (2011). Corrosion inhibition by leaves and stem extracts of *Sida acuta* for mild steel in 1 M H_2SO_4 solutions investigated by chemical and spectroscopic techniques. *Arabian Journal of Chemistry*.
- Umoren, S. A., & Solomon, M. M. (2015). Effect of halide ions on the corrosion

inhibition efficiency of different organic species – A review. *Journal of Industrial and Engineering Chemistry*, 21, 81–100.

- Umoren, S. a., Solomon, M. M., Eduok, U. M., Obot, I. B., & Israel, A. U. (2014). Inhibition of mild steel corrosion in H_2SO_4 solution by coconut coir dust extract obtained from different solvent systems and synergistic effect of iodide ions: Ethanol and acetone extracts. *Journal of Environmental Chemical Engineering*, 2(2), 1048–1060.
- Vinod Kumar, K. P., Sankara Narayanan Pillai, M., & Rexin Thusnavis, G. (2011). Green corrosion inhibitor from seed extract of Areca catechu for mild steel in hydrochloric acid medium. *Journal of Materials Science*, 46(15), 5208–5215.
- Yadav, M., Gope, L., Kumari, N., & Yadav, P. (2016). Corrosion inhibition performance of pyranopyrazole derivatives for mild steel in HCl solution: Gravimetric, electrochemical and DFT studies. *Journal of Molecular Liquids*, 216, 78–86.
- Yaro, A. S., Khadom, A. a., & Wael, R. K. (2013). Apricot juice as green corrosion inhibitor of mild steel in phosphoric acid. *Alexandria Engineering Journal*, 52(1), 129–135.
- Yüce, A. O., & Kardaş, G. (2012). Adsorption and inhibition effect of 2-thiohydantoin on mild steel corrosion in 0.1M HCl. *Corrosion Science*, 58, 86–94.
- Yong, J. W. H., Ge, L., Ng, Y. F., & Tan, S. N. (2009). The Chemical Composition and Biological Properties of Coconut (*Cocos nucifera* L.) Water. *Molecules*, 14(12), 5144–5164.
- Zakaria, K., Negm, N. A., Khamis, E. A., & Badr, E. A. (2016). Journal of the Taiwan Institute of Chemical Engineers Electrochemical and quantum chemical studies on carbon steel corrosion protection in 1M H_2SO_4 using new eco-friendly Schiff base metal complexes. *Journal of the Taiwan Institute of Chemical Engineers*. 61, 316–326.