



UNIVERSITI PUTRA MALAYSIA

***DEVELOPMENT AND CHARACTERIZATION OF THERMOPLASTIC
SUGAR PALM STARCH/AGAR POLYMER BLEND, REINFORCED
SEAWEED WASTE AND SUGAR PALM FIBER HYBRID COMPOSITE***

RIDHWAN BIN JUM Aidin

FK 2017 62



**DEVELOPMENT AND CHARACTERIZATION OF THERMOPLASTIC
SUGAR PALM STARCH/AGAR POLYMER BLEND, REINFORCED
SEAWEED WASTE AND SUGAR PALM FIBER HYBRID COMPOSITE**

By

RIDHWAN BIN JUMAIDIN

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in
Fulfillment of the Requirements for the Degree of Doctor of Philosophy**

May 2017

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



DEDICATION

To Al-Quran, the greatest source of knowledge

Bring me sheets of iron" - until, when he had leveled [them] between the two mountain walls, he said, "Blow [with bellows]," until when he had made it [like] fire, he said, "Bring me, that I may pour over it molten copper." (Al-Kahf:Verse 96)

&

To my beloved father and mother

&

To my beloved wife

&

To my beloved daughter and son

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Doctor of Philosophy

**DEVELOPMENT AND CHARACTERIZATION OF THERMOPLASTIC
SUGAR PALM STARCH/AGAR POLYMER BLEND, REINFORCED
SEAWEED WASTE AND SUGAR PALM FIBER HYBRID COMPOSITE**

By

RIDHWAN BIN JUMAIDIN

May 2017

Chairman : Mohd Sapuan Bin Salit, PhD
Faculty : Engineering

In recent, the needs to develop more environmental friendly product is increasing due to the accumulating of non-biodegradable waste, particularly the disposable product. Hence, various kinds of more environmental friendly materials were developed in order to tackle this issue. Biopolymer derived from renewable resources is a promising alternative material for petroleum based polymer since it is readily biodegradable and thus, more environmental friendly. Among the biopolymer, starch is one of the most promising due to the easy availability, low cost, abundant in nature, renewable, and biodegradable. Sugar palm is a versatile plant that is regarded as renewable source for fibre and starch. However, the inborn deterrent associated with the biopolymer derived from sugar palm starch (SPS) such as the poor mechanical properties has limits its potential applications. Meanwhile, *Eucheuma cottonii* seaweed is a resourceful macro alga which is massively cultivated for the production of its hydrocolloids, namely carrageenan. However, due to the relatively low carrageenan content in the raw seaweed, huge amount of solid wastes were produced during processing which is yet to be utilized. Hence, characterizations of the seaweed wastes were carried out to analyse its potential as reinforcement material. Then, several modification methods were employed to enhance the properties of thermoplastic SPS i. e; (1) blending thermoplastic SPS with agar polymer (2) reinforcement of thermoplastic SPS/agar (TPSA) blend with seaweed wastes, and (3) hybridization of seaweed wastes with sugar palm fibre in the TPSA composites. Consequently, thermoplastic SPS/agar blends were successfully developed by using melt-mixing and compression moulding method. The findings show that the tensile, flexural, and impact properties of the material were improved following the incorporation of agar. The thermal properties of the material were slightly improved as the agar content increased from 0 to 40 wt%. In terms of physical properties, the addition of agar has increased the water affinity characteristics of the polymer blend. Furthermore, the influence of seaweed wastes at varying content (0 to 40 wt%) on the mechanical, thermal, physical, and biodegradation characteristics of TPSA were investigated. Improvement in the tensile, flexural, and impact properties of the composites were evidence after incorporation of seaweed waste. It also evident from the thermogravimetric analysis (TGA) results that the thermal stability of the composites were enhanced with addition of seaweed waste. In terms of the physical properties, addition of seaweed has led to higher water affinity of the composites. After soil burial

for 2 and 4 weeks, the biodegradation of the composites were enhanced with the incorporation of seaweed waste. Lastly, the effects of sugar palm fibre hybridization with seaweed/TPSA composites were evaluated. Hybridized seaweed waste/SPF reinforcement at weight ratio of 0:100, 25:75, 50:50, 75:25, and 100:0 were prepared by using TPSA polymer blend as the matrix. Obtained results indicated that hybrid composites display improved tensile and flexural properties accompanied with lower impact resistance. Thermal stability of the hybrid composites were enhanced than the individual seaweed waste composite. Water absorption, thickness swelling, water solubility, and soil burial tests showed higher water and biodegradation resistance of the hybrid composites. Overall, the findings from the current study demonstrated that thermoplastic SPS modified by agar, seaweed wastes, and hybridization with SPF has shown improved functional characteristics than the origin material. In conclusion, the TPSA polymer blend reinforced seaweed waste/SPF hybrid composites are potential alternative material for biodegradable product i. e disposable tray with enhanced properties.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk Ijazah Doktor Falsafah

**PENYEDIAAN DAN PENCIRIAN KOMPOSIT HIBRID TERMOPLASTIK
CAMPURAN KANJI ENAU/AGAR MEMPERKUKUH RUMPAI
LAUT/GENTIAN ENAU**

Oleh

RIDHWAN BIN JUMAIDIN

Mei 2017

Pengerusi : Mohd Sapuan Bin Salit, PhD
Fakulti : Kejuruteraan

Sejak kebelakangan ini, keperluan untuk membangunkan lebih banyak produk mesra alam semakin meningkat disebabkan oleh sisa terkumpul yang tidak terbiodegradasi di tapak pelupusan sampah. Oleh itu, pelbagai jenis bahan-bahan yang lebih mesra alam telah dibangunkan untuk menangani isu ini. Biopolimer yang diperolehi daripada sumber yang boleh diperbaharui adalah bahan alternatif yang menarik untuk menggantikan polimer berasaskan petroleum kerana ianya mudah terbiodegradasikan dan dengan itu, lebih mesra alam berbanding polimer konvensional. Antara biopolimer, kanji adalah antara yang paling menarik kerana ianya mudah diperolehi, kos rendah, banyak dalam alam semula jadi, boleh diperbaharui dan mesra alam. Pokok enau adalah tumbuhan serba boleh yang dianggap sebagai sumber yang boleh diperbaharui untuk gentian dan kanji. Walau bagaimanapun, penghalang semula jadi yang berkaitan dengan biopolimer yang diperolehi daripada kanji enau (SPS) seperti sifat-sifat mekanikal yang lemah telah menghadkan potensi aplikasinya. Sementara itu, rumpai laut *Eucheuma cottonii* merupakan alga makro yang ditanam secara besar-besaran untuk pengeluaran hidrosoloid, iaitu karagenan. Walau bagaimanapun, disebabkan kandungan karagenan yang rendah dalam rumpai laut, sejumlah besar sisa pepejal telah dihasilkan semasa pemrosesan yang masih belum dimanfaatkan. Oleh itu, pencirian sisa rumpai laut telah dijalankan untuk menganalisis potensinya sebagai bahan penguat. Seterusnya, beberapa kaedah pengubahsuaian telah diambil untuk menambahbaik sifat-sifat termoplastik SPS iaitu; (1) pencampuran termoplastik SPS dengan polimer agar (2) pengukuhan termoplastik SPS/agar (TPSA) dengan sisa rumpai laut, dan (3) penghibridan sisa rumpai laut dengan gentian enau dalam komposit TPSA. Polimer campuran termoplastik SPS/agar telah berjaya dibangunkan dengan menggunakan kaedah pencampuran-lebur dan kaedah pengacuan mampatan. Dapatan kajian menunjukkan bahawa sifat tegangan, lenturan, dan impak bahan telah meningkat susulan daripada penggabungan agar ke dalam termoplastik SPS. Sifat termal termoplastik SPS menunjukkan sedikit peningkatan apabila kandungan agar meningkat (0 – 40%). Dari segi sifat fizikal, penambahan agar telah meningkatkan sifat pertalian air polimer campuran. Seterusnya, pengaruh sisa rumpai laut pada kandungan yang berbeza-beza (0-40% berat) kepada ciri-ciri mekanikal, termal, fizikal, dan biodegradasi TPSA telah disiasat. Peningkatan dalam

sifat tegangan, lenturan, dan impak bagi komposit dapat dilihat selepas diperbadankan dengan rumpai laut. Ia juga dapat dilihat daripada keputusan analisis termogravimetri (TGA) bahawa kestabilan terma bagi komposit telah dipertingkatkan dengan penambahan rumpai laut. Dari segi sifat-sifat fizikal, penambahan rumpai laut telah membawa kepada peningkatan sifat pertalian air bagi komposit. Selepas ditanam dalam tanah selama 2 dan 4 minggu, biodegradasi bagi komposit telah dipertingkatkan dengan penambahan rumpai laut. Akhir sekali, kesan penghibridan gentian enau (SPF) dengan komposit rumpai laut/TPSA telah dinilai. Penghibridan rumpai laut/SPF pada nisbah berat 25:75, 50:50 dan 75:25 telah disediakan dengan menggunakan TPSA sebagai matriks. Sifat-sifat mekanikal, termal dan fizikal komposit hibrid telah dikaji. Keputusan yang diperolehi menunjukkan bahawa komposit hibrid memaparkan sifat tegangan dan lenturan yang lebih baik disertai dengan rintangan impak yang lebih rendah. Mikrograf mikroskop imbasan elektron (SEM) untuk permukaan patah akibat tegangan menunjukkan ikatan gentian-matriks yang bagus. Kestabilan terma komposit hibrid telah dipertingkatkan berbanding komposit sisa rumpai laut individu. Ujian penyerapan air, pengembangan ketebalan, kelarutan air, dan penanaman dalam tanah bagi komposit hibrid menunjukkan ketahanan terhadap air dan biodegradasi yang lebih tinggi bagi komposit hibrid. Secara keseluruhan, dapatan daripada kajian semasa menunjukkan bahawa termoplastik SPS yang diubahsuai oleh agar, sisa rumpai laut, dan penghibridan dengan SPF telah menunjukkan ciri-ciri fungsi yang bertambah baik daripada bahan asal. Kesimpulannya, komposit hibrid polimer campuran TPSA memperkukuh sisa rumpai laut/gentian enau adalah bahan alternatif yang berpotensi untuk produk biodegradasi seperti dulang pakai buang dengan ciri-ciri yang dipertingkatkan.

ACKNOWLEDGEMENTS

In the name of Allah, the Most Gracious, the Most Merciful

Highest gratitude to Allah swt for granting me the strength, resilient, and knowledge to complete this thesis. The accomplishment of this thesis would not have materialized without His blessing and guidance. My deepest appreciation goes to my kind supervisor Professor Ir. Dr Mohd. Sapuan Bin Salit for his enormous support and encouraging supervision throughout my study. I was greatly inspired to explore the world of research and writing under his supervision. Thereafter, I would like to express my sincere appreciation for the guidance and coaching of my co-supervisors, Dr Mohammad Jawaid (Laboratory of Biocomposite Technology, INTROP, UPM), Dr Mohamad Ridzwan Ishak (Department of Aerospace Engineering, UPM) and Allahyarham Dr Sahari Japar (Universiti Malaysia Sabah) (May Allah grant him a peaceful place among the solihin).

I would like to convey my great appreciation to Universiti Teknikal Malaysia Melaka and Ministry of Higher Education Malaysia for providing the scholarship award for me to pursue this study. Special acknowledgment to Universiti Putra Malaysia for the financial support provided through Universiti Putra Malaysia Grant Scheme (project code GP-IPS/2015/9457200).

I owe a special thanks to my dear wife (Syarmeela Hadzwina Awang Musa) for her continuous support and sacrifice throughout my study. To my beloved father (Haji Jumaidin Haji Abas) and mother (Hajah Bunga Mohd Bakir) for the motivations and continuous prayer for my success in this world and in the hereafter. Special credit to my daughter (Anis Sumayyah Ridhwan) and son (Razin Ridhwan) for providing a cheerful environment during my study period.

I am thankful to all staff in Faculty of Engineering and Institute of Tropical and Forestry Product (INTROP) for their help and guidance. Last but not least, I would like to thank all of my friends in Engineering and INTROP for the knowledge sharing and support to the successful completion of this work.

Thank you all!

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Mohd Sapuan Salit, PhD

Professor, Ir
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Mohamad Ridzwan Ishak, PhD

Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Mohammad Jawaaid, PhD

Fellow Researcher
Institute of Tropical and Forestry Product
Universiti Putra Malaysia
(Member)

Sahari Japar, PhD

Senior Lecturer
Faculty of Science and Natural Resources
Universiti Malaysia Sabah
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____

Name of

Chairman of

Supervisory

Committee: Prof. Ir. Dr. Mohd Sapuan Bin Salit

Signature: _____

Name of

Member of

Supervisory

Committee: Dr. Mohamad Ridzwan Bin Ishak

Signature: _____

Name of

Member of

Supervisory

Committee: Dr. Mohamad Jawaid

Signature: _____

Name of

Member of

Supervisory

Committee: Dr. Sahari Bin Japar

TABLE OF CONTENTS

ABSTRACT	Page
ABSTRAK	i
ACKNOWLEDGEMENTS	iii
APPROVAL	v
DECLARATION	vi
LIST OF TABLES	viii
LIST OF FIGURES	xiv
	xv

CHAPTER

1	INTRODUCTION	
1.1	Background	1
1.2	Problem statement	1
1.3	Research objectives	2
1.4	Significance of study	3
1.5	Scope of study	3
1.6	Structure of thesis	4
2	LITERATURE REVIEW	
2.1	Introduction	6
2.2	Starch	6
2.3	Polymerization of Thermoplastic Starch	8
2.3.1	Thermoplastic Sugar Palm Starch	9
2.3.2	Thermoplastic Cassava Starch	11
2.3.3	Thermoplastic Corn Starch	19
2.3.4	Thermoplastic Rice Starch	23
2.3.5	Thermoplastic Potato Starch	24
2.4	Applications of Thermoplastic Starch	26
2.5	Seaweed	27
2.5.1	Seaweed overview	27
2.5.2	<i>Eucheuma cottonii</i> seaweed waste	28
2.6	Application of Seaweed	29
2.6.1	Seaweed as a source of food	29
2.6.2	Seaweed hydrocolloids	30
	2.6.2.1 Agar	31
	2.6.2.2 Carrageenan	34
	2.6.2.3 Alginate	35
2.7	Seaweed biopolymer	36
2.7.1	Agar biopolymer	36
	2.7.1.1 Agar based composites	36
	2.7.1.2 Agar as filler in polymer composites	39
	2.7.1.3 Biodegradability of agar film	40
	2.7.1.4 Agar based composites: Miscellaneous application	41

2.7.2	Carrageenan biopolymer	42
2.7.2.1	Carrageenan based composites	42
2.7.2.2	Carrageenan as filler in polymer composites	44
2.7.2.3	Carrageenan based composites: Miscellaneous applications	44
2.7.3	Alginate biopolymer	47
2.7.3.1	Alginate based composite	48
2.8	Seaweed as filler in polymer composites	50
2.9	Thermoplastic Starch Polymer Blend	52
2.10	Sugar palm fibre	60
2.10.1	Sugar palm fibre composites	61
2.11	Summary	64
3	METHODOLOGY	
3.1	Introduction	66
3.2	Materials	67
3.2.2	Seaweed wastes	67
3.2.3	Sugar palm starch	68
3.2.4	Sugar palm fibre	69
3.2.5	Others	69
3.3	Fabrication of thermoplastic SPS	70
3.4	Fabrication of thermoplastic sugar palm starch/agar polymer blend (TPSA)	71
3.5	Fabrication of TPSA/seaweed waste composites	72
3.6	Fabrication of TPSA reinforced seaweed waste/sugar palm fibre hybrid composites	74
3.7	Characterization of samples	75
3.7.1	Mechanical testing	75
3.7.1.1	Tensile testing	75
3.7.1.2	Flexural testing	76
3.7.1.3	Impact testing	76
3.7.2	Thermal analysis	76
3.7.2.1	Thermogravimetric analysis (TGA)	76
3.7.2.2	Differential scanning calorimetry (DSC)	76
3.7.3	Chemical analysis	77
3.7.3.1	Chemical composition	77
3.7.3.2	FT-IR analysis	77
3.7.4	Physical testing	77
3.7.4.1	Determination of moisture content	77
3.7.4.2	Water absorption	77
3.7.4.3	Thickness swelling	78
3.7.4.4	Moisture absorption	78
3.7.4.5	Density	78
3.7.4.6	Particle size analysis	79
3.7.4.7	X-ray diffraction (XRD)	79
3.7.4.8	Scanning electron microscope	79
3.7.5	Environmental testing	79
3.7.5.1	Water Solubility	79

	3.7.5.2	Soil burial	80
	3.7.6	Statistical analysis	80
4	CHARACTERISTICS OF EUCHEUMA COTTONII WASTE FROM EAST MALAYSIA: PHYSICAL, THERMAL, AND CHEMICAL COMPOSITION		81
		Acceptance letter	93
		Copyright Permission	94
5	CHARACTERISTICS OF THERMOPLASTIC SUGAR PALM STARCH/AGAR BLEND: THERMAL, TENSILE, AND PHYSICAL PROPERTIES		95
		Acceptance letter	108
		Copyright Permission	109
6	EFFECT OF SEAWEED ON MECHANICAL, THERMAL, AND BIODEGRADATION PROPERTIES OF THERMOPLASTIC SUGAR PALM STARCH/AGAR COMPOSITES		110
		Acceptance letter	127
		Copyright Permission	128
7	THERMAL, MECHANICAL, AND PHYSICAL PROPERTIES OF SEAWEED/SUGAR PALM FIBRE REINFORCED THERMOPLASTIC SUGAR PALM STARCH/AGAR HYBRID COMPOSITES		129
		Acceptance letter	148
		Copyright Permission	149
8	RESULTS AND DISCUSSION		
	8.1	Characteristics of Seaweed Waste from East Malaysia	150
	8.1.1	XRD analysis	
	8.2	Characteristics of Thermoplastic Sugar Palm Starch/Agar (TPSA) Polymer Blend	151
	8.2.1	Preparation of Thermoplastic Sugar Palm Starch/Agar (TPSA) Polymer blend	151
	8.2.2	Flexural tests	152
	8.2.3	Impact tests	154
	8.2.4	TGA analysis	155
	8.2.5	Density	157
	8.2.6	Moisture Content	157
	8.2.7	Water Absorption	158
	8.2.8	Thickness Swelling	159
	8.2.9	Water Solubility	160
	8.3	Characteristics of Thermoplastic Sugar Palm Starch/Agar Polymer Blend Reinforced Seaweed Waste Composite	161
	8.3.1	Moisture content	162
	8.3.2	Density	163
	8.3.3	Water absorption	163
	8.3.4	Thickness swelling	164

8.3.5	Water solubility	165
8.3.6	Moisture absorption	166
8.4	Characteristics of Thermoplastic Sugar Palm Starch/Agar Polymer Blend Reinforced Seaweed Waste/Sugar Palm Fibre Hybrid Composite	167
8.4.1	Potential Application of TPSA Reinforced Seaweed Waste/SPF Hybrid Composite	168
9	CONCLUSIONS AND RECOMMENDATIONS FOR FUTURE RESEARCH	
9.1	Conclusions	171
9.2	Recommendations for future research	173
	REFERENCES	174
	APPENDICES	196
	BIODATA OF STUDENT	203
	LIST OF PUBLICATIONS	204

LIST OF TABLES

Table		Page
2.1	Thermoplastic cassava starch composites	19
2.2	Thermoplastic corn starch composites	22
2.3	Thermoplastic potato starch composites	24
2.4	Thermoplastic starch from various sources	25
2.5	Thermoplastic starch from various sources	26
2.6	Agar polymer composite and their prospective applications	41
2.7	Carrageenan polymer composite and their prospective applications	46
2.8	Alginate polymer composite and their prospective applications	49
3.1	Material specification of agar	70
3.2	Material specification of glycerol	70
3.3	Relative amount of reinforcing materials in composites	75
4.1	Physical properties of seaweeds and other material	88
4.2	Comparison on chemical composition of seaweed	89
5.1	Summary of the analysis of variance (ANOVA) of thermoplastic SPS/agar	103
5.2	Glass transition, T _g and melting temperature, T _m of thermoplastic SPS/agar	105
6.1	Chemical composition of Eucheuma cottonii wastes	113
6.2	Summary of the analysis of variance (ANOVA) of mechanical properties	121
6.3	Summary of TGA results of TPSA/Seaweed composites	125
7.1	Relative amount of reinforcing materials in composites	132
7.2	Summary of the analysis of variance (ANOVA) of mechanical properties	139
7.3	Summary of TGA results for Sw/SPF reinforced TPSA composites	142
7.4	Physical properties of Sw/SPF hybrid composites	144
8.1	Summary of the analysis of variance (ANOVA) of thermoplastic SPS/agar	154
8.2	TGA results of thermoplastic SPS/agar	156
8.3	Primary characteristics of TPSA reinforced Sw/SPF composites and other polymers	169

LIST OF FIGURES

Figure		Page
2.1	Starch granules from sugar palm tree	6
2.2	Chemical structure of (a) amylose and (b) amylopectin	10
2.3	SEM micrograph of sugar palm TPS plasticized with different amount of glycerol	10
2.4	SEM micrograph of thermoplastic sugar palm starch (SPS) reinforced with different amount of sugar palm fibre	11
2.5	Mechanical properties of TPS/jute fibre and TPS/kapok fibre composite (a) stress at maximum load, (b) Young's modulus and (c) strain at maximum load	13
2.6	SEM micrograph of (a) TPS/jute fibre (b) TPS/kapok fibre	13
2.7	TGA curve of (a) TPS/jute fibre (b) TPS/kapok fibre	13
2.8	Mechanical properties of TPS/coconut fibre (a) tensile strength (b) Modulus of elasticity (c) Elongation at break	14
2.9	Fibre-matrix interface of TPS/coconut fibre composite	15
2.10	Water uptake of TPS/coconut fibre composite after water immersion for 2h and 24 h	15
2.11	SEM micrograph of (a) TPS matrix and (b) TPS/CBN20 composites (c) CBN	16
2.12	XRD curve of untreated (K) and treated kenaf fibre	16
2.13	FESEM micrograph of (a) TPS (b) TPS/K (c) TPS/KA (d) TPS/KB (e) TPS/CNCs	17
2.14	Weight loss of TPS/Eggshell and TPS/CaCo ₃ after soil burial for 15 days	18
2.15	SEM micrograph of TPS/EMMT at (a) 500x and (b) 10,000x	21
2.16	Green seaweed	28
2.17	Red seaweed	28
2.18	Brown seaweed	28
2.19	Eucheuma cottonii seaweed	29
2.20	Chemical structure of agar	31
2.21	Manufacturing process of agar	33
2.22	Chemical structure of k-carrageenan, i-carrageenan, and λ -carrageenan	35
2.23	Chemical structure of alginate	36
2.21	SEM micrographs of different TPCS/LDPE composites (a) TPCS/LDPE, (b) TPCS/LDPE/CG, (c) TPCS/LDPE/CF and (d) TPCS/LDPE/CG/CF	53
2.25	Mechanical properties of TPCS modified by carrageenan and/ or cotton fibres after soil burial test for 6 and 12 weeks (a) stress at maximum load, (b) Young's modulus and (c) strain at maximum load	53
2.26	Mechanical properties of the TPS modified by sodium alginate (a) stress at max load and Young's modulus and (b) strain at max load and hardness	54
2.27	SEM micrographs of TPS/LDPE modified by sodium alginate (a) 0%, (b) 10%, (c) 20%, and (d) 30%	55

2.28	Blown film extrusion of (a) TPS and (b) TPS/chitosan film	55
2.29	SEM micrograph of (a) TPS fracture surface and (b) TC10 fracture surface	56
2.30	FT-IR spectra of (a) TPS/chitosan and (b) TPS/chitin	57
2.31	Sugar palm plantation at Tawau, Sabah	60
2.32	Sugar palm fibre	61
3.1	Flow of research methodology	67
3.2	Eucheuma cottonii seaweed (raw and wastes)	68
3.3	Extraction method of sugar palm starch	69
3.4	Sugar palm fibre extraction	69
3.5	Fabrication of TPSA polymer blend	72
3.6	Preparation method for composites	73
3.7	Preparation method for seaweed waste/SPF hybrid composites	75
4.1	Eucheuma cottonii seaweed	83
4.2	Eucheuma cottonii wastes	84
4.3	Particle size distribution of (a) raw seaweed particles (b) seaweed wastes particles	86
4.4	SEM micrograph of Eucheuma cottonii particles	86
4.5	SEM micrograph of Eucheuma cottonii waste particles	87
4.6	TG and DTG curves of Eucheuma cottonii (raw and wastes)	90
4.7	FT-IR spectra of Eucheuma cottonii (raw and wastes)	91
4.8	XRD pattern of Eucheuma cottonii seaweed (raw and wastes)	92
5.1	FT-IR spectra of (a) native SPS and (b) native agar (c) neat SPS matrix (d) 10% agar (e) 20% agar (f) 30% agar (g) 40% agar	100
5.2	Tensile strength of thermoplastic SPS/agar	102
5.3	Tensile modulus of thermoplastic SPS/agar	102
5.4	Elongation at break of thermoplastic SPS/agar	102
5.5	SEM micrograph of fracture surface of thermoplastic SPS blended with different ratio of agar (a) 0 wt% (b) 10 wt% (c) 20 wt% (d) 30 wt% (e) 40 wt%	104
5.6	Moisture absorption behavior of thermoplastic SPS with different amount of agar	106
5.7	Thickness swelling behavior of thermoplastic SPS blends with different amount of agar	107
6.1	Micrograph of Eucheuma cottonii seaweed (a) raw seaweed (b) seaweed wastes (c) ground seaweed wastes	113
6.2	FT-IR spectra of TPSA/seaweed composites with various seaweed contents	117
6.3	Chemical structure of k-carrageenan	117
6.4	Tensile properties of TPSA/seaweed composites (a) tensile strength (b) tensile modulus (c) elongation at break	119
6.5	Flexural and impact properties of TPSA/seaweed composites (a) flexural strength (b) flexural modulus (c) impact strength	120
6.6	SEM investigation of tensile fracture surface of TPSA/seaweed composites: (a) TPSA matrix (b) 10% seaweed (c) 20% seaweed (d) 30% seaweed (e) 40% seaweed composites and (f) void in TPSA/seaweed composites	122
6.7	TGA results of TPSA/seaweed composites (a) TG curve (b) DTG curve	124
6.8	Weight loss of TPSA/seaweed composites after soil burial for 2 and 4 weeks	126

7.1	FT-IR spectra of Sw/SPF hybrid composites	137
7.2	Mechanical properties of Sw/SPF hybrid composites	139
7.3	Scanning electron micrograph of (a) Sw composites (b) HC1 composites (c) HC2 composites (d) magnified image of HC2 composites (e) HC3 composites and (f) SPF composites	140
7.4	TGA results of Sw/SPF hybrid composite	142
7.5	Moisture absorption behaviour of Sw/SPF hybrid composites	145
7.6	Weight loss of Sw/SPF hybrid composites after soil burial for 2 and 4 weeks	146
8.1	Thermoplastic SPS blends with agar (a) 10wt% (b) 20wt% (c) 30wt% (d) 40wt%	152
8.2	Flexural strength of thermoplastic SPS blended with agar	153
8.3	Flexural modulus of thermoplastic SPS blended with agar	153
8.4	Impact strength of thermoplastic SPS blended with agar	154
8.5	TGA curve of native agar, native SPS, and thermoplastic SPS blends	156
8.6	DTG curve of native agar, native SPS, and thermoplastic SPS blend	156
8.7	Density of Thermoplastic SPS blends	157
8.8	Moisture content of thermoplastic SPS blends	158
8.9	Water absorption capacity of thermoplastic SPS blends	159
8.10	Thickness swelling capacity of thermoplastic SPS blends	160
8.11	Solubility of thermoplastic SPS blends	161
8.12	Moisture content of TPSA/seaweed composite	162
8.13	Density of TPSA/seaweed composite	163
8.14	Water absorption of TPSA/seaweed composites	164
8.15	Thickness swelling of TPSA/seaweed composite	165
8.16	Solubility of TPSA/seaweed composites	166
8.17	Moisture absorption curves of TPSA/seaweed composites	166
8.18	TPSA reinforced seaweed waste/SPF hybrid composites	167

LIST OF ABBREVIATIONS

ASTM	American Society for Testing and Materials
ANOVA	Analysis Of Variance
CBN	Cellulose Nanofibre
CNC	Cellulose Nanocrystal
CNCs	Kenaf Cellulose Nanocrystals
CNT	Carbon Nanotubes
DSC	Differential Scanning Calorimetry
EMMT	Ethanolamine activated-montmorillonite
FESEM	Field Emission Scanning Electron Microscope
FTIR	Fourier Transform Infrared
HAS	High amylose starch
HC	Hybrid composite
HDPE	High-density polyethylene
HIPS	High impact polystyrene
KA	Alkali treated kenaf
KB	Bleached kenaf
LDPE	Low-density polyethylene
MAPE	Maleic anhydride- grafted-polyethylene
MFC	Microfibrillated cellulose
MMT	Montmorillonite
PBAT	Poly(butylene adipate-co-terephthalate)
PHB	Polyhydroxybutyrate
PHS	Photo-sensitizer
PLA	Poly (lactic acid)
PP	Polypropylene
PVOH	Polyvinyl alcohol
RH	Relative humidity
SEM	Scanning electron microscope
SPF	Sugar palm fibre
SPS	Sugar palm starch
ST-SA	Stearic acid-grafted starch
TGA	Thermal-gravimetric analysis
TPS	Thermoplastic Starch
TPSA	Thermoplastic Sugar Palm Starch/Agar
TPCS	Thermoplastic cassava starch
UV	Ultraviolet

W

WS

WVP

XRD

Weight

Water solubility

Water vapor permeability

X-ray diffraction



CHAPTER 1

INTRODUCTION

1.1 Background

In recent, the needs to develop more environmental friendly product is increasing due to the accumulating of non-biodegradable waste on the land fill. Hence, various kind of “green” materials were developed in order to tackle this issue. Biopolymer derived from renewable resources is a promising alternative material for petroleum based polymer since it is readily biodegradable and thus, more environmental friendly than the conventional polymers. Various kind of natural resources were used to develop biopolymer ranging from lipid, protein, cellulose, and starch. Among these sources, starch is considered as the most promising resource due to several attributes i. e low cost, renewable, and totally biodegradable (Sahari et al., 2013a). Under the presence of heat and plasticizer, starch can be converted into thermoplastic starch (TPS) which possesses similar process ability with the conventional thermoplastic. The thermoplasticity of this biopolymer is the main advantages for the processing of this material. This enables this biopolymer to be processed by using the conventional processing equipment used for synthetic thermoplastic such as extruder, injection moulding, and compression moulding.

Many varieties of natural material have been used as reinforcement in polymer composites. This including both natural fibres (such as kenaf, jute, sisal, and sugar palm) and also natural fillers (such as talc, clay, eggshell, and seaweed) (Bootklad & Kaewtatip, 2013; Coativy et al., 2014; Hassan et al., 2008; López et al., 2015). Incorporation of natural material as the reinforcement in polymer composites has created more environmental friendly characteristics to the composites. Moreover, this green approaches reduce the dependency of the manufacturing industry to the synthetic materials such as glass fibre which often related to high potential of hazard for the manufacturing workers. The development of more environmental friendly materials gives a new perspective to the manufacturing industry which is often related to the environmental pollution for both the production and disposal of the synthetic polymer.

1.2 Problem statement

High consumption of petroleum-based polymer by the society has created serious environmental problems mainly during the disposal stage. These wastes are not readily biodegradable when disposed into the environment i. e land or sea which brought serious problems to the society, wildlife, and environment as well. Moreover, air pollution is another concerning issue following the incineration of this wastes. In recent, many countries have banned the usage of plastic bag as an effort for handling

this issue. Hence, this study attempts to overcome this problem by developing a 100% renewable and biodegradable polymer composite from natural sources.

Sugar palm tree is a versatile plant which was reported to be able of producing 50 to 100 kg of starch from a single tree (Sahari et al., 2013c). Starch extracted from sugar palm tree can be transformed into thermoplastic material in the presence of heat and plasticizer which results to a rigid material. However, the neat thermoplastic starch (TPS) has disadvantage that limit its usage in commercial plastic industry such as the poor mechanical strength. The current thermoplastic sugar palm starch has only 2.42 MPa of tensile strength which is extremely low when compared to the current thermoplastic material (Sahari et al., 2013c). This limitation has restricted the potential application of this material in the real world. Therefore, proper modifications should be employed in order to improve the properties of this material. The potential modifications include blending with other polymers and reinforcing with natural filler and fibre.

Eucheuma cottonii seaweed (also known as *Kappaphycus alvarezii*) is a macroalgae which is largely cultivated in countries like Philippines, Indonesia, and Malaysia. This seaweed is mainly used for producing the hydrocolloids namely kappa-carrageenan (k-carrageenan) which act as thickening agent for food and non-food application as well. However, the content of k-carrageenan varies from only 25 to 35% from the whole seaweed weight, hence, leaving enormous amount of solid wastes which is yet to be utilized (Tan & Lee, 2014). The potential application of this seaweed waste as biosorbent material has been investigated in previous studies (Kang et al., 2011; Lee et al., 2011). The result shows that this material has great potential as biosorbent material for removal of heavy metal element in water namely chromium ion, copper ion, and nickel ion. Apart from these studies, there is no work reported on utilization of seaweed wastes of *Eucheuma cottonii* species for other applications. Meanwhile, previous works have used various kinds of seaweeds as the potential reinforcement for petroleum derived polymer composites. However, the decrease in the mechanical strength was shown by the composites due to the incompatibility between the hydrophilic seaweed and the hydrophobic polymer matrix (Chitra & Kumari, 2012; Luan et al., 2010). Moreover, the combination of natural materials such as seaweed with the petroleum based polymer matrix will only results to partially biodegradable material. Therefore it is important to utilize seaweed waste as reinforcement in polymer composites which use hydrophilic polymer as the matrix. Hence, the motivation of this study are (1) to improve the properties of thermoplastic sugar palm starch (2) to widen the potential application of seaweed waste (3) to tackle the incompatibility issue of seaweed reinforced composites and finally (4) to produce a fully biodegradable material which can be safely disposed to the environment.

1.3 Research objectives

The principal aim of this study is to develop and characterize totally renewable and biodegradable materials based on natural resources. The specific objectives are:

1. To characterize the thermal, chemical, physical, and morphological properties of *Eucheuma cottonii* seaweed wastes.
2. To evaluate the effect of agar on the thermal, mechanical, physical, and morphological properties of thermoplastic sugar palm starch.
3. To investigate the effect of *Eucheuma cottonii* seaweed waste loading on the properties of thermoplastic sugar palm starch/agar composites.
4. To develop and characterize hybrid composites from *Eucheuma cottonii* seaweed wastes and sugar palm fibre by using thermoplastic sugar palm starch/agar as polymer matrix.

1.4 Significance of study

1. The findings from the current study are expected to enrich the knowledge in developing biodegradable polymer from thermoplastic sugar palm starch and agar.
2. The development of biodegradable polymer with enhanced properties in this study is expected to aid in addressing the environmental problems regarding the alternative materials for petroleum based polymer.
3. The problems associated with petroleum based polymer such as environmental pollution during the production and disposal can be alleviated by using a fully biodegradable and renewable polymer composites derived from seaweed wastes, sugar palm fibre, and thermoplastic sugar palm starch/agar blend.
4. In terms of waste management, this study has explored a new potential application of *Eucheuma cottonii* seaweed wastes from the carrageenan extraction as novel reinforcement for biopolymer composites.
5. Moreover, this study also utilizes the sugar palm tree for yielding starch and fibre for the development of the composites. Hence, added more value for the sugar palm tree other than producing the sugar.

1.5 Scope of study

In this study, *Eucheuma cottonii* seaweed wastes and the raw seaweed were characterized for their thermal, chemical, and physical properties. Later, starch extracted from sugar palm tree was used as the based material for the development of thermoplastic sugar palm starch. Thermoplastic sugar palm starch was developed by using glycerol as the plasticizer and further modified by using agar. Characterizations of their thermal, mechanical, and physical properties were performed. For the composites, *Eucheuma cottonii* seaweed wastes were incorporated into the thermoplastic sugar palm starch/agar blend and their properties were characterized. Hybridization of the composites were carried out by using the combination of sugar palm fibre and seaweed wastes as the reinforcement and the thermoplastic sugar palm starch/agar polymer blend as matrix. The thermal, mechanical, physical, and biodegradation properties of the hybrid composites were carried out. The relevant application for the composites developed in this study is a short-life product. Therefore, the potential application of the hybrid composites as biodegradable product i. e

disposable tray was evaluated through comparison on the primary characteristics against the conventional material and the current thermoplastic starch.

1.6 Structure of thesis

The structure of this thesis is in accordance with the alternative thesis format of Universiti Putra Malaysia which is based on the publications of this study. Each research chapter represent a separate study that has the introduction, methodology, results and discussion, and conclusions. The details of the structure are as follows:

Chapter 1

The problems that initiate this research and the research objectives were clearly highlighted in this chapter. The significance of this work and the scope of study were also elaborated within the chapter.

Chapter 2

This chapter presents a comprehensive literature review on the areas related to the topic of this thesis. In addition, the research gaps obtained from the review were also clarified within the chapter.

Chapter 3

This chapter presents the methodology used in this study for the preparation of materials, testing procedure, and data collection.

Chapter 4

This chapter presents the first article entitled “**Characteristics of *Eucheuma cottonii* waste from East Malaysia: physical, thermal, and chemical composition**”. In this article, the characteristics of the seaweed wastes and the raw seaweed were investigated.

Chapter 5

This chapter presents the second article entitled “**Characteristics of thermoplastic Sugar Palm starch/agar blend: Thermal, tensile, and physical properties**”. The effect of agar at different concentrations (0 - 40 wt%) on the thermal, tensile, and physical properties (moisture absorption and thickness swelling) of thermoplastic sugar palm starch were investigated In this article,.

Chapter 6

This chapter presents the fifth article entitled “**Effect of Seaweed on Mechanical, Thermal, and Biodegradation Properties of Thermoplastic Sugar Palm Starch/Agar Composites**”. In this article, the effect of seaweed wastes loading (0 – 40 wt%) on the mechanical, thermal, and biodegradation properties of thermoplastic sugar palm starch/agar composites were investigated.

Chapter 7

This chapter present the seventh article entitled “**Thermal, Mechanical, and Physical Properties of Seaweed/Sugar Palm Fibre Reinforced Thermoplastic Sugar Palm Starch/Agar Hybrid Composites**”. In this paper, the effect of sugar palm fibre/seaweed hybridization at several ratios (0:100, 25:75, 50:50, 75:25, and 100:0) were investigated.

Chapter 8

This chapter present the additional results of this research including the analysis and presentation of data, the discussion of results, and the correlation between the findings.

Chapter 9

This chapter presents the overall conclusions from the whole study as well as future recommendations for further improvement of this study.

REFERENCES

- Abbott, I. A. (1978). The uses of seaweeds as food in Hawaii. *Economic Botany*, 32(4), 409–412.
- Abdollahi, M., Alboofetileh, M., Behrooz, R., Rezaei, M., & Miraki, R. (2013). Reducing water sensitivity of alginate bio-nanocomposite film using cellulose nanoparticles. *International Journal of Biological Macromolecules*, 54, 166–173.
- Abdou, E. S., & Sorour, M. a. (2014). Preparation and characterization of starch / carrageenan edible films. *International Food Research Journal*, 21(1), 189–193.
- Abirami, R. G., & Kowsalya, S. (2011). Nutrient and nutraceutical potentials of seaweed biomass *Ulva lactuca* and *Kappaphycus alvarezii*. *Agricultural Science and Technology*, 5(1), 1–7.
- Adhikary, K. B., Pang, S., & Staiger, M. P. (2008). Long-term moisture absorption and thickness swelling behaviour of recycled thermoplastics reinforced with *Pinus radiata* sawdust. *Chemical Engineering Journal*, 142, 190–198.
- Albano, C., Karam, a., Domínguez, N., Sánchez, Y., González, J., Aguirre, O., & Cataño, L. (2005). Thermal, mechanical, morphological, thermogravimetric, rheological and toxicological behavior of HDPE/seaweed residues composites. *Composite Structures*, 71(3-4), 282–288.
- Alboofetileh, M., Rezaei, M., Hosseini, H., & Abdollahi, M. (2013). Effect of montmorillonite clay and biopolymer concentration on the physical and mechanical properties of alginate nanocomposite films. *Journal of Food Engineering*, 117(1), 26–33.
- Aldalbahi, A., Chu, J., Feng, P., & Panhuis, M. In Het. (2012). Conducting composite materials from the biopolymer kappa-carrageenan and carbon nanotubes. *Beilstein Journal of Nanotechnology*, 3, 415–427.
- Alebiowu, G., & Osinoiki, K. A. (2010). Assessment of Tapioca starches obtained after different steeping periods as binders in a paracetamol tablet formulation. *Farmacia*, 58, 341–352.
- Ali, A., Sanuddin, a. B., & Ezzeddin, S. (2010). The effect of aging on *Arenga pinnata* fiber-reinforced epoxy composite. *Materials and Design*, 31(7), 3550–3554.
- Alkbir, M. F. M., Sapuan, S. M., Nuraini, A. A., & Ishak, M. R. (2016). Fibre properties and crashworthiness parameters of natural fibre-reinforced composite structure: A literature review. *Composite Structures*, 148, 59–73.
- Al-oqla, F. M., Salit, M. S., & Ishak, R. (2014). Combined Multi-criteria Evaluation Stage Technique as an Agro Waste Evaluation Indicator for Polymeric Composites : Date Palm Fibers as a Case Study. *BioResources*, 9(3), 4608–4621.
- Al-Oqla, F. M., & Sapuan, S. M. (2014). Natural fiber reinforced polymer composites in industrial applications: Feasibility of date palm fibers for sustainable automotive industry. *Journal of Cleaner Production*, 66, 347–354.
- Alves, V. D., Castelló, R., Ferreira, A. R., Costa, N., Fonseca, I. M., & Coelho, I. M. (2011). Barrier properties of carrageenan/pectin biodegradable composite films. *Procedia Food Science*, 1, 240–245.

- Alves, V. D., Costa, N., & Coelho, I. M. (2010). Barrier properties of biodegradable composite films based on kappa-carrageenan/pectin blends and mica flakes. *Carbohydrate Polymers*, 79(2), 269–276.
- Arismendi, C., Chillo, S., Conte, A., Del Nobile, M. A., Flores, S., & Gerschenson, L. N. (2013). Optimization of physical properties of xanthan gum/tapioca starch edible matrices containing potassium sorbate and evaluation of its antimicrobial effectiveness. *LWT - Food Science and Technology*, 53(1), 290–296.
- Armisen, R., & Galatas, F. (1987). Production, Properties, and Uses of Agar. In D. J. McHugh (Ed.), *Production and utilization of products from commercial seaweeds*. Va delle Terme di Caracalla, Rome: Food and Agriculture Organization of the United Nations.
- Asgari, S., Jahanshahi, M., & Rahimpour, A. (2014). Cost-effective nanoporous Agar-Agar polymer/Nickel powder composite particle for effective bio-products adsorption by expanded bed chromatography. *Journal of Chromatography. A*, 1361, 191–202.
- Ashori, A., & Sheshmani, S. (2010). Hybrid composites made from recycled materials: Moisture absorption and thickness swelling behavior. *Bioresource Technology*, 101(12), 4717–4720.
- ASTM D256-02 2002. Standard Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics. American Society for Testing Materials.
- ASTM D638-00 2001. Standard Test Method for Tensile Properties of Plastics. American Society for Testing Materials.
- ASTM D790-00 2001. Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials. American Society for Testing Materials.
- Atef, M., Rezaei, M., & Behrooz, R. (2014). Preparation and characterization agar-based nanocomposite film reinforced by nanocrystalline cellulose. *International Journal of Biological Macromolecules*, 70, 537–544.
- Avérous L, B. N. (2004). Biocomposites based on plasticized starch: thermal and mechanical behaviour. *Carbohydrate Polymers*, 56, 111–122.
- Bachtar, D., Salit, M. S., Zainudin, E., Abdan, K., & Dahlan, K. Z. H. M. (2011). Effects of alkaline treatment and a compatibilizing agent on tensile properties of sugar palm fibrereinforced high impact polystyrene composites. *BioResources*, 6, 4815–4823.
- Bajdik, J., Makai, Z., Berkesi, O., Süvegh, K., Marek, T., Eros, I., & Pintye-Hódi, K. (2009). Study of the effect of lactose on the structure of sodium alginate films. *Carbohydrate Polymers*, 77, 530–535.
- Barghini, A., Ivanova, V. I., Imam, S. H., & Chiellini, E. (2010). Poly-(ε-caprolactone) (PCL) and poly(hydroxy-butyrates) (PHB) blends containing seaweed fibers: Morphology and thermal-mechanical properties. *Journal of Polymer Science Part A: Polymer Chemistry*, 48(23), 5282–5288.
- Beilvert, A., Chaubet, F., Chaunier, L., Guilois, S., Pavon-Djavid, G., Letourneur, D., ... Lourdin, D. (2014). Shape-memory starch for resorbable biomedical devices. *Carbohydrate Polymers*, 99, 242–8.

- Belibi, P. C., Daou, T. J., Ndjaka, J. M. B., Nsom, B., Michelin, L., & Durand, B. (2014). A Comparative Study of Some Properties of Cassava and Tree Cassava Starch Films. *Physics Procedia*, 55, 220–226.
- Benavides, S., Villalobos-Carvajal, R., & Reyes, J. E. (2012). Physical, mechanical and antibacterial properties of alginate film: Effect of the crosslinking degree and oregano essential oil concentration. *Journal of Food Engineering*, 110(2), 232–239.
- Boateng, J. S., Pawar, H. V., & Tetteh, J. (2013). Polyox and carrageenan based composite film dressing containing anti-microbial and anti-inflammatory drugs for effective wound healing. *International Journal of Pharmaceutics*, 441(1-2), 181–91.
- Bodirlau, R., Teaca, C.-A., & Spiridon, I. (2013). Influence of natural fillers on the properties of starch-based biocomposite films. *Composites Part B: Engineering*, 44(1), 575–583.
- Bootklad, M., & Kaewtatip, K. (2013). Biodegradation of thermoplastic starch/eggshell powder composites. *Carbohydrate Polymers*, 97(2), 315–320.
- Brindle, L. P., & Krochta, J. M. (2008). Physical properties of whey protein-hydroxypropylmethylcellulose blend edible films. *Journal of Food Science*, 73(9).
- Bulota, M., & Budtova, T. (2015a). PLA/algae composites: Morphology and mechanical properties. *Composites Part A: Applied Science and Manufacturing*, 73, 109–115.
- Bulota, M., & Budtova, T. (2015b). PLA/algae composites: morphology and mechanical properties. *Composites Part A: Applied Science and Manufacturing*, 73, 109–115.
- Cai, J., Xiong, Z., Zhou, M., Tan, J., Zeng, F., Meihuma, ... Xiong, H. (2014). Thermal properties and crystallization behavior of thermoplastic starch/poly(ε-caprolactone) composites. *Carbohydrate Polymers*, 102, 746–754.
- Campos, A., Marconcini, J. M., Martins-Franchetti, S. M., & Mattoso, L. H. C. (2012). The influence of UV-C irradiation on the properties of thermoplastic starch and polycaprolactone biocomposite with sisal bleached fibers. *Polymer Degradation and Stability*, 97(10), 1948–1955.
- Castañó, J., Rodríguez-Llamazares, S., Contreras, K., Carrasco, C., Pozo, C., Bouza, R., ... Giraldo, D. (2014). Horse chestnut (*Aesculus hippocastanum* L.) starch: Basic physico-chemical characteristics and use as thermoplastic material. *Carbohydrate Polymers*, 112, 677–685.
- Castillo, L. a., López, O. V., Ghilardi, J., Villar, M. a., Barbosa, S. E., & García, M. A. (2015). Thermoplastic starch/talc bionanocomposites. Influence of particle morphology on final properties. *Food Hydrocolloids*, 51, 432–440.
- Castillo, L., López, O., López, C., Zaritzky, N., García, M. A., Barbosa, S., & Villar, M. (2013). Thermoplastic starch films reinforced with talc nanoparticles. *Carbohydrate Polymers*, 95(2), 664–674.

- Chalid, M., Rahman, A., Ferdian, R., Nofrijon, & Priyono, B. (2015). On the Tensile Properties of Polylactide (PLA)/Arenga Pinnata Ijuk Fibre Composite. *Macromolecular Symposia*, 353, 108–114.
- Chan, S. W., Mirhosseini, H., Taip, F. S., Ling, T. C., & Tan, C. P. (2013). Comparative study on the physicochemical properties of κ -carrageenan extracted from *Kappaphycus alvarezii* (doty) doty ex Silva in Tawau, Sabah, Malaysia and commercial κ -carrageenans. *Food Hydrocolloids*, 30(2), 581–588.
- Chang, Y.-J., Choi, H.-W., Kim, H.-S., Lee, H., Kim, W., Kim, D.-O., ... Baik, M.-Y. (2014). Physicochemical properties of granular and non-granular cationic starches prepared under ultra high pressure. *Carbohydrate Polymers*, 99, 385–93.
- Cheng, J., Zheng, P., Zhao, F., & Ma, X. (2013). The composites based on plasticized starch and carbon nanotubes. *International Journal of Biological Macromolecules*, 59, 13–19.
- Chiellini, E., Cinelli, P., Ilieva, V. I., & Martera, M. (2008). Biodegradable thermoplastic composites based on polyvinyl alcohol and algae. *Biomacromolecules*, 9(3), 1007–13.
- Chitra, N., & Kumari, R. (2012). Studies on Polypropylene Biocomposite with Sea Weeds. *Research Journal of Pharmaceutical, Biological and Chemical Sciences*, 3(3), 1165–1170.
- Coativy, G., Gautier, N., Pontoire, B., Buléon, A., Lourdin, D., & Leroy, E. (2014). Shape memory starch-clay bionanocomposites. *Carbohydrate Polymers*, 116, 307–313.
- Comaposada, J., Gou, P., Marcos, B., & Arnau, J. (2015). Physical properties of sodium alginate solutions and edible wet calcium alginate coatings. *LWT - Food Science and Technology*, 64(1), 212–219.
- Cyras, V. P., Manfredi, L. B., Ton-That, M.-T., & Vázquez, A. (2008). Physical and mechanical properties of thermoplastic starch/montmorillonite nanocomposite films. *Carbohydrate Polymers*, 73, 55–63.
- Bachtiar, J. P. Siregar, A. S. bin Sulaiman, M. R. bin M. R. (2015). Tensile Properties of Hybrid Sugar Palm/Kenaf Fibre Reinforced Polypropylene Composites. *Applied Mechanics and Materials*, 695, 155–158.
- Da Róz, A. L., Ferreira, A. M., Yamaji, F. M., & Carvalho, A. J. F. (2012). Compatible blends of thermoplastic starch and hydrolyzed ethylene-vinyl acetate copolymers. *Carbohydrate Polymers*, 90(1), 34–40.
- Dang, K. M., & Yoksan, R. (2015). Development of thermoplastic starch blown film by incorporating plasticized chitosan. *Carbohydrate Polymers*, 115, 575–581. 5
- De Graaf, R. A., Karman, A. P., & Janssen, L. P. B. M. (2003). Material properties and glass transition temperatures of different thermoplastic starches after extrusion processing. *Starch/Stärke*, 55, 80–86.
- De Souza, A. C., Dias, A. M. a, Sousa, H. C., & Tadini, C. C. (2014). Impregnation of cinnamaldehyde into cassava starch biocomposite films using supercritical fluid technology for the development of food active packaging. *Carbohydrate Polymers*, 102, 830–7.

- Deng, Y., & Catchmark, J. M. (2014). Insoluble starch composite foams produced through microwave expansion. *Carbohydrate Polymers*, 111, 864–9.
- Diaz-Bleis, D., Freile-Pelegrín, Y., Vales-Pinzón, C., Martínez-Torres, P., & Alvarado-Gil, J. J. (2012). Preparation and Characterization of Algal Polysaccharides/Magnetite Microparticles Composite Films. *International Journal of Thermophysics*, 33(10-11), 2125–2131.
- Diaz-Bleis, D., Vales-Pinzón, C., Freile-Pelegrín, Y., & Alvarado-Gil, J. J. (2014). Thermal characterization of magnetically aligned carbonyl iron/agar composites. *Carbohydrate Polymers*, 99, 84–90.
- Edhirej, A., Sapuan, S. M., Jawaid, M., & Nur Ismarrubie Zahari. (2015). Cassava: Its Polymer, Fiber, Composite, and Application. *Polymer Composites*, 16, 1–16.
- El-Dash, A. a., Gonzales, R., & Ciol, M. (1983). Response surface methodology in the control of thermoplastic extrusion of starch. *Journal of Food Engineering*, 2, 129–152.
- El-hefian, E. A., Nasef, M. M., Yahaya, A. H., & Khan, R. A. (2010). PREPARATION AND CHARACTERIZATION OF CHITOSAN/AGAR BLENDS. *J. Chil. Chem. Soc.*, 55(1), 130–136.
- EPS Technical Data. 2012. Retrieved 17 June 2017 from <http://www.insultech-eps.com/techdata.html>
- Esmaeili, C., Ghasemi, M., Heng, L. Y., Hassan, S. H. a, Abdi, M. M., Daud, W. R. W., ... Ismail, A. F. (2014). Synthesis and application of polypyrrole/carrageenan nano-bio composite as a cathode catalyst in microbial fuel cells. *Carbohydrate Polymers*, 114, 253–9. doi:10.1016/j.carbpol.2014.07.072
- Evingür, G. A., & Pekcan, Ö. (2013). Superelastic percolation network of polyacrylamide (PAAm)–kappa carrageenan (κ C) composite. *Cellulose*, 20, 1145–1151. doi:10.1007/s10570-013-9903-9
- Evingür, G. A., & Pekcan, Ö. (2015). Kinetic models for the dynamical behavior of polyacrylamide (PAAm)– κ -carrageenan (κ C) composite gels. *Journal of Biological Physics*, 41, 37–47. doi:10.1007/s10867-014-9364-x
- Fabra, M. J., Talens, P., & Chiralt, A. (2008). Effect of alginate and λ -carrageenan on tensile properties and water vapour permeability of sodium caseinate–lipid based film. *Carbohydrate Polymers*, 74, 419–426.
- Fakharian, M.-H., Tamimi, N., Abbaspour, H., Nafchi, A. M., & Karim, a. a. (2015). Effects of κ -Carrageenan on Rheological Properties of Dually Modified Sago Starch: Towards Finding Gelatin Alternative for Hard Capsules. *Carbohydrate Polymers*, 132, 156–163.
- Fang, J. M., Fowler, P. a., Tomkinson, J., & Hill, C. a S. (2002). The preparation and characterisation of a series of chemically modified potato starches. *Carbohydrate Polymers*, 47, 245–252. doi:10.1016/S0144-8617(01)00187-4
- FAO. (2015). FAO Global Aquaculture Production statistics database updated to 2013: Summary information. *Food and Agriculture Organization of the United Nations*. Retrieved from <http://www.fao.org/3/a-i4899e.pdf>

- Fiore, V., Valenza, a., & Di Bella, G. (2011). Artichoke (*Cynara cardunculus* L.) fibres as potential reinforcement of composite structures. *Composites Science and Technology*, 71(8), 1138–1144.
- Fleurence, J. (1999). Seaweed proteins: biochemical, nutritional aspects and potential uses. *Trends in Food Science & Technology*, 10, 25–28.
- Flores, A. C., Punzalan, E. R., & Ambangan, N. G. (2015). Effects of Kappa-Carrageenan on the Physico-Chemical Properties of Thermoplastic Starch. *Kimika*, 26(JANUARY), 11–17.
- Forssell, P. M., Hulleman, S. H. D., Myllärinen A, P. J., Moates, G. K., & Parker, R. (1999). Ageing of rubbery thermoplastic barley and oat starches. *Carbohydrate Polymers*, 39, 43–51.
- Fortea, M. I., López-Miranda, S., Serrano-Martínez, a, Hernández-Sánchez, P., Zafrilla, M. P., Martínez-Cachá, a, & Núñez-Delicado, E. (2011). Kinetic characterisation and thermal inactivation study of red alga (*Mastocarpus stellatus*) peroxidase. *Food Chemistry*, 127(3), 1091–6.
- Fouda, M. M. G., El-Aassar, M. R., El Fawal, G. F., Hafez, E. E., Masry, S. H. D., & Abdel-Megeed, A. (2015). k-Carrageenan/poly vinyl pyrrolidone/polyethylene glycol/silver nanoparticles film for biomedical application. *International Journal of Biological Macromolecules*, 74, 179–84.
- Freile-Pelegrín, Y., Madera-Santana, T., Robledo, D., Veleza, L., Quintana, P., & Azamar, J. a. (2007). Degradation of agar films in a humid tropical climate: Thermal, mechanical, morphological and structural changes. *Polymer Degradation and Stability*, 92(2), 244–252.
- Freitas, O. M. M., Martins, R. J. E., Delerue-Matos, C. M., & Boaventura, R. a R. (2008). Removal of Cd(II), Zn(II) and Pb(II) from aqueous solutions by brown marine macro algae: Kinetic modelling. *Journal of Hazardous Materials*, 153, 493–501.
- Gade, R., Tulasi, M. S., & Bhai, V. A. (2013). Seaweeds: A Novel Biomaterial. *International Journal of Pharmacy and Pharmaceutical Sciences*, 5(2), 40–44.
- Gao, Z., & Zhao, L. (2015). Effect of nano-fillers on the thermal conductivity of epoxy composites with micro-Al₂O₃ particles. *Materials & Design*, 66, 176–182.
- Gashti, M. P., Stir, M., & Hulliger, J. (2013). Synthesis of bone-like micro-porous calcium phosphate/iota-carrageenan composites by gel diffusion. *Colloids and Surfaces. B, Biointerfaces*, 110, 426–33.
- Ghosh, S., Kaushik, R., Nagalakshmi, K., Hoti, S. L., Menezes, G. a, Harish, B. N., & Vasan, H. N. (2010). Antimicrobial activity of highly stable silver nanoparticles embedded in agar-agar matrix as a thin film. *Carbohydrate Research*, 345(15), 2220–7.
- Giménez, B., López de Lacey, a., Pérez-Santín, E., López-Caballero, M. E., & Montero, P. (2013). Release of active compounds from agar and agar–gelatin films with green tea extract. *Food Hydrocolloids*, 30(1), 264–271.
- Gironès, J., López, J. P., Mutjé, P., Carvalho, a. J. F., Curvelo, a. a S., & Vilaseca, F. (2012). Natural fiber-reinforced thermoplastic starch composites obtained by melt processing. *Composites Science and Technology*, 72, 858–863.

- González, A., & Alvarez Igarzabal, C. I. (2013). Soy protein - Poly (lactic acid) bilayer films as biodegradable material for active food packaging. *Food Hydrocolloids*, 33(2), 289–296.
- Haciu, D., Saner, S., Türdoğru, O., & Ünal, U. (2013). Study of Antibacterial Effects of a Self-Standing Agar Based Film Incorporated with ZnO. *Frontiers in Science*, 3(3), 96–101.
- Halley, P., Rutgers, R., Coombs, S., Kettels, J., Gralton, J., Christie, G., ... Lonergan, G. (2001). Developing biodegradable mulch films from starch-based polymers. *Starch/Stärke*, 53, 362–367.
- Hambleton, A., Voilley, A., & Debeaufort, F. (2011). Transport parameters for aroma compounds through i-carrageenan and sodium alginate-based edible films. *Food Hydrocolloids*, 25(5), 1128–1133.
- Harley, C. D. G., Anderson, K. M., Demes, K. W., Jorve, J. P., Kordas, R. L., Coyle, T. a., & Graham, M. H. (2012). Effects of Climate Change on Global Seaweed Communities. *Journal of Phycology*, 48(5), 1064–1078.
- Hassan, M. M., Mueller, M., Tartakowska, D. J., & Wagner, M. H. (2011). Mechanical Performance of Hybrid Rice Straw / Sea Weed Polypropylene Composites. *Journal of Applied Polymer Science*, 120, 1843–1849.
- Hassan, M. M., Mueller, M., Tartakowska, D. J., Wagner, M. H., & Khan, M. a. (2012). Effect of γ -Radiation on the Mechanical Performance of Hybrid Rice Straw/Seaweed-Polypropylene Composites. *Journal of Adhesion Science and Technology*, 25(15), 1961–1971.
- Hassan, M. M., Mueller, M., & Wagners, M. H. (2008). Exploratory study on seaweed as novel filler in polypropylene composite. *Journal of Applied Polymer Science*, 109(2), 1242–1247.
- Hassan, M. M., Wagner, M. H., Zaman, H. U., & Khan, M. a. (2010). Physico-Mechanical Performance of Hybrid Betel Nut (Areca catechu) Short Fiber/Seaweed Polypropylene Composite. *Journal of Natural Fibers*, 7(3), 165–177.
- He, G., Liu, Q., & Thompson, M. (2013). Characterization of structure and properties of thermoplastic potato starch film surface cross-linked by UV irradiation. *Starch - Stärke*, 65, 304–311.
- Hietala, M., Mathew, A. P., & Oksman, K. (2013). Bionanocomposites of thermoplastic starch and cellulose nanofibers manufactured using twin-screw extrusion. *European Polymer Journal*, 49(4), 950–956.
- Hill, D. R. (1996). Thin Agar Film for Enhanced Fungal Growth and Microscopic Viewing in a New Sealable Fungal Culture Case. *Journal of Clinical Microbiology*, 34(9), 2140–2142.
- Hong, I. K., Jeon, H., & Lee, S. B. (2014). Comparison of red, brown and green seaweeds on enzymatic saccharification process. *Journal of Industrial and Engineering Chemistry*, 20(5), 2687–2691.
- Hosseinzadeh, H. (2011). Preparation and Properties of Carrageenan-g-Poly(Acrylic Acid)/Bentonite Superabsorbent Composite. *Journal of Biomaterials and Nanobiotechnology*, 02(July), 311–317.

- Huang, M., & Yu, J. (2006). Structure and properties of thermoplastic corn starch/montmorillonite biodegradable composites. *Journal of Applied Polymer Science*, 99, 170–176.
- Huq, T., Salmieri, S., Khan, A., Khan, R. a., Le Tien, C., Riedl, B., ... Lacroix, M. (2012). Nanocrystalline cellulose (NCC) reinforced alginate based biodegradable nanocomposite film. *Carbohydrate Polymers*, 90(4), 1757–1763.
- Iannace, S., Nocilla, G., & Nicolais, L. (1999). Biocomposites based on sea algae fibers and biodegradable thermoplastic matrices. *Journal of Applied Polymer Science*, 73, 583–592.
- Ibrahim, H., Farag, M., Megahed, H., & Mehanny, S. (2014). Characteristics of starch-based biodegradable composites reinforced with date palm and flax fibers. *Carbohydrate Polymers*, 101, 11–19.
- Ichiura, H., Konishi, T., & Morikawa, M. (2009). Alginate film prepared on polyethylene nonwoven sheet and its function for ellagic acid release in response to sodium ions. *Journal of Materials Science*, 44, 992–997.
- Ishak, M. R., Leman, Z., Sapuan, S. M., Salleh, M. Y., & Misri, S. (2009). the Effect of Sea Water Treatment on the Impact and Flexural Strength of Sugar Palm Fibre Reinforced Epoxy Composites. *International Journal of Mechanical and Materials Engineering (IJMME)*, 4(3), 316–320.
- Ishak, M. R., Sapuan, S. M., Leman, Z., Rahman, M. Z. a, & Anwar, U. M. K. (2012). Characterization of sugar palm (*Arenga pinnata*) fibres Tensile and thermal properties. *Journal of Thermal Analysis and Calorimetry*, 109, 981–989.
- Ishak, M. R., Sapuan, S. M., Leman, Z., Rahman, M. Z. a, Anwar, U. M. K., & Siregar, J. P. (2013a). Sugar palm (*Arenga pinnata*): Its fibres, polymers and composites. *Carbohydrate Polymers*, 91(2), 699–710.
- Ishak, M. R., Sapuan, S. M., Leman, Z., Rahman, M. Z. a, Anwar, U. M. K., & Siregar, J. P. (2013). Sugar palm (*Arenga pinnata*): Its fibres, polymers and composites. *Carbohydrate Polymers*, 91(2), 699–710.
- Ishak, M. R., Sapuan, S. M., Leman, Z., Rahman, M. Z. A., Anwar, U. M. K., & Siregar, J. P. (2013b). Sugar palm (*Arenga pinnata*): Its fibres, polymers and composites. *Carbohydrate Polymers*, 91(2), 699–710.
- Islam, M. S., Hamdan, S., Rusop, M., Rahman, M. R., Ahmed, A. S., & Idrus, M. A. M. M. (2012). Dimensional Stability and Water Repellent Efficiency Measurement of Chemically Modified Tropical Light Hardwood. *Bioresources*, 7(1), 1221–1231.
- Jamsiah, S., Ramli, N., Daik, R., & Yarmo, M. A. (2013). Determination of the functional properties of *Kappaphycus alvarezii* seaweed powder. *The Malaysian Journal of Analytical Sciences*, 17(2), 236–243.
- Jang, S.-A., Lim, G.-O., & Song, K. Bin. (2010). Original article: Use of nano-clay (Cloisite Na⁺) improves tensile strength and vapour permeability in agar rich red algae (*Gelidium corneum*)-gelatin composite films. *International Journal of Food Science & Technology*, 45(9), 1883–1888.
- Jang, Y. H., Han, S. O., Sim, I. N., & Kim, H.-I. (2013). Pretreatment effects of seaweed on the thermal and mechanical properties of seaweed/polypropylene

- biocomposites. *Composites Part A: Applied Science and Manufacturing*, 47, 83–90.
- Jaswir, I., Tawakalit Tope, A.-H., Raus, R. a., Ademola Monsur, H., & Ramli, N. (2014). Study on anti-bacterial potentials of some Malaysian brown seaweeds. *Food Hydrocolloids*, 42, 275–279.
- Jawaid, M., Abdul Khalil, H. P. S., & Abu Bakar, a. (2011). Woven hybrid composites: Tensile and flexural properties of oil palm-woven jute fibres based epoxy composites. *Materials Science and Engineering: A*, 528(15), 5190–5195.
- Jawaid, M., Abdul Khalil, H. P. S., Noorunnisa Khanam, P., & Abu Bakar, a. (2011). Hybrid Composites Made from Oil Palm Empty Fruit Bunches/Jute Fibres: Water Absorption, Thickness Swelling and Density Behaviours. *Journal of Polymers and the Environment*, 19, 106–109.
- Jumaidin, R., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Sahari, J. (2016). Characteristics of Thermoplastic Sugar Palm Starch/Agar Blend: Thermal, Tensile, and Physical Properties. *International Journal of Biological Macromolecules*, 89, 575–581.
- Kahar, a. W. M., Ismail, H., & Abdul Hamid, a. (2016). The correlation between crosslink density and thermal properties of high-density polyethylene/natural rubber/thermoplastic tapioca starch blends prepared via dynamic vulcanisation approach. *Journal of Thermal Analysis and Calorimetry*, 123(1), 301–308.
- Kang, O. L., Ramli, N., Said, M., Ahmad, M., Yasir, S. M., & Ariff, A. (2011). *Kappaphycus alvarezii* waste biomass: A potential biosorbent for chromium ions removal. *Journal of Environmental Sciences*, 23(6), 918–922.
- Kanmani, P., & Rhim, J.-W. (2014a). Antimicrobial and physical-mechanical properties of agar-based films incorporated with grapefruit seed extract. *Carbohydrate Polymers*, 102, 708–16.
- Kanmani, P., & Rhim, J.-W. (2014b). Development and characterization of carrageenan/grapefruit seed extract composite films for active packaging. *International Journal of Biological Macromolecules*, 68, 258–66.
- Kanmani, P., & Rhim, J.-W. (2014c). Properties and characterization of bionanocomposite films prepared with various biopolymers and ZnO nanoparticles. *Carbohydrate Polymers*, 106, 190–199.
- Kasim, A. N., Selamat, M. Z., Aznan, N., Sahadan, S. N., Daud, M. A. M., Jumaidin, R., & Salleh, S. (2015). Effect of Pineapple Leaf Fiber Loading on the Mechanical Properties of Pineapple Leaf-Fiber Polypropylene Composite. *Jurnal Teknologi*, 77(21), 117–123.
- Kawatsu, K., Sakata, J., Yonekita, T., & Kumeda, Y. (2015). Evaluation of an immunochromatographic assay for direct identification of thermostable direct hemolysin-producing *Vibrio parahaemolyticus* colonies on selective agar plates. *Journal of Microbiological Methods*, 119, 4–6.
- Kebelmann, K., Hornung, A., Karsten, U., & Griffiths, G. (2013). Thermo-chemical behaviour and chemical product formation from Polar seaweeds during intermediate pyrolysis. *Journal of Analytical and Applied Pyrolysis*, 104, 131–138.

- Khanoonkon, N., Yoksan, R., & Ogale, A. a. (2016). Effect of stearic acid-grafted starch compatibilizer on properties of linear low density polyethylene/thermoplastic starch blown film. *Carbohydrate Polymers*, 137, 165–173.
- Kibar, H., & Esen, B. (2010). The effect of moisture content on physical and mechanical properties of rice (. *Spanish Journal of Agricultural Research*, 8(3), 741–749.
- Knitter, M., & Dobrzyńska-Mizera, M. (2015). Mechanical properties of isotactic polypropylene modified with thermoplastic potato starch. *Mechanics of Composite Materials*, 51(2), 245–252.
- Kofler, M., Lenninger, M., Mayer, G., Neuwirt, H., Grimm, M., & Bechtold, T. (2016). Multi-chamber electroosmosis using textile reinforced agar membranes – A promising concept for the future of hemodialysis. *Carbohydrate Polymers*, 136, 81–86.
- Ku, K.-J., Hong, Y.-H., & Song, K. B. (2008). Mechanical properties of a Gelidium corneum edible film containing catechin and its application in sausages. *Journal of Food Science*, 73(3), C217–21.
- Kuciel, S., & Liber-Knec, A. (2009). Biocomposites on the Base of Thermoplastic Starch Filled by Wood and Kenaf Fiber. *Journal of Biobased Materials and Bioenergy*, 3(3), 269–274.
- Lafargue, D., Lourdin, D., & Doublier, J. L. (2007). Film-forming properties of a modified starch/??-carrageenan mixture in relation to its rheological behaviour. *Carbohydrate Polymers*, 70, 101–111.
- Lawrie, G., Keen, I., Drew, B., Chandler-Temple, A., Rintoul, L., Fredericks, P., & Grøndahl, L. (2007). Interactions between alginate and chitosan biopolymers characterized using FTIR and XPS. *Biomacromolecules*, 8, 2533–2541.
- Le Bolay, N., & Molina-Boisseau, S. (2014). Production of PVAc-starch composite materials by co-grinding - Influence of the amylopectin to amylose ratio on the properties. *Powder Technology*, 255, 36–43.
- Lee, J. M., Mohd Ishak, Z. a., Mat Taib, R., Law, T. T., & Ahmad Thirmizir, M. Z. (2013). Mechanical, Thermal and Water Absorption Properties of Kenaf-Fiber-Based Polypropylene and Poly(Butylene Succinate) Composites. *Journal of Polymers and the Environment*, 21, 293–302.
- Lee, K. O., Ramli, N., Said, M., Ahmad, M., Yasir, S. M., & Ariff, A. (2011). Copper (II) and Nickel (II) Sorption onto Seaweed (Kappaphycus alvarezii) Waste Biomass : Equilibrium and Mechanism Studies. *Middle-East Journal of Scientific Research*, 9(1), 84–89.
- Lee, M. W., Han, S. O., & Seo, Y. B. (2008). Red algae fibre/poly(butylene succinate) biocomposites: The effect of fibre content on their mechanical and thermal properties. *Composites Science and Technology*, 68(6), 1266–1272.
- Li, D., Chen, L., Zhang, X., Ye, N., & Xing, F. (2011). Pyrolytic characteristics and kinetic studies of three kinds of red algae. *Biomass and Bioenergy*, 35(5), 1765–1772.

- Li, J., Luo, X., Lin, X., & Zhou, Y. (2013). Comparative study on the blends of PBS/thermoplastic starch prepared from waxy and normal corn starches. *Starch/Staerke*, 65, 831–839.
- Li, L., Ni, R., Shao, Y., & Mao, S. (2014). Carrageenan and its applications in drug delivery. *Carbohydrate Polymers*, 103, 1–11.
- Li, M., Witt, T., Xie, F., Warren, F. J., Halley, P. J., & Gilbert, R. G. (2015). Biodegradation of starch films: The roles of molecular and crystalline structure. *Carbohydrate Polymers*, 122, 115–122.
- Liling, G., Di, Z., Jiachao, X., Xin, G., Xiaoting, F., & Qing, Z. (2016). Effects of ionic crosslinking on physical and mechanical properties of alginate mulching films. *Carbohydrate Polymers*, 136, 259–265.
- Lim, G.-O., Jang, S.-A., & Song, K. Bin. (2010). Physical and antimicrobial properties of Gelidium corneum/nano-clay composite film containing grapefruit seed extract or thymol. *Journal of Food Engineering*, 98(4), 415–420.
- Liu, D., Qi, Z., Zhang, Y., Xu, J., & Guo, B. (2015). Poly(butylene succinate) (PBS)/ionic liquid plasticized starch blends: Preparation, characterization, and properties. *Starch - Stärke*, 67, 802–809.
- Liu, J., Zhan, X., Wan, J., Wang, Y., & Wang, C. (2015). Review for carrageenan-based pharmaceutical biomaterials: favourable physical features versus adverse biological effects. *Carbohydrate Polymers*, 121, 27–36.
- Liu, K., Lin, X., Chen, L., Huang, L., & Cao, S. (2013). Dual-functional chitosan-methylisothiazolinone/microfibrillated cellulose biocomposites for enhancing antibacterial and mechanical properties of agar films. *Cellulose*, 21(1), 519–528.
- Lomelí Ramírez, M. G., Satyanarayana, K. G., Iwakiri, S., De Muniz, G. B., Tanobe, V., & Flores-Sahagun, T. S. (2011). Study of the properties of biocomposites. Part I. Cassava starch-green coir fibers from Brazil. *Carbohydrate Polymers*, 86, 1712–1722.
- Lomelí Ramírez, M. G., Satyanarayana, K. G., Iwakiri, S., de Muniz, G. B., Tanobe, V., & Flores-Sahagun, T. S. (2011). Study of the properties of biocomposites. Part I. Cassava starch-green coir fibers from Brazil. *Carbohydrate Polymers*, 86(4), 1712–1722.
- Lomelí-Ramírez, M. G., Kestur, S. G., Manríquez-González, R., Iwakiri, S., de Muniz, G. B., & Flores-Sahagun, T. S. (2014). Bio-composites of cassava starch-green coconut fiber: part II-Structure and properties. *Carbohydrate Polymers*, 102, 576–83.
- López, O., Castillo, L., Zaritzky, N., Barbosa, S., Villar, M., & García, M. A. (2015). Talc Nanoparticles Influence on Thermoplastic Corn Starch Film Properties. *Procedia Materials Science*, 8, 338–345.
- Lopez, O., Garcia, M. a., Villar, M. a., Gentili, a., Rodriguez, M. S., & Albertengo, L. (2014). Thermo-compression of biodegradable thermoplastic corn starch films containing chitin and chitosan. *LWT - Food Science and Technology*, 57(1), 106–115.

- López, O. V., Castillo, L. a., García, M. A., Villar, M. a., & Barbosa, S. E. (2014). Food packaging bags based on thermoplastic corn starch reinforced with talc nanoparticles. *Food Hydrocolloids*, 43, 18–24.
- Luan, L., Wu, W., Wagner, M. H., & Mueller, M. (2010). Seaweed as novel biofiller in polypropylene composites. *Journal of Applied Polymer Science*, 997–1005.
- Luk, C. M., Tang, L. B., Zhang, W. F., Yu, S. F., Teng, K. S., & Lau, S. P. (2012). An efficient and stable fluorescent graphene quantum dot–agar composite as a converting material in white light emitting diodes. *Journal of Materials Chemistry*, 22(42), 22378.
- Luzia, A., Róz, D., Veiga-santos, P., & Medeiros, A. (2015). Water Susceptibility and Mechanical Properties of Thermoplastic Starch – Pectin Blends Reactively Extruded with Edible Citric Acid. *Materials Research*, (C).
- Ma, X. F., Yu, J. G., & Wan, J. J. (2006). Urea and ethanolamine as a mixed plasticizer for thermoplastic starch. *Carbohydrate Polymers*, 64, 267–273.
- Mabeau, S., & Fleurence, J. (1993). Seaweed in food products: biochemical and nutritional aspects. *Trends in Food Science & Technology*, 4(April), 103–107.
- Madera-Santana, T. J., Robledo, D., & Freile-Pelegrín, Y. (2011). Physicochemical properties of biodegradable polyvinyl alcohol-agar films from the red algae *Hydropuntia cornea*. *Marine Biotechnology (New York, N.Y.)*, 13(4), 793–800.
- Magalhães, N. F., & Andrade, C. T. (2009). Thermoplastic corn starch/clay hybrids: Effect of clay type and content on physical properties. *Carbohydrate Polymers*, 75(4), 712–718.
- Mano, J. F., Koniarova, D., & Reis, R. L. (2003). Thermal properties of thermoplastic starch/synthetic polymer blends with potential biomedical applicability. *Journal of Materials Science: Materials in Medicine*, 14(i), 127–135.
- Maran, J. P., Sivakumar, V., Sridhar, R., & Thirugnanasambandham, K. (2013). Development of model for barrier and optical properties of tapioca starch based edible films. *Carbohydrate Polymers*, 92(2), 1335–47.
- Maran, J. P., Sivakumar, V., Thirugnanasambandham, K., & Sridhar, R. (2014). Degradation behavior of biocomposites based on cassava starch buried under indoor soil conditions. *Carbohydrate Polymers*, 101, 20–8.
- Margarida, A., & Sousa, M. De. (2014). Development and Optimization of an Alternative and Environmentally Friendly Agar Extraction Process. *PhD Thesis*.
- Martínez, D. G., Stading, M., & Hermansson, A. M. (2013). Viscoelasticity and microstructure of a hierarchical soft composite based on nano-cellulose and κ -carrageenan. *Rheologica Acta*, 52, 823–831.
- Martins, A. B., & Santana, R. M. C. (2016). Effect of carboxylic acids as compatibilizer agent on mechanical properties of thermoplastic starch and polypropylene blends. *Carbohydrate Polymers*, 135, 79–85.
- Martins, J. T., Cerqueira, M. a., Bourbon, A. I., Pinheiro, A. C., Souza, B. W. S., & Vicente, A. a. (2012). Synergistic effects between κ -carrageenan and locust bean gum on physicochemical properties of edible films made thereof. *Food Hydrocolloids*, 29(2), 280–289.

- Mathew, A. P., & Dufresne, A. (2002). Morphological Investigation of Nanocomposites from Sorbitol Plasticized Starch and Tunicin Whiskers. *Biomacromolecules*, 3, 609–617.
- McHugh, D. . (2003). *A guide to the seaweed industry*. FAO Fisheries Technical Paper 441. Rome: Food and Agriculture Organisation of the United Nations.
- McHugh, D. J. (1991). Worldwide distribution of commercial resources of seaweeds including Gelidium. *Hydrobiologia*, 221(1), 19–29.
- Mechakra, H., Nour, a., Lecheb, S., & Chellil, a. (2015). Mechanical characterizations of composite material with short Alfa fibers reinforcement. *Composite Structures*, 124, 152–162.
- Mendes, J. F., Paschoalin, R. ., Carmona, V. B., Sena Neto, A. R., Marques, a. C. P., Marconcini, J. M., ... Oliveira, J. E. (2015). Biodegradable Polymer Blends Based on Cornstarch and Thermoplastic Chitosan Processed By Extrusion. *Carbohydrate Polymers*, 137, 452–458.
- Misra, M., Drzal, L. T., & Robledo, D. (2009). Preparation and Characterization of Biodegradable Agar / Poly (butylene adipate- co -terephthalate) Composites. *Polymer Engineering and Science*.
- Miyashita, K., Mikami, N., & Hosokawa, M. (2013). Chemical and nutritional characteristics of brown seaweed lipids: A review. *Journal of Functional Foods*, 5(4), 1507–1517.
- Mogea, J., Seibert, B., & Smits, W. (1991). Multipurpose palms: the sugar palm (Arenga pinnata (Wurmb) Merr.). *Agroforestry Systems*, 13, 111–129.
- Mohammadi Nafchi, A., Moradpour, M., Saeidi, M., & Alias, A. K. (2013). Thermoplastic starches: Properties, challenges, and prospects. *Starch - Stärke*, 65, 61–72.
- Mohsenkhani, S., Jahanshahi, M., & Rahimpour, A. (2015). Cross-linked κ -carrageenan polymer/zinc nanoporous composite matrix for expanded bed application: Fabrication and hydrodynamic characterization. *Journal of Chromatography A*, 1408, 178–186.
- Moreira, R., Chenlo, F., Torres, M. D., Silva, C., Prieto, D. M., Sousa, a. M. M., ... Gonçalves, M. P. (2011). Drying Kinetics of Biofilms Obtained from Chestnut Starch and Carrageenan with and without Glycerol. *Drying Technology*, 29(9), 1058–1065.
- Mujaheddin, Jagadish, R., Sheshappa, R., & Guru, G. (2012). Miscibility Studies of Agar-Agar / Starch blends using Various Techniques. *International Journal of Research in Pharmacy and Chemistry*, 2(4), 1049–1056.
- Mukhtar, I., Leman, Z., Ishak, M. R., & Zainudin, E. S. (2016). Sugar Palm Fibre and its Composites: A Review of Recent Developments. *BioResources*, 11(4), 10756–10782.
- N. Saheb, D., & Jog, J. P. (1999). Natural fiber polymer composites: A review. *Advances in Polymer Technology*, 18(4), 351–363.
- Nadhari, W. N. A. W., Hashim, R., Hiziroglu, S., Sulaiman, O., Boon, J. G., Salleh, K. M., ... Sugimoto, T. (2014). Measurement of some properties of binderless

- composites manufactured from oil palm trunks and *Acacia mangium*. *Measurement: Journal of the International Measurement Confederation*, 50, 250–254.
- Nadlene, R., Sapuan, S. M., Jawaid, M., Ishak, M. R., & Yusriah, L. (2016). The Effects of Chemical Treatment on the Structural and Thermal, Physical, and Mechanical and Morphological Properties of Roselle Fiber-Reinforced Vinyl Ester Composites. *Polymers and Polymer Composites*, 1–14.
- Narkchamnan, S., & Sakdaronnarong, C. (2013). Thermo-molded biocomposite from cassava starch, natural fibers and lignin associated by laccase-mediator system. *Carbohydrate Polymers*, 96(1), 109–17.
- Nascimento, T. A., Calado, V., & Carvalho, C. W. P. (2012). Development and characterization of flexible film based on starch and passion fruit mesocarp flour with nanoparticles. *Food Research International*, 49(1), 588–595.
- Olivas, G. I., & Barbosa-Cánovas, G. V. (2008). Alginate-calcium films: Water vapor permeability and mechanical properties as affected by plasticizer and relative humidity. *LWT - Food Science and Technology*, 41, 359–366.
- Park, H., Lee, W., & Park, C. (2003). Environmentally friendly polymer hybrids. *Science*, 8, 909 – 915.
- Park, S. Y., Lee, B. I., Jung, S. T., & Park, H. J. (2001). Biopolymer composite films based on k-carrageenan and chitosan. *Materials Research Bulletin*, 36, 511–519.
- Patarra, R. F., Paiva, L., Neto, A. I., Lima, E., & Baptista, J. (2011). Nutritional value of selected macroalgae. *Journal of Applied Phycology*, 23, 205–208.
- Peddiredy, S., Longhurst, P. J., & Wagland, S. T. (2015). Characterising the composition of waste-derived fuels using a novel image analysis tool. *Waste Management*, 40, 9–13.
- Peinado, I., Girón, J., Koutsidis, G., & Ames, J. M. (2014). Chemical composition, antioxidant activity and sensory evaluation of five different species of brown edible seaweeds. *Food Research International*, 66, 36–44.
- Pereira, L., Sousa, A., Coelho, H., Amado, A. M., & Ribeiro-Claro, P. J. a. (2003). Use of FTIR, FT-Raman and ¹³C-NMR spectroscopy for identification of some seaweed phycocolloids. *Biomolecular Engineering*, 20, 223–228.
- Pereira, L., & Van De Velde, F. (2011). Portuguese carrageenophytes: Carrageenan composition and geographic distribution of eight species (Gigartinales, Rhodophyta). *Carbohydrate Polymers*, 84(1), 614–623.
- Pérez, S., Baldwin, P. M., & Gallant, D. J. (2009). *Structural Features of Starch Granules I. Starch* (Third Edit., pp. 149–192). Elsevier Inc.
- Phan, D., Debeaufort, F., & Luu, D. (2005). Functional Properties of Edible Agar-Based and Starch-Based Films for Food Quality Preservation. *Journal of Agricultural and Food Chemistry*, 53, 973–981.
- Phan The, D., Debeaufort, F., Luu, D., & Voilley, a. (2008). Moisture barrier, wetting and mechanical properties of shellac/agar or shellac/cassava starch bilayer biomembrane for food applications. *Journal of Membrane Science*, 325(1), 277–283.

- Phan The, D., Debeaufort, F., Voilley, a., & Luu, D. (2009). Biopolymer interactions affect the functional properties of edible films based on agar, cassava starch and arabinoxylan blends. *Journal of Food Engineering*, 90(4), 548–558.
- Polylactic Acid (PLA, Polylactide). 2016. Retrieved 17 June 2017 from <http://www.makeitfrom.com/material-properties/Polylactic-Acid-PLA-Polylactide>
- Polypropylene. 2017. Retrieved 17 June 2017 from <https://en.wikipedia.org/wiki/Polypropylene>
- Prachayawarakorn, J., Chaiwatyothin, S., Mueangta, S., & Hanchana, A. (2013). Effect of jute and kapok fibers on properties of thermoplastic cassava starch composites. *Materials and Design*, 47, 309–315.
- Prachayawarakorn, J., & Hwansanoet, W. (2012). Effect of silk protein fibers on properties of thermoplastic rice starch. *Fibers and Polymers*, 13(5), 606–612.
- Prachayawarakorn, J., Limsiriwong, N., Kongjindamunee, R., & Surakit, S. (2011). Effect of Agar and Cotton Fiber on Properties of Thermoplastic Waxy Rice Starch Composites. *Journal of Polymers and the Environment*, 20(1), 88–95.
- Prachayawarakorn, J., & Pomdage, W. (2014). Effect of carrageenan on properties of biodegradable thermoplastic cassava starch/low-density polyethylene composites reinforced by cotton fibers. *Materials & Design*, 61, 264–269.
- Prachayawarakorn, J., Ruttanabus, P., & Boonsom, P. (2011). Effect of Cotton Fiber Contents and Lengths on Properties of Thermoplastic Starch Composites Prepared from Rice and Waxy Rice Starches. *Journal of Polymers and the Environment*, 19, 274–282.
- Prachayawarakorn, J., Sangnitidej, P., & Boonpasith, P. (2010). Properties of thermoplastic rice starch composites reinforced by cotton fiber or low-density polyethylene. *Carbohydrate Polymers*, 81(2), 425–433.
- Prajapati, V. D., Maheriya, P. M., Jani, G. K., & Solanki, H. K. (2014). Carrageenan: a natural seaweed polysaccharide and its applications. *Carbohydrate Polymers*, 105, 97–112.
- Pranoto, Y., Salokhe, V. M., & Rakshit, S. K. (2005). Physical and antibacterial properties of alginate-based edible film incorporated with garlic oil. *Food Research International*, 38, 267–272.
- Priya, B., Gupta, V. K., Pathania, D., & Singha, A. S. (2014). Synthesis, characterization and antibacterial activity of biodegradable starch/PVA composite films reinforced with cellulosic fibre. *Carbohydrate Polymers*, 109, 171–9.
- Raabe, J., Fonseca, A. D. S., Bufalino, L., Ribeiro, C., Martins, M. A., Marconcini, J. M., ... Tonoli, G. H. D. (2015). Biocomposite of Cassava Starch Reinforced with Cellulose Pulp Fibers Modified with Deposition of Silica (SiO₂) Nanoparticles. *Journal of Nanomaterials*, 2015, 1–9.
- Rahmat, A. R., Rahman, W. A. W. A., Sin, L. T., & Yussuf, A. A. (2009). Approaches to improve compatibility of starch filled polymer system: A review. *Materials Science and Engineering C*, 29(8), 2370–2377.

- Ramanaiah, K., Ratna Prasad, a. V., & Hema Chandra Reddy, K. (2012). Effect of fiber loading on mechanical properties of borassus seed shoot fiber reinforced polyester composites. *Journal of Materials and Environmental Science*, 3(3), 374–378.
- Ramesh, S., Shanti, R., & Morris, E. (2012). Studies on the plasticization efficiency of deep eutectic solvent in suppressing the crystallinity of corn starch based polymer electrolytes. *Carbohydrate Polymers*, 87(1), 701–706.
- Raphael, E., Avellaneda, C. O., Manzolli, B., & Pawlicka, A. (2010). Agar-based films for application as polymer electrolytes. *Electrochimica Acta*, 55(4), 1455–1459.
- Rashid, B., Leman, Z., Jawaid, M., Ghazali, M. J., & Ishak, M. R. (2016). Physicochemical and thermal properties of lignocellulosic fiber from sugar palm fibers: effect of treatment. *Cellulose*, 1–12.
- Ray, S. S., & Bousmina, M. (2005). Biodegradable polymers and their layered silicate nanocomposites: In greening the 21st century materials world. *Progress in Materials Science*, 50, 962–1079.
- Razali, N., Salit, M. S., Jawaid, M., Ishak, M. R., & Lazim, Y. (2015). A Study on Chemical Composition, Physical, Tensile, Morphological, and Thermal Properties of Roselle Fibre: Effect of Fibre Maturity. *Bioresources*, 10, 1803–1823.
- Reddy, J. P., & Rhim, J.-W. (2014). Characterization of bionanocomposite films prepared with agar and paper-mulberry pulp nanocellulose. *Carbohydrate Polymers*, 110, 480–8.
- Rhim, J. W., Wang, L. F., & Hong, S. I. (2013). Preparation and characterization of agar/silver nanoparticles composite films with antimicrobial activity. *Food Hydrocolloids*, 33(2), 327–335.
- Rhim, J.-W. (2004). Physical and mechanical properties of water resistant sodium alginate films. *LWT - Food Science and Technology*, 37, 323–330.
- Rhim, J.-W. (2011). Effect of clay contents on mechanical and water vapor barrier properties of agar-based nanocomposite films. *Carbohydrate Polymers*, 86(2), 691–699.
- Rhim, J.-W. (2012). Physical-mechanical properties of agar/ κ -carrageenan blend film and derived clay nanocomposite film. *Journal of Food Science*, 77(12), N66–73.
- Rhim, J.-W., Lee, S.-B., & Hong, S.-I. (2011). Preparation and characterization of agar/clay nanocomposite films: the effect of clay type. *Journal of Food Science*, 76(3), N40–8.
- Rhim, J.-W., & Wang, L.-F. (2013). Mechanical and water barrier properties of agar/ κ -carrageenan/konjac glucomannan ternary blend biohydrogel films. *Carbohydrate Polymers*, 96(1), 71–81.
- Rhim, J.-W., & Wang, L.-F. (2014). Preparation and characterization of carrageenan-based nanocomposite films reinforced with clay mineral and silver nanoparticles. *Applied Clay Science*, 97–98, 174–181.

- Rhim, J.-W., Wang, L.-F., Lee, Y., & Hong, S.-I. (2014). Preparation and characterization of bio-nanocomposite films of agar and silver nanoparticles: laser ablation method. *Carbohydrate Polymers*, 103, 456–65.
- Rivadeneira, J., Carina Audisio, M., Boccaccini, a R., & Gorustovich, a a. (2013). In vitro antistaphylococcal effects of a novel 45S5 bioglass/agar-gelatin biocomposite films. *Journal of Applied Microbiology*, 115(2), 604–12.
- Robledo, D., Azamar, J. A., & Rı, C. R. (2010). Preparation and Characterization of Low Density Polyethylene-Agar Biocomposites: Torque-Rheological, Mechanical , Thermal and Morphological Properties. *Polymer Engineering and Science*.
- Rosa, R. C. R. S., & Andrade, C. T. (2004). Effect of Chitin Addition on Injection-Molded Thermoplastic Corn Starch. *Journal of Applied Polymer Science*, 92, 2706–2713.
- Ross, A. B., Jones, J. M., Kubacki, M. L., & Bridgeman, T. (2008). Classification of macroalgae as fuel and its thermochemical behaviour. *Bioresource Technology*, 99, 6494–6504.
- S. M. Sapuan; H. Y. Lok; M. R. Ishak; S. Misri. (2013). Mechanical properties of hybrid glass/sugar palm fibre reinforced unsaturated polyester composites. *Chinese Journal of Polymer Science*, 31(10), 1394–1403.
- Sabetzadeh, M., Bagheri, R., & Masoomi, M. (2016). Effect of nanoclay on the properties of low density polyethylene/linear low density polyethylene/thermoplastic starch blend films. *Carbohydrate Polymers*, 141, 75–81.
- Sahari, J., Salit, M. S., Zainudin, E. S., & Maleque, M. A. (2014). Degradation Characteristics of SPF / SPS Biocomposites. *FIBRES & TEXTILES in Eastern Europe*, 5(107), 96–98.
- Sahari, J., Sapuan, S. M., Ismarrubie, Z. N., & Rahman, M. Z. a. (2012). Physical and chemical properties of different morphological parts of sugar palm fibres. *Fibres and Textiles in Eastern Europe*, 91(91), 21–24.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. a. (2013a). Thermo-mechanical behaviors of thermoplastic starch derived from sugar palm tree (< i> Arenga pinnata</i>). *Carbohydrate Polymers*, 92(2), 1711–1716.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2012). A New Approach to Use Arenga pinnata as Sustainable Biopolymer : Effects of Plasticizers on Physical Properties. *Procedia Chemistry*, 4, 254–259.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2013a). Flexural and Impact Properties of Biopolymer Derived from Sugar Palm Tree. *Advanced Materials Research*, 701, 225–228.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2013b). Mechanical and thermal properties of environmentally friendly composites derived from sugar palm tree. *Materials and Design*, 49, 285–289.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. a. (2013b). Mechanical and thermal properties of environmentally friendly composites derived from sugar palm tree. *Materials and Design*, 49, 285–289.

- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2013c). Thermo-mechanical behaviors of thermoplastic starch derived from sugar palm tree (*Arenga pinnata*). *Carbohydrate Polymers*, 92, 1711–1716.
- Sahari, J., Sapuan, S. M., Zainudin, E. S., & Maleque, M. A. (2014). Physico-chemical and thermal properties of starch derived from sugar palm tree (*Arenga pinnata*). *Asian Journal of Chemistry*, 26(4), 955–959.
- Sánchez-García, M. D., Hilliou, L., & Lagarón, J. M. (2010). Morphology and water barrier properties of nanobiocomposites of κ /1-hybrid carrageenan and cellulose nanowhiskers. *Journal of Agricultural and Food Chemistry*, 58, 12847–57.
- Sanchez-Silva, L., López-González, D., Garcia-Minguillan, a. M., & Valverde, J. L. (2013). Pyrolysis, combustion and gasification characteristics of *Nannochloropsis gaditana* microalgae. *Bioresource Technology*, 130, 321–331.
- Santos, G. a. (1989). Carrageenans of species of *Eucheuma* J. Agardh and *Kappaphycus* Doty (Solieriaceae, Rhodophyta). *Aquatic Botany*, 36, 55–67.
- Sanyang, M. L., Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2015). Effect of Plasticizer Type and Concentration on Dynamic Mechanical Properties of Sugar Palm Starch Based Films. *International Journal of Polymer Analysis and Characterization*, (July), 150622104055002.
- Sanyang, M. L., Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2015). Effect of Plasticizer Type and Concentration on Tensile, Thermal and Barrier Properties of Biodegradable Films Based on Sugar Palm (*Arenga pinnata*) Starch. *Polymers*, 7, 1106–1124.
- Sanyang, M. L., Sapuan, S. M., Jawaidd, M., Ishak, M. R., & Sahari, J. (2016). Development and characterization of sugar palm starch and poly(lactic acid) bilayer films. *Carbohydrate Polymers*, 146, 36–45.
- Sapuan, S. M., & Bachtiar, D. (2012). Mechanical Properties of Sugar Palm Fibre Reinforced High Impact Polystyrene Composites. *Procedia Chemistry*, 4, 101–106.
- Sapuan, S. M., Lok, H. Y., Ishak, M. R., & Misri, S. (2013). Mechanical properties of hybrid glass/sugar palm fibre reinforced unsaturated polyester composites. *Chinese Journal of Polymer Science*, 31(10), 1394–1403. doi:10.1007/s10118-013-1342-4
- Sarifuddin, N., Ismail, H., & Ahmad, Z. (2012). Effect of fiber loading on properties of thermoplastic sago starch/kenaf core fiber biocomposites. *BioResources*, 7, 4294–4306.
- Sastra, H. Y., Siregar, J. P., Sapuan, S. M., & Hamdan, M. M. (2006). Tensile Properties of *Arenga pinnata* Fiber-Reinforced Epoxy Composites. *Polymer-Plastics Technology and Engineering*, 45(April 2015), 149–155.
- Selamat, M. Z., Razi, M., Kasim, A. N., Dharmalingam, S., Putra, A., Yaakob, M. Y., & Mohd Daud, M. A. (2016). Mechanical properties of starch composite reinforced by pineapple leaf fiber (PLF) from josapine cultivar. *ARPJ Journal of Engineering and Applied Sciences*, 11(16), 9783–9788.

- Selvakumaran, S., Muhamad, I. I., & Abd Razak, S. I. (2016). Evaluation of kappa carrageenan as potential carrier for floating drug delivery system: Effect of pore forming agents. *Carbohydrate Polymers*, 135, 207–214.
- Shamsuri, A., Daik, R., Zainudin, E., & Tahir, P. (2014). Compatibilization of HDPE/agar biocomposites with eutectic-based ionic liquid containing surfactant. *Journal of Reinforced Plastics and Composites*, 33(5), 440–453.
- Shankar, S., Reddy, J. P., Rhim, J.-W., & Kim, H.-Y. (2015). Preparation, characterization, and antimicrobial activity of chitin nanofibrils reinforced carrageenan nanocomposite films. *Carbohydrate Polymers*, 117, 468–475.
- Siddhanta, A. K., Prasad, K., Meena, R., Prasad, G., Mehta, G. K., Chhatbar, M. U., ... Sanandiyaa, N. D. (2009). Profiling of cellulose content in Indian seaweed species. *Bioresource Technology*, 100(24), 6669–73.
- Silva, M. A. Da, Bierhalz, A. C. K., & Kieckbusch, T. G. (2009). Alginate and pectin composite films crosslinked with Ca^{2+} ions: Effect of the plasticizer concentration. *Carbohydrate Polymers*, 77(4), 736–742.
- Sim, K. J., Han, S. O., & Seo, Y. B. (2010). Dynamic mechanical and thermal properties of red algae fiber reinforced poly(lactic acid) biocomposites. *Macromolecular Research*, 18(5), 489–495.
- Singh, N., Singh, J., Kaur, L., Sodhi, N. S., & Gill, B. S. (2003). Morphological, thermal and rheological properties of starches from different botanical sources. *Food Chemistry*, 81, 219–231.
- Singh, V., Okadome, H., Toyoshima, H., Isobe, S., & Ohtsubo, K. (2000). Thermal and physicochemical properties of rice grain, flour and starch. *Journal of Agricultural and Food Chemistry*, 48, 2639–2647.
- Sirviö, J. A., Kolehmainen, A., Liimatainen, H., Niinimäki, J., & Hormi, O. E. O. (2014). Biocomposite cellulose-alginate films: promising packaging materials. *Food Chemistry*, 151, 343–51.
- Sousa, A. M. M., & Gonçalves, M. P. (2015). Strategies to improve the mechanical strength and water resistance of agar films for food packaging applications. *Carbohydrate Polymers*, 132, 196–204.
- Sousa, A. M. M., Sereno, A. M., Hilliou, L., & Gonçalves, M. P. (2010). Biodegradable Agar Extracted from *Gracilaria Vermiculophylla*: Film Properties and Application to Edible Coating. *Materials Science Forum*, 636-637, 739–744.
- Sousa, A. M. M., Souza, H. K. S., Liu, L., & Gonçalves, M. P. (2015). Alternative Plasticizers for the Production of Thermo-compressed Agar Films. *International Journal of Biological Macromolecules*, 76, 138–145.
- Sreenivasan, V. S., Ravindran, D., Manikandan, V., & Narayanasamy, R. (2012). Influence of fibre treatments on mechanical properties of short *Sansevieria cylindrica*/polyester composites. *Materials and Design*, 37, 111–121.
- Stepito, R. F. T. (2003). The Processing of Starch as a Thermoplastic. *Macromolecular Symposia*, 201, 203–212.

- Syad, A. N., Shunmugiah, K. P., & Kasi, P. D. (2013). Seaweeds as nutritional supplements: Analysis of nutritional profile, physicochemical properties and proximate composition of *G. acerosa* and *S. wightii*. *Biomedicine & Preventive Nutrition*, 3(2), 139–144.
- Talavera, F. J. F., Guzmán, J. a S., Richter, H. G., Dueñas, R. S., & Quirarte, J. R. (2007). Effect of production variables on bending properties, water absorption and thickness swelling of bagasse/plastic composite boards. *Industrial Crops and Products*, 26, 1–7.
- Tan, I. S., & Lee, K. T. (2014). Enzymatic hydrolysis and fermentation of seaweed solid wastes for bioethanol production: An optimization study. *Energy*. doi:10.1016/j.energy.2014.04.080
- Tang, X., & Alavi, S. (2011). Recent advances in starch, polyvinyl alcohol based polymer blends, nanocomposites and their biodegradability. *Carbohydrate Polymers*, 85(1), 7–16.
- Teacă, C. A., Bodîrlău, R., & Spiridon, I. (2013). Effect of cellulose reinforcement on the properties of organic acid modified starch microparticles/plasticized starch bio-composite films. *Carbohydrate Polymers*, 93, 307–315.
- Teixeira, E. D. M., Curvelo, A. a S., Corrêa, A. C., Marconcini, J. M., Glenn, G. M., & Mattoso, L. H. C. (2012). Properties of thermoplastic starch from cassava bagasse and cassava starch and their blends with poly (lactic acid). *Industrial Crops and Products*, 37(1), 61–68.
- Teixeira, E. D. M., Pasquini, D., Curvelo, A. a S., Corradini, E., Belgacem, M. N., & Dufresne, A. (2009). Cassava bagasse cellulose nanofibrils reinforced thermoplastic cassava starch. *Carbohydrate Polymers*, 78(3), 422–431.
- Teixeira, E. de M., Lotti, C., Corre, A. C., Teodoro, K. B. R., Marconcini, J. M., & Mattoso, L. H. C. (2010). Thermoplastic Corn Starch Reinforced with Cotton Cellulose Nanofibers. *Journal of Applied Polymer Science*, 120, 2428–2433.
- Teixeira, E. M., Da Róz, a. L., Carvalho, a. J. F., & Curvelo, a. a S. (2007). The effect of glycerol/sugar/water and sugar/water mixtures on the plasticization of thermoplastic cassava starch. *Carbohydrate Polymers*, 69, 619–624.
- Tezcan, F., Günister, E., Ozen, G., & Erim, F. B. (2012). Biocomposite films based on alginate and organically modified clay. *International Journal of Biological Macromolecules*, 50(4), 1165–8.
- Thuwail, M., Boldizar, A., & Rigdahl, M. (2006). Extrusion processing of high amylose potato starch materials. *Carbohydrate Polymers*, 65, 441–446.
- Tomé, L. C., Fernandes, S. C. M., Sadocco, P., Causio, J., Silvestre, A. J. D., Neto, P., & Freire, C. S. R. (2012). Antibacterial thermoplastic starch-chitosan based materials prepared by melt-mixing. *BioResources*, 7, 3398–3409.
- Truong, M., Zhong, W., Boyko, S., & Alcock, M. (2009). A comparative study on natural fibre density measurement. *Journal of the Textile Institute*, 100(March 2015), 525–529.
- Utracki, L. A. (1999). Polymer blends: fundamentals. *Polypropylene: A - Z Reference*, (Kluwer Publishers, Dordrecht).

- Varghese, J. S., Chellappa, N., & Fathima, N. N. (2014). Gelatin–carrageenan hydrogels: Role of pore size distribution on drug delivery process. *Colloids and Surfaces B: Biointerfaces*, 113, 346–351.
- Vilaseca, F., Mendez, J. a., Pèlach, a., Llop, M., Cañigual, N., Gironès, J., ... Mutjé, P. (2007). Composite materials derived from biodegradable starch polymer and jute strands. *Process Biochemistry*, 42, 329–334.
- Wang, S., Jiang, X. M., Han, X. X., & Wang, H. (2008). Fusion Characteristic Study on Seaweed Biomass Ash. *Energy & Fuels*, 2000(3), 2229–2235.
- Weerapoprasit, C., & Prachayawarakorn, J. (2015). Properties of Biodegradable Thermoplastic Cassava Starch/Sodium Alginate Composites Prepared From Injection Molding Chayapa. *Polymer Composites*, 16(M), 1–8.
- Wei, D., Wang, H., Xiao, H., Zheng, A., & Yang, Y. (2015). Morphology and mechanical properties of poly(butylene adipate-co-terephthalate)/potato starch blends in the presence of synthesized reactive compatibilizer or modified poly(butylene adipate-co-terephthalate). *Carbohydrate Polymers*, 123, 275–282.
- Wu, Y., Geng, F., Chang, P. R., Yu, J., & Ma, X. (2009). Effect of agar on the microstructure and performance of potato starch film. *Carbohydrate Polymers*, 76(2), 299–304.
- Xie, F., Pollet, E., Halley, P. J., & Avérous, L. (2013). Starch-based nano-biocomposites. *Progress in Polymer Science*, 38(10-11), 1590–1628. doi:10.1016/j.progpolymsci.2013.05.002
- Xiong, Z., Yang, Y., Feng, J., Zhang, X., Zhang, C., Tang, Z., & Zhu, J. (2013). Preparation and characterization of poly(lactic acid)/starch composites toughened with epoxidized soybean oil. *Carbohydrate Polymers*, 92(1), 810–6.
- Yahaya, R., Sapuan, S. M., Jawaid, M., Leman, Z., & Zainudin, E. S. (2015). Effect of fibre orientations on the mechanical properties of kenaf–aramid hybrid composites for spall-liner application. *Defence Technology*, 12(1), 52–58.
- Yaich, H., Garna, H., Besbes, S., Paquot, M., Blecker, C., & Attia, H. (2011). Chemical composition and functional properties of *Ulva lactuca* seaweed collected in Tunisia. *Food Chemistry*, 128(4), 895–901.
- Yeh, J., Hou, Y., Cheng, L., Wang, Y.-Z., Yang, L., & Wang, C. (2015). Water proof and strength retention properties of thermoplastic starch based biocomposites modified with glutaraldehyde. *Carbohydrate Polymers*, 127, 135–144.
- Yu, L., Dean, K., & Li, L. (2006). Polymer blends and composites from renewable resources. *Progress in Polymer Science*, 31(6), 576–602.
- Z. Leman, S.M. Sapuan, S. S. (2011). Sugar Palm Fibre-Reinforced Unsaturated Polyester Composite Interface Characterisation by Pull-Out Test. *Key Engineering Materials*, 471-472, 1034–1039.
- Zactiti, E. M., & Kieckbusch, T. G. (2006). Potassium sorbate permeability in biodegradable alginate films: Effect of the antimicrobial agent concentration and crosslinking degree. *Journal of Food Engineering*, 77, 462–467.

- Zahran, M. K., Ahmed, H. B., & El-Rafie, M. H. (2014). Surface modification of cotton fabrics for antibacterial application by coating with AgNPs-alginate composite. *Carbohydrate Polymers*, 108, 145–52.
- Zainuddin, S. Y. Z., Ahmad, I., Kargarzadeh, H., Abdullah, I., & Dufresne, A. (2013). Potential of using multiscale kenaf fibers as reinforcing filler in cassava starch-kenaf biocomposites. *Carbohydrate Polymers*, 92(2), 2299–305.
- Zasytkin, D. V., Yuryev, V. P., Alexeyev, V. V., & Tolstoguzov, V. B. (1992). Mechanical properties of the products obtained by the thermoplastic extrusion of potato starch - soybean protein mixtures. *Carbohydrate Polymers*, 18, 119–124.
- Zeng, Q., Han, Y., Li, H., & Chang, J. (2014). Bioglass/alginate composite hydrogel beads as cell carriers for bone regeneration. *Journal of Biomedical Materials Research - Part B Applied Biomaterials*, 102, 42–51.
- Zhai, P., Chen, X. B., & Schreyer, D. J. (2015). PLGA/alginate composite microspheres for hydrophilic protein delivery. *Materials Science and Engineering: C*, 56, 251–259.
- Zhang, S. D., Zhang, Y. R., Zhu, J., Wang, X. L., Yang, K. K., & Wang, Y. Z. (2007). Modified corn starches with improved comprehensive properties for preparing thermoplastics. *Starch/Staerke*, 59, 258–268.
- Zhang, Y., Ma, Q., Critzer, F., Davidson, P. M., & Zhong, Q. (2015). Physical and antibacterial properties of alginate films containing cinnamon bark oil and soybean oil. *LWT - Food Science and Technology*, 64(1), 423–430.
- Zhang, Y. R., Wang, X. L., Zhao, G. M., & Wang, Y. Z. (2013). Influence of oxidized starch on the properties of thermoplastic starch. *Carbohydrate Polymers*, 96(1), 358–364.
- Zhang, Y., Rempel, C., & Liu, Q. (2014). Thermoplastic starch processing and characteristics-a review. *Critical Reviews in Food Science and Nutrition*, 54(February), 1353–70.
- Zhang, Y., Ye, L., Cui, M., Yang, B., Li, J., Sun, H., & Yao, F. (2015). Physically crosslinked poly(vinyl alcohol)-carrageenan composite hydrogels: pore structure stability and cell adhesive ability. *RSC Adv.*, 5, 78180–78191.
- Zhang, Z., Pang, T., Li, Q., Zhang, L., Li, L., & Liu, J. (2015). Transcriptome sequencing and characterization for *Kappaphycus alvarezii*. *European Journal of Phycology*, 50(January), 400–407.
- Zia, K. M., Zia, F., Zuber, M., Rehman, S., & Ahmad, M. N. (2015). Alginate based polyurethanes: A review of recent advances and perspective. *International Journal of Biological Macromolecules*, 79, 377–387.
- Zou, W., Yu, L., Liu, X., Chen, L., Zhang, X., Qiao, D., & Zhang, R. (2012). Effects of amylose/amylopectin ratio on starch-based superabsorbent polymers. *Carbohydrate Polymers*, 87(2), 1583–1588.