



**UNIVERSITI PUTRA MALAYSIA**

***PREPARATION AND EVALUATION OF AQUEOUS PHASE  
COMPATIBLE  
MOLECULARLY IMPRINTED POLYMERS  
FOR SHIKIMIC ACID***

**YEOH CHEE BENG**

**FS 2015 89**



**PREPARATION AND EVALUATION OF AQUEOUS PHASE COMPATIBLE  
MOLECULARLY IMPRINTED POLYMERS  
FOR SHIKIMIC ACID**

By

**YEOH CHEE BENG**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in  
Fulfilment of the Requirements for the Degree of Doctor of Philosophy**

**January 2015**

## COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia.



Abstract of thesis presented to Senate of University Putra Malaysia in fulfilment of the requirements for the degree of Doctor of Philosophy

**PREPARATION AND EVALUATION OF AQUEOUS PHASE COMPATIBLE  
MOLECULARLY IMPRINTED POLYMERS  
FOR SHIKIMIC ACID**

By

**YEOH CHEE BENG**

**January 2015**

**Chairperson : Professor Nor Azah Yusof, Ph.D.**  
**Faculty : Science**

Shikimic acid (SA) is an important component in the production of several important drugs particularly the anti-influenza drug, Oseltamivir. Naturally, SA exists as an intermediate in the plant biosynthesis of aromatic compounds via shikimate pathway. Commercially, SA is extracted from the Chinese star anise or produced through the fermentation process by modified strain of *Escherichia coli* (*E. coli*). Regardless of the method of production, SA needs to be purified before it can be used for the intended purpose. Conventional method in the purification of SA usually involved the use of non-specific adsorbents that are less effective in isolating the SA. Molecularly imprinted polymer (MIP) being one of the latest adsorbents in separation science, offers an alternative technique that is more selective and specific than the conventional adsorption methods.

MIP is known to be not compatible to the aqueous phase with usually low or no selectivity, making the preparation of MIP that work well in aqueous phase a challenge to those in the field. Reported in this thesis are exploratory work carried out to prepare non-covalent imprinted polymer for SA with the aim that the polymer prepared is capable of working in highly aqueous environment in which the raw extract of SA is usually in.

“Trial and error” approach was used as the preliminary tool in searching the right formulation of template:monomer:cross-linker (TMX) ratio that produced a good imprinted polymer judging from the imprinting factor (IF) scores of the polymer in batch rebinding experiments. The optimized TMX ratio finally determined was 1:6:10

in 10 mL methanol and water (4:1, v/v) porogen system. The best template: monomer (TM) ratio was also evaluated using ultraviolet (UV) spectroscopy approach, the results obtained were in agreement with the preliminary “trial and error” results, indicated that TM ratio of 1:6 was the optimal.

The polymer was physically characterized using Fourier transform infrared (FTIR) spectroscopy and scanning electron microscopy (SEM) techniques. Results indicated that complete polymerization was achieved and different morphologies observed between imprinted and control polymers may be used to explain the imprinting effect shown by the SA imprinted polymer. Optimization on the rebinding conditions suggested that the SA imprinted polymer performed best in 100% aqueous environment at pH 4.0.

Binding isotherm study suggested that the binding sites distribution was heterogeneous in nature and it can be well described using Freundlich isotherm model. Study of the polymer's adsorption kinetic concluded that the adsorption process obeyed pseudo second order kinetic with rate constant,  $K$  of  $0.0047 \text{ g}\cdot\mu\text{g}^{-1}\cdot\text{min}$  and the experimental maximum adsorption for SA imprinted polymer was determined as  $38.8 \mu\text{g}\cdot\text{g}^{-1}$ .

Cross-reactivity experiments results showed that the imprinted polymer having good selectivity toward SA and the polymer was packed into cartridge and used for the separation of SA from artificial mixture of SA, methyl shikimate (SE) and gallic acid (GA) in tap water. A clean separation with three isolated peaks as shown in high performance liquid chromatography (HPLC) chromatogram was obtained.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

## PENYEDIAAN DAN PENILAIAN POLIMER CETAKAN MOLEKUL ASID SYIKIMIK SERASI DENGAN FASA AKUEUS

Oleh

**YEOH CHEE BENG**

Januari 2015

**Pengerusi** : **Professor Nor Azah Yusof, Ph.D.**  
**Fakulti** : **Sains**

Asid syikimik (SA) merupakan satu sebatian penting dalam pengeluaran beberapa jenis ubat penting, terutamanya ubat anti-influenza dengan jenama Oseltamivir. Secara semula jadi, SA wujud sebagai sebatian perantara dalam proses biosintesis sebatian aromatik dalam tumbuhan yang berlangsung melalui laluan syikimat. Secara komersil, SA diekstrak dari bunga lawang Cina atau dihasilkan melalui proses fermentasi oleh strain *Escherichia coli* (*E. coli*) yang telah diubahsuai. Tanpa mengira kaedah penghasilannya, SA yang dihasilkan perlu melalui proses penulenan sebelum ia dapat digunakan untuk tujuannya. Secara konvensional, penulenan SA dilakukan dengan kaedah yang melibatkan penggunaan penjerap tidak spesifik yang kurang berkesan dalam pemisahan asid syikimik. Polimer cetakan molekul (MIP) merupakan antara penjerap baru dalam bidang Sains Permishan, yang menawarkan teknik alternatif pemisahan sebatian dengan lebih selektif serta spesifik berbanding kaedah penjerapan konvensional.

MIP sememangnya diketahui tidak serasi dengan fasa akueus dan biasanya menunjukkan selektiviti yang rendah ataupun tidak menunjukkan selektiviti, ini menyebabkan penyediaan MIP yang berfungsi baik dalam keadaan akueus suatu cabaran kepada mereka yang menceburi bidang ini. Tesis ini melaporkan hasil kerja penyelidikan awal tentang penyediaan polimer cetakan tidak kovalen bagi SA dengan matlamat polimer cetakan yang terhasil boleh berfungsi dalam persekitaran berkeandungan akueus yang tinggi, iaitu persekitaran di mana SA pada kebiasaannya wujud.

Kaedah “cuba-jaya” telah digunakan sebagai kaedah awal dalam menentukan rumusan nisbah templet:monomer:penyilang (TMX) yang sesuai untuk menghasilkan polimer

cetakan SA yang bagus, dinilai melalui skor cetakan (IF) polimer berkenaan dalam ujian penjerapan semula secara kelompok. Rumusan TMX 1:6:10 dalam 10 mL porogen campuran metanol-air (4:1, v/v) telah ditentukan sebagai rumusan optimum. Nisbah templet:monomer (TM) yang optimum juga dinilai dengan menggunakan kaedah spektroskopi ultraungu (UV), di mana keputusan yang diperolehi bersejua dengan keputusan awal dalam kaedah “cuba-jaya”, yang menunjukkan nisbah TM 1:6 adalah optimum.

Pencirian secara fizikal menggunakan spektroskopi transformasi inframerah Fourier (FTIR) dan mikroskopi elektron pengimbasan (SEM) telah dilakukan ke atas polimer yang dihasilkan. Keputusan pencirian menunjukkan bahawa proses pemolimeran telah berlangsung dengan lengkap, pemerhatian tentang perbezaan morfologi antara polimer bercetak dan polimer rujukan mungkin boleh digunakan bagi menerangkan prestasi penjerapan yang ditunjukkan polimer cetakan SA. Pengoptimuman keadaan penjerapan semula menunjukkan polimer cetakan SA menunjukkan prestasi penjerapan semula terbaik apabila ia berada dalam keadaan akueus 100% pada pH 4.0.

Kajian isoterma penjerapan menunjukkan taburan titik jerapan pada polimer cetakan adalah heterogen secara asasnya, dan model isoterma Freundlich adalah sesuai untuk menjelaskan keadaan ini.

Kajian kinetik proses penjerapan pada polimer cetakan SA yang dihasilkan menyimpulkan bahawa proses penjerapan adalah mengikut hukum kinetik pseudo tertib kedua dengan pemalar kadar,  $K$  iaitu  $0.0047 \text{ g} \cdot \mu\text{g}^{-1} \cdot \text{min}$  dan penjerapan maksimum secara eksperimental bagi polimer cetakan asid syikimik adalah  $38.8 \mu\text{g} \cdot \text{g}^{-1}$ .

Keputusan eksperimen reaktiviti bersilang menunjukkan polimer cetakan yang dihasilkan menunjukkan selektiviti yang baik terhadap SA. Polimer ini telah dipek dalam katrij dan digunakan dalam pemisahan SA dari campuran tiruan SA, metil syikimat (SE) dan asid galik (GA) dalam air paip. Pemisahan bersih yang memberikan tiga puncak berasingan seperti yang ditunjukkan dalam kromatogram kromatografi cecair berprestasi tinggi (HPLC) telah diperolehi.

## ACKNOWLEDGEMENTS

It would not have been possible to write this doctoral thesis without the help and support of the kind people around me, to only some of whom it is possible to give particular mention here.

Above all, I would like to thank my wife Pei Pei and my kids Zi Yu and Kai Zhe for their personal support and great patience at all times. My mother and my sisters have given me their unequivocal support throughout, as always, for which my mere expression of thanks likewise does not suffice.

I offer my sincerest gratitude to my main supervisor, Prof. Dr. Nor Azah Yusof, who has supported me throughout my thesis with her patience and knowledge whilst allowing me the room to work in my own way.

Besides my main supervisor, I would like to thank the rest of my supervisory committee: Dr. Tan Yew Ai, Assoc. Prof. Dr. Abdul Halim Abdullah, and Dr. Nor Azowa Ibrahim, for their encouragement, insightful comments, and suggestions. The good advice, support and friendship of my senior colleague Dr. Chong Chiew Let, has been invaluable on both an academic and a personal level, for which I am extremely grateful.

I would also like to thank Dr. Halimah Muhamad, Pn. Farah Khuwailah, Pn. Najwa, Pn. Nik Sasha Khatrina, Pn. Saw Mei Huey and the rest of AQD Unit, MPOB, for their help and back-up during my busy time in completing the study.

Last but not least, I thank the management of the Malaysian Palm Oil Board (MPOB) for the study leave and financial support.

For any errors or inadequacies that may remain in this work, of course, the responsibility is entirely my own.



I certify that a Thesis Examination Committee has met on 15 January 2015 to conduct the final examination of Yeoh Chee Beng on his thesis entitled “Preparation and Evaluation of Aqueous Phase Compatible Molecularly Imprinted Polymers for Shikimic Acid” in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

**Tan Yen Ping, PhD**

Senior Lecturer  
Faculty of Science  
Universiti Putra Malaysia  
(Chairman)

**Mansor bin Hj Ahmad @ Ayob, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Internal Examiner)

**Irmawati binti Ramli, PhD**

Associate Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Internal Examiner)

**Peter Cormarck, PhD**

Professor  
University of Strathclyde  
United Kingdom  
(External Examiner)



**ZULKARNAIN ZAINAL, PhD**

Professor and Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 15 April 2015

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

**Nor Azah binti Yusof, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Chairman)

**Abdul Halim bin Abdullah, PhD**

Associate Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Nor Azowa binti Ibrahim, PhD**

Senior Lecturer  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Tan Yew Ai, PhD**

Head of Unit  
Sustainability, Conservation & Certification Unit  
Malaysian Palm Oil Board  
(Member)

**BUJANG KIM HUAT, PhD**

Professor and Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:

## Declaration by Graduate Student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature \_\_\_\_\_

Date \_\_\_\_\_

Name and Matric No.: Yeoh Chee Beng. (GS 24041)

### Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature : \_\_\_\_\_  
Name of  
Chairman of  
Supervisory  
Committee : NOR AZAH YUSOF, PhD

Signature : \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee : ABDUL HALIM ABDULLAH, PhD

Signature : \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee : NOR AZOWA IBRAHIM, PhD

Signature : \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee : TAN YEW AI, PhD

## TABLE OF CONTENTS

|  | Page      |
|--|-----------|
| <b>ABSTRACT</b>  | i         |
| <b>ABSTRAK</b>   | iii       |
| <b>ACKNOWLEDGEMENTS</b>  | v         |
| <b>APPROVAL</b>  | vi        |
| <b>DECLARATION</b>   | viii      |
| <b>LIST OF TABLES</b>  | xiii      |
| <b>LIST OF FIGURES</b>   | xiv       |
| <b>LIST OF ABBREVIATIONS</b>   | xviii     |
| <b>CHAPTER</b>   |           |
| <b>1 INTRODUCTION</b>  | <b>1</b>  |
| 1.1 Shikimic Acid and Molecularly Imprinted Polymer  | 1         |
| 1.2 Problem Statement  | 2         |
| 1.3 Objectives of the Study  | 2         |
| <b>2 LITERATURE REVIEW</b>   | <b>3</b>  |
| 2.1 Molecular Imprinted Polymers   | 3         |
| 2.1.1 History of Molecularly Imprinted Polymer   | 4         |
| 2.1.2 Synthetic Approaches to Molecular Imprinting   | 5         |
| 2.1.3 Considerations in the Preparation of Molecularly Imprinted Polymer                     | 11        |
| 2.2 Water-Polymer Compatibility  | 18        |
| 2.3 Shikimic Acid  | 18        |
| 2.3.1 Basic Information  | 18        |
| 2.3.2 Shikimic Acid and Influenza  | 20        |
| 2.3.3 Sources of Shikimic Acid   | 20        |
| <b>3 MATERIALS AND METHODS</b>   | <b>23</b> |
| 3.1 List of Chemical and Reagent   | 23        |
| 3.2 Preliminary Studies Prior To the Execution of Current Study – Long Chain Carboxylic Acid | 24        |
| 3.2.1 Preparation of Lauric Acid Imprinted Polymer   | 24        |
| 3.2.2 Lauric Acid Stock and Working Solutions  | 26        |
| 3.2.3 Gas Chromatography Analysis of Lauric Acid   | 26        |
| 3.3 Preparation of Coenzyme Q10 Imprinted Polymer  | 26        |
| 3.4 Common Procedure for the Preparation of Shikimic Acid Imprinted Polymer                  | 27        |
| 3.5 Optimizing the Formulation for Shikimic Acid Imprinted Polymer                           | 27        |
| 3.5.1 Shikimic Acid and Functional Monomer Stock Solutions                                   | 27        |

|          |  |           |
|----------|--|-----------|
| 3.5.2    | Ultraviolet–visible Spectroscopy Titration Approach for the Best Template:Functional Monomer Ratio Determination | 28        |
| 3.5.3    | Monomer Selection  | 29        |
| 3.5.4    | Optimization of Template:Monomer Ratio   | 30        |
| 3.5.5    | Optimization of Cross-linker Ratio   | 30        |
| 3.5.6    | Effect of Using Different Porogens in Polymer Preparation  | 31        |
| 3.6      | Batch Rebinding Experiment   | 32        |
| 3.7      | High Performance Liquid Chromatography Analysis  | 32        |
| 3.7.1    | Determination of Shikimic Acid and Methyl Shikimate  | 32        |
| 3.7.2    | Determination of Shikimic Acid, Methyl Shikimate and Gallic Acid   | 32        |
| 3.8      | Polymer Characterizations  | 32        |
| 3.8.1    | Fourier Transform Infrared Spectroscopy Analysis   | 32        |
| 3.8.2    | Scanning Electron Microscope (SEM)   | 33        |
| 3.8.3    | Thermal Gravimetric Analysis (TGA)   | 33        |
| 3.8.4    | Surface Area Measurement   | 33        |
| 3.9      | Evaluation of External Factors Affecting the Binding Performance of Shikimic Acid Imprinted Polymer              | 33        |
| 3.9.1    | Effect of Water Content in the Rebinding Solutions   | 33        |
| 3.9.2    | Effect of pH   | 33        |
| 3.10     | Job Plot   | 34        |
| 3.11     | Kinetic of the Rebinding Process   | 34        |
| 3.12     | Cross-Reactivity Experiment  | 34        |
| 3.13     | Prepared Molecular Imprinted Polymer for Solid Phase Extraction Application                                      | 35        |
| 3.13.1   | Determination of Suitable Solid Phase Extraction Elution Profile   | 35        |
| 3.13.2   | Enrichment of Shikimic Acid from Artificial Mixture of Shikimic Acid, Methyl Shikimate and Gallic Acid           | 35        |
| <b>4</b> | <b>RESULTS AND DISCUSSION</b>  | <b>37</b> |
| 4.1      | Lauric Acid Imprinted Polymer Preparation and Preliminary Evaluation   | 37        |
| 4.2      | Coenzyme Q10 Imprinted Polymer Preparation and Preliminary Evaluation  | 39        |
| 4.3      | Shikimic Acid Imprinted Polymer Preparation and Optimization   | 39        |
| 4.3.1    | Template   | 40        |
| 4.3.2    | Selection of Monomer   | 41        |
| 4.3.3    | UV Titration Method in Determining optimum Template:Monomer Ratio  | 43        |
| 4.3.4    | Optimization of Cross-linker Ratio   | 47        |
| 4.3.5    | Rebinding Performances of Polymers Prepared in Different Porogens  | 50        |
| 4.4      | Characterization of the Polymer  | 54        |

|          |   |            |
|----------|---|------------|
| 4.4.1    | FTIR Analysis   | 54         |
| 4.4.2    | Polymer Morphology by Scanning Electron<br>Microscope       | 58         |
| 4.4.3    | Surface Area Determination                                  | 65         |
| 4.4.4    | Thermal Gravimetric Analysis                                | 65         |
| 4.5      | Optimization of Rebinding Conditions                        | 66         |
| 4.5.1    | Water Compatibility   | 66         |
| 4.5.2    | Effect of pH on the Rebinding Performance                   | 68         |
| 4.6      | The Binding Stoichiometry - Method of Continuous Variations | 70         |
| 4.7      | Binding Characterization                                    | 73         |
| 4.7.1    | Binding Isotherm  | 74         |
| 4.8      | Adsorption Kinetic  | 80         |
| 4.8.1    | Validation of Kinetic Models                                | 82         |
| 4.8.2    | Characterization of the Adsorption Process                  | 83         |
| 4.9      | Imprinted Polymer Selectivity                               | 85         |
| 4.9.1    | Shikimic Acid Vs Methyl Shikimate                           | 86         |
| 4.9.2    | Shikimic Acid Vs Gallic Acid                                | 89         |
| 4.10     | Separation of Shikimic Acid from Spiked Sample              | 90         |
| <b>5</b> | <b>CONCLUSIONS AND FUTURE RECOMMENDATIONS</b>               | <b>95</b>  |
| 5.1      | Conclusions   | 95         |
| 5.2      | Future Recommendations                                      | 96         |
|          | <b>REFERENCES</b>   | <b>99</b>  |
|          | <b>BIODATA OF STUDENT</b>                                   | <b>113</b> |
|          | <b>LIST OF PUBLICATIONS</b>                                 | <b>114</b> |

## LIST OF TABLES

| Table |   | Page |
|-------|---|------|
| 1     | Some Physicochemical Properties of SA   | 19   |
| 2     | Composition of LA Imprinted Polymers and Control Polymers Prepared in Preliminary Study | 25   |
| 3     | Polymer Compositions for Functional Monomer Selection and TM Ratio Optimization         | 30   |
| 4     | Polymer Compositions for Cross-Linker Ratio Optimization                                | 31   |
| 5     | Summary of Polymer Formulations Prepared in Different Porogens.                         | 31   |
| 6     | Rebinding Performances of LA Imprinted Polymer  | 37   |
| 7     | Batch Rebinding Results of Polymers with TM Ratio of 1:6 and 1:8                        | 47   |
| 8     | Batch Rebinding Results of 4VP Based Polymers at Cross-linker Ratio of 10               | 50   |
| 9     | Summary of the Kinetic Constants for the SA Imprinted Polymer                           | 83   |



## LIST OF FIGURES

| Figure |  | Page |
|--------|--|------|
| 1      | Schematic Representation for the Preparation of MIP Using Non-covalent Procedure (Haupt, 2010).  | 3    |
| 2      | Covalent Imprinted Polymer Introduced by Wulff and Sarhan (1972).  | 5    |
| 3      | Preparation of 4-nitrophenyl- $\alpha$ -D-mannopyranose Imprinted Polymer via Covalent Imprinting.   | 7    |
| 4      | Example of Interactions Found in Non-covalent Imprinting (Spivak, 2004).   | 9    |
| 5      | Schematic Representation for the Equilibrium Step during Template-Monomer Complex Formation in Non-covalent Imprinting (Step 1).   | 9    |
| 6      | Polymerization of N-propionyl-O-acryloyl-2-amino-3-(4-acryloyl-4-hydroxyphenyl)-1-propanol Followed by Hydrolysis Step to Give Imprinted Site for L-p-aminophenylalanine ethyl ester (Selligren and Andersson, 1990).  | 10   |
| 7      | Steric Effect during Rebinding Step in Semi-covalent Imprinted Polymer   | 11   |
| 8      | Semi-Covalent Imprinting of Cholesterol. a) Preparation of Template-Monomer Complex. b) Polymerization, the C=O Group of the Carbonate Ester is the Spacer. c) Hydrolysis Process to Remove the Template as well as the Spacer. d) Imprinted Cavity with Suitable Spacing to Accommodate the Rebinding of Cholesterol. | 12   |
| 9      | Example of Covalent Functional Monomers. A: 4-Vinylphenylboronic Acid, B: 4-Vinylbenzaldehyde, C: 2-(4-ethenylphenyl)propane-1,3-diol  | 14   |
| 10     | A Few Common Cross-linker for MIP Preparation 1: Ethylene glycol dimethacrylate (EGDMA), 2: Trimethylolpropane trimethacrylate (TRIM) and 3: Divinylbenzene (DVB)  | 15   |
| 11     | Chemical Structure of SA   | 19   |
| 12     | Chemical Structure of LA   | 38   |
| 13     | Chemical Structure of Coenzyme Q10   | 39   |
| 14     | SA Structure with Numbering  | 41   |

|    |   |    |
|----|---|----|
| 15 | UV Absorption Spectra of SA and Different Functional Monomers at 1 to 4 Ratio in MeOH and Water (4:1, v/v) Mixed Solvent.   | 44 |
| 16 | Rebinding Performances of Polymers Prepared with T:M:X Ratio of 1:4:20 in Water.  | 45 |
| 17 | UV Spectra of SA with Different Molar Ratios of SA to 4VP   | 46 |
| 18 | Possible Interaction Between SA and 4VP   | 46 |
| 19 | Rebinding of SA on 4VP Based MIP and NIP with Different Cross-linker Ratios   | 49 |
| 20 | Rebinding Results for Polymers Prepared in Different Porogens (Rebinding Experiment Conducted in 100 ppm SA Solution Prepared Using Water as Solvent)                   | 53 |
| 21 | FTIR Spectrum of EGDMA (Cross-linker)   | 55 |
| 22 | FTIR Spectrum of 4VP (Functional Monomer)   | 56 |
| 23 | FTIR Spectrum of SA Imprinted Polymer   | 57 |
| 24 | SEM Images for MSA1610 4VP (Left) and NSA1610 4VP (Right) Prepared in MeOH and Water (4:1, v/v) as Porogen. [A&D = X10,000, B&E = X15,000, C&F = X25,000 magnification] | 59 |
| 25 | SEM Images for MSA1610 4VP (Left) and NSA1610 4VP (Right) Prepared in MeOH as Porogen. [A&D = X10,000, B&E = X15,000, C&F = X25,000 magnification]                      | 60 |
| 26 | SEM Images for MSA1610 4VP (Left) and NSA1610 4VP (Right) Prepared in MeOH-ACN (2:3, v/v) as Porogen. [A&D = X10,000, B&E = X15,000, C&F = X25,000 magnification]       | 61 |
| 27 | SEM Images for MSA1610 4VP (Left) and NSA1610 4VP (Right) Prepared in ACN-Water (9:1, v/v) as Porogen. [A&D = X10,000, B&E = X15,000, C&F = X25,000 magnification]      | 62 |
| 28 | SEM Images for MSA1610 4VP (Left) and NSA1610 4VP (Right) Prepared in DMF as Porogen. [A&D = x10,000, B&E = x15,000, C&F = x25,000 magnification]                       | 63 |
| 29 | SEM Images for MSA1610 4VP (Left) and NSA1610 4VP (Right) Prepared in DMSO as Porogen. [A&D = X10,000, B&E = X15,000, C&F = X25,000 magnification]                      | 64 |

|    |  |    |
|----|--|----|
| 30 | TGA Decomposition Curves of SA MIP (MSA1610 4VP) and NIP (NSA1610 4VP)   | 65 |
| 31 | Rebinding Performance of Imprinted Polymer (MSA1610) in Mixed MeOH and Water Solution with Different Water Content, Inset is the Magnified Rebinding Result for Solution with 0 - 30% Water Content. | 67 |
| 32 | Rebinding Performance of Imprinted Polymer (MSA1610 4VP) and Its Control (NSA0610 4VP) at Different pH   | 69 |
| 33 | Dissociation of 4VP Conjugate Acid (Top) and SA (Bottom)   | 70 |
| 34 | a) Shifting of SA C-2 Vinylic Proton (in box) Upon the Addition of Py-d5.<br>b) Magnification of SA C-2 Vinylic Proton Shifting  | 72 |
| 35 | Job plot for the Association between 4VP and SA in CD <sub>3</sub> OD and D <sub>2</sub> O (4:1, v/v) Mixture at the Combined Concentration of 5mM   | 73 |
| 36 | Binding Isotherm for SA Imprinted Polymer (MIP) and Its Corresponding Control Polymer (NIP) (Langmuir Model)   | 75 |
| 37 | Scatchard Plot of SA (a) MIP and (b) NIP   | 76 |
| 38 | Binding Isotherm of SA Imprinted Polymer (MIP) and Its Corresponding Control (NIP) (Freundlich Model)  | 78 |
| 39 | Affinity Distributions for SA Imprinted Polymer (MIP) and Its Corresponding Control (NIP) (Freundlich Model)<br>a) Semi-Log Format b) Log-Log Format   | 79 |
| 40 | Time Dependence of the Adsorption Capacities of SA by MIP  | 80 |
| 41 | First Order Kinetic of the Adsorption Data for SA Imprinted Polymer  | 81 |
| 42 | Second Order Kinetic of the Adsorption Data for SA Imprinted Polymer   | 82 |
| 43 | Plot of Intra Particle Diffusion Model for the Adsorption of SA by SA Imprinted Polymer.   | 84 |
| 44 | Plot of External Diffusion Model for the Adsorption of SA by SA Imprinted Polymer.   | 85 |
| 45 | Selected Analogue Compounds in SA Imprinted Polymer Selectivity Test: SE (Left), GA (Right)  | 86 |

|    |   |    |
|----|---|----|
| 46 | Chromatogram of SA and SE Mixture Before (Blue) and After (Red) Adsorption by SA Imprinted Polymer  | 87 |
| 47 | Chromatograms of SA and SE Mixture Before (Blue) and After (Orange) Adsorption by NIP (Control)     | 88 |
| 48 | Chromatograms of SA and GA Mixture Before (Blue) and After (Red) Adsorption by SA Imprinted Polymer | 89 |
| 49 | Chromatograms of SA and GA Mixture Before (Blue) and After (Orange) Adsorption by NIP (Control)     | 89 |
| 50 | Elution of SE During Washing Step   | 91 |
| 51 | Elution of SA and GA During Eluting Step  | 92 |
| 52 | Separation of SA from Spiked Tab Water  | 93 |
| 53 | Schematic Diagram for the Formation of $\beta$ -cyclodextrin Base MIP                               | 98 |

## LIST OF ABBREVIATIONS

|                  |  |
|------------------|--|
| $^1\text{H}$ NMR | Proton nuclear magnetic resonance  |
| 4VP              | 4-vinylpyridine  |
| AAM              | Acrylamide   |
| ACN              | Acetonitrile   |
| ACVA             | 4,4-azobis-4-cyanovaleric acid   |
| <b>B</b>         | Concentration of template in its bound form during equilibrium in rebinding experiment |
| DMF              | Dimethylformamide  |
| DMSO             | Dimethyl sulfoxide   |
| DVB              | Divinylbenzene   |
| EGDMA            | Ethylene glycol dimethacrylate   |
| <b>F</b>         | Concentration of template in its free form during equilibrium in rebinding experiment  |
| FI               | Freundlich isotherm  |
| FTIR             | Fourier transform infrared spectroscopy  |
| GA               | Gallic acid  |
| IF               | Imprinting factor  |
| LA               | Lauric acid  |
| LI               | Langmuir isotherm  |
| MAA              | Methacrylic acid   |
| MeOH             | Methanol   |
| MIP              | Molecular imprinted polymer  |
| NIP              | Non-imprinted polymer (Control polymer)  |
| SA               | Shikimic acid  |
| SE               | Methyl shikimate   |
| SEM              | Scanning electron microscope   |
| TGA              | Thermal gravimetric analysis   |
| THF              | Tetrahydrofuran  |
| TM ratio         | Template:Monomer ratio   |
| TMX ratio        | Template:Monomer:Cross-linker ratio  |
| TRIM             | Trimethylolpropane trimethacrylate   |
| UV-Vis           | Ultraviolet-visible  |

## CHAPTER 1

### INTRODUCTION

#### 1.1 Shikimic Acid and Molecularly Imprinted Polymer

Shikimic Acid (SA) is the main raw material for the production of several important drugs used in the treatment of influenza and chemotherapy. Currently, commercial production of SA is achieved via the extraction from Chinese star anise or the biosynthesis process by modified strain of microorganisms. Although there are other reported sources for the extraction or synthesis of SA, all those methods are found to be not economically viable at this point in time. Recently, there was a report on the discovery of SA in the aqueous waste stream from the palm oil milling process (Ravigadevi *et al.*, 2011), this new discovery has triggered research to look into the possibility of extracting SA as an alternative to the two commercial routes mentioned above. Regardless of the method of production, crude SA always contain impurities that need to be removed, otherwise it will affect the quality and final usage of the product.

The enrichment of active components from natural source is a complicated process. The problem is doubled if the desired active components are present in trace quantities. Currently, the common methods to separate and enrich these active components involve the use of non-specific adsorbent such as silica gel (including the modified one), alumina oxide and meso- or macro-porous resin. The modes of separation usually relying on the polarity of the feed materials, polar components will be retained longer if the adsorbents are polar and when hydrophobic adsorbents are used, non-polar components will be retained. Another mode of separation is based on charge, the components having different charges from the adsorbent will be retained and those neutral or having the same charge as the adsorbent will be released. Molecular sizes can also be utilized in the separation and enrichment of active components in natural products. The adsorbents are usually resin with a narrow range of porosity which, during elution, will either allow or refuse the penetration of the components of interest. Through the differences in the elution profile, components of interest are separated.

Molecular imprinted polymers (MIP) are highly cross-linked polymeric materials that are formed during the polymerization process in the presence of template molecules. During polymerization, template molecules and functional monomers undergo self-assembly process as a result of bonding interactions such as covalent bonding, hydrogen bonding, van der Waals interaction,  $\pi - \pi$  interaction and others. Output from the self-assembly process is the formation of a polymer with the functional monomers framing the template molecules. Upon removal of the template molecules, the polymers now have voids in them in the shape of the template molecules. These voids are the sites which are capable of rebinding with the specific template or its analogue.

Although the effectiveness of MIP as the adsorbent in the separation or enrichment of chemical compounds is well known and proven (Chen and Shi, 2013, Pardo *et al.*, 2012), there are several challenges need to be overcome before MIP technique can really be used extensively as routine mode of separation. One of these challenges is the incompatibility of MIP in aqueous phase. This is especially true if the MIP interactions are mainly based on hydrogen bonding.

## 1.2 Problem Statement

It is well-known that the poor ability of imprinted polymer to bind selectively in the aqueous phase is one of the issues that need to be addressed in the field of MIP preparation. Unfortunately, many target molecules of interest are only present in aqueous media such as body fluids, wastewater and river. SA is a compound that has a very high solubility in water ( $18 \text{ g}\cdot\text{L}^{-1}$ ), due to its high medicinal value, the research in the area of SA production and purification has become one of the hottest topics in the respective fields. It is the aim of this study to develop a good formulation for the preparation of SA imprinted polymer that can work in a solvent with a high aqueous content, preferably close to 100%. Other aspects of MIP preparation such as rebinding condition optimization, polymer characterizations, binding sites evaluations and subsequently the application of the prepared MIP in the separation of SA from its analogue compounds are also the interest of this study.

## 1.3 Objectives of the Study

The following objectives are set for this study:-

- a) To prepare SA imprinted polymers that are compatible in aqueous phase.
- b) To identify the most suitable functional monomer to be used in the preparation of aqueous phase compatible SA imprinted polymers.
- c) To optimize the formulation of the SA imprinted polymers in term of Template: Monomer: Cross-linker (TMX) ratio and types of porogens.
- d) To optimize the rebinding conditions and to evaluate the aqueous compatibility of the prepared SA imprinted polymers.
- e) To characterize the prepared SA imprinted polymers.
- f) To use the prepared SA imprinted polymers in the enrichment of SA from artificial mixture of SA and its analogues.

## REFERENCES

- ADACHI, O., ANO, Y., TOYAMA, H. & MATSUSHITA, K. 2006. High Shikimate Production from Quinate with Two Enzymatic Systems of Acetic Acid Bacteria. *Biosci. Biotechnol. Biochem.*, 70, 2579-82.
- ADACHI, O., TANASUPAWAT, S., YOSHIHARA, N., TOYAMA, H. & MATSUSHITA, K. 2003a. 3-Dehydroquinate Production by Oxidative Fermentation and Further Conversion of 3-Dehydroquinate to the Intermediates in the Shikimate Pathway. *Biosci. Biotechnol. Biochem.*, 67, 2124-31.
- ADACHI, O., YOSHIHARA, N., TANASUPAWAT, S., TOYAMA, H. & MATSUSHITA, K. 2003b. Purification and Characterization of Membrane Bound Quinoprotein Quinate Dehydrogenase. *Biosci. Biotechnol. Biochem.*, 67, 2115-23.
- AMRHEIN, N., SCHAB, J. & STEINRÜCKEN, H. C. 1980. The Mode of Action of the Herbicide Glyphosate. *Naturwissenschaften*, 67, 356-57.
- ANDERSSON, H. S., KARLSSON, J. G., PILETSKY, S. A., KOCH-SCHMIDT, A.-C., MOSBACH, K. & NICHOLLS, I. A. 1999. Study of the Nature of Recognition in Molecularly Imprinted Polymers, II. *J. Chromatogr. A*, 848, 39-49.
- ANDERSSON, H. S. & NICHOLLS, I. A. 1997. Spectroscopic Evaluation of Molecular Imprinting Polymerization Systems. *Bioorg. Chem.*, 25, 203-11.
- ANDERSSON, H. S. & NICHOLLS, I. A. 2000. A Historical Perspective of the Development of Molecular Imprinting. In: BÖRJE, S. (ed.) *Molecularly Imprinted Polymers - Man-made Mimics of Antibodies and their Applications in Analytical Chemistry*. Elsevier.
- ARMSTRONG, J. S., WHITEMAN, M., ROSE, P. & JONES, D. P. 2003. The Coenzyme Q10 Analog Decylubiquinone Inhibits the Redox-activated Mitochondrial Permeability Transition: Role of Mitochondrial Respiratory Complex III. *J. Biol. Chem.*, 278, 49079-84.
- ASANUMA, H., HISHIYA, T. & KOMIYAMA, M. 2004. Efficient Separation of Hydrophobic Molecules by Molecularly Imprinted Cyclodextrin Polymers. *J. Incl. Phenom. Macrocycl. Chem.*, 50, 51-55.
- ASANUMA, H., KAKAZU, M., SHIBATA, M. & HISHIYA, T. 1997. Molecularly Imprinted Polymer of  $\beta$ -Cyclodextrin for the Efficient Recognition of Cholesterol. *Chem. Commun.*, 1971-72.



- BESTMANN, H. J. R. & HEID, H. A. 1971. Stereospecific Synthesis of Optically Pure Quinic Acid and Shikimic Acid from D-Arabinose. *Angew. Chem. Int. Edit.*, 10, 336-37.
- BIRCH, A. J., KELLY, L. F. & WEERASURIA, D. V. 1988. Facile Synthesis of (+)- and (-)-Shikimic Acid with Asymmetric Deuterium Labeling, Using Tricarbonyliron as a Lateral Control Group. *J. Org. Chem.*, 53, 278-81.
- BOCHKOV, D. V., SYSOLYATIN, S. V., KALASHNIKOV, A. I. & SURMACHEVA, I. A. 2012. Shikimic Acid: Review of its Analytical, Isolation, and Purification Techniques from Plant and Microbial Sources. *J. Chem. Biol.*, 5, 5-17.
- BOX, J. M., HARWOOD, L. M., HUMPHREYS, J. L., MORRIS, G. A., REDON, P. M. & WHITEHEAD, R. C. 2002. Dehydration of Quinate Derivatives: Synthesis of a Difluoromethylene Homologue of Shikimic Acid. *Synlett*, 2002, 358-60.
- CAMPBELL, M. M., SAINSBURY, M. & SEARLE, P. A. 1993. The Biosynthesis and Synthesis of Shikimic Acid, Chorismic Acid, and Related Compounds. *Synthesis*, 1993, 179-93.
- CASTRO LÓPEZ, M. D. M., CELA PÉREZ, M. C., DOPICO GARCÍA, M. S., LÓPEZ VILARIÑO, J. M., GONZÁLEZ RODRÍGUEZ, M. V. & BARRAL LOSADA, L. F. 2012. Preparation, Evaluation and Characterization of Quercetin-Molecularly Imprinted Polymer for Preconcentration and Clean-up of Catechins. *Anal. Chim. Acta*, 721, 68-78.
- CHEN, F. F. & SHI, Y. P. 2013. Application of Molecularly Imprinted Solid Phase Extraction in the Separation and Determination of Active Constituents from Natural Compounds. *Se Pu*, 31, 626-33.
- CHEN, L., XU, S. & LI, J. 2011. Recent Advances in Molecular Imprinting Technology: Current Status, Challenges and Highlighted Applications. *Chem. Soc. Rev.*, 40, 2922-42.
- CHENG, T. C., HUANG, Y. T., CHANG, C. Y., YAO, K. S. & HWANG, C. C. 2009. Molecular Recognition of Sulfaquinoxaline and Sulfapyridine with Molecularly Imprinted Polymer. *J. Chil. Chem. Soc.*, 54, 295-98.
- CLEOPHAX, J., MERCIER, D. & GÉRO, S. D. 1971. A Stereospecific Conversion of (-)-Methyl Tri-O-benzoylquininate to the Corresponding (-)-Methyl Shikimate. *Angew. Chem. Int. Edit.*, 10, 652-653.
- CORMACK, P. A. G. & ELORZA, A. Z. 2004. Molecularly Imprinted Polymers: Synthesis and Characterisation. *J. Chromatogr. B*, 804, 173-82.

- CYNTHIA, W. 2006. Pharmaceuticals: An Outbreak of New Sources of Avian Flu Drug. *Environ Health Perspect* [Online], 114. Available: <http://www.ncbi.nlm.nih.gov/pmc/articles/PMC1551983/> [Accessed 5 July 2013].
- DAMEN, J. & NECKERS, D. C. 1980. Memory of Synthesized Vinyl Polymers for Their Origins. *J. Org. Chem.*, 45, 1382-87.
- DANGSCHAT, G. & FISCHER, H. O. L. 1938. Übergang der Chinasäure in Shikimisäure. *Naturwissenschaften*, 26, 562-63.
- DAUWE, C. & SELLERGREN, B. 1996. Influence of Template Basicity and Hydrophobicity on the Molecular Recognition Properties of Molecularly Imprinted Polymers. *J. Chromatogr. A*, 753, 191-200.
- DAVIES, M. P., DE BIASI, V. & PERRETT, D. 2004. Approaches to the Rational Design of Molecularly Imprinted Polymers. *Anal. Chim. Acta*, 504, 7-14.
- DAVIS, B. D. 1951. Aromatic Biosynthesis. I. The Role of Shikimic Acid. *J. Biol. Chem.*, 191, 315-25.
- DAVIS, B. D. 1955. Intermediates in Amino Acid Biosynthesis. *Adv. Enzymol. Relat. Subj. Biochem.*, 16, 247-312.
- DICKEY, F. H. 1949. The Preparation of Specific Adsorbents. *Proc. Natl. Acad. Sci. U.S.A.*, 35, 227-29.
- DING, Z. Y. 2012. *Novel Method for Extracting and Separating Shikimic Acid in Illicium verum*. China Patent Application CN 201110167965.
- DONG, W., YAN, M., WU, G. & LIU, Z. 2005. Effect of Solvent on Molecular Recognition of Molecularly Imprinted Polymer: Experimental Investigation and Computational Quantum Chemistry Analysis. *CIESC Journal*, 56, 1247-52.
- DONG, X., SUN, H., L, X., WANG, H., LIU, S. & WANG, N. 2002. Separation of Ephedrine Stereoisomers by Molecularly Imprinted Polymers-Influence of Synthetic Conditions and Mobile Phase Compositions on the Chromatographic Performance. *Analyst*, 127, 1427-32.
- DRATHS, K. M., KNOP, D. R. & FROST, J. W. 1999. Shikimic Acid and Quinic Acid: Replacing Isolation from Plant Sources with Recombinant Microbial Biocatalysis. *J. Am. Chem. Soc.*, 121, 1603-04.
- ECKERT, F., LEITO, I., KALJURAND, I., KÜTT, A., KLAMT, A. & DIEDENHOFEN, M. 2009. Prediction of Acidity in Acetonitrile Solution with COSMO-RS. *J. Comput. Chem.*, 30, 799-810.

- EDMONDS, M. & PAYNE, R. 2005. Isolation of Shikimic Acid from Star Aniseed. *J. Chem. Educ.*, 82, 599-600.
- EIJKMAN, J. F. 1885. Sur les Principes Constituants de l'*Illicium religiosum* (Sieb.) (Shikimi-no-ki en japonais). *Recl. Trav. Chim. Pays-Bas*, 4, 32-54.
- ENRICH, L. B., SCHEUERMANN, M. L., MOHADJER, A., MATTHIAS, K. R., ELLER, C. F., NEWMAN, M. S., FUJINAKA, M. & POON, T. 2008. Liquidambar styraciflua: A Renewable Source of Shikimic Acid. *Tetrahedron Lett.*, 49, 2503-05.
- ERLENMEYER, H. 1966. *Filtermaterial auf Basis Kieselgel zur Adsorbierung von Nikotin aus Tabakrauch*. German Patent No. DE1218918.
- FARINA, V. & BROWN, J. D. 2006. Tamiflu: The Supply Problem. *Angew. Chem. Int. Edit.*, 45, 7330-34.
- FEDERSPIEL, M., FISCHER, R., HENNIG, M., MAIR, H.-J., OBERHAUSER, T., RIMMLER, G., ALBIEZ, T., BRUHIN, J., ESTERMANN, H., GANDERT, C., GÖCKEL, V., GÖTZÖ, S., HOFFMANN, U., HUBER, G., JANATSCH, G., LAUPER, S., RÖCKEL-STÄBLER, O., TRUSSARDI, R. & ZWAHLEN, A. G. 1999. Industrial Synthesis of the Key Precursor in the Synthesis of the Anti-Influenza Drug Oseltamivir Phosphate (Ro 64-0796/002, GS-4104-02): Ethyl (3R,4S,5S)-4,5-epoxy-3-(1-ethyl-propoxy)-cyclohex-1-ene-1-carboxylate. *Org. Process Res. Dev.*, 3, 266-74.
- FIL, B. A., YILMAZ, M. T., BAYAR, S. & ELKOCA, M. T. 2014. Investigation of Adsorption of the Dye stuff Astrazon Red Violet 3rn (Basic Violet 16) on Montmorillonite Clay. *Braz. J. Chem. Eng.*, 31, 17-82.
- FISCHER, H. O. L. & DANGSCHAT, G. 1934. Konstitution der Shikimisäure. (5. Mitteilung über Chinasäure und Derivate). *Helv. Chim. Acta*, 17, 1200-07.
- FISCHER, H. O. L. & DANGSCHAT, G. 1935. Abbau der Shikimisäure zur Aconitsäure. (6. Mitteilung über Chinasäure und Derivate). *Helv. Chim. Acta*, 18, 1204-06.
- FLEET, G. W. J. & SHING, T. K. M. 1983. An Entry to Chiral Cyclohexenes from Carbohydrates: A Short, Efficient, and Enantiospecific Synthesis of (-)-Shikimic Acid from D-Mannose. *J. Chem. Soc., Chem. Commun.*, 849-50.
- FLEET, G. W. J., SHING, T. K. M. & WARR, S. M. 1984. Enantiospecific Synthesis of Shikimic Acid from D-Mannose: Formation of a Chiral Cyclohexene by Intramolecular Olefination of a Carbohydrate-Derived Intermediate. *J. Chem. Soc., Perkin Trans. 1*, 905-08.

- FLORES, G. 2006. *Getting Around Flu Drug Shortage* [Online]. Available: <http://www.the-scientist.com/?articles.view/articleNo/23583/title/Getting-around-flu-drug-shortage/> [Accessed 3/7/2013 2013].
- FROST, J. W. 2007. *Methods and Materials for the Production of Shikimic Acid*. USA patent application US 10/572,976.
- GIBSON, J. M., THOMAS, P. S., THOMAS, J. D., BARKER, J. L., CHANDRAN, S. S., HARRUP, M. K., DRATHS, K. M. & FROST, J. W. 2001. Benzene-Free Synthesis of Phenol. *Angew. Chem. Int. Edit.*, 40, 1945-48.
- HAUPT, K. 2010. Biomaterials: Plastic Antibodies. *Nature Materials*, 9, 612-14.
- HAUPT, K., DZGOEV, A. & MOSBACH, K. 1998. Assay System for the Herbicide 2,4-Dichlorophenoxyacetic Acid Using a Molecularly Imprinted Polymer as an Artificial Recognition Element. *Anal. Chem.*, 70, 628-31.
- HSU, C.-Y., LIN, H.-Y., THOMAS, J. L. & CHOU, T.-C. 2006. Synthesis of and Recognition by Ribonuclease A Imprinted Polymers. *Nanotechnology*, 17, S77-S83.
- HIROSE, K. 2012. Quantitative Analysis of Binding Properties. *Analytical Methods in Supramolecular Chemistry*. Wiley-VCH Verlag GmbH & Co. KGaA.
- HUANG, F., XIU, Q., SUN, J. & HONG, E. 2002. Anti-Platelet and Anti-Thrombotic Effects of Triacetylshikimic Acid in Rats. *J. Cardiovasc. Pharm.*, 39, 262-70.
- IOMANTAS, Y. A. V., ABALKINA, E. G., POLANUER, B. M., YAMPOLSKAYA, T. A., BACHINA, T. A. & KOZLOV, Y. I. 2002. *Method for Producing Shikimic Acid*. US 09/532,800.
- IZE-LUDLOW, D., RAGONE, S., BERNSTEIN, J. N., BRUCK, I. S., DUCHOWNY, M. & GARCIA PENA, B. M. 2004. Chemical Composition of Chinese Star Anise (*Illicium verum*) and Neurotoxicity in Infants. *JAMA*, 291, 562-63.
- JIANG, P., WU, M., ZHENG, Y., WANG, C., LI, Y., XIN, J. & XU, G. 2004. Analysis of Coenzyme Q10 in Human Plasma by Column-Switching Liquid Chromatography. *J. Chromatogr. B*, 805, 297-301.
- JIANG, S., MEKKI, B., SINGH, G. & WIGHTMAN, R. H. 1994. Enantiospecific Synthesis of (-)-5-epi-Shikimic Acid and a New Route to (-)-Shikimic Acid. *Tetrahedron Lett.*, 35, 5505-08.
- JIANG, S. & SINGH, G. 1998. Chemical Synthesis of Shikimic Acid and its Analogues. *Tetrahedron*, 54, 4697-4753.

- JOHANSSON, L., LINDSKOG, A., SILFVERSPARRE, G., CIMANDER, C., NIELSEN, K. F. & LIDÉN, G. 2005. Shikimic Acid Production by a Modified Strain of *E. coli* (W3110.shik1) Under Phosphate-limited and Carbon-limited Conditions. *Biotechnol. Bioeng.*, 92, 541-552.
- KALJURAND, I., RODIMA, T., PIHL, A., MÄEMETS, V., LEITO, I., KOPPEL, I. A. & MISHIMA, M. 2003. Acid–Base Equilibria in Nonpolar Media. 4. Extension of the Self-Consistent Basicity Scale in THF Medium. Gas-Phase Basicities of Phosphazenes. *J. Org. Chem.*, 68, 9988-93.
- KARLSSON, J. G., KARLSSON, B., ANDERSSON, L. I. & NICHOLLS, I. A. 2004. The Roles of Template Complexation and Ligand Binding Conditions on Recognition in Bupivacaine Molecularly Imprinted Polymers. *Analyst*, 129, 456-62.
- KEMPE, M. 1996. Antibody-Mimicking Polymers as Chiral Stationary Phases in HPLC. *Anal. Chem.*, 68, 1948-53.
- KEMPE, M. & MOSBACH, K. 1995. Receptor Binding Mimetics: A Novel Molecularly Imprinted Polymer. *Tetrahedron Lett.*, 36, 3563-66.
- KEMPE, M., MOSBACH, K. & FISCHER, L. 1993. Chiral Separation Using Molecularly Imprinted Heteroaromatic Polymers. *J. Mol. Recognit.*, 6, 25-29.
- KITAGAWA, I., YOSHIKAWA, M., IKEDA, Y. & KAYAKIRI, H. 1982. Reductive One Step Elimination of an Acetoxy Residue at b-Position of a Nitro Group: Syntheses of (-)-Shikimic Acid from D-Mannose and 2-Deoxystreptamine pentaacetate from N -acetyl-D-glucosamine. *Heterocycles*, 17, 209-14.
- KNOP, D. R., DRATHS, K. M., CHANDRAN, S. S., BARKER, J. L., VON DAENIKEN, R., WEBER, W. & FROST, J. W. 2001. Hydroaromatic Equilibration During Biosynthesis of Shikimic Acid. *J. Am. Chem. Soc.*, 123, 10173-82.
- KOMIYAMA, M., TAKEUCHI, T., MUKAWA, T. & ASANUMA, H. 2004. Fundamentals of Molecular Imprinting. *Molecular Imprinting: From Fundamentals to Applications*. Wiley-VCH Verlag GmbH & Co. KGaA.
- KOREEDA, M. & CIUFOLINI, M. A. 1982. Natural Product Synthesis via Allylsilanes. 1. Synthesis and Reactions of (1E,3E)-4-acetoxy-1-(trimethylsilyl)-1,3-butadiene and its Use in the Total Synthesis of (±)-Shikimic Acid. *J. Am. Chem. Soc.*, 104, 2308-10.
- KOREEDA, M., TENG, K. & MURATA, T. 1990. (1E,3E)-4-acetoxy-1-phenyldimethylsilyl-1,3-butadiene as a Surrogate for (1E,3E)-1,4- diacetoxy-1,3-butadiene: A Highly Efficient Synthesis of (±)-Shikimic Acid. *Tetrahedron Lett.*, 31, 5997-6000.

- KUGIMIYA, A., MATSUI, J., TAKEUCHI, T., YANO, K., MUGURUMA, H., ELGERSMA, A. V. & KARUBE, I. 1995. Recognition of Sialic Acid Using Molecularly Imprinted Polymer. *Anal. Lett.*, 28, 2317-23.
- KÜTT, A., LEITO, I., KALJURAND, I., SOOVÄLI, L., VLASOV, V. M., YAGUPOLSKII, L. M. & KOPPEL, I. A. 2006. A Comprehensive Self-Consistent Spectrophotometric Acidity Scale of Neutral Brønsted Acids in Acetonitrile. *J. Org. Chem.*, 71, 2829-38.
- LEUNG, M. K. P., CHIU, B. K. W. & LAM, M. H. W. 2003. Molecular Sensing of 3-chloro-1,2-propanediol by Molecular Imprinting. *Anal. Chim. Acta*, 491, 15-25.
- LIU, A., LIU, Z. Z., ZOU, Z. M., CHEN, S. Z., XU, L. Z. & YANG, S. L. 2004. Synthesis of (+)-Zeylenone from Shikimic Acid. *Tetrahedron*, 60, 3689-94.
- LOUDON, G. M. 2005. *Organic Chemistry* (4th ed.), New York, Oxford University Press.
- LU, Y., LI, C., WANG, X., SUN, P. & XING, X. 2004. Influence of Polymerization Temperature on the Molecular Recognition of Imprinted Polymers. *J. Chromatogr. B*, 804, 53-59.
- LÜBKE, C., LÜBKE, M., WHITCOMBE, M. J. & VULFSON, E. N. 2000. Imprinted Polymers Prepared with Stoichiometric Template–Monomer Complexes: Efficient Binding of Ampicillin from Aqueous Solutions. *Macromolecules*, 33, 5098-5105.
- LULIŃSKI, P. & MACIEJEWSKA, D. 2009. Examination of Imprinting Process with Molsidomine as a Template. *Molecules*, 14, 2212-25.
- MAHONY, J., MOLINELLI, A., NOLAN, K., SMYTH, M. R. & MIZAIKOFF, B. 2005. Towards the Rational Development of Molecularly Imprinted Polymers: <sup>1</sup>H NMR Studies on Hydrophobicity and Ion-pair Interactions as Driving Forces for Selectivity. *Biosens. Bioelectron.*, 20, 1884-93.
- MARTIN, E., DUKE, J., PELKKI, M., CLAUSEN, E. C. & CARRIER, D. J. 2010. Sweetgum (*Liquidambar styraciflua* L.): Extraction of Shikimic Acid Coupled to Dilute Acid Pretreatment. *Appl. Biochem. Biotech.*, 162, 1660-68.
- MCCRINDLE, R., OVERTON, K. H. & RAPHAEL, R. A. 1960. 315. A Stereospecific Total Synthesis of D(-)-Shikimic Acid. *J. Chem. Soc. (Resumed)*, 1560-65.
- MOHAMED, M. H. & WILSON, L. D. 2012. Porous Copolymer Resins: Tuning Pore Structure and Surface Area with Non Reactive Porogens. *Nanomaterials*, 2, 163-86.

- MUHAMMAD, T., NUR, Z., PILETSKA, E. V., YIMIT, O. & PILETSKY, S. A. 2012. Rational Design of Molecularly Imprinted Polymer: the Choice of Cross-linker. *Analyst*, 137, 2623-28.
- NICHOLLS, I. A., ADBO, K., ANDERSSON, H. S., ANDERSSON, P. O., ANKARLOO, J., HEDIN-DAHLSTRÖM, J., JOKELA, P., KARLSSON, J. G., OLOFSSON, L., ROSENGREN, J., SHORAVI, S., SVENSON, J. & WIKMAN, S. 2001. Can We Rationally Design Molecularly Imprinted Polymers? *Anal. Chim. Acta*, 435, 9-18.
- NICHOLLS, I. A., RAMSTRÖM, O. & MOSBACH, K. 1995. Insights into the role of the hydrogen bond and hydrophobic effect on recognition in molecularly imprinted polymer synthetic peptide receptor mimics. *J. Chromatogr. A*, 691, 349-53.
- NOMACHI, M., KUBO, T., HOSOYA, K. & KAYA, K. 2006. Solvent Effects in the Preparation of Molecularly Imprinted Polymers for Melatonin Using N-propionyl-5-methoxytryptamine as the Pseudo Template. *Anal. Bioanal. Chem.*, 384, 1291-96.
- OLADOJA, N. A., ABOLUWOYE, C. O. & OLADIMEJI, Y. B. 2008. Kinetics and Isotherm Studies on Methylene Blue Adsorption onto Ground Palm Kernel Coat. *Turkish J. Eng. Env. Sci.*, 32, 303-12.
- OSMANI, Q., HUGHES, H., FLAVIN, K., HEDIN-DAHLSTROM, J., ALLENDER, C., FRISBY, J. & MCLOUGHLIN, P. 2008. The Use of FTIR and NMR Spectroscopies to Study Prepolymerisation Interactions in Nitrogen Heterocycles. *Anal. Bioanal. Chem.*, 391, 1229-36.
- PARDO, A., MESPOUILLE, L., DUBOIS, P., DUEZ, P. & BLANKERT, B. 2012. Targeted Extraction of Active Compounds from Natural Products by Molecularly Imprinted Polymers. *Cent. Eur. J. Chem.*, 10, 751-65.
- PATRIKKEEV, V. V., KLABUNOVSKII, E. I. & MARDASHEV, J. S. 1960. USSR Patent No. 125491.
- PATRIKKEEV, V. V. & SMIRNOVA, Z. S. USSR Patent No. 136096.
- PERRIN, D. D. 1965. *IUPAC Chemical Data Series: Dissociation Constants of Organic Bases in Aqueous Solution*, London, Butterworths.
- PILETSKA, E. V., GUERREIRO, A. N. R., WHITCOMBE, M. J. & PILETSKY, S. A. 2009. Influence of the Polymerization Conditions on the Performance of Molecularly Imprinted Polymers. *Macromolecules*, 42, 4921-28.

- PILETSKY, S. A., PILETSKA, E. V., KARIM, K., FREEBAIRN, K. W., LEGGE, C. H. & TURNER, A. P. F. 2002. Polymer Cookery: Influence of Polymerization Conditions on the Performance of Molecularly Imprinted Polymers. *Macromolecules*, 35, 7499-7504.
- POLYAKOV, M. V. 1931. Adsorption Properties and Structure of Silica Gel. *Zhurnal Fizicheskoi Khimii*, 2, 799-805.
- QUAGLIA, M., CHENON, K., HALL, A. J., DE LORENZI, E. & SELLERGRÉN, B. 2001. Target Analogue Imprinted Polymers with Affinity for Folic Acid and Related Compounds. *J. Am. Chem. Soc.*, 123, 2146-54.
- RAMSTROM, O. & ANSELL, R. J. 1998. Molecular Imprinting Technology: Challenges and Prospects for the Future. *Chirality*, 10, 195-209.
- RAVIGADEVI, S., YEW AI, T., KALYANA, S., MAHINDA, A., SAMBANDAN, T. G., CHOKYUN, R., ANTHONY, J. S., KRISHNAN, S., SOON-SEN, L., KENNETH, C. H. & MOHD BASRI, W. 2011. Oil Palm Vegetation Liquor: A New Source of Phenolic Bioactives. *Br. J. Nutr.*, 106, 1655-63.
- ROHLOFF, J. C., KENT, K. M., POSTICH, M. J., BECKER, M. W., CHAPMAN, H. H., KELLY, D. E., LEW, W., LOUIE, M. S., MCGEE, L. R., PRISBE, E. J., SCHULTZE, L. M., YU, R. H. & ZHANG, L. 1998. Practical Total Synthesis of the Anti-Influenza Drug GS-4104. *J. Org. Chem.*, 63, 4545-50.
- ROSTAMIZADEH, K., ABDOLLAHI, H. & PARSAJOO, C. 2013. Synthesis, Optimization, and Characterization of Molecularly Imprinted Nanoparticles. *Int. Nano Lett.*, 3, 20-28.
- RUSHTON, G. T., KARNS, C. L. & SHIMIZU, K. D. 2005. A Critical Examination of the Use of the Freundlich Isotherm in Characterizing Molecularly Imprinted Polymers (MIPs). *Anal. Chim. Acta*, 528, 107-13.
- SADEGHI, S. & JAHANI, M. 2013. Selective Solid Phase Extraction Using Molecular Imprinted Polymer Sorbent for the Analysis of Florfenicol in Food Samples. *Food Chem.*, 141, 1242-51.
- SARMINI, K. & KENNDLER, E. 1999. Ionization Constants of Weak Acids and Bases in Organic Solvents. *J. Biochem. Bioph. Meth.*, 38, 123-137.
- SCHNEIDER, H. J. & YATSIMIRSKY, A. K. 2000. *Principles and Methods in Supramolecular Chemistry*, New York, J. Wiley.
- SEECHAMNANTURAKIT, V. & SUEDEE, R. 2012. The Synthesis and Characterisation of Retinol-Molecularly Imprinted Polymers as a Sorbent in Solid Phase Extraction. *Int. J. Appl. Sci. Tech.*, 2, 81-93



- SELLERGREN, B. 1989. Molecular Imprinting by Noncovalent Interactions: Tailor Made Chiral Stationary Phases of High Selectivity and Sample Load Capacity. *Chirality*, 1, 63-68.
- SELLERGREN, B. 1999. Polymer- and Template-Related Factors Influencing the Efficiency in Molecularly Imprinted Solid-Phase Extractions. *TrAC-Trend Anal. Chem.*, 18, 164-74.
- SELLERGREN, B. 2001. Imprinted Chiral Stationary Phases in High-Performance Liquid Chromatography. *J. Chromatogr. A*, 906, 227-52.
- SELLERGREN, B. & ANDERSSON, L. 1990. Molecular Recognition in Macroporous Polymers Prepared by a Substrate Analog Imprinting Strategy. *J. Org. Chem.*, 55, 3381-83.
- SELLERGREN, B. & NILSSON, K. 1989. Molecular Imprinting by Multiple Noncovalent Host-Guest Interactions: Synthetic Polymers with Induced Specificity. *Method Mol. Cell. Biol.*, 59-62.
- SELLERGREN, B. & SHEA, K. J. 1993. Influence of Polymer Morphology on the Ability of Imprinted Network Polymers to Resolve Enantiomers. *J. Chromatogr. A*, 635, 31-49.
- SHEA, K. J. & DOUGHERTY, T. K. 1986. Molecular Recognition on Synthetic Amorphous Surfaces. The Influence of Functional Group Positioning on the Effectiveness of Molecular Recognition. *J. Am. Chem. Soc.*, 108, 1091-1093.
- SHEA, K. J. & SASAKI, D. Y. 1989. On the Control of Microenvironment Shape of Functionalized Network Polymers Prepared by Template Polymerization. *J. Am. Chem. Soc.*, 111, 3442-3444.
- SHEA, K. J. & SASAKI, D. Y. 1991. An Analysis of Small-Molecule Binding to Functionalized Synthetic Polymers by <sup>13</sup>C CP/MAS NMR and FT-IR Spectroscopy. *J. Am. Chem. Soc.*, 113, 4109-20.
- SHEA, K. J. & THOMPSON, E. 1978. Template Synthesis of Macromolecules: Selective Functionalization of an Organic Polymer. *J. Org. Chem.*, 43, 4253-55.
- SIBRIAN-VAZQUEZ, M. & SPIVAK, D. A. 2003. Enhanced Enantioselectivity of Molecularly Imprinted Polymers Formulated with Novel Cross-Linking Monomers. *Macromolecules*, 36, 5105-13.
- SIBRIAN-VAZQUEZ, M. & SPIVAK, D. A. 2004. Molecular Imprinting Made Easy. *J. Am. Chem. Soc.*, 126, 7827-33.

- SIMON, R., COLLINS, M. E. & SPIVAK, D. A. 2007. Shape Selectivity Versus Functional Group Pre-organization in Molecularly Imprinted Polymers. *Anal. Chim. Acta*, 591, 7-16.
- SING, K. S. W. 1982. Reporting Physisorption Data for Gas/Solid Systems with Special Reference to the Determination of Surface Area and Porosity (Provisional). *Pure Appl. Chem.*, 54, 2201-18.
- SMISSMAN, E. E., SUH, J. T., OXMAN, M. & DANIELS, R. 1959. A Stereospecific Synthesis of DL-Shikimic Acid. *J. Am. Chem. Soc.*, 81, 2909-10.
- SMISSMAN, E. E., SUH, J. T., OXMAN, M. & DANIELS, R. 1962. A Stereospecific Synthesis of D(-)-Shikimic Acid. *J. Am. Chem. Soc.*, 84, 1040-41.
- SONG, X., WANG, J. & ZHU, J. 2009. Effect of Porogenic Solvent on Selective Performance of Molecularly Imprinted Polymer for Quercetin. *Materials Research.*, 12, 299-304.
- SPIVAK, D. 2004. Selectivity in Molecularly Imprinted Matrices. In: MINGDI, Y. & OLOF, R. (eds.) *Molecularly Imprinted Materials- Science and Technology*. New York: Marcel Dekker.
- SPIVAK, D., GILMORE, M. A. & SHEA, K. J. 1997. Evaluation of Binding and Origins of Specificity of 9-Ethyladenine Imprinted Polymers. *J. Am. Chem. Soc.*, 119, 4388-93.
- SPIVAK, D. A. 2005. Optimization, Evaluation, and Characterization of Molecularly Imprinted Polymers. *Adv. Drug Deliv. Rev.*, 57, 1779-94.
- SPIVAK, D. A. & CAMPBELL, J. 2001. Systematic Study of Steric and Spatial Contributions to Molecular Recognition by Non-Covalent Imprinted Polymers. *Analyst*, 126, 793-97.
- SPRINSON, D. B. 1961. The Biosynthesis of Aromatic Compounds from D-Glucose. In: MELVILLE, L. W. & TIPSON, R. S. (eds.) *Advances in Carbohydrate Chemistry*. Academic Press.
- SUI, R. 2008. Separation of Shikimic Acid from Pine Needles. *Chem. Eng. Tech.*, 31, 469-73.
- SVENSON, J., ANDERSSON, H. S., PILETSKY, S. A. & NICHOLLS, I. A. 1998. Spectroscopic Studies of the Molecular Imprinting Self-Assembly Process. *J. Mol. Recognit.*, 11, 83-86.
- TAKEUCHI, T., MURASE, N., MAKI, H., MUKAWA, T. & SHINMORI, H. 2006. Dopamine Selective Molecularly Imprinted Polymers via Post-Imprinting Modification. *Org. Biomol. Chem.*, 4, 565-68.

- TANG, L., XIANG, H., SUN, Y., QIU, L., CHEN, D., DENG, C. & CHEN, W. 2009. Monopalmitoyloxy Shikimic Acid: Enzymatic Synthesis and Anticoagulation Activity Evaluation. *Appl Biochem Biotechnol*, 158, 408-15.
- THORDARSON, P. 2011. Determining Association Constants from Titration Experiments in Supramolecular Chemistry. *Chem. Soc. Rev.*, 40, 1305-23.
- TOM, L. A., SCHNECK, N. A. & WALTER, C. 2012. Improving the Imprinting Effect by Optimizing Template:Monomer:Cross-linker Ratios in a Molecularly Imprinted Polymer for Sulfadimethoxine. *J. Chromatogr. B*, 909, 61-64.
- USUKI, T., YASUDA, N., YOSHIZAWA-FUJITA, M. & RIKUKAWA, M. 2011. Extraction and Isolation of Shikimic Acid from Ginkgo Biloba Leaves Utilizing an Ionic Liquid that Dissolves Cellulose. *Chem. Commun.*, 47, 10560-62.
- WANG, X. J., XU, Z. L., YANG, Z. G. & BING, N. C. 2007. Molecular Recognition in Aqueous Media with Molecular Imprinting Technique. *Prog in Chemistry*, 19, 805-12.
- WHITCOMBE, M. J. & KIRSCH, N. 2004. The Semi-Covalent Approach. In: MINGDI, Y. & OLOF, R. (eds.) *Molecularly Imprinted Materials- Science and Technology*. New York: Marcel Dekker.
- WHITCOMBE, M. J., MARTIN, L. & VULFSON, E. N. 1998. Predicting the Selectivity of Imprinted Polymers. *Chromatographia*, 47, 457-64.
- WHITCOMBE, M. J., RODRIGUEZ, M. E., VILLAR, P. & VULFSON, E. N. 1995. A New Method for the Introduction of Recognition Site Functionality into Polymers Prepared by Molecular Imprinting: Synthesis and Characterization of Polymeric Receptors for Cholesterol. *J. Am. Chem. Soc.*, 117, 7105-11.
- WULFF, G. 1986. Molecular Recognition in Polymers Prepared by Imprinting with Templates. *Polymeric Reagents and Catalysts*. American Chemical Society.
- WULFF, G. 1995. Molecular Imprinting in Cross-linked Materials with the Aid of Molecular Templates— A Way towards Artificial Antibodies. *Angew. Chem. Int. Edit.*, 34, 1812-32.
- WULFF, G., BEST, W. & AKELAH, A. 1984. Enzyme-Analogue Built Polymers, 17 Investigations on the Racemic Resolution of Amino Acids. *Reactive Polymers, Ion Exchangers, Sorbents*, 2, 167-74.
- WULFF, G., GROBE-EINSLER, R., VESPER, W. & SARHAN, A. 1977a. Enzyme-Analogue Built Polymers, 5. On the Specificity Distribution of Chiral Cavities Prepared in Synthetic Polymers. *Macromol. Chem.*, 178, 2817-25.

- WULFF, G., OBERKOBUSCH, D. & MINÁRIK, M. 1985. Enzyme-Analogue Built Polymers, 18 Chiral Cavities in Polymer Layers Coated on Wide-Pore Silica. *Reactive Polymers, Ion Exchangers, Sorbents*, 3, 261-75.
- WULFF, G. & SARHAN, A. 1972. The Use of Polymers with Enzyme-Analogous Structures for the Resolution of Racemates. *Angew. Chem. Int. Edit.*, 11, 334-42.
- WULFF, G. & SCHAUHOFF, S. 1991. Enzyme-Analog Built Polymers, 27. Racemic Resolution of Free Sugars with Macroporous Polymers Prepared by Molecular Imprinting. Selectivity Dependence on the Arrangement of Functional Groups Versus Spatial Requirements. *J. Org. Chem.*, 56, 395-400.
- WULFF, G. & SCHULZE, I. 1978. Directed Cooperativity and Site Separation of Mercapto Groups in Synthetic Polymers. *Angew. Chem. Int. Edit.*, 17, 537-38.
- WULFF, G. & VESPER, W. 1978. Preparation of Chromatographic Sorbents with Chiral Cavities for Racemic Resolution. *J. Chromatogr. A*, 167, 171-86.
- WULFF, G., VESPER, W., GROBE-EINSLER, R. & SARHAN, A. 1977b. Enzyme-Analogue Built Polymers, 4. On the Synthesis of Polymers Containing Chiral Cavities and Their Use for the Resolution of Racemates. *Macromol. Chem.*, 178, 2799-2816.
- WULFF, G. & VIETMEIER, J. 1989. Enzyme-Analogue Built Polymers, 26. Enantioselective Synthesis of Amino Acids Using Polymers Possessing Chiral Cavities Obtained by an Imprinting Procedure with Template Molecules. *Macromol. Chem.*, 190, 1727-35.
- XU, Z.-G., LIU, Z.-M. & GUO, J.-Y. 2013. Water-Compatible Molecularly Imprinted Technique and its Application. *Chemical World*, 754-58.
- XUE, M., WANG, Y., MENG, Z., ZHANG, W., WU, Y. & JIANG, S. 2013. Extraction of Shikimic Acid from Chinese Star Anise Using Flash Column Chromatography on A Molecularly-Imprinted Polymer Column. *J. Liq. Chromatogr. R. T.*, 36, 2677-86.
- YAN, H. & ROW, K. H. 2006. Characteristic and Synthetic Approach of Molecularly Imprinted Polymer. *Int. J. Mol. Sci.*, 7, 155-78.
- YANG, H. Y. & SONG, J. F. 2006. Inclusion of Coenzyme Q10 with  $\beta$ -Cyclodextrin Studied by Polarography. *Yao Xue Xue Bao*, 41, 671-74.
- YILMAZ, E., MOSBACH, K. & HAUPT, K. 1999. Influence of Functional and Cross-linking Monomers and the Amount of Template on the Performance of Molecularly Imprinted Polymers in Binding Assays. *Anal. Commun.*, 36, 167-70.

- YOSHIZAKO, K., HOSOYA, K., IWAKOSHI, Y., KIMATA, K. & TANAKA, N. 1998. Porogen Imprinting Effects. *Anal. Chem.*, 70, 386-89.
- ZHANG, H. 2014. Water-Compatible Molecularly Imprinted Polymers: Promising Synthetic Substitutes for Biological Receptors. *Polymer*, 55, 699-714.
- ZHANG, H., HE, H., LI, J., LI, H. & YAO, Y. Y. 2011. Water Compatible Molecular Imprinting Separation Technique and its Application in Analytical Chemistry. *Progress in Chemistry*, 23, 2140-50.
- ZHANG, T., LIU, F., CHEN, W., WANG, J. & LI, K. 2001. Influence of Intramolecular Hydrogen Bond of Templates on Molecular Recognition of Molecularly Imprinted Polymers. *Anal. Chim. Acta*, 450, 53-61.
- ZHANG, Y., LIU, A., YE, Z. G., LIN, J., XU, L. Z. & YANG, S. L. 2006. New Approach to the Total Synthesis of (-)-Zeylenone from Shikimic Acid. *Chem. Pharm. Bull. (Tokyo)*, 54, 1459-61.
- ZHANG, Y., NA, Q., CHEN, N., CHEN, J., ZHOU, X. & BAI, L. 2013. Preparation and Evaluation of Melamine Molecularly Imprinted Polymers by Thermal- and Photo-Initiation Methods. *J. Chin. Chem. Soc.*, 60, 204-11.
- ZHU, X.-F., CAO, Q.-E., YANG, X.-Q., LI, F., WANG, G.-S. & DING, Z.-T. 2009. Preparation and Recognition Mechanism of Gallic Acid Imprinted Polymers. *Helv. Chim. Acta*, 92, 78-87.