



**UNIVERSITI PUTRA MALAYSIA**

***EXTRACTION AND CHARACTERIZATION OF NANOCRYSTALLINE  
CELLULOSE FROM OIL PALM EMPTY FRUIT BUNCH AND ITS  
POTENTIAL AS ADSORBENT FOR DYE REMOVAL***

**BAWAANII SHANMUGARAJAH**

**FK 2017 77**



**EXTRACTION AND CHARACTERIZATION OF NANOCRYSTALLINE  
CELLULOSE FROM OIL PALM EMPTY FRUIT BUNCH AND ITS  
POTENTIAL AS ADSORBENT FOR DYE REMOVAL**

By

**BAWAANII SHANMUGARAJAH**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra  
Malaysia, in Fulfillment of the Requirements for the Degree of  
Master of Science**

**May 2017**

## **COPYRIGHT**

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in  
fulfillment of the requirement for the Degree of Master of Science

**EXTRACTION AND CHARACTERIZATION OF NANOCRYSTALLINE  
CELLULOSE FROM OIL PALM EMPTY FRUIT BUNCH AND ITS  
POTENTIAL AS ADSORBENT FOR DYE REMOVAL**

By

**BAWAANII SHANMUGARAJAH**

**May 2017**

**Chairman : Professor Ir Thomas Choong Shean Yaw, PhD**  
**Faculty : Engineering**

Over the past few decades, enormous interest has been manifested in using biomass as a source of renewable energy and materials. Cellulose, in the form of Nanocrystalline Cellulose (NCC), gains prominence as a new nanostructured material. In this study, NCC was extracted from oil palm empty fruit bunch (EFB) via acid hydrolysis method. NCC was successfully extracted from EFB using 64 wt% sulfuric acid at 45°C for 45 min. The products obtained from each stage were characterized to confirm the removal of non-cellulosic components. In addition, X-ray Diffraction (XRD) results disclosed that nanocrystals exhibited crystallinity index of 60%. On the other hand, Transmission Electron Microscope (TEM) showed NCC exhibited network like structure. It also showed that the native cellulose crystalline network region is approximately 20 nm diameter, while Dynamic Light Scattering (DLS) suggested NCC to have an average particle size of 291.4 nm. Following that, NCC was employed for Methylene Blue (MB) dye removal. Batch adsorption studies were carried out to analyze the effect of contact time, initial dye concentration, adsorbent dosage and agitation speed at a temperature of  $30 \pm 2^\circ\text{C}$ . The obtained experimental data fitted well to Langmuir isotherm with monolayer adsorption capacity of 144.93 mg/g. Pseudo-second-order kinetic model provided a better correlation of the experimental data than others such as Lagergrens pseudo-first-order model. It was also found that intraparticle diffusion was not the only rate controlling step, instead, boundary layer diffusion was also contributing to the adsorption activity.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk Ijazah Sarjana Sains

**KAJIAN PENCIRIAN KRISTAL SELULOSA NANO DIEKSTRAK  
DARIPADA TEMPURUNG KELAPA SAWIT DAN POTENSINYA  
SEBAGAI PENYERAP UNTUK PENYINGKIRAN PEWARNA**

Oleh

**BAWAANII SHANMUGARAJAH**

**Mei 2017**

**Pengerusi : Profesor Ir Thomas Choong Shean Yaw, PhD**  
**Fakulti : Kejuruteraan**

Sejak beberapa dekad yang lalu, kepentingan yang sangat besar telah dimanifestasikan dalam menggunakan biojisim sebagai sumber tenaga dan bahan yang boleh diperbaharui. Selulosa, dalam bentuk selulosa kristal nano (NCC), mendapat kemasyhuran sebagai bahan baru yang bersize nano. Dalam kajian ini, NCC telah diasingkan daripada tempurung kelapa sawit (EFB) melalui proses asid hidrolisis. NCC telah berjaya diekstrak daripada EFB dengan menggunakan 64 wt% asid sulfurik pada suhu 45°C selama 45 min. Produk yang diperolehi dari setiap peringkat diuji menggunakan untuk mengesahkan penyingkiran komponen bukan selulosa. Selain itu, keputusan *X-ray Diffraction* (XRD) menunjukkan bahawa kristal nano mempamerkan indeks penghabluran sebanyak 60%. *Transmission Electron Microscope* (TEM) menunjukkan pendedahan kawasan rangkaian kristal nano asli (kira-kira 20 nm diameter), manakala *Dynamic Light Scattering* (DLS) mencadangkan NCC membawa saiz zarah purata 291.4 nm. Bahan tersebut kemudiannya digunakan untuk penyingkiran pewarna Metil Biru (MB). Kajian penjerapan kumpulan telah dijalankan untuk menganalisis kesan masa sentuhan, kepekatan awal pewarna, dos bahan penjerap dan kelajuan agitasi pada suhu  $30 \pm 2^\circ \text{C}$ . Data eksperimen yang diperolehi melengkapi *Langmuir isotherm* dengan kapasiti penjerapan monolayer pada 144.93 mg/g. Model kinetik *pseudo-second-order* memberi korelasi yang lebih baik bagi data eksperimen berbanding model lain seperti model kinetik *Lagergrens pseudo-first-order*. Didapati juga *intraparticle diffusion* bukan satu-satunya langkah kadar kawalan, sebaliknya, *boundary layer diffusion* juga menyumbang kepada aktiviti penjerapan.

## ACKNOWLEDGEMENTS

I would like to express my sincere appreciation and gratitude to Profesor Dr. Ir Thomas Choong Shean Yaw and Dr. Wan Azlina Bt Wan Abdul Karim Ghani for their guidance, patience, motivation and immense knowledge during my research. Besides my advisors, I would like to thank my dearest supervisor Dr. Tan Khang Wei for his guidance, support and sleepless night throughout my research and thesis writing. I am grateful to get such a wonderful supervisor.

My sincere thanks also go to Ms. Jully, Dr. Irene, Dr. Kiew, Mr. Mubarak for their encouragement and assistance throughout my undergraduate and postgraduate studies.

Besides that, my deepest gratitude goes to my parents and Lord for their blessings. Last but not least, I would like to thank Mr. Prasanna Mahadevan for his absolute support, especially in encouraging and motivating me to complete this endeavor.

This thesis was submitted to the Senate of the Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows:

**Thomas Choong Shean Yaw, PhD**

Professor, Ir  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Wan Azlina Bt Wan Abdul Karim Ghani, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)

**Tan Khang Wei, PhD**

Associate Professor  
Faculty of Engineering  
UCSI Universiti  
(Member)

---

**ROBIAH BINTI YUNUS, PhD**

Professor and Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:

## Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) were adhered to.

Signature: \_\_\_\_\_

Name of Chairman  
of Supervisory  
Committee:

Professor Ir Dr. Thomas Choong Shean Yaw

Signature: \_\_\_\_\_

Name of Member  
of Supervisory  
Committee:

Associate Professor Dr. Wan Azlina Bt Wan  
Abdul Karim Ghani

Signature: \_\_\_\_\_

Name of Member  
of Supervisory  
Committee:

Associate Professor Dr. Tan Khang Wei



## TABLE OF CONTENTS

	Page
<b>ABSTRACT</b>	i
<b>ABSTRAK</b>	ii
<b>ACKNOWLEDGEMENTS</b>	iii
<b>APPROVAL</b>	iv
<b>DECLARATION</b>	vi
<b>LIST OF TABLES</b>	xi
<b>LIST OF FIGURES</b>	xiii
<b>LIST OF ABBREVIATIONS</b>	xv
 <b>CHAPTER</b>	
 <b>1 INTRODUCTION</b>	 1
1.1 Background	1
1.2 Problem statement	1
1.3 Research objectives	2
1.4 Scope of research	2
1.5 Thesis outline	2
 <b>2 LITERATURE REVIEW</b>	 3
2.1 Introduction	3
2.2 Palm oil biomass	3
2.3 Empty Fruit Bunch (EFB)	5
2.4 Structure of cellulose	9
2.5 Crystalline cellulose	10
2.6 Cellulose source materials	11
2.7 Characteristics of NCC	11
2.7.1 Large specific surface area	11
2.7.2 Abundant surface hydroxyl groups	11
2.7.3 High crystallinity	12
2.7.4 High aspect ratio	12
2.8 Methods of isolation	14
2.8.1 Washing/ size reduction	14
2.8.2 Alkaline treatment	14
2.8.3 Bleaching treatment/delignification	15
2.8.4 Acid hydrolysis	17
2.8.5 Steam explosion (autohydrolysis)	18
2.8.6 Centrifugation and dialysis	19
2.8.7 Ultrasonication	19
2.9 Applications	22
2.9.1 Energy	22
2.9.2 Water treatment	23
2.9.3 Oil and gas	23
2.10 Dyes	23
2.10.1 Introduction	23
2.10.2 Dyes sources and their classification system	23

	2.10.3	Natural dyes	24
	2.10.4	Synthetic dyes	24
	2.11	Effects of dyes	27
	2.12	Dye removal methods	28
	2.13	Adsorption	29
	2.14	Adsorption Isotherms	29
	2.14.1	Langmuir Adsorption Isotherm	30
	2.14.2	Freundlich Adsorption Isotherm	30
<b>3</b>		<b>EXTRACTION OF NANOCRYSTALLINE CELLULOSE FROM OIL PALM BIOMASS</b>	<b>31</b>
	3.1	Introduction	31
	3.2	Methodology	32
	3.2.1	Materials	32
	3.2.2	Extraction of cellulose from empty fruit bunch	32
	3.2.3	Isolation of nanocrystalline cellulose	32
	3.2.4	ASTM Chemical Composition Analysis	35
	3.2.5	Fourier transform infrared spectroscopy	35
	3.2.6	Thermogravimetric analysis	35
	3.2.7	X-ray diffraction	36
	3.2.8	Electron microscopic analysis	36
	3.2.9	Particle size measurement	36
	3.3	Results and Discussion	36
	3.3.1	Acid hydrolysis at Various Conditions	36
	3.3.1.1	Effect of sulfuric acid concentration	37
	3.3.1.2	Effect of contact time and temperature	37
	3.3.2	Fourier Transform Infrared Spectroscopy	39
	3.3.3	Chemical composition and morphological study on NCC	42
	3.3.4	Dynamic Light Scattering	43
	3.3.5	Thermal Stability Analysis	44
	3.3.6	X-ray Diffraction Analysis	49
	3.4	Conclusion	50
<b>4</b>		<b>REMOVAL OF METHYLENE BLUE FROM AQUEOUS SOLUTION USING NANOCRYSTALLINE CELLULOSE</b>	<b>52</b>
	4.1	Introduction	52
	4.2	Materials and methods	53
	4.2.1	Adsorbate	53
	4.2.2	Preparation of NCC as adsorbent	53
	4.2.3	Equilibrium studies	53
	4.2.4	Batch kinetic studies	54
	4.3	Characterization of adsorbent	54
	4.3.1	Fourier transform infrared spectroscopy	54
	4.3.2	Microscopic analysis	54
	4.3.3	Surface physical properties	54
	4.4	Results and Discussion	55
	4.4.1	Characterization of NCC	55
	4.4.2	Adsorption studies	56

4.4.2.1	Adsorbent dosage	58
4.4.2.2	Solution pH	59
4.4.2.3	Agitation	60
4.4.2.4	Contact time and initial dye concentration	61
4.4.2.5	Adsorption kinetics	62
4.4.2.6	Isotherm analysis	67
4.5	Comparison of adsorption capacities between NCC and other adsorbents	69
4.6	Conclusion	70
<b>5</b>	<b>CONCLUSION AND RECOMMENDATIONS FOR FUTURE RESEARCH</b>	71
5.1	Conclusion	71
5.2	Recommendations for future research	71
	<b>REFERENCES</b>	72
	<b>APPENDICES</b>	79
	<b>BIODATA OF STUDENT</b>	80
	<b>LIST OF PUBLICATIONS</b>	81

## LIST OF TABLES

Table	Page
2.1 Oil palm Planted Area in hectares by State as of December 2016	4
2.2 Proximate and Ultimate Analysis of EFB	6
2.3 Summary on Structure, Morphology and Shape of Nanocellulose from Various Sources	13
2.4 Crystallinity Index Values of Nanocellulose from Various Sources	14
2.5 Various Alkali and Bleaching Treatments of Cellulose Fibers	16
2.6 Various Acid Hydrolysis Methods for Producing Cellulose Nanocrystals	21
2.7 Some Natural Dyes and Their Chemical Structure	26
2.8 Some Example of Dyes and Their Applications	27
2.9 The Advantages and Disadvantages on Different Dye Removal Methods	28
3.1 The Appearance of NCC Suspension Treated by Sulfuric Acid at Different Concentration	37
3.2 The Appearance of NCC Suspension after Pre-Fixed Contact Time	37
3.3 Effect of Temperature on the Appearance of NCC Suspension	38
3.4 Infrared Absorption Peaks ( $\text{cm}^{-1}$ ) of EFB at Different Stages	40
3.5 Chemical Composition of EFB at Various Stages of Chemical Treatment (ATSM Analysis)	43
3.6 Particle Size and Percentage Intensity of NCC	44
3.7 Thermal Analysis Values of EFB at Various Stages of Treatment	48
3.8 Crystallinity Index of the EFB at Different Stages of Treatment	49

4.1	Infrared Absorption Peaks ( $\text{cm}^{-1}$ ) of NCC before and after Adsorption	56
4.2	Kinetic Parameters for the Removal of MB from Aqueous Solution at 30°C	66
4.3	Feasibility of Langmuir Isotherm	67
4.4	Isotherm Parameters of MB Adsorption onto NCC	69
4.5	Comparison of Adsorption Capacities of Various Adsorbents for Methylene Blue	69



## LIST OF FIGURES

Figure		Page
2.1	Statistic on Oil Palm Plantation Area by Category	4
2.2	Oil Palm Wastes Generated During the Extraction	5
2.3	Intrachain and Interchain Hydrogen Bonded Bridging	7
2.4	Schematic Illustrations of Sugar Units for Hemicellulose	8
2.5	Schematic Illustration of Lignin	9
2.6	The Chemical Structure of Cellulose	10
2.7	The Formation of Cellulose Allomorphs	10
2.8	Isolation of Nanocrystalline Cellulose via Acid Hydrolysis	17
2.9	(a) Sulfuric Acid Hydrolysis Mechanism, (b) Esterification of NCC Surfaces	18
2.10	Schematic Diagram of Ultrasonication Process	20
2.11	Device Structure on NCC Substrate	22
2.12	Schematic Representation of MB Dye Formation	24
2.13	Classification of Dyes	25
2.14	Five types of isotherm	29
3.1	Outline of NCC Isolation from Empty Fruit Bunch (EFB)	33
3.2	Scheme of Cellulose Isolation from Empty Fruit Bunch (EFB)	34
3.3	Suspension at Various Acid Hydrolysis Conditions: (a) Black (45 wt%), (b) Brown (55 wt%), (c) Pale Brown (64 wt%), and (d) Pale Brown (64 wt%) After 5 Minutes of Settling Time	38
3.4	FTIR Spectra of EFB from Various Stages of Isolation: (a) Raw EFB upon Washing, (b) Alkali Treated Fibre, (c) Bleached Fibre and (d) NCC	41
3.5	TEM Images of Nanoscale Cellulose Crystalline Region.	42
3.6	Particle Size Distribution of NCC	44

3.7	Top) DTA and (Bottom) TGA Curves of EFB at Various Stages of Chemical Treatment	47
3.8	X-ray Diffractograms Patterns of EFB at Various Stages of Isolation	50
4.1	FTIR Spectra of NCC: (a) before and (b) after Dye Adsorption	56
4.2	FESEM Images of NCC (Top) before Adsorption and (Bottom) after Adsorption	57
4.3	Nitrogen Adsorption/Desorption Isotherms of NCC	58
4.4	The Percentage of MB Removal Relying on Adsorbent Dosage ( $C_0 = 50$ mg/L; $T = 30$ °C; $V = 150$ ml; pH 10 and RPM = 150)	59
4.5	The Adsorption of MB Affected by Solution pH ( $W = 0.01$ g; $C_0 = 50$ mg/L; $T = 30$ °C; $V = 150$ ml and RPM = 150)	60
4.6	The Speed of Agitation on MB Adsorption ( $W = 0.01$ g; $C_0 = 50$ mg/L; $T = 30$ °C; $V = 150$ ml; pH 10; $t = 60$ min)	61
4.7	The Initial Dye Concentration and Contact Time on MB Adsorption ( $W = 0.01$ g; pH 10; $T = 30$ °C; $V = 150$ ml and RPM = 150)	62
4.8	MB Adsorption described in Pseudo-first-order Kinetic Model	63
4.9	MB Adsorption described in Pseudo-second-order Kinetic Model	64
4.10	Intraparticle Diffusion Model with MB Initial Dye Concentration from 50 to 300 mg/L	65
4.11	Linearized Langmuir Adsorption Isotherm of MB on NCC	68
4.12	Linearized Freundlich Adsorption Isotherm of MB on NCC	68

## LIST OF ABBREVIATIONS

API	American Petroleum Institute
ASTM	American Society for Testing and Materials
BET	Brunauer-Emmett-Teller
BJH	Barrett-Joyner-Halenda
DLS	Dynamic Light Scattering
DTA	Differential Thermal Analysis
EFB	Empty fruit bunch
FESEM	Field Emission Scanning Electron Microscope
FTIR	Fourier Transform Infrared Spectrometer
GDP	Gross domestic product
HCl	Hydrochloric acid
ICr	Crystallinity Index
MB	Methylene blue
MF	Mesocarp fruit fibers
NaOH	Sodium hydroxide
NCC	Nanocrystalline cellulose
OPF	Oil palm fronds
OPT	Oil palm trunks
PCS	Photon Correlation Spectroscopy
PdI	Polydispersity Index
PKS	Palm kernel shell
POME	Palm oil mill effluent
PPF	Palm pressed fibers



RT	Room temperature
TGA	Thermogravimetric analysis
TEM	Transmission Electron Microscope
XRD	X-ray diffraction
Z-Avg	Z-Average



## CHAPTER 1

### INTRODUCTION

#### 1.1 Background

The growth of oil palm industry in Malaysia is phenomenal. Starting off as an ornamental plant, the crop has been developed into a multibillion ringgit industry. Basically, products from oil palm are being used widely in food industries, cosmetics, personal care, and pharmaceutical. However, with the increase in the demand globally, total wastage upon extraction also rises remarkably. Hence, a technique or ways need to be implemented in order to discard this wastage without affecting the environment (Mondragon et al., 2014).

Besides, environmental pollution has certainly been regarded as one of the most severe problem in developed and developing countries. One of the industries which produce the most high-polluting contaminants is the textile industry. Concerning their complex aromatic structure, dye poses significant threat to human health and aquatic life. Therefore, in relation to both the problems, effort to search for a more cost effective and environmental friendly solution need to be deliberated. Thus, attention has been shifted towards nanomaterials. Today, nanotechnology has a great potential to profoundly improve standard of living. The recent leaps in nanostructured materials encourage scientists and engineers to deliberately look for bio-based resources to make materials at nanoscale, leading a radical new approach in emerging green nanoparticle for quality improvement (Nanogov, 2016).

Cellulose in the form of nanocrystalline cellulose (NCC) gains notable attention among researchers. Not only the research activities had been increased remarkably in the past 10 years, the first pilot plant of nanocellulose owned by Innentia was launched in 2011, which has a capacity of 100 kg/day. Following that, CelluForce launched the world largest commercial-scale plant, with capacity to produce 300 tonnes of NCC per year (CelluForce, 2016). Engineers and researchers had continuously search for more cost-effective technology to obtain NCC from biomass. For instance, American Process Inc (API) and Blue Goose Biorefineries Inc. (Blue Goose) introduced BioPlus® Nanocellulose Fibrils & Crystals and R3™ technology, respectively, to preclude costly process from obtaining high quality NCC (American process, 2016 and Blue Goose Biorefineries Inc, 2016).

#### 1.2 Problem Statement

Palm oil industry has contributed significantly to Malaysia economy. However, lignocellulosic biomass specifically empty fruit bunch, which contributes 22% of total wastage from the palm oil extractions, has created a major disposal problem (Abdullah and Sulaiman, 2013). Therefore, this study attempts to convert empty fruit

bunch into a more valuable material which is in the form of nanocrystalline cellulose (NCC). Apart from that, methylene blue is one of the most common dyes used in adsorption related research. It is harmful to human, causing irritation to the gastrointestinal tract and eye burns. Adsorption has been proven to be an excellent method for removing dyes from aqueous solutions because of its significant advantages. Activated carbon is perhaps the most widely used adsorbent but it is prohibitively expensive. Therefore, enormous interest has been manifested in finding other suitable alternatives that are more economical and effective. This study aims to narrow this gap by isolating more environmentally friendly nano bio-material from agricultural solid wastes and a more effective alternative to treat dye from aqueous solution.

### 1.3 Research objectives

The objectives of the study are:

- To extract and characterize nanocrystalline cellulose from palm oil empty fruit bunch.
- To evaluate the adsorption performance of nanocrystalline cellulose for the removal of methylene blue from aqueous solution

### 1.4 Scope of research

The main objective of this study was to isolate nanostructured material in the form of NCC from agricultural solid wastes and to compare its removal efficiency of methylene blue from aqueous solution with other adsorbents. The NCC extracted from oil palm empty fruit bunch was characterized using FTIR, XRD, TGA, TEM and DLS. Only batch adsorption study was attempted. Ultraviolet-visible spectrophotometer was used to determine the removal rate of methylene blue. Several important parameters, i.e. pH, contact time and agitation speed were also investigated. The adsorption isotherms, i.e. Freundlich, and Langmuir were used to describe the interaction between adsorbent and adsorbate; and the adsorption kinetics was evaluated using pseudo-first order, pseudo-second order and intraparticle diffusion model.

### 1.5 Thesis outline

The dissertation begins with an introduction which comprised of background, aim, problem statement, research objectives and scope of the study (**Chapter 1**). Following that (**Chapter 2**), a short literature review was conducted on isolation of NCC and its potential in methylene blue removal. **Chapter 3** consists of a more comprehensive discussion on NCC isolation, as well as its characterization. **Chapter 4** discussed how NCC could be utilized to remove methylene blue from aqueous solution and short comparison study by using other adsorbents as a reference. The last, a short conclusion was drawn in **Chapter 5**, as well as future recommendation was included.

## REFERENCES

- Abdul Khalil, H., Bhat, A., & Ireana Yusra, A. (2012). Green composites from sustainable cellulose nanofibrils: A review. *Carbohydrate Polymers*, 87(2), 963-979.
- Abdallah, R. and Taha, S. (2012). Biosorption of methylene blue from aqueous solution by nonviable *Aspergillus fumigatus*. *Chemical Engineering Journal*, 195-196, pp.69-76.
- Abdullah, R., Ueda, K., & Saka, S. (2013). Decomposition behaviors of various crystalline celluloses as treated by semi-flow hot-compressed water. *Cellulose*, 20(5), 2321-2333.
- Abdullah, N. and Sulaim, F. (2013). *The Oil Palm Wastes in Malaysia*. [online] Available at: <http://www.intechopen.com/books/biomass-now-sustainable-growth-and-use/the-oil-palm-wastes-in-malaysia> [Accessed 5 Feb. 2016].
- Abraham, E., Deepa, B., Pothan, L., Jacob, M., Thomas, S., Cvelbar, U. and Anandjiwala, R. (2011). Extraction of nanocellulose fibrils from lignocellulosic fibres: A novel approach. *Carbohydrate Polymers*, 86(4), pp.1468-1475.
- Acharya, SK., Mishra, P. and Mehar, SK. (2011). Effect of surface treatment on the mechanical properties of bagasse fiber reinforced polymer composite. *Bioresources*, 6(3), 3155-65.
- Alves, L., Medronho, B., Antunes, F., Fernández-García, M., Ventura, J., Araújo, J., Romano, A. and Lindman, B. (2015). Unusual extraction and characterization of nanocrystalline cellulose from cellulose derivatives. *Journal of Molecular Liquids*, 210, pp.106-112.
- Batmaz, R., Mohammed, N., Zaman, M., Minhas, G., Berry, R. and Tam, K. (2014). Cellulose nanocrystals as promising adsorbents for the removal of cationic dyes. *Cellulose*, 21(3), pp.1655-1665.
- Boluk, Y. and Danumah, C. (2013). Analysis of cellulose nanocrystal rod lengths by dynamic light scattering and electron microscopy. *Journal of Nanoparticle Research*, 16(1).
- Brinchi, L., Cotana, F., Fortunati, E. and Kenny, J. (2013). Production of nanocrystalline cellulose from lignocellulosic biomass: Technology and applications. *Carbohydrate Polymers*, 94(1), pp.154-169.
- Brito, B., Pereira, F., Putaux, J. and Jean, B. (2012). Preparation, morphology and structure of cellulose nanocrystals from bamboo fibers. *Cellulose*, 19(5), pp.1527-1536.

- Chen, Y., Lee, H., Juan, J. and Phang, S. (2016). Production of new cellulose nanomaterial from red algae marine biomass *Gelidium elegans*. *Carbohydrate Polymers*, 151, pp.1210-1219.
- Chincholi, M., Sagwekar, P., Nagaria, C., Kulkarni, S., & Dhokpande, S. (2014). Removal of dye by adsorption on various adsorbents: A review. *International Journal of Science, Engineering and Technology Research*, 3(4).
- Coccia, V., Cotana, F., Cavalaglio, G., Gelosia, M. and Petrozzi, A. (2014). Cellulose Nanocrystals Obtained from *Cynara Cardunculus* and Their Application in the Paper Industry. *Sustainability*, 6(8), pp.5252-5264.
- Deng, H., Lu, J., Li, G., Zhang, G. and Wang, X. (2011). Adsorption of methylene blue on adsorbent materials produced from cotton stalk. *Chemical Engineering Journal*, 172(1), pp.326-334.
- Ditzel, F., Prestes, E., Carvalho, B., Demiate, I. and Pinheiro, L. (2017). Nanocrystalline cellulose extracted from pine wood and corncob. *Carbohydrate Polymers*, 157, pp.1577-1585.
- Duran, N., Paula Lemes, A. and B. Seabra, A. (2012). Review of Cellulose Nanocrystals Patents: Preparation, Composites and General Applications. *Recent Patents on Nanotechnology*, 6(1), pp.16-28.
- Flauzino Neto, W., Silvério, H., Dantas, N. and Pasquini, D. (2013). Extraction and characterization of cellulose nanocrystals from agro-industrial residue – Soy hulls. *Industrial Crops and Products*, 42, pp.480-488.
- Fortunati, E., Puglia, D., Monti, M., Peponi, L., Santulli, C., Kenny, J. and Torre, L. (2012). Extraction of Cellulose Nanocrystals from Phormium tenax Fibres. *Journal of Polymers and the Environment*, 21(2), pp.319-328.
- Gardner, D., Oporto, G., Mills, R., & Samir, M. (2008). Adhesion and Surface Issues in Cellulose and Nanocellulose. *Journal of Adhesion Science And Technology*, 22(5-6), 545-567.
- George, J. & S N, S. (2015). Cellulose nanocrystals: synthesis, functional properties, and applications. *Nanotechnology, Science and Applications*, 45.
- Gupta, V. & Suhas,. (2009). Application of low-cost adsorbents for dye removal – A review. *Journal of Environmental Management*, 90(8), 2313-2342.
- Habibi, Y., Lucia, L. and Rojas, O. (2010). Cellulose Nanocrystals: Chemistry, Self-Assembly, and Applications. *Chem. Rev.*, 110(6), pp.3479-3500.
- Hameed, B. and El-Khaiary, M. (2008). Sorption kinetics and isotherm studies of a cationic dye using agricultural waste: Broad bean peels. *Journal of Hazardous Materials*, 154(1-3), pp.639-648.

- Hameed, B. (2009). Evaluation of papaya seeds as a novel non-conventional low-cost adsorbent for removal of methylene blue. *Journal of Hazardous Materials*, 162(2-3), pp.939-944.
- Hameed, B. (2009). Spent tea leaves: A new non-conventional and low-cost adsorbent for removal of basic dye from aqueous solutions. *Journal of Hazardous Materials*, 161(2-3), pp.753-759.
- Hameed, B., Krishni, R. and Sata, S. (2009). A novel agricultural waste adsorbent for the removal of cationic dye from aqueous solutions. *Journal of Hazardous Materials*, 162(1), pp.305-311.
- History and Origin - The Oil Palm*. (2017). *The Oil Palm*. Retrieved 17 January 2017, from <http://theoilpalm.org/history-and-origin/>
- Hoon Yoon, S. (2016). *Classification of membranes according to pore size - OnlineMBR*. *OnlineMBR*. Retrieved 21 January 2017, from <http://onlinembr.info/membrane-process/classification-of-membranes-according-to-pore-size/>
- Huang, J., Cao, Y., Liu, Z., Deng, Z. and Wang, W. (2012). Application of titanate nanoflowers for dye removal: A comparative study with titanate nanotubes and nanowires. *Chemical Engineering Journal*, 191, pp.38-44.
- Jiang, F. and Hsieh, Y. (2013). Chemically and mechanically isolated nanocellulose and their self-assembled structures. *Carbohydrate Polymers*, 95(1), pp.32-40.
- Jiang, F. and Hsieh, Y. (2015). Cellulose nanocrystal isolation from tomato peels and assembled nanofibers. *Carbohydrate Polymers*, 122, pp.60-68.
- Johar, N., Ahmad, I. and Dufresne, A. (2012). Extraction, preparation and characterization of cellulose fibres and nanocrystals from rice husk. *Industrial Crops and Products*, 37(1), pp.93-99.
- Kallel, F., Bettaieb, F., Khiari, R., García, A., Bras, J. and Chaabouni, S. (2016). Isolation and structural characterization of cellulose nanocrystals extracted from garlic straw residues. *Industrial Crops and Products*, 87, pp.287-296.
- Kharub, M. (2012). Use of Various Technologies, Methods and Adsorbents for the Removal of Dye. *Journal of Environment Research and Development*, 6(3A).
- Konicki, W., Cendrowski, K., Chen, X. and Mijowska, E. (2013). Application of hollow mesoporous carbon nanospheres as an high effective adsorbent for the fast removal of acid dyes from aqueous solutions. *Chemical Engineering Journal*, 228, pp.824-833.



- Liao, P., Malik Ismael, Z., Zhang, W., Yuan, S., Tong, M., Wang, K. and Bao, J. (2012). Adsorption of dyes from aqueous solutions by microwave modified bamboo charcoal. *Chemical Engineering Journal*, 195-196, pp.339-346.
- Liu, Z., Li, X., Xie, W. and Deng, H. (2017). Extraction, isolation and characterization of nanocrystalline cellulose from industrial kelp (*Laminaria japonica*) waste. *Carbohydrate Polymers*, 173, pp.353-359.
- Lu, H., Gui, Y., Zheng, L. and Liu, X. (2013). Morphological, crystalline, thermal and physicochemical properties of cellulose nanocrystals obtained from sweet potato residue. *Food Research International*, 50(1), pp.121-128.
- Lu, P. and Hsieh, Y. (2010). Preparation and properties of cellulose nanocrystals: Rods, spheres, and network. *Carbohydrate Polymers*, 82(2), pp.329-336.
- Lu, P. and Hsieh, Y. (2012). Preparation and characterization of cellulose nanocrystals from rice straw. *Carbohydrate Polymers*, 87(1), pp.564-573.
- Lu, H., Gui, Y., Zheng, L. and Liu, X. (2013). Morphological, crystalline, thermal and physicochemical properties of cellulose nanocrystals obtained from sweet potato residue. *Food Research International*, 50(1), pp.121-128.
- Mahmoud, D., Salleh, M., Karim, W., Idris, A. and Abidin, Z. (2012). Batch adsorption of basic dye using acid treated kenaf fibre char: Equilibrium, kinetic and thermodynamic studies. *Chemical Engineering Journal*, 181-182, pp.449-457.
- Mendes, C., Ferreira, N., Furtado, C. and de Sousa, A. (2015). Isolation and characterization of nanocrystalline cellulose from corn husk. *Materials Letters*, 148, pp.26-29.
- Mondragon, G., Fernandes, S., Retegi, A., Peña, C., Algar, I., Eceiza, A. and Arbelaiz, A. (2014). A common strategy to extracting cellulose nanoentities from different plants. *Industrial Crops and Products*, 55, pp.140-148.
- Moon, R., Martini, A., Nairn, J., Simonsen, J., & Youngblood, J. (2011). Cellulose nanomaterials review: structure, properties and nanocomposites. *Chemical Society Reviews*, 40(7), 3941.
- Morais, J., Rosa, M., de Souza Filho, M., Nascimento, L., do Nascimento, D. and Cassales, A. (2013). Extraction and characterization of nanocellulose structures from raw cotton linter. *Carbohydrate Polymers*, 91(1), pp.229-235.
- National Biomass Strategy 2020: New wealth creation for Malaysia's biomass industry. (2013). 2nd ed. [ebook] Available at: <https://biobs.jrc.ec.europa.eu/sites/default/files/generated/files/policy/Biomass%20Strategy%202013.pdf> [Accessed 19 Feb. 2016].

- Nano.gov. (2016). *What is Nanotechnology? / Nano*. [online] Available at: <http://www.nano.gov/nanotech-101/what/definition> [Accessed 7 Apr. 2016].
- Ng, H., Sin, L., Tee, T., Bee, S., Hui, D., Low, C. and Rahmat, A. (2015). Extraction of cellulose nanocrystals from plant sources for application as reinforcing agent in polymers. *Composites Part B: Engineering*, 75, pp.176-200.
- Ogundare, S., Moodley, V. and van Zyl, W. (2017). Nanocrystalline cellulose isolated from discarded cigarette filters. *Carbohydrate Polymers*, 175, pp.273-281.
- Otieno, N., Dai, X., Barba, D., Bahman, A., Smedbol, E., Rajeb, M., & Jatón, L. (2016). Palm Oil Production in Malaysia: An Analytical Systems Model for Balancing Economic Prosperity, Forest Conservation and Social Welfare. *Agricultural Sciences*, 07(02), 55-69.
- Ozer, D., Dursun, G. and Ozer, A. (2007). Methylene blue adsorption from aqueous solution by dehydrated peanut hull. *Journal of Hazardous Materials*, 144(1-2), pp.171-179.
- Palm Oil - SCORE*. (2017). *Recoda.com.my*. Retrieved 17 January 2017, from <http://www.recoda.com.my/priority-sectors/palm-oil/>
- Prasad Reddy, J. and Rhim, J. (2014). Isolation and characterization of cellulose nanocrystals from garlic skin. *Materials Letters*, 129, pp.20-23.
- Rehman, N., de Miranda, M., Rosa, S., Pimentel, D., Nachtigall, S. and Bica, C. (2013). Cellulose and Nanocellulose from Maize Straw: An Insight on the Crystal Properties. *Journal of Polymers and the Environment*, 22(1), pp.252-259.
- Rhim, J., Reddy, J. and Luo, X. (2014). Isolation of cellulose nanocrystals from onion skin and their utilization for the preparation of agar-based bio-nanocomposites films. *Cellulose*, 22(1), pp.407-420.
- Rida, K., Bouraoui, S. and Hadnine, S. (2013). Adsorption of methylene blue from aqueous solution by kaolin and zeolite. *Applied Clay Science*, 83-84, pp.99-105.
- Rosa, M., Medeiros, E., Malmonge, J., Gregorski, K., Wood, D., Mattoso, L., Glenn, G., Orts, W. and Imam, S. (2010). Cellulose nanowhiskers from coconut husk fibers: Effect of preparation conditions on their thermal and morphological behavior. *Carbohydrate Polymers*, 81(1), pp.83-92.
- Salleh, M., Mahmoud, D., Karim, W., & Idris, A. (2011). Cationic and anionic dye adsorption by agricultural solid wastes: A comprehensive review. *Desalination*, 280(1-3), 1-13.



- Salam, A., Lucia, L. and Jameel, H. (2013). A Novel Cellulose Nanocrystals-Based Approach To Improve the Mechanical Properties of Recycled Paper. *ACS Sustainable Chem. Eng.*, 1(12), pp.1584-1592.
- Samiran, N., Mohd Jaafar, M., Tung Chong, C., & Jo-Han, N. (2015). A Review of Palm Oil Biomass as a Feedstock for Syngas Fuel Technology. *Jurnal Teknologi*, 72(5).
- Sen, T. (2013). Review on Dye Removal from Its Aqueous Solution into Alternative Cost Effective and Non-Conventional Adsorbents. *Journal of Chemical And Process Engineering*, 1:1-11.
- Sharma, M. and Yashonath, S. (2007). Correction to “Breakdown of Stokes–Einstein Relationship: Role of Interactions in the Size Dependence of Self-Diffusivity”. *The Journal of Physical Chemistry B*, 111(27), pp.7928-7928.
- Sheltami, R., Abdullah, I., Ahmad, I., Dufresne, A. and Kargarzadeh, H. (2012). Extraction of cellulose nanocrystals from mengkuang leaves (*Pandanus tectorius*). *Carbohydrate Polymers*, 88(2), pp.772-779.
- Silvério, H., Flauzino Neto, W., Dantas, N. and Pasquini, D. (2013). Extraction and characterization of cellulose nanocrystals from corncob for application as reinforcing agent in nanocomposites. *Industrial Crops and Products*, 44, pp.427-436.
- Siqueira, G., Bras, J., & Dufresne, A. (2010). Cellulosic Bionanocomposites: A Review of Preparation, Properties and Applications. *Polymers*, 2(4), 728-765.
- Slimani, R., El Ouahabi, I., Abidi, F., El Haddad, M., Regti, A., Laamari, M., Antri, S. and Lazar, S. (2014). Calcined eggshells as a new biosorbent to remove basic dye from aqueous solutions: Thermodynamics, kinetics, isotherms and error analysis. *Journal of the Taiwan Institute of Chemical Engineers*, 45(4), pp.1578-1587.
- Stelte, W. *Steam explosion for biomass pre-treatment*. Danish Technological Institute
- Structural Characteristics and Thermal Properties of Native Cellulose. (2013). In *Cellulose - Fundamental Aspects* (1st ed.). Retrieved from <http://www.intechopen.com/books/cellulose-fundamental-aspects/structural-characteristics-and-thermal-properties-of-native-cellulose>
- Sun, Y. & Cheng, J. (2002). Hydrolysis of lignocellulosic materials for ethanol production: a review. *Bioresource Technology*, 83(1), 1-11.

- Tanyildizi, M. (2011). Modeling of adsorption isotherms and kinetics of reactive dye from aqueous solution by peanut hull. *Chemical Engineering Journal*, 168(3), pp.1234-1240.
- Tsai, W., Yang, J., Lai, C., Cheng, Y., Lin, C. and Yeh, C. (2006). Characterization and adsorption properties of eggshells and eggshell membrane. *Bioresource Technology*, 97(3), pp.488-493.
- The Oil Palm Wastes in Malaysia. (2013). In *Biomass Now - Sustainable Growth and Use* (1st ed.). Retrieved from <http://www.intechopen.com/books/biomass-now-sustainable-growth-and-use/the-oil-palm-wastes-in-malaysia>
- The Oil Palm Tree*. (2017). Mpoc.org.my. Retrieved 17 January 2017, from [http://www.mpoc.org.my/The\\_Oil\\_Palm\\_Tree.aspx](http://www.mpoc.org.my/The_Oil_Palm_Tree.aspx)
- The Oil Palm Tree - Sustainable Malaysian Palm Oil*. (2017). *Palm Oil Health - Sustainable Malaysian Palm Oil*. Retrieved 17 January 2017, from <http://www.palmoilhealth.org/what-is-palm-oil/the-oil-palm-tree/>
- William Henry Perkin / Chemical Heritage Foundation. (2017). *Chemheritage.org*. Retrieved 21 January 2017, from <https://www.chemheritage.org/historical-profile/william-henry-perkin>
- Umoren, S., Etim, U. and Israel, A. (2013). Adsorption of methylene blue from industrial effluent using poly (vinyl alcohol). *Journal of Material Environmental Science*, 4(1), pp.75-86.
- Wang, Q., Zhu, J., Reiner, R., Verrill, S., Baxa, U. and McNeil, S. (2012). Approaching zero cellulose loss in cellulose nanocrystal (CNC) production: recovery and characterization of cellulosic solid residues (CSR) and CNC. *Cellulose*, 19(6), pp.2033-2047.
- Yagub, M., Sen, T., Afroze, S., & Ang, H. (2014). Dye and its removal from aqueous solution by adsorption: A review. *Advances in Colloid and Interface Science*, 209, 172-184.
- Zhang, Y., Su, P., Huang, J., Wang, Q. and Zhao, B. (2015). A magnetic nanomaterial modified with poly-lysine for efficient removal of anionic dyes from water. *Chemical Engineering Journal*, 262, pp.313-318.
- Zianor Azrina, Z., Beg, M., Rosli, M., Ramli, R., Junadi, N. and Alam, A. (2017). Spherical nanocrystalline cellulose (NCC) from oil palm empty fruit bunch pulp via ultrasound assisted hydrolysis. *Carbohydrate Polymers*, 162, pp.115-120.
- (2013). In *Biomass Now - Sustainable Growth and Use* (1st ed.). Retrieved from <http://www.intechopen.com/books/biomass-now-sustainable-growth-and-use/the-oil-palm-wastes-in-malaysia>