



UNIVERSITI PUTRA MALAYSIA

***DEVELOPMENT OF SUGAR PALM YARN AND WOVEN GLASS
FIBRE-REINFORCED UNSATURATED POLYESTER COMPOSITES***

MOHD NURAZZI BIN NORIZAN

FK 2018 88



**DEVELOPMENT OF SUGAR PALM YARN AND WOVEN GLASS
FIBRE-REINFORCED UNSATURATED POLYESTER COMPOSITES**

By

MOHD NURAZZI BIN NORIZAN

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,
in Fulfillment of the Requirements for the Degree of Doctor of Philosophy**

July 2018

COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs, and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Doctor of Philosophy

DEVELOPMENT OF SUGAR PALM YARN AND WOVEN GLASS FIBRE-REINFORCED UNSATURATED POLYESTER COMPOSITES

By

MOHD NURAZZI BIN NORIZAN

July 2018

Chairman : Associate Professor Khalina Abdan, PhD
Faculty : Engineering

This research was carried out to produce a composite material from sugar palm (*Arengga Pinnata*) yarn fibre as fibre reinforcement onto unsaturated polyester composites. Analysis of the curing characteristic of unsaturated polyester resin, the structural and morphological characteristics of sugar palm fibre, tensile strength of single sugar palm fibre and interfacial shear stress (IFSS) were studied. The gel time was decreased by up to 36% when 0.05% cobalt solution was used. Alkaline treatment using sodium hydroxide (NaOH) led to the enhancement of the single fibre tensile strength and the IFSS due to the internal morphological changes of the sugar palm fibres. The physical properties (water absorption, density and void content determination), mechanical properties (tensile, flexural, impact and compression), thermal (DMA and TGA) and morphological (SEM) properties of different sugar palm yarn fibre loadings from 10 to 50 wt.% composites was studied, followed by different orientations of fibres (45° and 90°) reinforced composites. From the experiment results, the percentage of water absorption increased as the sugar palm yarn fibre loading increased and reached the equilibrium of absorption on day 12. Increasing trends in the performance of tensile strength and flexural properties were shown for the yarn fibre loadings of up to 30 wt.%. However, a maximum impact strength and compression properties were achieved at 40 wt.% fibre loading. The thermal stability of the composites decreased as the fibre loading increased. The composites with 30 wt.% of fibre loading and 0° fibre orientation exhibited maximum tensile and flexural properties, respectively. While maximum impact and compression properties found at 40 wt.%, respectively. The experiment found the effect of treated sugar palm yarn fibre loading reinforced unsaturated polyester composites with 1% alkaline solutions decreased the physical, mechanical and thermal properties compared to the composites reinforced with untreated sugar palm yarn fibre. This is due to different interaction of single fibre and yarn fibre which affects the interfacial adhesion between the fibre with the matrix. The final 30 wt.% and 40 wt.% of fibres as reinforcement were chosen for

the hybridisation studies. Then, the ratio of reinforcement between the sugar palm yarn fibre and woven glass fibre was selected at 70/30, 60/40 and 50/50 wt.%, respectively, which equal to the volume of the mould. The physical, mechanical and thermal properties of the treated sugar palm yarn fibre hybrid composites were found to increase as the glass fibre loading increased up to 50/50 wt.% of fibre ratio for both 30 wt.% and 40 wt.% of fibre loadings. This is due to better interfacial bonding and better chemical interaction between the sugar palm fibre, glass fibre and unsaturated polyester resin as matrix. The improvement on the mechanical and thermal properties also contributed by the synergistic effect from the addition of glass fibre loadings. Hence, the study findings will pave the way towards a greater usage of sugar yarn fibre as a reinforcement for the structural applications such as anti-roll bar in automotive industry, bicycle frame and furniture.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

PEMBANGUNAN KOMPOSIT POLIESTER TAK TEPU BERTETULANG GENTIAN SERABUT ENAU DAN KACA TENUNAN

Oleh

MOHD NURAZZI BIN NORIZAN

Julai 2018

Pengerusi : Profesor Madya Khalina Abdan, PhD
Fakulti : Kejuruteraan

Penyelidikan ini dijalankan untuk menghasilkan bahan komposit daripada gentian serabut enau (*Arengga Pinnata*) sebagai tetulang gentian kepada komposit poliester tak tepu. Analisis ciri-ciri pengerasan resin poliester tak tepu, ciri-ciri struktur dan morfologi gentian enau, kekuatan tegangan serat enau, dan tegasan ricih antara muka (IFSS) telah dikaji. Tempoh pengegelan telah berkurang sehingga 36% apabila larutan kobalt 0.05% digunakan. Rawatan alkali dengan menggunakan natrium hidroksida (NaOH) telah membawa kepada peningkatan kekuatan tegangan serat dan IFSS yang disebabkan oleh perubahan morfologi dalaman gentian enau. Sifat-sifat fizikal (penyerapan air, ketumpatan, penentuan kandungan lowong), sifat-sifat mekanikal (kekuatan tegangan, lenturan, hentaman dan mampatan), sifat-sifat terma (DMA dan TGA) dan sifat-sifat morfologi (SEM) pada gentian serabut enau yang berbeza muatan daripada 10 hingga 50 peratusan berat (% berat) komposit telah dikaji, diikuti dengan orientasi komposit bertetulang gentian yang berbeza (45° dan 90°). Daripada hasil eksperimen, peratusan penyerapan air meningkat apabila muatan gentian serabut enau meningkat dan mencapai keseimbangan penyerapan pada hari ke-12. Peningkatan trend dalam prestasi kekuatan tegangan dan sifat lenturan telah dicerap bagi muatan gentian serabut sehingga 30 % berat. Namun, kekuatan hentaman dan mampatan yang maksimum telah dicapai pada muatan gentian 40 % berat. Kestabilan terma komposit telah berkurang apabila muatan gentian meningkat. Komposit dengan muatan gentian sebanyak 30 % berat dan orientasi gentian 0° telah menunjukkan sifat tegangan dan lenturan yang maksimum. Manakala kekuatan hentaman dan mampatan yang maksimum didapati berada pada 40 % berat. Eksperimen mendapati kesan rawatan komposit poliester tak tepu bertetulang gentian muatan serabut enau dengan 1% larutan beralkali mengurangkan sifat-sifat fizikal, mekanikal dan terma berbanding komposit yang bertetulang gentian serabut enau tak terawat. Ini adalah disebabkan perbezaan interaksi oleh gentian tunggal dan tetulang gentian dimana memberi kesan terhadap tegasan ricih antara muka di antara gentian dan matriks. Peratusan berat yang

terakhir sebanyak 30 % berat dan 40 % berat telah dipilih untuk kajian penghibridan. Nisbah tetulang antara gentian enau dan gentian kaca tenunan yang dipilih adalah 70/30, 60/40 dan 50/50 % berat, yang bersamaan dengan isipadu acuan pembentuk. Sifat-sifat fizikal, mekanikal dan terma komposit hibrid gentian enau terawat telah didapati meningkat apabila muatan gentian kaca ditingkatkan sehingga 50/50 % berat daripada nisbah gentian untuk kedua-dua muatan gentian sebanyak 30 % berat dan 40 % berat. Ini disebabkan pengikatan antara muka dan saling tindak balas kimia yang lebih baik antara gentian enau, gentian kaca, dan resin poliester tak tepu yang bertindak sebagai matriks. Penambahbaikan sifat-sifat mekanikal dan terma juga disumbangkan oleh kesan bersinergi daripada penambahan muatan gentian kaca. Oleh itu, hasil kajian akan dapat membuka jalan ke arah penggunaan gentian enau yang lebih meluas sebagai tetulang untuk aplikasi struktur sebagai contoh kit bar antigelong didalam industri automotif, kerangka basikal dan juga perabot.

ACKNOWLEDGEMENTS

Bismillahirrohmanirrohim

“Bring me blocks of iron.” At length, when he had filled up the space between the two steep mountain-sides, He said, “Blow (with your bellows)” Then, when he had made it (red) as fire, he said; “Bring me, that I may pour over it, molten lead. Thus were they made powerless to scale it or to dig through it.” (AlKahf:18:96-97)

This thesis dedicated for my mother, Mariyam,
For your patience and spirit.

My beloved wife, Nadzirah,
For your love and kindness.

My little sister, Aisyah,
For your sincere helps.

All my supervisors, especially Assoc. Prof. Dr. Khalina Abdan
and Assoc. Prof. Dr. Rahmah Mohamed,
Who has been a constant source of knowledge and inspiration.

My entire family,

My friends especially Dr Siti Hasnah Kamarudin for our friendship,

UPM and UITM staffs.

I certify that a Thesis Examination Committee has met on 17 July 2018 to conduct the final examination of Mohd Nurazzi bin Norizan on his thesis entitled "Development of Sugar Palm Yarn and Woven Glass Fibre-Reinforced Unsaturated Polyester Composites" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

Nor Azowa bt Ibrahim, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Edi Syams bin Zainudin, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Mohamad Ridzwan bin Ishak, PhD

Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Faiz Mohammad, PhD

Professor
Aligarh Muslim University
India
(External Examiner)



RUSLI HAJI ABDULLAH, PhD

Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 27 September 2018

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Khalina Abdan, PhD

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Sapuan Salit, PhD

Professor, Ir.
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Dayang Laila Abang Haji Abdul Majid, PhD

Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Rahmah Mohamed, PhD

Associate Professor
Faculty of Applied Sciences
Universiti Teknologi MARA (UiTM)
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software

Signature: _____

Date: _____

Name and Matric No: Mohd Nurazzi Bin Norizan, GS43732

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) were adhered to.

Signature: _____
Name of Chairman
of Supervisory
Committee: Associate Professor Dr. Khalina Abdan

Signature: _____
Name of Member
of Supervisory
Committee: Professor Ir. Dr. Sapuan Salit

Signature: _____
Name of Member
of Supervisory
Committee: Dr. Dayang Laila Abang Haji Abdul Majid

Signature: _____
Name of Member
of Supervisory
Committee: Associate Professor Dr. Rahmah Mohamed

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	iii
ACKNOWLEDGEMENTS	v
APPROVAL	vi
DECLARATION	viii
LIST OF TABLES	xiii
LIST OF FIGURES	xv
LIST OF ABBREVIATIONS	xx
LIST OF UNITS	xxii
 CHAPTER	
1 INTRODUCTION	1
1.1 Overview	1
1.2 Problem statement	2
1.3 Significance of Study	3
1.4 Objectives	4
1.5 Scope and limitations	4
1.6 Thesis outline	4
 2 LITERATURE REVIEW	 6
2.1 Matrix	6
2.2 Unsaturated polyester resin	7
2.3 Natural fibres	9
2.4 The structure of natural fibres	12
2.5 Challenges of natural fibres	17
2.6 Sugar palm fibre	20
2.7 Modification of natural fibres	24
2.8 Physical treatment	24
2.9 Chemical treatment	27
2.10 Sugar palm fibre reinforced thermosetting polymer composites from 2008 to 2017	29
2.11 Sugar palm fibre reinforced unsaturated polyester composites	29
2.12 Sugar palm fibre reinforced epoxy composites	31
2.13 Sugar palm fibre reinforced phenolic composites	32
2.14 Hybrid composites	36
2.15 Hybridisation of sugar palm fibre reinforced composites from 2010 to 2017	37
 3 RESEARCH METHODOLOGY	 42
3.1 Materials	45
3.2 Treatment of sugar palm fibre	45
3.3 Yarning process of sugar palm fibre	45
3.4 Analysis of unsaturated polyester resin and sugar palm fibre	47

3.4.1	Curing characteristics of unsaturated polyester resin	47
3.4.2	Determination of the glass transition temperature of unsaturated polyester resin	47
3.4.3	Chemical compositions analysis	48
3.4.4	FTIR analysis of sugar palm fibre	48
3.4.5	Morphological analysis of sugar palm fibre	48
3.4.6	Single fibre tensile test	48
3.4.7	Microdroplet test for single sugar palm fibre	49
3.5	Fabrication of composites	50
3.6	Physical testing	54
3.6.1	Water absorption determination	54
3.6.2	Density and void determination	54
3.7	Mechanical testing	55
3.7.1	Tensile test	55
3.7.2	Flexural test	56
3.7.3	Impact test	56
3.7.4	Compression test	56
3.8	Thermal testing	56
3.8.1	Dynamic mechanical analysis	56
3.8.2	Thermogravimetric analysis	57
3.9	Morphological testing	57
4	RESULTS AND DISCUSSION	58
4.1	Analysis of unsaturated polyester resin and a single sugar palm fibre	58
4.1.1	Gel time and curing time analysis of unsaturated polyester resin	58
4.1.2	Glass transition and exothermic reaction of unsaturated polyester resin	59
4.1.3	Chemical compositions analysis of sugar palm fibre	62
4.1.4	FTIR and morphological analysis of sugar palm fibre	62
4.1.5	Tensile properties of single sugar palm fibre	65
4.1.6	Interfacial shear stress of single sugar palm fibre embedded with unsaturated polyester resin	66
4.2	Characterisations of untreated sugar palm yarn fibre reinforced unsaturated polyester resin on the physical, mechanical and thermal properties	67
4.2.1	Water absorption properties	67
4.2.2	Density and void content	68
4.2.3	Tensile properties	69
4.2.4	Flexural properties	73
4.2.5	Impact properties	74
4.2.6	Compression properties	76
4.2.7	Dynamic mechanical analysis properties	77
4.2.8	Thermogravimetric analysis properties	80
4.2.9	Mechanical and thermal characterisations of the effect of different orientations of sugar palm yarn fibre reinforced unsaturated polyester composites	82

4.3	Effect of alkaline treatment on the physical, mechanical, thermal and morphological properties of treated sugar palm yarn fibre reinforced unsaturated polyester composites	89
4.3.1	Water absorption properties	89
4.3.2	Density and void content	91
4.3.3	Tensile properties	91
4.3.4	Flexural properties	94
4.3.5	Impact properties	96
4.3.6	Compression properties	97
4.3.7	Dynamic mechanical analysis properties	98
4.3.8	Thermogravimetric analysis properties	100
4.3.9	Morphological analysis between untreated and treated fibre composites	101
4.3.10	Effect of alkaline treatment	104
4.4	Effect of hybridisation and alkaline treatment of sugar palm yarn fibre/woven glass fibre reinforced unsaturated polyester composites on the physical, mechanical, thermal and morphological properties	106
4.4.1	Water absorption properties	106
4.4.2	Density and void content	108
4.4.3	Tensile properties	109
4.4.4	Flexural properties	114
4.4.5	Impact properties	116
4.4.6	Compression properties	118
4.4.7	Dynamic mechanical analysis properties	119
4.4.8	Thermogravimetric analysis properties	122
4.4.9	Morphological analysis between untreated and treated sugar palm fibre hybrid composites	124
5	CONCLUSIONS AND RECOMMENDATIONS	129
5.1	Conclusions	129
5.2	Recommendations for future research	130
	REFERENCES	131
	APPENDICES	151
	BIODATA OF STUDENT	160
	LIST OF PUBLICATIONS	161

LIST OF TABLES

Table	Page
2.1 Mechanical properties of thermosetting resins	6
2.2 Price of cobalt that commonly used in unsaturated polyester and coatings from SIGMA ALDRICH	8
2.3 Physical and mechanical properties of selected natural fibres and synthetic fibres	17
2.4 Tensile, physical and chemical properties of sugar palm frond, sugar palm bunch, sugar palm trunk and ijuk	22
2.5 Tensile properties and toughness of sugar palm fibre obtained from different heights of sugar palm tree	23
2.6 Chemical composition of sugar palm fibre obtained from different heights of sugar palm tree	23
2.7 Summary of research into the sugar palm fibre reinforced thermosetting composites from 2008 to 2017	34
2.8 Summary of hybrid sugar palm fibre reinforced thermosetting composites from 2010 to 2017	40
3.1 Formulation of composites for untreated and treated sugar palm yarn fibres	51
3.2 Examples of calculation for 30 wt.% of untreated sugar palm yarn fibre in composites	52
3.3 Formulation of hybrid composites between matrix, sugar palm yarn fibre and woven glass fibre	53
3.4 Examples of calculation for 60/40 wt.% ratio between matrix and reinforcement and 50/50 wt.% ratio of reinforcement between the untreated sugar palm yarn fibre and woven glass fibre	53
4.1 Effect of total curing time (min) on Tg with different percentages of cobalt	60
4.2 Chemical compositions of untreated and treated sugar palm fibre	62
4.3 Comparison of tensile properties of untreated and 1% treated sugar palm with other fibres	65

4.4	Variation of density of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites	69
4.5	Characteristic temperature at elevated weight loss	82
4.6	Variation of density of treated sugar palm yarn fibre loading reinforced unsaturated polyester composites	91
4.7	Characteristic temperature at elevated weight loss	100
4.8	Variation of density of treated sugar palm yarn fibre hybrid composites	109
4.9	Comparison of tensile modulus from experimental values and theoretical values from the rules of mixture (ROM) for hybrid composites	114
4.10	The characteristic temperatures of the thermal properties of untreated and treated sugar palm hybrid composites	123

LIST OF FIGURES

Figure	Page
2.1 Chemical structure of unsaturated polyester	7
2.2 Utilisation of natural fibre reinforced composites for the automotive industry in Germany and Austria 1996 to 2002	10
2.3 (a) Natural fibre reinforced composites in automotive applications and (b) inner door made of kenaf reinforced PP composites	10
2.4 (a) NFC in Mercedes-Benz A-Class, (b) NFC in Mercedes-Benz C-Class, (c) Eco Elise with interior parts, (d) Toyota RAUM spare tire cover and (e) Mitsubishi i-MiEV door panel	11
2.5 Use of natural fibre reinforced plastic composites in 2002	12
2.6 Classification between natural (cellulose/plants, animals and minerals) and synthetic fibres	13
2.7 Schematic structure of the main constituents of natural fibres	14
2.8 Schematic structure of (a) cellulose , (b) hemicellulose and (c) ligni	15
2.9 Factors contributing to the diverse properties of natural fibre	16
2.10 Cellulose structure	18
2.11 Factors influencing the performance of composites	19
2.12 (a) Sugar palm tree , (b) palm sugar and (c) collected sugar palm fibre	21
2.13 (a) Simple ply yarn, (b) double ply yarn, (c) three ply yarn, (d) four ply yarn and (e) simple cord yarn	25
2.14 (a) Combing the natural fibres using fixed metal spike and (b) drafting process using a series of rollers	26
2.15 Difference between carded and combed yarn	26
2.16 Schematic mechanism of the untreated and treated natural fibre using alkaline treatment	27
2.17 Mechanism of hybridisation components of natural fibres, synthetic fibres and a polymer matrix	37
2.18 Mini boat made from hybrid sugar palm fibre with glass fibre reinforced unsaturated polyester composites	41

3.1	Flow chart of process	44
3.2	Alkaline treatment for sugar palm fibre: (a) preparation of 1% of NaOH concentration and (b) soaking for 1 hour	45
3.3	(a) A bundle of sugar palm, (b) a bundle of sugar palm fibre after combing, (c) yarning process and (d) sugar palm yarn fibre with 2500 tex	46
3.4	(a) Gel timer machine and (b) unsaturated polyester resin starts to gel after a certain processing time	47
3.5	(a) Schematic specimen for single fibre test mounted on cardboard and (b) measured under microscope	49
3.6	(a) Schematic of micro droplet test and (b) current studies of unsaturated polyester microdroplets adhered to a single fibre under the microscope	50
3.7	Composites with different fibre orientations	51
3.8	Sequence of fibres between layers for hybridisation	54
4.1	Effect of gel time and total curing time of the unsaturated polyester	59
4.2	Glass transition analysis with different percentages of cobalt	60
4.3	Structure for (a) raw unsaturated polyester resin and (b) cured unsaturated polyester resin	61
4.4	FTIR spectra of untreated and treated sugar palm fibre	63
4.5	(a) Surface morphology of untreated and (b) treated single sugar palm fibre	64
4.6	IFSS of untreated and treated of sugar palm fibre	66
4.7	Effect of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composite on water absorption	68
4.8	Effect of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites on tensile properties	70
4.9	Comparison of tensile modulus from experimental values and theoretical values from rules of mixture (ROM)	72
4.10	Effect of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites on flexural properties	74

4.11	Effect of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites on impact strength	75
4.12	Effect of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites on compression properties	76
4.13	Storage modulus for 30 wt.% and 40 wt.% of sugar palm yarn fibre loading reinforced unsaturated polyester composites	78
4.14	Tan δ for 30 wt.% and 40 wt.% of sugar yarn fibre loading reinforced unsaturated polyester composites	79
4.15	Effect of untreated sugar palm fibre reinforced unsaturated polyester composites on thermal properties: (a) TGA curve and (b) DTG curve	81
4.16	Tensile properties of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites at 0°, 45° and 90° fibre orientation	84
4.17	Flexural properties of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites at 0°, 45° and 90° fibre orientation	85
4.18	(a) Schematic diagram of flexural test and (b) the mechanism of 0°, (c) 45° and (d) 90° orientation during force applied	86
4.19	Impact properties of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites at 0°, 45° and 90° fibre orientation	87
4.20	Compression properties of untreated sugar palm yarn fibre loading reinforced unsaturated polyester composites at 0°, 45° and 90° fibre orientation	88
4.21	Variation of storage modulus for 30 wt.% and 40 wt.% of sugar palm yarn fibre loading with different fibre orientations of reinforced unsaturated polyester composites	88
4.22	Variation of tan δ for 30 wt.% and 40 wt.% of sugar palm yarn fibre loading with different fibre orientations of reinforced unsaturated polyester composites	89
4.23	Effect of treated sugar palm yarn fibre loading reinforced unsaturated polyester composites on water absorption	90
4.24	Tensile properties of untreated and treated sugar palm yarn fibre loading reinforced unsaturated polyester composites	92
4.25	Comparison of tensile modulus from the experimental values and the theoretical values from the rules of mixture (ROM)	94

4.26	Flexural strength of untreated and treated sugar palm yarn fibre reinforced unsaturated polyester composites	95
4.27	Flexural modulus of untreated and treated sugar palm yarn fibre reinforced unsaturated polyester composites	95
4.28	Impact properties of untreated and treated sugar palm yarn fibre reinforced unsaturated polyester composites	96
4.29	Compressive strength properties of untreated and treated sugar palm yarn fibre reinforced unsaturated polyester composites	98
4.30	Compressive modulus properties of untreated and treated sugar palm yarn fibre reinforced unsaturated polyester composites	98
4.31	Storage modulus for untreated and treated sugar palm yarn fibre with 30 wt.% and 40 wt.% reinforced unsaturated polyester composites	99
4.32	Tan δ for untreated and treated sugar palm yarn fibre with 30 wt.% and 40 wt.% reinforced unsaturated polyester composites	99
4.33	EM image of tensile fracture surface of untreated fibre with (a) 10 wt.% (b) 20 wt.% (c) 30 wt.% (d) 40 wt.% and (e) 50 wt.% of sugar palm yarn fibre reinforced unsaturated polyester composites	102
4.34	SEM image of tensile fracture surface of treated fibre with (a) 10 wt.% (b) 20 wt.% (c) 30 wt.% (d) 40 wt.% and (e) 50 wt.% of sugar palm yarn fibre reinforced unsaturated polyester composite	103
4.35	Schematic proposed mechanism between untreated sugar palm fibre and (b) treated sugar palm fibre with unsaturated polyester resin	105
4.36	Water absorption of untreated sugar palm yarn fibre hybrid composites	107
4.37	Water absorption of treated sugar palm yarn fibre hybrid composites	107
4.38	Tensile properties of untreated and treated sugar palm yarn fibre hybrid composites	111
4.39	Layup segmentation of hybrid composites	113
4.40	Flexural properties of untreated and treated sugar palm yarn fibre hybrid composites	115
4.41	Segmentation of sugar palm yarn and glass fibres	115
4.42	Impact strength of untreated and treated sugar palm yarn fibre hybrid composites	117

4.43	Compression properties of untreated and treated sugar palm yarn fibre hybrid composites	118
4.44	Buckling effect during the compression test	119
4.45	Storage modulus of (a) untreated and (b) treated sugar palm yarn fibre hybrid composites	120
4.46	Tan δ of (a) untreated and (b) treated sugar palm yarn fibre hybrid composites	122
4.47	SEM image of tensile fracture surface of untreated 30 wt.% of fibre reinforced composites : (a) 70/30, (b) 60/40 and (c) 50/50 and untreated 40 wt.% of sugar palm yarn fibre hybrid composites: (d) 70/30, (e) 60/40 (e) and (f) 50/50	126
4.48	SEM image of tensile fracture surface of treated 30 wt.% of fibre reinforced composites : (a) 70/30, (b) 60/40 and (c) 50/50 and treated 40 wt.% of sugar palm yarn fibre hybrid composites: (d) 70/30, (e) 60/40 and (f) 50/50	127

LIST OF ABBREVIATIONS

ASTM	American Society for Testing and Materials
CBS	Cassava bagasse
CO ₂	Carbon dioxide
CS	Cassava starch
DMA	Dynamic mechanical analysis
DSC	Differential scanning calorimetry
DTG	Derivative thermogravimetric
E*	Complex modulus
E'	Storage modulus
E''	Loss modulus
EU	European union
FRP	Fibre reinforced polymer
FTIR	Fourier transform infrared
H ₂ O	Water
IR	Infrared
IFSS	Interfacial shear stress
KBr	Potassium bromide
LDPE	Low density polyethylene
MEKP	Methyl ethyl ketone peroxide
NaOH	Sodium hydroxide
NFC	Natural fibre reinforced composites
OH	Hydroxyl group
PE	Polyethylene

pc	Piece
POM	Polarize optical microscope
PP	Polypropylene
PS	Polystyrene
PU	Polyurethane
PVC	Polyvinylchloride
RTM	Resin transfer moulding
SEM	Scanning electron microscopy
SPF	Sugar palm fibre
Tan δ	Tan delta
TDI	Toluene diisocyanate
Tg	Glass transition temperature
TGA	Thermogravimetric analysis
vol	Volume
vol. %	Volume percent
wt. %	Weight percent
WVP	Water vapor permeability

LIST OF UNITS

°C	Degree celcius
°C/min	Degree celcius per minute
°	Degree
GPa	Gigapascal
gsm	gram square meter
tex	gram per 1000 meters
g/cm ³	gram per cubic centimeter
J/g	Joule per gram
J/m	Joule per meter
kJ	kilo Joule
kN	kilo Newtons
Kg/m ³	Kilogram per cubic meter
kJ/m ²	kilojoule per square meter
MPa	Megapascal
MPa√m	Megapascal square root meter
ms ⁻¹	meter per second
μm	micrometer
mm	millimeter
ml/min	milliliter per minute
min	minute
M	Molar
%	Percentage
cm ⁻¹	per centimeter
rpm	rotation per minute

CHAPTER 1

INTRODUCTION

1.1 Overview

A composite is the combination of two or more elements in any form and for a variety of uses. The concept of composite materials is based on combining different materials for a new material with superior performance beyond that exhibited by their individual constituents. As a result, their high strength-to-weight and high stiffness-to-weight ratios can be tailored towards specific applications. Applications for composite materials have grown steadily throughout the years, penetrating and conquering newer markets.

Modern established composite materials constitute a significant proportion of these engineered material markets, ranging from daily products to sophisticated niche applications. These advanced materials see use in construction, military, automotive and aerospace industries. Their technologies are especially attractive due to their advantages over legacy materials such as metal, as composites offer high specific strength, low density, light weight, enhanced corrosion and temperature capability. An added advantage would be their biodegradability (Ishak *et al.*, 2013; Nair *et al.*, 1996).

In recent years, natural fibres have attracted interest for the reinforcement of polymer composites in low-cost engineering materials. The use of natural fibres as a potential replacement for synthetic fibres such as glass and carbon fibres in composites materials has intensified research recently due to environmental and economic factors. The primary advantages of natural fibres over synthetic fibres include abundance and relatively low cost, low mass and specific density, high specific strength and renewability and biodegradability (Mohanty *et al.*, 2002). In the meantime, the present use of the term 'biodegradable' in natural fibre composites actually refers to the utilization of natural sources in the polymer industry, which could reduce dependence on petroleum resources and decrease industrial carbon dioxide (CO₂) emissions (Sahari *et al.*, 2013a).

Natural fibres, when compared to synthetic fibres, generally have lower mechanical properties. These low mechanical properties are a major inhibitory when trying to develop high performance products. A few methods for increasing mechanical performance is to modify the interfacial adhesion, chemical structure of natural fibres and hybridise the natural fibres with synthetic fibres. One benefit of hybridisation is that the advantage of one type of fibre can overcome the disadvantages of the other one type of fibre.

A viable compromise between the higher material properties of synthetic fibres and the environmental benefits of natural fibres is found by utilizing both synthetic and natural fibres to create a hybrid fibre reinforced composite system. Material properties are also improved by the efficient arrangement of the structural numbers. The use of hybrid natural and synthetic fibre reinforced composites for structural applications has been shown to be feasible alternative to traditional synthetic structural materials. (Musch, 2008). As a result, a balance in cost, performance and sustainability may be reached through a proper composite material design.

Natural fibre composites are essentially a plant fibre embedded within a thermoplastic or thermoset polymer. The density of these natural fibres is similar as their plastic counterparts, which are usually 40 to 50% lower than the density of glass fibre (Rajan and Curtin, 2015; Saba *et al.*, 2014). Therefore, polymeric materials could be reinforced or filled without having significant effects on their density. Several types of natural fibres, such as kenaf fibre, oil palm fibre, sugar palm fibre, pineapple leaf fibre, banana fibre, flax, hemp, sisal, coir and jute fibre, have attracted the attention of scientists and technologists for their widespread applications.

These fibres are used to reinforce thermoplastic polymer matrices such as polystyrene (PS), polypropylene (PP), polyethylene (PE), polyvinyl chloride (PVC), polyurethane (PU) and so on. Phenolic, unsaturated polyester, vinyl ester and epoxy resin are for thermosetting polymer matrices.

1.2 Problem statement

Unsaturated polyester resins are an important class of high-performance engineering polymers used in numerous structural applications, primarily compression moulding (sheet moulding compounds), injection moulding (bulk moulding compounds), resin transfer moulding (RTM), pultrusion, filament winding and hand lay-up process (Vilas *et al.*, 2001). To produce unsaturated polyester composite product, the determination of gel and curing time is a very important stage in the processing of unsaturated polyester resins, as in order to achieve a good quality of product, the curing reaction should occur in a controllable way (Jansen and Kraeger 2018). This is especially vital when using RTM or another complex shape is to be produced, as resin must be in working fluidic flow and unwanted fast cure must be observed in the equipment. Other than that, it is also important to take precautionary steps, especially in the estimation of mixing time, from the start of the initial mix until the resin is fully injected into the mould. These crucial steps include determining the right formulation mix of initiator and accelerator required to optimize the time needed before the resin starts to gel and harden within the required time.

Furthermore, since the structural performance of natural fibre reinforced composites is dependent on the performance of fibres itself to maximize the efficiencies of stress transfer mechanism from the matrix to the fibres. The challenge of raw sugar palm

fibres is that it is randomly wrapped along with palm leaf ribs. If directly used, this may affect interaction with the chain of the matrix of composites. The tangling nature of sugar palm fibre itself becoming harder to be ignored. When the long fibres are in a tangling form, the possibility of the fibres to become randomly oriented is high especially after the infusion of resin into the mould and during the lay-up process. According to Miao and Shan (2011), short and randomly oriented fibre reinforced composite structures possess much lower mechanical properties than those made with oriented structures. Therefore, they are not suitable for use in structural applications in which mechanical performance is of primary importance.

Composite materials using natural fibres which are environmentally friendly, biodegradable, reasonably strong, lightweight, hazard-free and abundant have potential for use in reinforcement materials. Despite the advantages listed, the main limitation of natural fibres, their hydrophilicity properties, potentially leads to deterioration of the physical, mechanical and thermal properties of the composites due to worst in the interfacial adhesion of natural fibres with the hydrophobic nature of synthetic fibres and matrix. Hydrophilic properties are a major drawback in terms of incompatibility between synthetic fibres and polymer matrices, which are hydrophobic in nature. Incompatibility will substantially affect the efficiency of applied stress between matrix and fibres.

Synthetic fibres like glass, aramid and carbon fibre are widely used as reinforcement fibres in composites, which have been proven to be a good mechanical strength enhancer. The desired tensile strengths and modulus of glass fibres are visibly much higher than natural fibres. The disadvantages of synthetic fibre are that without proper handling, it may cause skin irritation, causing it to be dangerous to human health, and its lack of biodegradability (Van de Velde and Kiekens, 2001). However, differences in the characteristics of glass and natural fibres are important when their applications and costs are taken into account (Bledzki and Gassan, 1999). Synthetic and natural fibres have been used in reinforcing polymers in such a way that fibres with a promising strength and matrix will convey the applied stress to the fibre structures. This combination is called hybridisation of composite materials, which refers to two materials with different properties being combined to produce new materials with novel properties.

1.3 Significance of Study

- 1- Development of novel composites from sugar palm yarn fibre.
- 2- A novel study on the interaction of untreated and treated sugar palm yarn fibre reinforced unsaturated polyester composites.
- 3- A novel study on the interaction of the hybridisation mechanism involved with sugar palm yarn fibre with woven glass fibre reinforced unsaturated polyester composites.

1.4 Objectives

The specific objectives of this research are:

- 1- To determine the curing characteristic of unsaturated polyester resin, chemical compositions and structural changes of untreated and treated sugar palm fibre, single fibre tensile and interfacial shear stress properties of untreated and treated single sugar palm fibre properties.
- 2- To determine the effects of sugar palm yarn fibre loading reinforced unsaturated polyester composites on its physical, mechanical, thermal, and morphological properties with different fibre orientations (0°, 45° and 90°).
- 3- To determine the effects of alkaline treatment of sugar palm yarn fibre reinforced unsaturated polyester composites on its physical, mechanical, thermal, and morphological properties.
- 4- To determine the effects of hybridisation of sugar palm yarn/woven glass fibres reinforced unsaturated polyester composites on its physical, mechanical, thermal, and morphological properties.

1.5 Scope and limitations

The fibre used is sugar palm fibre purchased from Hafiz Adha Enterprise at Kampung Kuala Jempol, Negeri Sembilan, and the thermosetting polymer used is unsaturated polyester resin purchased from CCP Composites Resins Malaysia Sdn. Bhd. The sugar palm fibre was yarned using a manual hand spinning machine with 2500 tex of twisting. The limitation of the machine on its capability to produce other than 2500 tex because this machine was design specifically for 2500 tex due to physical characteristic of sugar palm fibre that has spike and very coarse to be twisted in lower tex. Unsaturated polyester was reinforced with sugar palm yarn fibre with various fibre loadings. Different fibre loadings that were prepared are 10 wt.%, 20 wt.%, 30 wt.%, 40 wt.% and 50 wt.%. Sugar palm yarn fibre at 2500 tex needs better penetration of matrix in composite systems. Hence in this study was limited on using low viscosity of unsaturated polyester resin due to its ability to penetrate yarn's internal structure.

1.6 Thesis outline

This thesis is structured into five chapters. The first chapter contains an overview of natural and synthetic fibres composites, the significance of research, highlights of the research problems, and finally the objectives, scope, and limitations of the research. Chapter two is an overview of the literature on natural fibres reinforced composites with focusing on sugar palm composites. Chapter three presents the overall research methodology for the overall structure of the research work. This chapter describes the materials, a specific approach in designing and planning the experimental design, experimental test procedures and standards. The following chapter four presents the results and discussion of the research works. Chapter four is divided into four sections,

covering the analysis on the properties of unsaturated polyester resin and sugar palm fibre, the effects of untreated sugar palm yarn fibre reinforced unsaturated polyester composites, the effects of fibre orientation, the effects of alkaline treatment to the fibre reinforced composites, and lastly the effects of hybridisation of sugar palm yarn fibre and woven glass fibre reinforced unsaturated polyester composites on the physical, mechanical, thermal and morphological properties. Finally, chapter five presents a summary of the research findings and recommendations for future works.



REFERENCES

- Abdul Khalil, H.P.S., Hanida, S., Kang, C.W. and Nik Fuaad, N.A. 2007. Agro-hybrid composite: The effects on mechanical and physical properties of oil palm fiber (EFB)/glass hybrid reinforced polyester composites. *Journal of Reinforced Plastics and Composites* 26: 203-218.
- Aboul-Fadl, S., Zeronian, S., Kamal, M., Kim, M. and Ellison, M. 1985. Effect of mercerization on the relation between single fiber mechanical properties and fine structure for different cotton species. *Textile Research Journal* 55: 461-469.
- Afzaluddin, A., Jawaid, M., Sapuan, S.M. and Ishak, M.R. 2017. Effect of surface treatment on the mechanical properties of sugar palm/glass fiber-reinforced thermoplastic polyurethane hybrid composites. *BioResources* 13: 1174-1188.
- Ahmad, F., Choi, H.S. and Park, M.K. 2015. A review: natural fiber composites selection in view of mechanical, light weight, and economic properties. *Macromolecular Materials and Engineering* 300: 10-24.
- Alamri, H. and Low, I.M. 2012. Microstructural, mechanical, and thermal characteristics of recycled cellulose fiber- halloysite- epoxy hybrid nanocomposites. *Polymer Composites* 33: 589-600.
- Ali, A., Sanuddin, A.B. and Ezzeddin, S. 2010. The effect of aging on Arenga pinnata fiber-reinforced epoxy composite. *Materials & Design* 31: 3550-3554.
- Allorerung, D. 2007. Tanaman Aren Serba Guna. Pusat Penelitian dan Pengembangan Pertanian-Workshop Budidaya dan Pemanfaatan Aren untuk Bahan Pangan dan Energi.
- Al Maadeed, M.A., Kahraman, R., Khanam, P.N. and Madi, N. 2012. Date palm wood flour/glass fibre reinforced hybrid composites of recycled polypropylene: Mechanical and thermal properties. *Materials & Design* 42: 289-294.
- Ariawan, D., Mohd Ishak, Z.A., Salim, M.S., Mat Taib, R., Ahmad Thirmizir, M.Z. and Pauzi, H. 2016. The effect of alkalization on the mechanical and water absorption properties of nonwoven kenaf fiber/unsaturated polyester composites produced by resin- transfer molding. *Polymer Composites* 37: 3516-3526.
- Arib, R.M.N., Sapuan, S. M., Ahmad, M.M.H.M., Paridah, M.T. and Zaman, H.M.D. K. 2006. Mechanical properties of pineapple leaf fibre reinforced polypropylene composites. *Materials & Design* 27: 391-396.
- Ashori, A. 2008. Wood-plastic composites as promising green-composites for automotive industries. *Bioresource Technology* 99: 4661-4667.

- Asim, M., Jawaid, M., Abdan, K. and Ishak, M.R. 2016. Effect of alkali and silane treatments on mechanical and fibre-matrix bond strength of kenaf and pineapple leaf fibres. *Journal of Bionic Engineering* 13: 426-435.
- Asim, M., Jawaid, M., Nasir, M. and Saba, N. 2017. Effect of fiber loadings and treatment on dynamic mechanical, thermal and flammability properties of pineapple leaf fiber and kenaf phenolic composites. *Journal of Renewable Materials*.
- Atiqah, A., Maleque, M.A., Jawaid, M. and Iqbal, M. 2014. Development of kenaf-glass reinforced unsaturated polyester hybrid composite for structural applications. *Composites Part B: Engineering* 56: 68-73.
- Atiqah, A., Jawaid, M., Sapuan, S.M. and Ishak, M.R. 2017. Mechanical and thermal properties of sugar palm fiber reinforced thermoplastic polyurethane composites: effect of silane treatment and fiber loading. *Journal of Renewable Materials*.
- Azaman, M.D., Sapuan, S.M., Sulaiman, S., Zainudin, E.S. and Khalina, A. 2015. Processability of wood fibre-filled thermoplastic composite thin-walled parts using injection moulding manufacturing of natural fibre reinforced polymer composites. 351-367: Springer.
- Aziz, S.H. and Ansell, M.P. 2004. The effect of alkalization and fibre alignment on the mechanical and thermal properties of kenaf and hemp bast fibre composites: Part 1–polyester resin matrix. *Composites Science and Technology* 64: 1219-1230.
- Bachtiar, D., Sapuan, S.M., Ahmad, M.H.M. and Sastra, H.Y. 2006. Chemical composition of ijuk (*Arenga pinnata*) fibre as reinforcement for polymer matrix composites. *Journal of Applied Technology* 4: 1-7.
- Bachtiar, D., Sapuan, S.M. and Hamdan, M.M. 2008. The effect of alkaline treatment on tensile properties of sugar palm fibre reinforced epoxy composites. *Materials & Design* 29: 1285-1290.
- Bachtiar, D., Sapuan, S.M. and Hamdan, M.M. 2009. The influence of alkaline surface fibre treatment on the impact properties of sugar palm fibre-reinforced epoxy composites. *Polymer-Plastics Technology and Engineering* 48: 379-383.
- Bachtiar, D., Sapuan, S.M. and Hamdan, M.M. 2010. Flexural properties of alkaline treated sugar palm fibre reinforced epoxy composites. *International Journal of Automotive and Mechanical Engineering* 1: 79-90.
- Bachtiar, D., Sapuan, S.M., Zainudin, E.S., Khalina, A. and Dahlan, K.Z.M. 2010a. The tensile properties of single sugar palm (*Arenga pinnata*) fibre. *IOP Conference Series: Materials Science and Engineering* 11: 012012.

- Bachtiar, D., Salit, M.S., Zainuddin, E.S., Abdan, K. and Dahlan, K.Z.M. 2011. Effects of alkaline treatment and a compatibilizing agent on tensile properties of sugar palm fibre-reinforced high impact polystyrene composites. *BioResources* 6: 4815-4823.
- Bachtiar, D., Sapuan, S.M., Khalina, A., Zainudin, E.S. and Dahlan, K.Z.M. 2012. Flexural and impact properties of chemically treated sugar palm fiber reinforced high impact polystyrene composites. *Fibers and Polymers* 13: 894-898.
- Bachtiar, D., Siregar, J., Sulaiman, A.S. and Mat Rejab, M.R. 2015. Tensile properties of hybrid sugar palm/kenaf fibre reinforced polypropylene composites. *Applied Mechanics and Materials* 695: 155-158.
- Bakare, I.O., Okieimen, F.E., Pavithran, C., Abdul Khalil, H.P.S. and Brahmakumar, M. 2010. Mechanical and thermal properties of sisal fiber-reinforced rubber seed oil-based polyurethane composites. *Materials & Design* 31: 4274-4280.
- Bar, M., Alagirusamy, R. and Das, A. 2018. Advances in Natural Fibre Reinforced Thermoplastic Composite Manufacturing: Effect of Interface and Hybrid Yarn Structure on Composite Properties. *Advances in Natural Fibre Composites* 99-117: Springer.
- Bastiurea, M., Rodeanu, M.S., Dima, D., Murarescu, M., Andrei, G., 2015. Thermal and mechanical properties of polyester composites with graphene oxide and graphite. *Digest Journal of Nanomaterials & Biostructures (DJNB)* 10: 521-533.
- Bharat, D. 2012. Unsaturated polyester resin for specialty applications. Polyester: In Tech.
- Bismarck, A., Baltazar-Y-Jimenez, A. and Sarikakis, K. 2006. Green composites as panacea? socio-economic aspects of green materials. *Environment. Development and Sustainability* 8: 445-463.
- Bledzki, A. 1999. Composites reinforced with cellulose based fibres. *Progress in Polymer Science* 24: 221-274.
- Brydson, J.A. 1999. *Plastics materials*. Elsevier.
- Burrola-Núñez, H., Herrera-Franco, P.J., Rodríguez-Félix, D.E., Soto-Valdez, H. and Madera-Santana, T.J. 2018. Surface modification and performance of jute fibers as reinforcement on polymer matrix: an overview. *Journal of Natural Fibers* 1-17.
- Brown, R.M. 2004. Cellulose structure and biosynthesis: What is in store for the 21st century?. *Journal of Polymer Science Part A: Polymer Chemistry* 42: 487-495.

- Callister Jr, W.D. and Rethwisch, D.G. 2012. Fundamentals of materials science and engineering: an integrated approach: John Wiley & Sons.
- Cantero, G., Arbelaiz, A., Llano-Ponte, R. and Mondragon, I. 2003. Effects of fibre treatment on wettability and mechanical behaviour of flax/polypropylene composites. *Composites Science and Technology* 63: 1247-1254.
- Chen, H.Z. 2005. Biotechnology of lignocellulose: Springer.
- Cheung, H.Y., Ho, M.P., Lau, K.T., Cardona, F. and Hui, D. 2009. Natural fibre-reinforced composites for bioengineering and environmental engineering applications. *Composites Part B: Engineering* 40: 655-663.
- Chu, N.J. 1970. The conformation of the anhydrocellobiose units in cellulose I and II. *Journal of Applied Polymer Science* 14: 3129-3136.
- Chua, P.S. 1987. Dynamic mechanical analysis studies of the interphase. *Polymer Composites* 8: 308-313.
- Cordwainers Garden: Diary of a Hackney Community Garden (Category: natural fibres) Retrieved 30 July 2018 from <https://cordwainersgarden.wordpress.com>.
- Davoodi, M.M., Sapuan, S.M., Ahmad, D., Ali, A., Khalina, A. and Jonoobi, M. 2010. Mechanical properties of hybrid kenaf/glass reinforced epoxy composite for passenger car bumper beam. *Materials & Design* 31: 4927-4932.
- Devi, L.U., Bhagawan, S.S. and Thomas, S. 1997. Mechanical properties of pineapple leaf fiber- reinforced polyester composites. *Journal of Applied Polymer Science* 64: 1739-1748.
- Ding, X.D., Jiang, Z.H., Sun, J., Lian, J.S. and Xiao, L. 2002. Stress-strain behavior in initial yield stage of short fiber reinforced metal matrix composite. *Composites Science and Technology* 62: 841-850.
- Edeerozey, A.M.M., Akil, H.M., Azhar, A.B. and Ariffin, M.I.Z. 2007. Chemical modification of kenaf fibers. *Materials Letters* 61: 2023-2025.
- Edhirej, A., Sapuan, S.M., Jawaid, M. and Zahari, N.I. 2017. Cassava/sugar palm fiber reinforced cassava starch hybrid composites: Physical, thermal and structural properties. *International Journal of Biological Macromolecules* 101: 75-83.
- Edhirej, A., Sapuan, S.M., Jawaid, M. and Zahari, N.I. 2017a. Tensile, barrier, dynamic mechanical, and biodegradation properties of cassava/sugar palm fiber reinforced cassava starch hybrid composites. *BioResources* 12: 7145-7160.
- Faruk, O., Bledzki, A.K., Fink, H.P. and Sain, M. 2012. Biocomposites reinforced with natural fibers: 2000–2010. *Progress in Polymer Science* 37: 1552-1596.

- Ferreira, J.M., Errajhi, O.A.Z. and Richardson, M.O.W. 2006. Thermogravimetric analysis of aluminised E-glass fibre reinforced unsaturated polyester composites. *Polymer Testing* 25: 1091-1094.
- Fidelis, M.E.A., Pereira, T.V.C., Gomes, O.D.F.M., de Andrade Silva, F. and Toledo Filho, R.D. 2013. The effect of fiber morphology on the tensile strength of natural fibers. *Journal of Materials Research and Technology* 2: 149-157.
- Fogorasi, M.S. and Barbu, I. 2017. The potential of natural fibres for automotive sector-review. *IOP Conference Series: Materials Science and Engineering* 252: 012044.
- Fong, T.C., Saba, N., Liew, C.K., De Silva, R., Hoque, M.E. and Goh, K.L. 2015. Yarn flax fibres for polymer-coated sutures and hand layup polymer composite laminates manufacturing of natural fibre reinforced polymer composites (155-175): Springer.
- Fortea-Verdejo, M., Bumbaris, E., Burgstaller, C., Bismarck, A. and Lee, K.Y. 2017. Plant fibre-reinforced polymers: where do we stand in terms of tensile properties?. *International Materials Reviews* 1-24.
- Fu, S.Y., Feng, X.Q., Lauke, B. and Mai, Y.W. 2008. Effects of particle size, particle/matrix interface adhesion and particle loading on mechanical properties of particulate-polymer composites. *Composites Part B: Engineering* 39: 933-961.
- Gassan, J. and Bledzki, A.K. 1997. The influence of fiber-surface treatment on the mechanical properties of jute-polypropylene composites. *Composites Part A: Applied Science and Manufacturing* 28: 1001-1005.
- Gassan, J. and Bledzki, A.K. 1999. Possibilities for improving the mechanical properties of jute/epoxy composites by alkali treatment of fibres. *Composites Science and Technology* 59: 1303-1309.
- Girisha, C., Sanjeevamurthy, G. and Srinivas, G.R. 2012. Sisal/coconut coir natural fibers-epoxy composites: water absorption and mechanical properties. *International Journal of Engineering and Innovative Technology (IJEIT)* 2: 166-170.
- Goud, G. and Rao, R.N. 2011. Effect of fibre content and alkali treatment on mechanical properties of Roystonea regia-reinforced epoxy partially biodegradable composites. *Bulletin of Materials Science* 34: 1575-1581.
- Goud, G. and Rao, R.N. 2012. Mechanical and electrical performance of Roystonea regia/glass fibre reinforced epoxy hybrid composites. *Bulletin of Materials Science* 35: 595-599.
- Gu, H. 2009. Dynamic mechanical analysis of the seawater treated glass/polyester composites. *Materials & Design* 30: 2774-2777.

- Gurunathan, T., Mohanty, S. and Nayak, S.K. 2015. A review of the recent developments in biocomposites based on natural fibres and their application perspectives. *Composites Part A: Applied Science and Manufacturing* 77: 1-25.
- Habibi, Y., El-Zawawy, W.K., Ibrahim, M.M. and Dufresne, A. 2008. Processing and characterization of reinforced polyethylene composites made with lignocellulosic fibers from Egyptian agro-industrial residues. *Composites Science and Technology* 68: 1877-1885.
- Haneefa, A., Bindu, P., Aravind, I. and Thomas, S. 2008. Studies on tensile and flexural properties of short banana/glass hybrid fiber reinforced polystyrene composites. *Journal of Composite Materials* 42: 1471-1489.
- Hani, A., Rashid, A., Seang, C.T., Ahmad, R. and Mariatti, J.M. 2013. Impact and flexural properties of imbalance plain woven coir and kenaf composite. *Applied Mechanics and Materials* 271: 81-85.
- Hanifawati, I.N., Hanim, A., Sapuan, S.M. and Zainuddin, E.S. 2011. Tensile and flexural behavior of hybrid banana pseudostem/glass fibre reinforced polyester composites. *Key Engineering Materials* 471: 686-691.
- Hatem, A. and Meng, L.I. 2012. Mechanical properties and water absorption behaviour of recycled cellulose fibre reinforced epoxy composites. *Polymer Testing* 31: 620-628.
- Haameem, J.A.M., Majid, M.A., Afendi, M., Haslan, M. and Fahmi, I. 2016. Alkaline treatment and thermal properties of Napier grass fibres. *International Journal of Automotive and Mechanical Engineering* 13: 3238.
- Hearle, J.W.S. and Morton, W.E. 2008. Physical properties of textile fibres: Elsevier.
- Ho, M.P., Wang, H., Lee, J.H., Ho, C.K., Lau, K.T., Leng, J. and Hui, D. 2012. Critical factors on manufacturing processes of natural fibre composites. *Composites Part B: Engineering* 43: 3549-3562.
- Holbery, J. and Houston, D. 2006. Natural-fiber-reinforced polymer composites in automotive applications. *Journal of the Minerals, Metals and Materials Society* 58: 80-86.
- Hossain, M.M., Datta, E. and Rahman, S. 2016. A Review on Different Factors of Woven Fabrics' Strength Prediction. *Science Research* 4: 88-97.
- Hristov, V.N., Vasileva, S.T., Krumova, M., Lach, R. and Michler, G.H. 2004. Deformation mechanisms and mechanical properties of modified polypropylene/wood fiber composites. *Polymer Composites* 25: 521-526.

- Idicula, M., Malhotra, S.K., Joseph, K. and Thomas, S. 2005. Dynamic mechanical analysis of randomly oriented intimately mixed short banana/sisal hybrid fibre reinforced polyester composites. *Composites Science and Technology* 65: 1077-1087.
- Iijima, T., Tochimoto, T., Tomoi, M., 1991. Modification of epoxy resins with poly (aryl ether ketone)s. *Journal of Applied Polymer Science* 43: 1685-1692.
- Ishak, M.R., Leman, Z., Sapuan, S.M., Salleh, M.Y. and Misri, S. 2009. The effect of sea water treatment on the impact and flexural strength of sugar palm fibre reinforced epoxy composites. *International Journal of Mechanical and Materials Engineering* 4: 316-320.
- Ishak, M.R., Sapuan, S.M., Leman, Z., Sahari, J. and Ibrahim, M.S. 2010. Chemical composition of sugar palm (*Arenga pinnata*) fibres: the effects of natural degradation. Proceedings of the international conference on design and concurrent engineering (iDECON 2010), Malacca, Malaysia, 20-21.
- Ishak, M.R., Leman, Z., Sapuan, S.M., Rahman, M.Z.A. and Anwar, U.M.K. 2011a. Effects of impregnation pressure on physical and tensile properties of impregnated sugar palm (*Arenga pinnata*) fibres. *Key Engineering Materials* 471: 1153-1158.
- Ishak, M.R., Leman, Z., Sapuan, S.M., Rahman, M.Z.A. and Anwar, U.M.K. 2011b. Effects of impregnation time on physical and tensile properties of impregnated sugar palm (*Arenga pinnata*) fibres. *Key Engineering Materials* 471: 1147-1152.
- Ishak, M.R., Sapuan, S.M., Leman, Z., Rahman, M.Z.A. and Anwar, U.M.K. 2012. Characterization of sugar palm (*Arenga pinnata*) fibres. *Journal of Thermal Analysis and Calorimetry* 109: 981-989.
- Ishak, M.R., Sapuan, S.M., Leman, Z., Rahman, M.Z.A., Anwar, U.M.K. and Siregar, J. P. 2013. Sugar palm (*Arenga pinnata*): Its fibres, polymers and composites. *Carbohydrate Polymers* 91: 699-710.
- Ismail, H., Pasbakhsh, P., Fauzi, M.N.A. and Bakar, A.A. 2008. Morphological, thermal and tensile properties of halloysite nanotubes filled ethylene propylene diene monomer (EPDM) nanocomposites. *Polymer Testing* 27: 841-850.
- Ismail, H., Hamid Abdullah, A. and Abu Bakar, A. 2010. Kenaf core reinforced high-density polyethylene/soya powder composites: The effects of filler loading and compatibilizer. *Journal of Reinforced Plastics and Composites* 29: 2489-2497.
- Jaswal, S. and Gaur, B. 2014. New trends in vinyl ester resins. *Reviews in Chemical Engineering* 30: 567-581.

- Jawaid, M., Khalil, H.P.S.A., Hassan, A., Dungani, R. and Hadiyane, A. 2013. Effect of jute fibre loading on tensile and dynamic mechanical properties of oil palm epoxy composites. *Composites Part B: Engineering* 45: 619-624.
- Jansen, J., Kraeger, R.I., 2018. U.S. Patent No. 9,902,805. Washington, DC: U.S. Patent and Trademark Office.
- Jeyanthi, S. and Rani, J.J. 2012. Influence of natural long fiber in mechanical, thermal and recycling properties of thermoplastic composites in automotive components. *International Journal of Physical Sciences* 7: 5765-5771.
- John, M. and Thomas, S. 2008. Biofibres and biocomposites. *Carbohydrate Polymers* 71: 343-364.
- John, M.J. and Anandjiwala, R.D. 2008a. Recent developments in chemical modification and characterization of natural fiber- reinforced composites. *Polymer Composites* 29: 187-207.
- John, M.J. and Thomas, S. 2008b. Biofibres and biocomposites. *Carbohydrate Polymers* 71: 343-364.
- Joseph, P.V., Mathew, G., Joseph, K., Groeninckx, G. and Thomas, S. 2003. Dynamic mechanical properties of short sisal fibre reinforced polypropylene composites. *Composites Part A: Applied Science and Manufacturing* 34: 275-290.
- Jumaidin, R., Sapuan, S.M., Jawaid, M., Ishak, M.R. and Sahari, J. 2017. Thermal, mechanical, and physical properties of seaweed/sugar palm fibre reinforced thermoplastic sugar palm starch/agar hybrid composites. *International Journal of Biological Macromolecules* 97: 606-615.
- Kalia, S. (Ed.) 2017. Lignocellulosic Composite Materials. Springer.
- Kalia, S., Kaith, B.S. and Kaur, I. 2009. Pretreatments of natural fibers and their application as reinforcing material in polymer composites—a review. *Polymer Engineering & Science* 49: 1253-1272.
- Kargarzadeh, H., Sheltami, R.M., Ahmad, I., Abdullah, I. and Dufresne, A. 2014. Cellulose nanocrystal: A promising toughening agent for unsaturated polyester nanocomposite. *Polymer* 56: 346-357.
- Karus, M., Kaup, M. and Ortmann, S. 2003. Use of natural fibres in composites in the German and Austrian automotive industry—market survey 2002: status, analysis and trends. *Journal of Industrial Hemp* 8: 73-78.
- Kestur, G.S., Gregorio, G.C.A. and Fernando, W. 2009. Biodegradable composites based on lignocellulosic fibers—An overview. *Progress in Polymer Science* 34: 982-1021.

- Khan, R.A., Khan, M.A., Zaman, H.U., Pervin, S., Khan, N., Sultana, S., Saha, M., Mustafa, A.I. 2010. Comparative studies of mechanical and interfacial properties between jute and E-glass fiber-reinforced polypropylene composites. *Journal of Reinforced Plastics and Composites* 29: 1078-1088.
- Kim, J.P., Yoon, T.H., Mun, S.P., Rhee, J.M. and Lee, J.S. 2006. Wood–polyethylene composites using ethylene–vinyl alcohol copolymer as adhesion promoter. *Bioresource Technology* 97: 494-499.
- Koronis, G., Silva, A. and Fontul, M. 2013. Green composites: A review of adequate materials for automotive applications. *Composites Part B: Engineering* 44: 120-127.
- Kozłowski, R.M. 2012. Handbook of natural fibres: Processing and applications (2): Woodhead Publishing.
- Ku, H., Wang, H., Pattarachaiyakop, N. and Trada, M. 2011. A review on the tensile properties of natural fiber reinforced polymer composites. *Composites Part B: Engineering* 42: 856-873.
- Kwon, H.J., Sunthornvarabhas, J., Park, J.W., Lee, J.H., Kim, H.J., Piyachomkwan, K., Sriroth, K. and Cho, D. 2014. Tensile properties of kenaf fiber and corn husk flour reinforced poly (lactic acid) hybrid bio-composites: role of aspect ratio of natural fibers. *Composites Part B: Engineering* 56: 232-237.
- Laine, L. and Rozite, L. 2010. Eco-efficient composite materials. European Union European Regional Development Fund.
- Lawrence, C.A. 2003. Fundamentals of spun yarn technology: CRC Press.
- Leman, Z., Sapuan, S.M., Azwan, M., Ahmad, M.M.H.M. and Maleque, M. A. 2008. The effect of environmental treatments on fiber surface properties and tensile strength of sugar palm fiber-reinforced epoxy composites. *Polymer-Plastics Technology and Engineering* 47: 606-612.
- Leman, Z., Sapuan, S.M., Saifol, A.M., Maleque, M.A. and Ahmad, M.M.H.M. 2008a. Moisture absorption behavior of sugar palm fiber reinforced epoxy composites. *Materials & Design* 29: 1666-1670.
- Li, Y., Mai, Y.W. and Ye, L. 2000. Sisal fibre and its composites: a review of recent developments. *Composites Science and Technology* 60: 2037-2055.
- Liu, W., Mohanty, A.K., Askeland, P., Drzal, L.T. and Misra, M. 2004. Influence of fiber surface treatment on properties of Indian grass fiber reinforced soy protein based biocomposites. *Polymer* 45: 7589-7596.
- Malik, M., Choudhary, V. and Varma, I.K. 2000. Current status of unsaturated polyester resins. *Journal of Macromolecular Science, Part C: Polymer Reviews* 40: 139-165.

- Madsen, B. and Lilholt, H. 2003. Physical and mechanical properties of unidirectional plant fibre composites—an evaluation of the influence of porosity. *Composites Science and Technology* 63: 1265-1272.
- Maleque, M., Belal, F.Y. and Sapuan, S.M. 2007. Mechanical properties study of pseudo-stem banana fiber reinforced epoxy composite. *The Arabian Journal for Science and Engineering* 32: 359-364.
- Mallick, P.K. 2007. Fiber-reinforced composites: materials, manufacturing, and design: CRC press.
- Manfredi, L.B., Rodríguez, E.S., Wladyka-Przybylak, M. and Vázquez, A. 2006. Thermal degradation and fire resistance of unsaturated polyester, modified acrylic resins and their composites with natural fibres. *Polymer Degradation and Stability* 91: 255-261.
- Manikandan Nair, K.C., Thomas, S. and Groeninckx, G. 2001. Thermal and dynamic mechanical analysis of polystyrene composites reinforced with short sisal fibres. *Composites Science and Technology* 61: 2519-2529.
- Mansor, M.R., Sapuan, S.M., Zainudin, E.S., Nuraini, A.A. and Hambali, A. 2013. Stiffness prediction of hybrid kenaf/glass fiber reinforced polypropylene composites using rule of mixtures (ROM) and rule of hybrid mixtures (RoHM). *Journal of Polymer Materials* 30: 321.
- Matthews, F.L. and Rawlings, R.D. 1999. Composite materials: engineering and science: CRC Press.
- Merlini, C., Soldi, V. and Barra, G.M.O. 2011. Influence of fiber surface treatment and length on physico-chemical properties of short random banana fiber-reinforced castor oil polyurethane composites. *Polymer Testing* 30: 833-840.
- Miao, M., How, Y.L. and Cheng, K.P.S. 1994. The role of false twist in wrap spinning. *Textile Research Journal* 64: 41-48.
- Mishra, S., Misra, M., Tripathy, S.S., Nayak, S.K. and Mohanty, A.K. 2001. Potentiality of pineapple leaf fibre as reinforcement in palf-polyester composite: surface modification and mechanical performance. *Journal of Reinforced Plastics and Composites* 20: 321-334.
- Mishra, S., Mohanty, A.K., Drzal, L.T., Misra, M., Parija, S., Nayak, S.K. and Tripathy, S.S. 2003. Studies on mechanical performance of biofibre/glass reinforced polyester hybrid composites. *Composites Science and Technology* 63: 1377-1385.
- Misri, S., Leman, Z., Sapuan, S.M. and Ishak, M.R. 2010. Mechanical properties and fabrication of small boat using woven glass/sugar palm fibres reinforced unsaturated polyester hybrid composite. *IOP Conference Series: Materials Science and Engineering* 11: 012015.

- Moe Moe, T. and Kin, L. 2002. Effects of environmental aging on the mechanical properties of bamboo–glass fiber reinforced polymer matrix hybrid composites. *Composites Part A: Applied Science and Manufacturing* 33: 43-52.
- Mogea, J., Seibert, B. and Smits, W. 1991. Multipurpose palms: the sugar palm (*Arenga pinnata* (Wurmb) Merr.). *Agroforestry Systems* 13: 111-129.
- Mohammed, A.A., Bachtiar, D., Siregar, J.P. and Rejab, M.R.M. 2016. Effect of sodium hydroxide on the tensile properties of sugar palm fibre reinforced thermoplastic polyurethane composites. *Journal of Mechanical Engineering and Sciences* 10: 1765-1777.
- Mohammed, B.R., Leman, Z., Jawaid, M., Ghazali, M.J. and Ishak, M.R. 2017. Dynamic mechanical analysis of treated and untreated sugar palm fibre-based phenolic composites. *BioResources* 12: 3448-3462.
- Mohanty, A.K., Misra, M. and Hinrichsen, G. 2000. Biofibers, biodegradable polymers and biocomposites: an overview. *Macromolecular Materials and Engineering* 276: 1-24.
- Mohanty, A.K., Misra, M. and Drzal, L.T. 2001. Surface modifications of natural fibers and performance of the resulting biocomposites: an overview. *Composite Interfaces* 8: 313-343.
- Mohanty, A.K., Misra, M. and Drzal, L.T. 2002. Sustainable bio-composites from renewable resources: opportunities and challenges in the green materials world. *Journal of Polymers and the Environment* 10: 19-26.
- Mohanty, A.K., Misra, M. and Drzal, L.T. 2005. Natural fibers, biopolymers, and biocomposites: CRC press.
- Moharir, A.V. 2000. Structure and determinants of fibre strength in native cotton: NISCAIR-CSIR, India.
- Mohd Nurazzi, N., Khalina, A., Sapuan, S.M., Dayang Laila, A.H.A.M., Rahmah, M., Hanafee, Z. 2017. A Review: Fibres, polymer matrices and composites. *Pertanika Journal of Science & Technology* 25: 1085 – 1102.
- Mortazavian, S. and Fatemi, A. 2015. Effects of fiber orientation and anisotropy on tensile strength and elastic modulus of short fiber reinforced polymer composites. *Composites Part B: Engineering* 72: 116-129.
- Mouzakis, D.E., Zoga, H., Galiotis, C., 2008. Accelerated environmental ageing study of polyester/glass fiber reinforced composites (GFRPCs). *Composites Part B: Engineering* 39: 467-475.
- Mohammed, A.A., Bachtiar, D., Siregar, J.P. and Rejab, M.R.M. 2016. Effect of sodium hydroxide on the tensile properties of sugar palm fibre reinforced

thermoplastic polyurethane composites. *Journal of Mechanical Engineering and Sciences* 10: 1765-1777.

Munawar, S.S., Umemura, K., Tanaka, F. and Kawai, S. 2008. Effects of alkali, mild steam, and chitosan treatments on the properties of pineapple, ramie, and sansevieria fiber bundles. *Journal of Wood Science* 54: 28-35.

Musch, J.C.R. 2008. Design optimization of sustainable panel systems using hybrid natural/synthetic fiber reinforced polymer composites. (M.Sc. Thesis), Michigan State University, East Lansing, Michigan, United States.

Mwaikambo, L.Y. and Ansell, M.P. 2002. Chemical modification of hemp, sisal, jute, and kapok fibers by alkalization. *Journal of Applied Polymer Science* 84: 2222-2234.

Nabil, F.L., Zaidon, A., Jawaid, M., Anwar, U.M.K., Bakar, E.S., Paridah, M.T., Ridzuan, S.M.A. and Aizat, G.M. 2015. Physical and morphological properties of nanoclay in low molecular weight phenol formaldehyde resin by ultrasonication. *International Journal of Adhesion and Adhesives* 62: 124-129.

Nadlene, R., Sapuan, S.M., Jawaid, M., Ishak, M.R. and Yusriah, L. 2018. The effects of chemical treatment on the structural and thermal, physical, and mechanical and morphological properties of roselle fiber- reinforced vinyl ester composites. *Polymer Composites* 39: 274-287.

Naguib, H.M., Kandil, U.F., Hashem, A.I. and Boghdadi, Y.M. 2015. Effect of fiber loading on the mechanical and physical properties of “green” bagasse–polyester composite. *Journal of Radiation Research and Applied Sciences* 8: 544-548.

Nair, K.C., Diwan, S.M. and Thomas, S. 1996. Tensile properties of short sisal fiber reinforced polystyrene composites. *Journal of Applied Polymer Science* 60: 1483-1497.

Nair, K.C.M., Thomas, S. and Groeninckx, G., 2001. Thermal and dynamic mechanical analysis of polystyrene composites reinforced with short sisal fibres. *Composites Science and Technology* 61: 2519-2529.

Nirmal, U., Lau, S.T.W. and Hashim, J. 2014. Interfacial adhesion characteristics of kenaf fibres subjected to different polymer matrices and fibre treatments. *Journal of Composites* 1-12.

Nunna, S., Chandra, P.R., Shrivastava, S. and Jalan, A. 2012. A review on mechanical behavior of natural fiber based hybrid composites. *Journal of Reinforced Plastics and Composites* 31: 759-769.

Osman, E.A., Vakhguelt, A., Sbarski, I. and Mutasher, S.A. 2012. Curing behaviour and tensile properties of unsaturated polyester containing various styrene concentrations. *Malaysian Polymer Journal* 7: 46-55.

- Ouarhim, W., Essabir, H., Bensalah, M.O., Zari, N., Bouhfid, R. and el kacem Qaiss, A. 2018. Structural laminated hybrid composites based on raffia and glass fibers: Effect of alkali treatment, mechanical and thermal properties. *Composites Part B: Engineering* 154: 128-137.
- Pan, N. 1993. Prediction of statistical strengths of twisted fibre structures. *Journal of Materials Science* 28: 6107-6114.
- Pang, A. L., Ismail, H. and Bakar, A.A. 2015. Effects of kenaf loading on processability and properties of linear low-density polyethylene/poly(vinyl alcohol)/kenaf composites. *BioResources* 10: 7302-7314.
- Parween, A.K., Omer, S.Z., Basim, A.K. and Zainab, S.R. 2013. Fracture toughness of sugar palm fiber reinforced epoxy composites. *International Journal of Science and Research* 2: 273-279.
- Pereira, P.H.F., Rosa, M.D.F., Cioffi, M.O.H., Benini, K.C.C.D.C., Milanese, A.C., Voorwald, H.J.C. and Mulinari, D.R. 2015. Vegetal fibers in polymeric composites: a review. *Polímeros* 25: 9-22.
- Pothan, L.A., Oommen, Z. and Thomas, S. 2003. Dynamic mechanical analysis of banana fiber reinforced polyester composites. *Composites Science and Technology* 63: 283-293.
- Rahmah, M., Mohd Nurazzi, N., Farah Nordyana, A.R. and Syed Anas, S.M. 2017. Effect of epoxidised soybean oil loading as plasticiser on physical, mechanical and thermal properties of polyvinylchloride. *IOP Conf. Series: Materials Science and Engineering* 223: 012048.
- Rajan, V.P. and Curtin, W.A. 2015. Rational design of fiber-reinforced hybrid composites: A global load sharing analysis. *Composites Science and Technology* 117: 199-207.
- Rajesh, G., Reena, G., Rama, K.A. and Lakshmipathi, B.R. 2011. Effect of fibre volume fraction on the tensile strength of Banana fibre reinforced vinyl ester resin composites. *IJAEST-International Journal of Advanced Engineering Sciences and Technologies* 1: 89-91.
- Ramis, X. and Salla, J.M. 1997. Time- temperature transformation (TTT) cure diagram of an unsaturated polyester resin. *Journal of Polymer Science Part B: Polymer Physics* 35: 371-388.
- Rashid, B., Leman, Z., Jawaid, M., Ghazali, M.J. and Ishak, M.R. 2016. The mechanical performance of sugar palm fibres (ijuk) reinforced phenolic composites. *International Journal of Precision Engineering and Manufacturing* 17: 1001-1008.

- Rashid, B., Leman, Z., Jawaaid, M., Ghazali, M.J., Ishak, M.R., 2017. Effect of treatments on the physical and morphological properties of SPF/phenolic composites. *Journal of Natural Fibers* 1-13.
- Rashid, B., Leman, Z., Jawaaid, M., Ghazali, M.J. and Ishak, M.R. 2017a. Influence of treatments on the mechanical and thermal properties of sugar palm fibre reinforced phenolic composites. *BioResources* 12: 1447-1462.
- Rashid, B., Leman, Z., Jawaaid, M., Ghazali, M.J., Ishak, M.R. and Abdelgnei, M.A. 2017b. Dry sliding wear behavior of untreated and treated sugar palm fiber filled phenolic composites using factorial technique. *Wear* 380: 26-35.
- Ravi, M., Dubey, R.R., Shome, A., Guha, S. and Kumar, C.A 2018. Effect of surface treatment on Natural fibers composite. *IOP Conference Series: Materials Science and Engineering* 376: 012053.
- Ray, D. and Rout, J. 2005. Thermoset biocomposites. Natural fibers, biopolymers, and biocomposites: CRC Press.
- Ray, A.K., Mondal, S., Das, S.K. and Ramachandrarao, P. 2005. Bamboo—a functionally graded composite-correlation between microstructure and mechanical strength. *Journal of Materials Science* 40: 5249-5253.
- Reddy, N. and Yang, Y. 2005. Biofibers from agricultural byproducts for industrial applications. *Trends in Biotechnology*: 23: 22-27.
- Reddy, G.V., Naidu, S.V. and Rani, T.S. 2008. Impact Properties of Kapok Based Unsaturated Polyester Hybrid Composites. *Journal of Reinforced Plastics and Composites* 27: 1789-1804.
- Rong, M.Z., Zhang, M.Q., Liu, Y., Yang, G.C. and Zeng, H.M. 2001. The effect of fiber treatment on the mechanical properties of unidirectional sisal-reinforced epoxy composites. *Composites Science and Technology* 61: 1437-1447.
- Saba, N., Tahir, P. and Jawaaid, M. 2014. A Review on potentiality of nano filler/natural fiber filled polymer hybrid composites. *Polymers* 6: 2247-2273.
- Saba, N., Jawaaid, M., Alothman, O.Y. and Paridah, M.T. 2016. A review on dynamic mechanical properties of natural fibre reinforced polymer composites. *Construction and Building Materials* 106: 149-159.
- Sahari, J., Sapuan, S.M., Ismarrubie, Z.N. and Rahman, M.Z.A. 2011. Comparative study of physical properties based on different parts of sugar palm fibre reinforced unsaturated polyester composites. *Key Engineering Materials* 471: 455-460.

- Sahari, J., Sapuan, S.M., Ismarrubie, Z.N. and Rahman, M.Z.A. 2011a. Investigation on bending strength and stiffness of sugar palm fibre from different parts reinforced unsaturated polyester composites. *Key Engineering Materials* 471: 502-506.
- Sahari, J., Sapuan, S.M., Ismarrubie, Z.N. and Rahman, M.Z.A. 2012. Physical and chemical properties of different morphological parts of sugar palm fibres. *Fibres and Textiles in Eastern Europe* 91: 21-24.
- Sahari, J., Sapuan, S.M., Ismarrubie, Z.N. and Rahman, M.Z.A. 2012a. Tensile and impact properties of different morphological parts of sugar palm fibre-reinforced unsaturated polyester composites. *Polymers & Polymer Composites* 20: 861.
- Sahari, J., Sapuan, S.M., Zainudin, E.S. and Maleque, M.A. 2012b. A new approach to use *Arenga pinnata* as sustainable biopolymer: Effects of plasticizers on physical properties. *Procedia Chemistry* 4: 254-259.
- Sahari, J., Sapuan, S.M., Zainudin, E.S. and Maleque, M.A. 2013. Mechanical and thermal properties of environmentally friendly composites derived from sugar palm tree. *Materials & Design* 49: 285-289.
- Sahari, J., Sapuan, S. M., Zainudin, E. S. and Maleque, M. A. 2013a. Thermo-mechanical behaviors of thermoplastic starch derived from sugar palm tree (*Arenga pinnata*). *Carbohydrate Polymers* 92: 1711-1716.
- Saheb, D.N., Jog, J.P., 1999. Natural fiber polymer composites: a review. *Advances in Polymer Technology* 18: 351-363.
- Sain, M. and Panthapulakkal, S. 2004. Green fiber thermoplastic composites. *Green composites: Polymer Composites and The Environment* 181-206.
- Santiagoo, R., Ismail, H. and Hussin, K. 2011. Mechanical properties, water absorption, and swelling behaviour of rice husk powder filled polypropylene/recycled acrylonitrile butadiene rubber (PP/NBRr/RHP) biocomposites using silane as a coupling agent. *BioResources* 6: 3714-3726.
- Sapuan, S.M. and Bachtiar, D. 2012. Mechanical properties of sugar palm fibre reinforced high impact polystyrene composites. *Procedia Chemistry* 4: 101-106.
- Sapuan, S.M., Lok, H.Y., Ishak, M.R. and Misri, S. 2013. Mechanical properties of hybrid glass/sugar palm fibre reinforced unsaturated polyester composites. *Chinese Journal of Polymer Science* 31: 1394-1403.
- Satyanarayana, K.G., Arizaga, G.G.C. and Wypych, F. 2009. Biodegradable composites based on lignocellulosic fibers—An overview. *Progress in Polymer Science* 34: 982-1021.

- Schneider, M.H. and Brebner, K.I. 1985. Wood-polymer combinations: The chemical modification of wood by alkoxysilane coupling agents. *Wood Science and Technology* 19: 67-73.
- Sepe, R., Bollino, F., Boccarusso, L. and Caputo, F. 2018. Influence of chemical treatments on mechanical properties of hemp fiber reinforced composites. *Composites Part B: Engineering* 133: 210-217.
- Shalwan, A. and Yousif, B.F. 2013. In state of art: mechanical and tribological behaviour of polymeric composites based on natural fibres. *Materials & Design* 48: 14-24.
- Shanmugasundaram, N., Rajendran, I. and Ramkumar, T. 2018. Characterization of untreated and alkali treated new cellulosic fiber from an Areca palm leaf stalk as potential reinforcement in polymer composites. *Carbohydrate Polymers* 195: 566-575.
- SIGMA ALDRICH Catalog. Retrieved 30 July 2018 from <https://www.sigmaaldrich.com/catalog>.
- Siqueira, G., Bras, J., Dufresne, A., 2010. Cellulosic bionanocomposites: a review of preparation, properties and applications. *Polymers*, 2, 728-765.
- Siregar, J.P. 2005. Tensile and flexural properties of Arenga pinnata filament (ijuk filament) reinforced epoxy composites. (Ph.D Thesis), Universiti Putra Malaysia.
- Širvaitienė, A., Jankauskaitė, V., Bekampienė, P. and Kondratas, A. 2013. Influence of natural fibre treatment on interfacial adhesion in biocomposites. *Fibres & Textiles in Eastern Europe* 21: 123-129.
- Sloan, J. 2014. Styrene & cobalt: Headed for the exit?. Retrieved 4 January 2014 from <https://www.compositesworld.com/articles/styrene-cobalt-headed-for-the-exit>.
- Smith, W.F. and Hashemi, J. 2003. Fundamentals of Materials Science and Engineering. McGraw Hill, New York.
- Sockalingam, S., Nilakantan, G., 2012. Fiber-matrix interface characterization through the microbond test. *International Journal of Aeronautical and Space Sciences* 13: 282-295.
- Speight, J.G. 2005. Lange's handbook of chemistry. McGraw-Hill, New York.
- Sreekala, M.S., George, J., Kumaran, M.G. and Thomas, S. 2002. The mechanical performance of hybrid phenol-formaldehyde-based composites reinforced with glass and oil palm fibres. *Composites Science and Technology* 62: 339-353.

- Sreekumar, P.A., Joseph, K., Unnikrishnan, G. and Thomas, S. 2007. A comparative study on mechanical properties of sisal-leaf fibre-reinforced polyester composites prepared by resin transfer and compression moulding techniques. *Composites Science and Technology* 67: 453-461.
- Supri, A.G. and Ismail, H. 2011. The effect of isophorone diisocyanate-polyhydroxyl groups modified water hyacinth fibers (*Eichhornia crassiper*) on properties of low density polyethylene/acrylonitrile butadiene styrene (LDPE/ABS) composites. *Polymer-Plastics Technology and Engineering* 50: 113-120.
- Suwartapradja, O.S. 2003. *Arenga pinnata*: A case study of indigenous knowledge on the utilization of a wild food plant in West Java.
- Syed Azuan, S.A. 2013. Influence of fibre volume fraction and vacuum pressure on the flexural properties of sugar palm frond fibre reinforced polyester composites. *Australian Journal of Basic and Applied Sciences* 7: 318-322.
- Tang, Z.X., Fraser, W.B. and Wang, X. 2007. Modelling yarn balloon motion in ring spinning. *Applied Mathematical Modelling* 31: 1397-1410.
- Tajvidi, M. 2005. Static and dynamic mechanical properties of a kenaf fiber–wood flour/polypropylene hybrid composite. *Journal of Applied Polymer Science* 98: 665-672.
- Textilemates. Retrieved 29 January 2018 from <https://www.textilemates.com/yarn-structure/>.
- Thiruchitrambalam, M., Alavudeen, A., Athijayamani, A., Venkateshwaran, N. and Perumal, A.E. 2009. Improving mechanical properties of banana/kenaf polyester hybrid composites using sodium lauryl sulfate treatment. *Materials physics and Mechanics* 8: 165-173.
- Thomas, S., Pothan, L.A. and Cherian, B.M. 2009. Advances in natural fibre reinforced polymer composites: macro to nanoscales. *International Journal of Materials and Product Technology* 36: 317-333.
- Thwe, M.M. and Liao, K. 2002. Effects of environmental aging on the mechanical properties of bamboo–glass fiber reinforced polymer matrix hybrid composites. *Composites Part A: Applied Science and Manufacturing* 33: 43-52.
- Tungjitpornkull, S. and Sombatsompop, N. 2009. Processing technique and fiber orientation angle affecting the mechanical properties of E-glass fiber reinforced wood/PVC composites. *Journal of Materials Processing Technology* 209: 3079-3088.
- Tuttle, M. 2004. *Introduction In Structural analysis of Polymeric Composite Materials* University of Washington.

- Van de Velde, K. and Kiekens, P. 2001. Thermoplastic pultrusion of natural fibre reinforced composites. *Composite Structures* 54: 355-360.
- Varatharajan, R., Malhotra, S.K., Vijayaraghavan, L. and Krishnamurthy, R. 2006. Mechanical and machining characteristics of GF/PP and GF/Polyester composites. *Materials Science and Engineering: B* 132: 134-137.
- Varma, I. K., Anantha Krishnan, S. R. and Krishnamoorthy, S. 1989. Composites of glass/modified jute fabric and unsaturated polyester resin. *Composites* 20: 383-388.
- Vaxman, A., Narkis, M., Siegmann, A. and Kenig, S. 1989. Short- fiber- reinforced thermoplastics. Part III: Effect of fiber length on rheological properties and fiber orientation. *Polymer Composites* 10: 454-462.
- Venkata R.G., Venkata N.S. and Shobha R.T., 2008. Impact properties of kapok based unsaturated polyester hybrid composites. *Journal of Reinforced Plastics and Composites* 27: 1789-1804.
- Vieira, C.A.B., Susin, S.B., Estevão, F., Amico, S.C. and Zattera, A.J. 2009. Characterization of hybrid composites produced with mats made using different methods. *Materials Research* 12: 433-436.
- Vilas, J.L., Laza, J.M., Garay, M.T., Rodriguez, M. and Leon, L.M. 2001. Unsaturated polyester resins cure: Kinetic, rheologic, and mechanical dynamical analysis. II. The glass transition in the mechanical dynamical spectrum of polyester networks. *Journal of Polymer Science Part B: Polymer Physics* 39: 146-152.
- Vilay, V., Mariatti, M., Mat Taib, R. and Todo, M. 2008. Effect of fiber surface treatment and fiber loading on the properties of bagasse fiber-reinforced unsaturated polyester composites. *Composites Science and Technology* 68: 631-638.
- Wambua, P., Ivens, J. and Verpoest, I. 2003. Natural fibres: can they replace glass in fibre reinforced plastics?. *Composites Science and Technology* 63: 1259-1264.
- Watkins, D., Nuruddin, M., Hosur, M., Tcherbi-Narteh, A. and Jeelani, S. 2015. Extraction and characterization of lignin from different biomass resources. *Journal of Materials Research and Technology* 4: 26-32.
- Willis, M.R. and Masters, I. 2003. The effect of filler loading and process route on the three-point bend performance of waste based composites. *Composite Structures* 62: 475-479.
- Wise, L.E., Murphy, M. and Addiecs, A.A.D. 1963. Chlorite holocellulose, its fractionation and bearing on summative wood analysis and on studies on the hemicelluloses. *Paper Trade Journal* 122: 35.

- Wong, K.J., Yousif, B.F. and Low, K.O. 2010. The effects of alkali treatment on the interfacial adhesion of bamboo fibres. *Proceedings of the Institution of Mechanical Engineers, Part L: Journal of Materials: Design and Applications* 224: 139-148.
- Yahaya, R., Sapuan, S.M., Jawaidd, M., Leman, Z. and Zainudin, E.S. 2015. Effect of layering sequence and chemical treatment on the mechanical properties of woven kenaf–aramid hybrid laminated composites. *Materials & Design* 67: 173-179.
- Yang, H., Yan, R., Chen, H., Lee, D.H. and Zheng, C. 2007. Characteristics of hemicellulose, cellulose and lignin pyrolysis. *Fuel* 86: 1781-1788.
- Yussuf, A.A., Massoumi, I. and Hassan, A. 2010. Comparison of polylactic acid/kenaf and polylactic acid/rise husk composites: the influence of the natural fibers on the mechanical, thermal and biodegradability properties. *Journal of Polymers and the Environment* 18: 422-429.
- Yusra, A.I., Khalil, H.A., Hossain, M.S., Davoudpour, Y., Astimar, A.A., Zaidon, A., Dungani, R. and Omar, A.M. 2015. Characterization of plant nanofiber-reinforced epoxy composites. *BioResources* 10: 8268-8280.
- Zaidi, B.M., Magniez, K. and Miao, M. 2015. Prestressed natural fibre spun yarn reinforced polymer-matrix composites. *Composites Part A: Applied Science and Manufacturing* 75: 68-76.
- Zaihan, J., Rafeadah, R., Hashim, W.S. and Nasir, M. 2017. Development of high strength green nanocomposites reinforced with nanocrystalline cellulose and epoxy resin polymer. Paper presented at the Wood and Biofiber International Conference (WOBIC), Hotel Bangi Putrajaya, Selangor, Malaysia.
- Zhang, L. and Miao, M. 2010. Commingled natural fibre/polypropylene wrap spun yarns for structured thermoplastic composites. *Composites Science and Technology* 70: 130-135.
- Zhong, L.X., Fu, S.Y., Zhou, X.S. and Zhan, H.Y. 2011. Effect of surface microfibrillation of sisal fibre on the mechanical properties of sisal/aramid fibre hybrid composites. *Composites Part A: Applied Science and Manufacturing* 42: 244-252.
- Zhou, Y.M., Fu, S.Y., Zheng, L.M. and Zhan, H.Y. 2012. Effect of nanocellulose isolation techniques on the formation of reinforced poly (vinyl alcohol) nanocomposite films. *Express Polymer Letters* 6: 794-804.
- Zin, M.H., Abdan, K., Mazlan, N., Zainudin, E.S. and Liew, K.E. 2018. The effects of alkali treatment on the mechanical and chemical properties of pineapple leaf fibres (PALF) and adhesion to epoxy resin. *In IOP Conference Series: Materials Science and Engineering* 368: 012035.

Zini, E. and Scandola, M. 2011. Green composites: an overview. *Polymer composites* 32: 1905-1915.

