



**UNIVERSITI PUTRA MALAYSIA**

***PHYSICAL, STRUCTURAL AND OPTICAL PROPERTIES OF  
WILLEMITE-BASED GLASS-CERAMIC DOPED WITH  
MANGANESE OXIDE***

**MOHD HAFIZ BIN MOHD ZAID**

**FS 2016 5**



**PHYSICAL, STRUCTURAL AND OPTICAL PROPERTIES OF  
WILLEMITE-BASED GLASS-CERAMIC DOPED WITH  
MANGANESE OXIDE**

**By**

**MOHD HAFIZ BIN MOHD ZAID**

**Thesis submitted to the School of Graduate Studies, Universiti Putra  
Malaysia, in Fulfilment of the Requirements for the Degree of  
Doctor of Philosophy**

**May 2016**

## COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Dedicated to

To my beloved parents Mohd Zaid bin A. Bakar and Kamsiah binti Mustaffa  
For their unconditional love and support

To my siblings and family  
For making my life complete

To my beautiful wife Nurzia binti Mohamad and her family  
For their love and care

To all my very wonderful friends  
For making my life full of joy and happiness

To all my lecturers  
For helping me at a lot throughout this journey

Thank you all

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment  
of the requirement for the degree of Doctor of Philosophy

**PHYSICAL, STRUCTURAL AND OPTICAL PROPERTIES OF  
WILLEMITE-BASED GLASS-CERAMIC DOPED WITH  
MANGANESE OXIDE**

By

**MOHD HAFIZ BIN MOHD ZAID**

**May 2016**

**Chairman: Assoc. Prof. Khamirul Amin bin Matori, PhD**  
**Faculty: Science**

Over the last few decades, great deals of interest have been focused on the fabrication and synthesizing willemite based ceramic. However, only few of them used waste materials to fabricate the willemite in form of glass-ceramic. This research was carried out based on several objectives such as to synthesis and study the effect of ZnO addition on the physical, structure and optical properties of soda lime silica (SLS) glass system. Besides, this work also investigation the effect of various heat treatment temperatures on the physical, structure and optical of precursor glass and glass-ceramics and the influence of MnO doping on the physical, structure and optical properties of willemite based glass-ceramics. Thus, in this study, willemite based glass-ceramics were fabricate and synthesized using SLS glass waste as a source of silicon. A series of precursor glasses in the ZnO-SLS glass system was prepared by the conventional melt-quench technique. Willemite based glass-ceramics were derived from the selected precursor ZnO-SLS glass by a controlled crystallization process. The thermal, chemical and physical properties of precursor glass and glass-ceramics were measured by differential thermal analysis (DTA), energy dispersive X-ray fluorescence (EDXRF), average density and linear shrinkage measurement. The average density and linear shrinkage of glass and glass-ceramic samples were found increased with increasing of heat treatment temperature and concentration of dopant. Besides, the structural properties of precursor glass and formation of willemite crystal phase, morphology and size with increase in heat-treatment temperatures was examined by X-ray diffraction (XRD) and field-emission scanning electron microscopy (FESEM) techniques. The average calculated crystallite size obtained from XRD was found to be in the range 30-60 nm whereas the grain size observed in FESEM was 300-700 nm. Fourier transform infrared (FTIR) reflection spectroscopy was used to evaluate the structural of glass and glass-ceramics. The appearance of SiO<sub>2</sub>, ZnO<sub>4</sub> and Zn-O-Si bands detected from FTIR measurements indicate that the formation of willemite crystal phase. The study of the optical band gap has found that optical band gap of glass and glass-ceramics decreased as the percentage of dopant and heat treatment temperature increased. The

photoluminescence spectra of  $\text{Mn}^{2+}$  ions exhibit emission transitions of  ${}^4\text{T}_1(\text{G}) - {}^6\text{A}_1(\text{S})$  and its excitation spectra show an intense absorption band at 260 nm. Prominent green emission colors of  $\alpha\text{-Zn}_2\text{SiO}_4$  phase were observed centered at 525 nm while the yellow emission centered at 585 nm resulted from  $\beta\text{-Zn}_2\text{SiO}_4$  phase. These spectra reveal that the luminescence performance of the glass-ceramics is increase with the progression of dopant percentage and heat treatment temperatures. This enhancement is caused by partitioning of  $\text{Mn}^{2+}$  ions into the willemite crystals with progress of heat treatment temperatures. Such luminescent glass-ceramics are expected to find potential applications in phosphors and opto-electronic devices.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**SIFAT FIZIKAL, STRUKTUR DAN OPTIKAL WILLEMITE-ASAS KACA-SERAMIK DOP BERSAMA MANGAN OKSIDA**

Oleh

**MOHD HAFIZ BIN MOHD ZAID**

**Mei 2016**

**Pengerusi: Prof. Madya Khamirul Amin bin Matori, PhD.**

**Fakulti: Sains**

Sejak beberapa dekad yang lalu, penghasilan dan kajian terhadap willemite berasaskan seramik telah berjaya menarik minat dan tumpuan ramai penyelidik. Walau bagaimanapun, penyelidikan untuk menghasilkan willemite dalam bentuk kaca-seramik dengan menggunakan bahan asas dari bahan-bahan buangan adalah sangat sedikit dan terhad. Kajian ini dijalankan berdasarkan beberapa objektif seperti untuk sintesis dan mengkaji kesan penambahan ZnO pada fizikal, struktur dan ciri-ciri optik sistem kaca SLS. Selain itu, kerja-kerja ini juga penyiasatan kesan pelbagai suhu rawatan haba ke atas fizikal, struktur dan optik kaca pelopor dan kaca seramik dan pengaruh MnO dopan pada fizikal, struktur dan sifat optik willemite berasaskan kaca seramik. Oleh yang demikian, dalam kajian ini, willemite berasaskan kaca-seramik telah dihasilkan dengan menggunakan sisa kaca soda lime silika (SLS) sebagai sumber silikon dan beberapa kajian terhadap sifat-sifat willemite dalam bentuk kaca-seramik telah dijalankan. Beberapa siri kaca berasaskan sistem ZnO-SLS telah dihasilkan dengan menggunakan teknik teknik lindapan leburan. Willemite berasaskan kaca-seramik telah berjaya dihasilkan daripada kaca yang dipilih daripada siri kaca ZnO-SLS melalui proses penghabluran yang dikawal. Sifat haba, kimia dan fizikal kaca dan kaca-seramik telah diukur menggunakan alat DTA, EDXRF, purata ketumpatan dan pengukuran pengecutan linear. Didapati, purata ketumpatan dan pengecutan linear kaca dan kaca-seramik telah meningkat disebabkan oleh peningkatan suhu rawatan haba dan kepekatan dopan. Selain itu, sifat-sifat struktur kaca dan pembentukan fasa, morfologi dan saiz kristal willemite dengan peningkatan suhu rawatan haba telah diperiksa dengan menggunakan alat XRD dan FESEM. Didapati, purata saiz kristal yang diperolehi daripada XRD adalah dalam julat 30-60 nm manakala saiz butiran yang diperhatikan menggunakan FESEM adalah dalam julat 300-700 nm. FTIR spektroskopi telah digunakan untuk menilai struktur kaca dan kaca-seramik. Kemunculan dan penghasilan ikatan SiO<sub>2</sub>, ZnO<sub>4</sub> dan Zn-O-Si yang dikesan dari alat FTIR telah menunjukkan bahawa pembentukan kristal willemite telah berlaku. Kajian ke atas jurang jalur optik telah mendapati bahawa jumlah jurang jalur optik kaca dan kaca-seramik telah menurun disebabkan peningkatan peratusan dopan dan suhu rawatan haba. Selain itu,

spektrum kefotopendarcaayaan daripada peralihan  $Mn^{2+}$  ion daripada  ${}^4T_1(G) - {}^6A_1(S)$  dan spektrum pengujian yang menunjukkan satu jalur penyerapan pada jarak 260 nm. Warna hijau yang terhasil daripada fasa  $\alpha$ - $Zn_2SiO_4$  diperhatikan berpusat pada 525 nm manakala warna kuning berpusat pada 585 nm yang terhasil daripada fasa  $\beta$ - $Zn_2SiO_4$ . Spektrum ini telah mendedahkan bahawa prestasi kependarkilauan daripada kaca-seramik telah meningkat disebabkan peningkatan dalam peratusan dopan dan suhu rawatan haba. Peningkatan ini adalah disebabkan oleh pembahagian ion  $Mn^{2+}$  ke dalam kristal willemite dengan peningkatan suhu rawatan haba. Penghasilan kaca-seramik ini dijangka berpotensi untuk diaplikasikan ke dalam bahan fosfor dan peranti opto-elektronik.





## ACKNOWLEDGEMENTS

In the name of Allah S.W.T, the Most Gracious and Most Merciful. I am very grateful to Allah for the blessing to be able to complete my thesis.

Special appreciation goes to my supervisor, Assoc. Prof. Dr. Khamirul Amin Matori, for his supervision and constant support. His invaluable help of constructive comments and suggestions throughout the experimental and thesis works have contributed to the success of this research.

Not forgotten, my appreciation to the committee members Prof. Dr. Sidek Hj. Abdul Aziz, Prof. Dr. W. Mahmood Mat Yunus and Assoc. Prof. Dr. Halimah Mohamed Kamari for the support and guidance regarding this topic. Humble appreciation also goes to all the staff and technicians of the Faculty of Science and Institute of Advanced Technology Universiti Putra Malaysia for the co-operation and technical support provided.

Sincere thanks to all members of Glass, Ceramic, Composite and Metal (GCCM) Laboratory for their helps and moral supports upon the completion of my project.

Last but not least, my deepest gratitude goes to my parents, Mr. Mohd Zaid Bin A. Bakar and Mrs. Kamsiah Binti Mustaffa for their endless love, prayers and encouragement.

May Allah bless all of the people for giving me the utmost support in completion of this research.

I certify that a Thesis Examination Committee has met on 17 May 2016 to conduct the final examination of Mohd Hafiz bin Mohd Zaid on his thesis entitled "Physical, Structural and Optical Properties of Willemite-Based Glass-Ceramic Doped with Manganese Oxide" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

**Zainal Abidin b Talib, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Chairman)

**Azmi b Zakaria, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Internal Examiner)

**Zaidan b Abdul Wahab, PhD**

Associate Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Internal Examiner)

**Raouf Abdle Hamid El-Mallawany, PhD**

Professor  
Menofia University  
Egypt  
(External Examiner)



---

**ZULKARNAIN ZAINAL, PhD**

Professor and Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 26 July 2016

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

**Khamirul Amin bin Matori, PhD**

Associate Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Chairman)

**Sidek bin Ab Aziz, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**W. Mahmood bin Mat Yunus, PhD**

Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

**Halimah Mohamed binti Kamari, PhD**

Associate Professor  
Faculty of Science  
Universiti Putra Malaysia  
(Member)

---

**BUJANG KIM HUAT, PhD**

Professor and Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: \_\_\_\_\_ Date: \_\_\_\_\_

Name and Matric No.: Mohd Hafiz bin Mohd Zaid, (GS33760)

## Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: \_\_\_\_\_

  
Name of  
Chairman of  
Supervisory Committee:  
Khamirul Amin bin Maton, PhD

Signature: \_\_\_\_\_

Name of  
Member of  
Supervisory Committee:  
W. Mahmood bin Mat Yunus, PhD

Signature: \_\_\_\_\_

Name of  
Member of  
Supervisory Committee:  
Sidek bin Ab Aziz, PhD

Signature: \_\_\_\_\_

Name of  
Member of  
Supervisory Committee:  
Halimah binti Mohamed Kamari, PhD

## TABLE OF CONTENTS

<b>ABSTRACT</b>	<b>Page</b>
<b>ABSTRAK</b>	i
<b>ACKNOWLEDGEMENTS</b>	iii
<b>APPROVAL</b>	v
<b>DECLARATION</b>	vi
<b>LIST OF TABLES</b>	viii
<b>LIST OF FIGURES</b>	xiii
<b>LIST OF ABBREVIATIONS</b>	xv
	xxiii

### CHAPTER

<b>1</b>	<b>INTRODUCTION</b>	
	1.1 Research background	1
	1.2 Problem statement	3
	1.3 Research objective	4
	1.4 Scope of the study	4
	1.5 Importance of the study	5
	1.6 Outline of thesis	5
<b>2</b>	<b>LITERATURE REVIEW</b>	
	2.1 Introduction	6
	2.1.1 Glass waste	6
	2.1.2 Soda lime silica glass	7
	2.1.3 Glass-ceramics from waste	9
	2.1.4 MnO dopant	9
	2.1.5 Phase equilibrium	10
	2.2 Glass	13
	2.2.1 Glass formation	13
	2.2.2 Oxide Glasses	15
	2.2.3 Glass crystallization and phase transformation	18
	2.3 Glass-Ceramic	21
	2.3.1 Glass-ceramic processing	22
	2.3.2 Doping process	23
	2.4 Willemite	24
	2.4.1 $\alpha$ -phase willemite	25
	2.4.2 $\beta$ -phase willemite	26
	2.4.3 $\gamma$ -phase willemite	27
	2.4.4 Manganese doped willemite	27
	2.5 Physical Studies	29
	2.5.1 Chemical composition	29
	2.5.2 Linear shrinkage	30
	2.5.3 Density	30
	2.6 Structural Studies	32
	2.6.1 Phase structure	32
	2.6.2 Microstructure	34
	2.6.3 Chemical bonding	35
	2.7 Optical Studies	36

	2.7.1	Optical absorbance	37
	2.7.2	Optical band gap	37
	2.7.3	Photoluminescent	39
<b>3</b>		<b>METHODOLOGY</b>	
	3.1	Introduction	42
	3.2	Precursor glass preparation	42
	3.2.1	Weighing, mixing and milling process	44
	3.2.2	Glass melt-quenching technique	44
	3.2.3	Pelleting process	44
	3.2.4	Heat treatment process	45
	3.2.5	Doping process	45
	3.3	Energy dispersive X-ray fluorescence measurement	46
	3.4	Differential thermal analysis	47
	3.5	Linear shrinkage measurement	47
	3.6	Average density measurement	47
	3.7	X-Ray diffraction measurement	48
	3.8	Field emission scanning electron microscopy	50
	3.9	Fourier transforms infrared spectroscopy	50
	3.10	UV-Visible spectroscopy	51
	3.11	Photoluminescence spectrometer	52
<b>4</b>		<b>RESULTS AND DISCUSSION</b>	
	4.1	Introduction	54
	4.2	Precursor glass analysis	54
	4.2.1	Chemical composition of glasses	54
	4.2.1.1	EDXRF analysis	54
	4.2.2	Thermal properties of glasses	59
	4.2.2.1	DTA analysis	59
	4.2.3	Physical properties of glasses	59
	4.2.3.1	Density of glasses	59
	4.2.4	Structural properties of glasses	61
	4.2.4.1	XRD analysis	61
	4.2.4.2	FESEM analysis	62
	4.2.4.3	FTIR analysis	63
	4.2.5	Optical properties of glasses	66
	4.2.5.1	UV-Visible analysis	66
	4.2.5.2	Optical band gap analysis	67
	4.3	Glass-ceramic analysis	70
	4.3.1	Physical properties of glass-ceramic	70
	4.3.1.1	Density analysis	70
	4.3.1.2	Linear shrinkage analysis	72
	4.3.2	Structural properties of glass-ceramic	73
	4.3.2.1	XRD analysis	73
	4.3.2.2	FESEM analysis	76
	4.3.2.3	FTIR analysis	79
	4.3.3	Optical properties of glass-ceramic	81
	4.3.3.1	UV-Visible analysis	81
	4.3.3.2	Optical band gap analysis	82
	4.3.3.3	Photoluminescent analysis	86



4.4	Mn-doped willemite analysis	87
4.4.1	Physical properties of Mn-doped willemite	87
4.4.1.1	Density analysis	87
4.4.1.2	Linear shrinkage analysis	88
4.4.2	Structural properties of Mn-doped willemite	90
4.4.2.1	XRD analysis	90
4.4.2.2	FESEM analysis	94
4.4.2.3	FTIR analysis	115
4.4.3	Optical properties of Mn-doped willemite	119
4.4.3.1	UV-Visible analysis	119
4.4.3.2	Optical band gap analysis	122
4.4.3.3	Photoluminescent analysis	133
<b>5</b>	<b>CONCLUSION AND RECOMMENDATIONS</b>	
5.1	Introduction	137
5.2	Conclusion	137
5.3	Recommendations for Future Research	138
	<b>REFERENCES</b>	139
	<b>BIODATA OF STUDENT</b>	155
	<b>LIST OF PUBLICATIONS</b>	156



## LIST OF TABLES

Table		Page
2.1	Chemical composition of commercial SLS glasses	8
3.1	Chemical composition of ZnO-SLS based glass.	42
3.2	Chemical composition of Mn-doped willemite glass-ceramics.	45
4.1	Chemical composition of ZnO-SLS glass system (wt.%)	55
4.2	FTIR absorption bands and band assignment of ZnO-SiO <sub>2</sub> glasses	63
4.3	FTIR spectra band position of ZnO-SLS glass system	65
4.4	Variation of $E_{opt}$ for precursor ZnO-SLS glass system	68
4.5	The average crystallite size of 50ZnO50SLS glass and glass-ceramics at various heat treatment temperatures	75
4.6	Average grain size of precursor 50ZnO50SLS glass samples at various heat treatment temperatures	79
4.7	IR transmittance bands and band assignment of precursor 50ZnO50SLS glass and glass-ceramics after heat treatment process.	80
4.8	Variation of $E_{opt}$ for precursor 50ZnO50SLS glass and glass-ceramic samples at various heat treatment temperatures	83
4.9	Average density of Mn-doped willemite glass-ceramics at various heat treatment temperatures.	88
4.10	Linear shrinkage of Mn-doped willemite glass-ceramics at various heat treatment temperatures.	89
4.11	The average crystallite size of Mn-doped willemite glass-ceramics at various heat treatment temperatures.	93
4.12	Average grain size of Mn-doped willemite glass-ceramics at various heat treatment temperatures.	115
4.13	IR transmittance bands and band assignment of Mn-doped willemite glass-ceramics at various heat treatment temperatures.	118
4.14	Variation of $E_{opt}$ for 1 wt.% Mn-doped willemite glass-ceramic samples at various heat treatment temperatures.	125
4.15	Variation of $E_{opt}$ for 2 wt.% Mn-doped willemite glass-ceramic	125

samples at various heat treatment temperatures.

- |      |  |     |
|------|--|-----|
| 4.16 | Variation of $E_{opt}$ for 3 wt.% Mn-doped willemite glass-ceramic samples at various heat treatment temperatures. | 126 |
| 4.17 | Variation of $E_{opt}$ for 4 wt.% Mn-doped willemite glass-ceramic samples at various heat treatment temperatures. | 126 |
| 4.18 | Variation of $E_{opt}$ for 5 wt.% Mn-doped willemite glass-ceramic samples at various heat treatment temperatures. | 127 |



## LIST OF FIGURES

Figure		Page
2.1	Schematic diagram of glass container production process and recycle.	7
2.2	Binary phase diagrams (a) $\text{Na}_2\text{O}-\text{SiO}_2$ , (b) $\text{Na}_2\text{O}-\text{Al}_2\text{O}_3$ , (c) $\text{Al}_2\text{O}_3-\text{SiO}_2$ and (d) $\text{K}_2\text{O}-\text{SiO}_2$ .	11
2.3	Binary phase diagram of $\text{ZnO}-\text{SiO}_2$ system.	12
2.4	The volume-temperature diagram for a glass forming liquid	14
2.5	Schematic diagram of two-dimensional structure of (a) a crystalline compound $\text{A}_2\text{O}_3$ and (b) vitreous compound $\text{A}_2\text{O}_3$	16
2.6	Two-dimensional diagram of the structure of a $\text{Na}_2\text{O}-\text{SiO}_2$ glass	18
2.7	Schematic phase transformation of glass-ceramic	19
2.8	A schematic diagram of the effect of composition on free energy for a binary immiscible system	20
2.9	Schematic representation of phase separation via a) spinodal decomposition and b) nucleation and growth	21
2.10	Schematic diagram of two-stage heat-treatment process.	23
2.11	The microstructure of willemite ore	25
2.12	Crystalline structure of $\alpha\text{-Zn}_2\text{SiO}_4$	26
2.13	Emission peaks and ionic radii of guest ions for $\text{Zn}_2\text{SiO}_4$ host crystals	39
2.14	Energy level scheme describing the green color emission process in $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$	41
3.1	Schematic diagram of glass and glass-ceramics production	43
3.2	Diagram of constructive interference of diffracted wavelength	49
3.3	Schematic diagram of Interferometer	51
4.1	Chemical composition of SLS glass sample	56

4.2	Chemical composition of 10ZnO90SLS glass sample	56
4.3	Chemical composition of 20ZnO80SLS glass sample	57
4.4	Chemical composition of 30ZnO70SLS glass sample	57
4.5	Chemical composition of 40ZnO60SLS glass sample	58
4.6	Chemical composition of 50ZnO50SLS glass sample	58
4.7	DTA curves of precursor ZnO-SLS glass system	59
4.8	The average density of ZnO-SLS glass system	60
4.9	X-ray diffraction pattern of ZnO-SLS glass system.	61
4.10	FESEM micrograph of precursor ZnO-SLS glass system	62
4.11	FTIR spectra of precursor ZnO-SLS glass system	65
4.12	Optical absorption spectra of precursor ZnO-SLS glass system.	66
4.13	Plot of extinction coefficient vs. $(h\nu)$ for precursor ZnO-SLS glass system	67
4.14	$(\alpha h\nu)^{2/3}$ as a function of energy for $(h\nu)$ precursor ZnO-SLS glass system.	69
4.15	Compositional dependence of experimental optical band gap and optical band gap of ZnO-SLS glass system from Mott and Davis Model for $n = 3/2$ transition	70
4.16	The density of precursor 50ZnO50SLS glass and glass-ceramics at various heat treatment temperatures	71
4.17	The linear shrinkage of precursor 50ZnO50SLS glass and glass-ceramics at various heat treatment temperatures	72
4.18	X-ray diffraction pattern of precursor 50ZnO50SLS glass and glass-ceramics at various heat treatment temperatures	75
4.19	FESEM micrographs of precursor 50ZnO50SLS glass and glass-ceramic samples treated at (a) 27 °C (b) 600 °C (c) 700 °C (d) 800 °C (e) 900 °C and (f) 1000 °C for 2 hours duration.	76
4.20	Grain size distribution of precursor 50ZnO50SLS glass sample heat treated at 700 °C	77

4.21	Grain size distribution of precursor 50ZnO50SLS glass sample heat treated at 800 °C	78
4.22	Grain size distribution of precursor 50ZnO50SLS glass sample heat treated at 900 °C	78
4.23	Grain size distribution of precursor 50ZnO50SLS glass sample heat treated at 1000 °C	79
4.24	Fourier transform infrared spectra of precursor 50ZnO50SLS glass and glass-ceramics at various heat treatment temperatures	81
4.25	Optical absorption edge of precursor 50ZnO50SLS glass and glass-ceramic samples at various heat treatment temperatures	82
4.26	Plot of extinction coefficient vs. $h\nu$ for precursor 50ZnO50SLS glass and glass-ceramic samples at various heat treatment temperatures	83
4.27	$(ah\nu)^{2/3}$ as a function of energy for $h\nu$ precursor 50ZnO50SLS glass and glass-ceramic samples at various heat treatment temperatures	85
4.28	Compositional dependence of experimental optical band gap and optical band gap from Mott and Davis Model for $n = 3/2$ transition	85
4.29	Excitation and emission spectra of precursor 50ZnO50SLS glass and glass-ceramic samples at various heat treatment temperatures	86
4.30	The density of Mn-doped willemite glass-ceramics against various heat treatment temperatures	88
4.31	The linear shrinkage of Mn-doped willemite glass-ceramics against various heat treatment temperatures	89
4.32	X-ray diffraction pattern of 1 wt.% Mn-doped willemite glass-ceramics at various heat treatment temperatures	91
4.33	X-ray diffraction pattern of 2 wt.% Mn-doped willemite glass-ceramics at various heat treatment temperatures	91
4.34	X-ray diffraction pattern of 3 wt.% Mn-doped willemite glass-ceramics at various heat treatment temperatures	92
4.35	X-ray diffraction pattern of 4 wt.% Mn-doped willemite glass-ceramics at various heat treatment temperatures	92

4.36	X-ray diffraction pattern of 5 wt.% Mn-doped willemite glass-ceramics at various heat treatment temperatures	92
4.37	FESEM micrographs of 1 wt.% Mn-willemite glass-ceramic samples	95
4.38	FESEM micrographs of 2 wt.% Mn-willemite glass-ceramic samples	96
4.39	FESEM micrographs of 3 wt.% Mn-willemite glass-ceramic samples	97
4.40	FESEM micrographs of 4wt.% Mn-willemite glass-ceramic samples	98
4.41	FESEM micrographs of 5 wt.% Mn-willemite glass-ceramic samples	99
4.42	Grain size distribution of 1 wt.% Mn-doped willemite glass-ceramics heat treated at 27 °C for 2 hours.	100
4.43	Grain size distribution of 1 wt.% Mn-doped willemite glass-ceramics heat treated at 600 °C for 2 hours.	100
4.44	Grain size distribution of 1 wt.% Mn-doped willemite glass-ceramics heat treated at 700 °C for 2 hours.	101
4.45	Grain size distribution of 1 wt.% Mn-doped willemite glass-ceramics heat treated at 800 °C for 2 hours.	101
4.46	Grain size distribution of 1 wt.% Mn-doped willemite glass-ceramics heat treated at 900 °C for 2 hours.	102
4.47	Grain size distribution of 1 wt.% Mn-doped willemite glass-ceramics heat treated at 1000 °C for 2 hours	102
4.48	Grain size distribution of 2 wt.% Mn-doped willemite glass-ceramics heat treated at 27 °C for 2 hours	103
4.49	Grain size distribution of 2 wt.% Mn-doped willemite glass-ceramics heat treated at 600 °C for 2 hours	103
4.50	Grain size distribution of 2 wt.% Mn-doped willemite glass-ceramics heat treated at 700 °C for 2 hours	104
4.51	Grain size distribution of 2 wt.% Mn-doped willemite glass-ceramics heat treated at 800 °C for 2 hours.	104
4.52	Grain size distribution of 2 wt.% Mn-doped willemite glass-ceramics heat treated at 900 °C for 2 hours.	105

4.53	Grain size distribution of 2 wt.% Mn-doped willemite glass-ceramics heat treated at 1000 °C for 2 hours.	105
4.54	Grain size distribution of 3 wt.% Mn-doped willemite glass-ceramics heat treated at 27 °C for 2 hours.	106
4.55	Grain size distribution of 3 wt.% Mn-doped willemite glass-ceramics heat treated at 600 °C for 2 hours.	106
4.56	Grain size distribution of 3 wt.% Mn-doped willemite glass-ceramics heat treated at 700 °C for 2 hours.	107
4.57	Grain size distribution of 3 wt.% Mn-doped willemite glass-ceramics heat treated at 800 °C for 2 hours.	107
4.58	Grain size distribution of 3 wt.% Mn-doped willemite glass-ceramics heat treated at 900 °C for 2 hours.	108
4.59	Grain size distribution of 3 wt.% Mn-doped willemite glass-ceramics heat treated at 1000 °C for 2 hours.	108
4.60	Grain size distribution of 4 wt.% Mn-doped willemite glass-ceramics heat treated at 27 °C for 2 hours.	109
4.61	Grain size distribution of 4 wt.% Mn-doped willemite glass-ceramics heat treated at 600 °C for 2 hours.	109
4.62	Grain size distribution of 4 wt.% Mn-doped willemite glass-ceramics heat treated at 700 °C for 2 hours.	110
4.63	Grain size distribution of 4 wt.% Mn-doped willemite glass-ceramics heat treated at 800 °C for 2 hours.	110
4.64	Grain size distribution of 4 wt.% Mn-doped willemite glass-ceramics heat treated at 900 °C for 2 hours.	111
4.65	Grain size distribution of 4 wt.% Mn-doped willemite glass-ceramics heat treated at 1000 °C for 2 hours.	111
4.66	Grain size distribution of 5 wt.% Mn-doped willemite glass-ceramics heat treated at 27 °C for 2 hours.	112
4.67	Grain size distribution of 5 wt.% Mn-doped willemite glass-ceramics heat treated at 600 °C for 2 hours.	112
4.68	Grain size distribution of 5 wt.% Mn-doped willemite glass-ceramics heat treated at 700 °C for 2 hours.	113
4.69	Grain size distribution of 5 wt.% Mn-doped willemite glass-ceramics heat treated at 800 °C for 2 hours.	113



4.70	Grain size distribution of 5 wt.% Mn-doped willemite glass-ceramics heat treated at 900 °C for 2 hours.	114
4.71	Grain size distribution of 5 wt.% Mn-doped willemite glass-ceramics heat treated at 1000 °C for 2 hours.	114
4.72	Fourier transform infrared spectra of 1 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	116
4.73	Fourier transform infrared spectra of 2 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	116
4.74	Fourier transform infrared spectra of 3 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	117
4.75	Fourier transform infrared spectra of 4 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	117
4.76	Fourier transform infrared spectra of 5 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	118
4.77	Optical absorption edge of 1 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	119
4.78	Optical absorption edge of 2 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	120
4.79	Optical absorption edge of 3 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	120
4.80	Optical absorption edge of 4 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	121
4.81	Optical absorption edge of 5 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures.	121
4.82	Plot of extinction coefficient vs. $h\nu$ for 1 wt. % Mn-doped willemite glass ceramics at various heat treatment temperatures	122
4.83	Plot of extinction coefficient vs. $h\nu$ for 2 wt. % Mn-doped willemite glass ceramics at various heat treatment temperatures	123
4.84	Plot of extinction coefficient vs. $h\nu$ for 3 wt. % Mn-doped willemite glass ceramics at various heat treatment	123



	temperatures	
4.85	Plot of extinction coefficient vs. $h\nu$ for 4 wt. % Mn-doped willemite glass ceramics at various heat treatment temperatures	124
4.86	Plot of extinction coefficient vs. $h\nu$ for 5 wt. % Mn-doped willemite glass ceramics at various heat treatment temperatures	124
4.87	$(\alpha h\nu)^{2/3}$ as a function of photon energy $h\nu$ for 1 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures	128
4.88	$(\alpha h\nu)^{2/3}$ as a function of photon energy $h\nu$ for 2 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures	128
4.89	$(\alpha h\nu)^{2/3}$ as a function of photon energy $h\nu$ for 3 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures	129
4.90	$(\alpha h\nu)^{2/3}$ as a function of photon energy $h\nu$ for 4 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures	129
4.91	$(\alpha h\nu)^{2/3}$ as a function of photon energy $h\nu$ for 5 wt. % Mn-doped willemite glass-ceramics at various heat treatment temperatures	130
4.92	Compositional dependence of experimental optical band gap and optical band gap for 1 wt. % Mn-doped willemite glass-ceramics from Mott and Davis Model for $n = 3/2$ transition	130
4.93	Compositional dependence of experimental optical band gap and optical band gap for 2 wt. % Mn-doped willemite glass-ceramics from Mott and Davis Model for $n = 3/2$ transition	131
4.94	Compositional dependence of experimental optical band gap and optical band gap for 3 wt. % Mn-doped willemite glass-ceramics from Mott and Davis Model for $n = 3/2$ transition	131
4.95	Compositional dependence of experimental optical band gap and optical band gap for 4 wt. % Mn-doped willemite glass-ceramics from Mott and Davis Model for $n = 3/2$ transition	132
4.96	Compositional dependence of experimental optical band gap and optical band gap for 5 wt. % Mn-doped willemite glass-ceramics from Mott and Davis Model for $n = 3/2$ transition	132
4.97	Excitation and emission spectra of 1% Mn-doped $Zn_2SiO_4$ at various heat treatment temperatures	134

4.98	Excitation and emission spectra of 2% Mn-doped Zn <sub>2</sub> SiO <sub>4</sub> at various heat treatment temperatures	134
4.99	Excitation and emission spectra of 3% Mn-doped Zn <sub>2</sub> SiO <sub>4</sub> at various heat treatment temperatures	135
4.100	Excitation and emission spectra of 4% Mn-doped Zn <sub>2</sub> SiO <sub>4</sub> at various heat treatment temperatures	135
4.101	Excitation and emission spectra of 5% Mn-doped Zn <sub>2</sub> SiO <sub>4</sub> at various heat treatment temperatures	136



## LIST OF ABBREVIATIONS

Zn <sub>2</sub> SiO <sub>4</sub>	Willemite
Zn <sub>2</sub> SiO <sub>4</sub> :Mn <sup>2+</sup>	Willemite doped Manganese Oxide
Mn	Manganese
Eu	Europium
Co	Cobalt
Ni	Nickel
UV	Ultraviolet
SLS	Soda lime silica
SiO <sub>2</sub>	Silica oxide
ZnO	Zinc oxide
MnO	Manganese oxide
CaO	Calcium oxide
Na <sub>2</sub> O	Sodium oxide
Al <sub>2</sub> O <sub>3</sub>	Aluminium oxide
K <sub>2</sub> O	Potassium oxide
MgO	Magnesium oxide
Fe <sub>2</sub> O <sub>3</sub>	Ferric oxide
B <sub>2</sub> O <sub>3</sub>	Boron trioxide
BaO	Barium oxide
MnCO <sub>3</sub>	Manganese carbonate
ZnCl <sub>2</sub>	Zinc chloride
Na <sub>2</sub> SiO <sub>3</sub>	Sodium silicate
MnC <sub>2</sub> O <sub>4</sub>	Manganese oxalate
MnCl <sub>2</sub>	Manganese (II) chloride
α	Alpha phase
β	Beta phase
γ	Gamma phase
PVA	Polyvinyl alcohol
EDXRF	Energy dispersive X-ray fluorescence
XRD	X-Ray diffraction
FTIR	Fourier transform infrared
FESEM	Field emission scanning electron microscopy
UV-Vis	Ultraviolet-Visible
PL	Photoluminescence
<i>E</i> <sub>opt</sub>	Optical band gap
JCPDS	Joint committee on powder diffraction standards
NBO	Non-bridging oxygen

# CHAPTER 1

## INTRODUCTION

### 1.1 Research background

Manufacturing industry has played an important role for economic progress for the past decades. This industrial continues to maintain as the main sector for the development and economic growth. However, the fast change in industrial development generates enormous amount of waste disposal such as plastic, steel, paper, glass and others. This signaled the essential for a method to solve the waste problem through the solid waste management.

The existing of solid waste management system in Malaysia for municipal and industrial wastes gives a priority and promotes the consumption of recycle, treatment and disposal method such as composting, sanitary landfill or incineration (Victor and Agamuthu, 2013; Moh and Manaf, 2014). Nevertheless, this approach has been found creating many environmental problems such as illegal dumping, leaving large quantities of residues waste and the necessity for new land for the establishment of disposal facilities (Kadir *et al.*, 2013; Teo *et al.*, 2014; Zen *et al.*, 2014).

The vitrification process has been known as one of promising method to solve the solid waste problems and it has been applied for the stabilization of a variety of municipal, industrial, commercial and construction waste (Kavouras *et al.*, 2003). Besides, the vitrification process commonly results in a reduction of solid waste in large volume; benefits in terms of storage land or dumping site. Vitrification process is considered as an important technology for the treatment and remediation of non-combustible waste for the disposal of solid waste (Ponsot *et al.*, 2015).

Recently, upcycling the solid waste into more valuable and environment friendly products is a new focus across the world. This situation is comparable with the increasing demand especially for limited natural resource. Glass is an interesting material due to its various applications and widely used in optics such as data transmission, sensor detection, technology of sensor, and it is believed the best material for solid-state lasers (Prakash *et al.*, 2001; Ehrt, 2004; Zhou *et al.*, 2007; Hager *et al.*, 2011; Karaksina *et al.*, 2013).

Glass containing zinc oxide (ZnO) is one of the most preferred glass materials due to their good mechanical properties and low softening point compared with other glass systems (Yousef *et al.*, 2007; Abo-Mosallam *et al.*, 2010). This type of glass is a promising optical host material in solid-state laser when doped with transition metal and rare earth ions because this glass exhibits high transparency from UV to IR region, low refractive index and thermal expansion coefficient with high thermal

stability and possibility of incorporating large number of dopant ions (Rosmawati *et al.*, 2008; Yu *et al.*, 2008; Kim *et al.*, 2009; Hou *et al.*, 2014).

The conversion of waste glasses into glass-ceramics has gradually become an important method to improve the recycling of solid wastes into value-added materials (Boccaccini *et al.*, 1997). Glass with a suitable chemical composition can be transformed into glass-ceramics through the controlled heat treatment process (Barbieri *et al.*, 2000; Rawlings *et al.*, 2006; Salman *et al.*, 2015). Soda lime silica (SLS) glass is the most prevalent type of glasses and commonly used for window glass panes and glass containers (Clark *et al.*, 1976; Sehgal and Ito, 1998; Sheng *et al.*, 2002). SLS glass typically softens around 700 °C and this unique softening behaviour can influence the fabrication of glass-ceramic at temperatures lower than usually required to crystallize the glass-ceramic products (Zanotto, 1991; Pontikes *et al.*, 2007; Petrescu *et al.*, 2012; Marinoni *et al.*, 2013). Hence, the parent glass is transformed into a glass-ceramic in which the crystalline phase is bonded by the residual glass. Apart from that, glass-ceramics with a uniform fine-grain microstructure, non-porosity and wide range of properties can be tailored by altering the chemical composition (Karamanov *et al.*, 1999; El-Shennawi *et al.*, 2001; Hu *et al.*, 2005; Yekta *et al.*, 2007).

Zinc silicate ( $Zn_2SiO_4$ ) or also known by its mineral name willemite, is one of the zinc ore minerals with a phenakite structure. In the willemite structure, all the atoms occupy the overall position and composed of tetrahedral framework. With this kind of rigid lattice (non-centrosymmetric cationic sites), willemite provides special optical properties (Tarafder *et al.*, 2014). For this reason, willemite is very important and widely used as a phosphor in optic, opto-electronic and lighting devices (Xu *et al.*, 2010; Sivakumar *et al.*, 2012).

In addition, willemite is known as a suitable host matrix for numerous transition metal and rare-earth ions for high efficient luminescence (Takesue *et al.*, 2009; Choo *et al.*, 2010; Omri *et al.*, 2013). According to Takesue *et al.* (2009), the luminescent performance of the manganese doped willemite ( $Zn_2SiO_4:Mn^{2+}$ ) phosphors has been characterized by the transition of  $3d^5$  electron in the  $Mn^{2+}$  ion that acting as an activating center in the willemite structure. To be detailed, the transition from the lowest excited state,  $^4T_1(G)$  to the ground state  $^6A_1(S)$  transition is directly being responsible for the strong green emission under an ultraviolet light (Patra *et al.*, 2005; Hao and Wang, 2007; Lukic *et al.*, 2008; Seo *et al.*, 2009; Diao and Yang, 2010; Uegaito *et al.*, 2012; Park *et al.*, 2015).

In the current study, a series of zinc soda lime silica (ZnO-SLS) glasses are prepared from conventional melt-quenching technique and willemite based glass-ceramics are derived from these precursor glasses by a controlled heat treatment process. The properties of the precursor glass and willemite glass-ceramics have been characterized such as thermal, chemical, physical, structural, morphological and optical behaviour in order to study the effect of heat treatment temperature and MnO doping. The structural and optical properties of precursor glass and Mn-doped

willemite glass-ceramics have been studied by X-ray diffraction (XRD), field emission scanning electron microscopy (FESEM), Fourier transform infrared (FTIR), Uv-Visible (Uv-Vis) and photoluminescence (PL) spectroscopy. In view of above fact, the aim of this work is the fabrication and characterization of Mn-doped willemite glass-ceramics in ZnO-SLS glass system as a potential materials use in the field of opto-electronic as phosphor materials.

## 1.2 Problem statement

In recent years, glass and glass-ceramics doped with transition metal and rare earth ions are attracting prodigious interest in solid state lasers, phosphors, optical and lighting devices (Babu *et al.*, 2015). At present, researchers are aiming of using waste as starting material for producing willemite phosphor so that low energy processes and new technique may be developed. The conventional solid-state methods for commercial inorganic phosphors are completely established in industry. In this technique; pure raw materials such as ZnO and SiO<sub>2</sub> are well-mixed and fired at very high temperatures for several hours due to the high melting temperature of starting materials. To overcome high energy use problem, the productions of willemite using waste material such as glass waste as a silicon source are developed. Besides, there are limited reports and systematic study of physical, structure, and optical properties of precursor ZnO-SLS glass system and willemite based glass-ceramics.

Compared to several other conventional glass systems, SLS glass has drawn a great attention because of their superior glass forming nature (Abbasi and Hashemi, 2014). Furthermore, SLS glass also intriguing many researchers because of its excellent chemical, optical and mechanical properties such as low thermal expansion coefficient, nonlinear refractive index, fine chemical stability, high UV transparency, large tensile fracture strength and good durability for opto-electronic applications (Abo-Mosallam *et al.*, 2010; Chimalawong *et al.*, 2010; Marinoni *et al.*, 2013).

The transformation of glass into glass-ceramics has progressively become an important technique to improve the quality and properties of the final products. ZnO-SLS glasses are one of the most preferred parent glasses due to their improved mechanical properties and low softening temperature point compared with other glass systems (Shelby, 2005). This type of glass transformed into glass-ceramic with willemite as a main crystal phase. Willemite has a promising future in advanced materials as a favorably flexible luminescent material due to the broad range of multi-colors that can be obtained from various transition metal ions. Zn<sub>2</sub>SiO<sub>4</sub>:Mn<sup>2+</sup> has been used as a phosphor in fluorescent lamps, neon discharge lamps, oscilloscopes, black-and-white televisions, color televisions, and many other displays and lighting devices.

For that reasons, a comprehensive study of the crystallization, properties and effect of heat treatment on Mn-doped willemite glass-ceramics derived from precursor



ZnO-SLS glass system are carried out and the results of this research are expected to find potential application as phosphor material for opto-electronic devices.

### 1.3 Research objective

The main objective of this project is to develop and optimize willemite based glass-ceramics derived from ZnO-SLS glasses. This work involved design of suitable glass compositions, melt-quenching, development of heat treatment, progress of doping process and a series of fundamental studies of the crystallization process.

This research was carried out based on several objectives as in the following:

- 1) To synthesis and study the effect of ZnO addition on the physical, structure and optical properties of SLS glass system.
- 2) To investigate the effect of various heat treatment temperatures on the physical, structure and optical of precursor glass and glass-ceramics.
- 3) To analyze the influence of MnO doping on the physical, structure and optical properties of willemite based glass-ceramics.

### 1.4 Scope of the study

In order to achieve the objective of the study, the scopes of the study as follow:

- 1) A series of precursor glass based on the stoichiometric equation of  $x(\text{ZnO})100-x(\text{SLS})$  where  $x = 0, 10, 20, 30, 40$  and  $50$  wt.% has been prepared using SLS glass powder and ZnO powder by conventional melt-quenching technique.
- 2) The chemical composition of precursor ZnO-SLS glass system has been measured using EDXRF spectroscopy in order to confirm the oxide and percentage of chemical oxide in the glasses.
- 3) The glass transition temperature ( $T_g$ ) and glass crystallization temperature ( $T_c$ ) has been measured using DTA spectroscopy.
- 4) Willemite based glass-ceramics has been derived from the precursor ZnO-SLS glass system by a controlled crystallization process.
- 5) The physical, structural and optical properties of ZnO-SLS glass, willemite and Mn-doped willemite based glass-ceramics has been analyzed using Archimedes method, linear shrinkage, XRD, FESEM, FTIR, UV-Vis and PL spectroscopy.

## 1.5 Important of the study

Recently, glass and glass-ceramic from waste material opens a wide range of possibilities for designing new materials and attracting a significant interest in solid state lasers, phosphors and optics. A great deal of research has been focused on the fabrication and characterization of glass and glass-ceramics based phosphors in order to obtain efficient luminescent materials for fluorescent lamps, neon discharge lamps, oscilloscopes, color televisions, light emitting diode and many other displays and lighting devices (Bernardo *et al.*, 2008; Takesue *et al.*, 2009; Ding *et al.*, 2015).

Willemite has been identified as a suitable host matrix for many transition metal dopant ions for efficient luminescence. In willemite, all the atoms occupy overall position and composed of tetrahedral framework where in zinc and silicon positioned in three different fourfold crystallographic sites. This kind of rigid lattice gives the chance to obtain better optical properties (Taraferder *et al.*, 2014).

To the best of our knowledge, there are very few reports on physical, structural and optical properties of Mn-doped willemite glass-ceramics derived from precursor glass. In the present research, the preparation of precursor ZnO-SLS glass system by conventional melt-quenching technique and derived willemite based glass-ceramics by control crystallization process of precursor glasses is reported. Subsequently, the willemite glass-ceramics has been doped with manganese oxide (MnO) to increase the properties and quality of the final products.

## 1.6 Outline of thesis

The thesis arrangement is structured as follows. Chapter 1 gives an introduction of precursor ZnO-SLS glass, willemite glass-ceramic and Mn-doped willemite glass ceramics, the problem statements, the objectives, the scopes and also the importance of this study. The theory of glass, glass-ceramic and previous works including past and current has been carried out by other researchers are covered in Chapter 2. The apparatus, methodology and characterization of the precursor glass and willemite glass-ceramic doped manganese are explained in Chapter 3. The results concerning the effect of ZnO addition to the SLS glass, progression of heat treatment temperatures and different percentage of MnO doping content towards the physical, structural and optical properties of precursor ZnO-SLS glass and Mn-doped willemite glass-ceramic are analyzed and discussed in Chapter 4. Finally, the conclusion and suggestion for future works are presented in Chapter 5.



## REFERENCES

- Abbasi, M., & Hashemi, B. (2014). Fabrication and characterization of bioactive glass-ceramic using soda-lime-silica waste glass. *Materials Science and Engineering: C*, 37, 399-404.
- Abo-Mosallam, H. A., Darwish, H., & Salman, S. M. (2010). Crystallization characteristic and properties of some zinc containing soda lime silicate glasses. *Journal of Materials Science: Materials in Electronics*, 21(9), 889-896.
- Ahmadi, T. S., Haase, M., & Weller, H. (2000). Low-temperature synthesis of pure and Mn-doped willemite phosphor ( $Zn_2SiO_4:Mn$ ) in aqueous medium. *Materials Research Bulletin*, 35(11), 1869-1879.
- Al-Ani, S. K. J., Hogarth, C. A., & El-Mallawany, R. A. (1985). A study of optical absorption in tellurite and tungsten-tellurite glasses. *Journal of Materials Science*, 20(2), 661-667.
- Angell, C. A. (1995). Formation of glasses from liquids and biopolymers. *Science*, 267(5206), 1924-1935.
- Atwood, R. C., Sridhar, S., Zhang, W., & Lee, P. D. (2000). Diffusion-controlled growth of hydrogen pores in aluminium-silicon castings: in situ observation and modelling. *Acta Materialia*, 48(2), 405-417.
- Babu, S., Seshadri, M., Prasad, V. R., & Ratnakaram, Y. C. (2015). Spectroscopic and laser properties of  $Er^{3+}$  doped fluoro-phosphate glasses as promising candidates for broadband optical fiber lasers and amplifiers. *Materials Research Bulletin*, 70, 935-944.
- Barbieri, L., Bonamartini, A. C., & Lancellotti, I. (2000). Alkaline and alkaline-earth silicate glasses and glass-ceramics from municipal and industrial wastes. *Journal of the European Ceramic Society*, 20(14), 2477-2483.
- Barthou, C., Benoit, J., Benalloul, P., & Morell, A. (1994).  $Mn^{2+}$  concentration effect on the optical properties of  $Zn_2SiO_4:Mn$  phosphors. *Journal of the Electrochemical Society*, 141(2), 524-528.
- Bell, R. J., & Dean, P. (1972). The structure of vitreous silica: validity of the random network theory. *Philosophical Magazine*, 25(6), 1381-1398.
- Bernardo, E., Esposito, L., Rambaldi, E., Tucci, A., & Hreglich, S. (2008). Recycle of waste glass into "glass-ceramic stoneware". *Journal of the American Ceramic Society*, 91(7), 2156-2162.
- Bertail, C., Maron, S., Buissette, V., Le Mercier, T., Gacoin, T., & Boilot, J. P. (2011). Structural and photoluminescent properties of  $Zn_2SiO_4:Mn^{2+}$  nanoparticles prepared by a protected annealing process. *Chemistry of Materials*, 23(11), 2961-2967.
- Besmann, T. M., & Spear, K. E. (2002). Thermochemical modeling of oxide glasses. *Journal of the American Ceramic Society*, 85(12), 2887-2894.
- Bhalla, R. J. R. S. B., & White, E. W. (1972). Cathodoluminescence characteristics of  $Mn^{2+}$ -activated willemite ( $Zn_2SiO_4$ ) single crystals. *Journal of the Electrochemical Society*, 119(6), 740-743.
- Boccaccini, A. R., Bucker, M., Bossert, J., & Marszalek, K. (1997). Glass matrix composites from coal fly ash and waste glass. *Waste Management*, 17(1), 39-45.

- Boitier, F., Hidaka, C., & Takizawa, T. (2009). Enhancement of Mn red emission in  $\text{CaGa}_2\text{S}_4$  compounds by co-doping rare-earth elements. *Journal of Luminescence*, 129(5), 554-562.
- Boni, M., & Large, D. (2003). Nonsulfide zinc mineralization in Europe: An overview. *Economic Geology*, 98(4), 715-729.
- Boulay, E., Ragoen, C., Idrissi, H., Schryvers, D., & Godet, S. (2014). Influence of amorphous phase separation on the crystallization behavior of glass-ceramics in the  $\text{BaO-TiO}_2\text{-SiO}_2$  system. *Journal of Non-Crystalline Solids*, 384(1), 61-72.
- Bruel, M., & Floccari, M. (1983). U.S. Patent No. 4,368,083. Washington, DC: U.S. Patent and Trademark Office.
- Brunold, T. C., Güdel, H. U., & Cavalli, E. (1996). Absorption and luminescence spectroscopy of  $\text{Zn}_2\text{SiO}_4$  willemite crystals doped with  $\text{Co}^{2+}$ . *Chemical Physics Letters*, 252(1), 112-120.
- Bunting, E. N. (1930). Phase equilibria in the system  $\text{SiO}_2\text{-ZnO}$ . *Journal of the American Ceramic Society*, 13(1), 5-10.
- Burnett, D. G., & Douglas, R. W. (1970). Liquid-liquid phase separation in soda-lime-silica system. *Physics and Chemistry of Glasses*, 11(5), 125-135.
- Calestani, G., Montenero, A., Ferraguti, E., Ingletto, G., & Bettinelli, M. (1986). Influence of some oxides on the durability of a borosilicate glass. *Journal of Non-Crystalline Solids*, 84(1), 452-462.
- Cannas, C., Falqui, A., Musinu, A., Peddis, D., & Piccaluga, G. (2006).  $\text{CoFe}_2\text{O}_4$  nanocrystalline powders prepared by citrate-gel methods: Synthesis, structure and magnetic properties. *Journal of Nanoparticle Research*, 8(2), 255-267.
- Casasola, R., Rincón, J. M., & Romero, M. (2012). Glass-ceramic glazes for ceramic tiles: a review. *Journal of Materials Science*, 47(2), 553-582.
- Chakradhar, R. S., Nagabhushana, B. M., Chandrappa, G. T., Ramesh, K. P., & Rao, J. L. (2004). Solution combustion derived nanocrystalline  $\text{Zn}_2\text{SiO}_4\text{:Mn}$  phosphors: A spectroscopic view. *The Journal of Chemical Physics*, 121(20), 10250-10259.
- Chandrappa, G. T., Ghosh, S., & Patil, K. C. (1999). Synthesis and properties of willemite,  $\text{Zn}_2\text{SiO}_4$ , and  $\text{M}^{2+}\text{:Zn}_2\text{SiO}_4$  ( $\text{M} = \text{Co}$  and  $\text{Ni}$ ). *Journal of Materials Synthesis and Processing*, 7(5), 273-279.
- Chen, G. H. (2008). Sintering, crystallization, and properties of  $\text{CaO}$  doped cordierite-based glass-ceramics. *Journal of Alloys and Compounds*, 455(1), 298-302.
- Chen, G. H., & Liu, X. Y. (2007). Sintering, crystallization and properties of  $\text{MgO-Al}_2\text{O}_3\text{-SiO}_2$  system glass-ceramics containing  $\text{ZnO}$ . *Journal of Alloys and Compounds*, 431(1), 282-286.
- Chimalawong, P., Kaewkhao, J., Kedkaew, C., & Limsuwan, P. (2010). Optical and electronic polarizability investigation of  $\text{Nd}^{3+}$ -doped soda-lime silicate glasses. *Journal of Physics and Chemistry of Solids*, 71(7), 965-970.
- Cho, T. H., & Chang, H. J. (2003). Preparation and characterizations of  $\text{Zn}_2\text{SiO}_4\text{:Mn}$  green phosphors. *Ceramics International*, 29(6), 611-618.
- Choi, Y. G., Kim, K. H., Sohn, K. S., Park, H. D., & Lee, J. M. (1999). Mn K-edge X-ray absorption spectroscopic study of Mn-doped  $\text{Zn}_2\text{SiO}_4$  phosphors. *Journal of Materials Science Letters*, 18(8), 621-624.
- Choo, D. C., Ahn, S. D., Jung, H. S., Kim, T. W., Lee, J. Y., Park, J. H., & Kwon, M. S. (2010). Luminescence mechanisms of organic/inorganic hybrid organic

- light-emitting devices fabricated utilizing a  $\text{Zn}_2\text{SiO}_4\text{:Mn}$  color-conversion layer. *Thin Solid Films*, 518(22), 6308-6310.
- Clark, D. E., Dilmore, M. F., Ethridge, E. C., & Hench, L. L. (1976). Aqueous corrosion of soda-silica and soda-lime-silica glass. *Journal of the American Ceramic Society*, 59(1-2), 62-65.
- Colombo, P., Brusatin, G., Bernardo, E., & Scarinci, G. (2003). Inertization and reuse of waste materials by vitrification and fabrication of glass-based products. *Current Opinion in Solid State and Materials Science*, 7(3), 225-239.
- Coppola, V., Boni, M., Gilg, H. A., Balassone, G., & Dejonghe, L. (2008). The "calamine" nonsulfide Zn-Pb deposits of Belgium: petrographical, mineralogical and geochemical characterization. *Ore Geology Reviews*, 33(2), 187-210.
- Cormack, A. N., & Cao, Y. (1996). Molecular dynamics simulation of silicate glasses. *Molecular Engineering*, 6(1-2), 183-227.
- Cormier, L., Calas, G., & Beuneu, B. (2011). Structural changes between soda-lime silicate glass and melt. *Journal of Non-Crystalline Solids*, 357(3), 926-931.
- Curie, D., Barthou, C., & Canny, B. (1974). Covalent bonding of  $\text{Mn}^{2+}$  ions in octahedral and tetrahedral coordination. *The Journal of Chemical Physics*, 61(8), 3048-3062.
- Dai, P., Xu, Z., Yu, X., Wang, Y., Zhang, L., Li, G., Sun, Z., Liu, X., & Wu, M. (2015). Mesoporous hollow  $\text{Zn}_2\text{SiO}_4\text{:Mn}^{2+}$  nanospheres: The study of photoluminescence and adsorption properties. *Materials Research Bulletin*, 61(1), 76-82.
- Dai, X., Liu, X., Liu, L., Zhu, B., & Fang, Z. (2015). A novel image-guided FT-IR sensor using chalcogenide glass optical fibers for the detection of combustion gases. *Sensors and Actuators B: Chemical*, 220(1), 414-419.
- Dan, H. K., Zhou, D., Wang, R., Jiao, Q., Yang, Z., Song, Z., Xue, Y., & Qiu, J. (2015). Effect of  $\text{Mn}^{2+}$  ions on the enhancement upconversion emission and energy transfer of  $\text{Mn}^{2+}/\text{Tb}^{3+}/\text{Yb}^{3+}$  tri-doped transparent glass-ceramics. *Materials Letters*, 150(1), 76-80.
- Davis, E. A., & Mott, N. (1970). Conduction in non-crystalline systems V. Conductivity, optical absorption and photoconductivity in amorphous semiconductors. *Philosophical Magazine*, 22(179), 0903-0922.
- De Sousa, E., Rambo, C. R., Hotza, D., de Oliveira, A. N., Fey, T., & Greil, P. (2008). Microstructure and properties of LZSA glass-ceramic foams. *Materials Science and Engineering: A*, 476(1), 89-97.
- Diao, C. C., & Yang, C. F. (2010). Synthesis of high efficiency  $\text{Zn}_2\text{SiO}_4\text{:Mn}^{2+}$  green phosphors using nano-particles. *Ceramics International*, 36(5), 1653-1657.
- Ding, W. J., Peng, T. J., & Chen, J. M. (2012). Diopside-based glass-ceramics from chrysotile asbestos tailing. *In Advanced Materials Research*, 427(1), 26-31.
- Ding, L., Ning, W., Wang, Q., Shi, D., & Luo, L. (2015). Preparation and characterization of glass-ceramic foams from blast furnace slag and waste glass. *Materials Letters*, 141(1), 327-329.
- Dunken, H., & Doremus, R. H. (1987). Short time reactions of a  $\text{Na}_2\text{O-CaO-SiO}_2$  glass with water and salt solutions. *Journal of Non-Crystalline Solids*, 92(1), 61-72.
- Efimov, A. M. (1999). Vibrational spectra, related properties, and structure of inorganic glasses. *Journal of Non-Crystalline Solids*, 253(1), 95-118.



- Efimov, A. M., & Pogareva, V. G. (2006). IR absorption spectra of vitreous silica and silicate glasses: The nature of bands in the 1300 to 5000  $\text{cm}^{-1}$  region. *Chemical Geology*, 229(1), 198-217.
- Ehrt, D. (2004). Photoluminescence in the UV-VIS region of polyvalent ions in glasses. *Journal of Non-Crystalline Solids*, 348(1), 22-29.
- Ehrt, D., Herrmann, A., & Tiegel, M. (2011). Glasses and glass ceramics with blue, green and red photoluminescence. *Physics and Chemistry of Glasses-European Journal of Glass Science and Technology Part B-European Journal of Glass Science and Technology Part B*, 52(2), 68-76.
- Ehrt, D., Vu, H. T., Herrmann, A., & Völksch, G. (2008). Luminescent ZnO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> glasses and glass ceramics. *In Advanced Materials Research*, 39, 231-236.
- El-Deen, L. S., Al Salhi, M. S., & Elkholy, M. M. (2008). IR and UV spectral studies for rare earths-doped tellurite glasses. *Journal of Alloys and Compounds*, 465(1), 333-339.
- El-Diasty, F., Wahab, F. A. A., & Abdel-Baki, M. (2006). Optical band gap studies on lithium aluminum silicate glasses doped with Cr<sup>3+</sup> ions. *Journal of Applied Physics*, 100(9), 1-7.
- El Ghouli, J., & El Mir, L. (2014). Sol-gel synthesis and luminescence of undoped and Mn-doped zinc orthosilicate phosphor nanocomposites. *Journal of Luminescence*, 148(1), 82-88.
- El Ghouli, J., Omri, K., Alyamani, A., Barthou, C., & El Mir, L. (2013). Synthesis and luminescence of SiO<sub>2</sub>/Zn<sub>2</sub>SiO<sub>4</sub> and SiO<sub>2</sub>/Zn<sub>2</sub>SiO<sub>4</sub>:Mn composite with sol-gel methods. *Journal of Luminescence*, 138, 218-222.
- El Mir, L., Omri, K., & El Ghouli, J. (2015). Effect of crystallographic phase on green and yellow emissions in Mn-doped zinc silicate nanoparticles incorporated in silica host matrix. *Superlattices and Microstructures*, 85, 180-184.
- El-Mallawany, R. (1993). Longitudinal elastic constants of tellurite glasses. *Journal of Applied Physics*, 73(10), 4878-4880.
- El-Shennawi, A. W. A., Hamzawy, E. M. A., Khater, G. A., & Omar, A. A. (2001). Crystallization of some aluminosilicate glasses. *Ceramics International*, 27(7), 725-730.
- Eriksson, G., & Pelton, A. D. (1993). Critical evaluation and optimization of the thermodynamic properties and phase diagrams of the CaO-Al<sub>2</sub>O<sub>3</sub>, Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>, and CaO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> systems. *Metallurgical Transactions B*, 24(5), 807-816.
- Farnan, I., Grandinetti, P. J., Baltisberger, J. H., Stebbins, J. F., Werner, U., Eastman, M. A., & Pines, A. (1992). Quantification of the disorder in network-modified silicate glasses. *Nature*, 358(6381), 31-35.
- Feldman, C., & O'Hara, M., (1958). Luminescent phases in willemite films. *Journal of the Optical Society of America*, 48(11), 816-820.
- Fonda, G. R. (1940). The yellow and red zinc silicate phosphors. *The Journal of Physical Chemistry*, 44(7), 851-861.
- Francis, A. A. (2004). Conversion of blast furnace slag into new glass-ceramic material. *Journal of the European Ceramic Society*, 24(9), 2819-2824.
- Francis, A. A., Rawlings, R. D., Sweeney, R., & Boccaccini, A. R. (2004). Crystallization kinetic of glass particles prepared from a mixture of coal ash and soda-lime cullet glass. *Journal of Non-Crystalline Solids*, 333(2), 187-193.

- Gaft, M., Reisfeld, R., & Panczer, G. (2005). Modern luminescence spectroscopy of minerals and materials. Springer Science & Business Media.
- Gnutzmann, U., & Clausecker, K. (1974). Theory of direct optical transitions in an optical indirect semiconductor with a superlattice structure. *Applied Physics*, 3(1), 9-14.
- Goldman, D. E., & Richards, J. R. (1954). Measurement of high-frequency sound velocity in mammalian soft tissues. *The Journal of the Acoustical Society of America*, 26(6), 981-983.
- Goldschmidt, V. M. (1929). Crystal structure and chemical constitution. *Transactions of the Faraday Society*, 25, 253-283.
- Goldstein, J., Newbury, D.E., Echlin, P., Joy, D.C., Romig Jr, A.D., Lyman, C.E., Fiori, C. & Lifshin, E., 2012. Scanning electron microscopy and X-ray microanalysis: a text for biologists, materials scientists, and geologists. Springer Science & Business Media.
- Götz, J., & Masson, C. R. (1970). Trimethylsilyl derivatives for the study of silicate structures. Part I. A direct method of trimethylsilylation. *Journal of the Chemical Society A: Inorganic, Physical, Theoretical*, 2683-2686.
- Graça, M. P. F., da Silva, M. F., Sombra, A. S. B., & Valente, M. A. (2007). Electric and dielectric properties of a SiO<sub>2</sub>-Na<sub>2</sub>O-Nb<sub>2</sub>O<sub>5</sub> glass subject to a controlled heat-treatment process. *Physica B: Condensed Matter*, 396(1), 62-69.
- Hager, I. Z., El-Mallawany, R., & Bulou, A. (2011). Luminescence spectra and optical properties of TeO<sub>2</sub>-WO<sub>3</sub>-Li<sub>2</sub>O glasses doped with Nd, Sm and Er rare earth ions. *Physica B: Condensed Matter*, 406(4), 972-980.
- Hao, Y., & Wang, Y. (2007). Luminescent properties of Zn<sub>2</sub>SiO<sub>4</sub>:Mn<sup>2+</sup> phosphor under UV, VUV and CR excitation. *Journal of Luminescence*, 122, 1006-1008.
- Hasegawa, S., & Kitagawa, M. (1978). Effects of annealing on localized states in amorphous Ge films. *Solid State Communications*, 27(9), 855-858.
- Hoppe, U., Yousef, E., Rüssel, C., Neuefeind, J., & Hannon, A. C. (2004). Structure of zinc and niobium tellurite glasses by neutron and X-ray diffraction. *Journal of Physics: Condensed Matter*, 16(9), 1645.
- Hou, L., Zuo, G., Shen, Y., Meng, Y., & Li, H. (2014). Effects of the replacing content of ZnBr<sub>2</sub> on the properties of ZnO-B<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>:Mn<sup>2+</sup> glass-ceramics. *Ceramics International*, 40(8), 13097-13103.
- Hench, L. L. (1977). Physical chemistry of glass surfaces. *Journal of Non-Crystalline Solids*, 25(1), 343-369.
- Heo, J. (2014). Rare-earth-doped chalcogenide glass for lasers and amplifiers. *Chalcogenide Glasses: Preparation, Properties and Applications*.
- Hitzman, M. W., Reynolds, N. A., Sangster, D. F., Allen, C. R., & Carman, C. E. (2003). Classification, genesis, and exploration guides for nonsulfide zinc deposits. *Economic Geology*, 98(4), 685-714.
- Höland, W., Rheinberger, V., & Schweiger, M. (2003). Control of nucleation in glass ceramics. *Philosophical Transactions of the Royal Society of London A: Mathematical, Physical and Engineering Sciences*, 361(1804), 575-589.
- Hu, A. M., Li, M., Dali, D. M., & Liang, K. M. (2005). Crystallization and properties of a spodumene-willemite glass ceramic. *Thermochimica Acta*, 437(1), 110-113.
- Hurt, J. C., & Phillips, C. J. (1970). Structural role of zinc oxide in glasses in the system Na<sub>2</sub>O-ZnO-SiO<sub>2</sub>. *Journal of the American Ceramic Society*, 53(5), 269-273.

- Husung, R. D., & Doremus, R. H. (1990). The infrared transmission spectra of four silicate glasses before and after exposure to water. *Journal of Materials Research*, 5(10), 2209-2217.
- Imteaz, M. A., Ali, M. Y., & Arulrajah, A. (2012). Possible environmental impacts of recycled glass used as a pavement base material. *Waste Management & Research*, 30(9), 917-921.
- Jak, E., Hayes, P. C., Degterov, S., Pelton, A. D., & Wu, P. (1997). Thermodynamic optimization of the systems PbO-SiO<sub>2</sub>, PbO-ZnO, ZnO-SiO<sub>2</sub> and PbO-ZnO-SiO<sub>2</sub>. *Metallurgical and Materials Transactions B*, 28(6), 1011-1018.
- James, P. F. (1975). Liquid-phase separation in glass-forming systems. *Journal of Materials Science*, 10(10), 1802-1825.
- Kadir, S. A. S. A., Yin, C. Y., Sulaiman, M. R., Chen, X., & El-Harbawi, M. (2013). Incineration of municipal solid waste in Malaysia: Salient issues, policies and waste-to-energy initiatives. *Renewable and Sustainable Energy Reviews*, 24(1), 181-186.
- Kadono, K., Itakura, N., Akai, T., Yamashita, M., & Yazawa, T. (2009). Effect of additive ions on the optical density and stability of the color centers induced by X-ray irradiation in soda-lime silicate glass. *Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms*, 267(14), 2411-2415.
- Kamitsos, E. I., Yiannopoulos, Y. D., Varsamis, C. P., & Jain, H. (1997). Structure-property correlation in glasses by infrared reflectance spectroscopy. *Journal of Non-Crystalline Solids*, 222(1), 59-68.
- Kang, S. J. L. (2004). Sintering: densification, grain growth and microstructure. Butterworth-Heinemann.
- Karaksina, E. V., Shiryayev, V. S., & Ketkova, L. A. (2013). Preparation of composite materials for fiber optics based on chalcogenide glasses containing ZnS(ZnSe):Cr(2<sup>+</sup>) crystals. *Journal of Non-Crystalline Solids*, 377(1), 220-224.
- Karamanov, A., Pisciella, P., & Pelino, M. (1999). The effect of Cr<sub>2</sub>O<sub>3</sub> as a nucleating agent in iron-rich glass-ceramics. *Journal of the European Ceramic Society*, 19(15), 2641-2645.
- Kaur, G., Kumar, M., Arora, A., Pandey, O. P., & Singh, K. (2011). Influence of Y<sub>2</sub>O<sub>3</sub> on structural and optical properties of SiO<sub>2</sub>-BaO-ZnO-xB<sub>2</sub>O<sub>3</sub>-(10-x)Y<sub>2</sub>O<sub>3</sub> glasses and glass ceramics. *Journal of Non-Crystalline Solids*, 357(3), 858-863.
- Kauzmann, W. (1948). The nature of the glassy state and the behavior of liquids at low temperatures. *Chemical Reviews*, 43(2), 219-256.
- Kavouras, P., Komninou, P., Chrissafis, K., Kaimakamis, G., Kokkou, S., Paraskevopoulos, K., & Karakostas, T. (2003). Microstructural changes of processed vitrified solid waste products. *Journal of the European Ceramic Society*, 23(8), 1305-1311.
- Kawamoto, Y., & Tomozawa, M. (1981). Prediction of immiscibility boundaries of the systems K<sub>2</sub>O-SiO<sub>2</sub>, K<sub>2</sub>O-Li<sub>2</sub>O-SiO<sub>2</sub>, K<sub>2</sub>O-Na<sub>2</sub>O-SiO<sub>2</sub>, and K<sub>2</sub>O-BaO-SiO<sub>2</sub>. *Journal of the American Ceramic Society*, 64(5), 289-292.
- Khalil, E. M. A., El Batal, F. H., Hamdy, Y. M., Zidan, H. M., Aziz, M. S., & Abdelghany, A. M. (2010). Infrared absorption spectra of transition metals-doped soda lime silica glasses. *Physica B: Condensed Matter*, 405(5), 1294-1300.



- Kahn, A. H., & Leyendecker, A. J. (1964). Electronic energy bands in strontium titanate. *Physical Review*, 135(5), 1321-1325.
- Kiliç, G., & Ertunç, A. R. A. L. (2009). Determination of optical band gaps and structural properties of Cu<sup>2+</sup> doped B<sub>2</sub>O<sub>3</sub>-Na<sub>2</sub>O-Al<sub>2</sub>O<sub>3</sub>-V<sub>2</sub>O<sub>5</sub> glasses. *Gazi University Journal of Science*, 22(3), 129-139.
- Kim, N. J., La, Y. H., Im, S. H., Han, W. T., & Ryu, B. K. (2009). Effect of ZnO on physical and optical properties of bismuth borate glasses. *Electronic Materials Letters*, 5(4), 209-212.
- Klick, C. C., & Schulman, J. H. (1952). On the luminescence of divalent manganese in solids. *Journal of the Optical Society of America*, 42(12), 910-916.
- Kohara, S., Suzuya, K., Takeuchi, K., Loong, C. K., Grimsditch, M., Weber, J. K. R., Tangeman J. A., & Key, T. S. (2004). Glass formation at the limit of insufficient network formers. *Science*, 303(5664), 1649-1652.
- Kozhukharov, V., Bürger, H., Neov, S., & Sidzhimov, B. (1986). Atomic arrangement of a zinc-tellurite glass. *Polyhedron*, 5(3), 771-777.
- Lakshminarayana, G., & Wondraczek, L. (2011). Photoluminescence and energy transfer in Tb<sup>3+</sup>/Mn<sup>2+</sup> co-doped ZnAl<sub>2</sub>O<sub>4</sub> glass ceramics. *Journal of Solid State Chemistry*, 184(8), 1931-1938.
- Landi, E., Tampieri, A., Celotti, G., & Sprio, S. (2000). Densification behaviour and mechanisms of synthetic hydroxyapatites. *Journal of the European Ceramic Society*, 20(14), 2377-2387.
- Lange, F. F. (1989). Thermodynamics of densification: II, grain growth in porous compacts and relation to densification. *Journal of the American Ceramic Society*, 72(5), 735-741.
- Lange, F. F. (1989). Powder processing science and technology for increased reliability. *Journal of American Ceramics Society*, 72(1), 3-15.
- Lee, W. E., Ojovan, M. I., Stennett, M. C., & Hyatt, N. C. (2006). Immobilisation of radioactive waste in glasses, glass composite materials and ceramics. *Advances in Applied Ceramics*, 105(1), 3-12.
- Lee, W. E., & Rainforth, M. (1994). Ceramic microstructures: property control by processing. Springer Science & Business Media.
- Leenakul, W., Tunkasiri, T., Tongsir, N., Pengpat, K., & Ruangsuriya, J. (2016). Effect of sintering temperature variations on fabrication of 45S5 bioactive glass-ceramics using rice husk as a source for silica. *Materials Science and Engineering: C*, 61, 695-704.
- Legodi, M. A., & De Waal, D. (2007). The preparation of magnetite, goethite, hematite and maghemite of pigment quality from mill scale iron waste. *Dyes and Pigments*, 74(1), 161-168.
- Levelut, C., Le Parc, R., Faivre, A., & Champagnon, B. (2006). Influence of thermal history on the structure and properties of silicate glasses. *Journal of Non-Crystalline Solids*, 352(42), 4495-4499.
- Leverenz, H. W., & Seitz, F. (1939). Luminescent materials. *Journal of Applied Physics*, 10(7), 479-493.
- Li, Z. Y., & Zhang, Z. Q. (2000). Fragility of photonic band gaps in inverse-opal photonic crystals. *Physical Review B*, 62(3), 1516-1519.
- Lim, S.G., Kriventsov, S., Jackson, T.N., Haeni, J.H., Schlom, D.G., Balbashov, A.M., Uecker, R., Reiche, P., Freeouf, J.L. and Lucovsky, G., (2002). Dielectric functions and optical bandgaps of high-K dielectrics for metal-oxide- semiconductor field-effect transistors by far ultraviolet spectroscopic ellipsometry. *Journal of Applied Physics*, 91(7), 4500-4505.

- Lin, C. C., & Shen, P. (1994). Sol-gel synthesis of zinc orthosilicate. *Journal of Non-Crystalline Solids*, 171(3), 281-289.
- Lin, J., Huang, W., Sun, Z., Ray, C. S., & Day, D. E. (2004). Structure and non-linear optical performance of TeO<sub>2</sub>-Nb<sub>2</sub>O<sub>5</sub>-ZnO glasses. *Journal of Non-Crystalline Solids*, 336(3), 189-194.
- Lu, Q., Wang, P., & Li, J. (2011). Structure and luminescence properties of Mn-doped Zn<sub>2</sub>SiO<sub>4</sub> prepared with extracted mesoporous silica. *Materials Research Bulletin*, 46(6), 791-795.
- Lu, Y., Ding, Z., & Tang, Y. (1988). Structural change of soda lime glass with minor P<sub>2</sub>O<sub>5</sub> addition and heat treatment. *Journal of Non-Crystalline Solids*, 106(1), 391-394.
- Lukić, S. R., Petrović, D. M., Dramićanin, M. D., Mitrić, M., & Đaćanin, L. (2008). Optical and structural properties of Zn<sub>2</sub>SiO<sub>4</sub>:Mn<sup>2+</sup> green phosphor nanoparticles obtained by a polymer-assisted sol-gel method. *Scripta Materialia*, 58(8), 655-658.
- Lusvardi, G., Malavasi, G., Menabue, L., & Menziani, M. C. (2002). Synthesis, characterization, and molecular dynamics simulation of Na<sub>2</sub>O-CaO-SiO<sub>2</sub>-ZnO glasses. *The Journal of Physical Chemistry B*, 106(38), 9753-9760.
- Lusvardi, G., Malavasi, G., Menabue, L., Menziani, M. C., Segre, U., Carnasciali, M. M., & Ubaldini, A. (2004). A combined experimental and computational approach to (Na<sub>2</sub>O)<sub>1-x</sub>·CaO·(ZnO)<sub>x</sub>·2SiO<sub>2</sub> glasses characterization. *Journal of Non-Crystalline Solids*, 345(1), 710-714.
- Madhuri, V., Kumar, J. S., Rao, M. S., & Cole, S. (2015). Investigations on spectral features of tungsten ions in sodium lead alumino borate glass system. *Journal of Physics and Chemistry of Solids*, 78(1), 70-77.
- Mai, M., & Feldmann, C. (2009). Two-color emission of Zn<sub>2</sub>SiO<sub>4</sub>:Mn from ionic liquid mediated synthesis. *Solid State Sciences*, 11(2), 528-532.
- Malavasi, G., Lusvardi, G., Pedone, A., Menziani, M. C., Dappiaggi, M., Gualtieri, A., & Menabue, L. (2007). Crystallization kinetics of bioactive glasses in the ZnO-Na<sub>2</sub>O-CaO-SiO<sub>2</sub> system. *The Journal of Physical Chemistry A*, 111(34), 8401-8408.
- Mallur, S. B., Czarnecki, T., Adhikari, A., & Babu, P. K. (2015). Compositional dependence of optical band gap and refractive index in lead and bismuth borate glasses. *Materials Research Bulletin*, 68, 27-34.
- Manfredi, O., Wuth, W., & Bohlinger, I. (1997). Characterizing the physical and chemical properties of aluminum dross. *The Journal of the Minerals, Metals & Materials Society*, 49(11), 48-51.
- Maragkos, I., Giannopoulou, I. P., & Papias, D. (2009). Synthesis of ferronickel slag-based geopolymers. *Minerals Engineering*, 22(2), 196-203.
- Marinoni, N., D'Alessio, D., Diella, V., Pavese, A., & Francescon, F. (2013). Effects of soda-lime-silica waste glass on mullite formation kinetics and microstructures development in vitreous ceramics. *Journal of Environmental Management*, 124(1), 100-107.
- Masuno, A., Inoue, H., Yu, J., & Arai, Y. (2010). Refractive index dispersion, optical transmittance, and Raman scattering of BaTi<sub>2</sub>O<sub>5</sub> glass. *Journal of Applied Physics*, 108(6), 063520-1-063520-5.
- Matori, K. A., Zaid, M. H. M., Sidek, H. A. A., Halimah, M. K., Wahab, Z. A., & Sabri, M. G. M. (2010). Influence of ZnO on the ultrasonic velocity and elastic moduli of soda lime silicate glasses. *International Journal of Physical Sciences*, 5(14), 2212-2216.



- Matori, K. A., Zaid, M. H. M., Quah, H. J., Sidek, H. A. A., Wahab, Z. A., & Sabri, M. G. M. (2015). Studying the effect of ZnO on physical and elastic properties of  $(\text{ZnO})_x(\text{P}_2\text{O}_5)_{1-x}$  glasses using nondestructive ultrasonic method. *Advances in Materials Science and Engineering*, 2015, 1-8.
- Matusita, K., Komatsu, T., & Yokota, R. (1984). Kinetics of non-isothermal crystallization process and activation energy for crystal growth in amorphous materials. *Journal of Materials Science*, 19(1), 291-296.
- Merzbacher, C. I., & White, W. B. (1991). The structure of alkaline earth aluminosilicate glasses as determined by vibrational spectroscopy. *Journal of Non-Crystalline Solids*, 130(1), 18-34.
- Mirsaneh, M., Reaney, I. M., Hatton, P. V., & James, P. F. (2004). Characterization of high-fracture toughness K-Fluorrichterite-Fluorapatite glass ceramics. *Journal of the American Ceramic Society*, 87(2), 240-246.
- Miyata, T., Minami, T., Saikai, K., & Takata, S. (1994).  $\text{Zn}_2\text{SiO}_4$  as a host material for phosphor-emitting layers of TFEL devices. *Journal of Luminescence*, 60, 926-929.
- Moh, Y. C., & Manaf, L. A. (2014). Overview of household solid waste recycling policy status and challenges in Malaysia. *Resources, Conservation and Recycling*, 82, 50-61.
- Mohamed, N. B., Yahya, A. K., Deni, M. S. M., Mohamed, S. N., Halimah, M. K., & Sidek, H. A. A. (2010). Effects of concurrent  $\text{TeO}_2$  reduction and ZnO addition on elastic and structural properties of  $(90-x)\text{TeO}_2-10\text{Nb}_2\text{O}_5-(x)\text{ZnO}$  glass. *Journal of Non-Crystalline Solids*, 356(33), 1626-1630.
- Molla, A. R., Tarafder, A., & Karmakar, B. (2011). Synthesis and properties of glasses in the  $\text{K}_2\text{O}-\text{SiO}_2-\text{Bi}_2\text{O}_3-\text{TiO}_2$  system and bismuth titanate ( $\text{Bi}_4\text{Ti}_3\text{O}_{12}$ ) nano glass-ceramics thereof. *Journal of Materials Science*, 46(9), 2967-2976.
- Mott, N. F., & Davis, E. A., (2012). Electronic processes in non-crystalline materials. Oxford University Press.
- Mukherjee, G. D., Vaidya, S. N., & Sugandhi, V. (2001). Direct observation of amorphous to amorphous apparently first-order phase transition in fused quartz. *Physical Review Letters*, 87(19), 195501-195507.
- Müller, R., Zanutto, E. D., & Fokin, V. M. (2000). Surface crystallization of silicate glasses: nucleation sites and kinetics. *Journal of Non-Crystalline Solids*, 274(1), 208-231.
- Omri, K., El Ghoul, J., Alyamani, A., Barthou, C., & El Mir, L. (2013). Luminescence properties of green emission of  $\text{SiO}_2/\text{Zn}_2\text{SiO}_4:\text{Mn}$  nanocomposite prepared by sol-gel method. *Physica E: Low-dimensional Systems and Nanostructures*, 53(1), 48-54.
- Omri, K., & El Mir, L. (2014). Effect of manganese concentration on photoluminescence properties of  $\text{Zn}_2\text{SiO}_4:\text{Mn}$  nanophosphor material. *Superlattices and Microstructures*, 70(1), 24-32.
- Ojovan, M. I., & Lee, W. B. E. (2010). Connectivity and glass transition in disordered oxide systems. *Journal of Non-Crystalline Solids*, 356(44), 2534-2540.
- Park, K. W., Lim, H. S., Park, S. W., Deressa, G., & Kim, J. S. (2015). Strong blue absorption of green  $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$  phosphor by doping heavy  $\text{Mn}^{2+}$  concentrations. *Chemical Physics Letters*, 636(1), 141-145.
- Park, Y. J., Moon, S. O., & Heo, J. (2003). Crystalline phase control of glass ceramics obtained from sewage sludge fly ash. *Ceramics International*, 29(2), 223-227.

- Partyka, J. (2015). Effect of BaO ratio on the structure of glass-ceramic composite materials from the SiO<sub>2</sub>-Al<sub>2</sub>O<sub>3</sub>-Na<sub>2</sub>O-K<sub>2</sub>O-CaO system. *Ceramics International*, 41(8), 9337-9343.
- Patra, A., Baker, G. A., & Baker, S. N. (2005). Effects of dopant concentration and annealing temperature on the phosphorescence from Zn<sub>2</sub>SiO<sub>4</sub>:Mn<sup>2+</sup> nanocrystals. *Journal of Luminescence*, 111(1), 105-111.
- Paul, A. (1990). Chemistry of glasses. Springer Science & Business Media.
- Pavani, P. G., Sadhana, K., & Mouli, V. C. (2011). Optical, physical and structural studies of boro-zinc tellurite glasses. *Physica B: Condensed Matter*, 406(6), 1242-1247.
- Pedone, A. (2009). Properties calculations of silica-based glasses by atomistic simulations techniques: a review. *The Journal of Physical Chemistry C*, 113(49), 20773-20784.
- Petrescu, S., Constantinescu, M., Anghel, E. M., Atkinson, I., Olteanu, M., & Zaharescu, M. (2012). Structural and physico-chemical characterization of some soda lime zinc alumino-silicate glasses. *Journal of Non-Crystalline Solids*, 358(23), 3280-3288.
- Pfeiffer, H. G., & Fonda, G. R. (1952). The zinc silicate phosphors fluorescing in the yellow and red. *Journal of the Electrochemical Society*, 99(4), 140-143.
- Pinckney, L. R. (2006). Transparent glass-ceramics based on ZnO crystals. *Physics and Chemistry of Glasses-European Journal of Glass Science and Technology Part B*, 47(2), 127-130.
- Pisciella, P., Crisucci, S., Karamanov, A., & Pelino, M. (2001). Chemical durability of glasses obtained by vitrification of industrial wastes. *Waste Management*, 21(1), 1-9.
- Ponsot, I., Bernardo, E., Bontempi, E., Depero, L., Detsch, R., Chinnam, R. K., & Boccaccini, A. R. (2015). Recycling of pre-stabilized municipal waste incinerator fly ash and soda-lime glass into sintered glass-ceramics. *Journal of Cleaner Production*, 89, 224-230.
- Pontikes, Y., Esposito, L., Tucci, A., & Angelopoulos, G. N. (2007). Thermal behaviour of clays for traditional ceramics with soda-lime-silica waste glass admixture. *Journal of the European Ceramic Society*, 27(2), 1657-1663.
- Prakash, G. V., Rao, D. N., & Bhatnagar, A. K. (2001). Linear optical properties of niobium-based tellurite glasses. *Solid State Communications*, 119(1), 39-44.
- Qian, G., Baccaro, S., Falconieri, M., Bei, J., Cecilia, A., & Chen, G. (2008). Photoluminescent properties and Raman spectra of ZnO-based scintillating glasses. *Journal of Non-Crystalline Solids*, 354(40), 4626-4629.
- Ramachari, D., Moorthy, L. R., & Jayasankar, C. K. (2014). Optical absorption and emission properties of Nd<sup>3+</sup>-doped oxyfluorosilicate glasses for solid state lasers. *Infrared Physics & Technology*, 67(1), 555-559.
- Ramakrishna, P. V., Murthy, D. B. R. K., Sastry, D. L., & Samatha, K. (2014). Synthesis, structural and luminescence properties of Mn doped ZnO/Zn<sub>2</sub>SiO<sub>4</sub> composite microphosphor. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 129(1), 274-279.
- Ramakrishna, P. V., Murthy, D. B. R. K., & Sastry, D. L. (2014). White-light emitting Eu<sup>3+</sup> co-doped ZnO/Zn<sub>2</sub>SiO<sub>4</sub>:Mn<sup>2+</sup> composite microphosphor. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 125, 234-238.
- Rao, T. G. V. M., Kumar, A. R., Neeraja, K., Veeraiah, N., & Reddy, M. R. (2013). Optical and structural investigation of Eu<sup>3+</sup> ions in Nd<sup>3+</sup> co-doped

- magnesium lead borosilicate glasses. *Journal of Alloys and Compounds*, 557, 209-217.
- Rawlings, R. D., Wu, J. P., & Boccaccini, A. R. (2006). Glass-ceramics: their production from wastes-a review. *Journal of Materials Science*, 41(3), 733-761.
- Rawson, H. (1967). *Inorganic glass-forming systems*. London: Academic press.
- Renuka, C., Reddy, N.S., Reddy, M.S., Viswanatha, R., Reddy, C.N. (2015). Optical properties of microwave prepared glasses containing manganese ions. *International Journal of Luminescence and Applications*, 5, 121-124.
- Romero, M., Rawlings, R. D., & Rincón, J. M. (1999). Development of a new glass-ceramic by means of controlled vitrification and crystallisation of inorganic wastes from urban incineration. *Journal of the European Ceramic Society*, 19(12), 2049-2058.
- Romero-Serrano, A., Gomez-Yañez, C., Hallen-Lopez, M., & Araujo-Osorio, J. (2005). Thermodynamic modeling of alkali metal oxide-silica binary melts. *Journal of the American Ceramic Society*, 88(1), 141-145.
- Ronda, C. R. (1997). Recent achievements in research on phosphors for lamps and displays. *Journal of Luminescence*, 72, 49-54.
- Rooksby, H. P., & McKeag, A. H. (1941). The yellow fluorescent form of zinc silicate. *Transactions of the Faraday Society*, 37, 308-311.
- Rosmawati, S., Sidek, H. A. A., Zainal, A. T., & Mohd Zobir, H. (2008). Effect of zinc on the physical properties of tellurite glass. *Journal of Applied Sciences*, 8, 1956-1961.
- Salman, S. M., Salama, S. N., & Mahdy, E. A. (2015). The effect of strontium oxide replacing calcium oxide on the crystallization and thermal expansion properties of  $\text{Li}_2\text{O-CaO-SiO}_2$  glasses. *Ceramics International*, 41(1), 137-143.
- Schicke, K. D., Beyer, J., Hessenkemper, H., & Heitmann, J. (2016). Optical modifications at the intrinsic absorption threshold in soda lime silicate glass by  $\text{Ag}^+-\text{Na}^+$  ion exchange. *Journal of Non-Crystalline Solids*, 447(1), 134-140.
- Schlautt, C. M., & Roy, D. M. (1965). Crystalline solution in the system  $\text{MgO-Mg, SiO}_4\text{-MgAl}_2\text{O}_4$ . *Journal of the American Ceramic Society*, 48(5), 248-251.
- Schneider, J., Boni, M., Laukamp, C., Bechstädt, T., & Petzel, V. (2008). Willemite ( $\text{Zn}_2\text{SiO}_4$ ) as a possible Rb-Sr geochronometer for dating nonsulfide Zn-Pb mineralization: examples from the Otavi Mountainland (Namibia). *Ore Geology Reviews*, 33(2), 152-167.
- Segadães, A. M. (2006). Use of phase diagrams to guide ceramic production from wastes. *Advances in Applied Ceramics*, 105(1), 46-54.
- Sehgal, J., & Ito, S. (1998). A new low-brittleness glass in the soda-lime-silica glass family. *Journal of the American Ceramic Society*, 81(9), 2485-2488.
- Selomulya, R., Ski, S., Pita, K., Kam, C. H., Zhang, Q. Y., & Buddhudu, S. (2003). Luminescence properties of  $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$  thin-films by a sol-gel process. *Materials Science and Engineering: B*, 100(2), 136-141.
- Seo, K. I., Park, J. H., Kim, J. S., Kim, G. C., & Yoo, J. H. (2009). Highly efficient transparent  $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$  phosphor film on quartz glass. *Journal of Luminescence*, 129(7), 715-719.
- Shao, Y., Lefort, T., Moras, S., & Rodriguez, D. (2000). Studies on concrete containing ground waste glass. *Cement and Concrete Research*, 30(1), 91-100.



- Shelby, J. E. (1981). Effect of crystal content on the properties of willemite glass-ceramics. *Journal of Non-Crystalline Solids*, 43(2), 255-265.
- Shelby, J. E. (2005). Introduction to glass science and technology. Royal Society of Chemistry.
- Shelby, J. E., & Nichols, M. C. (1983). Effect of thermal history on the properties of a willemite glass-ceramic. *Journal of the American Ceramic Society*, 66(3), 200-204.
- Sheng, J., Kadono, K., Utagawa, Y., & Yazawa, T. (2002). X-ray irradiation on the soda-lime container glass. *Applied Radiation and Isotopes*, 56(4), 621-626.
- Sidek, H. A. A., Rosmawati, S., Talib, Z. A., Halimah, M. K., & Daud, W. M. (2009). Synthesis and optical properties of ZnO-TeO<sub>2</sub> glass system. *American Journal of Applied Sciences*, 6(8), 1489-1494.
- Singh, A. K. (2013). A comparative study on optical properties of Se-Zn-In and Se-Zn-Te-In chalcogenide glasses. *Optik-International Journal for Light and Electron Optics*, 124(15), 2187-2190.
- Sinton, C. W., & LaCourse, W. C. (2001). Experimental survey of the chemical durability of commercial soda-lime-silicate glasses. *Materials Research Bulletin*, 36(13), 2471-2479.
- Sivakumar, V., Lakshmanan, A., Kalpana, S., Rani, R. S., Kumar, R. S., & Jose, M. T. (2012). Low-temperature synthesis of Zn<sub>2</sub>SiO<sub>4</sub>:Mn green photoluminescence phosphor. *Journal of Luminescence*, 132(8), 1917-1920.
- Smekal, A. G. (1951). On the structure of glass. *Journal of the Society of Glass Technology*, 35(1), 392-395.
- Sohn, K. S., Cho, B., & Park, H. D. (1999). Photoluminescence behavior of Manganese-doped zinc silicate phosphors. *Journal of the American Ceramic Society*, 82(10), 2779-2784.
- Sohn, K. S., Cho, B., Chang, H., & Park, H. D. (1999). Effect of Co-doping on the photoluminescence behavior of Zn<sub>2</sub>SiO<sub>4</sub>:Mn phosphors. *Journal of the Electrochemical Society*, 146(6), 2353-2356.
- Sohn, K. R., Kim, K. T., & Song, J. W. (2002). Optical fiber sensor for water detection using a side-polished fiber coupler with a planar glass-overlay-waveguide. *Sensors and Actuators A: Physical*, 101(1), 137-142.
- Soraru, G. D., Modena, S., Guadagnino, E., Colombo, P., Egan, J., & Pantano, C. (2002). Chemical durability of silicon oxycarbide glasses. *Journal of the American Ceramic Society*, 85(6), 1529-1536.
- Stefan, R., Culea, E., & Pascuta, P. (2012). The effect of copper ions addition on structural and optical properties of zinc borate glasses. *Journal of Non-Crystalline Solids*, 358(4), 839-846.
- Stevens, A. L. N., & Vink, A. T. (1974). Fine structure in the low temperature luminescence of Zn<sub>2</sub>SiO<sub>4</sub>:Mn and Mg<sub>4</sub>Ta<sub>2</sub>O<sub>9</sub>:Mn. *Journal of Luminescence*, 8(6), 443-451.
- Stillinger, F. H. (1995). A topographic view of supercooled liquids and glass formation. *Science*, 267(5206), 1935-1939.
- Suzuki, T., Horibuchi, K., & Ohishi, Y. (2005). Structural and optical properties of ZnO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> system glass-ceramics containing Ni<sup>2+</sup>-doped nanocrystals. *Journal of Non-Crystalline Solids*, 351(27), 2304-2309.
- Suryanarayana, C., & Norton, M. G. (2013). X-ray diffraction: a practical approach. Springer Science & Business Media.
- Syamimi, N. F., Matori, K. A., Lim, W. F., Sidek H. A. A., & Zaid, M. H. M., (2014). Effect of sintering temperature on structural and morphological

- properties of europium (III) oxide doped willemite. *Journal of Spectroscopy*, 2014, 1-7.
- Taghavinia, N., Lerondel, G., Makino, H., Yamamoto, A., Yao, T., Kawazoe, Y., & Goto, T. (2001). Nanocrystalline  $Zn_2SiO_4:Mn^{2+}$  grown in oxidized porous silicon. *Nanotechnology*, 12(4), 547-551.
- Taghavinia, N., Lerondel, G., Makino, H., Yamamoto, A., Yao, T., Kawazoe, Y., & Goto, T. (2002). Growth of luminescent  $Zn_2SiO_4:Mn^{2+}$  particles inside oxidized porous silicon: emergence of yellow luminescence. *Journal of Crystal Growth*, 237(1), 869-873.
- Takesue, M., Hayashi, H., & Smith, R. L. (2009). Thermal and chemical methods for producing zinc silicate (willemite): A review. *Progress in Crystal Growth and Characterization of Materials*, 55(3), 98-124.
- Takesue, M., Shimoyama, K., Murakami, S., Hakuta, Y., Hayashi, H., & Smith, R. L. (2007). Phase formation of Mn-doped zinc silicate in water at high-temperatures and high-pressures. *The Journal of Supercritical Fluids*, 43(2), 214-221.
- Takesue, M., Suino, A., Shimoyama, K., Hakuta, Y., Hayashi, H., & Smith, R. L. (2008). Formation of  $\alpha$ - and  $\beta$ -phase Mn-doped zinc silicate in supercritical water and its luminescence properties at Si/(Zn+Mn) ratios from 0.25 to 1.25. *Journal of Crystal Growth*, 310(18), 4185-4189.
- Talib, Z. A., Loh, Y. N., Sidek, H. A. A., Yusoff, W. M. D. W., Yunus, W. M. M., & Shaari, A. H. (2004). Optical absorption spectrum of  $(LiCl)_x(P_2O_5)_{1-x}$  glass. *Ceramics International*, 30(7), 1715-1717.
- Tanabe, S. (1999). Optical transitions of rare earth ions for amplifiers: how the local structure works in glass. *Journal of Non-Crystalline Solids*, 259(1), 1-9.
- Tanabe, S., Hayashi, H., Hanada, T., & Onodera, N. (2002). Fluorescence properties of  $Er^{3+}$  ions in glass ceramics containing  $LaF_3$  nanocrystals. *Optical Materials*, 19(3), 343-349.
- Tanaka, M. (2002). Photoluminescence properties of  $Mn^{2+}$ -doped II-VI semiconductor nanocrystals. *Journal of Luminescence*, 100(1), 163-173.
- Tarafder, A., Molla, A. R., Dey, C., & Karmakar, B. (2013). Thermal, structural, and enhanced photoluminescence properties of  $Eu^{3+}$ -doped transparent willemite glass-ceramic nanocomposites. *Journal of the American Ceramic Society*, 96(8), 2424-2431.
- Tarafder, A., Molla, A. R., Mukhopadhyay, S., & Karmakar, B. (2014). Fabrication and enhanced photoluminescence properties of  $Sm^{3+}$ -doped  $ZnO-Al_2O_3-B_2O_3-SiO_2$  glass derived willemite glass-ceramic nanocomposites. *Optical Materials*, 36(9), 1463-1470.
- Tauc, J., Grigorovici, R., & Vancu, A. (1966). Optical properties and electronic structure of amorphous germanium. *Physica Status Solidi (b)*, 15(2), 627-637.
- Taylor, H. F. W. (1962). The dehydration of hemimorphite. *American Mineral*, 47, 932-944.
- Teo, P. T., Anasyida, A. S., Basu, P., & Nurulakmal, M. S. (2014). Recycling of Malaysia's electric arc furnace (EAF) slag waste into heavy-duty green ceramic tile. *Waste Management*, 34(12), 2697-2708.
- Terry, B., & Monhemius, A. J. (1983). Acid dissolution of willemite  $(Zn, Mn)_2SiO_4$  and hemimorphite  $(Zn_4Si_2O_7(OH)_2H_2O)$ . *Metallurgical Transactions B*, 14(3), 335-346.

- Ticha, H., Kincl, M., & Tichy, L. (2013). Some structural and optical properties of  $(\text{Bi}_2\text{O}_3)_x(\text{ZnO})_{60-x}(\text{B}_2\text{O}_3)_{40}$  glasses. *Materials Chemistry and Physics*, 138(2), 633-639.
- Tomozawa, M., Hong, J. W., & Ryu, S. R. (2005). Infrared (IR) investigation of the structural changes of silica glasses with fictive temperature. *Journal of Non-Crystalline Solids*, 351(12), 1054-1060.
- Toya, T., Kameshima, Y., Yasumori, A., & Okada, K. (2004). Preparation and properties of glass-ceramics from wastes (Kira) of silica sand and kaolin clay refining. *Journal of the European Ceramic Society*, 24(8), 2367-2372.
- Turnbull, D., & Cohen, M. H. (1961). Free-volume model of the amorphous phase: glass transition. *The Journal of Chemical Physics*, 34(1), 120-125.
- Uegaito, K., Hosokawa, S., & Inoue, M. (2012). Effect of heat treatments on the luminescence properties of  $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$  phosphors prepared by glycothermal methods. *Journal of Luminescence*, 132(1), 64-70.
- Urbach, F. (1953). The long-wavelength edge of photographic sensitivity and of the electronic absorption of solids. *Physical Review*, 92(5), 1324.
- Van der Kolk, E., Dorenbos, P., Van Eijk, C. W. E., Bechtel, H., Jüstel, T., Nikol, H., Ronda, C. R., & Wiechert, D. U. (2000). Optimised co-activated willemite phosphors for application in plasma display panels. *Journal of Luminescence*, 87(1), 1246-1249.
- Varshneya, A. K. (2013). *Fundamentals of inorganic glasses*. Elsevier.
- Vellini, M., & Savioli, M. (2009). Energy and environmental analysis of glass container production and recycling. *Energy*, 34(12), 2137-2143.
- Victor, D., & Agamuthu, P. (2013). Strategic environmental assessment policy integration model for solid waste management in Malaysia. *Environmental Science & Policy*, 33(1), 233-245.
- Vitale-Brovarone, C., Novajra, G., Milanese, D., Lousteau, J., & Knowles, J. C. (2011). Novel phosphate glasses with different amounts of  $\text{TiO}_2$  for biomedical applications: dissolution tests and proof of concept of fibre drawing. *Materials Science and Engineering: C*, 31(2), 434-442.
- Wachs, I. E. (2005). Recent conceptual advances in the catalysis science of mixed metal oxide catalytic materials. *Catalysis Today*, 100(1), 79-94.
- Wan, J., Wang, Z., Chen, X., Mu, L., Yu, W., & Qian, Y. (2006). Controlled synthesis and relationship between luminescent properties and shape/crystal structure of  $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$  phosphor. *Journal of Luminescence*, 121(1), 32-38.
- Wang, L. H., & Hon, M. H. (1992). Effects of sulfidization and sintering temperatures of  $\text{CaLa}_2\text{S}_4$  powder on its optical property. *Japanese Journal of Applied Physics*, 31(1), 2177-2180.
- Wang, L., Liu, X., Hou, Z., Li, C., Yang, P., Cheng, Z., Lian, H., & Lin, J. (2008). Electrospinning synthesis and luminescence properties of one-dimensional  $\text{Zn}_2\text{SiO}_4:\text{Mn}^{2+}$  microfibers and microbelts. *The Journal of Physical Chemistry C*, 112(48), 18882-18888.
- Weber, L., & Oswald, H. R. (1975). Investigation of phase intergrowth morphologies in the system  $\text{Zn}_2\text{SiO}_4\text{-SiO}_2$  by photo-emission electron microscopy. *Journal of Materials Science*, 10(6), 973-982.
- Williamson, J., & Glasser, F. P. (1964). Crystallisation of zinc silicate liquids and glasses. *Physics and Chemistry of Glasses*, 5(1), 52-59.



- Wu, P., Eriksson, G., & Pelton, A. D. (1993). Optimization of the thermodynamic properties and phase diagrams of the Na<sub>2</sub>O-SiO<sub>2</sub> and K<sub>2</sub>O-SiO<sub>2</sub> systems. *Journal of the American Ceramic Society*, 76(8), 2059-2064.
- Xiong, L., Shi, J., Gu, J., Li, L., Huang, W., Gao, J., & Ruan, M. (2005). A mesoporous template route to the low-temperature preparation of efficient green light emitting Zn<sub>2</sub>SiO<sub>4</sub>:Mn phosphors. *The Journal of Physical Chemistry B*, 109(2), 731-735.
- Xu, G. Q., Xu, H. T., Zheng, Z. X., & Wu, Y. C. (2010). Preparation and characterization of Zn<sub>2</sub>SiO<sub>4</sub>:Mn phosphors with hydrothermal methods. *Journal of Luminescence*, 130(10), 1717-1720.
- Xu, X. J., Ray, C. S., & Day, D. E. (1991). Nucleation and crystallization of Na<sub>2</sub>O·2CaO·3SiO<sub>2</sub> glass by differential thermal analysis. *Journal of the American Ceramic Society*, 74(5), 909-914.
- Yan, B., & Huang, H. (2007). Matrix-inducing synthesis and luminescence of Zn<sub>2</sub>SiO<sub>4</sub>:xTb<sup>3+</sup> submicrometer phosphors derived from the sol-gel assembling of different multicomponent hybrid precursors. *Journal of Alloys and Compounds*, 429(1), 338-342.
- Yanbo, Q., Ning, D., Mingying, P., Lüyun, Y., Danping, C., Jianrong, Q., Congshan, Z., & Akai, T. (2006). Spectroscopic properties of Nd<sup>3+</sup>-doped high silica glass prepared by sintering porous glass. *Journal of Rare Earths*, 24(6), 765-770.
- Yang, H., Hazen, R. M., Downs, R. T., & Finger, L. W. (1997). Structural change associated with the incommensurate-normal phase transition in akermanite, Ca<sub>2</sub>MgSi<sub>2</sub>O<sub>7</sub>, at high pressure. *Physics and Chemistry of Minerals*, 24(7), 510-519.
- Ye, R., Ma, H., Zhang, C., Gao, Y., Hua, Y., Deng, D., Liu, P., & Xu, S. (2013). Luminescence properties and energy transfer mechanism of Ce<sup>3+</sup>/Mn<sup>2+</sup> co-doped transparent glass-ceramics containing β-Zn<sub>2</sub>SiO<sub>4</sub> nano-crystals for white light emission. *Journal of Alloys and Compounds*, 566(1), 73-77.
- Yekta, B. E., Alizadeh, P., & Rezazadeh, L. (2007). Synthesis of glass-ceramic glazes in the ZnO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>-ZrO<sub>2</sub> system. *Journal of the European Ceramic Society*, 27(5), 2311-2315.
- Yousef, E., Hotzel, M., & Rüssel, C. (2007). Effect of ZnO and Bi<sub>2</sub>O<sub>3</sub> addition on linear and non-linear optical properties of tellurite glasses. *Journal of Non-Crystalline Solids*, 353(4), 333-338.
- Yu, Y., Wang, Y., Chen, D., Huang, P., Ma, E., & Bao, F. (2008). Enhanced emissions of Eu<sup>3+</sup> by energy transfer from ZnO quantum dots embedded in SiO<sub>2</sub> glass. *Nanotechnology*, 19(5), 1-5.
- Yuritsyn, N. S. (2015). Influence of preformed nuclei on crystal nucleation kinetics in soda-lime-silica glass. *Journal of Non-Crystalline Solids*, 427(1), 139-145.
- Zachariasen, W. H. (1932). The atomic arrangement in glass. *Journal of the American Chemical Society*, 54(10), 3841-3851.
- Zanotto, E. D. (1991). Surface crystallization kinetics in soda-lime-silica glasses. *Journal of Non-Crystalline Solids*, 129(1), 183-190.
- Zanotto, E. D., & Craievich, A. F. (1981). The role of amorphous phase separation in crystal nucleation in splat cooled Li<sub>2</sub>O-SiO<sub>2</sub> glasses. *Journal of Materials Science*, 16(4), 973-982.
- Zen, I. S., Noor, Z. Z., & Yusuf, R. O. (2014). The profiles of household solid waste recyclers and non-recyclers in Kuala Lumpur, Malaysia. *Habitat International*, 42(1), 83-89.

- Zhang, L., & Jahanshahi, S. (1998). Review and modeling of viscosity of silicate melts: Part I. Viscosity of binary and ternary silicates containing CaO, MgO, and MnO. *Metallurgical and Materials Transactions B*, 29(1), 177-186.
- Zhang, W., & Liu, H. (2013). A low cost route for fabrication of wollastonite glass-ceramics directly using soda-lime waste glass by reactive crystallization-sintering. *Ceramics International*, 39(2), 1943-1949.
- Zhang, Y., Huang, J., Ma, T., Wang, X., Deng, C., & Dai, X. (2011). Sintering temperature dependence of energy-storage properties in (Ba, Sr) TiO<sub>3</sub> glass-ceramics. *Journal of the American Ceramic Society*, 94(6), 1805-1810.
- Zhou, S., Dong, H., Feng, G., Wu, B., Zeng, H., & Qiu, J. (2007). Broadband optical amplification in silicate glass-ceramic containing  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>:Ni<sup>2+</sup> nanocrystals. *Optics Express*, 15(9), 5477-5481.
- Zhou, Y., Ma, Q., Lü, M., Qiu, Z., Zhang, A., & Yang, Z. (2008). Preparation and photoluminescence of SrNb<sub>2</sub>O<sub>6</sub> nanoparticles prepared by combustion method. *Materials Science and Engineering: B*, 150(1), 66-69.
- Zhu, W., Chen, J., Hao, C., & Zhang, J. (2014). Microstructure and strength of Al<sub>2</sub>O<sub>3</sub>/Al<sub>2</sub>O<sub>3</sub> joints bonded with ZnO-Al<sub>2</sub>O<sub>3</sub>-B<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> glass-ceramic. *Journal of Materials Science & Technology*, 30(9), 944-948.