



UNIVERSITI PUTRA MALAYSIA

***CHARACTERIZATION OF EXTRACTED CARBOXYMETHYL
CELLULOSE FROM OIL PALM EMPTY FRUIT BUNCH STALK FIBERS
FOR ICE CREAM APPLICATION***

DZIEDA BINTI MUHAMAD PARID

FK 2018 127



**CHARACTERIZATION OF EXTRACTED CARBOXYMETHYL
CELLULOSE FROM OIL PALM EMPTY FRUIT BUNCH STALK FIBERS
FOR ICE CREAM APPLICATION**

By

DZIEDA BINTI MUHAMAD PARID

**Thesis submitted to the School of Graduate Studies, Universiti Putra
Malaysia, in fulfilment of the requirement for the Degree of
Master of Science**

May 2018

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia





*Dedicated to my family
For your endless love, support and encouragement*

© COPYRIGHT UPM

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in
fulfilment of the requirement for the degree of Master of Science

**CHARACTERIZATION OF EXTRACTED CARBOXYMETHYL
CELLULOSE (CMC) FROM OIL PALM EMPTY FRUIT BUNCH (OPEFB)
STALK FIBERS FOR ICE CREAM APPLICATION**

By

DZIEDA BINTI MUHAMAD PARID

May 2018

Chairman : Nur 'Aliaa Abd Rahman, PhD
Faculty : Engineering

The current extraction of carboxymethyl cellulose (CMC) from wood has created competition with wood industries. Interest in alternative sources is critical to ensure the sustainable production of CMC. Therefore, the extraction of CMC from oil palm empty fruit bunch (OPEFB) stalk fibers was evaluated. Based on previous work, highest cellulose content was obtained from raw stalk fibers with the least amount of lignin and residual oil as compared to the empty fruit bunch (EFB) and spikelet. Based on the results, OPEFB stalks fibers is suitable to be used as the substrate to produce CMC as proven by its cellulose composition (76.45%), proven morphology images, changes of diffraction patterns and new functional group occurred throughout the extraction process. Meanwhile, extracted CMC in powder form shows a good physicochemical properties in terms of its moisture content (11.18%), densities, flowability, good water retention capacity (21.55%), approaching desired colour of CMC and good physical appearance. Extracted CMC in its aqueous form also shows a comparable viscosity behaviour as it depicts a good shear thinning characteristics at 4% and the same flow behaviour curve as shown by the commercial CMC at 1% and 4% concentration.

Prior to the production of the extracted CMC, the potential application of the extracted CMC from OPEFB stalk fibers were analysed on hard ice cream properties. Such data are useful in accessing the overall quality during the production and handling of hard ice cream, as well as in developing a desirable mouthfeel. The extracted CMC from OPEFB stalks fibers was able to increase the viscosity of liquid ice cream mixture (129.4cp) and hard ice cream produced by using the extracted CMC shows a good and comparable melting characteristics

as it shows the same melting rate with hard ice cream produced using commercial CMC, with melting resistance (60.28%), lower overrun (35.2%) and lower hardness (28.88N) which will make the hard ice cream creamier, smoother and richer taste and the hard ice cream produced using sCMC shows a viscoelastic behaviour same as the hard ice cream produced using commercial CMC.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk Ijazah Sarjana Sains

**PENCIRIAN KARBOKSIMETIL SELULOSA YANG DIEKSTRAK DARI
SERAT TANDAN BUAH KELAPA SAWIT KOSONG UNTUK APLIKASI
DI DALAM AIS KRIM**

Oleh

DZIEDA BINTI MUHAMAD PARID

May 2018

Penyelia : Nur 'Aliaa Abd Rahman, PhD
Fakulti : Kejuruteraan

Pengekstrakan terkini karboksimetil selulosa (CMC) dari kayu telah mewujudkan persaingan dengan industri kayu. Kepentingan dalam sumber alternatif adalah penting untuk memastikan pengeluaran CMC yang mampan. Oleh itu, pengekstrakan CMC dari serat tandan buah kelapa sawit kosong (OPEFB) telah diuji. Berdasarkan projek sebelum ini, kandungan selulosa tertinggi diperolehi dari serat tangkai mentah dengan jumlah sisa minyak dan lignin yang paling sedikit berbanding dengan seluruh tandan buah kelapa sawit kosong (EFB) dan spikelet. Berdasarkan hasilnya, serat tangkai OPEFB sesuai untuk digunakan sebagai substrat untuk menghasilkan CMC sebagaimana terbukti dengan jumlah komposisi selulosa (76.45%), gambar morfologi yang telah terbukti, perubahan corak difraksi dan kumpulan fungsi telah terjadi sepanjang proses pengekstrakan. Sementara itu, CMC yang diekstrak dalam bentuk serbuk menunjukkan sifat fizikokimia yang baik dari segi kandungan lembapannya (11.18%), ketumpatan, pengaliran, kapasiti pengekalan air yang baik (21.55%), menghampiri warna CMC yang dikehendaki dan penampilan fizikal yang baik. CMC yang diekstrak dalam bentuk cecair juga menunjukkan sifat kelikatan yang setanding dengan CMC komersil kerana ia menggambarkan ciri-ciri penipisan ricih yang baik pada kepekatan 4% dan lengkung sifat aliran yang sama seperti yang ditunjukkan oleh CMC komersil pada kepekatan 1% dan 4%.

CMC yang diekstrak dari serat tangkai OPEFB dianalisis pada sifat ais krim. Data sedemikian berguna dalam mengakses kualiti keseluruhan semasa pengeluaran dan pengendalian ais krim, serta sifat ais krim dalam mulut yang wajar. CMC yang diekstrak daripada serat tangkai OPEFB dapat meningkatkan kelikatan campuran ais krim (129.4cp) dan ais krim yang dihasilkan dengan menggunakan CMC yang diekstrak memberikan ciri pencairan yang baik dan

setanding dengan ais krim yang dihasilkan dengan CMC komersil kerana ia menunjukkan kadar lebur yang sama dengan rintangan lebur (60.28%), overrun lebih rendah (35.2%) dan kekerasan (28.88N) yang akan menjadikan ais krim mempunyai rasa yang lebih bagus dan enak. Tambahan lagi, ais krim yang dihasilkan menggunakan sCMC menunjukkan sifat viscoelastik yang sama seperti ais krim yang dihasilkan menggunakan CMC komersial.



ACKNOWLEDGEMENT

Alhamdulillah, thank you Allah SWT for giving me endless strength and courage to complete my project. First of all, I would like to express my sincere gratitude to my main supervisor and supervisory committee, Dr Nur 'Aliaa Abd Rahman, Dr Azhari Samsu Baharuddin and Dr Mohd Afandi P Mohammed for their guidance, enthusiasm, encouragement, support and inspiring knowledge in this project.

Furthermore, special thanks to my university, Universiti Putra Malaysia for providing me with a comfortable environment and equipment needed to carry out my MSc project. I also would like to take this opportunity to express my uncountable thanks to the lab technicians from the Department of Process and Food Engineering for their help throughout the experimental work in indicating the equipment and devices that I required and in making the setup for the processes. A special appreciation also goes to my fellow Ice Cream Research Group: Siti Zubaidah, Amiruddin and others for their joyful and memorable friendship moments. Not to forget, my seniors, Dr Halimatun, Dr Nadia, Loo Xiang, Sobah and Termizi who always helped me in handling experiments and giving advice based on their precious experiences, thank you so much for lending your time and willingness. The appreciation is beyond words.

Up and foremost, my indebtedness goes to my dearest parents, Hj Muhamad Parid and Hjh Norehan, my lovely husband, Syed Fuad and not to forget my supportive siblings, Dzuan, Dzuady, Dziela and their entire family, for their faith, understanding, endless support and motivation and most importantly their prayers.

Thank you for the love and strength.

I certify that a Thesis Examination Committee has met on 24 May 2018 to conduct the final examination of Dzieda binti Muhamad Parid on her thesis entitled "Characterization of Extracted Carboxymethyl Cellulose from Oil Palm Empty Fruit Bunch Stalk Fibers for Ice Cream Application" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Master of Science.

Members of the Thesis Examination Committee were as follows:

Mohd Nazli Naim, PhD
Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Siti Mazlina bt Mustapa Kamal, PhD
Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Ling Tau Chuan, PhD
Professor
University of Malaya
Malaysia
(External Examiner)



RUSLI HAJI ABDULLAH, PhD
Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 30 August 2018

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows;

Nur 'Aliaa Abd Rahman, PhD

Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Azhari Samsu Baharuddin, PhD

Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Mohd Afandi P. Mohamed, PhD

Senior Lecturer,
Faculty of Engineering
Universiti Putra Malaysia
(Member)

ROBIAH BINTI YUNUS, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: _____ Date: _____

Name and Matric No: Dzieda binti Muhamad Parid (GS 43868)

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____

Name of Chairman of

Supervisory Committee: Dr Nur 'Aliaa Abd Rahman

Signature: _____

Name of Member of

Supervisory Committee: Dr Azhari Samsu Baharuddin

Signature: _____

Name of Member of

Supervisory Committee: Dr Mohd Afandi P Mohammed

TABLE OF CONTENTS

	Page
ABSTRACT	i
ABSTRAK	iii
ACKNOWLEDGEMENTS	v
APPROVAL	vi
DECLARATION	viii
LIST OF TABLES	xiii
LIST OF FIGURES	xiv
LIST OF ABBREVIATIONS	xvi
LIST OF SYMBOLS	xviii
CHAPTER	
1 INTRODUCTION	
1.1 Research Background	1
1.2 Problem Statement	2
1.3 Objectives of the studies	3
1.4 Scope of research	3
1.5 Thesis structure	4
2 LITERATURE REVIEW	
2.1 Introduction	5
2.2 Oil palm industry in Malaysia	5
2.3 Oil palm empty fruit bunch (OPEFB)	5
2.3.1 Chemical characteristics of OPEFB	6
2.4 Overview of lignocellulosic biomass	7
2.5 Cellulose	8
2.6 Carboxymethyl cellulose (CMC)	9
2.6.1 Synthesis process	9
2.6.2 Mechanism of carboxymethyl cellulose (CMC)	10
2.7 Application of carboxymethyl cellulose (CMC) in ice cream	10
2.7.1 Manufacturing process of ice cream/ Major operation unit	12
2.7.2 Roles of ingredients in ice cream	15
2.7.3 Carboxymethyl cellulose (CMC) as a stabilizer in ice cream	16
2.7.4 Advantages of CMC compared to other materials	17
2.7.5 Effects of CMC in ice cream properties	18
2.7.5.1 Viscosity of ice cream mix	18
2.7.5.2 Melting characteristics	19
2.7.5.3 Overrun	19
2.7.5.4 Hardness	21
2.7.5.5 Mechanical loading tests	22

2.8	Concluding Remarks	23
3	MATERIALS AND METHODS	
3.1	Introduction	24
3.2	Materials	25
3.3	Overall experimental framework	26
3.4	Preparation of carboxymethyl cellulose (sCMC)	27
3.4.1	Isolation of α -cellulose	27
3.4.2	Extraction of carboxymethyl cellulose (sCMC)	27
3.5	Characterization of carboxymethyl cellulose (sCMC) - lignocellulosic compositions	28
3.6	X-ray diffractometry (XRD)	29
3.7	Fourier Transform Infrared Spectroscopy (FT-IR)	29
3.8	Scanning electron microscopy (SEM)	29
3.9	Physicochemical properties of CMC	29
3.9.1	Moisture content	30
3.9.2	Density of CMC powders	30
3.9.3	Flowability test	31
3.9.4	Colour analysis	31
3.9.5	Water Retention Capacity (WRC)	31
3.9.6	pH value, solubility, foam formability and organoleptic properties	32
3.10	Viscosity testing	32
3.11	Application of carboxymethyl cellulose (CMC) in hard ice cream	33
3.12	Textural properties	35
3.12.1	Viscosity of ice cream mix	35
3.12.2	Melting characteristics	35
3.12.3	Overrun	36
3.13	Mechanical testing	36
3.13.1	Hardness	36
3.13.2	Compression test	36
3.13.2.1	Mechanism of force measurement	37
3.14	Statistical analysis	39
4	RESULTS AND DISCUSSION	
4.1	Characteristics of raw OPEFB stalk fibers, cellulose and carboxymethyl cellulose (CMC)	40
4.1.1	Lignocellulosic composition	40
4.1.2	XRD analysis	41
4.1.3	FTIR analysis	43
4.1.4	Microstructural analysis	46
4.2	Properties of extracted carboxymethyl cellulose (CMC) from OPEFB stalk fibers	48
4.2.1	Physicochemical properties	48
4.2.2	Viscosity behaviour	52

4.3	Potential application of sCMC in hard ice cream - textural properties	56
4.3.1	Viscosity of ice cream mixture	56
4.3.2	Melting characteristics of hard ice cream	58
4.3.3	Overrun	60
4.4	Mechanical behaviour of hard ice cream	61
4.4.1	Hardness	61
4.4.2	Compression test	62
4.4.2.1	Loading-unloading compression test	63
4.4.2.2	Stress relaxation	65
5	CONCLUSION AND RECOMMENDATIONS	
5.1	Conclusion	68
5.2	Recommendations for future research	69
	REFERENCES	70
	APPENDICES	81
	BIODATA OF STUDENT	97
	PUBLICATIONS	98

LIST OF TABLES

Table		Page
2.1	Chemical properties and composition of OPEFB	7
2.2	Common ice cream mix composition	12
3.1	Formulations used to prepare hard ice cream to be analyzed	34
4.1	Densities of sCMC, COMM1 and COMM2	49
4.2	Flow characters of CMC samples	51
4.3	Values of L , a , and b for Each Type of CMC Powder	52
4.4	Extracted CMC from OPEFB stalk fibers (sCMC) parameters	52
4.5	Flow index and consistency index of sCMC and commercial CMC	55

LIST OF FIGURES

Figure		Page
2.1	Carboxymethylation process of cellulose	9
2.2	Schematic illustration of ice cream structure	11
2.3	Overall process flow diagram for ice cream manufacturing process	14
2.4	Schematic diagram of the fat globule stabilized with and without emulsifiers.	15
2.5	Engineering stress-strain curve in compression test	22
3.1	(a) Whole bunch of OPEFB, (b) OPEFB stalk bundle and (c) shredded OPEFB stalk fibers	25
3.2	Flow chart of overall experimental framework of this project	26
3.3	α -cellulose extracted from OPEFB stalk fibers	27
3.4	Carboxymethyl cellulose (sCMC) extracted from OPEFB stalk fibers	28
3.5	CMC solutions prepared for rheological testing. Left: sCMC, Right: commercial CMC	33
3.6	Sample of hard ice cream used for testing	34
3.7	Hard ice cream samples for melting characteristics test	35
3.8	LEGO Mindstorms EV3 structure and additional material used for the experiments :(a) whole LEGO structure, (b) closer view of the compression region, (c) endoscope, (d) FUTEK load cell (-20°C), (e) whole LEGO system	37
4.1	Lignocellulosic composition of raw OPEFB stalk fibers, bleached OPEFB stalk fibers, and OPEFB stalk α -cellulose	40
4.2	X-ray diffractograms of (a) raw OPEFB stalk fibers, (b) cellulose extracted from OPEFB stalk fibers, and (c) sCMC	42
4.3	FTIR spectra of (a) raw OPEFB stalk fibre, (b) bleached OPEFB stalk fibre, (c) OPEFB stalk α -cellulose, (d) sCMC, (e) COMM1, and (f) COMM2	44
4.4	SEM images of (a) raw OPEFB stalk fibers, (b) bleached OPEFB stalk fibers, (c) OPEFB stalk α -cellulose, (d) sCMC (e) COMM1 and (f) COMM2 at 300x magnification	47
4.5	Moisture content of sCMC, COMM1 and COMM2	48
4.6	Hausner ratio of sCMC, COMM1 and COMM2	50
4.7	Carr index of sCMC, COMM1 and COMM2	50
4.8	Water retention capacity of sCMC, COMM1 and COMM2.	51

4.9	Flow behaviour curves of sCMC, COMM1, and COMM2 solutions at: (a) 1% CMC solution and (b) 4% CMC solution	53
4.10	Viscosity as a function of shear rate for CMC solutions at (a) 1% CMC solution and (b) 4% CMC solution	54
4.11	Effects of stabilizers on viscosity of ice cream mixture	57
4.12	Effects of stabilizers on melt-down rate of hard ice cream	58
4.13	Effect of stabilizers on melting resistance of hard ice cream	59
4.14	Effect of stabilizers on overrun of ice cream	60
4.15	Effect of stabilizers on instrumental hardness of hard ice cream	62
4.16	Effect on loading unloading compression test on hard ice cream sample with commercial CMC and sCMC	64
4.17	Compression relaxation test results on ice cream sample with (a) commercial CMC and (b) sCMC. All tests are performed at 0.2mm/s	65
4.18	Step relaxation test result on ice cream sample with (a) commercial CMC and (b) sCMC. Test are performed at 0.2mm/s	67

LIST OF ABBREVIATIONS

ADF	acid detergent fibre
ADL	acid detergent lignin
C	carbon
CI	Carr index
CMC	Carboxymethyl cellulose
COMM1	CMC from Warisnove, Pahang, Malaysia
COMM2	CMC from R&M Chemicals, Petaling Jaya, Malaysia
CrI	crystallinity index
EFB	Empty fruit bunches
FFB	Fresh fruit bunches
FELCRA	Federal Land Consolidation and Rehabilitation Authority
FELDA	Federal Land Development Authority
FTIR	Fourier Transmission Infrared
G	guaicyls
H	ρ -hydroxyphenyls
H	hydrogen
HR	Hausner ratio
MCC	Microcrystalline cellulose
MPOB	Malaysian Palm Oil Board
N	nitrogen
NaClO ₂	sodium chlorite

NaOH	sodium hydroxide
NDF	Neutral detergent fibre
OPEFB	Oil palm empty fruit bunch
O	oxygen
PTFE	Polytetrafluoroethylene
S	syringyls
sCMC	CMC extracted from OPEFB stalk fibers
SEM	Scanning Electron Microscopy
WI	whiteness index
WRC	water retention capacity
XRD	X-ray diffractometer
YI	yellowness index
V_{gas}	volume of gas
V_{liquid}	volume of liquid
ρ_{tapped}	tapped density
ρ_{bulk}	bulk density
ΔE	total color difference

LIST OF SYMBOLS

°C	degree celcius
g/L	gram per litre
%	percentage
rev/min	revolutions per minute
β	beta
O ₂	oxygen
CO ₂	carbon dioxide
H ₂ O	water
h	hour
min	minutes
μm	micrometer
mm	milimeter
Pa	Pascal
U/g	unit per gram

CHAPTER 1

INTRODUCTION

1.1 Research Background

Southeast Asian countries like Malaysia generated abundance of biomass leftover particularly produced from the mill itself including the plantation area whilst oil palm is considered as the main crop in the country. Palm oil industry contribute a few types of solid biomass and the oil palm empty fruit bunch (OPEFB) is considered the largest solid waste produced. During the threshing process, the fresh fruit bunches (FFB) are rolled and threshed in rotating steel drums to separate the fruits from the stalks and this process generates the oil palm empty fruit bunches (OPEFB). The two main parts of OPEFB are stalk and spikelet, where Xiang et al. (2016) reported that the raw stalk fibers yielded the highest cellulose content and had the lowest lignin content. Likewise, the raw stalk fibers contained the lowest residual oil content when compared to the OPEFB as a whole and spikelets (Yunos et al. 2015; Xiang et al. 2016). Spikelets was surrounded by the fruitlets, which were the main source of oil and make it comprised of a higher amount of residual oil. Residual oil on the oil palm fibres need to be omitted because it can influence the derivation of cellulose production, thus it must go through a supplemental pre-treatment step.

The attempts to transform OPEFB into value-added products have gained wide attention because it is one of the most produced biomasses that come from oil palm refineries since it was known to have a rich source of cellulose. Cellulose must be transformed into its derivatives to be used in the food industry, such as carboxymethyl cellulose (CMC). CMC is a linear, water soluble, long-chain, and an anionic polysachharide artificial modified cellulose and it can be described as a white to cream color, tasteless, odorless, and free-flowing powder (Adinugraha et al., 2005) that is widely applicable for foods and pharmaceuticals (Tasaso, 2015). Extraction of CMC from oil palm fibers has been favourable given that Asian countries such as Malaysia generates abundance of oil palm biomass. OPEFB which is made up of lignocellulosic components will be used as the raw material to produce CMC.

The extracted cellulose; CMC act as a stabilizers and functional ingredients in hard ice cream. The solubility of these cellulose derivatives in cold and hot water causes the modification of rheological properties and produces structure and texture improvements of hard ice cream since hard ice cream is prepared in two phases which are during ice cream mix preparation and freezing process. Only small amount of CMC can be utilized to achieved its credit functionality to hard

ice cream texture and condition. Besides, 0.5% is the highest amount that can be used in order to utilize CMC in hard ice cream. This study will also focus on the potential application of extracted CMC on hard ice cream attributes. Such data are useful in accessing the overall quality during the production and handling of hard ice cream, as well as in developing a desirable mouthfeel. The texture, which can be defined as the physical and mouthfeel characteristics of a food or drink, is very unique in hard ice cream due to the fact that it contains all three state of matter: solid (found in the ice crystals and fat globules), liquid (found in the sugar solution), and gas (found in the air bubbles). The desired texture is essential for customer satisfaction and can be evaluated through a variety of viscoelastic and mechanical properties, which include its viscosity behaviour, hardness, compressive strength, and stress relaxation. Mechanical tests for each of these properties were developed in order to compare the textural characteristics of regular hard ice creams due to its different composition (Casarotto, 2015).

No report on utilizing the raw OPEFB stalk fibers to produce carboxymethyl cellulose (CMC) is currently available. Main objective is to create a complete link of using palm oil mill by-product to produce valuable food enhancer and application of it. Thus, it is an essential to have a proper study to recover the lignocellulosic components for the conversion of cellulose derivatives. This study also will help the palm industry to provide further information about the oil palm biomass, which is important for future bioconversion processes. The production of CMC from raw OPEFB stalk fibers was conducted by using a chemical extraction method, prior to proceeding with the physicochemical and rheological analyses of the extracted CMC. Comparison was made between the CMC produced in this study with those commercially available. The current research provided the first step towards the feasibility of clean OPEFB stalk fibers as a source to produce CMC. This will promote the usage of raw material and may boost the economic value of hard ice cream product in Malaysia since it utilizes the palm oil by-product abundance.

1.2 Problem Statement

Development of products that transform waste materials to beneficial products is of great importance and need to be prioritized. During oil collection in the palm oil mills, excessive waste are generated after the threshing process. One of the abundance is the oil palm empty fruit bunch (OPEFB). Although there are plenty of studies were done to acquire cellulose derivatives from oil palm fibers, all projects generally emphasized on the whole bunch of OPEFB, without specific study on particular parts of OPEFB for instance stalk and spikelet. It is often utilized as a whole but researchers have found that raw stalks fibers comprised the highest percentage of cellulose and the lowest lignin content compared to OPEFB as a whole and spikelet fibres. On top of that, lack studies

emphasized on the potential application of the extracted CMC have been tested on the hard ice cream quality in terms of its textural properties and mechanical behaviour.

1.3 Objectives of the Studies

The main objective of this thesis work is to characterize carboxymethyl cellulose (CMC) derived from oil palm empty fruit bunch (OPEFB) stalks fibers for hard ice cream application. To be specific, this research aims:

1. To characterize physicochemical properties of carboxymethyl cellulose (CMC) extracted from oil palm empty fruit bunches (OPEFB) stalks fibers;
2. To assess the potential application of extracted CMC by analysing the textural properties and mechanical behaviour of hard ice cream.

1.4 Scope of Research

This study is principally concerned about the feasibility study of utilizing the oil palm empty fruit bunch (OPEFB) stalk fibers as the material to be extracted as carboxymethyl cellulose (CMC). The research continues with the potential application of the extracted CMC on hard ice cream properties. During this research, an in depth study has been performed in studying the characteristics of the material throughout the extraction process that involved lignocellulosic properties, FTIR analysis, XRD analysis and microstructural analysis. Then, the extracted CMC were further analyse on its properties; physicochemical properties and viscosity properties. On the other hand, the potential application of the extracted CMC has been tested on hard ice cream properties that involved the textural properties and mechanical behaviour and the performance were compared with the hard ice cream prepared using commercial CMC. The potential application of the extracted CMC from OPEFB stalk fibers were analysed on hard ice cream properties including viscosity of ice cream mix, melting characteristics, overrun, hardness test and mechanical compression. The properties were compared with ice cream prepared using commercial CMC. Some limitation occurred for mechanical test of hard ice cream samples by using the actual texture analyser from commercial brand. This was because when the test was done at room temperature, the hard ice cream did not hold its structure and melted faster. Hence, a toy-brick miniature tester was designed to study the compression behaviour of hard ice cream produced using the extracted CMC in a small freezer to maintain the hard ice cream temperature and shape. Lego Mindstorms EV3 consists of microprocessors, motors, and sensors that can be programmed to perform basic tasks on repeat. It involves a capable software to manage any essential movement that will assist the features of the toy-brick.

Matlab programme was used to navigate a simple up, down, up, move sequence on a loop.

1.5 Thesis Structure

There are 5 chapters in this thesis. In Chapter 1, a brief introduction of the overall research was written together with objectives of the study and the problem statement of the research. In Chapter 2, extensive literature review was written covering current available knowledge on the oil palm biomass, carboxymethyl cellulose (CMC) and hard ice cream properties. In Chapter 3, the overall experimental framework was explained on how the materials were prepared, method used on extracting carboxymethyl cellulose (CMC), characterization of materials throughout the extraction process, analysis on CMC properties and the procedure on determining the hard ice cream properties. The objectives of the research were further explained in Chapter 4. First objective was well intricate in which to produce and characterize the extracted carboxymethyl cellulose (CMC) extracted from oil palm empty fruit bunch (OPEFB) stalk fibers. Meanwhile, second objective was elaborated in which to study the potential application of the extracted CMC from OPEFB stalk fibers on hard ice cream properties. The hard ice cream properties were compared with hard ice cream prepared using commercial CMC. Finally, in Chapter 5, final conclusions and some of recommendations were mentioned. Appendix and references used in this entire study was listed at the back of the thesis.

REFERENCES

- Abdullah, E. C. and Geldart, D. (1999). The use of bulk density measurements as flowability indicators. *Powder Technology*, 102, 151-165.
- Abraham, E., Deepa, B., Pothan, L. A., John, M. J., Thomas, S., Anandjiwala, R., and Cvelbar, U. (2011). Extraction of nanocellulose fibrils from lignocellulosic fibres- A novel approach. *Carbohydrate Polymers*, 86(4), 1468-1475.
- Adinugraha, M. P., Marseno, D. W., and Haryadi (2005). Synthesis and characterization of sodium carboxymethylcellulose from cavendish banana pseudo stem (*Musa cavendishii* LAMBERT), *Carbohydrate Polymers*, 62(2), 164-169.
- Ahmad, F. B., Zhang, Z., Doherty, W. O. S., O'Hara, I. M. (2016). Evaluation of oil production from oil palm empty fruit bunch by oleaginous micro-organisms. *Biofuels, Bioproducts & Biorefining*, 10(4), 378-392.
- Arbuckle, W. S. (1986). Ice cream, ed Arbuckel, W. S. pp 120-140, New York: Springer US.
- ASTM D1439-03 (2008). Standard test methods for sodium carboxymethylcellulose, *ASTM International*, West Conshocken, PA.
- Azubuike, C. P., and Okhamafe, A. O. (2012). Physicochemical, spectroscopic and thermal properties of microcrystalline cellulose derived from corn cobs. *International Journal of Recycling Organic Waste in Agriculture*, 1(1), 9-12.
- Baharuddin, A. S., Hock, L. S., Yusof, M. Z. M., Abdul, N. A. R., Shah, U. K. M., Hassan, M. A., Wakisaka, M., Sakai, K., Shirai, Y. (2010). The effect of palm oil mill effluent (POME) anaerobic sludge from 500 m³ of closed anaerobic methane digested tank on pressed-shredded empty fruit bunch (EFB) composting process. *African Journal of Biotechnology*, 9 (16), 2427-2436.
- Baharuddin, A. S., Sulaiman, A., Kim, D. H., Mokhtar, M. N., Hassan, M. A., Wakisaka, M., Shirai, Y., Nishida, H. (2013). Selective component degradation of oil palm empty fruit bunches (OPEFB) using high-pressure steam. *Biomass and Bioenergy*, 55, 268-275.
- Bahramparvar, M. and Mazehari Tehrani, M. (2011). Application and functions of stabilizers in ice cream. *Food Reviews International*, 27(4), 389-407.
- Bahramparvar, M., Mazaheri Tehrani, M. and Razavi, S. M. A. (2013). Effects of a novel stabilizer blend and presence of κ -carrageenan on some properties of vanilla ice cream during storage. *Food Bioscience*, 3 (0), 10-18.

- Benchabane, A. and Bekkour, K. (2008). Rheological properties of carboxymethyl cellulose solutions. *Colloid Polymer Science*, 286, 1173-1180.
- Benjamins, J., Vingerhoeds, M. H., Zoet, F. D., de Hoog, E. H. A., van Aken, G. A. (2009). Partial coalescence as a tool to control sensory perception of emulsions. *Food Hydrocolloids*, 23(1), 102-115.
- Bennion, M. (1975). *Introductory foods*, 6th ed. Macmillan Publishing Co. Inc., New York and Collier Macmillan Publishers London.
- Berger, K. G. (1990). Ice cream. In: *food Emulsions*. ed. Larsson, K. and Friberg, S. E. pp 21-50. New York: Marcel Dekker Inc.
- Berger, K. G. (1997). Ice cream, 3rd ed. In: *food Emulsions*. ed. Larsson, K. and Friberg, S. E. pp 82-120. New York: Marcel Dekker Inc.
- Berger, K. G., and White, G., W. (1971). An electron microscopical investigation of fat destabilization in ice cream. *Journal of Food Technology*, 6, 285-294.
- Berger, K. G., Bullimore, B. K., White, G. W., and Wright, W. B. (1972). The structure of ice cream. *Dairy Industry* 37, 419-425, 493-497.
- Bhandari, V. (2001). *Ice cream manufacture and technology*. ed. Murtaza, C. F. pp 100-130, New Delhi: Tata McGraw Hill Pub. Co.Ltd.
- Bhattacharyya, D., Singhal, R. S., and Kulkarni, P. R. (1995). A comparative account of conditions for synthesis of sodium carboxymethyl starch from corn and amaranth starch. *Carbohydrate Polymers*, 27(4), 247-253.
- Biswal, D. R., and Singh, R. P. (2004). Characterisation of carboxymethyl cellulose and polyacrylamide graft copolymer. *Carbohydrate Polymers*, 57(4), 379-387.
- Bono, A., Ying, P. H., Yan, F. Y., Muei, C. L., Sarbatly, R., and Krishnaiah, D. (2009). Synthesis and characterization of carboxymethyl cellulose from palm kernel cake. *Advances in Natural and Applied Sciences*, 3(1), 5-11.
- Casarotto, A.,Lundgren, K.,and Wolfgang, E. (2015). Effects of composition and flavor on viscoelastic properties of ice cream. *Worcester Polytechnic Institute, England*.
- Chang, Y. and Hartel, R. W. (2002). Development of air cells in a batch ice cream freezer. *Journal of Food Engineering*, 55, 71-78.

- Charalambides, M. N. and Dean, G. D. (1997). Constitutive models and their data requirements for use in Finite Element Analysis of adhesives under impact loading, *CMMT (A)*59.
- Chinnan, M. S., McWaters, K. H., and Rao, V. N. M. (1985). Rheological characterization of garin legume pastes and effect of hydration time and water level on apparent viscosity. *Journal of Food Science*, 50, 1167-1171.
- Clarke, C. (2004). Making ice Cream in the factory. In *The Science of Ice Cream* ed. Clarke ,C. pp 72-75, UK: The Royal Society of Chemistry.
- Clarke, C. (2008). *The Science of Ice Cream* 3rd edition. ed. Clarke ,C. pp 88-175, UK: The Royal Society of Chemistry.
- Crouter, A., and Briens, L. (2014). The effect of moisture on the flowability of pharmaceutical excipients. *AAPS PharmSciTech*, 15(1), 65-74.
- Damerow, G. (1994). *Ice cream: The whole scoop*. ed. Damerow, G. pp. 100-201, UK: Glenbridge Publishing Ltd.
- Dashtban, M. (2009). Fungal bioconversion of lignocellulosic residues: Opportunities and perspectives. *International Journal of Biological Sciences*, 5 (6), 578-595.
- Davies, E., Dickinson, E. and Bee, R. D. (2000). Shear stability of sodium caseinate emulsions containing monoglyceride and triglyceride crystals. *Food Hydrocolloids*, 14, 145-153.
- Davies, E., Dickinson, E. and Bee, R.D. (2001). Orthokinetic destabilization of emulsions by saturated and unsaturated monoglycerides. *International Dairy Journal*, 11(10), 827-836.
- Desrosier, N. N. and Desrosier, J. N. (1977). *The Technology of Food Preservation*. (4th ed). ed. Desrosier, J. N. pp 154-165. USA: AVI Publishing Co. Inc.
- Dickinson, E., and Tanai, S. (1992). Protein displacement from the emulsion droplet surface by oil- soluble and water-soluble surfactants. *Journal of Agricultural Food and Chemistry*, 40, 179- 183
- Eisner, M. D., Wildmoser, H., Windhab, E. J. (2005). Air cell microstructuring in a high viscous ice cream matrix. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 263, 390-399.
- Elanthikkal, S., Gopalakrishnanpanicker, U., Varghese, S., and Guthrie, J. T. (2010). Cellulose microfibrils produce from banana plant wastes: Isolation and characterization. *Carbohydrate Polymers*, 80(3), 852-859.

- Fahma, F., Iwamoto, S., Hori, N., Iwata, T., and Takemura, A. (2010). Isolation, preparation, and characterization of nanofibers from oil palm empty fruit bunch. *Cellulose*, 17(5), 977-985.
- Fang, J. M., Fowler, P.A., Tomkinson, J., Hill, C. A. S. (2002). The preparation and characterisation of a series of chemically modified potato starches. *Carbohydrate Polymers* 47(3), 245-252.
- FAO/World Health Organization (WHO) Expert Committee (2011). *Compendium of Food Additive Specifications*, Food and Agriculture Organization of the United Nations, Rome, Italy.
- Fiol, C., Prado, D., Romero, C., Laburu, N., Mora, M., Alava, I. (2017). Introduction of a new family ice creams. *International Journal of Gastronomy and Food Science*, 7, 5-10.
- Fisher, A. B. and Fong, S. S. (2014). Lignin biodegradation and industrial implications. *AIMS Bioengineering*, 1(2), 92-112.
- Fitzpatrick, J. J., Barringer, S. A., and Iqbal, T. (2004). Flow property measurement of food powders and sensitivity of Jenike's hopper design methodology to the measured values. *Journal of Food Engineering*, 61, 399-405.
- Foster E. M., F. E. Nelson, M. L. Speck, R. N., Olson, J. C. (1958). Dairy Microbiology, ed. Olson, J. C. pp 44-90, UK: MacMillan and Co Ltd.
- Garcia-Nunez, J. A., Ramirez-Contreras, N. E., Rodriguez, D. T., Silva-Lora, E., Frear, C. S., Stockle, C., Garcia-Perez, M. (2016). Evolution of palm oil mills into bio-refineries: Literature review on current and potential uses of residual biomass and effluents. *Resources, Conservation and Recycling*, 110, 99-114.
- Gelin, J. L., Poyen, L., Rizzotti, R., Le Meste, M., Courthadon, J. L., Lorient, D. (1996). Interactions between food components in ice cream. Part 1: Unfrozen emulsions. *Food Hydrocolloids*, 10, 385-93.
- Granger, C., Barey P., Combe, N., Veschambre, P., Cansell, M. (2003). Influence of the fat characteristics on the physicochemical behaviour of oil-in-water emulsions based on milk proteins-glycerol esters mixtures. *Colloids and Surfaces B: Biointerfaces*, 32, 353-363.
- Goff, H. D. (1997). Instability and partial coalescence in shippable dairy
- Goff, H. D. (2015). Ice cream and frozen desserts. *Ullmann's Encyclopedia of Industrial Chemistry*, Weinheim, Germany.

- Goff, H. D. and Hartel, R. W. (2013). Ice cream structure. In Ice Cream 7th edition. ed. Goff, H. D. & Hartel, R. W. pp. 325-33. New York: Springer.
- Goh, C. S., Tan, K. T., Lee, K. T., Bhatia, S. (2010). Bio-ethanol from lignocelluloses: Status, perspectives and challenges in Malaysia. *Bioresource Technology*, 101, 4834-4841.
- Gulati, I., Park, J., Maken, S., Lee, M. G. (2014). Production of Carboxymethylcellulose fibers from waste lignocellulosic sawdust using NaOH/NaClO₂ pretreatment. *Fibers and Polymers*, 15(4), 680-686.
- Hartel, R.W. (1996). Ice crystallization during the manufacture of ice cream. *Trends Food Science and Technology*, 7, 315-321.
- Hasenhuettl, G. L. (2008). Overview of food emulsifiers. In Food emulsifiers and their applications. 2nd edition. ed. Hasenhuettl, G. L. and Hartel, R. W. pp 1-10, New York: Springer.
- Hassan, A., Salema, A. A., Ani, F. N., Bakar, A. A. (2010). A review on oil palm empty fruit bunch fiber-reinforced polymer composite materials. *Polymer Composites*, 31(12), 2079-2101.
- He, X., Wu, S., Fu, D., Ni, J. (2009). Preparation of sodium carboxymethyl cellulose from paper sludge. *Journal of Chemical Technology and Biotechnology*, 84(3), 427-434.
- Hui, Y. H., Legaretta, I. G., Cornillon, P., Lim, M. H., Murrell, K. D. and Nip, W. K. (2004). *Handbook of Frozen Foods*. pp. 499-519. New York: CRC Press.
- Hunterlab (2012). *Measuring Color Using Hunter L, a, b Versus CIE 1976 L*a*b**, Hunter Associates Laboratory Inc., Reston, VA, USA.
- Introduction to Interpretation of Infrared Spectra. N.d. Retrieved 16 July 2018 from www2.ups.edu/faculty/hanson/Spectroscopy/IR/IRInterpretation.htm
- Kalia, S., Kaith, B., and Kaur, I. (2009). Pretreatments of natural fibers and their application as reinforcing material in polymer composites - A review. *Polymer Engineering & Science*, 49(7), 1253-1272.
- Keeney, P. G. (1958). The fat stability problem in ice cream. *Ice Cream Review*, 42(7), 26-45
- Kilcast, D., and Clegg, S. (2002). Sensory perception of creaminess and its relationship with food structure. *Food Quality and Preference*, 13, 609-623.

- Kirk, R. E., and Othmer, D. F. (1967) Cellulose encyclopedia of chemical technology 2nd edition. ed. Othmer, D. F. pp 593-683, New York: Wiley.
- Kumar, P., Barrett, D. M., Delwiche, M. J., and Stroeve, P. (2009). Methods for pretreatment of lignocellulosic biomass for efficient hydrolysis and biofuel production. *Industrial and Engineering Chemistry Research*, 48(8), 3713-3729.
- Khalil, M. I., Hasem, A., and Habeish, A. (1990). Carboxymethylation of maize starch. *Starch* 42(2), 60-63.
- Larrauri, J. A., Ruperez, P., Borroto, B., and Saura-Calixto, F. (1996). Mango peels as a new tropical fibre- Preparation and characterization, *LWT- Food Science and Technology*, 29(8), 729-733.
- Mamdouh, T. G., and Esmail, M. N. (1997). Rheological properties of carboxymethyl cellulose. *Journal of Applied Polymer Science*, 64(2), 289-301.
- Mario, P. A., Djagal, W. M., and Haryadi (2005). Synthesis and characterization of sodium carboxymethylcellulose from cavendish banana psuedo stem (*Musa cavendishii*), *Carbohydrate Polymers*, 62, 164-169.
- Marshall, R. T., Goff, H. D., and Hartel, R.W. (2003). Ice cream 3rd ed., ed. Hartel, R. W. pp 203-349, New York: Aspen Publishers.
- Marshall, R.T. and Arbuckle, W.S. (1996) Ice Cream. 5th Edition, Chapman & Hill, New York.
- Maryam, B. and Mostafa, M. T. (2011). Applications and functions of stabilizers in ice cream. *Food Reviews International*, 27, 389-407.
- Mazaheri, H., Lee, K. T., Bhatia, S. Mohamed, A. R. (2010). Subcritical water liquefaction of oil palm fruit press fiber for the production of bio oil: Effect of catalyts. *Bioresource Technology*, 101(2), 745-751.
- Moeenfarid, M. and Tehrani, M. M. (2008). Effect of some stabilizers on the physicochemical and sensory properties of ice cream type frozen yogurt. *American-Eurasian Journal of Agriculture and Environmental Science*, 4(5), 584-589.
- Mohammed M. A. P. 2012. *Mechanical characterization, processing and microstructure of wheat flour dough*, PhD Thesis, Imperial College London.
- Mohammed, M. A. A., Salmiaton, A., Wan Azlina, W. A. K. G., and Mohamad Amran, M. (2012). Gasification of oil palm empty fruit bunches- A characterization and kinetic study. *Bioresource Technology*, 110, 628-636.

- Mondal, M. I. H., Yeasmin, M. S., and Rahman, M. S. (2015). Preparation of food grade carboxymethyl cellulose from corn husk agrowaste. *International Journal of Biological Macromolecules*, 79, 144-150.
- Mullins, L. (1947). Effect of stretching on the properties of rubber. *Journal of Rubber Research*, 16, 275-289.
- Muse, M. R. and Hartel, R. W. (2004). Ice cream structural elements that affect melting rate and hardness. *Journal of Dairy Sciences*, 87, 1-10.
- Mwaikambo, L. Y. and Ansell, M. P. (2001). The determination of porosity and cellulose content of plant fibers by density methods. *Journal of Materials Science Letters*, 20(23), 2095-2096.
- Nazir, M. S., Wahjoedi, B. A., Yussof, A. W., and Abdullah, M. A. (2013). Eco-friendly extraction and characterization of cellulose from oil palm empty fruit bunches. *BioResources*, 8(2), 2161-2172.
- Nielsen, B. J. (1984). Combined emulsifier/ stabilizer for ice cream. *Ice cream frozen confectionary*, 35, 401-409.
- Obi Reddy, K., Shukla, M., Maheswari, C. U., Rajulu, A. V. (2012). Evaluation of mechanical behaviour of chemically modified *Borassus* fruit short fiber/unsaturated polyester composites. *Journal of Composite Materials*, 46(23), 2987-2998.
- Ozdemir, C., Dagdemir, E., Ozdemir, S., Sagdic, O. (2008). The effects of using alternative sweeteners to sucrose on ice cream quality. *Journal of Food Quality*, 31(4), 415-428.
- Peckham, G. (1974). Foundations of food preparation 3rd edition, ed. Peckham, G. pp 39-178. New York: Macmillan Publishing Co., Inc.
- Petersen, W. E. (1950). Dairy Science, 2nd ed., eds. Gregory, R. W. Lippinotco. pp 102-143, New York: Macmillan Publishing Co. Inc.
- Pintor, A. and Totosaus, A. (2012). Ice cream properties affected by lambda-carrageenan or iota-carrageenan interaction with locust bean gum/ carboxymethylcellulose mixture. *International Food Research Journal*, 4, 1409-1414.
- Potter, N. N. (1978). Food Science. ed. Potter, N. N. pp. 56-86, USA: AVI Publishing Co., Inc.
- Pushpamalar, V., Langford, S. J., Ahmad, M., and Lim, Y. Y. (2006). Optimization of reaction conditions for preparing carboxymethyl cellulose from sago waste, *Carbohydrate Polymers* 64(2), 312-318.

- Rachatanapun, P., Luangkamin, S., Tanprasert, K., and Suriyatem, R. (2012). Carboxymethyl cellulose film from durian rind. *Food Science and Technology*, 48(1), 52-58.
- Ramli, R., Junadi, N., Beg, M. D. H., and Abdullah, M. A. (2013). Microcrystalline cellulose from oil palm empty fruit bunch fiber *via* simultaneous ultrasonic and alkali treatment. *International Journal of Chemical, Nuclear, Materials, and Metallurgical Engineering* 8(2), 8-11.
- Razali, N., Hossain, M. S., Taiwo, O. A., Ibrahim, M., Nadzri, N. W. M., Razak, N., and Kassim, M. H. M. (2017). Influence of acid hydrolysis reaction time on the isolation of cellulose nanowhiskers from oil palm empty fruit bunch microcrystalline cellulose. *BioResources*, 12(3), 6773-6788.
- Robinson, R. K. (1981). Dairy microbiology. ed. Robinson, R. K. pp. 108-132, UK: Applied Science Publishers.
- Roland, A. M., Phillips, L. G., Boor, K. J. (1999). Effects of fat content on the sensory properties, melting, color, and hardness of ice cream. *Journal of Dairy Sciences*, 82(1), 32-38.
- Roncero, M. B., Torres, A. L., Colom, J. F., and Vidal, T. (2005). The effect of xylanase on lignocellulosic components during the bleaching of wood pulps. *Bioresource Technology*, 96(1), 21-30.
- Rosalina, P. S. and Richard, W. H. (2004). Effects of overrun on structural and physical characteristics of ice cream. *International Dairy Journal*, 14, 255-262.
- Sakurai, K., Kokubo, S., Hakamata, K., Tomita, M., Yoshida, S. (1996). Effect of production conditions on ice cream melting resistance and hardness. *Milchwissenschaft*, 51(8), 451-4.
- Sánchez, C. (2009). Lignocellulosic residues: Biodegradation and bioconversion by fungi. *Biotechnology Advances*, 27(2), 185-194.
- Segal, L., Creely, J. J., Martin, A. E., and Conrad, C.M. (1959). An empirical method for estimating the degree of crystallinity of native cellulose using X-ray diffractometer *Textile Research Journal*, 29, 786-794.
- Segall, K. I. and Goff, H. D. (2002). A modified ice cream processing routine that promotes fat destabilization in the absence of added emulsifier. *International Dairy Journal*, 12(2), 1013-1018.
- Shukri, W. H. Z., Hamzah, E. N. H., Halim, N. R. A., Isa, M. I. N., Sarbon, N. M. (2014). Effect of different types of hydrocolloids on the physical and

sensory properties of ice cream with fermented glutinous rice (tapai pulut). *International Food Research Journal*, 21(5), 1777-1787.

Sofjan, R. P., and Hartel, R. W. (2004). Effects of overrun on structural and physical characteristics of ice cream. *International Dairy Journal*, 14, 255-262.

Sopade, P. A., and Kassum, A. L. (1992). rheological characterization of Akamu, a semi-liquid food from maize, millet and sorghum. *Journal of Cereal Science*, 15, 193-202.

Tasaso, P. (2015). Optimization of reaction conditions for synthesis of carboxymethyl cellulose from oil palm fronds. *International Journal of Chemical Engineering and Applications*, 6(2), 101-104.

Taylor, A. J., and Linforth, R. S. T. (1996). Flavour release in the mouth. *Trends in Food Science and Technology*, 7, 342-346.

Tharp, B. W., Forrest, B., Swan, C., Dunning, L., Hilmo, M. (1998). Basic factors affecting ice cream meltdown. Pages 54-64 in *Ice Cream: Proceedings of the International Symposium held in Athens, Greece, 18-19 September 1997*. W. Buchheim, ed. International Dairy Federation, Brussels, Belgium.

Tharp, B. W. and Young, L. S. (2013). *An encyclopedic guide to ice cream science and technology*. ed. Tharp, B. W. pp 31-42. USA: DEStech Publications, Inc.

Tijsen, C. J., Kolk, H. J., Stamhuis, E. J., Beenackers, A. A. C. M. (2001). An experimental study on the carboxymethylation of granular potato starch in non-aqueous media. *Carbohydrate Polymers*, 45, 219-226.

Thomas, G., Paquita, E., Thomas, J. (2002). Cellulose ethers: Encyclopedia of polymer science and technology. ed. Thomas J. pp 11-35, New York : Wiley.

Trgo, C. (2003). Factors affecting texture of ice cream (Vol. 1). ed. Trgo, C. pp. 109-113, UK: Woodhead Publishing Ltd.

Vanapalli, S. and Coupland, J. N. (2001). Emulsions under shear - The formation and properties of partially coalesced lipid structures. *Food Hydrocolloids*, 15(4), 507-512.

Van Aken, G. A. (2003). Competitive adsorption of protein and surfactants in highly concentrated emulsions: Effect on coalescence mechanisms. *Colloid and Surfaces A: Physicochemical and Engineering Aspects*, 213(2-3), 209-219.

Varnam, A. H. and Sutherland, J. P. (1994). *Milk and Milk products: Technology, chemistry and microbiology*. ed. Sutherland, J. P. pp. 109-118, UK: Chapman and Hall.

- Wahab, A. G. (2015) Palm oil PSD revisions. GAIN Report for USDA Foreign Agricultural Service. GAIN Report No: MY5014.
- Walstra, P. (1983). Formation of emulsions. In *Encyclopedia of Emulsion Technology*, Volume I, ed. Dekker, M. pp 57-127. New York: Wiley.
- Walstra, P. and Jonkman, M. (1998) The role of milk fat and protein in ice cream, in *Ice Cream*, ed. Buchheim, C. W. pp. 17-24, International Dairy Federation, Brussels.
- Wan Razali, W. A., Baharuddin, A. S., Talib, A. T., Sulaiman, A., Naim, M. N., Hassan, M. A., Shirai, Y. (2012). Degradation of oil palm empty fruit bunches (OPEFB) fibre during composting process using in-vessel composter. *BioResources*, 7(4), 4786-4805.
- Wilbey, R. A., Cooke, T., and Dimos, G. (1998). Effects of solute concentration, overrun and storage on the hardness of ice cream. Pages 186-187 in *Ice Cream: Proceedings of the International Symposium held in Athens, Greece, 18-19 September 1997*. W. Buchheim, ed. International Dairy Federation, Brussels, Belgium.
- Wilbey, R.A. (2003). Homogenization. In: *Encyclopedia of food sciences and nutrition*. eds. Caballero, B., Trugo, L. and Finglas, P. M. pp 3119-3125, London: Academic Press.
- Williams, A. and Dickinson, E. (1995). Shear induced instability of oil-in-water emulsions. In *Food macromolecules and colloids*. ed. Dickison, E. and Lorient, D. pp 252-255. UK: Royal Society of Chemistry.
- Xiang, L. Y., Hanipah, S. H., Mohammed, M. A. P., Baharuddin, A. S., and Lazim, A. M. (2015). Microstructural, mechanical, and physicochemical behaviours of alkali pre-treated oil palm stalk fibres. *BioResources*, 10(2), 2783-2796.
- Xiang, L. Y., Mohammed, M. A. P., and Baharuddin, A. S. (2016). Characterisation of microcrystalline cellulose from oil palm fibres for food applications. *Carbohydrate Polymers*, 148, 11-20.
- Yanmei, Z., Xiaoyi, H., Min, Z., Xiaofeng, Z., and Jingyang, N. (2012). Preparation and characterization of modified cellulose for adsorption of Cd (II), Hg (II), and acid fuchsin from aqueous solutions. *Industrial and Engineering Chemistry Research*, 52(2), 876-884.
- Yunos, N. S. H. M., Baharuddin, A. S., Yunos, K. F. M., Naim, M. N., and Nishida, H. (2012). Physicochemical property changes of oil palm mesocarp fibers treated with high-pressure steam. *BioResources*, 7(4), 5983-5994.

Yunos N. S. H. M, Baharuddin A. S., Md Yunos K. F., Hafid H. S., Busu Z., Mokhtar M. N., Md Som A. (2015). The Physicochemical Characteristics of Residual Oil and Fibers from Oil Palm Empty Fruit Bunches. *Bio Resources*, 10(1), 14-29.

Zhang, J. and Wu, D. (1992). Characteristics of the aqueous solution of carboxymethyl starch ether. *Journal of Applied Polymer Science*, 46(2), 369-374.

