UNIVERSITI PUTRA MALAYSIA

MECHANICAL AND TRIBOLOGICAL ENHANCEMENT OF AA6063 ALUMINUM ALLOY USING SOLID SPHERE FLY ASH PARTICLES REINFORCEMENT

ALAA MOHAMMED RAZZAQ

FK 2018 130

MECHANICAL AND TRIBOLOGICAL ENHANCEMENT OF AA6063 ALUMINUM ALLOY USING SOLID SPHERE FLY ASH PARTICLES REINFORCEMENT

By

ALAA MOHAMMED RAZZAQ

Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in Fulfillment of the Requirements for the Degree of Doctor of Philosophy

May 2018

DEDICATION

This thesis is dedicated to:

The sake of Allah, my Creator and my Master,

My great teacher and messenger, Mohammed (May Allah bless and grant him and his family),

The memory of my parents, my late father and my late mother, whose prayers, support and dream.
My humble effort I dedicate to my sweet and loving Wife **(Roieda)**
I am grateful to her support ….
To my daughter (Wseq) and sons (Mohammed and Reda), whose prayers and wishes.

All the people in my life who touch my heart,

I dedicate this research.

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy

MECHANICAL AND TRIBOLOGICAL ENHANCEMENT OF AA6063 ALUMINUM ALLOY USING SOLID SPHERE FLY ASH PARTICLES REINFORCEMENT

By

ALAA MOHAMMED RAZZAQ

May 2018

Chairman : Dayang Laila Abang Abdul Majid, PhD
Faculty : Engineering

Fly ash (FA) has gathered widespread attention as a potential reinforcement for metal matrix composites (MMCs) to enhance the properties and reduce the cost of production. It is the most inexpensive and low density reinforcement available in large quantities as solid waste by-product. Aluminum alloys have been used in various engineering fields, such as automotive and aerospace industries, due to their low density and good mechanical properties. There is need to improve the performance of these alloys by adding reinforcements to extend their usage in many applications under wider service conditions. In this work, efforts are directed to improve the mechanical and tribological properties of AA6063 with solid sphere FA reinforcements. Relevant works were found to focus only on cenosphere FA particulates. There are many fabrication techniques available to manufacture these composites according to matrix and reinforcement materials. The compocasting technique for the fabrication of the AA6063 matrix composite reinforced with FA particles is the focus of this research. FA content, in the range of 0 –12 wt. % in increasing increments of 2% were added to the molten AA6063 alloy until they were completely blended and cooled down just below the liquidus to keep the slurry in the semi-solid state. Afterwards, the molten AA6063-FA composites were cast into prepared cast iron molds. Several techniques were used to evaluate the microstructure properties of these composites. The bulk density, porosity percentage and thermal properties of the composites were tested. This study also investigated the effect of FA addition on the mechanical properties of AA6063-FA composites. The effect of FA addition, applied load and sliding speed on the dry sliding frictional and wear behaviour has been considered in this study. Pin on disc test were conducted at different loads (24.5, 49, and 73.5 N) as well as the various sliding speeds using in this test (150, 200, and 250 rmp.) with a constant period time (10 minutes). The microstructural results showed good distribution of FA particles in the AA6063 matrix with interfacial bonding. The AA6063-FA composites exhibited good mechanical and tribological properties than the unreinforced AA6063 aluminum

alloy. The microhardness and the strength significantly increased with increase of FA content. While the impact energy and density decreased with increase in the FA content. The tensile strength of AA6063 alloy increased by 28 % with 10 wt. % of FA, the compression strength improved by 100 % with 10 wt. % of FA. Wear rate decreased with increase of FA content but increased with increase of sliding speed and applied load. The coefficient of friction declined with increase of FA content, sliding speed, and applied load.

The findings from the statistical analysis are the order of significance of the design parameters, which revealed the FA content as having the highest influence on the wear rate and coefficient of friction, followed by applied load and sliding speed. Addition to that, the strongest interaction effects is FA content with applied load. The models produced would be a useful tool in the process of AA6063-FA composites design, and can be used as a replacement for the expensive conventional experimental tests.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

PENAMBAHBAIKAN MEKANIKAL DAN TRIBOLOGI BAGI ALOI ALUMINUM AA6063 DIPERKUKUHKAN DENGAN ZARAH ABU TERBANG BERSFERA PADU

Oleh

ALAA MOHAMMED RAZZAQ

Mei 2018

Pengerusi : Dayang Laila Abang Abdul Majid, PhD
Fakulti : Kejuruteraan

Abu terbang (FA) telah menarik minat ramai sebagai satu potensi pengukuhan terhadap komposit matriks logam (MMC) dalam meningkatkan sifat-sifat dan mengurangkan kos pengeluaran. Ia merupakan bahan pengukuhan yang murah dan berketumpatan rendah yang wujud dalam kuantiti yang banyak sebagai produk sampingan sisa pepejal. Aluminum alloys have been used in various engineering fields, such as automotive and aerospace industries, due to their low density and good mechanical properties. Aloi aluminum telah digunakan dalam pelbagai bidang kejuruteraan seperti industri automotif dan aeroangkasa, kerana ketumpatannya yang rendah dan sifat mekanikalnya yang baik. Terdapat keperluan untuk memperbaiki prestasi aloi ini melalui penambahan pengukuhan untuk meningkatkan penggunaannya dalam banyak aplikasi di bawah keadaan perkhidmatan yang lebih meluas. Dalam kajian ini, usaha ditumpukan untuk memperbaiki sifat mekanikal dan tribologikal AA6063 diperkukuhkan dengan zarah abu terbang bersfera padu. Kajian yang berkaitan menumpukan kepada zarah abu terbang senosfera sahaja. Terdapat pelbagai teknik fabrikasi yang wujud dalam menghasilkan komposit sebegini berdasarkan kepada matriks dan bahan pengukuhan. Teknik penuangan kompo untuk proses fabrikasi komposit matriks AA6063 yang dikukuhkan dengan zarah FA merupakan fokus dalam kajian ini, Kandungan FA dalam julat berat 0-12 % dengan kenaikan 2% telah digunakan. Zarah FA telah ditambahkan kepada leburan aloi AA6063 sehingga campuran betul-betul sekata dan disejukkan di bawah takat cecair untuk mengekalkan bahan dalam keadaan separa-pepejal. Kemudian, komposit AA6063 yang dileburkan ditempa di dalam acuan besi tempa yang telah disediakan, Pelbagai teknik telah digunakan dalam menilai sifat mikrostruktur bagi komposit ini. Ketumpatan pukal, peratusan rongga dan sifat termal bagi komposit ini telah dikaji. Kajian ini turut menyelidik kesan penambahan FA terhadap sifat mekanikal komposit AA6063-FA. Kesan daripada penambahan FA, beban yang dikenakan dan kelajuan gelinciran terhadap gelinciran geseran kering dan kehausan telah dipertimbangkan di

dalam kajian ini. Ujian pin atas cakera telah dijalankan pada tahap beban yang berbeza (24.5, 49, dan 73.5 N). Kelajuan gelinciran yang berbeza turut digunakan di dalam kajian ini (150, 200, dan 250 rpm) dengan tempoh masa yang tetap (10 minit). Hasil yang diperolehi menunjukkan zarah FA disebarkan secara baik dalam matriks AA6063 dengan ikatan antara muka. Komposit AA6063-FA menunjukkan sifat mekanikal dan tribologi yang baik berbanding aluminum aloi AA6063 yang tidak dikukuhkan. Kekerasan mikro telah meningkat dengan ketara bagi semua peratusan kandungan FA, peningkatan kenaikan kekuatan regangan dan mampatan adalah terhad kepada 10% pecahan berat bagi zarah FA. Sementara itu, tenaga impak dan ketumpatan berkurang dengan penambahan kandungan FA. Kekuatan regangan aloi AA6063 meningkat 28 % dengan berat 10% FA. Kekuatan mampatan tanpa FA meningkat oleh 28 % dengan berat 10% FA. Kadar kehausan berkurangan dengan peningkatan kandungan FA, namun meningkat dengan pertambahan kelajuan gelinciran dan beban yang dikenakan. Pekali geseran menurun dengan peningkatan kandungan FA, kelajuan gelinciran dan beban yang dikenakan.

Penemuan dari analisis statistik adalah susunan kepentingan bagi parameter rekabentuk yang menunjukkan bahawa kandungan FA memberikan kesan yang paling tinggi ke atas kadar haus dan pekali geseran, diikuti dengan beban yang dikenakan dan kelajuan gelinciran. Selain itu, kesan interaksi yang paling tinggi/kuat adalah kandungan FA dengan beban yang dikenakan. Model yang dihasilkan akan menjadi alat yang berguna dalam proses rekabentuk komposit AA6063-FA, dan dapat digunakan sebagai pengganti bagi ujian konvensional yang mahal.

ACKNOWLEDGEMENTS

In the Name of ALLAH, the most Merciful and Beneficent

I am very grateful to Allah S.W.T. who has given me blessed, strength, courage, and patience to complete my thesis successfully.

Special appreciation goes to my supervisor, **Dr. Dayang Laila Abang Abdul Majid** for her supervision and constant support. Her invaluable help of constructive comments and suggestions throughout the experimental and thesis works have contributed to the success of this research. Many thanks and gratitude also goes to the supervisory committee, **Dr. Mohamad Ridzwan Bin Ishak**, and **Dr. Uday M. Basheer Al Naib** for their guidance and advice. I would like to thank my friends **Eng. Qassim, Eng. Ahamed and Eng. Mostafa Malik** for their help and support. I would like to thank **Dr. Wissam Hashim Jeber** for his support.

Also, I would like to express my utmost appreciation and gratitude to UTM-Centre for Low Carbon Transport, Institute for Vehicle Systems and Engineering at Universiti Teknologi Malaysia (UTM) for providing the research facilities. This research work has been supported by the the UTM Research FRGS Grant (No. R.J1300000.7824.4F723). Special thanks to Eng. Eng Ahmad Saifol Abu Samah, Eng. Muhammad Wildan, and Eng. Mohd Saiful for their technical supports. Sincere thanks to the staff of Faculty of Mechanical Engineering, Universiti Teknologi Malaysia Skudai UTM for their help and moral supports upon the completion of casting process with the collaboration of foundry personnel.

Finally, I would like to thank the Oil Products Distribution Company, Iraq Ministry of oil, and Ministry of Higher Education and Scientific Research, Iraq for the scholarship.

Alaa Mohammed Razzaq

February 2018

I certify that a Thesis Examination Committee has met on 24 May 2018 to conduct the final examination of Alaa Mohammed Razzaq on his thesis entitled "Mechanical and Tribological Enhancement of AA6063 Aluminum Alloy using Solid Sphere Fly Ash Particles Reinforcement" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

Nasri bin Sulaiman, PhD
Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Azmin Shakrine bin Mohd Rafie, PhD
Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Azmah Hanim binti Mohamed Ariff, PhD
Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Internal Examiner)

Recep Calin, PhD
Professor
Kirikkale University
Turkey
(External Examiner)

NOR AINI AB. SHUKOR, PhD
Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 28 June 2018

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Dayang Laila Abang Abdul Majid, PhD
Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Mohamad Ridzwan Bin Ishak, PhD
Senior Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Uday M. Basheer Al-Naib, PhD
Senior Lecturer
Faculty of Engineering
Universiti Teknologi Malaysia
(Member)

ROBIAH BINTI YUNUS, PhD
Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: _____ Date: _____

Name and Matric No: Alaa Mohammed Razzaq (GS40814)

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____

Name of Chairman of Supervisory Committee: Associate Professor Dr. Dayang Laila Abang Abdul Majid

Dr. Mohamad Ridzwan Ishak
Pensyarah Kanan
Jabatan Kejuruteraan Aeroangkasa
Fakulti Kejuruteraan
Universiti Putra Malaysia
Email: ridzwan@eng.upm.edu.my

Signature: _____

Name of Member of Supervisory Committee: Dr. Mohamad Ridzwan Bin Ishak

DR. UDAY M. BASHEER AL-NAIB
Faculty of Mechanical Engineering
UTM Centre For Low Carbon Transport
In Cooperation With Imperial College London
Institute For Vehicle Systems and Engineering
Universiti Teknologi Malaysia
81310 Skudai Johor Malaysia
Tel : +6017-497 1905 Ext No.: +607-553 6495

Signature: _____

Name of Member of Supervisory Committee: Dr. Uday M. Basheer Al-naib

TABLE OF CONTENT

LIST OF TABLES

LIST OF FIGURES

LIST OF ABBREVIATIONS

min	Minute
rpm	Revolution per minute
ASTM	American Society For Testing and Materials
FA	Fly ash
Al	Aluminum
AA6063	AA6063 aluminum alloy
AA6063-FA	AA6063 aluminum alloy-fly ash composites
MMCs	Metal matrix composites
AMCs	Aluminum matrix composites
AMMCs	Aluminum metal matrix composites
Al-FA	Aluminum – fly ash
CTE	Coefficient of thermal expansion
Al_2O_3	Aluminum Oxide
SiC	Silicon Carbide
SiO_2	Silicon dioxide
B_4C	Boron carbide
Graphite	Gr
Cubic boron nitride	CBN
Hexagonal boron nitride	HBN
Titanium diboride	TiB_2
Carbon nanotubes	CNT
XRD	X-ray Diffraction
XRF	X-ray fluorescence

VPSEM	Variable Pressure Scanning Electron Microscope
EDX	Energy-dispersive X-ray
FESEM	Field-Emission Scanning Electron Microscopy
RSM	Response surface method
DRAMCs	Discontinuously reinforced aluminum matrix composites
CFA	Fly ash cenosphere
PFA	Fly ash precipitator
TGA	Thermogravimetric Analysis
UTM	Universal Testing Machine
MTS	Material testing system
LVDT	Linear variable differential transformer
YS	Yield tensile strength (MPa)
UTS	Ultimate tensile strength (MPa)
UCS	Ultimate compression strength (MPa)
SS	Semisolid-semisolid
SL	Semisolid-liquid

LIST OF SYMBOLS

θ	The contact angle measurement of the liquid-solid (Wettability)
γ_{sg}	Interfacial energies between solid and gas phase
γ_{sl}	Interfacial energies between solid and liquid phase
γ_{lg}	Interfacial energies between liquid, and gas phase
W_{ad}	Energy required to separate a unit area (J/m^2)
BHN	Brinell Hardness Number
F_n	The normal force
V_r	Relative velocity
T_o	The initial temperature
T_p	Thermal properties
M_p	Mechanical properties
Ch_p	Chemical properties
HRD	Rockwell Hardness
V_f	Volume fraction
A_n	Nominal contact area of the wearing source (mm^2)
H_o	Room-temperature hardness of the softer sliding member
A	Thermal diffusivity ($mm^2\ S^{-1}$)
r_o	The radius of the circular nominal contact area (mm)
W	Volume lost per unit area of surface per unit slide distance slide (mm^3)
P_n	Normal pressure applied between the surface (N/mm^2)
H	The hardness (MPa)

K	The Archard's wear coefficient is dimensionless, always less than unity
W_r	Wear rate (mm^3/m)
F_r	Coefficient of friction
D_m	Dry mass
S_m	The mass of the test specimen after soaking
M_s	Saturated mass
Ve	Exterior volume
B	Bulk density
ρ	Apparent porosity
ρ_{FA}	Al-fly ash composites density ($gram/cm^3$)
M	Composite sample mass in air (gram)
m_1	Composite sample mass in distilled water (gram)
ρ_{H2O}	Distilled water density
Δl	Change in length (mm)
L_0	Original test piece length (mm)
α	Mean linear thermal expansion coefficient (K^{-1})
W_i	Wear rate function
T_1	Reference temperature (°C or °K)
T_2	Test temperature (°K)
σ_t	Tensile strength (MPa)
F_t	Tensile force N
A	Cross sectional area (mm^2)
ε	Strain
σ_c	Compression strength (MPa)

F_c	Compression force N
H_v	Vickers microhardness (MPa)
Wp	Weight of pendulum (Kgf)
g	Gravitational acceleration (m/s^2)
r	Distance from axis of rotation to center of gravity of pendulum (m)
α_1	Angle of fall of pendulum
β	Angle of rise of pendulum in its swing after breaking test sample
μ	The coefficient of friction
F_T	Tangential force (N)
F_N	Normal force (N)
V	Volume loss (mm^3)
S	Sliding speed (rpm)
L	Applied load (N)
W_{rp}	Predicted wear rate
F_{rp}	Predicted coefficient of friction
W_{re}	Experimental wear rate
F_{re}	Experimental coefficient of friction
W_{ra}	Average of experimental wear rate
F_{ra}	Average of experimental coefficient of friction
Vol.%	Percentage of volume fraction
Wt. %	Percentage of weight fraction

CHAPTER 1

INTRODUCTION

1.1 Introduction

Over the past decades, the demand for light weight structural materials has increased rapidly, especially in the automotive and aerospace industries. In recent times, aluminum alloys have gained wide acceptance in such applications owing to its properties and comparative advantages such as lightweight, good machinability, and energy efficiency-low power consumption. Aluminum AA6063 alloy is widely employed for construction and transportation applications [1]. As a base line material, it possesses good formability, weldability, machinability, and corrosion resistance, as well as a medium strength relative to other grades of aluminum alloys [2, 3]. However, with a view to implementing them as high performance materials for use in the aerospace, automobile, chemical and transportation industries it is essential to improve the strength, elastic modulus and wear resistance of the AA6063 alloy over the conventional base [4].

In spite of their attractive properties, AA6063 alloy has not been able to completely satisfy the overall requirements in applications such as automotive industry. For instance brake discs drums and rotors, pistons, automobile drive shafts, brake discs for railway applications, fan exit guide vanes, and blade sleeves for aerospace applications, are required to withstand high mechanical, thermal stresses during their service lives and also under tribological conditions. In order to overcome these drawbacks and to meet the ever increasing demand of modern day technology, composite materials have been proposed as the most promising candidate. With the inclusion of high strength and high modulus refractory particles such as SiC, TiC, B4C, Al2O3, MgO, TiO2, etc.to a ductile metal matrix, a material whose mechanical property lies between that of the matrix alloy and the ceramic reinforcement is generated [5-8].

Among the liquid phase processing methods, the stir casting is an attractive processing method to produce aluminum matrix composites (AMCs). It has salient features, a cost-effective manufacturing processes (relatively inexpensive) and offers a wide selection of materials, and processing conditions and fit for mass production without damaging the reinforcement particles [9]. Compocasting technique is adopted over the stirring process as this eliminates wettability problem of particles and results in better properties of AMCs [10].

1.2 Background

Specific material property requirements for application have highly increased, making several conventional alloy systems inappropriate. Metal matrix composites (MMCs) are new generation materials with a strong ceramic reinforcement incorporated into the metal matrix to improve its properties. MMCs combine metallic properties of matrix alloys (ductility and toughness) with ceramic properties of reinforcements (high strength and high modulus), leading to greater strength in shear and compression and higher service-temperature capabilities [11, 12]. In contrast to monolithic alloys, MMCs possess significantly improved properties such as high specific strength, high stability at elevated temperatures, lower coefficients of thermal expansion and good wear resistance [13]. Moreover, the remarkable physical and mechanical properties of the aluminum metal matrix composites (AMMCs) have made these materials attractive for applications in the aerospace and automotive industries, thermal management areas and industrial products etc. [13-15].

Meanwhile, out of the various types of MMCs, particulate reinforced composites in particular, the particulate reinforced aluminum matrix composite have aroused the interest of experts in the field owing to their low cost with advantages like isotropic properties and the possibility of secondary processing facilitating fabrication of secondary components [16]. Ceramic materials such as Al_2O_3, SiC, SiO_2, and B_4C have been reported as suitable reinforcement particles. Then seen from recent research endeavors and increasing awareness towards nurturing a green environment, fly ash (FA) has aroused the interest of researchers as promising reinforcement candidate due to its low density, economic viability and availability in commercial quantity.

In their work, Ramachandra, M. and Radhakrishna [17] observed an increase in the wear resistance of AMCs with increasing FA content, but decreases with increase in normal load and sliding velocity. More so, they observed that the corrosion resistance decreased with increasing FA content. FA as a filler has proven suitable for mechanical, physical and tribological properties enhancement including hardness, stiffness, wear and abrasion resistance as well as decrease density. Furthermore, it also improves the maintainability, damping capacity, and coefficient of friction which are most desirable in automotive and industrial applications [16, 18-23].

Notably, the mechanical properties of composites can be controlled by the properties of the constituent phases, relative amount and dispersed phase geometry including particle size, shape and orientation in the matrix [14, 24, 25]. Meanwhile, it has been observed thus far, that the particle size and weight fraction of the reinforcement phase in metal matrix composites influences the formation of dislocations due to thermal mismatch and the concurrent development of residual and internal stresses. Also worthy of note is that the metal matrix composites have remarkable benefits owing to the combined metallic and ceramic properties, thereby yielding improved physical and mechanical properties [26-28].

From the existing literature, the casting technique has been showcased as the most preferred choice for aluminum MMCs fabrication. In particular, the stir casting technique is economically viable and also promotes the distribution of the particulate reinforcement along the grain boundaries of aluminum melt. With a view to homogenizing the matrix material with the reinforcement particles, mechanical stirring of the composite is performed by a stirring bars, and then poured in a mould for solidification. By investigating the effect of the three different stir casting methods on the properties of FA reinforced Al-7Si-0.35Mg alloy, Rajan et al. [29] reported that the dispersion of FA particles were more effective in compocasting method than in liquid metal stir casting due to the shearing of FA particles by the solid primary phases existing in semisolid slurry. Using the stir casting method, Shirvanimoghaddam et al. [30] investigated the influence of processing temperature on the mechanical properties of aluminum composites reinforced with micron-sized particles. They observed significant improvement 125% increase in the hardness and 52% in tensile strength.

Anilkumar et al. [20] prepared Al6061 reinforced with FA through the utilization of the stir casting technique and concluded that the tensile strength increased with increasing weight percentage of FA. Their finding was attributed to the role played by the hard FA particles during sample failure as barriers to the advancing dislocation front, thus strengthening the matrix. Similarly, the good bonding of smaller size FA particles with the matrix was also reported as an additional factor for this behaviour. However, the authors observed a decrease in the tensile strength beyond the 15 wt% mark of FA reinforcement due to the poor wettability of the reinforcement with the matrix in this sample formulations. Meanwhile, the particle size increase of the FA has been reported to promote mechanical property deterioration in AMCs [31]. By employing the compocasting technique, Ervina et al. [13] successfully incorporated FA into the semi-solid state of LM6 melt to fabricate FA reinforced aluminum composites. Selvam et al. [32] observed that the addition of FA particles enhanced the microhardness and tensile strength of the AMCs. Moreover, FA ash particles are thermodynamically stable at the applied casting temperature. Hence, the interface between the aluminum matrix and FA particle was clear and the bonding was proper. More so, no interfacial reaction was observed between FA particles and aluminum matrix during the casting process. The processing temperature for the compocasting method is considerably low as compared to the stir casting method which is insufficient to initiate interfacial reactions. In addition the incorporation of FA particles into semi-solid aluminum alloy was observed to have improved the wettability.

Recently, most of the existing literature in this field of study have focused more on the aluminum alloy based composites, such as A357, A359, 2618, 2214, 6061 and 7075 [33-35]. However, the use of AA6063 as a base material for the development of Al matrix composites is rarely reported [36, 37]. Relative to other aluminum alloys, the AA6063 alloy is often available in commercial quantity in the metal markets of most developing countries [38]. However, one of the major drawbacks of these materials is their low strength and wear resistance. This limitation is due to the fact that AA6063 alloy undergo extensive plastic deformation and material removal under

sliding wear conditions[39]. The FA particles collected by electrostatic precipitators from the exhaust gases in thermal power stations[40]. Solid FA particles can be used as reinforcement material. Relevant works [41, 42]were found to focus only on cenosphere FA particulates. Hence, this research investigates the physical, thermal, mechanical, and tribological properties of AA6063-FA composite after fabrication with the compocasting method.

1.3 Problem Statement

The AA6063 alloy doesn't always provide the required properties under all service conditions which is overcome by reinforcing this alloy with ceramic particles. Meanwhile, the high cost and limited supply of conventional ceramic materials are the major setbacks encountered especially in most developing countries where the development of discontinuously reinforced aluminum matrix composites [43] is yet to be fully explored. Despite their potential benefits in weight reduction, increased composites life and improved recyclability, the high cost of the present day MMCs compared to aluminum alloys has inhibited the large scale production of these composite materials in areas such as the automotive industry and specialized applications [26, 42, 44]. Hence, it becomes imperative to promote the economic viability of these group of materials by utilizing cheaper reinforcements. With a view to overcoming this limitation, several research and development programs have focused on the improvement of aluminum-based MMCs using low cost industrial wastes as the reinforcement particulate [45, 46].

Currently, waste materials from rice husk ash, red mud, FA has attracted the interest of several researchers as inexpensive reinforcement particles for the fabrication of AMCs [13, 43, 47]. Meanwhile, FA a solid waste byproduct during the combustion of coal has been considered as one of the most inexpensive and low density reinforcement available in commercial quantity [13, 16, 48]. So far, many studies have reported that the Al-FA composites can adequately increase the hardness, strength, and stiffness while decreasing the density of an unreinforced alloy [13, 32, 49-51]. More so, they are also capable of improving the wear resistance and coefficient of friction which are desirable parameters in automotive and industrial applications [52]. This also solves the storage problems of FA as well as brings down the production cost, giving an economical and eco-friendly solution. Thus far, studies on aluminum–FA composites have shown great prospects in various applications.

Literature reveals that most of the researchers are using AA6063 alloy matrix reinforced with several types of reinforcement for high properties whereas, insufficient information is available on reinforcement of FA particles in AA6063 alloy matrix. Hence, it becomes imperative to study the effect of FA addition on the physical, thermal, mechanical, tribological properties of AA6063 alloy and also to develop a benchmark of property data which can be employed in evaluating these materials for future use.

1.4 Objectives

The main objective of this experimental research work is to develop AA6063-FA composite and investigate the effect of FA as a particulate reinforced AA6063 alloy matrix composites produced by compocasting technique. The specific objectives are as follows:

- To analyze the microstructural features and particulate distribution uniformity of FA particles in the AA6063-FA composite using VPSEM.
- To investigate the physical, thermal, and mechanical properties such as bulk density, apparent porosity, thermal expansion, tensile strength, compressive strength, hardness, and impact, for AA6063 alloy and AA6063-FA composite with different percentage of FA.
- To evaluate the FA addition, applied load and sliding speed on tribological behaviour of AA6063 alloy and AA6063-FA composite.
- To perform fracture mechanics studies and hence analyze the metallurgical and fracture surface as well as to characterize interfacial bonding.
- To develop mathematical models (wear rate, and coefficient of friction) and predict the relationship between the FA content, applied load, sliding speed and wear behavior.

1.5 Scope and Limitation

In this research, AA6063 alloy is used as a matrix material due its better fluidity and castability with good mechanical properties. AA6063 belongs to aluminium 6000 series which contains Silicon as a major alloying element in the aluminium metal matrix and therefore, this study is limited within these range of aluminium alloy only. With regard to FA particulate types, this work only focus on fly ash with solid sphere as the major component. The present investigation has been focused on utilization of different weight fraction of waste FA as reinforcement material. The range of weight fraction of 2% up to 12% were considered due to research findings that suggested higher percentages will pose agglomeration problems, reduction in toughness and impact performance.

The compocasting is employed without agents to manufacture the composite material by addition of FA after preheated at 900°C and the casting process temperature reduced to 600°C a stirring speed of 300 rpm were found to be best in order to produce uniform distributions of FA.

This research is interested in the measurement of physical properties, thermal properties, mechanical properties and tribological behaviour of AA6063 the as well as microstructure of the raw and composite materials.

1.6 Thesis layout

This thesis is divided into five chapters that cover systematically the whole work as follows:

- Chapter 1; provides a general overview of current research efforts to produce inexpensive aluminum composites with short background of the AL-FA composites with possibly, the motivation of the research, the statement of problem, the objectives of the research, and the layout of this thesis.
- Chapter 2; presents a scientific literature review and previous work focused on the researches dealing with the issue of Al-FA composites and its production. It also discusses FA effect on physical, mechanical and tribological properties of aluminum metal matrix composites (MMCs).
- Chapter 3; presents materials, experimental procedures and statistical methods.
- Chapter 4; this chapter is divided into two main sections. The first, discusses the experimental results obtained from this work, and second, describes the development of the mathematical models with ANOVA of wear rate and coefficient of friction.
- Chapter 5; summarizes the conclusions emanating from the results presented in Chapter 4, looking back at the various topics touched upon this thesis, attempting to objectively evaluate the results obtained. The recommendations for future work in terms of both possible improvements and new research directions are described.

REFERENCES

[1] C.-t. Z. Hong-ying Li, Mao-sheng Han, Jiao-jiao Liu, Xiao-Chao Lu "Time–temperature–property curves for quench sensitivity of 6063 aluminum alloy," *Transactions of Nonferrous Metals Society of China,* vol. 23, pp. 38-45, 2013.

[2] G. H. M. J. Nemati, S. Sulaiman, B.T.H.T. Baharudin, MA. Azmah Hanim, "Effect of equal channel angular extrusion on Al-6063 bending fatigue characteristics," *International Journal of Minerals, Metallurgy, and Materials,* vol. 22, pp. 395-404, 2015.

[3] R. N. S Natarajan, S.P Kumaresh Babu, G Dinesh, B Anil Kumar, K Sivaprasad, "Sliding wear behaviour of Al 6063/TiB 2 in situ composites at elevated temperatures," *Materials & Design,* vol. 30, pp. 2521-2531, 2009.

[4] S. P. K. B. K. Sivaprasad, S. Natarajan, R. Narayanasamy, and G. D. B. Anil Kumar, "Study on abrasive and erosive wear behaviour of Al 6063/TiB 2 in situ composites," *Materials Science and Engineering: A,* vol. 498, pp. 495-500, 2008.

[5] J. Hashim, L. Looney, and M. Hashmi, "Metal matrix composites: production by the stir casting method," *Journal of Materials Processing Technology,* vol. 92, pp. 1-7, 1999.

[6] R. P. A Sakthivel, R Velmurugan, P Raghothama Rao, "Production and mechanical properties of SiCp particle-reinforced 2618 aluminum alloy composites," *Journal of materials science,* vol. 43, pp. 7047-7056, 2008.

[7] J. M. E. Bayraktar, R Caplain, C Bathias., "Manufacturing and damage mechanisms in metal matrix composites," *Journal of Achievements in Materials and Manufacturing Engineering,* vol. 31, pp. 294-300, 2008.

[8] B. S. Yigezu, P. Jha, and M. Mahapatra, "The key attributes of synthesizing ceramic particulate reinforced Al-based matrix composites through stir casting process: a review," *Materials and Manufacturing Processes,* vol. 28, pp. 969-979, 2013.

[9] J. D. R. Selvam, D. R. Smart, and I. Dinaharan, "Synthesis and characterization of Al6061-Fly Ashp-SiCp composites by stir casting and compocasting methods," *Energy procedia,* vol. 34, pp. 637-646, 2013.

[10] B. Mithun, M. Nagaral, V. Auradi, and V. Bharath, "Microstructure and Mechanical Properties of Cu-Coated Al 2 O 3 Particulate Reinforced 6061 Al Metal Matrix Composite," *Materials Today: Proceedings,* vol. 4, pp. 11015-11022, 2017.

[11] M. Kok, "Production and mechanical properties of Al 2 O 3 particle-reinforced 2024 aluminium alloy composites," *Journal of Materials Processing Technology,* vol. 161, pp. 381-387, 2005.

[12] A. Kumar, S. Lal, and S. Kumar, "Fabrication and characterization of A359/Al 2 O 3 metal matrix composite using electromagnetic stir casting method," *Journal of Materials Research and Technology,* vol. 2, pp. 250-254, 2013.

[13] S. S. N. Efzan Ervina Noor Mohd, and J. Emerson., "Properties of Aluminum Matrix Composite (AMCs) for Electronic Packaging," in *Materials Science Forum*, 2016, pp. 18-21.

[14] M. H. Rahman and H. M. Al Rashed, "Characterization of silicon carbide reinforced aluminum matrix composites," *Procedia Engineering*, vol. 90, pp. 103-109, 2014.

[15] M. Surappa, "Aluminium matrix composites: Challenges and opportunities," *Sadhana*, vol. 28, pp. 319-334, 2003.

[16] D. Singla and S. Mediratta, "Evaluation of mechanical properties of Al 7075-fly ash composite material," *International Journal of Innovative Research in Science, Engineering and Technology*, vol. 2, 2013.

[17] M. Ramachandra and K. Radhakrishna, "Effect of reinforcement of flyash on sliding wear, slurry erosive wear and corrosive behavior of aluminium matrix composite," *Wear*, vol. 262, pp. 1450-1462, 2007.

[18] D. M. Rao and B. R. Bandam, "Preparation and characterization of Al-Fly ash metal matrix composite by stir casting method," *International Journal of Innovative Science and Modern Engineering (IJISME)*, vol. 3, 2014.

[19] G. Pandi and S. Muthusamy, "A review on machining and tribological behaviors of aluminium hybrid composites," *Procedia Engineering*, vol. 38, pp. 1399-1408, 2012.

[20] H. Anilkumar, H. Hebbar, and K. Ravishankar, "Mechanical properties of fly ash reinforced aluminium alloy (Al6061) composites," *International Journal of Mechanical and Materials Engineering*, vol. 6, pp. 41-45, 2011.

[21] V. Kumar, R. D. Gupta, and N. Batra, "Comparison of Mechanical Properties and Effect of Sliding Velocity on Wear Properties of Al 6061, Mg 4%, Fly Ash and Al 6061, Mg 4%, Graphite 4%, Fly Ash Hybrid Metal Matrix Composite," *Procedia Materials Science*, vol. 6, pp. 1365-1375, 2014.

[22] H. Kala, K. Mer, and S. Kumar, "A Review on Mechanical and Tribological Behaviors of Stir Cast Aluminum Matrix Composites," *Procedia Materials Science*, vol. 6, pp. 1951-1960, 2014.

[23] P. Rohatgi, D. Weiss, and N. Gupta, "Applications of fly ash in synthesizing low-cost MMCs for automotive and other applications," *JOM*, vol. 58, pp. 71-76, 2006.

[24] G. Totten and D. S. MacKenzie, "Handbook of aluminum: Alloy production and materials manufacturing, Vol. 2," ed: Dekker, New York, 2003.

[25] W. D. Callister and D. G. Rethwisch, *Materials science and engineering: an introduction* vol. 7: Wiley New York, 2007.

[26] T. R. Vijayaram., "Fabrication methods, mechanical properties, and industrial applications of metal matrix composite materials. International Journal on Design and Manufacturing Technologies, 2010. 4(2): p.1-5.."

[27] S. C. Sharma, K. H. W. Seah, B. M. Girish, R. Kamath, B. M. Satisha., "Mechanical properties and fractography of cast lead-alloy/quartz particulate composites," *Materials & design,* vol. 18, pp. 149-153, 1997.

[28] M. Sayuti, "Properties of titanium carbide reinforced aluminium silicon alloy matrix," Universiti Putra Malaysia, 2012.

[29] R. P. TPD Rajan, BC Pai, KG Satyanarayana, PK Rohatgi., "Fabrication and characterisation of Al–7Si–0.35 Mg/fly ash metal matrix composites processed by different stir casting routes," *Composites Science and Technology,* vol. 67, pp. 3369-3377, 2007.

[30] H. K. K. Shirvanimoghaddam, H. Abdizadeh, M. Karbalaei Akbari, A.H. Pakseresht, F. Abdi, A. Abbasi, M. Naebe, "Effect of B4C, TiB2 and ZrSiO4 ceramic particles on mechanical properties of aluminium matrix composites: Experimental investigation and predictive modelling," *Mater. Sci. Eng. A. 2016,* vol. 498, pp. 53-58, 2016.

[31] S. Aravindan, P. Rao, and K. Ponappa, "Evaluation of physical and mechanical properties of AZ91D/SiC composites by two step stir casting process," *Journal of Magnesium and Alloys,* vol. 3, pp. 52-62, 2015.

[32] J. D. R. Selvam, D. R. Smart, and I. Dinaharan, "Microstructure and some mechanical properties of fly ash particulate reinforced AA6061 aluminum alloy composites prepared by compocasting," *Materials & Design,* vol. 49, pp. 28-34, 2013.

[33] T. Christy, N. Murugan, and S. Kumar, "A comparative study on the microstructures and mechanical properties of Al 6061 alloy and the MMC Al 6061/TiB2/12p," *Journal of Minerals and Materials Characterization and Engineering,* vol. 9, p. 57, 2010.

[34] A. Pakdel, H. Farhangi, and M. Emamy, "Effect of extrusion process on ductility and fracture behaviour of SiCp/aluminum-alloy composites," in *Proceedings of 8th International Fracture Conference*, 2007, pp. 460-470.

[35] B.-K. Hwu, S.-J. Lin, and M.-T. Jahn, "Effects of process parameters on the properties of squeeze-cast SiCp-6061 Al metal-matrix composite," *Materials Science and Engineering: A,* vol. 207, pp. 135-141, 1996.

[36] T. A. Khalifa and T. S. Mahmoud, "Elevated temperature mechanical properties of Al alloy AA6063/SiCp MMCs," in *Proceedings of the World Congress on Engineering WCE 2009, July 1 - 3, 2009, London, U.K.*, 2009, pp. 1-3.

[37] K. K. AlanemeaΨ and A. O. Alukob, "Production and age-hardening behaviour of borax premixed SiC reinforced Al-Mg-Si alloy composites developed by double stir-casting technique," 2012.

[38] A. A. Abioye, O. S. I. Fayomi, A. P. I. Popoola, and O. P. Abioye, "Equal Channel Angular Extrusion Characteristics on Mechanical Behavior of Aluminum Alloy," in *Aluminium Alloys-Recent Trends in Processing, Characterization, Mechanical Behavior and Applications*, ed: InTech, 2017.

[39] J. Singh, "Fabrication characteristics and tribological behavior of Al/SiC/Gr hybrid aluminum matrix composites: A review," *Friction,* vol. 4, pp. 191-207, 2016.

[40] K. Tosun-Felekoğlu, E. Gödek, M. Keskinateş, and B. Felekoğlu, "Utilization and selection of proper fly ash in cost effective green HTPP-ECC design," *Journal of Cleaner Production,* vol. 149, pp. 557-568, 2017.

[41] S. S. Sachin Prabha, Karthik S., Vinod R., "Fabrication and Characterization of Metal Matri Cenosphere. Journal of Materials Science & Surface Engineering. 2016, 4 (6):p 463-466."

[42] V. Saravanan, P. Thyla, and S. Balakrishnan, "A low cost, light weight cenosphere–aluminium composite for brake disc application," *Bulletin of Materials Science,* vol. 39, pp. 299-305, 2016.

[43] M. O. Bodunrin, K. K. Alaneme, and L. H. Chown, "Aluminium matrix hybrid composites: a review of reinforcement philosophies; mechanical, corrosion and tribological characteristics," *Journal of Materials Research and Technology,* vol. 4, pp. 434-445, 2015.

[44] K. V. Harish K.Garg, Alakesh Manna, Rajesh Kumar., "Hybrid Metal Matrix Composites and further improvement in their machinability-A Review," *International Journal of Latest Research in Science and Technology,* vol. 1, pp. 36-44, 2012.

[45] D. S. Y.R. Loh, M.E. Rahman, C.A. Das., "Sugarcane bagasse—The future composite material: A literature review," *Resources, Conservation and Recycling,* vol. 75, pp. 14-22, 2013.

[46] V. S. A. J.E. Oghenevweta, G.B. Nyior, F. Asuke., "Mechanical properties and microstructural analysis of Al–Si–Mg/carbonized maize stalk waste particulate composites," *Journal of King Saud University-Engineering Sciences,* vol. 28, pp. 222-229, 2016.

[47] S. Debnath, L. Lancaster, and M. Lung, "Utilization of Agro-Industrial Waste in Metal Matrix Composites: Towards Sustainability," 2013.

[48] L. Arun, D. S. K. N. Kulkarni, and B. Kuldeep, "Characteristic Studies on Aluminium Based Silicon Carbide and Fly Ash Particulate Metal Matrix Composite," *International Journal of Engineering Research & Technology (IJERT) ISSN,* pp. 2278-0181, 2013.

[49] M. Surappa, "Dry sliding wear of fly ash particle reinforced A356 Al composites," *Wear,* vol. 265, pp. 349-360, 2008.

[50] S. Kulkarni, J. Meghnani, and A. Lal, "Effect of fly ash hybrid reinforcement on mechanical property and density of aluminium 356 alloy," *Procedia Materials Science,* vol. 5, pp. 746-754, 2014.

[51] J. David Raja Selvam, I. Dinaharan, and P. Mashinini, "High temperature sliding wear behavior of AA6061/fly ash aluminum matrix composites prepared using compocasting process," *Tribology-Materials, Surfaces & Interfaces,* vol. 11, pp. 39-46, 2017.

[52] Z. Y. D. G.H. Wu, L.T. Jiang, J.H. Cao., "Damping properties of aluminum matrix–fly ash composites," *Materials Letters,* vol. 60, pp. 2945-2948, 2006.

[53] S. K. Panigrahi and R. Jayaganthan, "Effect of annealing on precipitation, microstructural stability, and mechanical properties of cryorolled Al 6063 alloy," *Journal of materials science,* vol. 45, pp. 5624-5636, 2010.

[54] S. K. Panigrahi and R. Jayaganthan, "Development of ultrafine-grained Al 6063 alloy by cryorolling with the optimized initial heat treatment conditions," *Materials & Design,* vol. 32, pp. 2172-2180, 2011.

[55] S. K. Panigrahi, R. Jayaganthan, and V. Pancholi, "Effect of plastic deformation conditions on microstructural characteristics and mechanical properties of Al 6063 alloy," *Materials & Design,* vol. 30, pp. 1894-1901, 2009.

[56] K. J. Al-Fadhalah, A. I. Almazrouee, and A. S. Aloraier, "Microstructure and mechanical properties of multi-pass friction stir processed aluminum alloy 6063," *Materials & Design,* vol. 53, pp. 550-560, 2014.

[57] K. Alaneme and A. Aluko, "Fracture toughness (K1C) and tensile properties of as-cast and age-hardened aluminium (6063)–silicon carbide particulate composites," *Scientia Iranica,* vol. 19, pp. 992-996, 2012.

[58] K. Alaneme and M. Bodunrin, "Corrosion behavior of alumina reinforced aluminium (6063) metal matrix composites," *Journal of Minerals and Materials Characterization and Engineering,* vol. 10, p. 1153, 2011.

[59] "http://asm.matweb.com/search/SpecificMaterial.asp?bassnum=MA6063T5."

[60] J. G. Kaufman, *Introduction to aluminum alloys and tempers*: ASM international, 2000.

[61] F. J. Gilbert Kaufman, "Properties of Aluminm Alloys," 1999.

[62] M. N. Sallahauddin Attar, H N Reddappa and V Auradi., "A Review on Particulate Reinforced Aluminium Metal Matrix Composites," *Journal of Emerging Technologies and Innovative Research (JETIR).* vol. 2, 2015.

[63] O. H. Famodimu, "Additive Manufacturing of Aluminium-Metal Matrix Composite developed through Mechanical Alloying," .Doctor philosopy thesis, Wolverhampton, 2016

[64] M. W. C. H. Zhang, K.T. Ramesh, J.Ye, J.M. Schoenung, E.S.C. Chin., "Tensile behavior and dynamic failure of aluminum 6092/B 4 C composites," *Materials Science and Engineering: A,* vol. 433, pp. 70-82, 2006.

[65] J. Singh and A. Chauhan, "Characterization of hybrid aluminum matrix composites for advanced applications–A review," *Journal of Materials Research and Technology,* vol. 5, pp. 159-169, 2016.

[66] B. S. A Macke, Pradeep Rohatgi, "Metal matrix composites offer the automotive industry an opportunity to reduce vehicle weight, improve performance," *Advanced materials & processes,* vol. 170, pp. 19-23, 2012.

[67] T. S. A. A. B. Vijaya Ramnath. C. Elanchezhian, RM. Annamalai, V. Vignesh, S.Aravind, and C.Subramanian, "Aluminium metal matrix composites–a review," *Rev. Adv. Mater. Sci,* vol. 38, 2014.

[68] K. U. Kainer, "Basics of metal matrix composites," *Metal Matrix Composites, 1st ed., Wiley-VCH Verlag GmbH & Co., Weinheim,* pp. 1-54, 2006.

[69] M. I. Pech-Canul, "Aluminum Alloys for Al/SiC Composites," *Recent Trends in Processing and Degradation of Aluminum Alloys. Shanghai: InTech,* vol. 299, 2011.

[70] R. Casati and M. Vedani, "Metal matrix composites reinforced by nano-particles—a review," *Metals,* vol. 4, pp. 65-83, 2014.

[71] H. Zakaria, "Microstructural and corrosion behavior of Al/SiC metal matrix composites," *Ain Shams Engineering Journal,* vol. 5, pp. 831-838, 2014.

[72] S. C. K.L. Firestein, A.E. Steinman, A.T. Matveev, A.M. Kovalskii, I.V. Sukhorukova, D. Golberg, D.V. Shtansky., "High-strength aluminum-based composites reinforced with BN, AlB 2 and AlN particles fabricated via reactive spark plasma sintering of Al-BN powder mixtures," *Materials Science and Engineering: A,* vol. 681, pp. 1-9, 2017.

[73] A. A. C.S. Ramesh, B.H. Channabasappa, R. Keshavamurthy., "Development of Al 6063–TiB 2 in situ composites," *Materials & Design,* vol. 31, pp. 2230-2236, 2010.

[74] C. A. Reddy and E. Zitoun, "Tensile behavior of 6063/Al^ sub 2^ o^ sub 3^ particulate metal matrix composites fabricated by investment casting process," *International Journal of Applied Engineering Research,* vol. 1, p. 542, 2010.

[75] K. Alaneme and M. Bodunrin, "Mechanical behaviour of alumina reinforced AA 6063 metal matrix composites developed by two step-stir casting process," *Acta Technica Corviniensis-bulletin of engineering,* vol. 6, p. 105, 2013.

[76] K. K. Alaneme, "Mechanical Behaviour of Cold Deformed and Solution Heat-treated Alumina Reinforced AA 6063 Metal Matrix Composites," *The West Indian Journal of Engineering,* vol. 35, pp. 31-35, 2013.

[77] V. D. Jebin, D. Shivalingappa, and J. J. Rino, "Wear behavior of AL6063-alumina metal Matrix composite," *Wear,* vol. 3, p. 8, 2013.

[78] K. Hemalatha, V. Venkatachalapathy, and N. Alagumurthy, "Processing and synthesis of metal matrix Al 6063/Al2O3 Metal Matrix Composite by stir casting process," *International Journal of Engineering Research and Applications,* vol. 3, pp. 1390-1394, 2013.

[79] K. S. Sucitharan, P Shivalingappa, D Rino, J Jenix, "Wear behaviour of Al6063-zircon sand metal matrix composite," *Wear,* vol. 3, 2013.

[80] E. I. A. S.O. Adeosun, O. I. Sekunowo,W. A. Ayoola, and S. A. Balogun., "Mechanical Characteristics of 6063 Aluminum-Steel Dust Composite," *ISRN Mechanical Engineering,* vol. 2012, 2012.

[81] O. O. Daramola, A. A. Adediran, and A. T. Fadumiye, "Evaluation of the mechanical properties and corrosion behaviour of coconut shell ash reinforced aluminium (6063) alloy composites," *Leonardo Electronic Journal of Practices and Technologies,* pp. 107-119, 2015.

[82] A. S. Verma, N. Suri, and S. Kant, "Effect of Process parameter of AL-6063 based fly ash composites using Taguchi," *International Journal of Applied Engineering Research,* vol. 7, p. 2012, 2012.

[83] A. S. Verma, S. Kant, and N. Suri, "Modelling of Process variables for fly ash based Al-6063 composites using Artificial Neural Network," *International Journal of Scientific and Research Publications,* vol. 3, pp. 1-5, 2013.

[84] M. R. Kumar, M. ShunmugaPriyana, and A. Mani, "Investigation of Mechanical and Wear properties of Aluminum-Fly Ash composite material produced by Stir Casting Method," *International Journal of Scientific & Engineering Research,* vol. 5, 2014.

[85] D. D. S. J.Jenix Rino, Halesh Koti, V.Daniel Jebin, "Properties of Al6063 MMC reinforced with zircon sand and alumina," *IOSR Journal of Mechanical and Civil Engineering,* vol. 5, pp. 72-77, 2013.

[86] O. O. Mo. Bodunrin, OO. Daramola, KK. Alaneme, NB. Maledi, "Porosity measurement and wear performance of aluminium hybrid composites reinforced with silica sand and bamboo leaf ash," *Annals of the Faculty of Engineering Hunedoara,* vol. 14, p. 231, 2016.

[87] J. P. K. Gowri Shankar M.C, Raviraj Shetty, Achutha Kini and Sharma S.S, "Individual and combined effect of reinforcements on stir cast aluminium metal matrix composites-a review," *International Journal of Current Engineering and Technology,* vol. 3, pp. 922-934, 2013.

[88] M. I. H Junaedi, HR Ammar, AM Samuel, MS Soliman, AA Almajid and FH SamuelS, "Effect of testing temperature on the strength and fracture behavior of Al-B4C composites," *Journal of Composite Materials,* vol. 50, pp. 2871-2880, 2016.

[89] V. S. Z. A.V. Pozdniakov, R.Yu. Barkov, A. Lotfy, A.I. Bazlov, "Microstructure and material characterization of 6063/B 4 C and 1545K/B 4 C composites produced by two stir casting techniques for nuclear applications," *Journal of Alloys and Compounds,* vol. 664, pp. 317-320, 2016.

[90] A. K. Fatih Toptan, Ahmet Karaaslan, Mustafa Cigdem, Isil Kerti, "Processing and microstructural characterisation of AA 1070 and AA 6063 matrix B 4 C p reinforced composites," *Materials & Design,* vol. 31, pp. S87-S91, 2010.

[91] K. Alaneme, "Corrosion behaviour of heat-treated Al-6063/SiCp composites immersed in 5 wt% NaCl solution," *Leonardo Journal of science,* vol. 18, pp. 55-64, 2011.

[92] M. Bodunrin, K. Alaneme, and S. Olusegun, "Influence of Thermomechanical Processing on the Corrosion Behaviour of Aluminium (6063)-SiCp Composites in NaCl and H2SO4 Environment," *Science Journal Ubon Ratchathani University,* vol. 2, pp. 17-25, 2011.

[93] K. Alaneme, "Influence of thermo-mechanical treatment on the tensile behaviour and CNT evaluated fracture toughness of borax premixed SiCp reinforced aluminum (6063) composites," *International Journal of Mechanical and Materials Engineering,* vol. 7, pp. 96-100, 2012.

[94] I. Balasubramanian and R. Maheswaran, "Effect of inclusion of SiC particulates on the mechanical resistance behaviour of stir-cast AA6063/SiC composites," *Materials & Design (1980-2015),* vol. 65, pp. 511-520, 2015.

[95] K. Meena, A. Manna, and S. Banwait, "An Analysis of Mechanical Properties of the Developed Al/SiC-MMC's," *American Journal of Mechanical Engineering,* vol. 1, pp. 14-19, 2013.

[96] U. A. K. Jamaluddin Hindi, S. S. Sharma, B.M Gurumurthy, and M. C Gowri Shankar, "Mechanical Characterization of Stir Cast Al 6063 Matrix SiC Reinforced Metal Matrix Composites," 5th International Conference on Automotive, Mechanical and Materials Engineering (ICAMME'2015) A. 2015.

[97] B. S. Yigezu, M. M. Mahapatra, and P. K. Jha, "Influence of reinforcement type on microstructure, hardness, and tensile properties of an aluminum alloy metal matrix composite," 2013.

[98] S. S. Sumit Kumar Tiwari, R S Rana,. Alok Singh, "Effect of Heat Treatment on Mechanical Properties of Aluminium alloy-Fly ash Metal Matrix Composite," *Materials Today: Proceedings,* vol. 4, pp. 3458-3465, 2017.

[99] D. Lloyd, "Particle reinforced aluminium and magnesium matrix composites," *International Materials Reviews,* vol. 39, pp. 1-23, 1994.

[100] A. Bhandakkar, R. Prasad, and S. M. Sastry, "Fracture Toughness of AA2024 Aluminum Fly Ash Metal Matrix Composites," *International Journal of Composite Materials,* vol. 4, pp. 108-124, 2014.

[101] O. B. Fatile, J. I. Akinruli, and A. A. Amori, "Microstructure and mechanical behaviour of stir-cast Al-Mg-Sl alloy matrix hybrid composite reinforced with corn cob ash and silicon carbide," *International Journal of Engineering and Technology Innovation,* vol. 4, pp. 251-259, 2014.

[102] P. Madakson, D. Yawas, and A. Apasi, "Characterization of coconut shell ash for potential utilization in metal matrix composites for automotive applications," *International journal of engineering science and technology,* vol. 4, pp. 1190-1198, 2012.

[103] S. B. H. V.S. Aigbodion, E.T. Dauda and R.A. Mohammed, "The development of mathematical model for the prediction of ageing behaviour for Al-Cu-Mg/bagasse ash particulate composites," *Journal of Minerals and Materials Characterization and Engineering,* vol. 9, p. 907, 2010.

[104] D. S. Prasad and R. Krishna, "Production and mechanical properties of A356. 2/RHA composites," *International journal of advanced science and technology,* vol. 33, pp. 51-58, 2011.

[105] I. B. A. Keneth Kanayo Alaneme, Peter Apata Olubambi, Tolulope M. Adewale, "Fabrication characteristics and mechanical behaviour of rice husk ash–Alumina reinforced Al-Mg-Si alloy matrix hybrid composites," *journal of Materials Research and Technology,* vol. 2, pp. 60-67, 2013.

[106] H. T. C. Y.Q. Liua, W.Wang, C.H. Sun, H.M. Cheng, "AlN nanoparticle-reinforced nanocrystalline Al matrix composites: Fabrication and mechanical properties," *Materials Science and Engineering: A,* vol. 505, pp. 151-156, 2009.

[107] B. L. Z. Sadeghian, M.H. Enayati, P. Beiss, "Microstructural and mechanical evaluation of Al–TiB 2 nanostructured composite fabricated by mechanical alloying," *Journal of Alloys and Compounds,* vol. 509, pp. 7758-7763, 2011.

[108] T. T. Zhihui Zhang, Ying Li, Rustin Vogt, Yizhang Zhou, Chris Haines, Joseph Paras, Deepak Kapoor, Julie M. Schoenung and Enrique J. Lavernia, "Mechanical behavior of ultrafine-grained Al composites reinforced with B 4 C nanoparticles," *Scripta Materialia,* vol. 65, pp. 652-655, 2011.

[109] S. C. Tjong and S. Tjong, "Processing and deformation characteristics of metals reinforced with ceramic nanoparticles," *Nanocrystalline Materials: Their Synthesis-Structure-Property Relationships and Applications,* p. 269, 2013.

[110] A. Mazahery and M. O. Shabani, "Characterization of cast A356 alloy reinforced with nano SiC composites," *Transactions of Nonferrous Metals Society of China,* vol. 22, pp. 275-280, 2012.

[111] A. T. I Mobasherpour, M Ebrahimi, "Effect of nano-size Al 2 O 3 reinforcement on the mechanical behavior of synthesis 7075 aluminum alloy composites by mechanical alloying," *Materials chemistry and physics,* vol. 138, pp. 535-541, 2013.

[112] K. K. Poovazhagan.L, Rajadurai.A and Senthilvelan.V, "Characterization of hybrid silicon carbide and boron carbide nanoparticles-reinforced aluminum alloy composites," *Procedia Engineering,* vol. 64, pp. 681-689, 2013.

[113] D. C. J.Jenix Rino, K.S.Sucitharan, "An overview on development of aluminium metal matrix composites with hybrid reinforcement," *IJSR, India online ISSN,* pp. 2319-7064, 2012.

[114] H. Shivaraja and B. Praveen Kumar, "Experimental Determination and Analysis of Fracture Toughness of MMC," *International Journal of Science and Research (IJSR),* vol. 3, 2014.

[115] B. G. Narasimha, V. M. Krishna, and A. M. Xavior, "A review on processing of particulate metal matrix composites and its properties," *International Journal of Applied Engineering Research,* vol. 8, pp. 647-666, 2013.

[116] B. Ashish, J. Saini, and B. Sharma, "A review of tool wear prediction during friction stir welding of aluminium matrix composite," *Transactions of Nonferrous Metals Society of China,* vol. 26, pp. 2003-2018, 2016.

[117] B. F. S. Anthony Macke, Pradeep K Rohatgi, Nikhil Gupta, "Metal matrix composites for automotive applications," *Advanced Composite Materials for Automotive Applications: Structural Integrity and Crashworthiness,* pp. 311-344, 2013.

[118] A. A. Iqbal and D. M. Nuruzzaman, "Effect of the Reinforcement on the Mechanical Properties of Aluminium Matrix Composite: A Review," *International Journal of Applied Engineering Research,* vol. 11, pp. 10408-10413, 2016.

[119] B. Previtali, D. Pocci, and C. Taccardo, "Application of traditional investment casting process to aluminium matrix composites," *Composites Part A: Applied Science and Manufacturing,* vol. 39, pp. 1606-1617, 2008.

[120] S. Das, S. Das, and K. Das, "Abrasive wear of zircon sand and alumina reinforced Al–4.5 wt% Cu alloy matrix composites–A comparative study," *Composites Science and Technology,* vol. 67, pp. 746-751, 2007.

[121] R. Blissett and N. Rowson, "A review of the multi-component utilisation of coal fly ash," *Fuel,* vol. 97, pp. 1-23, 2012.

[122] A. U. Abubakar and K. S. Baharudin, "Potential use of Malaysian thermal power plants coal bottom ash in construction," *International Journal of Sustainable Construction Engineering and Technology,* vol. 3, pp. 25-37, 2012.

[123] V. Pa, "The Experimental Analysis of Stir Casting Method on Aluminium-Fly Ash Composites," 2013.

[124] L.-J. Fan and S. H. Juang, "Reaction effect of fly ash with Al–3Mg melt on the microstructure and hardness of aluminum matrix composites," *Materials & Design,* vol. 89, pp. 941-949, 2016.

[125] J. B. Rao, D. V. Rao, and N. Bhargava, "Development of light weight ALFA composites," *International Journal of Engineering, Science and Technology,* vol. 2, 2010.

[126] J. D. R. Selvam, D. R. Smart, and I. Dinaharan, "Influence of fly ash particles on dry sliding wear behaviour of AA6061 aluminium alloy," *Kovove Mater,* vol. 54, pp. 175-183, 2016.

[127] S. H. Juang, L.-J. Fan, and H. P. O. Yang, "Influence of preheating temperatures and adding rates on distributions of fly ash in aluminum matrix composites prepared by stir casting," *International Journal of Precision Engineering and Manufacturing,* vol. 16, pp. 1321-1327, 2015.

[128] H. Anilkumar and H. S. Hebbar, "Effect of particle size of fly ash on mechanical and tribological properties of aluminium alloy (Al6061) composites and their correlations," *International Journal of Mechanic Systems Engineering,* vol. 3, pp. 6-3, 2013.

[129] P. Sharma, D. Khanduja, and S. Sharma, "Tribological and mechanical behavior of particulate aluminum matrix composites," *Journal of Reinforced Plastics and Composites,* vol. 33, pp. 2192-2202, 2014.

[130] J. Hashim, L. Looney, and M. Hashmi, "The wettability of SiC particles by molten aluminium alloy," *Journal of Materials Processing Technology,* vol. 119, pp. 324-328, 2001.

[131] N. M. S. J Allyn Kingsly Gladston, I Dinaharan, J David Raja Selvam, "Production and characterization of rich husk ash particulate reinforced AA6061 aluminum alloy composites by compocasting," *Transactions of Nonferrous Metals Society of China,* vol. 25, pp. 683-691, 2015.

[132] N. E. Mehdi Rahimian, Nader Parvin, Hamid reza Baharvandi, "The effect of particle size, sintering temperature and sintering time on the properties of Al–Al 2 O 3 composites, made by powder metallurgy," *Journal of Materials Processing Technology,* vol. 209, pp. 5387-5393, 2009.

[133] C. S. B. Srinivasaraoa, K. Oh-ishi, K. Hono, "Microstructure and mechanical properties of Al–Zr nanocomposite materials," *Materials Science and Engineering: A,* vol. 518, pp. 100-107, 2009.

[134] K. Kalaiselvan, N. Murugan, and S. Parameswaran, "Production and characterization of AA6061–B 4 C stir cast composite," *Materials & Design,* vol. 32, pp. 4004-4009, 2011.

[135] W. Y. Ziyang Xiu, Guoqing Chen, Longtao Jiang, Kang Ma, Gaohui Wu, "Microstructure and tensile properties of Si 3 N 4p/2024Al composite fabricated by pressure infiltration method," *Materials & Design,* vol. 33, pp. 350-355, 2012.

[136] M. R. R. Sajjad Amirkhanlou, Behzad Niroumand, Mohammad Reza Toroghinejad, "High-strength and highly-uniform composites produced by compocasting and cold rolling processes," *Materials & Design,* vol. 32, pp. 2085-2090, 2011.

[137] V. Srivastava and S. Ojha, "Microstructure and electrical conductivity of Al-SiCp composites produced by spray forming process," *Bulletin of Materials Science,* vol. 28, pp. 125-130, 2005.

[138] S. A. S. Hamid Reza Ezatpour, Mohsen Haddad Sabzevar, Yizhong Huang, "Investigation of microstructure and mechanical properties of Al6061-nanocomposite fabricated by stir casting," *Materials & Design,* vol. 55, pp. 921-928, 2014.

[139] I. Kerti and F. Toptan, "Microstructural variations in cast B 4 C-reinforced aluminium matrix composites (AMCs)," *Materials letters,* vol. 62, pp. 1215-1218, 2008.

[140] V. M. S. K.R. Ravi, R.M. Pillai, Chandan Mahato, K.R. Amaranathan, R. Arul kumar, B.C. Pai, "Optimization of mixing parameters through a water model for metal matrix composites synthesis," *Materials & design,* vol. 28, pp. 871-881, 2007.

[141] B. Abbasipour, B. Niroumand, and S. M. Vaghefi, "Compocasting of A356-CNT composite," *Transactions of Nonferrous Metals Society of China,* vol. 20, pp. 1561-1566, 2010.

[142] S. GG, P. S Balasivanandha, and V. VSK, "Effect of processing paramters on metal matrix composites: stir casting process," *Journal of Surface Engineered Materials and Advanced Technology,* vol. 2012, 2012.

[143] S. K. Thandalam, S. Ramanathan, and S. Sundarrajan, "Synthesis, microstructural and mechanical properties of ex situ zircon particles (ZrSiO 4) reinforced Metal Matrix Composites (MMCs): a review," *Journal of Materials Research and Technology,* vol. 4, pp. 333-347, 2015.

[144] P. Sharma, G. Chauhan, and N. Sharma, "Production of AMC by stir casting–an overview," *International Journal of Contemporary Practices,* vol. 2, pp. 23-46, 2011.

[145] B. C. Kandpal and H. Singh, "Fabrication and characterisation of Al2O3/aluminium alloy 6061 composites fabricated by Stir casting," *Materials Today: Proceedings,* vol. 4, pp. 2783-2792, 2017.

[146] J. Hashim, "The production of cast metal matrix composite by a modified stir casting method," *Jurnal teknologi,* vol. 35, pp. 9-20, 2001.

[147] S. Gopalakrishnan and N. Murugan, "Prediction of tensile strength of friction stir welded aluminium matrix TiC p particulate reinforced composite," *Materials & Design,* vol. 32, pp. 462-467, 2011.

[148] N. Panwar and A. Chauhan, "Development of aluminum composites using Red mud as reinforcement-A review," in *Engineering and Computational Sciences (RAECS), 2014 Recent Advances in*, 2014, pp. 1-4.

[149] S. S. N. Ervina Efzan M.N., Mohd Mustafa Al Bakri Abdullah, "Fabrication Method of Aluminum Matrix Composite (AMCs): A Review," in *Key Engineering Materials*, 2016, pp. 102-110.

[150] N. S. B. S.Tzamtzis, N. Hari Babua, J. Patel, B.K. Dhindaw, Z. Fan, "Processing of advanced Al/SiC particulate metal matrix composites under intensive shearing–A novel Rheo-process," *Composites Part A: Applied Science and Manufacturing,* vol. 40, pp. 144-151, 2009.

[151] F. Akhlaghi, A. Lajevardi, and H. Maghanaki, "Effects of casting temperature on the microstructure and wear resistance of compocast A356/SiC p composites: a comparison between SS and SL routes," *Journal of Materials Processing Technology,* vol. 155, pp. 1874-1880, 2004.

[152] M. Ghahremainian and B. Niroumand, "Compocasting of an Al-Si-SiCp Composite Using Powder Injection Method," in *Solid state Phenomena*, 2008, pp. 175-180.

[153] M. T. P. S.A. Sajjadi, H.R. Ezatpour, A. Sedghi, "Fabrication of A356 composite reinforced with micro and nano Al 2 O 3 particles by a developed compocasting method and study of its properties," *Journal of alloys and compounds,* vol. 511, pp. 226-231, 2012.

[154] H. Khosravi, H. Bakhshi, and E. Salahinejad, "Effects of compocasting process parameters on microstructural characteristics and tensile properties of A356–SiCp composites," *Transactions of Nonferrous Metals Society of China,* vol. 24, pp. 2482-2488, 2014.

[155] V. Balaji, N. Sateesh, and M. M. Hussain, "Manufacture of Aluminium Metal Matrix Composite (Al7075-SiC) by Stir Casting Technique," *Materials Today: Proceedings,* vol. 2, pp. 3403-3408, 2015.

[156] S. S. S.Sarkar, S.C. Mishra, "Studies on Aluminum—Fly-Ash Composite Produced by Impeller Mixing," *Journal of reinforced plastics and composites,* vol. 29, pp. 144-148, 2010.

[157] M. K. Akbari, H. Baharvandi, and O. Mirzaee, "Nano-sized aluminum oxide reinforced commercial casting A356 alloy matrix: Evaluation of hardness, wear resistance and compressive strength focusing on particle distribution in aluminum matrix," *Composites Part B: Engineering,* vol. 52, pp. 262-268, 2013.

[158] I. Ibrahim, F. Mohamed, and E. Lavernia, "Particulate reinforced metal matrix composites—a review," *Journal of materials science,* vol. 26, pp. 1137-1156, 1991.

[159] Y. Sahin, "Preparation and some properties of SiC particle reinforced aluminium alloy composites," *Materials & design,* vol. 24, pp. 671-679, 2003.

[160] T. Miyajima and Y. Iwai, "Effects of reinforcements on sliding wear behavior of aluminum matrix composites," *Wear,* vol. 255, pp. 606-616, 2003.

[161] J. Hashim, L. Looney, and M. Hashmi, "The enhancement of wettability of SiC particles in cast aluminium matrix composites," *Journal of Materials Processing Technology,* vol. 119, pp. 329-335, 2001.

[162] G. Arslan and A. Kalemtas, "Processing of silicon carbide–boron carbide–aluminium composites," *Journal of the European Ceramic Society,* vol. 29, pp. 473-480, 2009.

[163] S. Dhinakaran and T. Moorthy, "Fabrication and Characteristic of Boron Carbide Particulate Reinforced Aluminum Metal Matrix Composites." International Journal of Engineering Research Science, Vol. 3, Issue 7, pp.1051-78, 2014.

[164] F. Toptan, A. Kilicarslan, and I. Kerti, "The effect of Ti addition on the properties of Al-B4C interface: A microstructural study," in Materials Science Forum, 2010, pp. 192-197.

[165] R. Asthana and P. Rohatgi, "On the melt infiltration of plain and nickel-coated reinforcements with aluminium alloys," *Journal of materials science letters,* vol. 12, pp. 442-445, 1993.

[166] J.-M. C. Ruth Klauser, T.J. Chuang, L.M. Chen, M.C. Shih, J.-C. Lin, "The interaction of oxygen and hydrogen on a diamond C (111) surface: a synchrotron radiation photoemission, LEED and AES study," *Surface science,* vol. 356, pp. L410-L416, 1996.

[167] R. K. CS Ramesh, BH Channabasappab, Abrar Ahmed, "Microstructure and mechanical properties of Ni–P coated Si 3 N 4 reinforced Al6061 composites," *Materials Science and Engineering: A,* vol. 502, pp. 99-106, 2009.

[168] L. Ceschini, G. Minak, and A. Morri, "Tensile and fatigue properties of the AA6061/20vol% Al 2 O 3p and AA7005/10vol% Al 2 O 3p composites," *Composites Science and Technology,* vol. 66, pp. 333-342, 2006.

[169] S. A. Sajjadi, H. Ezatpour, and M. T. Parizi, "Comparison of microstructure and mechanical properties of A356 aluminum alloy/Al 2 O 3 composites fabricated by stir and compo-casting processes," *Materials & Design,* vol. 34, pp. 106-111, 2012.

[170] S. Amirkhanlou and B. Niroumand, "Fabrication and characterization of Al356/SiC p semisolid composites by injecting SiC p containing composite powders," *Journal of Materials Processing Technology,* vol. 212, pp. 841-847, 2012.

[171] S. Amirkhanlou and B. Niroumand, "Synthesis and characterization of 356-SiCp composites by stir casting and compocasting methods," *Transactions of Nonferrous Metals Society of China,* vol. 20, pp. s788-s793, 2010.

[172] P. Shanmughasundaram, R. Subramanian, and G. Prabhu, "Some studies on aluminium–fly ash composites fabricated by two step stir casting method," *European journal of scientific research,* vol. 63, pp. 204-218, 2011.

[173] S. C. Tjong and Z. Ma, "Microstructural and mechanical characteristics of in situ metal matrix composites," *Materials Science and Engineering: R: Reports,* vol. 29, pp. 49-113, 2000.

[174] D. Priyadarshi and R. K. Sharma, "Porosity in aluminium matrix composites: cause, effect and defence," *Materials Science: An Indian Journal,* vol. 14, pp. 119-129, 2016.

[175] H. Ye and X. Liu, "Review of recent studies in magnesium matrix composites," *Journal of materials science,* vol. 39, pp. 6153-6171, 2004.

[176] N. Bonora and A. Ruggiero, "Micromechanical modeling of composites with mechanical interface–Part II: Damage mechanics assessment," *Composites science and technology,* vol. 66, pp. 323-332, 2006.

[177] A. S. Verma and N. M. Suri, "Corrosion Behavior of Aluminum Base Particulate Metal Matrix Composites: A Review," *Materials Today: Proceedings,* vol. 2, pp. 2840-2851, 2015.

[178] S. Zahi and A. Daud, "Fly ash characterization and application in Al–based Mg alloys," *Materials & Design,* vol. 32, pp. 1337-1346, 2011.

[179] A. A. M. N. Natarajan, R. Sivakumar, M. Manojkumar, M. Suresh, "Dry sliding wear and mechanical behavior of aluminium/fly ash/graphite hybrid metal matrix composite using taguchi method," *International Journal of Modern Engineering Research (IJMER),* vol. 2, pp. 1224-1230, 2012.

[180] R. Guo and P. Rohatgi, "Chemical reactions between aluminum and fly ash during synthesis and reheating of Al-fly ash composite," *Metallurgical and materials transactions B,* vol. 29, pp. 519-525, 1998.

[181] J. S. N. Sobczak, J. Morgiel, L. Stobierski, "TEM characterization of the reaction products in aluminium–fly ash couples," *Materials Chemistry and Physics,* vol. 81, pp. 296-300, 2003.

[182] C. G. R Escalera-Lozano, MA Pech-Canul, MI Pech-Canul, "Corrosion characteristics of hybrid Al/SiC p/MgAl 2 O 4 composites fabricated with fly ash and recycled aluminum," *Materials Characterization,* vol. 58, pp. 953-960, 2007.

[183] H. T. Hyun Bom Lee, Equo Kobayashi, Tatsuo Sato and Kee Do Woo, "Fabrication and mechanical properties of Al-based in situ nano-composites reinforced by Al2O3 and intermetallic compounds," *Materials Transactions,* vol. 53, pp. 428-434, 2012.

[184] N. Chawla and Y.-L. Shen, "Mechanical behavior of particle reinforced metal matrix composites," *Advanced engineering materials,* vol. 3, pp. 357-370, 2001.

[185] M. Milan and P. Bowen, "Tensile and fracture toughness properties of SiC p reinforced Al alloys: Effects of particle size, particle volume fraction, and matrix strength," *Journal of materials engineering and performance,* vol. 13, pp. 775-783, 2004.

[186] A. C. Reddy, "Influence of volume fraction, size, cracking, clustering of particulates and porosity on the strength and stiffness of 6063/SiCp metal matrix composites," *International Journal of Research in Engineering and Technology,* vol. 4, 2015.

[187] G. Gautam, N. Kumar, A. Mohan, R. Gautam, and S. Mohan, "Strengthening mechanisms of (Al3Zrmp+ ZrB2np)/AA5052 hybrid composites," *Journal of Composite Materials,* vol. 50, pp. 4123-4133, 2016.

[188] J. Singh and A. Chauhan, "Overview of wear performance of aluminium matrix composites reinforced with ceramic materials under the influence of controllable variables," *Ceramics International,* vol. 42, pp. 56-81, 2016.

[189] L. K. S Balasivanandha Prabu, S Kathiresan, B Mohan, "Influence of stirring speed and stirring time on distribution of particles in cast metal matrix composite," *Journal of Materials Processing Technology,* vol. 171, pp. 268-273, 2006.

[190] S. Naher, D. Brabazon, and L. Looney, "Development and assessment of a new quick quench stir caster design for the production of metal matrix composites," *Journal of Materials Processing Technology,* vol. 166, pp. 430-439, 2005.

[191] R. Bauri, D. Yadav, and G. Suhas, "Effect of friction stir processing (FSP) on microstructure and properties of Al–TiC in situ composite," *Materials Science and Engineering: A,* vol. 528, pp. 4732-4739, 2011.

[192] P. K. Rohatgi, "Low-cost, fly-ash-containing aluminum-matrix composites," *JOM Journal of the Minerals, Metals and Materials Society,* vol. 46, pp. 55-59, 1994.

[193] G. W. Zuoyong Dou, Xiaoli Huang, Dongli Sun, Longtao Jiang, "Electromagnetic shielding effectiveness of aluminum alloy–fly ash composites," *Composites Part A: Applied Science and Manufacturing,* vol. 38, pp. 186-191, 2007.

[194] J. K. PK Rohatgia, N Gupta, Simon Alaraj, A Daoud, "Compressive characteristics of A356/fly ash cenosphere composites synthesized by pressure infiltration technique," *Composites Part A: applied science and manufacturing,* vol. 37, pp. 430-437, 2006.

[195] P. Rohatgi, N. Gupta, and S. Alaraj, "Thermal expansion of aluminum–fly ash cenosphere composites synthesized by pressure infiltration technique," *Journal of Composite materials,* vol. 40, pp. 1163-1174, 2006.

[196] M. Surappa, "Synthesis of fly ash particle reinforced A356 Al composites and their characterization," *Materials Science and Engineering: A,* vol. 480, pp. 117-124, 2008.

[197] N. Suresh, S. Venkateswaran, and S. Seetharamu, "Influence of cenospheres of fly ash on the mechanical properties and wear of permanent moulded eutectic Al–Si alloys," *Materials Science-Poland,* vol. 28, pp. 55-65, 2010.

[198] R. Guo, P. Rohatgi, and D. Nath, "Preparation of aluminium-fly ash particulate composite by powder metallurgy technique," *Journal of materials science,* vol. 32, pp. 3971-3974, 1997.

[199] K. Mahendra and K. Radhakrishna, "Fabrication of Al-4.5% Cu alloy with fly ash metal matrix composites and its characterization," *Materials Science-Poland,* vol. 25, pp. 57-68, 2007.

[200] M. M. Boopathi, K. Arulshri, and N. Iyandurai, "Evaluation of mechanical properties of aluminium alloy 2024 reinforced with silicon carbide and fly ash hybrid metal matrix composites," *American journal of applied sciences,* vol. 10, p. 219, 2013.

[201] S. Malhotra, R. Narayan, and R. Gupta, "Synthesis and Characterization of Aluminium 6061 Alloy-Flyash & Zirconia Metal Matrix Composite," 2013.

[202] A. K. Senapati, P. C. Mishra, and B. C. Routara, "Use of Waste Flyash in Fabrication of Aluminium Alloy Matrix Composite," *Int. J. Eng. Technol,* vol. 6, pp. 905-912, 2014.

[203] A. Senapatia, A. Senapatib, and O. Mishrac, "Mechanical Properties of Fly Ash Reinforced Al-Si Alloy Based MMC," in *International Journal of Research in Advent Technology (E-ISSN: 2321-9637) Special Issue National Conference "IAEISDISE*, 2014.

[204] S. K. N. Kulkarni, "Effect of AL2O3 and fly ash reinforced particulates for fatigue behavior of the AL6061T6 alloy matrix composites." International Journal of Engineering Research. 2016, 5 (6), pp: 1129 - 1254

[205] R. Ilandjezian and S. Gopalakannan, "Tensile Fracture and Compression failure Behavior of Cenosphere Reinforced AA6061 Metal Matrix Composite," *Procedia Engineering,* vol. 173, pp. 1239-1245, 2017.

[206] M. P. K. Suragimath and G. Purohit, "A study on mechanical properties of aluminium alloy (LM6) reinforced with SiC and fly ash," *IOSR J. Mechanical and Civil Engg,* vol. 8, pp. 13-18, 2013.

[207] D. Miracle, "Metal matrix composites–from science to technological significance," *Composites science and technology,* vol. 65, pp. 2526-2540, 2005.

[208] S. Zahi and A. R. Daud, "Fly ash characterization and application in Al–based Mg alloys," *Materials & Design,* vol. 32, pp. 1337-1346, 2011.

[209] Y. K. CS Lee, KS Han, T Lim, "Wear behaviour of aluminium matrix composite materials," *Journal of Materials Science,* vol. 27, pp. 793-800, 1992.

[210] S. Kuo and D. Rigney, "Sliding behavior of aluminum," *Materials Science and Engineering: A,* vol. 157, pp. 131-143, 1992.

[211] A. Sannino and H. Rack, "Dry sliding wear of discontinuously reinforced aluminum composites: review and discussion," *Wear,* vol. 189, pp. 1-19, 1995.

[212] B. S. Ünlü, "Investigation of tribological and mechanical properties Al 2 O 3–SiC reinforced Al composites manufactured by casting or P/M method," *Materials & Design,* vol. 29, pp. 2002-2008, 2008.

[213] B. S. PK Rohatgi, A Daoud, WW Zhang, "Tribological performance of A206 aluminum alloy containing silica sand particles," *Tribology International,* vol. 43, pp. 455-466, 2010.

[214] S. Mahdavi and F. Akhlaghi, "Effect of the graphite content on the tribological behavior of Al/Gr and Al/30SiC/Gr composites processed by in situ powder metallurgy (IPM) method," *Tribology Letters,* vol. 44, pp. 1-12, 2011.

[215] R. Deuis, C. Subramanian, and J. Yellup, "Dry sliding wear of aluminium composites—a review," *Composites Science and Technology,* vol. 57, pp. 415-435, 1997.

[216] Q. X. Mingwu Bai, Xiue Wang, Yong Wan, Weiming Liu, "Wear mechanism of SiC whisker-reinforced 2024 aluminum alloy matrix composites in oscillating sliding wear tests," *Wear,* vol. 185, pp. 197-202, 1995.

[217] F. B. A Alahelisten, M Olsson, S Hogmark, "On the wear of aluminium and magnesium metal matrix composites," *Wear,* vol. 165, pp. 221-226, 1993.

[218] A. Pramanik, "Effects of reinforcement on wear resistance of aluminum matrix composites," *Transactions of Nonferrous Metals Society of China,* vol. 26, pp. 348-358, 2016.

[219] S. D. RN Rao, DP Mondal, G Dixit, SL Tulasi Devi, "Dry sliding wear maps for AA7010 (Al–Zn–Mg–Cu) aluminium matrix composite," *Tribology International,* vol. 60, pp. 77-82, 2013.

[220] R. Rao and S. Das, "Effect of SiC content and sliding speed on the wear behaviour of aluminium matrix composites," *Materials & Design,* vol. 32, pp. 1066-1071, 2011.

[221] J. Archard, "Contact and rubbing of flat surfaces," *Journal of applied physics,* vol. 24, pp. 981-988, 1953.

[222] F. Q. Delong Yang, Qinglong Zhao, Lei Wang, Qichuan Jiang, "The abrasive wear behavior of Al2014 composites reinforced with Ti 5 Si 3-coated SiC P," *Tribology International,* vol. 112, pp. 33-41, 2017.

[223] S. Wilson and A. Alpas, "Wear mechanism maps for metal matrix composites," *Wear,* vol. 212, pp. 41-49, 1997.

[224] S. Lim, M. Ashby, and J. Brunton, "Wear-rate transitions and their relationship to wear mechanisms," *Acta metallurgica,* vol. 35, pp. 1343-1348, 1987.

[225] R. Antoniou and C. Subramanian, "Wear mechanism map for aluminium alloys," *Scripta metallurgica,* vol. 22, pp. 809-814, 1988.

[226] S. Wilson and A. Alpas, "Thermal effects on mild wear transitions in dry sliding of an aluminum alloy," *Wear,* vol. 225, pp. 440-449, 1999.

[227] S. Zhiqiang, Z. Di, and L. Guobin, "Evaluation of dry sliding wear behavior of silicon particles reinforced aluminum matrix composites," *Materials & design,* vol. 26, pp. 454-458, 2005.

[228] V. S. K Ramachandran, PV Ananthapadmanabhan, KP Sreekumar., "Microstructure, adhesion, microhardness, abrasive wear resistance and electrical resistivity of the plasma sprayed alumina and alumina–titania coatings," *Thin Solid Films,* vol. 315, pp. 144-152, 1998.

[229] N. Suh, "Delamination wear of dispersion-hardened alloys," *Journal of Engineering for Industry,* p. 289, 1977.

[230] K. R. Kumar, K. Mohanasundaram, G. Arumaikkannu, and R. Subramanian, "Analysis of parameters influencing wear and frictional behavior of aluminum–fly ash composites," *Tribology Transactions,* vol. 55, pp. 723-729, 2012.

[231] K. Naplocha and K. Granat, "Wear performance of aluminium/Al 2 O 3/C hybrid composites," *Archives of Materials Science,* vol. 82, p. 82, 2008.

[232] R. N. Marigoudar and K. Sadashivappa, "Dry sliding wear behaviour of SiC particles reinforced Zinc-Aluminium (ZA43) alloy metal matrix composites," *Journal of Minerals and Materials Characterization and Engineering,* vol. 10, p. 419, 2011.

[233] T. Rajmohan, K. Palanikumar, and S. Ranganathan, "Evaluation of mechanical and wear properties of hybrid aluminium matrix composites," *Transactions of nonferrous metals society of China,* vol. 23, pp. 2509-2517, 2013.

[234] D. P. M. M. Singh, O.P. Modi, A.K. Jha, "Two-body abrasive wear behaviour of aluminium alloy–sillimanite particle reinforced composite," *Wear,* vol. 253, pp. 357-368, 2002.

[235] S. D. DP Mondal, AK Jha, AH Yegneswaran, "Abrasive wear of Al alloy–Al 2 O 3 particle composite: a study on the combined effect of load and size of abrasive," *Wear,* vol. 223, pp. 131-138, 1998.

[236] D. Mondal and S. Das, "High stress abrasive wear behaviour of aluminium hard particle composites: Effect of experimental parameters, particle size and volume fraction," *Tribology international,* vol. 39, pp. 470-478, 2006.

[237] S. Kumar and V. Balasubramanian, "Effect of reinforcement size and volume fraction on the abrasive wear behaviour of AA7075 Al/SiC p P/M composites—A statistical analysis," *Tribology international,* vol. 43, pp. 414-422, 2010.

[238] L. Huei-Long, L. Wun-Hwa, and S. L.-I. Chan, "Abrasive wear of powder metallurgy Al alloy 6061-SiC particle composites," *Wear,* vol. 159, pp. 223-231, 1992.

[239] S. Mohanty and Y. Chugh, "Development of fly ash-based automotive brake lining," *Tribology International,* vol. 40, pp. 1217-1224, 2007.

[240] K. Mahendra and K. Radhakrishna, "Castable composites and their application in automobiles," *Proceedings of the Institution of Mechanical Engineers, Part D: Journal of Automobile Engineering,* vol. 221, pp. 135-140, 2007.

[241] M. Uthayakumar, S. T. Kumaran, and S. Aravindan, "Dry sliding friction and wear studies of fly ash reinforced AA-6351 metal matrix composites," *Advances in Tribology,* vol. 2013, 2013.

[242] D. V. R. J Babu Rao, K Siva Prasad, NRMR Bhargava, "Dry sliding wear behaviour of fly ash particles reinforced AA 2024 composites," *Materials Science-Poland,* vol. 30, pp. 204-211, 2012.

[243] K. Prasad and M. Ramachandra, "Effect of Squeeze Pressure on The Hardness and Wear Resistance of Aluminium Fly Ash Composite Manufactured by Stir-Squeeze Casting," ed: IJEI, 2013.

[244] K. Prasad and M. Ramachandra, "Evaluation Of Factors Affecting Sliding Wear Behaviour Of Al-Flyash Metal Matrix Composites By Using Design Of Experiments," *International Journal of Modern Engineering Research, India,* vol. 3, pp. 2591-2599, 2013.

[245] P. J. Udaya and T. Moorthy, "Adhesive Wear Behaviour of Aluminium Alloy/Fly Ash Composites," in *Advanced Materials Research,* pp. 1290-1294, 2013.

[246] Q. Wang, F. Min, and J. Zhu, "Microstructural characterization and mechanical property of Fly Ash/Al-25Mg composites," *Journal of Wuhan University of Technology-Mater. Sci. Ed.,* vol. 29, pp. 1019-1022, 2014.

[247] F. S. DT Kountouras, A Tsouknidas, CA Vogiatzis, SM Skolianos, "Properties of High Volume Fraction Fly Ash/Al Alloy Composites Produced by Infiltration Process," *Journal of Materials Engineering and Performance,* vol. 24, pp. 3315-3322, 2015.

[248] A. C373-14a, "Standard Test Method for Water Absorption, Bulk Density, Apparent Porosity, and Apparent Specific Gravity of Fired Whiteware Products, Ceramic Tiles, and Glass Tiles, ASTM International, West Conshohocken.," 2014.

[249] A. E831-14, "Standard Test Method for Linear Thermal Expansion of Solid. Materials by Thermomechanical Analysis, ASTM International, West. Conshohocken, 2014. ," 2014.

[250] A. E. E8M-15a, "Standard Test Methods for Tension Testing of Metallic Materials, ASTM International, West Conshohocken, PA.," 2015.

[251] A. s. E9-09, "Standard Test Methods of Compression Testing of Metallic Materials at Room Temperature, ASTM International, West Conshohocken, PA.," 2009.

[252] A. Standard, "E384-16, Standard test method for microindentation hardness of materials," *West Conshohocken, PA: ASTM International,* 2016.

[253] E.-b. ASTM, "Standard Test Methods for Notched Bar Impact Testing of Metallic Materials," *ASTM Standards,* 2016.

[254] W. Bolton, *Higher engineering science*: Routledge, 2012.

[255] A. Standard, "G99-05, Standard test method for wear testing with a pin-on-disk apparatus," *Annual Book of ASTM Standards, G99-05,* vol. 3, 2005.

[256] R. Uyyuru, M. Surappa, and S. Brusethaug, "Tribological behavior of Al–Si–SiC p composites/automobile brake pad system under dry sliding conditions," *Tribology International,* vol. 40, pp. 365-373, 2007.

[257] R. Uyyuru, M. Surappa, and S. Brusethaug, "Effect of reinforcement volume fraction and size distribution on the tribological behavior of Al-composite/brake pad tribo-couple," *Wear,* vol. 260, pp. 1248-1255, 2006.

[258] S. Gopalakrishnan and N. Murugan, "Production and wear characterisation of AA 6061 matrix titanium carbide particulate reinforced composite by enhanced stir casting method," *Composites Part B: Engineering,* vol. 43, pp. 302-308, 2012.

[259] S. Aruna, V. W. Grips, and K. Rajam, "Ni-based electrodeposited composite coating exhibiting improved microhardness, corrosion and wear resistance properties," *Journal of Alloys and compounds,* vol. 468, pp. 546-552, 2009.

[260] S.-E. Inc., "Design-Expert software user's guide, Technical manual 2000.," vol. v10,, 2016.

[261] A. L. V Balasubramanian, R Varahamoorthy, S Babu, "Application of response surface methodolody to prediction of dilution in plasma transferred arc hardfacing of stainless steel on carbon steel," *Journal of Iron and Steel Research, International,* vol. 16, pp. 44-53, 2009.

[262] K. Elangovan, V. Balasubramanian, and S. Babu, "Predicting tensile strength of friction stir welded AA6061 aluminium alloy joints by a mathematical model," *Materials & Design,* vol. 30, pp. 188-193, 2009.

[263] S. Kumar and V. Balasubramanian, "Developing a mathematical model to evaluate wear rate of AA7075/SiC p powder metallurgy composites," *Wear,* vol. 264, pp. 1026-1034, 2008.

[264] S. Madhusudan, M. M. M. Sarcar, and N. B. R. M. Rao, "Mechanical properties of Aluminum-Copper (p) composite metallic materials," *Journal of applied research and technology,* vol. 14, pp. 293-299, 2016.

[265] E. Gikunoo, O. Omotoso, and I. Oguocha, "Effect of fly ash particles on the mechanical properties of aluminium casting alloy A535," *Materials science and technology,* vol. 21, pp. 143-152, 2005.

[266] A. M. Samuel, A. Gotmare, and F. H. Samuel, "Effect of solidification rate and metal feedability on porosity and SiCAl2O3 particle distribution in an Al-Si-Mg (359) alloy," *Composites Science and Technology,* vol. 53, pp. 301-315, 1995/01/01/ 1995.

[267] I. O. C Tekmen, U Cocen, K Onel, "The mechanical response of Al–Si–Mg/SiC p composite: influence of porosity," *Materials Science and Engineering: A,* vol. 360, pp. 365-371, 2003.

[268] T. C. PN Bindumadhavan, M Chandrasekaran, Heng Keng Wah, Loh Nee Lam, O Prabhakar, "Effect of particle-porosity clusters on tribological behavior of cast aluminum alloy A356-SiC p metal matrix composites," *Materials Science and Engineering: A,* vol. 315, pp. 217-226, 2001.

[269] M. Surappa and P. Rohatgi, "Fluidity of aluminum-silicon-alumina composite," *Metallurgical and Materials Transactions B,* vol. 12, pp. 327-332, 1981.

[270] M. O. S. A. Mazahery, M. R. Rahimipour, A. A. Tofigh, M. Razavi, "Effect of coated B4C reinforcement on mechanical properties of squeeze cast A356 composites," *Kovove Mater,* vol. 50, pp. 107-113, 2012.

[271] D. G. K.V. Shivananda Murthy, R Keshavamurthy, Temel Varol, Praveennath G. Koppa, "Mechanical and thermal properties of AA7075/TiO 2/Fly ash hybrid composites obtained by hot forging," *Progress in Natural Science: Materials International,* 2017.

[272] S. Basavarajappa, G. Chandramohan, and A. Dinesh, "Mechanical properties of mmc's-An experimental investigation," in *Int. symposium of research on Materials and Engineering, IIT, Madras, December,* 2004, pp. 1-8.

[273] S. KR, HB Niranjan, P Martin Jebaraj, MP Chowdiah, "Tensile and wear properties of aluminum composites," *Wear,* vol. 255, pp. 638-642, 2003.

[274] I. Dinaharan, N. Murugan, and S. Parameswaran, "Influence of in situ formed ZrB 2 particles on microstructure and mechanical properties of AA6061 metal matrix composites," *Materials Science and Engineering: A,* vol. 528, pp. 5733-5740, 2011.

[275] B. A. Kumar and N. Murugan, "Metallurgical and mechanical characterization of stir cast AA6061-T6–AlN p composite," *Materials & Design,* vol. 40, pp. 52-58, 2012.

[276] M. Ramachandra and K. Radhakrishna, "Microstructure, mechanical properties, wear and corrosion behaviour of Al–Si/FLYASHP composite," *Materials science and technology,* vol. 21, pp. 1337-1343, 2005.

[277] J. B. Rao, D. V. Rao, I. N. Murthy, and N. Bhargava, "Mechanical properties and corrosion behaviour of fly ash particles reinforced AA 2024 composites," *Journal of Composite Materials,* vol. 46, pp. 1393-1404, 2012.

[278] A. D. PK Rohatgi, BF Schultz, T Puri, "Microstructure and mechanical behavior of die casting AZ91D-Fly ash cenosphere composites," *Composites Part A: Applied Science and Manufacturing,* vol. 40, pp. 883-896, 2009.

[279] Y. Nishida, *Introduction to Metal Matrix Composites: Fabrication and Recycling*: Springer Science & Business Media, 2013.

[280] A. K. Srivastava and K. Das, "Microstructural and mechanical characterization of in situ TiC and (Ti, W) C-reinforced high manganese austenitic steel matrix composites," *Materials Science and Engineering: A,* vol. 516, pp. 1-6, 2009.

[281] I. D. J. Allwyn Kingsly Gladston, N. Mohamed Sheriff, J. David Raja Selvam, "Dry sliding wear behavior of AA6061 aluminum alloy composites reinforced rice husk ash particulates produced using compocasting," *Journal of Asian Ceramic Societies,* 2017.

[282] V. Rajeev, D. Dwivedi, and S. Jain, "Reciprocating wear behaviour of Al-Si-SiCp composites. indian conference.pp.1-7, 2013."

[283] K. M. K Ravi Kumar, G Arumaikkannu, R Subramanian, B Anandavel, "Influence of particle size on dry sliding friction and wear behavior of fly ash particle-reinforced A-380 Al matrix composites," *European Journal of Scientific Research,* vol. 60, pp. 410-420, 2011.

[284] G. C. S. Basavarajappa, K. Mukund, M. Ashwin, and M. Prabu, "Dry sliding wear behavior of Al 2219/SiCp-Gr hybrid metal matrix composites," *Journal of Materials Engineering and Performance,* vol. 15, pp. 668-674, 2006.

[285] B. P. M Singh, DP Mondal, AK Jha, "Dry sliding wear behaviour of an aluminium alloy–granite particle composite," *Tribology International,* vol. 34, pp. 557-567, 2001.

[286] K. M. M. Krishnan Ravi Kumar, Ganesan Arumaikkannu, Ramanathan Subramanian, "Effect of particle size on mechanical properties and tribological behaviour of aluminium/fly ash composites." Science and Engineering of Composite Materials Volume 19, Issue 3, pp. 247–253, 2012.

[287] M. Ramachandra and K. Radhakrishna, "Synthesis-microstructure-mechanical properties-wear and corrosion behavior of an Al-Si (12%)—Flyash metal matrix composite," *Journal of Materials Science,* vol. 40, pp. 5989-5997, 2005.

[288] G. V. Kumar, C. Rao, and N. Selvaraj, "Mechanical and tribological behavior of particulate reinforced aluminum metal matrix composites–a review," *Journal of minerals and materials characterization and engineering,* vol. 10, p. 59, 2011.

[289] C. Ramesh and A. Ahamed, "Friction and wear behaviour of cast Al 6063 based in situ metal matrix composites," *Wear,* vol. 271, pp. 1928-1939, 2011.

[290] K. Umanath, K. Palanikumar, and S. Selvamani, "Analysis of dry sliding wear behaviour of Al6061/SiC/Al 2 O 3 hybrid metal matrix composites," *Composites Part B: Engineering,* vol. 53, pp. 159-168, 2013.

[291] A. Baradeswaran, A. Elayaperumal, and R. F. Issac, "A statistical analysis of optimization of wear behaviour of al-al2o3 composites using taguchi technique," *Procedia Engineering,* vol. 64, pp. 973-982, 2013.

[292] Y. Hirai, T. Sato, T. Fukui, K. Yamada, K. Tanizawa, and H. Usami, "Effect of surface groove and graphite penetration on friction properties of sulfide containing copper alloy journal bearing in dry condition," *Procedia Engineering,* vol. 68, pp. 37-42, 2013.

[293] A. M. Al-Qutub, I. M. Allam, and M. A. Samad, "Wear and friction of Al–Al2O3 composites at various sliding speeds," *Journal of Materials Science,* vol. 43, pp. 5797-5803, 2008.

[294] N. S. Prabhakar, N. Radhika, and R. Raghu, "Analysis of tribological behavior of aluminium/B4C composite under dry sliding motion," *Procedia Engineering,* vol. 97, pp. 994-1003, 2014.

[295] S. H. J. L. Faiz Ahmad, Muhammad Aslam, Ahmad Haziq, "Tribology behaviour of alumina particles reinforced aluminium matrix composites and brake disc materials.," *Procedia engineering,* vol. 68, 2013.

[296] L. F. Xavier and P. Suresh, "Wear Behavior of Aluminium Metal Matrix Composite Prepared from Industrial Waste," *The Scientific World Journal,* vol. 2016, 2016.

[297] V. K. Sharma, R. Singh, and R. Chaudhary, "Effect of flyash particles with aluminium melt on the wear of aluminium metal matrix composites," Engineering Science and Technology, International Journal, 20(4), pp.1318–1323, 2017.

[298] S. K. PRS Kumar, T Srinivasa Rao, S Natarajan, "High temperature sliding wear behavior of press-extruded AA6061/fly ash composite," *Materials Science and Engineering: A,* vol. 527, pp. 1501-1509, 2010.

[299] N. Radhika, R. Subramanian, and S. V. Prasat, "Tribological behaviour of aluminium/alumina/graphite hybrid metal matrix composite using Taguchi's techniques," *Journal of Minerals and Materials Characterization and Engineering,* vol. 10, p. 427, 2011.

[300] K. Holmberg and A. Matthews, "Tribological properties of metallic and ceramic coatings," vol. 2, ed: CRC Press, Boca Raton, FL, 2001, pp. 827-870.

[301] S. Zhang and F. Wang, "Comparison of friction and wear performances of brake material dry sliding against two aluminum matrix composites reinforced with different SiC particles," *Journal of Materials Processing Technology,* vol. 182, pp. 122-127, 2007.

[302] V. R. Rajeev, D. K. Dwivedi, and S. C. Jain, "Effect of experimental parameters on reciprocating wear behavior of Al-Si-SiCp composites under dry condition," *Tribology Online*, vol. 4, pp. 115-126, 2009.

[303] D. S. Badkar, K. S. Pandey, and G. Buvanashekaran, "Development of RSM- and ANN-based models to predict and analyze the effects of process parameters of laser-hardened commercially pure titanium on heat input and tensile strength," *The International Journal of Advanced Manufacturing Technology*, pp. 1-20, 2013.