



**UNIVERSITI PUTRA MALAYSIA**

***EFFECTS OF PULPING CONDITIONS AND PROCESSING VARIABLES  
ON  
THE PERFORMANCE OF KENAF MEDIUM DENSITY FIBRE BOARD***

**MAJID DEGHAN NAYERI**

**IPTPH 2014 8**



**EFFECTS OF PULPING CONDITIONS AND PROCESSING VARIABLES ON  
THE PERFORMANCE OF KENAF MEDIUM DENSITY FIBRE BOARD**

**By**

**MAJID DEHGHAN NAYERI**

**Thesis submitted to the School of Graduate Studies, Universiti Putra Malaysia, in  
Fulfillment of the Requirements for the Degree of Doctor of Philosophy**

**July 2014**

## **COPYRIGHT**

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



**Dedicated To**

**This thesis is dedicated to my lovely children Amin, Ali and Mohammad, my dear wife, and my parents that I owe them all of success in my life.**



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Doctor of Philosophy

**EFFECTS OF PULPING CONDITIONS AND PROCESSING VARIABLES ON THE PERFORMANCE OF KENAF MEDIUM DENSITY FIBRE BOARD**

By

**MAJID DEGHAN NAYERI**

**July 2014**

**Chairman: Professor Paridah Md. Tahir, PhD**

**Institute: Institute of Tropical Forestry and Forest Products**

Kenaf, *Hibiscus cannabinus* L., is an environmentally friendly crop which is recognized as one of the potential lignocellulosic materials to replace wood in different kinds of wood-based products. Kenaf has excellent properties for pulp and paper, medium density fibre board (MDF), and other composites, as it has a low density, little abrasion during processing, high filling levels, and high specific mechanical properties. The kenaf stem is composed of an outer layer (bast) and a core which either by chemicals and/or by enzymatic retting is easy to separate. The bast constitutes 25 to 40% of the stem dry weight and shows a dense structure. Alternatively, the core is wood-like and makes up the remaining 60 to 75% of the stem. Both portions are greatly different in terms of anatomy, physical and chemical content.

Studies concerning the production of medium density fibre board (MDF) with kenaf as an alternative fibrous material have been carried out as an attempt to provide a sustainable and viable destination for this lignocellulosic material. This work aimed to evaluate the properties of kenaf fibres at different refining conditions and to produce kenaf MDF of acceptable strength. In this dissertation, MDF was prepared from kenaf and rubber wood and their mixture. The parameters of preparation and the resulting intermediate products as well as the final products, MDF, were characterized and compared at each experimental step.

The investigation of fibre dimensions based on pulping of bast and core fibre resulted in different behavior of the two classes of fibre. There are significant variations in all aspects of fibre morphology of bast fibre at different pulping temperatures and pulping time, and a significant interaction was detected between both parameters. The bast fibre produced longer and thinner fibre, compared to the core fibre, thus yielding fibre of higher aspect ratio. The changes in fibre morphology were clear when the pulped temperature increased. The core fibre exhibited significant variations in fibre length, fibre width, and wall thickness in all parameters. The lumen diameter and aspect ratio

fibre width, and wall thickness in all parameters. The lumen diameter and aspect ratio were not significantly affected by differences in pulping temperature, pulping time, and the interaction between both parameters. The fibre width was reduced at an increasing pulping temperature and time, but lumen diameter was not significantly affected. The aspect ratio also decreased with increasing pulping temperature and time. The length of core fibre decreased with increasing pulping temperature and pulping time. The fibre width shows constant reduction as the pulping condition become more severe. Consequently the Runkel ratio was decreased also. The pH value of both fibres was reduced as the temperature increased; core fibre was more acidic (pH= 3.8) compared to bast fibre (pH= 4.5). It is evident from results that bast fibre is more resistant to acid and displayed greater acid buffering capacity compared to core fibre.

The investigation of the effect of refining pressure (6 and 8) and resin content (10, 12, 14 %) on physical (WA and TS), and mechanical (MOE, MOR, IB) properties MDF made from a mixture of biomass kenaf (*Hibiscus cannabinus* L.) stem and rubberwood showed thermo-mechanical refining and resin content were influential in the increment of physical and mechanical properties of the MDF. For 8 bar of refining pressure with 14% resin content, the MDF recorded optimum WA of 83.12%, TS of 20.2%, MOR of 25.3 MPa, MOE of 3450 MPa and IB of 0.51 MPa [density 700 (kg/m<sup>3</sup>)].

Response surface methodology was used to establish the optimum process variables (resin content, and pressure) for effect on board properties. By using response surface and contour plots, the optimum set of operating variables can be obtained graphically, in order to achieve the desired board properties. Therefore, it was recommended that the board properties increase when the resin content and pressure increased. It can be inferred that any parameters, individually, had a positive effect on the increase of board properties. The main effects of parameters are in following order: main effect of resin content > pressure.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk Ijazah Master Sains

**KESAN PEMBOLEHUBAH PENAPISAN KE ATAS SIFAT GENTIAN KENAF  
DAN PENGARUH TERHADAP PERSASTI PAPAN GENTIAN  
BERKETUMPATAN SEDERHANA**

Oleh

**MAJID DEGHAN NAYERI**

**Julai 2014**

**Pengerusi: Professor Paridah MD Tahir, PhD**

**Institut: Institut Perhutanan Tropika dan Produk Hutan**

*Kenaf*, *Hibiscus cannabinus L.*, adalah tanaman mesra alam yang diiktiraf sebagai salah satu bahan lignoselulosik yang berpotensi untuk menggantikan kayu dalam pelbagai jenis produk berasaskan kayu. Kenaf mempunyai ciri-ciri yang sangat baik untuk pulpa dan kertas, papan gentian berkepadatan sederhana (MDF), dan komposit lain kerana ia mempunyai ketumpatan yang rendah, sedikit lelasan semasa pemprosesan, tahap pengisian yang tinggi, dan sifat-sifat mekanikal yang tinggi. Batang kenaf terdiri daripada lapisan luar (bast) dan teras yang mudah dipisahkan sama ada dengan menggunakan bahan kimia atau enzim pengeratan. Bast yang membentuk 25 hingga 40% daripada berat batang kering mempunyai struktur yang padat. Teras kenaf pula mempunyai sifat seperti kayu dan membentuk 60-75 % daripada batang kenaf. Kedua-dua bahagian adalah sangat berbeza dari segi anatomi, fizikal dan kandungan kimia.

Kajian mengenai pengeluaran papan gentian berkepadatan sederhana (MDF) dengan kenaf sebagai bahan berserabut alternatif telah dijalankan sebagai satu usaha untuk menyediakan destinasi mampan dan berdaya maju untuk bahan lignoselulosik ini. Kajian ini bertujuan untuk menilai sifat-sifat gentian kenaf pada keadaan penapisan yang berbeza dan untuk menghasilkan MDF kenaf dengan kekuatan yang boleh diterima. Di dalam disertasi ini, MDF telah disediakan daripada kenaf dan kayu getah dan juga campuran kedua-dua bahan. Parameter penyediaan dan produk perantaraan serta produk akhir, MDF, telah disifatkan dan dibandingkan pada setiap langkah eksperimen.

Siasatan dimensi ke atas serat berasaskan pulpa daripada bast dan teras menunjukkan tingkah laku yang berbeza antara kedua-dua serat tersebut. Terdapat variasi yang ketara dalam semua aspek morfologi gentian bast pada suhu dan masa pulpupaan yang berbeza, dan interaksi yang nyata telah dikesan di antara kedua-dua parameter tersebut.

Bast menghasilkan serat yang lebih nipis dan panjang berbanding dengan teras, dengan itu menghasilkan serat yang mempunyai nisbah aspek ratio yang lebih tinggi. Perubahan dalam serat morfologi adalah jelas apabila suhu pulped meningkat. Serat teras mempamerkan variasi ketara dalam panjang gentian, lebar serat, dan ketebalan dinding pada semua parameter. Garis pusat lumen dan nisbah aspek ratio tidak terjejas ketara oleh perbezaan dalam suhu pulpa, masa pulpa, dan interaksi antara kedua-dua parameter tersebut. Lebar serat berkurangan dengan peningkatan suhu dan masa pulpulpaan, tetapi diameter lumen tidak terjejas dengan ketara. Nisbah aspek ratio juga menurun dengan peningkatan suhu dan masa pulpulpaan. Panjang serat teras menurun dengan peningkatan suhu dan masa pulpulpaan. Lebar serat menunjukkan pengurangan berterusan kerana keadaan pulpa menjadi lebih teruk. Oleh yang demikian, nisbah Runkel turut menurun. Nilai pH bagi kedua-dua serat berkurangan apabila suhu meningkat; gentian teras adalah lebih berasid ( $\text{pH} = 3.8$ ) berbanding dengan gentian kulit ( $\text{pH} = 4.5$ ). Ianya jelas bahawa gentian kulit adalah lebih tahan asid dan memaparkan kapasiti buffering asid yang lebih besar berbanding dengan gentian teras. Siasatan daripada kesan tekanan penapisan (6 dan 8) dan kandungan resin (10, 12, 14 %) pada sifat fizikal (WA dan TS), dan mekanikal (MOE, MOR, IB) MDF dibuat daripada campuran batang kenaf (*Hibiscus cannabinus* L.) dan kayu getah menunjukkan bahawa penapisan termo-mekanikal dan kandungan resin mempengaruhi kenaikan sifat-sifat fizikal dan mekanikal MDF. Pada tekanan penapisan 8 bar dengan kandungan resin 14%, MDF merekodkan WA yang optimum iaitu 83.12 %, TS sebanyak 20.2 %, MOR sebanyak 25.3 MPa, MOE sebanyak 3450 MPa dan IB sebanyak 0.51 MPa [kepadatan  $700 \text{ (kg/m}^3\text{)}$ ].

Kaedah gerak balas permukaan telah digunakan untuk mewujudkan pemboleh ubah proses yang optimum (kandungan resin, dan tekanan) untuk kesan terhadap ciri papan. Dengan menggunakan permukaan sambutan dan plot kontur, set optimum pembolehubah operasi boleh diperolehi secara grafik, untuk mencapai ciri papan yang dikehendaki. Oleh itu, adalah dicadangkan bahawa ciri papan meningkat apabila kandungan resin dan tekanan meningkat. Kesimpulan boleh dibuat bahawa mana-mana parameter, secara individu, mempunyai kesan yang positif terhadap peningkatan ciri papan. Kesan utama parameter diatur seperti berikut: Kesan utama kandungan resin > tekanan.



## ACKNOWLEDGEMENTS

All praise and thanks to Allah, the owner of humankind, and all that exists.

I wish to express my sincere appreciation and gratitude to my supervisor, Professor Dr. Paridah MD Tahir, and co-supervisors, Professor Dr. Jalaluddin B Harun, Associate Professor Dr. Edi Suhaimi Bakar and Professor Dr. Luqman Chuah Abdullah for their invaluable guidance, advice, constructive comments and encouragement throughout my project and in preparing this thesis.

I also wish to thank exactly my wife, and my sons, for their patience, understanding, love and support. Without you, I could not have accomplished this task.

Last, but not the least, my deepest appreciation to my parents who have made me who I am today. Words cannot express how grateful I am for their eternal love and support. I would never have gotten to this point without you.

I certify that a Thesis Examination Committee has met on 18 July 2014 to conduct the final examination of Majid Dehghan Nayyeri on his thesis entitled "Effects Of Pulping Conditions and Processing Variables on the Performance of Kenaf Medium Density Fibre Board" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

**H Ng Paik San, PhD**  
Associate Professor  
Faculty of Forestry  
Universiti Putra Malaysia  
(Chairman)

**Jegatheswaran a/l Ratnasingam, PhD**  
Professor  
Faculty of Forestry  
Universiti Putra Malaysia  
(Internal Examiner)

**Mohd Sapuan bin Salit @ Sinon, PhD**  
Professor Ir.  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Gyu - Hyeok Kim, PhD**  
Professor  
Korea University  
Republic of Korea  
(External Examiner)



---

**NORITAH OMAR, PhD**  
Associate Professor and Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 19 September 2014

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

**Paridah Mohd Tahir**

Professor  
Institute Tropical Forestry and Forest Product  
Faculty of Forestry  
Universiti Putra Malaysia  
(Chairman)

**Jalaluddin B Harun**

Professor  
Institute Tropical Forestry and Forest Product  
Universiti Putra Malaysia  
(Member)

**Edi Suhaimi Bakar**

Associate Professor,  
Faculty of Forestry  
Universiti Putra Malaysia  
(Member)

**Luqman Chuah Abdullah**

Professor,  
Department Of Chemical and Environmental Engineering /  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)

---

**BIJANG BIN KIM HUAT, PhD**

Professor and Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date:

## Declaration by the student

I hereby confirm that:

- this thesis is my original work
- quotations, illustrations and citations have been duly referenced
- the thesis has not been submitted previously or concurrently for any other degree at any institutions
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be owned from supervisor and deputy vice –chancellor (Research and innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- there is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software

Signature: \_\_\_\_\_ Date: \_\_\_\_\_

Name and Matric No.: Majid Dehghan Nayeri GS16378

## Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: \_\_\_\_\_  
Name of  
Chairman of  
Supervisory  
Committee: \_\_\_\_\_

Signature: \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee: \_\_\_\_\_

Signature: \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee: \_\_\_\_\_

Signature: \_\_\_\_\_  
Name of  
Member of  
Supervisory  
Committee: \_\_\_\_\_

## TABLE OF CONTENTS

	<b>Page</b>
<b>ABSTRACT</b>	i
<b>ABSTRAK</b>	iii
<b>ACKNOWLEDGEMENTS</b>	v
<b>APPROVAL</b>	vi
<b>DECLARATION</b>	vii
<b>LIST OF TABLES</b>	xiii
<b>LIST OF FIGURES</b>	xv
<b>LIST OF ABBREVIATIONS</b>	xix
<b>CHAPTER</b>	
<b>1 INTRODUCTION</b>	
1.1 Background	1
1.1.1 Kenaf Anatom	1
1.1.2 MDF Manufacture	1
1.2 Problem Statemen	2
1.3 Objectives	3
<b>2 LITERATURE REVIEW</b>	
2.1 Natural Fibers	5
2.1.1 Development of Plant Based Natural Fibres to the Composite Board	9
2.2 Kenaf ( <i>Hibiscus cannabinus</i> L.)	
2.2.1 Physical Properties of Kenaf ( <i>Hibiscus cannabinus</i> L.)	11
2.2.2 Morphology of Kenaf Fibre	12
2.2.3 Chemical Composition of Kenaf	13
2.2.4 Kenaf, a Fibre for the Future of Malaysia	14
2.3 Medium Density Fiberboard (MDF) Industry	17
2.4 Pulping Process for Medium Density Fiberboard (MDF) Producing	18
2.4.1 Mechanical Pulping	20
2.4.2 Thermomechanical Pulping (TMP)	20
2.4.3 Plate Pastern Design	22
2.5 Pulping Processing Parameters	23
2.5.1 Steam Pressure	24
2.5.2 Temperature	24
2.5.3 Retention Time	24
2.6 Thermo-mechanical Pulping (TMP) of Wood and Non Wood Materials	25
2.7 Fibre Morphological Characteristics	25
2.7.1 Runkel Ratio (RR)	25
2.7.2 Aspect Ratio (AR)	26
2.7.3 Flexibility Ratio	26
2.8 Effect of Pulping Process on the Fibre Morphological Characteristics	26
2.8.1 Fibre Surface	27

2.8.2	PH and fibre Buffering capacity	29
2.9	The Effect of Refining Condition and Fibre Properties on the MDF Performance	
2.9.1	The Effect of Refining Conditions and Fibre Properties on the Mechanical Properties of MDF Panel	29
2.10	Application of MDF	30
2.11	Response Surfaces Methodology (RSM)	31
<b>3</b>	<b>EFFECTS OF TEMPRATURE AND TIME ON THE MORPHOLOGY OF BAST AND CORE KENAF FIBRES</b>	
3.1	Introduction	34
3.2	Materials and Methods	34
3.2.1	Raw Material Preparation	36
3.2.2	Chipping and Flaking	36
3.2.3	Pulping and Refining	38
3.2.4	Morphological Characteristics	38
3.2.4.1	Measurement of Fibre Dimension	38
3.2.4.2	Aspect Ratio (AR)	38
3.2.4.3	Runkel Ratio (RR)	39
3.2.4.4	Flexibility Ratio	39
3.2.5	Evaluation of Fibre Surface	39
3.2.6	Data Analysis	39
3.3	Results and Discussion	40
3.3.1	Effect of Refining Condition on Fibre Properties	40
<b>4</b>	<b>EFFECTS OF TEMPRATURE AND TIME ON PH AND BUFFERING CAPACITY OF BAST AND CORE KENAF FIBRES</b>	
4.1	Introduction	60
4.2	Materials and Methods	60
4.2.1	Raw Material Preparation	60
4.2.2	Determination of Fibre Buffering Capacity	62
4.2.3	Data Analysis	62
4.3	Results and Discussion	62
4.3.1	Effect of pulping condition on fibre pH and buffering capacity	63
<b>5</b>	<b>EFFECT OF THERMO-MECHANICAL REFINING AND RESIN CONTENT ON PROPERTIES OF MEDIUM DENSITY FIBREBOARD MADE FROM KENAF (<i>HIBISCUS CANNABINUS L.</i>) STEM</b>	
5.1	Introduction	69
5.2	Materials and Methods	69
5.2.1	Raw Material Preparation	69
5.2.2	Preparation of MDF Board	69
5.2.3	Characterization	70

5.2.4	Gas permeability measurement	71
5.2.5	Data Analysis	73
5.3	Results and Discussion	74
5.3.1	Effects of Refining Conditions and Resin Content on the Mechanical Properties of MDF Samples	74
5.3.2	Overall mechanical and physical properties	83
<b>6</b>	<b>OPTIMAIZATION OF PROCESSING VARIABLES IN KENAF – RUBBERWOOD COMPOSITE PANEL MANUFACTURING TECHNOLOGY</b>	
6.1	Introduction	84
6.2	Material and methods	84
6.2.1	Experimental materials	85
6.2.2	Experimental Design	85
6.2.3	MDF manufacturing	86
6.2.4	Characterization	86
6.2.5	Data Analysis and Statistical Methods	87
6.3	Results and Discussion	88
6.3.1	Analysis of Variance and Regression Coefficients of Factors	88
6.3.2	Relationship between Response and Independent Variables	91
<b>7</b>	<b>CONCLUSIONS AND RECOMMENDATIONS</b>	<b>99</b>
	<b>REFERENCES</b>	<b>101</b>
	<b>BIODATA OF STUDENT</b>	<b>110</b>
	<b>LIST OF PUBLICATIONS</b>	<b>111</b>



## LIST OF TABLES

<b>Table</b>	<b>Page</b>
2.1 Physical properties of plant natural fibres	7
2.2 Advantages and disadvantage of natural fibers products	9
2.3 World production of kenaf	11
2.4 Chemical composition and physical properties of core and bast kenaf fibres	13
2.5 Kenaf Environment-friendly properties	15
2.6 Comparison of pulping processes	19
2.7 Comparison of Kraft & Thermomechanical Pulp (TMP) fibres	19
2.8 Plate pattern design	23
3.1 Properties of kenaf plant in this study	35
3.2 Pulping process condition for bast and core fibre	37
3.3 Summary of ANOVA on the fibre morphology of bast fibre	40
3.4 Fibre dimensions and properties of bast fibre	41
3.5 Summary of ANOVA on the fibre morphology of core fibre	44
3.6 Fibre dimensions and properties of core fibre	50
4.1 The pH value of bast and core fibre after pulping and refining	63
5.1 Lab panel manufacturing parameters	70
5.2 Experimental Design and adjusted test results	73
5.3 Summary of ANOVA on the mechanical and physical properties of MDF samples	82
6.1 Factors and corresponding levels for response surface design	86
6.2 Lab panel manufacturing parameters	86
6.3 Experimental Design and adjusted test results	88

6.4	ANOVA for response surface quadratic model of MOR Probability of variable	89
6.5	ANOVA for response surface quadratic model of MOE Probability of variable	89
6.6	ANOVA for response surface quadratic model of IB Probability of variable	90
6.7	ANOVA for response surface quadratic model of WA Probability of variable	90
6.8	ANOVA for response surface quadratic model of TS Probability of variable	91

## LIST OF FIGURES

<b>Figure</b>		<b>Page</b>
2.1	Classification of natural and synthetic fibres	6
2.2	Common plant based natural fibres	8
2.3	( A and B) The green stalk of kenaf, (C and D) bast and core parts of kenaf	12
2.4	Organic car components from kenaf	16
2.5	Heat Conductive Bioplastics from Kenaf	16
2.6	different section of refiner	21
2.6	The uses of MDF in office storage, tough environment storage, table tops, and exhibition furniture	31
3.1	Experimental design for determination the fibre characteristics	35
3.2	Kenaf raw material used in this project	36
3.3	Double slender digester and pulp digester	37
3.4	Refiner Mechanical Pulp (RMP)	37
3.5	Image analysis system	38
3.6	Bast fibre lengths in different time and temperatures	42
3.7	Bast fibre width in different time and temperatures	42
3.8	Bast fibre lumen diameter in different time and temperatures	43
3.9	Bast fibre Thickness wall in different time and temperatures	43
3.10	Bast fibre Runkle ratio in different time and temperatures	44

3.11	Bast fibre Aspect ratio in different time and temperatures	44
3.12	Bast fibre IFlexibility in different time and temperatures	45
3.13	Image analysis micrograph of bast fibre refined at different temperatures and time	46
3.14	SEM micrograph of bast fibre refined at 150°C for 3 hours	47
3.15	SEM micrograph of bast fibre refined at 150°C for 3 hours	47
3.16	SEM micrograph of bast fibre refined at 180°C for 3 hours	48
3.17	SEM micrograph of bast fibre refined at 180°C for 3 hours	48
3.18	Core fibre lengths in different time and temperatures	51
3.19	Core fibre width in different time and temperatures	51
3.20	Core fibre lumen diameter in different time and temperatures	52
3.21	Core fibre Tickness wall in different time and temperatures	52
3.22	Core fibre Runkle ratio in different time and temperatures	53
3.23	Core fibre Aspect ratio in different time and temperatures	53
3.24	Core fibre IFlexibility in different time and temperatures	54
3.25	Image analysis micrograph of core fibre refined at different temperatures and time	55
3.26	SEM micrograph of core fibre refined at 150°C for 3 hours	56
3.27	SEM micrograph of core fibre refined at 150°C for 3 hours	56
3.28	SEM micrograph of core fibre refined at 180°C for 3 hours	57

3.29	SEM micrograph of core fibre refined at 180°C for 3 hours	57
4.1	Buffering capacity test	62
4.2	Bast fibre buffering capacity in acidic conditions	64
4.3	Core fibre buffering capacity in acidic conditions	65
4.4	Bast fibre buffering capacity in alkaline conditions	67
4.5	Core fibre buffering capacity in alkaline conditions	67
5.1	Mechanical test	71
5.2	Sampling scheme for obtainment of the specimens for permeability tests	71
5.3	Overview of the gas permeability apparatus	72
5.4	Modulus of rupture of the samples manufactured with refining pressure bar and different resin content	74
5.5	Modulus of rupture of the samples manufactured with refining pressure bar and different resin content	75
5.6	Modulus of elasticity of the samples manufactured with refining pressure bar and different resin content	76
5.7	Modulus of elasticity of the samples manufactured with refining pressure bar and different resin content	76
5.8	Internal bonding of the samples manufactured with refining pressure bar and different resin content	77
5.9	Internal bonding of the samples manufactured with refining pressure bar and different resin content	77
5.10	Water absorption of the samples manufactured with refining pressure bar and different resin content	78
5.11.	Water absorption of the samples manufactured with refining pressure bar and different resin content	79

5.12.	Thickness swelling of the samples manufactured with refining pressure bar and different resin content	80
5.13.	Thickness swelling of the samples manufactured with refining pressure bar and different resin content	80
5.14.	Specific gas permeability values of the two different vacuum pressures for different MDF raw materials	81
5.15	Water absorption and thickness swelling values of the different MDF raw material	82
6.1	Response surface with contour plot (3D) showing the effects of refining pressure (A) and resin content on the response of IB	92
6.2	Response surface with contour plot (3D) showing the effects of refining pressure (A) and resin content on the response of MOR	93
6.3	Response surface with contour plot (3D) showing the effects of refining pressure (A) and resin content on the response of MOE	94
6.4	Response surface with contour plot (3D) showing the effects of refining pressure (A) and resin content on the response of WA	95
6.5	Response surface with contour plot (3D) showing the effects of refining pressure (A) and resin content on the response of TS	96

## LIST OF ABBREVIATIONS

AFM	Atomic force microscopy
ANOVA	Analysis of variance
AR	Aspect ratio
BC	Buffering capacity
CCD	Central composite design
CMP	Chemical mechanical pulp
CR	Compression ratio
CTMP	Chemical thermo-mechanical pulp
D/IF	Delamination/internal fibrillation
EFB	Empty fruit bunch
HCL	Hydrochloric acid
IB	Internal bond strength
INTROP	Institute of Tropical Forestry and Forest Products
JANS	Japan, Australia and New Zealand Standard
L/D	Length to diameter ratio
LE	Linear expansion
LSD	Least significant difference
MC	Moisture content
MDF	Medium Density Fiberboard
MOE	Modulus of elasticity
MPOB	Malaysian Palm Oil Board
MUF	Melamine modified urea-formaldehyde
NaOH	Sodium hydroxide
NSSC	Neutral sulphite semi-chemical
RMP	Refiner mechanical pulping
RR	Runkel ratio
RSM	Response Surfaces Methodology
RW	Rubber wood
SAS	Statistical analysis system
TMP	Thermomechanical Pulping
TS	Thickness swelling
UF	Urea-formaldehyde
WA	Water absorption

## CHAPTER 1

### INTRODUCTION

#### 1.1 Background

The available supply of wood is becoming limited in many parts of the world as a result of environmental and green movement, landfill regulations and recycling trends. Due to poor resources of wood for composite board manufacturing, non-wood fibres play a major role in providing the equilibrium between supply and demand (Kalaycioglu and Nemli, 2006a). However many factors such as politic, trade and industry, social, geographic and ecology determine the accessibility and end use of these renewable bio-resources throughout the world (Aji et al., 2009).

Medium density fibreboard (MDF) is manufactured by reconstituting fibres through a flexible and wide range of manufacturing conditions; any non-wood fibre, including various agricultural crops, could be potential raw material for the manufacture of MDF (Xing et al., 2006). Wide varieties of crops from many different regions around the world have been studied for this purpose (Papadopoulos, 2003). In general, lignocellulosic non-wood fibres are a relatively inexpensive substitute to higher-quality wood fibres (Ye et al., 2007).

Kenaf, *Hibiscus cannabinus* L., is a biodegradable and environmentally friendly crop with one of the highest rates of CO<sub>2</sub> absorption of any plant (Kalaycioglu and Nemli, 2006b). It is very effective in mitigating the effects of global warming and is currently being grown in many continents (tropical and subtropical) for its beneficial properties.

Nowadays, there are various new applications for kenaf including paper products (newsprint, bond paper, and corrugated liner board) (Mossello et al., 2010). Recent researches to have further increased the diversity of uses for kenaf by demonstrating its suitability in building materials (fibreboards), textiles, adsorbents, and fibres in new and recycled plastics (Russo et al., 2012). One of the most rapidly expanding applications for kenaf fibres at present is in composites. The interest in using natural fibres in composites has increased during recent years due to their combustible, non-toxic lightweight, non-abrasive, low-cost and biodegradable properties (Jawaid and Abdul Khalil, 2011).

In Malaysia, realizing the diverse possibilities of commercially exploitable derived products from kenaf, the National Kenaf Research and Development Program has been formed in an effort to develop kenaf as a possible new industrial crop for Malaysia. The government has allocated RM12 mil for research and further development of the kenaf-based industry under the 9th Malaysia Plan (2006–2010) in recognition of kenaf as a commercially viable crop (Abdul Khalil et al., 2010).

##### 1.1.1 Kenaf anatomy and its influence in pulping condition

The kenaf stem is composed of an outer layer (bark) and a core. It is easy to separate the stem into bark and core, either by chemicals and/or by enzymatic retting. The bark constitutes 25 to 40% of the stem dry weight and shows a dense structure. On the other hand, the core is wood-like and makes up the remaining 60 to 75% of the stem. The core exhibits an isotropic and almost amorphous pattern (Aji et al., 2009). However, the bark shows an orientated, highly crystalline fibre pattern. Kenaf bast and core are quite different with respect to their chemical compositions. Research indicates that kenaf core



fibres are higher in holocellulose and lignin, while kenaf bast fibres are higher in cellulose, extractive, and ash content (Abdul Khalil et al., 2010).

### **1.1.2 MDF manufacture**

A recent research trend has been aimed at improving the characteristics of MDF. Most important factors that influence the strength of the MDF as a composite material are the inherent strength of its components; fibres and the bond strength between fibres and binder. Recently, the focus of research was shifted to increase the yield of pulping processes without affecting the quality of the product. Furthermore, attention is being given to increasing the use of mechanical and thermo-mechanical pulp in fibre productions. In the MDF production, thermo-mechanical pulping (TMP) is commonly used to refine raw material into fibres (Li et al., 2011). In the refining step, the raw materials are ground to fibres. During grinding hot steam is used to heat the fibres and thus soften the lignin. This saves electrical energy and yields longer and stronger fibres. The crucial unit in fibreboard production is the refiner, since it controls the basic properties of the fibres. Bad refining cannot be compensated in the subsequent processing steps. Schematically, refiner mechanical pulping (RMP) and thermo-mechanical pulping (TMP) essentially consist of three phases: fibrization of chips/fibre bundles to convert them to intact single or broken fibres, the fibrillation of single or broken fibres to develop bonding ability, and finally, the creation of fines (Xing, Deng, et al., 2006). The refining process can be augmented by pressure and temperature using processes known as the pressurized refiner mechanical pulping and thermo-mechanical pulping. Some researchers have shown that thermal–mechanical refining conditions have obvious effects on final MDF panel properties. However, Labosky (Labosky et al., 1993) reported that an increase in refining pressure did not significantly affect MDF strength or dimensional stability properties. Krug (2001) suggested that increasing the steam pressure resulted in shorter fibre lengths, lower strength, and elastic properties, but improved long-term swelling properties. Roffael et al. found that high pulping temperature resulted in lower thickness swelling (TS) and water absorption (WA) of MDF panels (Roffael et al., 2007).

Groom et al. (2004) studied the effects of varying refining pressure on the properties of refined fibres. They found that steam pressure caused some changes in the chemical composition of refined fibres. The percentages of extractives and glucose increased, while the xylose, galactose, and mannose decreased with increasing refining pressure. Xing (2006) reported that both preheating retention time and steam pressure directly affected MDF panel properties.

## **1.2 Problem statement**

Within the past few years, there has been a dramatic increase in the use of natural fibres such as kenaf for making a new type of environmentally–friendly composites. Recent advances in natural fibre development, genetic engineering, and composite's science offer significant opportunities for improving materials from renewable resources with enhanced support for global sustainability.

Out of the variety of non-woods available (eg. bagasse, hemp, cornstalk, wheat straw, kenaf), kenaf was chosen as the raw material to work with because it is widely grown in tropical and subtropical regions and its high fibre quality. It is regarded as the most promising and suitable raw material for both developing and developed countries. Given the supply of wood, particularly in developing countries, it was decided to study kenaf for the production of MDF manufacturing. An extensive literature review revealed the few efforts have been made in the mechanical pulping of kenaf and MDF production.

Kenaf can be used as the form of whole stem, bast or core. Using the whole stem is a more attractive method as it bears significant practical and economic advantages: it is a simple process and free of the additional separation costs. Some researchers have reported that newsprint paper of excellent quality can be made from whole kenaf stalks and that kenaf pulp can be mixed with conventional softwood pulps to produce a wide range of paper grades ( Li et al., 2011). By properly selecting the right pulp and refining condition kenaf can be a suitable material for fibre production in MDF manufacturing.

The evidence outlined above suggests potential usage of kenaf as whole raw materials for MDF. It is critical to obtain the right refining condition to product good fibre properties that will result in good MDF performance. In this study, whole kenaf stems were refined using TMP refiner under different refining parameters. The fibre properties were analyzed for each refining condition. The fibres then were used in the MDF production and MDF performances were evaluated. The main purpose of the study was to determine the optimum refining conditions for whole stem to produce MDF panels with high-strength properties and good dimensional stability. This research will have an impact on economic development in Malaysia and other southern states by providing agriculturists with alternatives in crop choices and adding value to the kenaf crop.

### **1.3 Objectives**

The main object of this study was to evaluate and optimized the refining/pulping variables for kenaf stem for the production of MDF of acceptance strength. In this thesis, MDF was prepared from kenaf, rubberwood and their mixture. The parameters of preparation and the resulting intermediate products as well as the final MDF, were characterized and compared at each experimental step. The present research concentrated on the conditions of preparation (pulping, fibre processing) and the factors that influenced the main properties of MDF boards such as mechanical and physical properties.

The objectives of this study were to:

1. Determine the effect of temperature and time on the morphological properties of Kenaf, bast and core such as length of fibre, fibre diameter, wall thickness of fibre, Runkel ratio (RR), Aspect ratio (AR) and Compression ratio (CR).
2. Determine the effect of temperature and time on the pH and buffering capacity of kenaf bast and core fibres.
3. Evaluate the effect of thermo mechanical pulping (TMP) refining variables on the basic properties of MDF manufactured from kenaf and rubber wood fibres.
4. Optimize of the processing variables in kenaf-rubber wood MDF panel manufacturing technology.

Several analyses are employed to characterize the physical properties of fibres and the subsequent changes of fibre structure as a result of refining. The analyses include the following aspects:

- 1) Morphological modification: fibre separation modes, changes in fibre length, width, pit structure, lumen area and cell wall thickness, Aspect ratio, Runkel ratio and Compression ratio, etc.
- 2) MDF board characteristics: density profile, bonding ability, tensile strength, modulus of rupture and modulus of elasticity, thickness swelling, water absorption, etc.

The results from these analyses were compared and analyzed against those of the microscopic micrographs to establish possible interrelations between the fibre characteristics and MDF properties. Correlation regressions were established between fibre morphology and board properties.

## REFERENCES

- Abdul Khalil, H. P. S., Yusra, A. F. I., Bhat, A. H., and Jawaid, M. (2010). Cell wall ultrastructure, anatomy, lignin distribution, and chemical composition of Malaysian cultivated kenaf fiber. *Industrial Crops and Products*, 31(1), 113–121.
- Aisyah, H., Paridah, M., and Sahri, M. (2012). Influence of Thermo Mechanical Pulping Production Parameters on Properties of Medium Density Fibreboard Made from Kenaf Bast. *Journal of Applied Science*, 12(6), 575–580.
- Aji, I. S., Sapuan, S. M., Zainudin, E. S., and Abdan, K. (2009). Kenaf fibres as reinforcement for polymeric composites : a review. *International Journal of Mechanical and Material Engineering*, 4(3), 239–248.
- Azizi, A. M., Ibrahim, R., Harun, J., and Paridah, M. T. (2010). A Review of Literatures Related of Using Kenaf for Pulp Production ( Beating , Fractionation , and Recycled Fiber ). *Modern Applied Science*, 4(9), 21–29.
- Azizi Mossello, A., Jalaluddin, H., Resalati, H., Rushdan, I., Shmas, S. R., and Paridah, M. T. (2010). New approach to use of kenaf for paper and paperboard production. *BioResources*, 5(4), 2112–2122.
- Belini, U., Tomazello, F., and Oliveira, J. (2008). Alterations of the anatomical structure of eucalypt wood chips in three refining conditions for MDF panels production. *Proceedings of the 51st International Convention of Society of Wood Science and Technology*, 1–7.
- Bogoeva-Gaceva, G. (2007). Natural fiber eco-composites. *Polymer Composites*, 28 (1), 97-107
- Carley, K.M., Kamneva, N.Y., and Reminga, J. (2004). *Response surfaces methodology CASOS technical report*.
- Choon, K. (1995). Manufacture of Medium Density Fiberboard from Malaysian Fast Growing Tree Species and Bamboo ( Research note ). *Bulletin of the Forestry and Forest Products Research Institute*, 12(369), 177–187.
- Cui, C., Sadeghifar, H., Sen, S., and Argyropoulos, D. (2013). Toward Thermoplastic Lignin Polymers; Part II: Thermal and Polymer Characteristics of kraft Lignin and Derivatives. *BioResources*, 8, 864–886.
- Deng, J., Yang, D., and Geng, X. (2006). “Effect of process parameters on fungal resistance of MDF panels, *Forest Products Journal*, 56(3), 75-81.

- Dutt, D., and Tyagi, C. H. (2011). Comparison of various eucalyptus species for their morphological, chemical, pulp and paper making characteristics. *Indian Journal of Chemical Technology*, 18, 145-51.
- Erine, R. . (2005). *Factors effecting the optimization of lipse-catalyzed palm-based esters synthesis*. University Putra Malaysia.
- Fernando, D., Dino, M., Per, E., and Geoffrey, D. (2011). Fundamental understanding of pulp property development under different thermomechanical pulp refining conditions as observed by a new Simons' staining method and SEM observation of the ultrastructure of fibre surfaces. *Holzforchung*, 65.
- Fowler, P., Hughes, J., and Elias, R. (2006). Biocomposites: technology, environmental credentials and market forces. *Journal of the Science of Food and Agriculture*. 86 (12), 1781–1789.
- G. A. Smook (2002). Handbook for Pulp and Paper Technologists.
- Gao, Z., Wang, X., Wan, H., and Brunette, G. (2011). Binderless panels made with black spruce bark. *BioResources*, 6(4), 3960–3972.
- Garmendia, I., Garci, J., and Garci, M. (2007). Influence of natural fiber type in eco-composites.
- Garrote, G., Dominguez, H., and Parajo, J. (1999). Hydrothermal processing of lignocellulosic materials. *Journal of Wood and Wood Products*, 57, 191–202.
- Gejo, G., Joseph, K., Boudenne, A., and Thomas, S. (2010). Recent advances in green composites. *Key Engineering Materials*, 425, 107–166.
- Gorski, D. ATMP Process : Improved energy efficiency in TMP refining utilizing selective wood disintegration and targeted applications of chemicals. Ph.D Thesis, Mid Sweden University, Sweden, 2011.
- Groom, Leslie; So, Chi-Leung; Elder, Thomas; Pesacreta, Thomas; Rials, T. (2004). Effect of refining pressure and resin viscosity and resin flow, distribution, and penetration of MDF fibers. *the 7th Pacific Rim Bio-Based Composites Symposium*, 1(2), 227–239.
- H'ng, P., Khor, B., Tadashi, N., Aini, A. S. ., and Paridah, M. (2009). Anatomical Structures and Fiber Morphology of New Kenaf Varieties. *Asian Journal of Scientific Research*, 2(3), 161–166.
- Halvarsson, S., Edlund, H., and Norgren, M. (2008). Properties of medium-density fibreboard (MDF) based on wheat straw and melamine modified urea formaldehyde (UMF) resin. *Industrial Crops and Products*, 28(1), 37–46.

- Halvarsson, S., Edlund, H., and Norgren, M. (2010). Wheat straw as raw material for manufacture of medium density fiberboard(MDF). *BioResources*, 5(2), 1215–1231.
- Härkönen E., Kortelainen J., Virtanen, J. and Vuorio, P. (2003). Fibre development in TMP main line. In *International mechanical pulping congress* (pp. 171–178).
- Hassan, E. (2012). Plant fibers reinforced poly lactic acid as a green composite: review. *International Journal of Engineering*, 4(10), 4429–4439.
- Ho, M., Wang, H., Lee, J.-H., Ho, C., Lau, K., Leng, J., and Hui, D. (2012). Critical factors on manufacturing processes of natural fibre composites. *Composites Part B: Engineering*, 43(8), 3549–3562.
- Honkasalo, J. (2004). *Behaviour of different furnish mixtures in mechanical printing papers*. Helsinki University of Technology.
- Hubbe, M. A. (2006). Bonding between cellulosic fibres in the absence and presence of dry-strength agents - A review. *BioResources*, 1(2), 281–318.
- Illikainen, M. (2008). Mechanisms of thermomechanical pulp refining. Ph.D Thesis, University of Oulu, Finland.
- Illikainen, M., Harkonen, E., Ullmar, M., and Niinimaki, J. (2007a). Power consumption distribution in a TMP refiner: comparison of the first and second stages. *Tappi Journal*, (9), 18–23.
- IJ.K. Kim, D.Z. Wo, L.M. Zhou, H.T. Huang, K. T. L. and M. W. (2007). The Bending Strength of Medium Density Fibreboard (MDF) from Different Ratios of Kenaf and Oil Palm Empty Fruit Bunches (EFB) Admixture for Light Weight Construction. *Key Engineering Materials*, 77, 334–335.
- Jackson, M.; et al., (1979). *Factors Limiting the Strength Characteristics of Thermomechanical Pulp*. Proceedings of the International Mechanical Pulping Conference, pp. 37-48.
- Jawaid, M., and Abdul Khalil, H. P. S. (2011). Cellulosic/synthetic fibre reinforced polymer hybrid composites: A review. *Carbohydrate Polymers*, 86(1), 1–18.
- Joshi, S. ., Drzal, L. ., Mohanty, a. ., and Arora, S. (2004). Are natural fiber composites environmentally superior to glass fiber reinforced composites? *Composites Part A: Applied Science and Manufacturing*, 35(3), 371–376.
- Jun, Z., Xiang-Ming, W., Jian-Min, C., and Kai, Z. (2008). Optimization of processing variables in wood-rubber composite panel manufacturing technology. *Bioresource Technology*, 99(7), 2384–91.

- Kalaycioglu, H., and Nemli, G. (2006a). Producing composite particleboard from kenaf (*Hibiscus cannabinus* L.) stalks. *Industrial Crops and Products*, 24(2), 177–180.
- Kalaycioglu, H., and Nemli, G. (2006b). Producing composite particleboard from kenaf (*Hibiscus cannabinus* L.) stalks. *Industrial Crops and Products*, 24(2), 177–180.
- Kargarfard, A., and Latibari, A. J. (2011). The performance of corn and cotton stalks for medium density fiberboard production. *BioResources*, 6(2), 1147-1157.
- Kelley, S. S., EUee, T., and Leslie H. Groom? (2005). Changes in the chemical composition and spectroscopy of loblolly pine medium density fiberboard furnish as a function of age and refining pressure. *Wood and Fibre Science*, 37(1), 14-22.
- Keshani, S., Chuah, L., Nourouzi, M. M., and Jamilah. (2010). Optimization of concentration process on pomelo fruit juice using response surface methodology ( RSM ). *International Food Research Journal*, 17, 733–742.
- Khalil, H. P. S. A., and Suraya, N. L. (2011). Anhydrid modification of cultivated kenaf bast fibers: morphological, spectroscopic, and thermal studies. *BioResources*, 6(2), 1122–1135.
- Kilickap, E. (2010). Analysis and modeling of delamination factor in drilling glass fiber reinforced plastic using response surface methodology. *Journal of Composite Materials*, 45(6), 727–736.
- Krug D, K. E. (2001). Influence of high pulping pressures on permanent swelling-tempered medium density fiberboard. *Holz als Roh- und Werkstoff*, 59, 342–343.
- Krukanont, P., and Prasertsan, S. (2004). Geographical distribution of biomass and potential sites of rubber wood fired power plants in Southern Thailand. *Biomass and Bioenergy*, 26(1), 47–59.
- Kulkarni, A. ., Sanatyanary, K. ., and Rohatgi, P. . (1983). Mechanical properties of banana fibres. *Journal of Materials Science*, 2290–2296.
- Labosky P Jr, Yobp RD, Janowiak JJ, B. P. (1993). Effect of steam pressure refining and resin levels on the properties of UF-bonded red maple MDF. *Forest Product Journal*, 43(11/12), 82–88.
- Laemsak, N., and Okuma, M. (2000). Development of boards made from oil palm frond II: properties of binderless boards from steam-exploded fibers of oil palm frond. *Journal of Wood Science*, 46, 322–326.
- Lenth, R. (2009). Response-Surface Methods in R, using RSM. *Journal of Statistical Software*, 32(7), 1-21.

- Li, B., Li, H., Zha, Q., Bandekar, R., Alsaggaf, A., and Ni, Y. (2011). Review: effects of wood quality and refining process on TMP pulp and paper quality. *BioResources*, 6(3), 3569–3584.
- Li, Y., and Mai, Y. (2006). Interfacial characteristics of sisal fiber and polymeric matrices. *The Journal of Adhesion*, 82(5), 527–554.
- Lorraine C. V. W. (2004). The Structure and Physical Properties of Pulpwood Fibers. Ph.D. thesis. Institute of Paper Science and Technology, Georgia Institute of Technology
- Majeed, K., Jawaid, M., Hassan, a., Abu Bakar, a., Abdul Khalil, H. P. S., Salema, a. a., and Inuwa, I. (2013). Potential materials for food packaging from nanoclay/natural fibres filled hybrid composites. *Materials and Design*, 46, 391–410.
- Maloney, T. M. (1993). *Modern particleboard and dry-process fiberboard manufacturing*. San Francisco: Miller Freeman Publications.
- McDonald, D., Miles, K., and Amiri, R. (2004). The nature of the mechanical pulping process. *Pulp and Paper Canada*, 8, 181–186.
- Mohamad, M. (2010). Natural fibres for the 3 rd millennium. *JEC composite*, (55), 24–28.
- Mohebbi, B., Ilbeighi, F., and Kazemi-Najafi, S. (2008). Influence of hydrothermal modification of fibers on some physical and mechanical properties of medium density fiberboard (MDF). *Holz als Roh- und Werkstoff*, 66(3), 213–218.
- Montgomery, D., Runger, G. ., and Hubbele, N. (2001). *Engineering statistics* (Second Edition). John Wiley and Sons,. New york.
- Mossello, A., Harun, J., and Resalati, H. (2010). New approach to use of kenaf for paper and paperboard production. *BioResources*, 5(4), 2112–2122.
- Mwaikambo, L. Y., Tucker, N., and Clark, A. J. (2007). Mechanical Properties of Hemp-Fibre-Reinforced Euphorbia Composites. *Macromolecular Materials and Engineering*, 292(9), 993–1000.
- Myers, G. (1983). Relationship of fiber preparation and characteristics to performance of medium-density hardboards. *Forest Products Journal*, 33(10), 43–51.
- Navarro, M., Michiardi, a, Castaño, O., and Planell, J. a. (2008). Biomaterials in orthopaedics. *Journal of the Royal Society, the Royal Society*, 5(27), 1137–58.
- Nayeri, M., Paridah, M., Harun, J., Abdullah, L. C., Bakar, E. S., Jawaid, M., and Namvar, F. (2013). Effects of temperature and time on the morphology, pH, and buffering capacity of bast and core kenaf fibres. *BioResources*, 8(2), 1801–1812.



- Nkaa, F., Ogbonnaya, C., and Onyike, N. (2007). Effect of differential irrigation on physical and histochemical properties of kenaf (*Hibiscus cannabinus* L.) grown in the field in Eastern Nigeria. *African Journal Agriculture Research*, 2(6), 252–260.
- Nourbakhsh, A., and Ashori, a. (2009). Preparation and Properties of wood plastic composites made of recycled high-density polyethylene. *Journal of Composite Materials*, 43(8), 877–883.
- Ong, S., Jin, X., and Sinniah, R. (1996). Image analysis of tissue sections. *Computers in Biology and Medicine*, 26(3), 269–279.
- Papadopoulos, A. (2003). The potential for using flax (*Linum usitatissimum* L.) shiv as a lignocellulosic raw material for particleboard. *Industrial Crops and Products*, 17, 143–147.
- Paridah, M., Basher, A., SaifulAzry, S., and Ahmed, Z. (2011). Retting process of some bast plant fibres and its effect on fibre quality: A review. *BioResources*, 6(4), 5260–5281.
- Paridah, M.T. and Khalina, A. Effects of Soda Retting on The Tensile Strength of Kenaf (*Hibiscus cannabinus* L.) Bast Fibres, Project Report Kenaf EPU, 21 pp, 2009.
- Paridah, M.T., Nor Hafizah, A.W., Zaidon, A., Azmi, I., Mohd Nor, M.Y. and Nor Yuziah, M.Y. (2009). Bonding properties and performance of multi-layered kenaf board. *Journal of Tropical Forest Science*. 21(2) : 113–122.
- Pearson, A. J. (1983). Towards a unified theory of mechanical pulping and refining. In *International Mechanical Pulping Conference* : Washington, D.C., June 13-17.
- Pelegri, a. a., and Tekkam, a. (2003). Optimization of Laminates' Fracture Toughness Using Design of Experiments and Response Surface. *Journal of Composite Materials*, 37(7), 579–596.
- Prakash, S., and Palanikumar, K. (2010). Modeling for prediction of surface roughness in drilling MDF panels using response surface methodology. *Journal of Composite Materials*, 45(16), 1639–1646.
- Requejo, A., Rodríguez, A., and Colodette, J. (2012). Optimization of ecf bleaching and refining of kraft pulping from olive tree pruning. *BioResources*, 7(3), 4046–4055.
- Rodríguez, A., Moral, A., Serrano, L., Labidi, J., and Jiménez, L. (2008). Rice straw pulp obtained by using various methods. *Bioresource technology*, 99(8), 2881–6.
- Roffael, E. (2008). On the release of volatile acids from wood-based panels – chemical aspects –. *Holz als Roh- und Werkstoff*, 66(5), 373–378.

- Roffael, E., Dix, B., and Schneider, T. (2007). Influence of pulping process on the emission of formaldehyde and volatile organic acids from pulps and medium density fibreboards (MDF). *Holz als Roh- und Werkstoff*, 145–148.
- Rowell, R. M., Han, J. S., & Rowell, J. S. (2000). Characterization and factors effecting fiber properties. *Natural Polymers and Agrofibers Bases Composites. Embrapa Instrumentacao Agropecuaria, P. O. Box 741, Sao Carlos, 13560-970 SP, Brazil, 2000.*, 115-134.
- Russo, P., Cimino, F., and Acierno, D. (2012). Biodegradable Composites Reinforced with Kenaf Fibers : Thermal , Mechanical , and Morphological Issue. *Advances in Polymer Technology*,, 32(1), 313-332.
- Saad, M. J., and Kamal, I. (2012). Mechanical and Physical Properties of Low Density Kenaf Core Particleboards Bonded with Different Resins. *Journal of Science and Technology*, 4(1), 17–32.
- Sabharwal, B. H. S., Akhtar, M., Blanchette, R. A., Young, R. A., and Technology, B. (1995). Refiner Mechanical and Biomechanical Pulping of Jute, *49*, 537–544.
- Sabharwal, H., Akhtar, M., Blanchette, R., and Young, R. (1994). Biomechanical pulping of kenaf. *Tappi Journal*, 77(12).
- Schneider, T.; Roffael, E.; Dix, B. (2000). The effect of pulping process (TMP and CTMP) and pulping conditions on the physical and technological properties of medium density fibreboard (MDF). *Holz als Roh- und Werkstoff*, 58(1-2), 123–124.
- Shahwahid, M., Othman, H., Rahim, A., and Samad, A. (2009). A Preliminary Study of Strategic Competitiveness of MDF Industry in Peninsular Malaysia by Using SWOT Analysis. *international journal of business and management*, 4(8), 205–214.
- Shi, J., Shi, S. Q., Barnes, H. M., Horstemeyer, M., Wang, J., and Hassan, E.-B. M. (2011). Kenaf Bast Fibers—Part I: Hermetical Alkali Digestion. *International Journal of Polymer Science*, 2011, 1–8.
- Snell, Lr., Groom, L. H., and Rials, T. (2001). Characterizing the Surface Roughness of Thermomechanical Pulp Fibers with Atomic Force Microscopy. *Holzforschung*, 55, 511–520.
- Stark, N. M., and Rowlands, R. E. (2003). Effects of wood fiber characteristics on mechanical properties of wood/polypropylene composites. *Wood and fiber science*, 35(2), 167-174.
- Taghiyari, H. R. (2013). Nano-zycosil in MDF: gas and liquid permeability. *European Journal of Wood and Wood Products*, 71(3), 353–360.

- Taghiyari, H. R., Karimi, A.-N., Parsapajouh, D., and Pourtahmasi, K. (2010). Study on the Longitudinal Gas Permeability of Juvenile Wood and Mature Wood. *Special Topics and Reviews in Porous Media - An International Journal*, 1(1), 31–38.
- Teoh, Y. P., Don, M. M., and Ujang, S. (2011). Assessment of the properties, utilization, and preservation of rubberwood (*Hevea brasiliensis*): a case study in Malaysia. *Journal of Wood Science*, 57(4), 255–266.
- Ticoalu, A. (2010). A review of current development in natural fiber composites for structural and infrastructure applications. *Proceedings of the Southern Region Engineering Conference (SREC 2010)*, 10-12 Nov 2010, Toowoomba, Australia. ..., (November), 1–5.
- Udohitinah, J., and Oluwadare, A. (2011). Pulping properties of kraft pulp of Nigerian-grown kenaf (*Hibiscus cannabinus* L.). *BioResources*, 6(1), 751–761.
- Ververis, C., Georghiou, K., Christodoulakis, N., Santas, P., and Santas, R. (2004). Fiber dimensions, lignin and cellulose content of various plant materials and their suitability for paper production. *Industrial Crops and Products*, 19(3), 245–254.
- Voulgaridis, E., Passialis, C., and Grigoriou, A. (2000). Anatomical characteristics and properties of kenaf stems (*Hibiscus cannabinus*). *IAWA Journal*, 21(4), 435–442.
- Walther, T., Kartal, S. N., Hwang, W. J., Umemura, K., and Kawai, S. (2007). Strength, decay and termite resistance of oriented kenaf fiberboards. *Journal of Wood Science*, 53(6), 481–486.
- Wong, E., Zhang, M., Wang, Q., and Kawai, S. (1999). Formation of the density profile and its effects on the properties of particleboard. *Wood Science and Technology*, 46(3), 202-209
- Woon, W., and Norini, H. (2002). Trends in Malaysian forest policy. *Policy Trend Report*, 12–28.
- Xing, C., Deng, J., and Zhang, S. Y. (2006). Effect of thermo-mechanical refining on properties of MDF made from black spruce bark. *Wood Science and Technology*, 41(4), 329–338.
- Xing, C., Zhang, S. Y., Deng, J., Riedl, B., and Cloutier, A. (2006). Medium-density fiberboard performance as affected by wood fiber acidity, bulk density, and size distribution. *Wood Science and Technology*, 40(8), 637–646.
- Xing, C., Zhang, S. Y., Deng, J., and Wang, S. (2007). Investigation of the effects of bark fiber as core material and its resin content on three-layer MDF performance by response surface methodology. *Wood Science and Technology*, 41(7), 585–595.

- Xu, J., Han, G., Wong, E. D., and Kawai, S. (2003). Development of binderless particleboard from kenaf core using steam-injection pressing. *Journal of Wood Science*, 49(4), 327–332.
- Xu, J., Widyorini, R., Yamauchi, H., and Kawai, S. (2006). Development of binderless fiberboard from kenaf core. *Journal of Wood Science*, 52(3), 236–243.
- Ye, X. P., Julson, J., Kuo, M., Womac, A., and Myers, D. (2007). Properties of medium density fiberboards made from renewable biomass. *Bioresource technology*, 98(5), 1077–84.
- Zhu, W., Zhu, J. Y., Gleisner, R., and Pan, X. J. (2010). On energy consumption for size-reduction and yields from subsequent enzymatic saccharification of pretreated lodgepole pine. *Bioresource technology*, 101(8), 2782–92.
- Zini, E., and Scandola, M. (2011). Green composites: an overview. *Polymer composites*, 32(12), 1905-1915