



UNIVERSITI PUTRA MALAYSIA

***CORROSION BEHAVIOUR OF FRICTION STIR WELDED LAP JOINTS
OF 6061-T6 ALUMINUM ALLOY***

FARHAD GHARAVI

ITMA 2014 9



**CORROSION BEHAVIOUR OF FRICTION STIR WELDED LAP
JOINTS OF 6061-T6 ALUMINUM ALLOY**

By

FARHAD GHARAVI

**Thesis Submitted to the School of Graduate Studies,
Universiti Putra Malaysia, in Fulfilment of Requirement for the Degree of
Doctor of Philosophy**

October 2014

COPYRIGHT

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia



Dedicated to *my father, and my mother* for their encouragement throughout my study career. The completion of this work would not have been possible without their support.



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment
of the requirement for the degree of Doctor of Philosophy

CORROSION BEHAVIOUR OF FRICTION STIR WELDED LAP JOINTS OF 6061-T6 ALUMINUM ALLOY

By

FARHAD GHARAVI

October 2014

Chairman: Khamirul Amin Matori, PhD

Faculty: Institute of Advanced Technology

Friction stir welding (FSW) process is an emerging “green” solid-state method in which is accepted as a favourable joining method for aluminium alloys and other engineering materials. The joining of metal plates is done at below their melting point temperature and based on a thermo-mechanical action used by a non-consumable welding tool onto metal plates. However, the microstructure of aluminium alloy and chemistry as well as dimension and distribution of the intermetallic particles in the matrix of aluminium alloy may be modified owing to heat generated and severe plastic deformation during the welding process. Accordingly, mechanical and corrosion properties of weldments can be changed after welding as opposed to the parent alloy. In this work, lap-welded joints of 6061-T6 aluminium alloy were produced by FSW, and the influence of process parameters on their welds quality of weldments in terms of welding defects, microstructure, hardness distribution, and tensile properties as well as effective plate thickness (EPT) by applying the rotation speed and welding speed in the range of 900-1200 rpm and 20-60 mm/min, respectively, have been investigated using visual inspection, CT-scan, optical microscopy, scanning electron microscopy (SEM) equipped with energy dispersive x-ray (EDX) facilities, and mechanical test such as microhardness test and lap shear tensile test on the lap-welded joints, as the first and second objectives.

The welding results obtained showed that among all the welding conditions, two welding conditions including 1000 rpm–60 mm/min and 900 rpm–40 mm/min were acceptable and desirable weldments with the highest mechanical properties. Thus, corrosion behaviour of acceptable welded lap joints, which was marked as FSLW 1 with 1000 rpm–60 mm/min and FSLW 2 with 900 rpm–40 mm/min welding conditions, has been evaluated as the third objective by potentiodynamic polarization (Tafel and cyclic polarization) and Intergranular corrosion (IGC) tests as well as ex-situ SEM and atomic force microscopy (AFM) examinations.

The IGC test results showed that Intergranular corrosion resistance of heat effect zone (HAZ) was poor compared to weld nugget zone (WNZ) in FSLW 1 and FSLW 2 samples. Tafel polarization test revealed that the corrosion resistance of parent alloy (PA) was higher than the weld regions in FSLW 1 and FSLW 2 samples. The PA, WNZ, and HAZ represented similar corrosion potential values after heat treatment (T6). Cyclic polarization test results for both FSLW 1 and FSLW 2 samples were good agreement with the previous results from the Tafel polarization test. Corrosion behaviour of different positions (top and bottom) of weld nugget zone revealed that the corrosion resistance of the top nugget zone was higher than that of bottom and parent alloy in both FSLW 1 and FSLW 2 samples. Finally, from these results, it is found that the welding process has a major effect on corrosion resistance of weld regions, which is attributed to the breaking down and dissolution of intermetallic particles.

Abstrak tesis yang dikemukakan kepada Senat of Universiti Putra Malaysia sebagai memenuhi keperluan untuk Ijazah Doktor Falsafah

TINGKAH LAKU KAKISAN BAGI KIMPALAN GESERAN KACAU PANGKUAN SENDI BAGI 6061-T6 ALOI ALUMINUM

Oleh

FARHAD GHARAVI

October 2014

Pengerusi: Khamirul Amin Matori, PhD

Fakulti: Institut Teknologi Maju

Kimpalan kacau geseran (FSW) adalah suatu proses baru yang ‘hijau’ bagi keadaan pepejal yang sedang diterokai dan diterima sebagai satu kaedah yang baik untuk menyambung aloi aluminium dan bahan-bahan kejuruteraan yang lain. Penyambungan plat-plat logam dilakukan di bawah suhu takat lebur dan berdasarkan kepada tindakan termo-mekanikal yang digunakan oleh alat kimpalan tidak haus ke atas plat-plat logam. Sendi pangkuan aloi aluminium 6061-T6 adalah dihasilkan oleh FSW, dan proses parameter yang mempengaruhi kualiti kimpalan ke atas kimpalan telah disiasat dari segi kecacatan kimpalan, mikrostruktur, taburan kekerasan, dan ketegangan serta tebal plat yang berkesan (EPT) dengan menggunakan kelajuan putaran dan kelajuan kimpalan masing-masing dalam lingkungan 900-1200 rpm dan 20-60 mm/min. Keputusan kimpalan yang diperolehi menunjukkan antara semua syarat kimpalan, dua syarat kimpalan termasuk yang menggunakan kelajuan 1000 rpm-60 mm/min dan 900 rpm-40 mm/min adalah boleh diterima dan mempunyai sifat-sifat mekanikal tertinggi. Oleh itu, syarat kakisan yang diterima untuk kimpalan sendi pangkuan yang ditandai sebagai FSLW 1 dengan 1000 rpm-60 mm/min dan FSLW 2 dengan 900 rpm-40 mm/min, yang telah dinilai sebagai objektif kedua oleh polarisasi “potentiodynamic” (Tafel dan polarisasi kitaran) dan kakisan antara butiran (IGC) serta ex-situ FE-SEM. Keputusan ujian menunjukkan bahawa ketahanan kakisan antara butiran (IGC) dengan kesan haba zon (HAZ) adalah lebih rendah berbanding dengan zon nugget kimpal (WNZ) dalam sampel FSLW 1 dan FSLW 2.

Ujian polarisasi Tafel mendedahkan bahawa rintangan kakisan aloi asal (PA) adalah lebih tinggi daripada kawasan kimpalan dalam FSLW 1 dan FSLW 2. PA, WNZ, dan HAZ diwakili oleh nilai potensi hakisan sama selepas rawatan haba (T6). Keputusan ujian polarisasi kitaran untuk kedua-dua FSLW 1 dan FSLW 2 adalah menghampiri dengan keputusan sebelumnya dari ujian polarisasi Tafel. Tingkah laku kakisan untuk kedudukan yang berbeza (atas dan bawah) dari zon kimpalan nugget mendedahkan bahawa rintangan kakisan zon nugget atas adalah lebih tinggi daripada

bahagian bawah dan aloi bagi kedua-dua aloi FSLW 1 dan FSLW 2. Akhirnya, dari keputusan ini, didapati bahawa proses kimpalan mempunyai kesan yang besar ke atas rintangan kakisan kawasan kimpalan, yang boleh dikaitkan dengan pemecahan dan pembubaran zarah antara logam.



AKNOWLEDGMENTS

I would like to express my gratitude and sincere respect to my supervisor ***Dr. Khamirul Amin Matori*** for his guidance and support throughout my research.

I would also like to thank my co-supervisors ***Professor Robiah Yunus, and Dr. Norinsan Kamil Othman*** for providing useful suggestions for the completion of this research.

I would like to thank ***Professor Abdul Razak Daud*** for his valuable support.

This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Khamirul Amin Matori, PhD

Senior Lecturer
Institute of Advanced Technology
Universiti Putra Malaysia
(Chairman)

Robiah Yunus, PhD

Professor
Institute of Advanced Technology
Universiti Putra Malaysia
(Member)

Norinsan Kamil Othman, PhD

Associate Professor
School of Applied Physics, Faculty of Science and Technology
Universiti Kebangsaan Malaysia,
(Member)

BUJANG KIM HUAT, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:

Declaration by graduate student

I hereby confirm that:

- this thesis is my original work;
- quotations, illustrations and citations have been duly referenced;
- this thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) Rules 2012;
- written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- There is no plagiarism or data falsification/fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: _____

Date: _____

Name and Matric No.: Farhad Gharavi, GS 30901

Declaration by Members of Supervisory Committee

This is to confirm that:

- the research conducted and the writing of this thesis was under our supervision;
- Supervision responsibilities as stated in the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature: _____

Name of chairman of
Supervisory Committee

Khamirul Amin Matori, PhD

Signature: _____

Name of Members of
Supervisory Committee

Robiah Yunus, Professor

Signature: _____

Name of Members of
Supervisory Committee

Norinsan Kamil Othman, PhD

TABLE OF CONTENTS

	Page
ABSTRACT	I
ABSTRAK	III
ACKNOWLEDGEMENT	V
APPROVAL	VI
DECLARATION	VIII
LIST OF TABLES	XIV
LIST OF FIGURES	XVI
LIST OF ABBREVIATIONS	XXIV
 CHAPTER	
1 INTRODUCTION	1
1.1 Problem Statement	2
1.2 Research Objectives	3
 2 LITERATURE REVIEW	4
2.1 Aluminium and Its Alloys: An Overview	4
2.1.1 Introduction	4
2.1.2 Alloy Designation System	4
2.1.3 Temper Designation System	5
2.1.4 Structure-Property Relationships	6
2.1.5 Physical Metallurgy of Aluminium Alloys	7
2.1.6 Effect of Alloy Elements	9
2.1.7 Weldability of aluminium and its alloys	10
2.1.8 AA6XXX Series Aluminium Alloys	10
2.1.9 Properties of AA6XXX Alloys	14
2.1.10 Application of AA6XXX Alloys	15
2.1.11 Corrosion of AA6XXX aluminium alloy	17
2.2 Friction Stir Welding (FSW)	27
2.2.1 Introduction	27
2.2.2 Background	27
2.2.3 Principle of Operation	28
2.2.4 Types of FSW Processes	30
2.2.5 FSW Welding Configuration	32
2.2.6 Generation and Flow of Heat	34
2.2.7 Weld Zones Geometry in FSW	34
2.2.8 Process Zones in FSW	35
2.2.9 Material Flow in FSW Process	36
2.2.10 FSW Process Parameters	41
2.2.11 FSW Process Window	50

2.2.12	Flaws and Failures in FSW	51
2.2.13	FSW Advantages and Disadvantages	53
2.2.14	Application of FSW in the Industry	53
2.3	Corrosion of Aluminium Alloy	56
2.3.1	Introduction	56
2.3.2	Aluminium oxide film	56
2.3.3	Corrosion in aqueous environments	57
2.3.4	Influence of Alloying Elements on Aluminium Corrosion	59
2.3.5	Pitting Corrosion	62
2.3.6	Structural Corrosion	68
2.3.7	Crevice corrosion	73
2.3.8	Galvanic corrosion	74
2.3.9	Corrosion of Aluminum Alloy Friction Stir Welds: An Overview	74
2.4	Review for Lap Joint Publication	81
2.4.1	Published Results for FSL Welded Al 6061	81
2.4.2	Published Results for Corrosion in FSL Welded Al 6061	82
3	METHODOLOGY	87
3.1	Material Selection	88
3.2	Welding Preparations	88
3.2.1	Plate Preparation	88
3.2.2	FSW Machine and Clamping System	89
3.2.3	Welding Tool Preparation	91
3.2.4	Selection of Welding Conditions	92
3.3	Macro- Structure Evaluation of FSLW weldments	93
3.3.1	Sample Preparation	93
3.4	Micro- Structure Evaluation of FSLW weldments	93
3.4.1	Sample Preparation	93
3.4.2	Grain Size Measurements	94
3.5	Investigation of Welding Defects	94
3.6	Mechanical Properties Evaluation	94
3.6.1	Micro-Hardness Testing	94
3.6.2	Lap-Shear Tensile Testing	95
3.6.3	Fracture Behavior Evaluation of Weldments	97
3.7	Heat Treatment after Welding	97
3.8	Corrosion Experiments	98
3.8.1	Immersion Test	98
3.8.2	Electrochemical Measurements	99
3.9	Characterization Techniques	100
4	CHARACTERIZATION OF THE AA6061-T6 FRICTION STIR WELDED JOINTS	101
4.1	Weld appearance	101
4.2	CT-Scan Inspection (X-Ray Image System)	103
4.3	Macro-Structure of FSL Welds	104

4.3.1	The Effects of Welding Speed (v) and Rotation Speed (ω) on the Shape and Size of Weld Region	105
4.3.2	Relation between welding parameters with Hooking and Thinning Properties	108
4.3.3	Influence of Effective Plate Thickness (EPT) on Joint Strength	111
4.4	Micro-Structure of FSL Welds	113
4.4.1	Microstructure Observations	113
4.4.2	The Effect of Welding Speed and Rotation Speed on Average Grain Size of Weld Regions	120
4.5	Mechanical Characterization	123
4.5.1	Evaluation of Testing Setup	123
4.5.2	Welding parameter impacts on Tensile Shear Strength	124
4.5.3	The Effect of v and ω on Joint Efficiency	127
4.6	Micro-Hardness Test of FSL Welds	128
4.6.1	Investigation of Hardness Distribution in the Weld Region	128
4.6.2	The Effect of v and ω on Variation of Micro-Hardness of WNZ and HAZ	131
4.7	Fracture Behavior	132
4.7.1	Influence of welding parameters on Mode and Mechanism of Fracture	132
4.8	Summary	136
5	CORROSION CHARACTERIZATION OF LAP WELDS	138
5.1	Microstructural Analysis before Corrosion	138
5.2	Intergranular Corrosion (IGC) Investigation in Parent Alloy	143
5.2.1	Corrosion Observations after 24 h Immersion	143
5.2.2	Corrosion Observations after 48 h Immersion	144
5.3	Intergranular Corrosion (IGC) investigation in FSLW 1 joint	146
5.3.1	Corrosion Observations after 24 h Immersion	146
5.3.2	Corrosion Observations after 48 h Immersion	148
5.4	Intergranular Corrosion (IGC) investigation in FSLW 2 joint	152
5.4.1	Corrosion Observations after 24 h Immersion	152
5.4.2	Corrosion Observations after 48 h Immersion	153
5.5	Investigation of Tafel Polarization Method	156
5.5.1	Tafel Polarization Curves	156
5.5.2	Corrosion observations	160
5.6	The Effect of Post Weld Heat Treatment on Corrosion Behaviour of FSLW 1 and FSLW 2 joints	165
5.6.1	Tafel Polarization Curves	165
5.7	Specific Investigation on Corrosion Behaviour of Weld Nugget Zones (WNZ) in FSLW 1 and FSLW 2 joints	168
5.7.1	Micrographs of Grains and Distribution of Intermetallic Particles	168
5.7.2	Tafel Polarization Curves	172
5.8.3	Corrosion observation	175
5.8	Investigation of Cyclic Polarization (Pitting Scan Technique)	179
5.8.1	Cyclic Polarization Plots	179

5.8.2	Corrosion observations	182
5.9	Summary	194
6	CONCLUSIONS	197
	REFERENCES	199
	BIODATA OF STUDENT	227
	LIST OF PUBLICATIONS	228



LIST OF TABLES

Table	Page
2.1 Aluminium Alloy Designation System [6]	5
2.2 Property-Microstructure Relationships in Aluminium Alloys [7]	6
2.3 Typical composition for commercial aluminium alloys (wt%) [30]	11
2.4 Overview over some selected temper designations [41]	12
2.5 Properties of AA6XXX alloys in annealed condition [48]	15
2.6 Properties of AA6XXX alloys in T6 condition [48]	15
2.7 Use of AA6XXX Aluminium Alloys [52]	16
2.8 Dissolution potential of solid solution and some common intermetallic phases observed in aluminium alloys [75]	26
2.9 Corrosion potentials for intermetallic compounds common in aluminium alloys [192]	62
2.10 Schematic general relationship between microstructure, significant localized corrosion forms and main corrosion investigation techniques for high-strength aluminium alloys friction stir welds [238]	78
3.1 Nominal composition of parent alloy used in the welding test	88
3.2 Mechanical properties of the 6061-T6 aluminium alloy	88
3.3 Summary of dimensions of the tools used in FSLW experiments	88
3.4 Process Parameters for fabricating FSLW joints at constant rotation speed	92
3.5 Process Parameters for fabricating FSLW joints at constant welding speed	93
4.1 α and β deviations for different welds and rotational speeds [328]	108
4.2 Average grain size of the WNZ and HAZ	120
4.3 Average tensile shear strength of friction stir welded Al 6061-T6 with different welding speed	125
4.4 Average tensile shear strength of friction stir welded Al 6061-T6 with different rotation speed	126
4.5 Effect of welding speed on fracture properties welded lap joints	133
4.6 Effect of rotation speed on fracture properties welded lap joints	134
5.1 EDS analysis (wt%) of different intermetallic precipitates highlighted in weld regions and parent alloy	143
5.2 Effect of Welding Conditions on Variations of Corrosion Potential and Current Density	159

5.3	Effect of heat treatment on variations of corrosion potential and current density	166
5.4	EDS analysis (wt%) of different intermetallic precipitates highlighted in weld regions and parent alloy shown in Figures 5.23 and 5.24	172
5.5	Effect of Welding Conditions on Variations of Corrosion Potential and Current Density	174
5.6	Average characteristic potential (mV vs. SCE) of welded lap joint pitting scans	179
5.7	Average characteristic potential (mV vs. SCE) of welded lap joint from pitting scans	179



LIST OF FIGURES

Figure		Page
2.1	Equilibrium Binary Solid Solubility As A Function of Temperature For Alloying Elements Most Frequently Added to Aluminium [8]	7
2.2	Phase Diagram of A Hypothetical Alloy System Showing the B Solvus And GP Zone Solvus. For Composition (A). ΔT_1 is the Temperature Range for Solution Heat Treatment, and ΔT_2 is the Temperature Range for Precipitation Heat Treatment [7]	8
2.3	Contributions from dissolved alloying elements in solid solution (A) and particles from precipitation hardening (B, C)[44]	13
2.4	Effect of artificial ageing and naturally ageing on the strength evolution in AlMgSi alloys. Naturally ageing only allows GP-zones to form [47]	14
2.5	Suggested IGC mechanism in Cu containing AlMgSi alloys. The Q-phase is a Cu-rich cathodic precipitate with the chemical composition being $Al_4Mg_8Si_7Cu_2$ [54,55]	17
2.6	Figure illustrates the corrosion rate as a function of Mn content in an AlMgSi alloy with various Fe levels [61,66]	19
2.7	Figure illustrates the mechanisms responsible for the different corrosion modes observed during ageing of an AlMgSi alloy [54]	20
2.8	Isothermal time transformation (ITT) diagram illustrating various corrosion modes as a function of temperature and holding time (i.e. ageing time) in AlMgSi alloys [57]	21
2.9	Effect of ageing time on the susceptibility to IGC in an air cooled AlMgSi alloy containing 0.60, 0.55 and 0.17 wt% of Si, Mg and Cu respectively [58]	21
2.10	Effect of ageing time on the susceptibility to IGC in a water quenched AlMgSi alloy containing 0.60, 0.55 and 0.17 wt% of Si, Mg and Cu respectively [58]	22
2.11	Effect of cooling rate after extrusion on the susceptibility towards IGC in an AlMgSi alloy containing 0.60, 0.55 and 0.17 wt% of Si, Mg and Cu respectively. A) Air cooled and B) Water quenched [58]	22
2.12	Pitting corrosion around an Al_3Fe particle and an oxide particle in an aluminium alloy [76]	23
2.13	Effect of ageing on pitting potential in an Al-Cu alloy containing 3.33wt% Cu. [77]	24
2.14	Maximum pit depth as a function of exposure time for some selected alloys [79]	26
2.15	Representation of the main parameters and nomenclature of FSW joints [86]	29

2.16	The FSSW process. (a) Tool rotation begins, (b) rotating tool plunges into the workpiece and dwells, and (c) the rotating tool retracts [95]	30
2.17	Various weld configurations possible with Friction Stir Welding. a) Butt Weld, b) Corner Weld, c) Double T-Joint Weld, d) Lap Weld, e) Multiple plate Lap Weld, f) T-joint weld, and g) Fillet Weld [4]	33
2.18	a) Right-handed lap weld configuration and b) Left-handed lap weld configuration [112]	33
2.19	Weld zone geometry illustrating the parent material (A), the Heat Affected Zone (B), the Thermo-Mechanically Affected Zone (C), and the Nugget (D). The asymmetry of the weld zone is shown where the left side of the picture corresponds to the advancing side of a weld [4]	35
2.20	Metallurgical processing zone developed during friction stir welding [118]	36
2.21	Metal flow zone developed during friction stir joining [120]	36
2.22	Void formation at the flow zone interfaces [120]	37
2.23	(a) SEM image of pin-workpiece couple obtained by the pin stop action showing the formation of sheared layer around pin driven downward, (b) cross section of weld, (c) higher magnification image of region P1 in Figure 2.24b and (d) schematic illustration of material flow which results in formation of hooking during FSLW [122]	38
2.24	Microstructures of Al 5083 FSL weld made using $\omega=584$ rpm and $v=120$ mm/min: (a) macrograph (white line indicate the fracture path during tensile shear testing), (b) cold lap defect on retreating side and (c) hook on advancing side [112]	39
2.25	SEM image showing hooking, (b) EDS scan line for oxygen, and (c) EDS scan line for aluminium [112]	39
2.26	Macrographs of Al 6061 to Al 5052 FSL welds made using $v=267$ mm/min and $\omega=$ (a) 1250 rpm, (b) 2500 rpm, and (c) 3600 rpm; and $\omega=1600$ rpm and $v=$ (d) 127 mm/min, (e) 267 mm/min, and (f) 507 mm/min [133]	40
2.27	The shoulder contact leaves in its wake a sequence of almost semi-circular ripples that points towards the start position in the weld track [86]	43
2.28	Sample of a macrograph for hot (left) and cold (right) FSW conditions from a transversal section of a FSW butt joint of AA6056 [144]	43
2.29	Cylindrical tool design [148,149]	47
2.30	Basic variants on the Whorl type probes [148,149]	47
2.31	Triflute tool with frustum shaped probe with three flutes [148-150]	47
2.32	Flared Triflute design [148-150]	48

2.33	A-Skew tool (a) side view, (b) front view, and (c) swept region encompassed by skew action [148-150]	48
2.34	Process window shows power as f (friction tool force [N], tool shoulder velocity [m/s]) vs weld speed, v , [mm/s] and thickness, t , [mm] for chemical composition/hot strength [154]	51
2.35	Cold lap shown schematically in FSW Lap weld [156]	52
2.36	Hooking/Thinning shown schematically in FSW Lap weld [156]	52
2.37	Passivation of aluminium alloy [160]	56
2.38	Pourbaix diagram for Al in the presence of water at 25 °C [171]	58
2.39	Effect of alloy elements on the corrosion potential of aluminium alloys [165,178]	60
2.40	A schematic diagram illustrating the mechanism of pitting corrosion on an AlMgSi alloy [199]	64
2.41	Experimental pH-potential diagram for Al in sea water [206]	66
2.42	Pitting potential scan diagram for Al {111} in 0.5 mol L ⁻¹ NaCl after Yasuda et al. [207]	67
2.43	Two Different Intergranular Corrosion Mechanisms [213]	69
2.44	SEM image of IGC attack on an AA6005 aluminium alloy exposed in acidic NaCl solution [213]	69
2.45	Short transverse cross section showing IGC attacks on an AA6005 aluminium alloy exposed in acidic NaCl solution [213]	69
2.46	Exfoliation corrosion in a 7020-T4 welded assembly [160]	72
2.47	Propagation mechanisms for SCC of aluminium alloys [229]	73
2.48	Coarse grain boundary, intergranular precipitates and wide precipitate-free zones in the heat-affected zone of a 7075-T7 friction stir weld [245]	75
2.49	(A) Initial stage of intergranular corrosion on a heat-affected zone with the attack of the precipitate-free zones. (B) Complete attack and dissolution of the precipitate-free zones and the grain boundary phases in the plunge area of a 7075-T651 FSW [246]	75
2.50	Localized corrosion along a longitudinal section of a round tensile specimen immersed in a 3.5 wt% NaCl solution (ASTM G129) [246]	76
2.51	Onion rings microstructure present after the corrosion immersion tests (ASTM G110-92) for a 7075-O friction stir weld [238]	77
3.1	A CNC vertical milling machine used for FSLW experiments	89
3.2	Programming the CNC machine to performance of the FSW	89
3.3	Schematic of joint configuration utilized in this research	90
3.4	The real shape of fixture used in this work	90
3.5	Designed tool for Friction Stir Lap Welding	92
3.6	The Location of Hardness Points on the Cross Section of Specimens	94
3.7	Micro-Hardness Testing Machine	95
3.8	Overlap shear test sample (all dimensions are in mm) [326]	96

3.9	Testing configurations used to evaluate lap weld quality in this study[126,128,129]	96
3.10	An Instron universal Testing machine used for lap-shear tensile test	97
3.11	T6- heat treatment cycle performed on the FSLW samples[263]	98
3.12	Performing of the IGC test and their equipments	98
3.13	Performing of the electrochemical tests and their equipments	99
4.1	Surface appearance of welded lap joints after welding at (a) 900 rpm-40 mm/min (b) 1000 rpm-40 mm/min (c) 1200 rpm-40 mm/min (d) 1000 rpm-20 mm/min (e) 1000 rpm-50 mm/min (f) 1000 rpm -60 mm/min	102
4.2	X-Ray image for selected sample (a) top, (b) side, (c) view	103
4.3	Cross section of macrograph of selected welded lap joint with different weld region	104
4.4	Macro-structures of weldments at constant welding speed 40 mm/min (a) 900 rpm (b) 1000 rpm (c) 1200 rpm	105
4.5	Macro-structures of weldments at Constant rotation speed (ω) of 1000 rpm (a) 20 mm/min (b) 40 mm/min (c) 50 mm/min (d) 60 mm/min	106
4.6	Schematic of FSLW (a) and affected area (b) by shoulder and pin used in this study [328]	107
4.7	Cross-section macrostructure of lap joint section AA6061-T6 Al alloy at different rotational speeds: (a) 1200 rpm/min; (b) 900 rpm/min [328]	108
4.8	Cross-section macro-structures of welded lap joints at Constant rotation speed (ω) of 1000 rpm (a) 20 mm/min (b) 40 mm/min (c) 50 mm/min (d) 60 mm/min	109
4.9	Cross-section macro-structures of welded lap joints at constant welding speed 40 mm/min (a) 900 rpm (b) 1000 rpm (c) 1200 rpm	109
4.10	Changing in hooking shape and direction, (a) 40 mm/min (hooking tip is moving down), (b) 50 m/min (tip is almost parallel to interface) (c) 60 m/min (tip is folding up) (all images are in 150X) [329]	111
4.11	Effect of welding speeds on effective plate thickness (EPT)	112
4.12	Effect of rotation speeds on effective plate thickness (EPT)	112
4.13	Optical image of parent alloy at the longitudinal plane	114
4.14	Optical images of the HAZ microstructure at different welding conditions	115
4.15	Optical images of weld regions microstructure at different welding conditions (a,b) 900 rpm-40 m/min (c,d) 1000 rpm-40 mm/min (e,f) 1200 rpm- 40 mm/min	116
4.16	Optical images of weld regions microstructure at different welding conditions (a,b) 1000 rpm-20 m/min (c,d) 1000 rpm-40 mm/min (e,f) 1000 rpm- 50 mm/min (g,h) 1000 rpm-60 mm/min	117

4.17	Optical images of weld nugget zone's microstructure at different welding conditions (a,b) 900 rpm-40 m/min (c,d) 1000 rpm-40 mm/min (e,f) 1200 rpm- 40 mm/min	118
4.18	Optical images of weld nugget zone's microstructure at different welding conditions (a,b) 1000 rpm-20 m/min (c,d) 1000 rpm-40 mm/min (e,f) 1000 rpm- 50 mm/min (g,h) 1000 rpm-60 mm/min	119
4.19	Effect of welding speeds at constant rotation speed on the average grain size of weld nugget zone (WNZ), and heat affected zone (HAZ)	120
4.20	Effect of rotation speeds at constant welding speed on the average grain size of weld nugget zone (WNZ), and heat affected zone (HAZ)	121
4.21	Variation of average grain size in upper and lower weld nugget zone (WNZ) with welding speed at constant rotation speed	122
4.22	Variation of average grain size in upper and lower weld nugget zone (WNZ) with rotation speed at constant welding speed	122
4.23	Method part of tensile shear testing setup on lap shear strength	123
4.24	Effect of tensile shear testing setup on the results of lap shear strength at constant rotation speed	124
4.25	Effect of tensile shear testing setup on results of lap shear strength at constant welding speed	124
4.26	Effect of welding speed on variation of Ultimate shear strength and heat index at constant rotation speed	125
4.27	Effect of rotation speed on variation of Ultimate shear strength and heat index at constant welding speed	126
4.28	Effect of welding speeds on joint efficiency	127
4.29	Influence of rotation speeds on joint efficiency	127
4.30	Hardness distributions along the mid-thickness of upper and lower plate at constant welding speed (40 mm/min) and various rotation speeds (a) 900 rpm (b) 1000 rpm (c) 1200 rpm	129
4.31	Effect of welding speed (a) 20 mm/min (b) 40 mm/min (c) 50 mm/min (d) 60 mm/min on hardness distributions along the mid-thickness of upper and bottom plate at a constant rotation speed (1000 rpm)	130
4.32	Variation of micro hardness in the WNZ with rotation speeds	131
4.33	Variation of micro hardness in the WNZ with welding speeds	131
4.34	Effect of welding speeds on average micro hardness of weld nugget zone (WNZ) and heat affected zone (HAZ)	132
4.35	Effect of rotation speeds on average micro hardness of weld nugget zone (WNZ) and heat affected zone (HAZ)	132
4.36	The fracture surface of the overlap shear test samples by mode FM1	133

4.37	The fracture surface of the overlap shear test samples by mode FM2	134
4.38	EDX Spectrum and quantitative results of point A	135
5.1	SEM micrographs of intermetallic precipitates in parent alloy shows the intermetallic particles including Fe-rich as bright points (A) and Si-rich as dark points (B)	139
5.2	SEM micrographs of precipitates on grain boundaries in parent alloy	140
5.3	SEM micrographs of WNZ region in (a) FSLW 1 joint (b) FSLW 2 joint, Fe-rich intermetallic as bright points (I, G) and Si-rich intermetallic as dark points (J, H)	141
5.4	SEM micrographs of HAZ region in (a) FSLW 1 joint (b) FSLW 2 joint, Fe-rich intermetallic as bright points (E, C) and Si-rich intermetallic as dark points (F, D)	142
5.5	SEM examination of parent alloy after 24 h of immersion (a) low, and (b) high magnification	144
5.6	(a) SEM examination of parent alloy after 48 h of immersion, (b) EDX of particle	145
5.7	SEM Microscopic images of corrosion attacks in the weld regions	147
5.8	SEM examination of corrosion attacks in the weld regions after 48 h of immersion, (a) low magnification (b) HAZ region (d) EDX of particle	149
5.9	SEM examination of corrosion attacks in the weld regions after 48 h of immersion, (a) low magnification (b) corrosion chimney (c) Nugget region (d) EDX of particle	150
5.10	(a) The created chimney in the WNZ, and (b) cross section of corrosion Chimney [313], (c) EDX of corrosion products	151
5.11	SEM images of corrosion attacks in (a) the WNZ, and (b) EDX of particle	152
5.12	SEM images of corrosion attacks in the HAZ (a) low magnification, and (b, c) high magnification	153
5.13	SEM images of corrosion attacks in the HAZ region (a) low magnification, and (b) high magnification	154
5.14	SEM morphology of in the WNZ region (a) low magnification, and (b) high magnification (c) corrosion chimney (d) EDX of particle	155
5.15	Tafel polarization diagrams of parent alloy, weld nugget zone (WNZ), and heat affected zone (HAZ) in FSLW1 joint	158
5.16	Tafel polarization diagrams of parent alloy, weld nugget zone (WNZ), and heat affected zone (HAZ) in FSLW2 joint	159
5.17	SEM examination of parent alloy surface after the corrosion test	161
5.18	SEM micrograph of small grain boundary phases in parent alloy	162
5.19	SEM examination of (a) WNZ (b) HAZ surfaces of FSLW 1 joint	163

5.20	SEM examination of (a) WNZ (b) HAZ surfaces of FSLW 2 joint after corrosion	164
5.21	The effect of T6 heat treatment on Tafel polarization diagrams of parent alloy, weld nugget zone, and heat affected zone in FSLW 1 joint	166
5.22	The effect of T6 heat treatment on Tafel polarization diagrams of parent alloy, weld nugget zone, and heat affected zone in FSLW 2 joint	167
5.23	Cross section of the macrograph (a), SEM micrograph of grains and distribution of intermetallic particles in FSLW 1 joint (b) top (c) bottom	170
5.24	SEM micrographs of grains and distribution of intermetallic particles in FSLW 2 joint (a) top (b) bottom	171
5.25	Tafel polarization curves obtained with different positions of WNZ along thickness of plates at parent alloy and FSLW 1 joint	173
5.26	Tafel polarization curves obtained with different positions of WNZ along thickness of plates at parent alloy and FSLW 2 joint	174
5.27	Corrosion morphology of parent alloy	175
5.28	Corrosion morphology of the different position of WNZ: (b) top (c) bottom of FSLW 1 joint samples	176
5.29	Corrosion morphology of the different position of WNZ: (b) top (c) bottom of FSLW 1 joint samples	177
5.30	Cyclic polarization diagrams of parent alloy, weld nugget zone (WNZ) and heat affected zone (HAZ) in FSLW 1 joint	180
5.31	Cyclic polarization diagrams of parent alloy, weld nugget zone (WNZ), and heat affected zone (HAZ) in FSLW 2 joint	181
5.32	SEM image of WNZ surface of FSLW1 joint, after pitting scans	184
5.33	Three-dimensional AFM images of the WNZ surface in FSLW 1 joint, after pitting scans	185
5.34	SEM image of HAZ surface of FSLW 1 joint, after pitting scans	186
5.35	Three-dimensional AFM images of the HAZ surface in FSLW 1 joint, after pitting scans	187
5.36	SEM examination of WNZ surfaces of FSLW 2 joint, after pitting scans (a) Secondary electron (b) Back Scatter electron images	188
5.37	Three-dimensional AFM images of the WNZ surface in FSLW 2 joint, after pitting scans	189
5.38	SEM examination of HAZ surfaces of FSLW 2 joint, after pitting scans (a) Secondary electron (b) Back Scatter electron images	190
5.39	Three-dimensional AFM images of the HAZ surface in FSLW 2 joint, after pitting scans	191

5.40	SEM examination of parent alloy (PA) surface after Pitting scans (a) Secondary electron (b) Back Scatter electron images	192
5.41	Three-dimensional AFM images of the parent alloy's surface after pitting scans	193



LIST OF ABBREVIATIONS

AA6061	Aluminium Alloy
FSW	Friction stir welding
OM	Optical Microscope
SEM	Scanning Electron Microscope
AFM	Atomic Force Microscopy
EDX	Electron Depressive X-ray
PA	Parent Alloy
HAZ	Heat Affected Zone
TMAZ	Thermo Mechanical Affected Zone
WNZ	Weld Nugget Zone
AS	Advancing side of WNZ
RS	Retreating side of WNZ
SZ	Stir zone
HI	Heat Index
$\omega(\Omega)$	Rotation Speed (rpm)
v	Welding Speed (mm/min)
TWI	The Welding Institute
OCP	Open circuit potential
E_{corr}	Corrosion potential
I_{corr}	Corrosion current (A/cm^2)
I_{pass}	Passivation current density
E_{pass}	Passive potential
E_{pit}	Pitting Potential
E_{prot}	Protection Potential
E_{rp}	Repassivation Potential
E_{ptp}	Pitting Protection Potential
IGC	Intergranular Corrosion
NAMLT	Nitric acid metal loss test
SCC	Stress Corrosion Cracking
wt%	Weight percent
g/l	Gram per litter
mm	Millimetre

μm	Micrometre
A/cm^2	Amper per centimetre square
SCE	Saturated calomel electrode
h	Hour
HV	Vickers Hardness
Kg	Kilogram
kV	Kilo volt
LSM	Laser surface melting
mV	Millivolt



CHAPTER 1

INTRODUCTION

Aluminum and aluminum alloys are widely used in various industries including structural, transportation, shipbuilding, and aerospace. The main reasons for using this material are the result of its favorable mechanical properties, acceptable corrosion resistance, light weight, appropriate weldability, and increased toughness. Recently, aluminum alloys have become very attractive materials for scientists and engineers, and they have been studied extensively due to their beneficial properties [1]. AlMgSi alloys, often referred to as the 6XXX series, are wrought; The strength-to-weight ratio offered by AA6XXX alloys and their enhanced mechanical properties have become crucial criteria for their use in the transport, aerospace, and automotive industry, as well as for architectural and marine applications. The main application is as extruded products and approximately half of all extruded profiles produced worldwide are AlMgSi alloys [2]. AA 6061 (Al-Mg-Si alloy), examined in this study, is a precipitation hardening aluminium alloy, containing magnesium and silicon as its major alloying elements. It has good mechanical properties and exhibits good weldability. It is one of the most common alloys of aluminium for general purpose use. Applications include construction of aircraft structures, such as wings and fuselages, ship structures, marine frames, pipeline, storage tank, automotive parts, such as wheel spacers. Many aluminium docks and gangways are constructed with 6061-T6 extrusions, and welded into place. Although this kind of aluminium alloy is tried to join by conventional fusion welding processes, but it is difficult to make a joining due to creation of solidification cracking, liquation cracking and micro porosity formation in the fusion zone. Accordingly, Friction Stir Welding (FSW) has increasingly been applied particularly in situations where these defects need to be avoided.

The Welding Institute (TWI) of Cambridge, UK developed Friction Stir Welding (FSW) in 1991 as an emerging green solid state joining process, friction stir welding is used to join Al alloys of all compositions such as alloys essentially considered unweldable [3]. In this process, joining metal plates is done based on a thermo-mechanical action used by a non-consumable welding tool onto metal plates [3]. The material being joined is never melted at any point during the process, which avoids some of the defects seen in fusion welds. Because of this, FSW is seen as one of the most important welding developments in over a decade [4]. FSW process was invented as a replacement method to fusion joining processes for aluminium alloys and other engineering materials. With use of this process, the porosity and hot cracking defects, often generated with fusion welding, are largely eliminated with resulting improved mechanical and corrosion properties.

As a part of the fabrication process, welding is one of the most important manufacturing technologies used in the aluminum alloy industry. Accordingly, the welding of aluminum and its alloys has always represented a great challenge for designers and technologists. As a matter of fact, the main problem associated with

this kind of joint process can arise from the focus on heat-treatable alloys because heat, generated by the welding process, is responsible for the decay of mechanical properties by causing phase transformations and inducing softening of the alloy [1,2,4]. It has been shown that minor differences in the composition and microstructure of the weldment can create an electrochemical potential difference between various regions of welded joints and, thus, generates localized galvanic corrosion. It has been demonstrated that the conventional fusion welding process would cause less resistance to corrosion as a result of having many defects on the edges such as high porosity, cracks, residual stress, incorrectly selected filler, and an incorrect design. Elimination of these defects by using friction-stir welding (FSW), which is a solid-state process, substantially increases an alloy's corrosion resistance [4].

1.1 problem statement

The research presented in this thesis involves a specific weld joint called a lap joint. This weld configuration can be suitable for many industries where the butt configuration is not practical or required. This type of weld joint poses unique challenges not present in other friction stir weld joints. In fact, aerospace structures such as airplane panels, wing frames and floor decks which are regularly supported with stringers, they are usually joined to the outer skins with lap-welded joints [4]. Moreover, many parts in automotive industry such as automotive engine frames, wheel rims, and car back supports are certainly involved with lap-welded joints [4]. Although, butt joint has been considered by many researchers in order to study for it, meanwhile study of friction stir lap welding (FSLW) has received considerably less attention. The corrosion behaviour of the FSW in different aluminium alloy has been examined by a number of researchers. In this case, the most investigation of corrosion behaviour is performed on butt joints and lap configuration joints are rarely considered.

Most AA6XXX alloys are generally considered to have good corrosion resistance compared to other series of aluminium alloy. However, some treatments or processes such as thermo mechanical treatment or alloying have an effect on the localized corrosion alloys. Accordingly, the treatments or processes can lead to create a pitting corrosion and intergranular corrosion (IGC) in the alloys [1-4,7]. In fact, FSW is a thermo mechanical treatment, which combines frictional heating and stirring motion to soften and mix the interface between two metal plates to produce fully consolidated welds [2-4]. Although the heat input in the FSW process is relatively low and the time at temperature is short compared to fusion welding, various grain structures and grains recrystallization phenomena dynamically occurring during the FSW process, 6XXX series of stir welded Al alloy, have different mechanical properties and various corrosion susceptibility in each area of the jointed zone [3-9,12]. The effect of welding parameters on the corrosion resistance in AlMgSi alloys, despite its industrial importance, has not received considerable attention and is not fully understood.

1.2 Research Objectives

Actually, this comprehensive study is the first report attempting to quantify the corrosion evaluation of FSLW in AA6061-T6 aluminium alloy according to welding parameters and process sensitivity. The goals of the present study is to evaluate the influence of FSW parameters mainly ω and v on the microstructure and mechanical properties of AA6061-T6 and then corrosion behaviors of desirable AA 6061-T6 welded lap joints. In this study, parametric studies were performed involving a lap type of weld including process parameters such as rotation speed (ω , rpm) and welding speed (v , mm/min). Different rotation speeds and welding speeds were determined according to predefine welding process parameters. Overlap shear tensile testing and micro- hardness measurement was conducted for evaluating the effect of the FSW process on the mechanical properties of weldments. Metallography examinations of weldments structure (i.e. macro and micro) was performed for investigating the influence of the FSW process on the microstructure of AA6061-T6 aluminum alloy. According to ASTM standards, corrosion behaviors of desirable AA 6061-T6 welded lap joints was examined by using various corrosion test methods including immersion test (i.e. intergranular corrosion test, ASTM G110) and potentiodynamic polarization tests (i.e. Tafel plots and pitting scans, ASTM G59 & G61). Optical microscopy (OM), atomic force microscopy (AFM), and field emission scanning electron microscopy (FE-SEM) equipped with dispersive energy X-ray (EDX) analysis were utilized for characterizing the weldment microstructures.

The summery of research objectives are listed as following:

1- To Prepare the AA6061-T6 weldments by friction stir welding process.

This step is including:

- 1.1 Selection of main welding variable parameters (welding speed and rotation speed)
- 1.2 Joint design (lap joint)
- 1.3 Pin designing
- 1.4 Lap joint fabrication
- 1.5 Welding performance by use of CNC machine according to welding procedure (different welding and rotation speeds)
- 1.6 Soundness inspection of lap welded joints by visual inspection and CT-scan

2- To evaluate the sound lap welded joint for selecting the desirable joints.

- 2.1 Metallography examinations of weldments structure (macro and micro)
- 2.2 Mechanical properties tests such as micro-hardness test and overlap shear testing

3- To study the corrosion behaviors of desirable AA 6061-T6 welded lap joints by using corrosion test methods such as:

- 3.1 Immersion test (Intergranular Corrosion (IGC)) (ASTM G110)
- 3.2 Potentiodynamic polarization tests
 - 3.2.1 Tafel Polarization Method (ASTM G59)
 - 3.2.2 Cyclic Polarization (Pitting Scans) (ASTM G61)



REFERENCES

- [1] E. Eltai, E. Mahdi and A. Alfantazi, 2013, "The Effect of Gas Tungsten Arch Welding on the Corrosion and Mechanical Properties of AA6061 T6", International Journal of Electrochemical Science, 8, pp.7004-7015.
- [2] J. K. Solberg, 2009, "Teknologiske metaller og legeringer", Institutt for material teknologi, Norwegian University of Science and Technology, NTNU, pp. 215-217.
- [3] T. Ole. Midling, E. J. Morley and A. Sandvik, 1996, "Friction stir welding", The Welding Institute, UK, Assignee, Patent 5813592.
- [4] R.S. Mishra and Z.Y. Ma, 2005, "Friction Stir Welding and Processing", Materials Science and Engineering R, 50, pp.1- 78.
- [5] D. Altenpohl, 1982, 'Aluminium Viewed From Within', Aluminium-Verlag Dusseldorf.
- [6] "Aluminium Standards and Data", Eighth Edition, 1984, the Aluminium Association Inc. New York.
- [7] C. P. Blakenship. Jr. E. A. Starke, and E. Hombogen, 1996, "In Microstructure and Properties of Materials", p. 1, J. C. M. Li. Editor, World Scientific. Singapore
- [8] ASM Specialty Handbook, 1993, "Aluminium and Aluminium Alloys", J. R. Davis and Davis & Associates. Editors. ASM International. Materials Park. OH.
- [9] R. Ambat, A. Davenport, G. Scamans and A. Afseth, 2006, "Effect of Iron-Containing Intermetallic Particles on the Corrosion Behaviour of Aluminium", Corrosion Science, 48 (11), pp. 3455-3471.
- [10] A. Al-Rawajfeh and S. Al Qawabah, 2009, "Investigation of Copper Addition on the Mechanical Properties and Corrosion Resistance of Commercially Pure", Emirates Journal for Engineering Research, 14 (1), pp. 47-52.
- [11] S. Court, K. Gatenby and D. Lloyd, 2001, "Factors Affecting the Strength and Formability of Alloys based on Al-3 wt% Mg", Materials Science and Engineering A, 319-321, pp. 443- 447.
- [12] J. R. Davis, 1999, "Corrosion of Aluminium and its Alloys", Published by ASM International, USA
- [13] M. Carroll, P. Gouma, M. Mills, G. Daehn and R. Dunbar, 2000, "Effects of Zn Additions on the Grain Boundary Precipitation and Corrosion of Al-5083", Scripta Materialia, 42, pp. 335-340.

- [14] C. Vargel, 2004, "Corrosion of Aluminium", Published by Elsevier, France.
- [15] V. Ocenasek and M. Slamova, 2001, "Resistance to Recrystallization Due to Sc and Zr Addition to Al–Mg Alloys", *Material Characterization*, 47, pp. 157-162.
- [16] S. Kang, J. Kim and H. Kim, 2006, "Effect of Deformation Route and Sc and Zr Addition on Ultra-Fine Grain Formation and Superplasticity in Al-Mg Alloys", *Materials Science Forum*, 519-521, pp. 847-852.
- [17] I. Török, K. Juhász, Á. Meilinger and A. Balogh, 2012, "Main Characteristics of Fusion and Pressure Welding of Aluminium Alloys", *Journal of Production Processes and Systems*, 6 (1), pp. 91-106.
- [18] R. Ilyushenko and V. Nesterenkov, 2006, "Novel Technique for Joining of Thick Section Difficult-to-Weld Aluminium Alloys", *Materials Science Forum*, 519-521, pp. 1125-1130.
- [19] G. Mathers, 2002, "The Welding of Aluminium and Its Alloys", Published by Wood head Publishing Limited Ltd, UK.
- [20] W. Hufnagel, 1999, "Key to Aluminium Alloys", Aluminium Publication, Dusseldorf, Germany.
- [21] T. R. Ramachandran, 2006, "Advances in Aluminium Processing and Its Automotive Application", *Workshop Lecture Notes*, pp. 28-32, Indian Institute of Metals, Pune Chapter.
- [22] G. Dieter, 1988, "Mechanical Metallurgy", SI Metric Edition, McGraw-Hill, London, UK.
- [23] W. D. Callister, 2001, "Fundamentals of Materials Science and Engineering", John Wiley & Sons, Hoboken, NJ, USA.
- [24] J. Hirsch, B. Skrotzki, and G. Gottstein, 2008, "Aluminium Alloys, Their Physical and Mechanical Properties", Wiley-VCH, Weinheim, Germany.
- [25] 2010, 'Alloy Composition Details', <http://aluminium.matter.org.uk/aluselect/06compositionbrowse.asp>.
- [26] D. Kopeliovich, 2010, "Wrought aluminium-magnesium-silicon alloys (6XXX), <http://www.substech.com/dokuwiki/doku.php?id=wrough.aluminiummagnesium-siliconalloys6XXX>.
- [27] 2010, The Aluminium Association, ' Technical FAQs & Information', <http://www.aluminum.org/resources/technical-faqs-information>
- [28] G. Gottstein, 2004, "Physical Foundations of Materials Science", Springer, Berlin, Germany.

- [29] F. J. Humphreys and M. Hatherly, 2004, "Recrystallization and Related Annealing Phenomena", Elsevier, Oxford, UK.
- [30] H. Zhan, J. M. C. Mol, F. Hannour, L. Zhuang, H. Terry and J. H. W. de Wit, 2008, "The Influence of Copper Content on Intergranular Corrosion of Model AlMgSi(Cu) Alloys", *Materials and Corrosion*, 59 (8), pp.670-675.
- [31] M. H. Larsen, 2010, "Effect of Composition and Thermo-Mechanical Processing on the Intergranular Corrosion of AA6000 Aluminium Alloys", Norwegian University of Science and Technology, NTNU.
- [32] P. Mukhopadhyay, 2012, "Alloy Designation, Processing, and Use of AA6XXX Series Aluminium Alloys", International Scholarly Research Network, ISRN Metallurgy, Article ID 165082, pp. 1-15.
- [33] A. Simar, Y. Bréchet, B. de Meester, A. Denquin, C. Gallais and T. Pardoen, 2012, "Integrated Modelling of Friction Stir Welding of 6XXX Series Al Alloys: Process, Microstructure and Properties", *Progress in Materials Science*, 57, pp. 95-183.
- [34] A.K. Gupta and D.J. Lloyd, 1992, "The Precipitation in a Super Purity Al–Mg–Si Alloy", In: 3rd International. Conference of. Aluminium Alloys, Trondheim, Norway.
- [35] A.K. Gupta, D.J. Lloyd and S.A. Court, 2001, "Precipitation Hardening Processes in an Al-0.4% Mg-1.3% Si-0.25% Fe Aluminum Alloy", *Materials Science and Engineering A*, 301, pp.140-146.
- [36] C. Gallais, A. Simar, D. Fabrègue, A. Denquin, G. Lapasset and B. de Meester, 2007, "Multiscale Analysis of The Strength and Ductility of AA6056 Aluminium Friction Stir Welds", *Metallurgical and Materials Transaction A*, 38 (5), pp.964-981.
- [37] A. Simar. 2007, "A Multiscale Multiphysics Investigation of Aluminium Friction Stir Welds from Thermal Modelling to Mechanical Properties through Precipitation Evolution and Hardening", PhD Thesis, Université catholique de Louvain, Louvain-la- Neuve, Belgium.
- [38] I. T. Taylor, 1973, "The Relationship between Cooling Rate and Age-Hardening Characteristics of a Number of Aluminium-Magnesium-Silicide Alloys", *Canadian Journal of Metallurgy*, 12, pp.93-103.
- [39] O.S. Es-Said and J.G. Morris, 1988, "Homogenization and Annealing of Aluminium and Copper Alloys", In: H.D. Merchant, J. Crane, E.H. Chia, Editors, Warrendale. PA: TMS; pp. 183-207.

- [40] C. Gallais, A. Denquin, Y. Bréchet and G. Lapasset, 2008, "Precipitation Microstructures in an AA6056 Aluminium Alloy after Friction Stir Welding: Characterization and Modelling", *Materials Science and Engineering A*, 496, pp.77-89.
- [41] Alumatter, 2013, "Corrosion and Corrosion Control", <http://aluminium.matter.org.uk/content/html/eng/default.asp?catid=177&pageid=2144416642>.
- [42] O.R. Myhr, O. Grong, H.G. Fjaer, and C.D. Marioara, 2004, "Modelling of the Microstructure and Strength Evolution in Al–Mg–Si Alloys During Multistage Thermal Processing", *Acta Materialia*, 52 (17) , pp.4997–5008.
- [43] O.R. Myhr, S. Klokkehaug, O. Grong, H.G. Fjaer, and A.O. Kluken, 1998, "Modelling of Microstructure Evolution, Residual Stresses and Distortions in 6082-T9 Aluminium Weldments", *Welding Research*, pp. 286-292.
- [44] O. R. Myhr and O. Grong, 2011, "A Combined Precipitation, Yield Strength and Work Hardening Model for Al-Mg-Si Alloys", 11th International Summer School on Aluminium Alloy Technology, Thermo-mechanical Processing and Forming, Trondheim, Norway.
- [45] H.S. Hasting, 2006, "Clustering and Precipitation in 6XXX Al Alloys: TEM and APT Studies", Department of Physics, Norwegian University of Science and Technology.
- [46] C. D. Marioara, S. J. Andersen, T. N. Stene, H. Hasting, J. Walmsley, A. T. J. Van Helvoort, and R. Holmestad, 2007, "The Effect of Cu on Precipitation in Al-Mg-Si Alloys", *Philosophical Magazine*, 87 (23), pp.3385-3413.
- [47] O. Grong, 2012, "Recent Advances in Solid-State Joining of Aluminium", *Welding journal*, 91(1), pp.26–33.
- [48] D. Steele, D. Evans, P. Nolan and D. J. Lloyd, 2007, "Quantification of Grain Boundary Precipitation and the Influence of Quench Rate In 6XXX Aluminium Alloys", *Materials Characterization*, 58, pp.40-45.
- [49] T. R. Ramachandran, 2006, "Advances in Aluminium Processing and Its Automotive Application", Workshop Lecture Notes, pp. 28-32, Indian Institute of Metals, Pune Chapter.
- [50] R. P. Garrett, J. Lin, and T. A. Dean, 2005, "An Investigation of the Effects of Solution Heat Treatment on Mechanical Properties for AA 6XXX Alloys: Experimentation and Modelling", *International Journal of Plasticity*, 21 (8), pp. 1640-1657.
- [51] L. P. Troeger and E. A. Starke, 2000, "Microstructural and Mechanical Characterization of a Superplastic 6XXX Aluminium Alloy", *Materials Science and Engineering A*, 277 (1-2), pp. 102-113.

- [52] King power, 'Aluminium Profile supplier Kingpower Aluminium Industry', <http://www.seobility.net/en/seocheck/www.aluminium-profile-extrusion.com>.
- [53] M. H. Larsen, 2010, "Effect of Composition and Thermo Mechanical Processing on the Intergranular Corrosion of AA6XXX Aluminium Alloys", Norwegian University of Science and Technology.
- [54] G. Svenningsen, M.H. Larsen, J.C. Walmsley, J.H. Nordlien, and K. Nisancioglu, 2006, "Effect of Artificial Aging on Intergranular Corrosion of Extruded AlMgSi Alloy with Small Cu Content", *Corrosion Science* 48 (6), pp.1528-1543.
- [55] M. H. Larsen, J. C. Walmsley, O. Lunder, R. H. Mathiesen, and K. Nisancioglu, 2008, "Intergranular Corrosion of Copper-Containing AA6XXX AlMgSi Aluminium Alloys", *Journal of the Electrochemical Society*, 155 (11), pp.C550-C556.
- [56] M. H. Larsen, J. C. Walmsley, O. Lunder, and K. Nisancioglu, 2010, "Effect of Excess Silicon and Small Copper Content on Intergranular Corrosion of 6000-Series Aluminium Alloys", *Journal of the Electrochemical Society*, 157 (2), pp.C61-C68.
- [57] G. Svenningsen, M.H. Larsen, J.H. Nordlien, and K. Nisancioglu, 2006, "Effect of High Temperature Heat Treatment on Intergranular Corrosion of AlMgSi(Cu) Model Alloy", *Corrosion Science* 48 (1), pp.258-272.
- [58] G. Svenningsen, M. H. Larsen, J. H. Nordlien, and K. Nisancioglu, 2006, "Effect of Thermo mechanical History on Intergranular Corrosion of Extruded AlMgSi(Cu) Model Alloy", *Corrosion Science* 48 (12), pp.3969-3987.
- [59] G. Svenningsen, J.E. Lein, A. Bjorgum, J.H. Nordlien, Y.D. Yu, and K. Nisancioglu, 2006, "Effect of Low Copper Content and Heat Treatment on Intergranular Corrosion of Model AlMgSi Alloys", *Corrosion Science* 48 (1), pp.226-242.
- [60] Y. Liu, X. Zhou, G. E. Thompson, T. Hashimoto, G. M. Scamans, and A. Afseth, 2007, "Precipitation in an AA6111 Aluminium Alloy and Cosmetic Corrosion", *Acta Materialia*, 55 (1), pp.353-360.
- [61] L.F. Mondolfo, 1976, "Aluminium Alloys: Structure and Properties", Butterworths, UK.
- [62] K. Nisancioglu, 1980, "Corrosion of AlMgSi alloys with Cu Additions: Final Report", Technical Report, SINTEF rapport (SINTEF. "The Foundation for Scientific and Industrial Research" Avdeling for Metallurgi, Norwegian).
- [63] K. Nisancioglu, 1990, "Electrochemical Behaviour of Aluminium-Base Intermetallics Containing Iron", *Journal of the Electrochemical Society*, 137 (1), pp.69-77.

- [64] J.O. Park, C.H. Paik, Y.H. Huang, and R.C. Alkire, 1999, "Influence of Fe-Rich Intermetallic Inclusions on Pit Initiation on Aluminium Alloys in Aerated NaCl", *Journal of the Electrochemical Society*, 146 (2), pp.517-523.
- [65] L.F. Mondolfo, 1977, "Manganese in aluminium alloys", Neuilly Sur Seine: Manganese Centre, France.
- [66] R. Chadwick, 1953, "The Effect of Iron, Manganese, and Chromium on the Properties in Sheet Form of Aluminium Alloys Containing 0.7-Percent Magnesium and 1.0 Percent Silicon", *Journal of the Institute of Metals* 82 (2), pp.75.
- [67] L. M. Iduvirges and J. R. Galvele, 1977, "Pitting Potential of High-Purity Binary Aluminium-Alloys .2. Al-Mg and Al-Zn Alloys", *Corrosion Science*, 17 (12), pp.995-1007.
- [68] A.K. Bhattamishra and K. Lal, 1997, "Microstructural Studies on the Effect of Si and Cr on the Intergranular Corrosion in Al-Mg-Si Alloys", *Materials and Design*, 18 (1), pp.25-28.
- [69] F. Eckermann, T. Suter, P. J. Uggowitzer, A. Afseth, and P. Schmutz, 2008, "The Influence of MgSi Particle Reactivity and Dissolution Processes on Corrosion in Al-Mg-Si Alloys", *Electrochimica Acta*, 54 (2), pp.844-855.
- [70] T. Onda, Y. Hirano and T. Doko, 1993, "Effect of Mg and Si Addition on the Intergranular Corrosion of Aluminium Alloy", *Society of Automotive Engineers*, 268 (19), pp.217-219.
- [71] K. El-Menshawy, A.W. A. El-Sayed, M.E. El -Bedawy, H. A. Ahmed, and S. M. El-Raghy, 2012, "Effect of Aging Time at Low Aging Temperatures on the Corrosion of Aluminum Alloy 6061", *Corrosion Science*, 54, pp.167-173.
- [72] T. Minoda and H. Yoshida, 2000, "The Effect of Microstructure on Intergranular Corrosion Resistance of 6061 Alloy Extrusion", 331-3(Part 1-3):1689-1694, 7th International Conference on Aluminium Alloys (ICAA7), Charlottesville, Virginia.
- [73] G.S. Frankel, 1998, "Pitting Corrosion of Metals - A Review of the Critical Factors", *Journal of the Electrochemical Society*, 145 (6), pp.2186-2198.
- [74] G. E. Totten and D. S. MacKenzie, 2003, *Handbook of aluminium*, Vol. 2, "Alloy Production and Materials Manufacturing", B. Raton, Fla.: Taylor and Francis/Marcel Dekker, Ch. 11.
- [75] E. Bardal, 1985, "Korrosjon og korrosjonsvern", Tapir Forlag, pp. 112-121.
- [76] P. Martin, S. C. Vargel, M. Jacques, 2004, "Corrosion of Aluminium", Elsevier, First Edition, pp. 113-121.

- [77] I.L. Muller and J.R. Galvele, 1977, "Pitting Potential of High-Purity Binary Aluminium-Alloys.1. Al-Cu Alloys- Pitting and Intergranular Corrosion", Corrosion Science, 17 (3), pp.179-189.
- [78] K.S. Rao and K.P. Rao, 2004, "Pitting Corrosion of Heat-Treatable Aluminium Alloys and Welds: A Review", Transactions of the Indian Institute of Metals, 57 (6), pp.593-610.
- [79] E. Bardal, 1977, "Korrosjonsprøving - korttidsmetoder. Sammenfattende Sluttrapport", Del 1, STF16 A77034. Korrosjonssenteret, SINTEF, Trondheim.
- [80] C. J. Dawes, 1999, 'Friction Stir Welding', [www. Alueurope.eu/talat/lectures/4410.pdf](http://www.alueurope.eu/talat/lectures/4410.pdf)
- [81] W. M. Thomas, E. D. Nicholas, J.C. Nidham, 1991, US Patent No. 5,460,317.
- [82] Terry Khaled ,2005, An Outside Looks at Friction Stir Welding, Federal Aviation Administration, Lakewood, CA, USA, <https://www.faa.gov/search/?omni=MainSearch&q=an+outsider+looks+at+friction+stir+welding&x=32&y=6>
- [83] ASM Handbook, 1993, "Welding, Brazing and Soldering", Vol. 6, pp. 297-324.
- [84] K. E. Knipstrom and B. Pekkari, 1997, "Friction Stir Welding Process Goes Commercial", Welding Journal, 76 (9), pp. 55-57.
- [85] E. D. Nicholas, Advanced Materials & Processing (1999), pp. 69-71.
- [86] P. Vilaça and W. Thomas, 2012, "Friction Stir Welding Technology", Advanced Structure Materials, 8, pp. 85-124.
- [87] B.T. Gibson, D.H. Lammlein, T.J. Prater, W.R. Longhurst, C.D. Cox, M.C. Ballun, K.J. Dharmaraj, G.E. Cook and A.M. Strauss, 2014, "Friction Stir Welding: Process, Automation, and Control", Journal of Manufacturing Processes, 16 (1), pp. 56-73.
- [88] R.W. Carter, 2004, "Auto-Adjustable Tool for Self-Reacting and Conventional Friction Stir Welding", U.S. Patent 6,758,382.
- [89] J.A. Schneider, A.C. Nunes and M.S. Brendel, 2010, "The Influence of Friction Stir Weld Tool Form and Welding Parameters on Weld Structure and Properties: Nugget Bulge in Self-Reacting Friction Stir Welds", In: Proceedings of the 8th International Symposium on Friction Stir Welding, TWI.
- [90] J. Hilgert, J.F. dos Santos and N. Huber, 2012, "Numerical Simulation in Bobbin Tool FSW Process Development", In: Proceedings of the 9th International Symposium on Friction Stir Welding, TWI.

- [91] J. Chen, H. Fujii, Y. Sun, Y. Morisada and K. Kondoh, 2012, "Effect of Material Flow by Double-Sided Friction Stir Welding on Weld Structure and Mechanical Properties of Magnesium Alloy", In: Proceedings of the 9th International Symposium on Friction Stir Welding, TWI.
- [92] R.S. Mishra and M.W. Mahoney, 2007, "Friction stir spot welding, Friction stir welding and processing", Materials Park, OH: ASM International; pp. 235-72.
- [93] K. Feldman, G. Kohn and A. Stern, 2012, "Friction stir spot welding", The Engineering Center, <http://www.engineers.org.il/Uploads/3294feldman160107.pdf>
- [94] M. Fujimoto, H. Okada and K. Kamimuki, 2012, "Application Study on Refill FSSW on Aerospace Industries", In: Proceedings of the 9th International Symposium on Friction Stir Welding, TWI.
- [95] C.D. Cox, B.T. Gibson, A.M. Strauss and G.E. Cook, 2012, "Effect of Pin Length and Rotation Rate on The Tensile Strength of A Friction Stir Spot-Welded Al Alloy: A Contribution to Automated Production", Materials and Manufacturing Processes, 27 (4), pp.472-478.
- [96] C. Schilling and J. dos Santos, 2004, "Method and Device for joining at Least two Adjoining Work Pieces by Friction Welding", U.S. Patent 6,722,556.
- [97] F. Hunt, H. Badarinarayan and K. Okamoto, 2006, "Design of Experiments for Friction Stir Stitch Welding of Aluminium Alloy 6022-T4", In: SAE Technical Paper 2006-01-0970, <http://dx.doi.org/10.4271/2006-01-0970>.
- [98] F. Hunt, Q. Yang, H. Badarinarayan, K. Okamoto and D. Zhou, 2008, "Friction Stir Welding Of Aluminium for Automotive Closure Panel Applications". In: SAE Technical Paper 2008-01-0145, <http://dx.doi.org/10.4271/2008-01-0145>.
- [99] C.D. Cox, B.T. Gibson, A.M. Strauss and G.E. Cook. 2012, "The Application of a Rotating Anvil in Friction Stir Spot Welding: An Experimental and Numerical Study", In: 9th International Conference on Trends in Welding Research.
- [100] P. Sinclair, 2009, "Heated Friction Stir Welding: An Investigation into How Preheating Aluminium 6061 Affects Process Forces", M.S. Thesis, Vanderbilt University.
- [101] P. Sinclair, W.R. Longhurst, C.D. Cox, D.H. Lammlein, A.M. Strauss and E. Cook, 2010, "Heated Friction Stir Welding: An Experimental and Theoretical Investigation into How Preheating Influences Process Forces", Materials and Manufacturing Processes, 25 (11), pp.1283-1291.
- [102] S. Kou and G. Cao, 2006, "Arc-Enhanced Friction Stir Welding", U.S. Patent 7,078,647.

- [103] E. Scutelnicu, D. Birsan and R. Cojocaru, 2011, "Research on Friction Stir Welding and Tungsten Inert Gas assisted Friction Stir Welding of Copper", Recent Advances in Manufacturing Engineering, pp. 97-102.
- [104] F. Palm, 2004, "Laser Supported Friction Stir Welding Method", U.S. Patent 6,793,118.
- [105] B. Cabage, 2006, "New Way to Weld: ORNL Team Adds Laser Tech to Expand the Reach of a New Welding Technique", In: Oak Ridge National Laboratory Reporter, 84, pp. 1-4.
- [106] B.M. Tweedy, W. Arbegast and C. Allen, 2005, "Friction Stir Welding of Ferrous Alloys Using Induction Preheating", Friction Stir Welding and Processing III. Warrendale, PA: The Minerals, Metals & Materials Society.
- [107] Vehicle Technologies Program , Office of Energy Efficiency and Renewable Energy, U.S. Department of Energy, 2012, http://www1.eere.energy.gov/vehiclesandfuels/pdfs/hswr2005/fy05_hswr4h.pdf
- [108] W.A. Ferrando, D. Lammlein, M. Posada and A. Floyd, 2012, "The Concept of Electrically Assisted Friction Stir Welding and Application to Processing of Various Metals", In: Proceedings of the 9th International Symposium on Friction Stir Welding, TWI.
- [109] V. Balasubramanian, V. Ravisankar and G.M. Reddy, 2008, "Effect of Pulsed Current Welding on Mechanical Properties of High Strength Aluminium Alloy", The International Journal of Advanced Manufacturing Technology, 36 (3-4), pp. 254-262.
- [110] W.M. Thomas, K.I. Johnson and C.S. Wiesner, 2003, "Friction Stir Welding – Recent Developments in Tool and Process Technologies", Advanced Engineering Materials, 5 (7), pp. 485-490.
- [111] I. Eberl, C. Hantrais, J.C. Ehrtsrom and C. Nardin, 2010, "Friction Stir Welding Dissimilar Alloys for Tailoring Properties of Aerospace Parts", Science and Technology of Welding and Joining, 15 (8), pp. 699-705.
- [112] G. M. D.Cantin, S. A. David, W. M. Thomas, E. Lara-Curzio, and S. S. Babu, 2005, "Friction Skew-Stir Welding of Lap Joints in 5083–0 Aluminium", Science and Technology of Welding and Joining, 10 (3), pp. 268-280.
- [113] S. David, T. DebRoy, J. DuPont, T. Koseki and H. Smartt, 2008, "Trends in welding research", Proceedings of the 8th International Conference, Pine Mountain, Georgia, USA, pp. 1-10.
- [114] P. Threadgill and M. Nunn, 2003, "A Review of FSW Part (1), Process Review", TWI Report, No.760.

- [115] O. Frigaard, O. Grong, and O. T. Midling, 2001, "A Process Model for Friction Stir Welding of Age Hardening Aluminium Alloys", *Metallurgical and Materials Transactions A*, 32 (5), pp. 1189-1200.
- [116] P. Threadgill and A. Leonard, 1999, "Macro and Microstructural Features of Friction Stir Welds in Various Materials", TWI Report, No. 693.
- [117] M. Guerra, C. Schmidt, J. C. McClure, L. E. Murr, and A. C. Nunes, 2002, "Flow Patterns During Friction Stir Welding", *Materials Characterization*, 49 (2), pp. 95-101.
- [118] W. Arbegast, 2003, "Modeling Friction Stir Joining as a Metalworking Process", *Hot Deformation of Aluminium Alloys III*, Edited by Z Jin. TMS, the Minerals, Metals, and Materials Society, China.
- [119] W. Arbegast, 2005, "Using Process Forces as a Statistical Process Control Tool for Friction Stir Welding", *Friction Stir Welding and Processing III*, Edited by K Jata, et al. TMS, the Minerals, Metals, and Materials Society.
- [120] K. Cooligan, 1999, "Material Flow Behaviour during Friction Stir Welding of Aluminium", *Supplement to the Welding Journal*, 78(7), pp. 229s-237s.
- [121] C. E. Hendricks. 2009, "The Mechanical Effects of Weave Track on Friction Stir Welds in a Lap Configuration", M.S. Thesis, Nashville University.
- [122] Z. W. Chen and S. Cui, 2008, "On the Forming Mechanism of Banded Structures in Aluminium Alloy Friction Stir Welds", *Scripta Materialia*, 58 (5), pp. 417-420.
- [123] P. L. Threadgil, A. J. Leonard, and H. R. Shercliff, 2009, "Friction Stir Welding of Aluminium Alloys", *International Material Reviews*, 54 (2), pp. 49-93.
- [124] M. K. Yavada, R. S. Mishra, and Y. L. Chen, 2010, "Study of Friction Stir Joining of Thin Aluminium Sheets in Lap Joint Configuration", *Science and Technology of Welding & Joining*, 15 (1), pp. 70-75.
- [125] L. Dubourg, A. Merati, and M. Jahazi, 2010, "Process Optimization and Mechanical Properties of Friction Stir Lap Welds of 7075-T6 Stringers on 2024-T3 Skin", *Materials & Design*, 31 (7), pp. 3324-3330.
- [126] Q. Yang, X. Li, and K. Chen, 2011, "Effect of Tool Geometry and Process Condition on Static Strength of a Magnesium Friction Stir Lap Linear Weld", *Materials Science & Engineering A*, 528 (6), pp. 2463-2478.
- [127] X. Cao and M. Jahazi, 2011, "Effect of Tool Rotation Speed and Probe Length on Lap Joint Quality of a Friction Stir Welded Magnesium Alloy", *Materials and Design*, 32 (1), pp. 1-11.

- [128] L. Cederqvist and A.P. Reynolds, 2001, "Factors Affecting the Properties of Friction Stir Welded Aluminium Lap Joints", *Welding Journal*, 80 (12), pp. 281-287.
- [129] X. Cao and M. Jahazi, 2009, "Effect of Welding Speed on Lap Joint Quality of Friction Stir Welded AZ31 Magnesium Alloy", In *Proceedings of the 8th ASM International Conference, Trends in Welding Research*, Georgia, USA.
- [130] M. Yadava, R. S. Mishra, and Y. L. Chen, 2007, "Friction Stir Lap Welds of AA6611 Aluminium Alloy", In *Friction Stir Welding and Processing IV*, Orlando, Florida.
- [131] G. Buffa, G. Campanile, and L. Fratini, 2009, "Friction Stir Welding of Lap Joints: Influence of Process Parameters on The Metallurgical and Mechanical Properties", *Materials Science & Engineering A*, 519 (1-2), pp. 19-26.
- [132] V. Soundararajan, E. Yarrapareddy, and R. Kovacevic, 2006, "Investigation of the Friction Stir Lap Welding of Aluminium Alloys AA 5182 and AA 6022", *Journal of Materials Engineering and Performance*, 16 (4), pp. 477-484.
- [133] C. Y. Lee, W. B. Lee, and J. W. Kim, 2008, "Lap Joint Properties of FSWed Dissimilar Formed 5052 Al and 6061 Al Alloys with Different Thickness", *Journal of Materials Science Letters*, 43 (9), pp. 3296-330.
- [134] W.J. Arbogast and P.J. Hartley, 1998, "Friction Stir Weld Technology Development at Lockheed Martin Michoud Space Systems- An Overview", In *Proceedings of the Fifth International Conference of Trends in Welding Research: Pine Mountain, GA*. pp. 541.
- [135] S. R. Ren, Z. Y. MA, and L. Q. Chen, 2007, "Effect of Welding Parameters on Tensile Properties and Fracture Behaviour of Friction Stir Welded Al-Mg-Si Alloy", *Scripta Materialia*, 56 (1), pp. 69-72.
- [136] Z. Y. MA, 2008, "Influence of Tool Dimension and Welding Parameters on Microstructure and Mechanical Properties of Friction-Stir-Welded 6061-T651 Aluminium Alloy", *Metallurgical and Materials Transactions A*, 39 (10), pp. 2378-2389.
- [137] K. Colligan, 1999, In *Proceedings of the First International Symposium on Friction Stir Welding*, Thousand Oaks, CA, USA.
- [138] K. Colligan, 1999, *Welding Journal*, 78 (), pp. 229s-237s.
- [139] Y. Li, L.E. Murr and J.C. McClure, 1999, "Solid-State Flow Visualization in the Friction-Stir Welding of 2024 Al to 6061 Al", *Scripta Materialia*, 40 (9), pp. 1041-1046.

- [140] T.U. Seidel and A.P. Reynolds, 2001, "Visualization of The Material Flow in AA2195 Friction-Stir Welds Using a Marker Insert Technique", *Metallurgical and Materials Transactions A*, 32 (11), pp. 2879-2884.
- [141] A. K. Hussain and S. A. Quadri, 2010, "Evaluation of Parameters of Friction Stir Welding for Aluminium AA6351 Alloy", *International Journal of Engineering Science and Technology*, 2 (10), pp. 5977-5984.
- [142] R. Nandan, T. Debroy, and H.K. Bhadeshia. 2008, "Recent Advances in Friction Stir Welding Process, Weldments Structure and Properties", *Progress in Materials Science*, 53, pp. 980-1023.
- [143] P. Vilaça, L. Quintino, J.F. dos Santos, R. Zettler and S. Sheikhi, 2007, "Quality Assessment of Friction Stir Welding Joints via an Analytical Thermal Model, STIR", *Materials Science and Engineering A*, 445–446, pp. 501–508.
- [144] P. Vilaça, L. Quintino and J.F dos Santos, 2005, "STIR—Analytical Thermal Model for Friction Stir Welding", *Journal of Materials Processing Technology*, 169 (3), pp. 452–465.
- [145] R. Rai, A. De., H. K. D. H. Bhadeshia and T. DebRoy, 2011, "Review: Friction Stir Welding", *Tools Science and Technology of Welding and Joining*, 16 (4), pp. 325-342.
- [146] W. J. Arbogast, 2003, "Friction Stir Joining: Characteristic Defects", *Advanced Materials Processing Center*, Ohio University, USA.
- [147] Y. N. Zhang, X. Cao, S. Larose and P. Wanjara, 2012, "Review of Tools for Friction Stir Welding and Processing", *Canadian Metallurgical Quarterly*, 51 (3), pp. 250-261.
- [148] W.M. Thomas, E.D. Nicholas, J.C. Needham, P. Temple-Smith, S.W.K.W. Kallee and J.C. Dawes, 1996, "Friction Stir Welding", UK Patent application, GB 2306366A
- [149] W.M. Thomas. 1999, "High Performance Tools for Friction Stir Welding", Patent Filing, WO 99/ 52669.
- [150] W. Thomas, K. Johnson and C. Wiesner, 2003, "Friction Stir Welding – Recent Developments in Tool and Process Technologies", *Advanced Engineering Materials*, 5 (7), pp. 485-490.
- [151] www.gruppofrattura.it/ors/index.php/aim/article/download/811/771
- [152] P. Wanjara, B. Monsarrat, and S. Larose, 2013, "Gap Tolerance Allowance and Robotic Operational Window for Friction Stir Butt Welding of AA6061", *Journal of Materials Processing Technology*, 213 (4), pp. 631-640.

- [153] K. Inada, H. Fuiji, Y.S. Ji, Y.F. Sun and Y. Morisada, 2010, "Effect of Gap on FSW Joint Formation and Development of Friction Powder Processing Science and Technology of Welding & joining, 15 (2), pp. 131-136.
- [154] 'Joining- Friction Stir Welding', 2002, European Aluminium Association, www.alueurope.eu/wp.../01/AAM-Joining-3-Friction-stir-welding.pdf
- [155] L. Cederqvist and A. Reynolds, 2000, "Properties of Friction Stir Welded Aluminium Lap Joints", Proceedings of the 2nd International Friction Stir Welding Symposium, sponsored by TWI, Ltd., Gothenburg, Sweden.
- [156] A. Leonard, 2003, "Flaws in Friction Stir Welding", 4th International Symposium on Friction Stir Welding, Park City, Utah, USA.
- [157] G. D. Sylva, C. D. Allen, D. R. High, 2011, 'Patent US 8079276, 'Dynamic Calibration Assembly for a Friction Stir Welding Machine', http://www.twi.co.uk/j32k/unprotected/band_1/fswintro.html
- [158] <http://www.materialteknologi.hig.no/materiallaere.htm>
- [159] B.Z. Shakhashiri, 2008, "Chemical of the Week: Aluminium", SciFun.org. University of Wisconsin.
- [160] M. C. Reboul and B. Baroux, 2011, "Metallurgical Aspects of Corrosion Resistance of Aluminium Alloys", Materials and Corrosion, 62 (3), pp. 215-233.
- [161] S. Gustafsson, 2011, Corrosion Properties of Aluminium Alloys and Surface Treated Alloys in Tap Water, www.diva-portal.org/smash/get/diva2:436113/fulltext01.pdf
- [162] L. Xu, Y. Ma, X. Li and H. Wang, 2010, NACE International, Corrosion Conference and EXPO, Report No.10397, pp. 1-8.
- [163] K. Shimizu, R. Furneaux, G. Thompson, G. Wood and A. Gotoh, 1991, "On The Nature of "Easy Paths" for The Diffusion of Oxygen in Thermal Oxide Films on Aluminium", Oxidation of Metals, 35 (5-6), pp. 427-439.
- [164] I.J. Polmear, 2006, "Light Alloys from Traditional Alloys to Nanocrystals", Fourth Edition, Published by Elsevier, UK.
- [165] Z. Szklarska-Smialowska, 1992, 'Pitting Corrosion of Aluminium Alloys', Corrosion Science, 33 (8), pp. 1193-1202.
- [166] G.E. Thompson, Surface Characteristics of Aluminium and Alloys, Training Aluminium Application Technologies, Lecture 5101.
- [167] G. E. Thompson, 1996, "Corrosion and Filming Behaviour of Aluminium and its Alloys", Material Science Forum, 217-222, pp. 95-106.

- [168] S. Umoren and M. Solomon, 2010, "Effect of Halide Ions Additives on the Corrosion Inhibition of Aluminium in HCl by Polyacrylamide", *The Arabian Journal for Science and Engineering*, 35 (2A), pp. 115-129.
- [169] F. King, "Aluminium and its Alloys", 1997, Published by Ellis Horwood Limited, UK.
- [170] B. D. Crag, 1995, "Handbook of Corrosion Data", ASM International, Second Edition.
- [171] 'Aluminium E- pH (Pourbaix) Diagram, <http://corrosion-doctors.org/Corrosion-Thermodynamics/Potential-pH-diagramaluminum.htm>.
- [172] ASM Metals Handbook 1987, Vol. 13, "Corrosion of Aluminium and Aluminium alloys", Metals Handbook, Ninth Edition. ASM Intl, Ohio, pp. 583–609.
- [173] M. G. Fontana, 1987, "Corrosion Engineering", Third Edition, Published by McGraw-Hill international, UK.
- [174] W. Carrol and C. Breslin, 1991, "Stability of Passive Films Formed on Aluminium in Aqueous Halide Solutions", *British Corrosion Journal*, 26 (4), pp. 255-259.
- [175] E. Ghali, 2010, "Corrosion Resistance of Aluminium and Magnesium Alloys", Published by John Wiley & Sons, Inc., Hoboken, New Jersey.
- [176] I.J. Polmear, 2005, "Wrought Aluminium Alloys, in Light Alloys", Fourth Edition, Butterworth-Heinemann: Oxford, pp. 97-204.
- [177] N. Idusuyi and O. Oluwole, 2012, "Aluminium Anode Activation Research – A Review", *International Journal of Science and Technology*, 2 (8), pp. 561-566.
- [178] K. Yasakau, M. Zheludkevich, S. Lamarka and M. Ferreira, 2007, "Role of Intermetallic Phases in Localized Corrosion of AA5083", *Electrochimica Acta*, 52 (27), pp. 7651-7659.
- [179] W.W. Smeltzer, 1955, "Principles Applicable to the Oxidation and Corrosion of Metals and Alloys", *Corrosion*, 11 (9), pp. 18-26.
- [180] M. Bethecourt, F. Botana, J. Calvino, M. Marcos, J. Pérez and M. Rodriguez, 1998, "The Influence of the Surface Distribution of Al₆(MnFe) Intermetallic on the Electrochemical Response of AA5083 Aluminium Alloy in NaCl Solutions", *Materials Science Forum*, 289-292, pp. 567-574.
- [181] I. J. Polmear, 1995, "Light Alloys", Third Edition, Arnold, London, UK.

- [182] N. Birbilis, and R. G. Buchheit, 2005, "Electrochemical Characteristics of Intermetallic Phases in Aluminium Alloys: An Experimental Survey and Discussion", *Journal of the Electrochemical Society*, 152 (4), pp. B140-B151.
- [183] J. E. Hatch, 1984, "Aluminium: Properties and Physical Metallurgy", Editor, ASM, Metals Park, OH.
- [184] J. L. Searles, P. I. Gouma, and R. G. Buchheit, 2001, "Stress Corrosion Cracking of Sensitized AA5083 (Al-4.5Mg-1.0Mn)", *Metallurgical and Materials Transaction A*, 32 (11), pp. 2859-2867.
- [185] R. G. Buchheit, 1995, "A Compilation of Corrosion Potentials Reported for Intermetallic Phases in Aluminium Alloys", *Journal of the Electrochemical Society*, 142 (11), pp. 3994-3996.
- [186] M. Büchler, T. Watari, and W. H. Smyrl, 2000, "Investigation of the Initiation of Localized Corrosion on Aluminium Alloys by Using Fluorescence Microscopy", *Corrosion Science*, 42 (9), pp.1661-1668.
- [187] G. O. Ilevbare, O. Schneider, R. G. Kelly, and J. R. Scully, 2004, "In Situ Confocal Laser Scanning Microscopy of AA 2024-T3 Corrosion Metrology: I. Localized Corrosion of Particles", *Journal of the Electrochemical Society*, 151 (8), pp. 453-464.
- [188] O. Schneider, G. O. Ilevbare, R. G. Kelly, and J. R. Scully, 2004, "In Situ Confocal Laser Scanning Microscopy of AA 2024-T3 Corrosion Metrology: II. Trench Formation around Particles", *Journal of the Electrochemical Society*, 151 (8), pp. 465-472.
- [189] I.L. Muller, and J.R. Gavele, 1977, "Pitting Potential of High Purity Binary Aluminium Alloys-II. Al-Mg and Al-Zn Alloys", *Corrosion Science*, 17 (12), pp. 995-1007.
- [190] H. Ezuber, A. El-Houd and F. El-Shawesh, 2008, "A Study on the Corrosion Behaviour of Aluminium Alloys in Seawater", *Materials and Design*, 29 (4), pp. 801-805.
- [191] M. Trueba and S. Trasatti, 2010, "Study of Al Alloy Corrosion in Neutral NaCl by the Pitting Scan Technique", *Materials Chemistry and Physics*, 121 (3), pp. 523-533.
- [192] A. Davoodi, J. Pan, C. Leygraf and S. Norgren, 2008, "The Role of Intermetallic Particles in Localized Corrosion of an Aluminium Alloy Studied by SKPFM and Integrated AFM/SECM", *Journal of the Electrochemical Society*, 155 (5), pp. 211-218.
- [193] C. M. Liao, J. M. Olive, M. Gao and R. P. Wei, 1998, "In-Situ Monitoring of Pitting Corrosion in Aluminium Alloy 2024", *Corrosion*, 54 (6), pp.451-459.

- [194] E. McCafferty, 2003, "General Relations Regarding Graph Theory and the Passivity of Binary Alloys", *Journal of the Electrochemical Society*, 150 (5), pp. 238-247.
- [195] K. Nisancioglu, 1990, "Electrochemical Behaviour of Aluminium-Base Intermetallics Containing Iron", *Journal of the Electrochemical Society*, 137 (1), pp. 69-77.
- [196] T. J. R. Leclère and R. C. Newman, 2002, "Self-Regulation of the Cathodic Reaction Kinetics during Corrosion of AlCu Alloys", *Journal of the Electrochemical Society*, 149 (2), pp. 52-56.
- [197] R. G. Buchheit, L. P. Montes, M. A. Martinez, J. Michael, and P. F. Hlava, 1999, "The Electrochemical Characteristics of Bulk-Synthesized Al_2CuMg ", *Journal of the Electrochemical Society*, 146 (12), pp. 4424-4428.
- [198] Ch. Blanc and G. Mankowski, 1998, "Pit Propagation Rate on the 2024 and 6056 Aluminium Alloys", *Corrosion Science*, 40 (2-3), pp. 411-429.
- [199] B. J. Melrose, 2010, "The Use of Friction-Surface Processing as a Method of Corrosion Protection of a Friction-Stir Weld in the Al-Li-Cu Alloy AA2050-T851", M.S. Thesis, The University of Birmingham.
- [200] P. Marcus, 2002, "Corrosion Mechanisms in Theory and Practice", Second Edition, Published by Marcel Dekker, Inc, New York, USA.
- [201] P. Markus, V. Maurice and H. Strehblow, 2008, "Localized Corrosion (Pitting): A Model of Passivity Breakdown including The Role of the Oxide Layer Nanostructure", *Corrosion Science*, 50 (9), pp. 2698-2704.
- [202] C. Choa, L. Lin and D. MacDonald, 1981, "A Point Defect Model for Anodic Passive Films: I. Film Growth Kinetics", *Journal of the Electrochemical Society*, 128 (6), pp. 1187-1194.
- [203] S. Katsas, J. Nikolaou and G. Papadimitriou, 2007, "Corrosion Resistance of Repair Welded Naval Aluminium Alloys", *Materials and Design*, 28 (3), pp. 831-836.
- [204] S. Dymek and M. Dollar, 2003, "TEM Investigation of Age-Hardenable Al 2519 Alloy Subjected to Stress Corrosion Cracking Tests", *Materials Chemistry and Physics*, 81 (2-3), pp. 286- 288.
- [205] Ph. Gimenez, J. J. Rameau and M. Reboul, 1981, "Experimental pH-Potential Diagram of Aluminium for Seawater", *Corrosion*, 37 (12), pp. 673-682.
- [206] "Standard Recommended Practice for Examination and Evaluation of Pitting Corrosion, G46", *Annual Book of ASTM Standards*, American Society for Testing and Materials.

- [207] M. Yasuda, F. Weinberg and D. Tromans, 1990, "Pitting Corrosion of Al and Al-Cu Single Crystals", *Journal of the Electrochemical Society*, 137 (12), pp. 3708–3715.
- [208] E. Kus, Z. Lee, S. Nutt and F. Mansfeld, 2006, "A Comparison of the Corrosion Behaviour of Nanocrystalline and Conventional Al 5083 Samples", *Corrosion* 62 (2), pp. 152–161.
- [209] M. Sheffer, A. Groysman and D. Mandler, 2003, "Electrodeposition of Sol-Gel Films on Al for Corrosion Protection", *Corrosion. Science*, 45 (12), pp. 2893–2904.
- [210] B. Zaid, D. Saidi, A. Benzaid and S. Hadji, 2008, "Effects of pH and Chloride Concentration on Pitting Corrosion of AA6061 Aluminium Alloy", *Corrosion Science* 50 (7), pp.1841–1847.
- [211] H.W. Pickering, 1986, "On the Roles of Corrosion Products in Local Cell Processes", *Corrosion* 42 (1), pp. 125–140.
- [212] D. O. Sprowls and R. H. Brown, 1967, "Fundamental Aspects of Stress Corrosion Cracking", the Ohio State University, pp. 466-512.
- [213] G. Svenningsen, 2003, 'Corrosion of Aluminium Alloys', www.sintef.no/static/mt/norlight/.../gaute_svenningsen.pdf
- [214] R. Braun, 2005, "Effect of Thermal Exposure on the Microstructure, Tensile Properties and the Corrosion Behaviour of 6061 Aluminium Alloy Sheet", *Materials and Corrosion*, 56 (3), pp. 159-163.
- [215] J.R. Galvele and S.M. De Micheli, 1970, "Mechanism of Intergranular Corrosion of Al-Cu Alloys", *Corrosion Science*, 10 (11), pp. 795-807.
- [216] W. Zhang and G.S. Frankel, 2003, "Transitions Between Pitting and Intergranular Corrosion in AA2024", *Electrochimica Acta*, 48 (9), pp. 1193-1210.
- [217] M. Posada, L.E. Murr and R.M. Arrowood, 1997, *Microstructure Science*, 25, pp. 131.
- [218] G. H. Koch, 1999, Paper 516, in *Corrosion '99*, NACE, Houston, TX
- [219] R.G. Buchheit, J.P. Moran and G.E. Stoner, 1990, "Localized Corrosion Behavior of Alloy 2090 - Role of Microstructural Heterogeneity", *Corrosion*, 46 (8), pp. 610-617.
- [220] K. Orushino and K. Sugimoto, 1979, "Stress-Corrosion Cracking of Aged Al-Cu-Mg Alloys in NaCl Solution", *Corrosion Science*, 19 (4), pp. 225-229.
- [221] A. Garner and D. Tromans, 1979, "Direct Observation of Intergranular Corrosion in Al-4 wt% Cu Alloy", *Corrosion*, 35 (2), pp. 55-60.

- [222] K. Sugimoto, K. Hoshino, M. Kageyama, S. Kageyama and Y. Sawada, 1975, "Stress Corrosion Cracking of Aged Al-4%Cu Alloy In NaCl Solution", *Corrosion Science*, 15 (6-12), pp. 709-720.
- [223] M.J. Robinson and N.C. Jackson, 1999, "Exfoliation Corrosion of High Strength Al-Cu-Mg Alloys: Effect of Grain Structure", *British Corrosion Journal*, 34 (1), pp. 45-49.
- [224] M.O. Speidel and M.V. Hyatt, in: M.G. Fontana, R.W. Staehle (Eds.), 1972, 'Advances in Corrosion Science and Technology', Vol. 2, Plenum Press, New York, USA.
- [225] "Standard Practice for Evaluating Intergranular Corrosion Resistance of Heat Treatable Aluminium Alloys by Immersion in Sodium Chloride + Hydrogen Peroxide Solution", 2009, ASTM Standard, G110-92.
- [226] "Standard Test Method for Determining the Susceptibility to Intergranular Corrosion of 5XXX Series Aluminium Alloys by Mass Loss after Exposure to Nitric Acid (NAMLT Test)", 1999, ASTM standard, G 67
- [227] "Corrosion of Metals and Alloys, Determination of Resistance to Intergranular Corrosion of Solution Heat- Treatable Aluminium Alloys", 1996, British Standard BS11846.
- [228] D. Adenis, A. Guilhaudis and Me'moires, 1967, *Science Reverse Metallurgy*, 10, pp. 877.
- [229] M. Reboul and J. Bouvaist, 1979, "Exfoliation Corrosion Mechanisms in the 7020 Aluminium Alloy", *Materials and Corrosion*, 30, pp. 700-705.
- [230] M. O. Speidel, 1975, "Stress Corrosion Cracking of Aluminium Alloys", *Metallurgical and Materials Transaction A*, 6 (4), pp. 631-651.
- [231] N. J. H. Holroyd, 1989, "In: Environment Induced Cracking of Metals", NACE, Houston, USA.
- [232] M. C. Reboul, T. Magnin and T. J. Warner, 1992, 3rd International Conference on Aluminium Alloys ICAA3, Trondheim Norway.
- [233] S. Osaki, D. Ito and M. Nakai, 2001, "SCC Properties of 7050 Series Aluminum Alloys in T6 and RRA Tempers", *Journal of Japanese Institute of Light Metals* 51 (4), pp. 222-227.
- [234] J. R. Scully and G. A. Young, 2000, *Corrosion 2000*, Orlando 26-30 March NACE, Houston, paper 368.
- [235] M. Dixit, R. S. Mishra, 2008, "Structure-Property Correlations in Al 7050 and Al 7055 High-Strength Aluminium Alloys", *Materials Science and Engineering A*, 478 (1-2), pp. 163-172.

- [236] J. C. Lin, H. L. Liao, W. D. Jenhng, C. H. Chang and S. L. Lee, 2006, "Effect of Heat Treatments on the Tensile Strength and SCC-Resistance of AA7050 in an Alkaline Saline Solution", *Corrosion Science*, 48 (10), pp. 3139-3156.
- [237] B. J. Connolly and J. R. Scully, 2000, "Corrosion Cracking Susceptibility in Al-Li-Cu Alloys 2090 And 2096 as a Function of Isothermal Aging Time", *Scripta Materialia*, 42 (11), pp.1039-1045.
- [238] C.S. Paglia and R.G. Buchheit, 2008, "A Look in the Corrosion of Aluminium Alloy Friction Stir Welds", *Scripta Materialia*, 58 (5), pp. 383–387.
- [239] J.B. Lumsden, M.W. Mahoney, G. Pollock and C.G. Rhodes, 1999, "Intergranular Corrosion Following Friction Stir Welding of Aluminium Alloy 7075-T651", *Corrosion*, 55 (12), pp. 1127-1135
- [240] G. Biallas, R. Braun, C. Dalle Donne, G. Staniek and W.A. Kaysser, 1999, In: *The 1st International Symposium on Friction Stir Welding*, California.
- [241] F. Hannour, A.J. Davenport and M. Strangwood, 2000, In: *The 2nd International Symposium on Friction Stir Welding*, Sweden.
- [242] J.O. Corral, E.A. Trillo and L.E. Murr, 2001, In: *The 27th MAES International Symposium and Career Fair*, Texas, pp. 9–19.
- [243] N. Padgett, C.S. Paglia and R.G. Buchheit, 2003, In: *The 132th TMS-ASM Meeting*, California, pp. 55–64.
- [244] R. Braun and L.L. Dobrzynska, 2002, "Friction Stir Welding of Al-Cu-Mg-Ag Alloys", *Materials Science Forum*, 396–402, pp. 1531–1536.
- [245] C.G. Rhodes, M.W. Mahoney, W.H. Bingel, R.A. Spurling and C.C. Bampton, 1997, "Effects of Friction Stir Welding on Microstructure of 7075 Aluminium", *Scripta Materillia*, 36 (1), pp. 69-75.
- [246] C.S. Paglia, L.M. Ungaro, B.C. Pitts, M.C. Carroll and R.G. Buchheit, 2003, In: *The 132th TMS-ASM Meeting*, California, pp. 65–75.
- [247] J.B. Lumsden, M.W Mahoney, G. Pollock, D. Waldron and A. Guinasso, 1999, In: *The 1st International Symposium on Friction Stir Welding*, California.
- [248] R. Braun, C. Dalle Donne and G. Staniek, 2000, "Laser Beam Welding and Friction Stir Welding of 6013-T6 Aluminium Alloy Sheet", *Materials and Corrosion*, 31, pp. 1017–1026.
- [249] C.S. Paglia and R.G. Buchheit, 2006, "Microstructure, Microchemistry and Environmental Cracking Susceptibility of Friction Stir Welded 2219-T87", *Materials Science and Engineering A*, 429 (1-2), pp. 107–114.

- [250] K.V. Jata and S.L. Semiatin, 2000, "Continuous Dynamic Recrystallization during Friction Stir Welding of High Strength Aluminium Alloys", *Scripta Materialia*, 43 (8), pp. 743-749.
- [251] K.V. Jata, K.K. Sankaran and J.J. Ruschau, 2000, "Friction-Stir Welding Effects on Microstructure and Fatigue of Aluminium Alloy 7050-T7451", *Metallurgical and Materials Transaction A*, 31 (9), pp. 2181-2192.
- [252] G.S. Frankel and Z. Xia, 1999, "Localized Corrosion and Stress Corrosion Cracking Resistance of Friction Stir Welded Aluminium Alloy 5454", *Corrosion*, 55 (2), pp.139-150.
- [253] P.S. Pao, S.J. Gill, C.R. Feng and K.K. Sankaran, 2001, In: *The TMS Annual Meeting*, Louisiana, USA.
- [254] M.W. Mahoney, C.G. Rhodes, J.G. Flintoff, R.A. Spurling and W.H. Bingel, 1998, "Properties of Friction-Stir-Welded 7075 T651 Aluminium", *Metallurgical and Materials Transaction A*, 29 (7), pp.1955-1964.
- [255] W. Hu and E.I. Meletis, 2000, "Corrosion and Environment-Assisted Cracking Behaviour of Friction Stir Welded Al 2195 and Al 2219 Alloys", *Materials Science Forum*, 331-337, pp. 1683-1688.
- [256] E.I. Meletis, 1984, "Fracture: Measurement of Localized Deformation by Novel Techniques, the Materials Society, Pennsylvania, USA.
- [257] C.S. Paglia, M.C. Carroll, B.C. Pitts, A.P. Reynolds and R.G. Buchheit, 2002, In: *The 8th International Conference on Aluminium Alloys ICAA 8*, Cambridge, UK, pp. 1677–1684.
- [258] N. Jayaraman, P. Preve'y and M. Mahoney, 2003, In: *The 132th TMS-ASM Meeting*, California.
- [259] A.J. Davenport, M. Jariyaboon, B.J. Conolly, C. Padovani and N. Tareelap, 2005, In: *Tri-service Corrosion Conference*, Florida.
- [260] Rockwell Scientific Co., 2004, *Final Report 2004–2004 Nr. A 580234*, Thousand Oaks California, p. 21.
- [261] D. Burford, C. Widener and B. Tweedy, 2006, In: *Air Framer 3*.
- [262] W.M. Thomas, I.M. Norris, D.G. Staines and E.R. Watts, 2005, In: *Friction Stir Welding-Process Developments and Variant Techniques*, the SME, Wisconsin, USA.
- [263] *Metals Handbook*, 2003, Vol. 4, "Heat Treating", ASM International.
- [264] R.W. Fonda and S.G. Lambrakos, 2002, In: *The 6th International Conference on Trends in Welding Research*, Georgia, pp. 241-246.

- [265] M. Zahedul, H. Khandkar, J.A. Khan and A.P. Reynolds, 2002, In: The 6th International Conference on Trends in Welding Research, Georgia, pp. 218-223.
- [266] S. Yazdanian, Z. W. Chen and G. Littlefair, 2012, "Effects of Friction Stir Lap Welding Parameters on Weld Features on Advancing Side and Fracture Strength of AA6060-T5 Welds", *Journal of Materials Science*, 47 (3), pp.1251-1261.
- [267] E. Cerri and P. Leo, 2011, "Mechanical Properties Evolution during Post-Welding-Heat Treatments of Double-Lap Friction Stir Welded Joints", *Materials and Design*, 32 (6), pp. 3465-3475.
- [268] M. K. Kulekci, I. Sevim, and U. Esme, 2012, "Fracture Toughness of Friction Stir-Welded Lap Joints of Aluminium Alloys", *Journal of Material Engineering and Performance*, 21 (7), pp. 1260-1265.
- [269] Y. Song, X. Yang, L. Cui, X. Hou, Zh. Shen and Y. Xu, 2014, "Defect Features and Mechanical Properties of Friction Stir Lap Welded Dissimilar AA2024-AA7075 Aluminium Alloy Sheets", *Materials and Design*, 55, pp. 9-18.
- [270] Ch.Y. Lee, W.B. Lee, J.W. Kim, D.H. Choi, Y.M. Yeon and S.B. Jung, 2008, "Lap Joint Properties of FSWed Dissimilar Formed 5052 Al And 6061 Al Alloys with Different Thickness", *Journal of Materials Science*, 43 (9), pp. 3296-3304.
- [271] V. Soundararajan, E. Yarrapareddy and R. Kovacevic, 2007, "Investigation of the Friction Stir Lap Welding of Aluminium Alloys AA 5182 and AA 6022", *Journal of Material Engineering and Performance*, 16 (4), pp. 477-484.
- [272] S. Babu, G.D. Janaki Ram, P.V. Venkitakrishnan, G. Madhusudhan Reddy and K. Prasad Rao, 2012, "Microstructure and Mechanical Properties of Friction Stir Lap Welded Aluminium Alloy AA2014", *Journal of Materials Science and Technology*, 28 (5), pp. 414-426.
- [273] H. Bisadi, M. Tour and A. Tavakoli, 2011, "The Influence of Process Parameters on Microstructure and Mechanical Properties of Friction Stir Welded Al 5083 alloy Lap joint", *American Journal of Materials Science* 1(2), pp. 93-97.
- [274] G. D'Urso and C. Giardini, 2010, "The Influence of Process Parameters and Tool Geometry on Mechanical Properties of Friction Stir Welded Aluminium Lap Joints", *International Journal of Materials Forming*, 3 (1), pp. 1011-1014.

- [275] J.W. Kwon, M.S. Kang, S.O. Yoon, Y.J. Kwon, S.T. Hong, D.I. Kim, K.H. Lee, J.D. Seo, J.S. Moon and K.S. Han, 2012, "Influence of Tool Plunge Depth and Welding Distance on Friction Stir Lap Welding of AA5454-O Aluminium Alloy Plates with Different Thicknesses", Transactions of Nonferrous Metals Society of China, 22, pp. s624-s628.
- [276] M. K. Kulekci, A. Şik and E. Kaluç, 2008, "Effects of Tool Rotation and Pin Diameter on Fatigue Properties of Friction Stir Welded Lap Joints International", Journal of Advanced Manufacture Technology, 36 (9-10), pp. 877-882.
- [277] D. Fersini and A. Pirondi, 2008, "Analysis and Modelling of Fatigue Failure of Friction Stir Welded Aluminium Alloy Single-Lap Joints", Engineering Fracture Mechanics, 75 (3-4), pp. 790-803.
- [278] M. Ericsson, L.Z. Jin and R. Sandstrom, 2007, "Fatigue Properties of Friction Stir Overlap Welds", International Journal of Fatigue, 29 (1), pp. 57-68.
- [279] X. Xu, X. Yang, G. Zhou and J. Tong, 2012, "Microstructures and Fatigue Properties of Friction Stir Lap Welds in Aluminium Alloy AA6061-T6", Materials and Design, 35, pp. 175-183.
- [280] M. Jariyaboon, A.J. Davenport, R. Ambat, B.J. Connolly, S.W. Williams and D.A. Price, 2007, "The Effect of Welding Parameters on The Corrosion Behaviour of Friction Stir Welded AA2024-T351", Corrosion Science, 49 (2), pp. 877-909.
- [281] K. Surekha, B.S. Murty and K. Prasad Rao, 2009, "Effect of Processing Parameters on the Corrosion Behaviour of Friction Stir Processed AA2219 Aluminium Alloy", Solid State Sciences, 11 (4), pp. 907-917.
- [282] K. Surekha, B.S. Murty and K. Prasad Rao, 2011, "Comparison of Corrosion Behaviour of Friction Stir Processed and Laser Melted AA 2219 Aluminium Alloy", Materials and Design, 32 (8-9), pp. 4502-4508.
- [283] M. K. Abbass, H. A. Ameen and Kh. S. Hassan, 2011, "Effect of Heat Treatment on Corrosion Resistance of Friction Stir Welded AA2024 Aluminium Alloy", American Journal of Scientific and Industrial Research, 2 (2), pp. 297-306.
- [284] F. Zucchi, G. Trabanelli and V. Grassi, 2001, "Pitting and Stress Corrosion Cracking Resistance of Friction Stir Welded AA5083", Materials and Corrosion, 52 (11), pp. 853-859.
- [285] S. Lim, S. Kim, Ch. G. Lee and S. Kim, 2005, "Stress Corrosion Cracking Behaviour of Friction-Stir-Welded Al 6061-T651", Metallurgical and Materials Transactions A, 36 (7), pp. 1977-1980.

- [286] J.B. Lumsden, M.W. Mahoney, C.G. Rhodes and G.A. Pollok, 2003, "Corrosion Behaviour of Friction-Stir-Welded AA7050-T7651", *Corrosion*, 59 (3), pp. 212-219.
- [287] D.A. Wadeson, X. Zhou, G.E. Thompson, P. Skeldon, L. Djapic Oosterkamp and G. Scamense, 2006, "Corrosion Behaviour of Friction Stir Welded AA7108 T79 Aluminium Alloy", *Corrosion Science*, 48 (4), pp. 887-897.
- [288] E. Bousquet, A. P. Quintin, M. Puiggali, O. Devos and M. Touzet, 2011, "Relationship between Microstructure, Microhardness and Corrosion Sensitivity of an AA2024-T3 Friction Stir Welded Joint", *Corrosion Science*, 53 (9), pp. 3026-3034.
- [289] Z. Nikseresht, F. Karimzadeh, M.A. Golozar and M. Heidarbeigy, 2010, "Effect of Heat Treatment on Microstructure and Corrosion Behaviour of Al6061 Alloy Weldment", *Materials and Design*, 31 (5), pp. 2643-2648.
- [290] V. Fahimpour, S.K. Sadrnezhaad and F. Karimzadeh, 2012, "Corrosion Behaviour of Aluminium 6061 Alloy Joined by Friction Stir Welding and Gas Tungsten Arc Welding Methods", *Materials and Design*, 39, pp. 329-333.
- [291] A. Squillace, A. De Fenzo, G. Giorleo and F. Bellucci, 2004, "A Comparison between FSW and TIG Welding Techniques: Modifications of Microstructure and Pitting Corrosion Resistance in AA2024-T3 Butt Joints", *Journal of Materials Processing Technology*, 152 (1), pp. 97-105.
- [292] S. Maggiolino and Ch. Schmid, 2008, "Corrosion Resistance in FSW and in MIG Welding Techniques of AA6XXX", *Journal of Materials Processing Technology*, 197 (1-3), pp. 237-240.
- [293] J. Kang, R. D. Fu, G.H. Luan, Ch. L. Dong and M. He, 2010, "In-Situ Investigation on the Pitting Corrosion Behaviour of Friction Stir Welded Joint of AA2024-T3 Aluminium Alloy", *Corrosion Science*, 52 (2), pp. 620-626.
- [294] W. Xu and J. Liu, 2009, "Microstructure and Pitting Corrosion of Friction Stir Welded Joints in 2219-O Aluminium Alloy Thick Plate", *Corrosion Science*, 51 (11), pp. 2743-2751.
- [295] W. Xu, J. Liu and H. Zhu, 2010, "Pitting Corrosion of Friction Stir Welded Aluminium Alloy Thick Plate in Alkaline Chloride Solution", *Electrochimica Acta*, 55, pp. 2918-2923.
- [296] R.W. Fonda, P.S. Paoa, H.N. Jonesa, C.R. Fenga, B.J. Connollyb and A.J. Davenport, 2009, "Microstructure, Mechanical Properties, and Corrosion of Friction Stir Welded Al 5456", *Materials Science and Engineering A*, 519 (1-2), pp. 1-8.

- [297] S. Rajakumar, C. Muralidharan and V. Balasubramanian, 2011, "Predicting Tensile Strength, Hardness and Corrosion Rate of Friction Stir Welded AA6061-T6 Aluminium Alloy Joints", *Materials and Design*, 32 (5), pp. 2878-2890.
- [298] P. Balasrinivasana, K.S. Arora, W. Dietzela, S. Pandeyb and M.K. Schaperc, 2010, "Characterization of Microstructure, Mechanical Properties and Corrosion Behaviour of an AA2219 Friction Stir Weldment", *Journal of Alloys and Compounds*, 492 (1-2), pp. 631-637.
- [299] P. Dong, D. Sun, B. Wang, Y. Zhang and H. Li, 2014, "Microstructure, Microhardness and Corrosion Susceptibility of Friction Stir Welded AlMgSiCu Alloy", *Materials and Design*, 54, pp. 760-765.
- [300] C.S. Paglia and R.G. Buchheit, 2008, "The Time-Temperature-Corrosion Susceptibility in AA7050-T7451 Friction Stir Weld", *Materials Science and Engineering A*, 492 (1-2), pp. 250-254.
- [301] C. S. Paglia, K. V. Jata and R. G. Buchheit, 2007, "The Influence of Artificial Aging on the Microstructure, Mechanical Properties, Corrosion, and Environmental Cracking Susceptibility of AA7075 Friction-Stir-Weld", *Materials and Corrosion*, 58 (10), pp. 737-750.
- [302] S. H. Park, J. Sh. Kim, M.S. Han and S.J. Kim, 2009, "Corrosion and Optimum Corrosion Protection Potential of Friction Stir Welded 5083-O Al Alloy for Leisure Ship", *Transactions of Nonferrous Metals Society of China*, 19 (4), pp. 898-903.
- [303] V. Proton, J. Alexis, E. Andrieu, J. Delfosse, M. Ch. Lafont and Ch. Blanc, 2013, "Characterization and Understanding of the Corrosion Behaviour of the Nugget in A2050 Aluminium Alloy Friction Stir Welding Joint", *Corrosion Science*, 73, pp. 130-142.
- [304] W.J. Liang, P.A. Rometsch, L.F. Cao, N. Birbilis, 2013, "General Aspects Related to the Corrosion of 6XXX Series Aluminium Alloys: Exploring the Influence of Mg/Si Ratio and Cu", *Corrosion Science*, 76, pp. 119-128.
- [305] American Welding Society, 2010, AWS D17.3/ D13.3M, "Specification for Friction Stir Welding of Aluminium Alloys for Aerospace Applications", American national standard.
- [306] S. W. Kallee, E. D. Nicholas and W. M. Thomas, 2001, "Industrialisation of Friction Stir Welding for Aerospace Structures", The 3th European Conference on Structures and Technologies - Challenges for Future Launchers, Strasbourg France.
- [307] R. S. Mishra and M. W. Mahoney, 2007, "Friction Stir Welding and Processing", ASM International, Metals Park, Ohio. DOI: 10.1361/fswp2007p001.

- [308] R. Rai, A. De, H. K. D. H. Bhadeshia and T. DebRoy, 2011, "Review: friction stir welding tools", *Science and Technology of Welding and Joining*, 16(4), pp. 325-342.
- [309] L. Liu, H. Nakayama, S.J. Fukumoto, A. Yamamoto, and H. Tsubakino, 2004, "Microscopic Observations of Friction Stir Welded 6061 Aluminium Alloy", *Materials Transactions*, 45 (2), pp. 288-291.
- [310] G. Liu, L.E. Murr, C.S. Niou, and J.C. McClure, 1997, "Microstructural Aspects of the Friction-Stir Welding of 6061-T6 Aluminium", *Scripta Materialia*, 37 (3), pp. 355-361.
- [311] A. Heidarzadeh, H. Khodaverdizadeh, A. Mahmoudi, and E. Nazari, 2012, "Tensile behavior of Friction Stir Welded AA 6061-T4 Aluminum Alloy Joints", *Materials and Design*, 37, pp. 166-173.
- [312] W. B. Lee, Y.M. Yeon and S.B. Jung, 2004, "Mechanical Properties Related to Microstructural Variation of 6061 Al Alloy Joints by Friction Stir Welding", *Materials Transactions*, 45(5), pp. 1700-1705.
- [313] P. J. Ramulu, R. G. Narayanan, S. V. Kailas and J. Reddy, 2012, "Internal Defect and Process Parameter Analysis during Friction Stir Welding of Al 6061 Sheets", *International Journal of Advanced Manufacturing Technology*, 65, pp. 1515-1528.
- [314] A.H. Feng, D.L. Chen, and Z.Y. Ma, 2010, "Microstructure and Low-Cycle Fatigue of a Friction-Stir-Welded 6061 Aluminum Alloy", *Metallurgical and Materials Transactions A*, 41, pp. 2626-2641.
- [315] K. Elangovan and V. Balasubramanian, 2008, "Influences of Tool Pin Profile and Tool Shoulder Diameter on the Formation of Friction Stir Processing Zone in AA6061 Aluminium Alloy", *Materials and Design*, 29, pp. 362-373.
- [316] D.M. Rodrigues, A. Loureiro, C. Leitao, R.M. Leal, B.M. Chaparro and P. Vilaça, 2009, "Influence of Friction Stir Welding Parameters on the Microstructural and Mechanical Properties of AA 6016-T4 Thin Welds", *Materials and Design*, 30, pp. 1913-1921.
- [317] L. Karthikeyan and V.S. Senthil Kumar, 2011, "Relationship between Process Parameters and Mechanical Properties of Friction Stir Processed AA6063-T6 Aluminum Alloy", *Materials and Design*, 32, pp. 3085-3091.
- [318] V. Balasubramanian, 2008, "Relationship between Base Metal Properties and Friction Stir Welding Process Parameters", *Materials Science and Engineering A*, 480, pp. 397-403.
- [319] P. Cavaliere, A. Squillace and F. Panella, 2008, "Effect of Welding Parameters on Mechanical and Microstructural Properties of AA6082 Joints Produced by Friction Stir Welding", *Journal of Materials Processing Technology*, 200, pp. 364-372.

- [320] S.R. Ren, Z.Y. Ma and L.Q. Chen, 2007, "Effect of Welding Parameters on Tensile Properties and Fracture behavior of Friction Stir Welded Al–Mg–Si Alloy", *Scripta Materialia*, 56, pp. 69-72.
- [321] G. M. Reddy, P. Mastanaiah, K. S. Prasad and T. Mohandas, 2009, "Microstructure and Mechanical Property Correlations in AA 6061 Aluminium Alloy Friction Stir Welds", *Transactions of the Indian Institute of Metals*, 62(1), pp. 49-58.
- [322] F.C. Liu and Z.Y. Ma, 2008, "Influence of Tool Dimension and Welding Parameters on Microstructure and Mechanical Properties of Friction-Stir-Welded 6061-T651 Aluminum Alloy", *Metallurgical and Materials Transactions A*, 39, pp. 2378-2388.
- [323] "Standard Test Method for Macro etching Metals and Alloys", 1999, ASTM Standard, E340.
- [324] "Standard Test Method for Micro etching Metals and Alloys", 2007, ASTM Standard, E407.
- [325] "Standard Test Method for Knoop and Vickers Hardness of Materials", 2011, ASTM Standard, E384.
- [326] "Standard Test Method for Strength Properties of Adhesively Bonded Plastic Lap Shear Sandwich Joints in Shear by Tension Loading", 2003, ASTM Standard, D3164.
- [327] "Qualification Standard for Welding and Brazing Procedures, Welders, Brazers and Welding and Brazing Operators", American Society of Mechanical Engineers (ASME) Section IX.
- [328] F. Fadaeifard, K. A. Matori, M. Toozandehjani, A. R. Daud, M. K. A. M. Ariffin, N. K. Othman, F. Gharavi, A. H. Ramzani and F. Ostovan, 2014, "Influence of Rotational Speed on Mechanical Properties of Friction Stir Lap Welded 6061-T6 Al Alloy", *Transactions of Nonferrous Metals Society of China*, 24, pp. 1004-1011.
- [329] F. Fadaeifard, F. Gharavi, K. A. Matori, A. R. Daud, M. K. A. M. Ariffin and M. Awang, 2014, "Investigation of Microstructure and Mechanical Properties of Friction Stir Lap Welded AA6061-T6 in Various Welding Speeds", *Journal of Applied Sciences*, 14(3), pp. 221-228.
- [330] V.L. Niranjani, K.C. Hari Kumar, and S.S. Subramanja, 2009, "Development of High Strength Al–Mg–Si AA6061 Alloy through Cold Rolling and Ageing", *Materials Science and Engineering A*, 515 (1-2), pp. 169-174.
- [331] Z.Y. Ma, 2008, "Friction Stir Processing Technology: A Review", *Metallurgical and Materials Transaction A*, 39 (3), pp. 642-658.

- [332] C. Sharma, D.K. Dwivedi, and P. Kumar, 2012, "Effect of Welding Parameters on Microstructure and Mechanical Properties of Friction Stir Welded Joints of AA7039 Aluminium Alloy", *Materials and Design*, 36, pp. 379-390.
- [333] S. Rajakumar, C. Muralidharan, and V. Balasubramaian, 2011, "Statistical Analysis to Predict Grain Size and Hardness of The Weld Nugget of Friction-Stir-Welded AA6061-T6 Aluminium Alloy Joints", *International Journal of Advanced Manufacture Technology*, 57 (1-4), pp. 151-165.
- [334] W. Xu, J. Liu, G. Luan, and C. Dong, 2009, "Temperature Evolution, Microstructure and Mechanical Properties of Friction Stir Welded Thick 2219-O Aluminium Alloy Joints", *Materials and Design*, 30 (6), pp. 1886-1893.
- [335] A.A. Zadpoor, J. Sinke, and R. Benedictus, 2009, "Fracture Mechanism of Aluminium Friction Stir Welded Blanks", *International Journal of Materials Forming*, 2, pp. 319-322.
- [336] T.D. Burleigh, E. Ludwiczack and R.A. Petri, 1995, "Intergranular Corrosion of an Aluminium-Magnesium-Silicon-Copper Alloy", *Corrosion*, 51 (1), pp. 50-55.
- [337] J.M. Sanchez-Amaya, L. Gonzalez-Rovira and F.J. Botana, 2012, "Experimental Correlation between Metallographic Evaluation and Electrochemical Noise in Intergranular Corrosion Tests of Aluminum Alloys", *surface and interface analyses*, 44, 1279-1286.
- [338] ASM Handbook, 1987, Vol. 13, "Corrosion", ASM International Committee.
- [339] C. Vargel, M. Jacques and M.P. Schmidt, 2004, "Corrosion of Aluminium", Elsevier, pp. 125.
- [340] G. Venkatasubramanian, A. Sheik Mideen and K. J.H.A. Abhay. 2012, "Corrosion Behavior of Aluminium Alloy AA2219-T87 Welded Plates in Sea Water", *Indian Journal of Science and Technology*, 5 (11), pp. 3578-3583.
- [341] R.C. Zeng, J. Chen, W. Dietzel, R. Settler, J.F. Dos Santos and M.L. Nascimento, 2009, "Corrosion of Friction Stir Welded Magnesium Alloy AM50", *Corrosion Science*, 51 (8), pp. 1738-1746.
- [342] M. Amini, F. Kazemzade and M.H. Moayed. 2009, "An Approach To Predict Galvanic Corrosion Using Identical Couple Electrodes; Investigation of Weld Zone and Parent Alloy in AA6XXX Welded Through FSW Technique", In *Proceedings of Iran International Aluminium Conference (IIAC2009)*, Tehran.

- [343] S.H. Kim, U. Erb and K.T. Aust, 2001, "Grain Boundary Character Distribution and Intergranular Corrosion Behavior in High Purity", *Aluminum Scripta Materialia*, 44 (5), pp. 835-839.
- [344] D. Song, A. Ma, J. Jiang, P. Lin, D. Yang and J. Fan, 2010, "Corrosion Behavior of Equal-Channel-Angular-Pressed Pure Magnesium in NaCl Aqueous Solution", *Corrosion Science*, 52 (2), pp. 481-490.
- [345] T.J. Summerson and D.O. Sprowls, 1986, "Corrosion Behavior of Aluminium Alloys", Edited by E.A. Stark, and T.H. Sanders, EMAS, Cradley Health,; pp. 1575.
- [346] L. Fratini and G. Buffa, 2005, "CDRX Modelling in Friction Stir Welding of Aluminium Alloys", *International Journal of Machine Tools and Manufacture*, 45 (10), pp. 1188-1194.
- [347] T. Hashimoto, S. Jyogan, K. Nakata, Y.G. Kim and M. Ushio, 1999, In *Proceeding of the 1th International Symposium on Friction Stir Welding*, Thousand Oaks, CA.
- [348] M.B. Hariri, S.G. Shiri, Y. Yaghoubinezhad and M.M. Rahvard, 2013, " The Optimum Combination of Tool Rotation Rate and Welding Speed for Obtaining the Preferable Corrosion Behaviour and Mechanical Properties of Friction Stir Welded AA5052 Aluminium Alloy", *Materials and Design*, 50, pp. 620-634.
- [349] V. Guillaumin, G. Mankowski, 2000, "Localized Corrosion of 6056 T6 Aluminium Alloy in Chloride Media", *Corrosion Science*, 42 (1), pp. 105-125.
- [350] N. Birbillis and R.G. Buchheit, 2008, "Investigation and Discussion of Characteristics for Intermetallic Phases Common to Aluminium Alloys as a Function of Solution pH", *Journal of the Electrochemistry Society*, 155 (3), pp. C117-C126.