

# **UNIVERSITI PUTRA MALAYSIA**

# PHOTOPYROELECTRIC TECHNIQUE IN THERMAL DIFFUSIVITY DETERMINATION AND SPECTROSCOPIC RESPONSE OF SOLID SAMPLES

# LIAW HOCK SANG

FSAS 2003 42

### PHOTOPYROELECTRIC TECHNIQUE IN THERMAL DIFFUSIVITY DETERMINATION AND SPECTROSCOPIC RESPONSE OF SOLID SAMPLES

By

LIAW HOCK SANG

Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia, in Fulfilment of the Requirements for the Degree of Master of Science

August 2003



# SPECIALLY DEDICATED TO MY BELOVED FAMILY MEMBERS AND LAU SIEH HIE

.



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirements for the degree of Master of Science.

### PHOTOPYROELECTRIC TECHNIQUE IN THERMAL DIFFUSIVITY DETERMINATION AND SPECTROSCOPIC RESPONSE OF SOLID SAMPLES

By

### LIAW HOCK SANG

### August 2003

Chairman : Azmi Zakaria, Ph.D.

Faculty : Science and Environmental Studies

Conventional photopyroelectric (PPE) measurement of thermal diffusivity of optically opaque sample was done in case of thermally thick sample, but it underwent a great attenuation of signal. In this study, the generalisation of Mandelis and Zver special cases of thermally thin-thick sample has been derived and was used to determine the thermal diffusivity. The method was experimentally tested for aluminium samples of different thickness and copper sample, and the values obtained were close to the literature values.

The Bennett and Patty theory in the generation of photoacoustic signal has been successfully adopted in the generation of PPE signal. An equation of complex PPE signal was derived. A normalisation procedure was used to eliminate a number of unknown parameters in PPE cell. The method was experimentally tested for aluminium, copper, and nickel samples, and the values obtained were close to the literature values.



Previous data acquisition program written in QBASIC has been modified to further increase the spectrometer reliability and performance. The method of getting both the optical and the thermal transmission spectra of solid samples has demonstrated by using an intact green leaf and by poly (methyl methacrylate) doped with methyl red polymer. These spectra showed a strong inversion between each other, and were obtainable on the exactly same sample and detector by simply varying the light chopping frequency.

The thermal transmission spectrum was used to determine the band-gap energy of the ZnO substituted with different CoO mol percentage. The powdered samples were prepared in a thickness that the spectrum is obtainable. Even though the prepared sample was deposited on a 50µm-thick stainless steel substrate, which was totally opaque, the unsaturated thermal transmission spectra have been obtained. This suggests that thin film deposited on opaque substrate can be studied with current PPE system. The band-gap energy of ZnO is 3.16eV and that of CoO-substituted ZnO decreases as the CoO mol% increases.

The monochromator was replaced by a motorised monochromator to further increase the performance of PPE spectrometer system. A PCI I/O card was used to add two more COM ports. Utility program, which was written in LabVIEW programming language served as data acquisition program for the new monochromator, has been successfully modified to integrate with lock-in amplifier. This system was applied to Neodymium oxide sample in UV-VIS regions. In this case, less sample preparation was required and the peaks at spectrum were in good agreement with literatures.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains.

### TEKNIK FOTOPIROELEKTRIK DALAM PENENTUAN KERESAPAN TERMA DAN RESPONS SPEKTROSKOPI BAGI SAMPEL-SAMPEL PEPEJAL

Oleh

### LIAW HOCK SANG

#### **Ogos 2003**

Pengerusi : Azmi Zakaria, Ph.D.

Fakulti : Sains dan Pengajian Alam Sekitar

Pengukuran fotopiroelektrik (PPE) lazim bagi keresapan terma bagi sampel legap telah dibuat dalam kes sampel yang tebal secara terma, tetapi ia mengalami pengecilan isyarat yang besar. Dalam kajian ini, kesimpulan umum kes-kes khas Mandelis dan Zver bagi sampel nipis-tebal secara terma telah diterbitkan dan telah digunakan untuk menentukan keresapan terma. Kaedah ini telah diuji secara experimen pada sampel aluminium yang berlainan ketebalan dan sampel tembaga. Nilai-nilai yang diperolehi adalah menghampiri nilai-nilai literatur.

Teori Bennett dan Patty dalam penjanaan isyarat fotoakustik telah berjaya dicerapkan dalam penjanaan isyarat PPE. Satu persamaan kompleks isyarat PPE telah diterbitkan. Prosedur normalisasi telah digunakan untuk menghapuskan sebilangan parameter yang tidak diketahui dalam sel PPE. Kaedah ini telah diuji secara eksperimen bagi sampel aluminium, tembaga, dan nikel. Nilai-nilai yang diperolehi adalah hampir dengan nilai-nilai literatur. Program pemerolehan data sebelumnya yang ditulis dalam QBASIC pada spektrometer PPE telah diubahsuai untuk meningkatkan kebolehpercayaan dan prestasinya. Kaedah untuk mendapatkan kedua-dua spektrum transmisi optik dan terma bagi sampel pepejal telah didemonstrasi dengan menggunakan daun hijau dan polimetilmetakrilat yang didopkan dengan metil merah. Spektrum-spektrum ini menunjukkan songsangan yang kuat di antara satu sama lain dan boleh diperolehi pada sampel dan pengesan yang sama dengan hanya mengubahkan frekuensi pencantas cahaya.

Spektrum-spektrum transmisi terma telah digunakan untuk menentukan tenaga jurang-jalur bagi ZnO yang digantikan dengan CoO yang berlainan peratus molnya. Sampel serbuk itu telah disediakan dengan ketebalan yang membolehkan spektrum itu diperolehi. Walaupun sampel itu didiposisi di atas substrak keluli tahan karat yang berketebalan 50µm dan betul-betul legap, spektrum transmisi terma tak-tepu telah diperolehi. Ini mencadangkan bahawa filem yang didiposisi di atas substrak legap boleh dikaji dengan sistem PPE ini. Tenaga jurang-jalur bagi ZnO ialah 3.16eV dan ZnO yang digantikan dengan CoO, tenaga ini menurun dengan peningkatan mol% CoO.

Monokromator telah digantikan dengan suatu monokromator yang bermotor untuk meningkatkan prestasi sistem spektrometer PPE. Satu kad PCI I/O telah digunakan untuk menambahkan dua lagi port COM. Progam utiliti yang ditulis dalam bahasa pengaturcaraan LabVIEW yang diguna sebagai program pemerolehan data bagi monokromator baru itu telah berjaya diubahsuaikan untuk berintegrasi dengan amplifier lock-in. Sistem ini telah diaplikasikan bagi sampel Neodimium oksida





dalam rantau UV-VIS. Dalam kes ini, penyediaan sampel hampir tidak diperlukan dan puncak-puncak spektrum yang terhasil adalah berpadanan dengan literatur.



### ACKNOWLEDGEMENTS

First of all, I am very grateful beyond words to Assoc. Prof. Dr. Azmi bin Zakaria for giving me an opportunity to study and conduct a research in this field. His most patience, understandings, encouragement, constant availability and constructive advice has all guided me not only to complete this study but also to be a better person. I would also like to thank my co-supervisors, Prof. Dr. W. Mahmood bin Mat Yunus and Prof. Dr. Mohd. Maarof H. A. Moksin for all their indispensable support and discussions. Not forgetting Assoc. Prof. Dr. Mansor bin Hashim and Assoc. Prof. Dr. Wan Mohd. Daud bin Wan Yusoff for advice and constructive comments, which keeps me in track and focus during this period of time.

Special word of appreciation to Prof. Dr. Abd. Halim Shaari, Prof. Dr. W. Mahmood bin Mat Yunus, Assoc. Prof. Dr. Mansor bin Hashim and Dr. Norhana Yahya for their kindness and friendliness to allow me to use the furnace, diode laser, planetary micromill, polarizer, chemicals, and the other supportive apparatus. I would also like to express my gratitude to all the staff in the Department for their assistance and cooperation throughout my study.

Last but not least, my sincere thanks to all my friends, seniors, lecturers and neighbours, especially Ling Yoke Ting, Josephine Liew, Sabrina Shapee, Lim Chee Seong, Lim Kean Pah, Chan Kok Sheng, Chia Pei Fung, and Lim Kien Hui, who have, directly or indirectly, contributed towards the success of this study. Thank you for making my study of master in UPM a memorable and enjoyable one.



# **TABLE OF CONTENTS**

xii

Page
ii
iii

DEDICATION	ii
ABSTRACT	iii
ABSTRAK	v
ACKNOWLEDGEMENTS	viii
APPROVAL	ix
DECLARATION	xi
LIST OF TABLES	xiv
LIST OF FIGURES	XV
LIST OF ABBREVIATIONS	XX
LIST OF SYMBOLS	xxi

# CHAPTER

1	INTR	ODUCTION	1,1
	1.1	Photothermal Spectroscopy	1.1
	1.2	Photopyroelectric Detection	1.3
	1.3	Thermal Diffusivity	1.5
	1.4	Objectives	1.6
2	LITE	RATURE REVIEW	2.1
	2.1	Photopyroelectric Detection Technique	2.1
		2.1.1 Contact PPE Configuration	2.1
		2.1.2 Non-Contact PPE Configuration	2.5
	2.2	Existing Theories of Photopyroelectric Spectroscopy	2.6
	2.3	Poly (methyl methacrylate) and Methyl Red	2.10
	2.4	Leaf	2.13
		2.4.1 Light Absorbing Pigments	2.14
		2.4.2 Light Reaction	2.17
	2.5	Zinc Oxide	2.19
	2.6	Neodymium Oxide	2.22
3	THE	ORY	3.1
	3.1	Photopyroelectric Effect	3.1
		3.1.1 One-Dimensional Model of PPE Theory	3.2
		3.1.2 Optically Opaque and Thermally Thick Pyroelectric 3.1.3 Fitting Equation for PPE Measurement of Thermal	3.4
		Diffusivity	35
	32	Thermal Wave Interferometry in Photoacoustic Effect	3.6
	5.2	3.2.1 One-Dimensional Model of Thermal Wave	5.0
		Interferometry	38
		3.2.2 Fitting Equation for PPE Measurement of Thermal	2.0
		Diffusivity	3.8
4	MET	HODOLOGY	4.1
	4.1	Thermal Diffusivity Measurement System	4.1
		4.1.1 Excitation Source	4.2



		4.1.2	Light Modulation Apparatus	4.3
		4.1.3	Detection Scheme	4.4
		4.1.4	Signal Processing and Data Acquisition System	4.5
	4.2	Spectr	ometer System	4.7
		4.2.1	Excitation Source	4.8
		4.2.2	Light Modulation Apparatus	4.10
		4.2.3	Detection Scheme	4.10
		4.2.4	Signal Processing and Data Acquisition System	4.10
	4.3	Setting	g Up Thermal Diffusivity Measurement System	4.10
	4.4	Setting	g Up Spectrometer System	4.11
		4.4.1	Data Acquisition Program in QBASIC	4.11
		4.4.2	Replacement of Monochromator	4.13
		4.4.3	PCI I/O Card	4.14
		4.4.4	Graphical Programming with LabVIEW	4.14
		4.4.5	Calibration of the PPE System	4.25
	4.5	Fitting	Procedure in Determining Thermal Diffusivity	4.29
		4.5.1	Equation Based on PPE Theory by Mandelis	4.29
		4.5.2	Equation Based on the Theory of Thermal Wave	
			Interferometry in Photoacoustic Effect	4 32
	46	Sampl	e Prenaration	4 33
	1.0	4 6 1	Poly (methyl methacrylate) Doned with Methyl Red	4.33
		462	Zinc Oxide Substituted with Cobalt Oxide	4 33
		4.0.2 163	Neodymium Ovide	4.55
		<b>-</b> .0.5		7.57
5	RESU	LTS A	ND DICUSSION	5.1
	5.1	Therm	al Diffusivity Measurements	5.1
		5.1.1	Fitting Equation Based on Mandelis and Zver PPE	
			Theory	5.1
		5.1.2	Fitting Equation Based on the Bennett and Patty	
			Theory of Thermal Wave Interferometry in	
			Photoacoustic Effect	5.5
	52	Spect	rosconic Study	59
	5.2	5 2 1	Spectroscopy of MR-Doped PMMA Using PVDF	5.7
		5.2.1	Conting $P \sim 1$	5 10
		577	Spectroscopy of MP Doped DMMA Using DVDE	5.10
		J.Z.Z	Casting D . 0	5 1 9
		5 7 7	Coaing, K ≈ 0	5.10
		5.2.5	Spectroscopy of Green Lear	5.21
		5.2.4	Band-gap Energy of Co-Substituted ZnO Ceramic	5.20
		5.2.5	Neodymium Oxide	5.55
6	CON	CLUSIC	N	6.1
	6.1	Concl	usions	61
	6.2	Sugge	stions for Future Work	64
	0.2			0.1
				р 1
KEFEKENUED K.I			K.I	
APP	ENDIC	ES		A.I
BIODATA OF THE AUTHOR B.I			R'I	



### LIST OF TABLES

Table		Page
2.1	Spectral characteristic of solid samples as predicted by two PPE theories, $\mu_s$ is thermal diffusion length, $l_\beta$ is optical absorption length, and R is reflectivity of pyroelectric coating.	2.7
2.2	Typical properties of PMMA.	2.11
2.3	Properties of photosynthesis pigment.	2.15
4.1	The functions of control buttons excluding Go Scan button on the front panel.	4.24
5.1	The comparison of present thermal diffusivity values to the literature values.	5.4
5.2	The obtained $\alpha$ values for materials used in the experiment.	5.8
5.3	The percentage difference between the calculated and the literature values.	5.8
5.4	The variation of the band-gap energy of CoO-substituted ZnO.	5.32
5.5	The identified transition associated with each peak in PPE spectrum of $Nd_2O_3$ .	5.35



## **LIST OF FIGURES**

Figure		Page
1.1	PT phenomena caused by illumination of a surface by modulated beam of light with corresponding detection technique in parenthesis (Almond and Patel, 1996).	1.3
2.1	Most commonly used photopyroelectric (PPE) configurations: (a) Standard (SPPE), (b) Inverse (IPPE), (c) Non-Contact-Back-(NC- BPPE) and (d) Non-Contact-Front- (NC-FPPE) configuration.	2.1
2.2	Reflectivity of metals (Al – aluminum, Au – gold, Fe – iron, and W – tungsten) with respect to wavelength (Almond and Patel, 1996).	2.9
2.3	Polymerisation of poly (methyl methacrylate) (PMMA).	2.10
2.4	Chemical structure of methyl red.	2.11
2.5	Intramolecular protonation equilibrium of methyl red.	2.12
2.6	Absorption spectra of various photosynthesis pigments.	2.16
2.7	Molecular formulas of chlorophyll a and b.	2.17
2.8	Principal absorption bands of chlorophyll.	2.18
2.9	Wurzite structure of ZnO.	2.20
2.10	Energy level diagram for Nd-doped solids.	2.24
3.1	One-dimensional geometry of a PPE cell: g, gas; s, sample; p, PE detector; and b, backing material.	3.1
3.2	Thermal wave in each regions of PA cell. The thermal waves initiated by light absorbed between $x$ and $x+dx$ within the sample.	3.6
3.3	Thermal wave in each regions of PPE cell. The thermal waves are partially reflected and transmitted upon striking the boundaries. g, s, c, p, and b stands for gas, sample, coating, PE detector, and backing, respectively.	3.9
3.4	Theoretical PPE phase signal frequency caused by the infinite terms of thermal wave in the left coating in contact with Ni sample. The solid line represents the best-fit line with slope m.	3.13
4.1	Schematic diagram of PPE system for thermal diffusivity measurement with He-Ne laser as the excitation source.	4.1
4.2	Schematic diagram of PPE system for thermal diffusivity	

xv

	measurement with diode laser as the excitation source.	4.2
4.3	The 30mW He-Ne laser head (Melles Griot, 05LHR991) and its power supply (Melles Griot, 05-LPL-915-065).	4.3
4.4	The optical chopper with 2 different types of chopper blades.	4.4
4.5	Schematic diagram of PPE cell.	4.4
4.6	The low-noise preamplifier (Standford Research System, SR560).	4.5
4.7	The lock-in amplifier (Standford Research System, SR530).	4.6
4.8	Schematic diagram of PPE system for spectroscopic study.	4.8
4.9	Schematic diagram of PPE system for spectroscopic study with the stepper motor and the driver board integrated in the monochromator.	4.8
4.10	Spectral irradiance of several types of arc lamps.	4.9
4.11	The 1000W arc lamp power supply (Oriel, 68920) and the 1000W Research arc lamp housing (Oreil, 66921).	4.9
4.12	Cornerstone <sup>™</sup> 260 1/4M motorised monochromator (Oriel, 74100).	4.13
4.13	The front panel of the data acquisition program.	4.17
4.14	The block diagram of the data acquisition program.	4.18
4.15	The first subVI that was executed on the block diagram of the data acquisition program.	4.19
4.16	The nodes that used to make the control buttons and busy indicator on the front panel into unpressed and invisible condition respectively.	4 19
4 17	The nodes that would be executed if the error status were true	4 19
4.18	Pop-up communication dialog box prompting user to input proper COM ports for laboratory instruments.	4.21
4.19	The nodes that used to read the Present Wavelength, Shutter's status, and current unit in use from the monochromator and update the corresponding indicators on the front panel.	4.21
4.20	Current parameters of monochromator were checked and updated on the front panel.	4.22
4.21	The nodes that check which button has been pressed on the front	



	panel.	4.23
4.22	The nodes that supply 3 important data for wavelength scanning.	4.24
4.23	Plot of He-Ne laser spectra at $10 - 100 \mu m$ output slit width.	4.25
4.24	Plot of He-Ne laser spectra at $200 - 2000\mu$ m output slit width.	4.25
4.25	A plot of spectrum's peak against the monochromator slit width.	4.27
4.26	A plot of spectrum's line width against the monochromator slit width.	4.27
4.27	Typical signal of photodiode positioned at the side of the monochromator.	4.28
4.28	Normalised power spectrum obtained with PVDF sensor alone.	4.28
4.29	Graphic user interface of Microcal Origin 6.0 software in defining the fitting equation and parameters with the experimental plot indicated in background.	4.31
4.30	Graphic user interface of Microcal Origin 6.0 software in fitting session with the experimental plot and simulated curve indicated in background.	4.31
4.31	Graphic user interface of Microcal Origin 6.0 software in fitting session with the experimental plot and selected data range indicated in background.	4.32
5.1	PPE signal amplitude versus modulation frequency for Al sample of thickness 863 micron.	5.2
5.2	PPE signal amplitude versus modulation frequency for Al sample of thickness 283 micron.	5.2
5.3	PPE signal amplitude versus modulation frequency for Cu sample of thickness 50 micron.	5.3
5.4	PPE phase signal of aluminium sample as a function of square root chopping frequency. The solid line represents the best-fit line with slope $m$ .	5.6
5.5	PPE phase signal of copper sample as a function of square root chopping frequency. The solid line represents the best-fit line with slope $m$ .	5.6
5.6	PPE phase signal of nickel sample as a function of square root chopping frequency. The solid line represents the best-fit line with slope $m$ .	5.7



5.7	Transmission spectrum of $27\mu$ m-thick MR-doped PMMA recorded by conventional optical spectrophotometer and corresponding calculated optical absorption length.	5.11
5.8	The optical absorption length with respect to wavelength, the thermal diffusion length at various chopping frequencies, and the physical thickness of $27\mu m$ for PMMA-MR sample.	5.12
5.9	PPE thermal transmission spectrum taken at various chopping frequencies.	5.13
5.10	PPE optical transmission spectrum taken at various chopping frequencies.	5.14
5.11	PPE spectrum taken at various chopping frequencies.	5.15
5.12	a) The thermal and b) the optical transmission spectrum of MR-doped PMMA.	5.16
5.13	The graph shows the decrease of nature logarithmic signal with increasing square root of chopping frequency at three different wavelength of MR-doped PMMA.	5.17
5.14	The spectra of MR-doped PMMA with thickness of $27\mu m$ using blacken PVDF transducer at two different chopping frequencies.	5.19
5.15	The spectra of MR-doped PMMA with thickness of $27\mu m$ using blacken PVDF transducer at three different chopping frequencies.	5.19
5.16	The graph shows the decrease of nature logarithmic signal with increasing square root of chopping frequency at three different wavelengths of MR-doped PMMA.	5.20
5.17	PPE thermal transmission spectrum of green leaf taken at various chopping frequencies.	5.22
5.18	PPE optical transmission spectrum of green leaf taken at various chopping frequencies.	5.22
5.19	PPE spectrum of green leaf taken at various chopping frequencies.	5.24
5.20	a) The thermal and b) the optical transmission spectrum of green leaf.	5.25
5.21	The graph shows the decrease of logarithmic signal with increasing square root of chopping frequency at three different wavelengths of green leaf.	5.26
5.22	XRD patterns for all samples sintered at 600°C.	5.27



5.23	PPE thermal transmission spectra for all samples normalised to unity at 370nm.	5.27
5.24	Plot of $(\rho hv)^2$ versus $hv$ for pure ZnO sample. Band-gap energy is determined to be 3.16eV.	5.30
5.25	Plot of $(\rho hv)^2$ versus $hv$ for 1mol% CoO-substituted ZnO sample. Band-gap energy is determined to be 3.15eV.	5.30
5.26	Plot of $(\rho hv)^2$ versus $hv$ for 5mol% CoO-substituted ZnO sample. Band-gap energy is determined to be 2.99eV.	5.31
5.27	Plot of $(\rho hv)^2$ versus $hv$ for 15mol% CoO-substituted ZnO sample. Band-gap energy is determined to be 2.91eV.	5.31
5.28	The variation of band-gap energy for ZnO substituted with different mol% CoO.	5.32
5.29	The Xenon lamp spectrum obtained at 8Hz of chopping frequency, detected with carbon soot deposited on Al foil.	5.33
5.30	Spectra of Neodymium oxide recorded at various chopping frequencies with the identified transition from ground state indicated.	5.34
5.31	The graph shows the decrease of logarithmic signal with increasing square root of chopping frequency at three different wavelengths of $Nd_2O_3$ .	5.36



# LIST OF ABBREVIATIONS

BPPE	Back-detection PPE
FPPE	Front-detection PPE
IPPE	Inverse PPE
LabVIEW	Laboratory Virtual Instrument Engineering
	Workbench
MOR	Modulated optical reflectance
MR	Methyl red
NC-BPPE	Non-Contact-Back PPE
NC-FPPE	Non-Contact-Front PPE
OBD	Optical beam deflection
PA	Photoacoustic
PAS	Photoacoustic spectroscopy
PDS	Photothermal deflection spectroscopy
PMMA	Poly (methyl methacrylate)
PE	Pyroelectric
PPE	Photopyroelectric
РТ	Photothermal
PTD	Photothermal displacement
PTR	Photothermal radiometry
PVDF	Polyvinylidene diflouride
PZ	Piezoelectric
RPPE	Reflective PPE
SPPE	Standard PPE
VIs	Virtual instruments

h.



## LIST OF SYMBOLS

- $\alpha$  Thermal diffusivity
- *b* Ratio of thermal effusivities
- $\beta$  Optical absorption coefficient
- c Specific heat
- e Thermal effusivity
- $E_g$  Energy gap
- $\varepsilon$  Dielectric constant
- $\varepsilon_o$  Vacuum permittivity
- f Modulation frequency
- hv Quantized photon energy
- *i* √-1
- *I*<sub>o</sub> Optical intensity
- k Thermal conductivity
- $I_{\beta}$  Optical absorption length
- *m* Slope or gradient
- L Thickness
- $\lambda$  Wavelength
- $\eta$  Light-to-heat conversion efficiency
- *p* Pyroelectric coefficient
- $\rho$  Density
- $Q_o$  Heat source intensity
- $R_n$  Thermal wave reflection coefficient
- $R(\lambda)$  Optical reflectivity at wavelength  $\lambda$
- $T_n$  Thermal wave transmission coefficient
- $\mu$ . Thermal diffusion length
- $\omega$  Angular modulation frequency.



### **CHAPTER 1**

### **INTRODUCTION**

### **1.1 Photothermal Spectroscopy**

Spectroscopy is concerned with the study of the interaction of light energy with matter covering many techniques and disciplines. Conventional optical spectroscopy is the earliest form of spectroscopy in studying the optical energy with respect to wavelength in the form of photons that are transmitted through, scattered or reflected from the material under investigation. The respective wavelength of the optical energy is ranging from less than 1Å in the X-ray region to 100µm in the far-infrared region. A plot of the data recorded by detecting these photons after their interaction with the material is called a spectrum (Rosencwaig, 1978; 1980).

In spites of its long history, optical spectroscopy is still the most used and active spectroscopic field, partly, because it forms a nondestructive investigation materials. However, the conventional transmission and reflection type of optical spectroscopy is not readily to work with materials in a wide variety of physical forms, especially those materials with (Rosencwaig, 1978; 1980; Miller, 1987):

- i. very low optical density,
- ii. very high optical density,
- iii. light scattering, and
- iv. specularly reflecting materials.



These materials include transparent gas mixtures containing small quantities of absorbing species or pollutant, window materials, powders, amorphous solids, intact biological samples, and thin films.

Over the years, several techniques have been developed to allow optical investigation of such materials. Diffuse reflectance, attenuated total reflection (or internal reflection spectroscopy), and Raman scattering were among the techniques invented. All these techniques have been found to be very useful for a small category of materials over a small range of wavelength.

Photopyroelectric (PPE) spectroscopy is one of the several photothermal (PT) spectroscopic techniques that is suitable to study those materials. In conventional techniques, the interaction of these photons with the material under study is investigated through subsequent detection and analysis of the photons. In PT techniques, even though the incident energy is in form of photons, the subsequent detection and analysis is a direct measure of the energy absorbed by the material due to its interaction with the photon beam. Energy absorbed is partly converted into heat as result of non-radiative de-excitation. Since the sample heating is a direct consequence of optical absorption, the PT signal is directly dependent on light absorption. Reflection and scattering loses do not produce PT signal and do not cause serious problems in photothermal spectroscopy (Bialkowski, 1996).

PT science covers a wide range of techniques and phenomena to study optical and thermal characteristic of a sample based upon a subsequence effect of the conversion of absorbed optical energy into heat. The basis of the PT process is a photo-induced change in their thermal state of the sample. The state of the sample can be in form of solid, liquid, or gas. In all PT systems, a modulated or pulsed excitation source is used to generate periodic or transient heating, respectively, in the sample. In a series of non-radiative de-excitation, the absorbed optical energy is converted into thermal energy. This thermal energy causes a number of physical changes in and around the sample. Figure 1.1 is a schematic illustration of the phenomena resulting from the exposure of a sample surface to periodically modulated light source. These effects form the basis of several detection schemes, which are divided into three detection groups: acoustic, optical and thermal detection.



Figure 1.1: PT phenomena caused by illumination of a surface by modulated beam of light with corresponding detection technique in parenthesis (Almond and Patel, 1996).

### **1.2 Photopyroelectric Detection**

Pyroelectricity is the property of certain material to produce a state of electrical polarization due to the change of temperature. This spontaneous or frozen



